

SPECIFICATION**PROCESS FOR REGENERATING SOLID CATALYST**5 Technical Field

 The present invention relates to a process for
regenerating a solid catalyst. More particularly, the present
invention relates to a process for very efficiently regenerating
a solid catalyst used for producing propylene oxide through
10 epoxidation of propylene with an organic peroxide in a reactor
in which the solid catalyst is packed.

Background Art

 It is publicly known to produce propylene oxide by
15 epoxidation of propylene with an organic peroxide in a reactor
in which the solid catalyst is packed. But, the activity of
the catalyst deteriorates with time used. The catalyst in which
the activity has deteriorated, require recovery of the activity
by changing to a new one or regenerating it.

20

Disclosure of the Invention

 Under such situations, the subject to be solved by the
present invention is to provide a process for regenerating a
solid catalyst, which permits the regeneration of the catalyst
25 with extremely high efficiency, without the needs for taking
the catalyst to be regenerated out of the reactor when the solid
catalyst used for producing propylene oxide by epoxidation of

propylene with an organic peroxide in the reactor in which the solid catalyst is packed.

Namely, the present invention relates to a process for regenerating a solid catalyst which has been used for producing propylene oxide through an epoxidation reaction of propylene with an organic peroxide in a reactor packed with the solid catalyst, which comprises allowing a liquid to flow through the catalyst packed in the reactor at a temperature not lower than the maximum reaction temperature of the epoxidation reaction.

Best Mode for Carrying out the Invention

In the present invention, the solid catalyst to be regenerated, is a solid catalyst which has been used for producing propylene oxide through epoxidation of propylene with an organic peroxide in a reactor packed with the solid catalyst.

As the solid catalyst, it is preferable to use a titanium-containing silicon oxide solid catalyst, and as these catalysts, so-called Ti-silica catalysts containing Ti chemically bonded to silicon oxide, are preferable.

For example, there are illustrated a product in which a Ti compound is supported on silica carrier, a product in which a Ti-compound is mixed with silicon oxide by a co-precipitation method or a sol-gel method, a zeolite compound containing Ti, and the like. As a shape of the solid catalyst, any shape such as powder, granule, particle, mass or the like can be adopted, but, it is preferable to use a catalyst having several hundreds

of micron meters to several tens of millimeters in size taking account of separability of a reaction liquid and a pressure loss of a reactor. Further, when a catalyst is primarily powder, it is preferable to use after making it large in size to some extent through molding.

As the organic peroxide to be reacted with propylene, cumene hydroperoxide, ethylbenzene hydroperoxide and t-butyl hydroperoxide can be exemplified.

As the reactor, a slurry-type reactor, a fixed bed reactor and the like can be used. In a case of a large scale operation, it is preferable to use a fixed bed reactor. Further, the reaction can be carried out by a batch process, semi-continuous process or continuous process. The epoxidation temperature is usually 0 to 200°C, and preferably 25 to 200°C. The pressure may be a pressure enough to keep a reaction mixture to a liquid state, and it is advantageously 100 to 10,000kPa in usual.

The regeneration process of the present invention is a regeneration process of a solid catalyst, which comprises allowing to flow a liquid through a catalyst packed in a reactor used for an epoxidation reaction at a temperature of not lower than the maximum reaction temperature in the epoxidation reaction. Namely, the regeneration is carried out without taking the catalyst out of the reactor used for the epoxidation reaction, therefore it is extremely high efficient. The temperature during the regeneration is a temperature not lower than the maximum reaction temperature in the epoxidation reaction, preferably a temperature higher by 5°C or more than

the maximum reaction temperature, further preferably a temperature higher by 10°C or more than the maximum reaction temperature.

When the temperature during regeneration is lower than the maximum reaction temperature of epoxidation, an effect of regeneration becomes insufficient. Herein, there is a case of elevating gradually the epoxidation temperature for compensating a deterioration of the activity with time during the reaction, and the maximum reaction temperature means that in that case.

Further, the temperature at regeneration is preferably 300°C or less from the viewpoint of durability of the catalyst. In addition, herein, the reaction temperature is a temperature of a catalyst layer, and when there is temperature distribution in the catalyst layer, it is a temperature at the lowest part in temperature.

As the liquid to be flown at regeneration, a liquid used in the reaction system is preferable from the viewpoint of prevention of contamination of a product and the system, and the epoxidation reaction liquid, cumene, liquid propylene and the like can be illustrated, and liquid propylene is the most preferred. Herein, the liquid propylene also includes a super critical fluid of propylene. As the regeneration process, a liquid may be passed through the catalyst, and as preferable conditions, a LHSV of 0.5 h^{-1} or more and a flow time of 1 hour or more are mentioned.

Example

Example 1

5 cc of a silicon oxide catalyst containing 1.3 % by weight of Ti (average particle diameter 0.9 mm, molded article) was packed in a reactor, and a cumene solution having a cumene hydroperoxide concentration of 25 to 35 % by weight and propylene were allowed to flow to conduct an epoxidation reaction. The reaction was initiated at a LHSV of 18 h^{-1} , reaction pressure of 5.5 MPaG and reaction temperature of 80°C , and the temperature was gradually raised with deterioration of the activity. The reaction temperature became 110°C after 1800 hours. Next, for regeneration operation, the feed of the cumene solution was stopped, then the temperature of the catalyst layer was elevated to 120°C and only liquid propylene was allowed to flow through the catalyst layer at a rate of 0.3 g/minute for 18 hours. After liquid propylene was flown, the epoxidation reaction was carried out by allowing to flow a 25 weight% cumene hydroperoxide solution and propylene at 110°C , again. The result is shown in Table 1.

20

Comparative Example 1

An epoxidation reaction was carried out in the same manner as in Example 1 except that, as regeneration operation, the temperature at which only liquid propylene was flown, was 105°C . The result is shown in Table 1.

25

Example 2

5 cc of a silicon oxide catalyst containing 1.3 % by weight of Ti (average particle diameter 0.9 mm, molded article) was packed in a reactor, and a cumene solution having a cumene hydroperoxide concentration of 25 to 35 % by weight and propylene were allowed to flow to conduct an epoxidation reaction. A LHSV of 18 h^{-1} and reaction pressure of 5.5 MPaG were adopted, and after the reaction of 1500 hours, the reaction temperature was 110°C . Next, for regeneration operation, the feed of the cumene solution was stopped, then the temperature of the catalyst layer was elevated to 130°C and only liquid propylene was allowed to flow through the catalyst layer at a rate of 0.7 g/minute for 20 hours. After liquid propylene was flown, the epoxidation reaction was carried out by allowing to flow a 25 weight% cumene hydroperoxide solution and propylene at 110°C , again. The result is shown in Table 1.

Table 1

	Example 1	Comparative Example 1	Example 2
Maximum temperature in epoxidation $^\circ\text{C}$	110	110	110
Regeneration temperature $^\circ\text{C}$	120	105	130
CMHP conversion *1 %			
Before regeneration	54.8	54.8	42.4
After regeneration	60.8	54.8	73.9

*1: CMHP; Cumene hydroperoxide

: CMHP conversion = converted CMHP(mol)/feed CMHP (mol)

X 100

Industrial Applicability

As described above, according to the present invention,
5 there can be provided a process for regenerating a solid catalyst,
which permits the regeneration of the catalyst with extremely
high efficiency, without the needs for taking the catalyst to
be regenerated out of the reactor when the solid catalyst used
for producing propylene oxide by epoxidation of propylene with
10 an organic peroxide in the reactor in which the solid catalyst
is packed, is regenerated.

CLAIMS

1. A process for regenerating a solid catalyst which has been used for producing propylene oxide through an epoxidation reaction of propylene with an organic peroxide in a reactor packed with the solid catalyst, which comprises allowing a liquid propylene to flow through the catalyst packed in the reactor at a temperature higher by 5 °C or more than the maximum reaction temperature of the epoxidation reaction.

2. The process according to claim 1, wherein the temperature at which the liquid is flown, is higher by 10 °C or more than the maximum temperature in the epoxidation reaction.

3. The process according to claim 1, wherein the catalyst is a titanium-containing silicon oxide solid catalyst.

4. The process according to claim 1, wherein the organic peroxide is cumene hydroperoxide.