

DESCRIPTION

[Title of Invention]

SURFACE-TREATMENT AGENT, METHOD FOR PRODUCING COATED STEEL
5 SHEET USING THE SURFACE-TREATMENT AGENT, AND COATED STEEL
SHEET

[Technical Field]

[0001]

The present invention relates to a surface-treatment
10 agent for coated steel sheets that is optimally used for
applications of automobiles, household electrical appliances,
and building materials, in particular, an environmentally
friendly surface-treatment agent that is completely free
from chromium and the like at the time of production and
15 during production; a method for producing a coated steel
sheet using the treatment agent; and a surface-treated
coated steel sheet.

[Background Art]

[0002]

20 Steel sheets obtained by subjecting surfaces of
galvanized steel sheets to a chromate treatment with a
treatment solution mainly containing chromic acid, dichromic
acid, or a salt of the foregoing for the purpose of
enhancing corrosion resistance (white-rust resistance and
25 red-rust resistance) are widely used as steel sheets for

household electrical appliances, steel sheets for building materials, and steel sheets for automobiles. The chromate treatment provides excellent corrosion resistance and is an economical treatment that can be relatively easily performed.

5 [0003]

The chromate treatment employs hexavalent chromium, which is a regulated substance causing pollution. However, the chromate treatment employs hexavalent chromium within a closed system and completely reduces and collects hexavalent chromium without releasing it into the nature. In addition, organic films can provide a sealing function of substantially preventing release of chromium from chromate films. Accordingly, the chromate treatment does not substantially cause contamination of the environment or human bodies with hexavalent chromium. However, due to recent global environmental issues, there has been a strong trend toward voluntary reduction in use of hexavalent chromium. In addition, to prevent environmental contamination caused by dumping of shredded dust of discarded products, there has already been a trend toward, in products, minimization of the amount of hexavalent chromium or reduction in the amount of hexavalent chromium.

20 [0004]

Accordingly, a large number of treatment techniques for suppressing the generation of white rust on galvanized steel

5 sheets without employing the chromate treatment, that is, chromium-free techniques, have been developed. For example, there is a technique of forming surface-treatment films on galvanized steel sheets by using an inorganic compound, an organic compound, an organic polymer material, or a composition containing the foregoing in combination. Although various advantageous techniques have been developed, with commercial use of these chromium-free techniques, objects that were not recognized and need to be achieved have been newly found.

[0005]

The first object is to enhance corrosion resistance in processed portions of surface-treated galvanized steel sheets. Surface-treated galvanized steel sheets are subjected to processing (cutting, bending, welding of parts, and painting) to be turned into products. When a surface-treated galvanized steel sheet is bent, a coated layer in the front surface of the bent portion is extended. In this case, a surface-treatment film is also extended by the bending and the surface-treatment film is damaged and the galvanized surface is exposed. Degradation of corrosion resistance in such exposed portions is problematic. In particular, unlike cupping causing local damage, bending causes continuous damage in the film and the coated layer. Accordingly, it is very difficult to provide processed

portions having sufficient corrosion resistance.

[0006]

The second object is to ensure solvent resistance of a surface-treatment film. In the above-described processing, oil stains on the surface of the film or symbols written with a magic marker are sometimes wiped off with a solvent. In these cases, use of the solvent often causes a phenomenon where the surface-treatment film becomes separated and discolored so as to have a pale color (whitening). When a surface-treatment film is separated from a (surface-treated) galvanized steel sheet, the steel sheet does not have corrosion resistance. When a surface-treatment film turns white, the appearance quality is degraded.

[0007]

The third object is to ensure paintability of a surface-treatment film. There are cases where the surfaces of a surface-treated galvanized steel sheet that is processed as described above are cleaned with an alkaline cleaning agent or the like (alkaline degreasing) and the cleaned surfaces are painted. Accordingly, overpaintability of surfaces having been subjected to alkaline degreasing is sometimes required. However, there are no publicly known references regarding studies on such a characteristic.

[0008]

The fourth object is to achieve sufficient corrosion

resistance of a surface-treatment film and sufficient storage stability of a surface-treatment agent. Recent chromium-free techniques most commonly employ formation of a surface-treatment film on a galvanized steel sheet by application and drying, that is, application formation. To impart a barrier effect to a surface-treatment film formed in such a manner, the surface-treatment film needs to have predetermined water resistance. This is because it is difficult for a surface-treatment film that readily dissolves back into water to have corrosion resistance (barrier effect). In addition, in industry, it is important that a surface-treatment agent prepared as a one-component agent by mixing raw materials with predetermined proportions can be stored with stability. Considering summer, it is desirable that a surface-treatment agent can be stored with stability without alteration for a long period of time at 35°C to 40°C. To achieve such storage stability, it is necessary that an increase in viscosity, gelation, precipitation, and the like do not occur in a surface-treatment agent, that is, the surface-treatment agent has predetermined water solubility; and the surface-treatment agent can maintain the quality at the time of the preparation thereof even after storage over a long period of time.

As described above, surface-treated galvanized steel sheets having more excellent characteristics are demanded. Hereafter, specific examples of existing chromium-free techniques will be described. Patent Literature 1 discloses a method in which an aqueous solution containing a water-dispersible silica, an alkyd resin, and a trialkoxysilane compound is applied to a metal surface and dried to thereby form a coating film. Patent Literatures 2 and 3 disclose a surface-treatment method employing a water-soluble resin composed of a hydroxypyrrone compound derivative to impart corrosion resistance to metal materials; and a method employing an aqueous solution of a hydroxystyrene compound or a water-dispersible polymer to impart corrosion resistance to metal materials. Patent Literature 4 discloses a technique employing a surface-treatment agent obtained by mixing an aqueous resin, colloidal silica, and ammonium vanadate with specific proportions. However, any of these techniques cannot achieve a film that provides corrosion resistance that is sufficient to replace chromate films.

[0010]

Patent Literature 5 discloses a technique of a surface-treatment film containing an organic resin and a thiocarbonyl-group-containing compound; however, the surface-treatment film does not provide sufficient corrosion

resistance after being subjected to alkaline degreasing.

Patent Literature 6 discloses a technique in which a surface of a metal plate is treated with a treatment solution that is an aqueous solution of lithium silicate containing an

5 organic resin, a silane coupling agent, and a solid lubricant; however, the inorganic components tend to form a rigid polymer and hence corrosion resistance in portions processed by bending or the like is insufficient. In

addition, due to the presence of the alkali metal, secondary
10 adhesion of painting is poor. Patent Literature 7 discloses a technique of forming a resin film with a resin aqueous solution containing a carboxyl-group-containing polyurethane resin, an aqueous dispersion of an ethylene-unsaturated

carboxylic acid copolymer, silica particles, and a silane
15 coupling agent with specific proportions; however, solvent resistance and corrosion resistance in processed portions are not sufficiently achieved. Patent Literature 8

discloses a steel sheet having a film containing a urethane resin, a lubricant, an inorganic colloid compound, and a
20 silane coupling agent with specific proportions. This film is designed for electrodeposition and excellent in terms of electrodeposition properties, but does not provide sufficient corrosion resistance in processed portions.

[0011]

25 Patent Literature 9 discloses a surface-treatment

solution containing a silane coupling agent and a urethane resin and adjusted so as to have a pH of 2.5 to 4.5; however, the solution does not provide sufficient corrosion resistance after alkaline degreasing and does not provide sufficient solvent resistance. Patent Literature 10 discloses a technique of forming a film with a treatment solution containing a water-dispersible resin, silica particles, and organic titanate with specific proportions; however the technique does not provide sufficient corrosion resistance in processed portions. Patent Literatures 11 and 12 disclose a technique of forming a film with a treatment solution containing an aqueous dispersion of a specific epoxy resin, a dispersion of a urethane resin, a silane coupling agent, phosphoric acid and/or a phosphate compound, and a compound having 1 to 5 fluorine atoms in a molecule; however, the film has insufficient alkali resistance and it is difficult for the film to have sufficient corrosion resistance and paintability after alkaline degreasing; and the film does not provide sufficient corrosion resistance in processed portions or sufficient solvent resistance.

[0012]

Patent Literature 13 discloses a technique of forming a film with a treatment solution containing a specific resin compound, a vanadium compound, and a metal compound containing a specific metal; however, the film has

insufficient alkali resistance and does not provide sufficient corrosion resistance after alkaline degreasing; and the film has unresolved problems that, for example, the film tends to turn yellow under heating. Patent Literature

5 14 discloses a technique of forming a film with a treatment agent containing a specific resin compound, a cationic urethane resin having a cationic functional group, a silane coupling agent having a reactive functional group, a Ti compound, and an acid compound with specific proportions.

10 This technique provides a film excellent in terms of corrosion resistance and fingerprint resistance. However, corrosion resistance after alkaline degreasing, corrosion resistance in processed portions, and solvent resistance are not studied and these characteristics are not sufficiently

15 achieved. Patent Literature 15 discloses a technique relating to a surface-treatment agent containing at least one aqueous resin selected from a cationic resin and a nonionic resin, a metal compound containing a specific metal, and water. Similarly, alkali resistance, corrosion

20 resistance in processed portions, and solvent resistance are not studied and these characteristics are not sufficiently achieved. Patent Literature 16 discloses a technique employing a surface-treatment agent containing a cationic urethane, a cationic phenol polycondensate, and a compound

25 containing titanium and a specific metal with specific

proportions; however, solvent resistance and paintability are not studied and these characteristics are not sufficiently achieved.

[0013]

5 In addition, all the existing surface-treatment agents containing silane coupling agents tend to have poor storage stability. Accordingly, even when surface-treatment agents after storage have normal appearance, the surface-treatment agents do not often provide desired characteristics.

10 Existing techniques do not study such a problem at all.

[Citation List]

[Patent Literature]

[0014]

PTL 1: Japanese Unexamined Patent Application

15 Publication No. 53-121034

PTL 2: Japanese Examined Patent Application Publication
No. 57-44751

PTL 3: Japanese Unexamined Patent Application
Publication No. 1-177380

20 PTL 4: Japanese Unexamined Patent Application
Publication No. 11-310757

PTL 5: Japanese Unexamined Patent Application
Publication No. 2000-248369

PTL 6: Japanese Unexamined Patent Application
25 Publication No. 11-58599

PTL 7: Japanese Unexamined Patent Application
Publication No. 2006-43913

PTL 8: Japanese Patent No. 3573307

PTL 9: Japanese Unexamined Patent Application
5 Publication No. 2001-59184

PTL 10: Japanese Unexamined Patent Application
Publication No. 2003-155451

PTL 11: Japanese Unexamined Patent Application
Publication No. 2006-82365

10 PTL 12: Japanese Unexamined Patent Application
Publication No. 2004-238716

PTL 13: Japanese Unexamined Patent Application
Publication No. 2001-181860

PTL 14: Japanese Patent No. 3883831

15 PTL 15: Japanese Patent No. 4078044

PTL 16: Japanese Unexamined Patent Application
Publication No. 2006-152436

[Summary of Invention]

[Technical Problem]

20 [0015]

An object of the present invention is to provide a
chromium-free surface-treatment agent that is used for
coated steel sheets, overcomes the above-described problems
of existing techniques, allows for formation of films having
25 excellent corrosion resistance on surfaces of metal

materials, provides excellent corrosion resistance in bent portions, solvent resistance, and paintability after alkaline degreasing, and has excellent storage stability in the state of a one-component agent; a method for producing a coated steel sheet with the treatment agent; and a surface-treated coated steel sheet.

[Solution to Problem]

[0016]

The inventors of the present invention have thoroughly studied how to achieve the object and have newly found the following findings. By treating a surface of a galvanized steel sheet with a surface-treatment agent containing a specific resin compound, a specific cationic urethane resin, a silane coupling agent having a specific functional group, a specific organic Ti chelate compound, a tetravalent vanadyl compound, with specific proportions, a film having excellent corrosion resistance can be formed and a film that is excellent in terms of solvent resistance and paintability can be formed. In addition, similar films can be formed with the surface-treatment agent even after storage. Thus, the present invention has been accomplished. The present invention is based on the findings and features thereof will be described below.

[0017]

(1) A surface-treatment agent includes

(A) a resin compound (hereafter, referred to as "resin compound (A)") having a bisphenol skeleton represented by a general formula (I) below;

(B) a cationic urethane resin emulsion (hereafter, referred to as "cationic urethane (B)") having at least one cationic functional group selected from primary to tertiary amino groups and a quaternary ammonium salt group;

(C) at least one silane coupling agent having at least one reactive functional group selected from an active-hydrogen-containing amino group, an epoxy group, a mercapto group, and a methacryloxy group;

(D) an organic titanium chelate compound;

(E) a tetravalent vanadyl compound; and

(F) water,

15 wherein, a mass ratio $[(b)/\{(a) + (b) + (c)\}]$ of a solid content of the cationic urethane (B) to a total of solid contents of the resin compound (A), the cationic urethane (B), and the silane coupling agent (C) is 0.1 to 0.3, a mass ratio $[(c)/\{(a) + (b) + (c)\}]$ of the solid content of the silane coupling agent (C) to the total of the solid contents of the resin compound (A), the cationic urethane (B), and the silane coupling agent (C) is 0.6 to 0.85,

25 a mass ratio $\{(c)/Ti\}$ of the solid content of the silane coupling agent (C) to a content of the organic


titanium chelate compound (D) in terms of titanium is 50 to 70,

a mass ratio (V/Ti) of a content of the tetravalent vanadyl compound (E) in terms of vanadium to the content of the organic titanium chelate compound (D) in terms of titanium is 0.3 to 0.5,

the surface-treatment agent has a pH of 4 to 5,


in the formulae, (a) represents the solid content of the resin compound (A), (b) represents the solid content of the cationic urethane (B), (c) represents the solid content of the silane coupling agent (C), Ti represents the content of the organic titanium chelate compound (D) in terms of titanium, and V represents the content of the tetravalent vanadyl compound (E) in terms of vanadium,

[Chemical formula 1]




where Y_1 and Y_2 bonded to benzene rings each independently represent hydrogen or a Z group represented by a general formula (II) or (III) below; an average substitution number of the Z group per benzene ring is 0.2 to 1.0; n represents an integer of 2 to 50, and

[Chemical formula 2]



[Chemical formula 3]



in the formulae (II) and (III), R_1 , R_2 , R_3 , R_4 , and R_5 each independently represent

a hydrogen atom, an alkyl group having 1 to 10 carbon atoms, or a hydroxyalkyl group having 1 to 10 carbon atoms; and A^- represents a hydroxide ion or an acid ion.

[0018]

(2) The surface-treatment agent according to (1) above

10 further includes (W) a wax,

wherein a mass ratio $[(w)/\{(a) + (b)\}]$ of a solid content of the wax (W) to a total of the solid contents of the resin compound (A) and the cationic urethane (B) is 0.2 to 0.4, and

15 in the formula, (w) represents the solid content of the wax (W), (a) represents the solid content of the resin compound (A), and (b) represents the solid content of the cationic urethane (B).

[0019]

20 (3) A method for producing a coated steel sheet includes applying the surface-treatment agent according to (1) or (2) above to a coated steel sheet, and drying the surface-

treatment agent at a sheet temperature of 50°C to 180°C to form a surface-treatment film having a coating weight of 0.2 to 1.8 g/m² on a surface of the steel sheet.

[0020]

- 5 (4) A coated steel sheet produced by the method for producing a coated steel sheet according to (3) above.

[Advantageous Effects of Invention]

[0021]

According to the present invention, a film can be
10 formed that has corrosion resistance equivalent to that of chromate films and is excellent in terms of corrosion resistance in processed portions formed during production process, solvent resistance, and paintability after alkaline degreasing. Thus, chromium-free coated steel sheets that
15 are more useful than existing products can be provided. In addition, a chromium-free surface-treatment agent for coated steel sheets according to the present invention is also excellent in terms of storage stability and hence is very advantageous in industrial usage.

20 [Description of Embodiments]

[0022]

Hereinafter, details of the present invention and reasons for the limitations in the present invention will be described. Steel sheets serving as bases of surface-treated
25 steel sheets according to the present invention are coated

steel sheets that are produced from cold-rolled sheet steels and used for household electrical appliances, building materials, and automobile parts. To provide advantages of a surface-treatment agent according to the present invention

5 markedly, galvanized steel sheets are preferably used.

Examples of galvanized steel sheets include

electrogalvanized steel sheets, hot dip galvanized steel sheets, zinc-aluminum alloy-coated steel sheets, zinc-iron alloy-coated steel sheets, zinc-magnesium coated steel

10 sheets, and zinc-aluminum-magnesium alloy-coated steel

sheets. The present invention is also applicable to

aluminum materials such as aluminum-coated steel sheets, aluminum-Si alloy-coated steel sheets, and aluminum sheets;

however, most preferably, the present invention is applied

15 to galvanized steel sheets.

[0023]

Such galvanized steel sheets may be provided, for the purpose of enhancing blackening resistance of galvanized steel sheets, by adding a small amount of Ni or Co to

20 coating or by precipitating Ni, Co, and Fe on surfaces of the galvanized steel sheets using an acid or alkali aqueous solution containing these metals.

[0024]

Hereinafter, a surface-treatment agent according to the
25 present invention will be described.

[0025]

A surface-treatment agent according to the present invention includes (A) a resin compound represented by a general formula (I) below; (B) a cationic urethane; (C) at least one silane coupling agent having at least one reactive functional group selected from an active-hydrogen-containing amino group, an epoxy group, a mercapto group, and a methacryloxy group; (D) an organic titanium chelate compound; (E) a tetravalent vanadyl compound; and (F) water, wherein, a mass ratio $[(b)/\{(a) + (b) + (c)\}]$ of the solid content of the cationic urethane (B) to the total of the solid contents of the resin compound (A), the cationic urethane (B), and the silane coupling agent (C) is 0.1 to 0.3; a mass ratio $[(c)/\{(a) + (b) + (c)\}]$ of the solid content of the silane coupling agent (C) to the total of the solid contents of the resin compound (A), the cationic urethane (B), and the silane coupling agent (C) is 0.6 to 0.85; a mass ratio $\{(c)/Ti\}$ of the solid content of the silane coupling agent (C) to the content of the organic titanium chelate compound (D) in terms of titanium is 50 to 70; a mass ratio (V/Ti) of the content of the tetravalent vanadyl compound (E) in terms of vanadium to the content of the organic titanium chelate compound (D) in terms of titanium is 0.3 to 0.5; and the surface-treatment agent has a pH of 4 to 5.


In the formulae, (a) represents the solid content of the resin compound (A), (b) represents the solid content of the cationic urethane (B), (c) represents the solid content of the silane coupling agent (C), Ti represents the content of the organic titanium chelate compound (D) in terms of titanium, and V represents the content of the tetravalent vanadyl compound (E) in terms of vanadium. Hereafter, the same definitions are used.

[0026]

10 In a surface-treatment agent according to the present invention, the resin compound (A) is represented by the following general formula (I).

[0027]

[Chemical formula 4]



In the formula, Y_1 and Y_2 bonded to benzene rings each independently represent hydrogen or a Z group represented by the general formula (II) or (III) below; an average
 5 substitution number of the Z group per benzene ring is 0.2 to 1.0; and n represents an integer of 2 to 50.

[0028]

Herein, the average substitution number of the Z group is a value obtained by dividing the total number of the Z groups introduced by the total number of the benzene rings (that is, $2n$). In the present invention, when the Z groups
 10 are selected for Y_1 and Y_2 , the resin compound (A) has cationic functional groups of a secondary amino group, a tertiary amino group and a quaternary ammonium salt group.


Accordingly, the resin compound (A) can dissolve with more stability in a surface-treatment agent that is acidic (pH 4 to 5) according to the present invention. In the present invention, average degree of polymerization n is defined as

5 2 to 50. When n is less than 2, the effect of imparting corrosion resistance is insufficient. When n is more than 50, degradation of water solubility, an increase in viscosity, or the like occurs and stability in the treatment agent is degraded, which results in insufficient storage

10 stability.


[0029]

[Chemical formula 5]



[0030]

15 [Chemical formula 6]



In the formulae (II) and (III), R_1 , R_2 , R_3 , R_4 , and R_5 each

independently represent

a hydrogen atom, an alkyl group having 1 to 10 carbon atoms,
or a hydroxyalkyl group having 1 to 10 carbon atoms. When
the number of the carbon atoms of the alkyl group or the
5 hydroxyalkyl group is more than 10, the resin compound (A)
cannot be sufficiently dissolved in water, becomes unstable
in the treatment agent, and cannot be used. Specific
examples of R_1 , R_2 , R_3 , R_4 , and R_5 include methyl, ethyl,
propyl, butyl, hydroxyethyl, 2-hydroxypropyl, and

10 hydroxyisobutyl.

[0031]

A^- represents a hydroxide ion or an acid ion. Specific
examples of the acid ion include an acetate ion, a phosphate
ion, and formate ion.

15 [0032]

The resin compound (A) represented by the general
formula (I) is a bisphenol-formalin condensate and a
synthetic method thereof is not limited. For example, the
resin compound (A) can be obtained by allowing formalin and
20 amine to react with bisphenol A in the presence of an
alkaline catalyst.

[0033]

The cationic urethane (B) in a surface-treatment
composition according to the present invention is not
25 particularly limited in terms of a polyol component and an

isocyanate component that are monomer components forming the cationic urethane (B) and polymerization method as long as the cationic urethane (B) has at least one cationic functional group selected from primary to tertiary amino groups and a quaternary ammonium salt group. Examples of the cationic functional group include an amino group, a methylamino group, an ethylamino group, a dimethylamino group, a diethylamino group, a trimethylamino group, and a triethylamino group. However, the cationic functional groups are not limited as long as they are primary to tertiary amino groups and a quaternary ammonium salt group and they do not degrade performance of the present invention.

[0034]

The silane coupling agent (C) in a surface-treatment agent according to the present invention has at least one reactive functional group selected from an active-hydrogen-containing amino group, an epoxy group, a mercapto group, and a methacryloxy group. The silane coupling agent (C) is preferably a trialkoxysilane having three alkoxy. Such at least one silane coupling agent may be used without particular limitations. Specific examples of the silane coupling agent include N-(aminoethyl)3-aminopropyltrimethoxysilane, 3-aminopropyltrimethoxysilane, 3-glycidoxypropyltrimethoxysilane, 3-glycidoxypropylmethyldimethoxysilane, 2-

(3,4epoxycyclohexyl)ethyltriethoxysilane, and 3-mercaptopropyltrimethoxysilane.

[0035]

Examples of the organic titanium chelate compound (D)

5 in a surface-treatment agent according to the present invention include acetylacetonato titanium, titanium octylene glycolate, tetraacetylacetonato titanium, and titanium ethyl acetoacetate. Inorganic salts such as titanium nitrate, titanium sulfate, titanium acetate,
10 titanium phosphate, and titanium carbonate cannot dissolve with stability in a treatment agent according to the present invention or do not provide the effect of enhancing corrosion resistance, which is not preferable.

Fluorotitanic acid provides the effect. When fluorotitanic
15 acid is used, fluorotitanic acid is preferably added such that the fluorine content relative to the total of the solid contents of the resin compound (A), the cationic urethane (B), and the silane coupling agent (C) is 0.8 mass% or less. When the fluorine content is more than 0.8 mass%, corrosion
20 resistance in processed portions is degraded. When the organic titanium chelate compound is dissolved in water, titanium dissolves in the form of a chelate complex. Accordingly, high-polarity water-soluble solvents and peroxides that affect the complex are not preferably added
25 to a treatment agent according to the present invention.

[0036]

The tetravalent vanadyl compound (E) used in a surface-treatment agent according to the present invention is also not particularly limited. Specific examples of the
5 tetravalent vanadyl compound (E) include vanadyl sulfate, vanadyl dichloride, vanadyl phosphate, vanadyl oxalate, and vanadyl acetylacetonate. Pentavalent vanadium compounds have high water solubility and hence have a high probability of being released from films and do not sufficiently provide
10 the effect of enhancing corrosion resistance. The tetravalent vanadium compound used in a surface-treatment agent according to the present invention is most preferably a vanadyl compound that provides VO^{2+} (vanadyl) ions because the maximum effect of enhancing corrosion resistance is
15 provided.

[0037]

In a surface-treatment agent according to the present invention, a mass ratio $[(b)/\{(a) + (b) + (c)\}]$ of the solid content of the cationic urethane (B) to the total of the
20 solid contents of the resin compound (A), the cationic urethane (B), and the silane coupling agent (C) is preferably 0.1 to 0.3, more preferably 0.12 to 0.28. When the ratio is less than 0.1, the proportion of the urethane resin is too low and corrosion resistance in bent portions,
25 heat resistance, and storage stability of the surface-

treatment agent become poor. When the ratio is more than 0.3, solvent resistance becomes poor.

[0038]

In a surface-treatment agent according to the present invention, a mass ratio $[(c)/\{(a) + (b) + (c)\}]$ of the solid content of the silane coupling agent (C) to the total of the solid contents of the resin compound (A), the cationic urethane (B), and the silane coupling agent (C) is preferably 0.6 to 0.85, more preferably 0.65 to 0.80. When the ratio is less than 0.6, solvent resistance becomes poor. When the ratio is more than 0.85, corrosion resistance in processed portions and storage stability of the surface-treatment agent become poor.

[0039]

In a surface-treatment agent according to the present invention, a mass ratio $\{(c)/Ti\}$ of the solid content of the silane coupling agent (C) to the content of the organic titanium chelate compound (D) in terms of titanium is 50 to 70, preferably 55 to 65. When the ratio is less than 50, corrosion resistance in processed portions and storage stability become poor. When the ratio is more than 70, the probability of being released from a film increases and paintability after alkaline degreasing becomes poor.

[0040]

Note that, in the calculation of the mass ratios in the

present invention, the mass of the silane coupling agent (C) is defined as the mass of silanol ($\text{R-Si}(-\text{OH})_3$) provided by hydrolysis of alkoxy silane ($\text{R-Si}(-\text{OR}_1)_3$). This is because, when the silane coupling agent is dissolved in water, the most portion thereof is hydrolyzed and alcohol generated by the hydrolysis evaporates in the formation of a film by applying and drying a treatment agent according to the present invention and does not function as an active component.

10 [0041]

In a surface-treatment agent according to the present invention, a mass ratio (V/Ti) of the content of the tetravalent vanadyl compound (E) in terms of vanadium to the content of the organic titanium chelate compound (D) in terms of titanium is 0.3 to 0.5, preferably 0.35 to 0.48. When the ratio is less than 0.3, corrosion resistance becomes poor. When the ratio is more than 0.5, paintability after alkaline degreasing becomes poor.

[0042]

20 A surface-treatment agent according to the present invention has a pH of 4 to 5. When the pH is less than 4, a large amount of zinc is released from galvanized steel sheets that are surface-treated and corrosion resistance becomes poor. When the pH is more than 5, the surface-
25 treatment agent does not have stability. An acid component

used for adjusting the pH to be in the range of 4 to 5 is preferably phosphoric acid, acetic acid, formic acid, hydrofluoric acid, a fluoride, or the like. Strong acids such as sulfuric acid and nitric acid are not preferred.

- 5 When sulfuric acid or nitric acid is used, pH shock (local rapid change in pH) in the pH adjustment tends to cause gelation of cationic phenol and cationic urethane in the surface-treatment agent; in addition, salts generated in the gelation have a high probability of being released and
- 10 corrosion resistance becomes poor. Acetic acid and formic acid, which are weak acids, are suitable for the pH adjustment. In addition, these acids have a high probability of evaporation and evaporate in the drying of an agent according to the present invention and the amounts of
- 15 the acids remaining in the film become small. Accordingly, even when excessive amounts of the acids are added, degradation of performance is less likely to be caused, which is preferable. When phosphoric acid is used, the content of phosphoric acid relative to the total of the
- 20 solid contents of the resin compound (A), the cationic urethane (B), and the silane coupling agent (C) is preferably 8 mass% or less, more preferably 6 mass% or less. The lower limit is not particularly set; however, to enhance corrosion resistance, the phosphoric-acid content is
- 25 preferably 0.1 mass% or more, particularly preferably 0.5

mass% or more. Although phosphoric acid enhances corrosion resistance, a phosphoric-acid content of more than 8 mass% may cause degradation of storage stability. When hydrofluoric acid or a fluoride is used, hydrofluoric acid or a fluoride is added such that the fluorine content relative to the total of the solid contents of the resin compound (A), the cationic urethane (B), and the silane coupling agent (C) is 0.8 mass% or less. When the fluorine content is more than 0.8 mass%, there is a high probability of etching a zinc coating and corrosion resistance in processed portions is degraded. An alkaline component used for adjusting the pH to be in the range of 4 to 5 is preferably aqueous ammonia or an amine having a boiling point of 100°C or less. When a strong alkali such as NaOH or KOH is used, pH shock causes formation of a gel material or storage stability is degraded.

[0043]

In the present invention, a surface-treatment agent may contain a wax (W) for the purpose of ensuring lubricity of films. The wax (W) is preferably added such that a mass ratio $[(w)/\{(a) + (b)\}]$ of the solid content of the wax (W) to the total of the solid contents of the resin compound (A) and the cationic urethane (B) is 0.2 to 0.4, more preferably 0.3 to 0.4. Herein, (w) represents the solid content of the wax (W). Hereafter, the same definition is used. When the

mass ratio is 0.2 or more, lubricity is provided; and when the mass ratio is 0.4 or less, lubricity is ensured without economical disadvantage or degradation of corrosion resistance, which is preferable. As the wax (W), one or
5 more waxes having a melting point of 70°C to 120°C are preferably used. Specific examples of the wax (W) include polyethylene wax, polyethylene oxide wax, polypropylene wax, and microcrystalline wax. When the melting point is 70°C or more, lubricity is provided. When the melting point is
10 120°C or less, a film does not become too hard and has lubricity. The wax (W) is preferably used in the form of an emulsion in which the wax (W) is stably dispersed in water with an emulsifying agent. The wax (W) preferably has a particle size of 0.08 to 0.3 μm . When the particle size is
15 0.08 μm or more, the lubricity effect is provided and the amount of an emulsifying agent used does not increase and hence alkali resistance and paintability are not degraded. When the particle size is 0.3 μm or less, flotation separation of the wax (W) in the treatment agent due to low
20 specific gravity of the wax (W) does not occur and excellent storage stably is achieved, which is preferable.

[0044]

The water (F) used in the present invention is preferably a water that is less likely to affect the
25 components of the resin compound (A), the cationic urethane

(B), the silane coupling agent (C), and the organic titanium chelate compound (D); and an acid component and an alkaline component used for pH adjustment. Hardness components such as Mg, Ca, and Si contained in water as impurities degrade solubility and dispersibility of the resin compound (A) and the cationic urethane (B) according to the present invention and may cause generation of aggregates of (A) and (B). In addition, when Na, Cl, and the like contained in water as impurities remain in films, they may degrade corrosion resistance or painting adhesion. Accordingly, the water (F) used preferably contains small amounts of impurities and, for example, preferably has an electrical conductivity of less than 100 $\mu\text{S}/\text{cm}$, more preferably 50 $\mu\text{S}/\text{cm}$ or less, still more preferably 10 $\mu\text{S}/\text{cm}$ or less.

15 [0045]

A surface-treatment agent according to the present invention may optionally contain a defoaming agent or a wettability enhancer. The type of the defoaming agent is not particularly limited and may be, for example, an emulsion of silicone or a fatty acid. The wettability enhancer is an agent that decreases the surface tension of the surface-treatment agent to enhance the wettability of the surface-treatment agent to galvanized steel sheets to thereby enhance appearance uniformity. The wettability enhancer may be a water-soluble solvent such as ethanol, T-

butanol, or butyl cellosolve; however, the wettability enhancer is not limited to these solvents. For example, a wettability enhancer containing acetylene has a defoaming effect and is preferable. A surface-treatment agent according to the present invention may optionally contain a nitrate such as nickel nitrate or ammonium nitrate for the purpose of enhancing blackening resistance. While nitric acid causes pH shock as described above, nitrates do not cause pH shock.

10 [0046]

Hereinafter, a method for producing a coated steel sheet employing the surface-treatment agent will be described.

A surface-treatment film is preferably formed on a coated steel sheet using a surface-treatment agent according to the present invention by applying the surface-treatment agent to the coated steel sheet and drying the surface-treatment agent at a sheet temperature of 50°C to 180°C to form a surface-treatment film having a coating weight of 0.2 to 1.8 g/m² relative to a single surface of the steel sheet. The coating weight is more preferably 0.3 to 1.6 g/m², still more preferably 0.4 to 1.4 g/m². When the coating weight is less than 0.2 g/m², corrosion resistance is not sufficiently provided. When the coating weight is more than 1.8 g/m², the effect in terms of coating weight is saturated and such a

coating weight is economically disadvantageous and also degrades paintability. A surface-treatment agent according to the present invention may be applied to a coated steel sheet with a roll coater (having a three-roll configuration, a two-roll configuration, or the like), a squeeze coater, a die coater, or the like. After the coating treatment with a squeeze coater or the like, an immersion treatment, or a spraying treatment is performed, an air knife method or a roll-squeezing method may be used to adjust the coating weight and to make the appearance and thickness of the film be uniform.

[0047]

After a coated steel sheet is coated with a surface-treatment agent according to the present invention, the surface-treatment agent is preferably dried under heating without being rinsed. The drying may be performed with a dryer, an air-heating furnace, a high-frequency induction furnace, an infrared furnace, or the like. The drying is performed at a coated-steel-sheet temperature of 50°C to 180°C. When the sheet temperature is less than 50°C, a large amount of water remains in the film and corrosion resistance becomes insufficient. When the sheet temperature is more than 180°C, which is not economical, the film becomes hard and brittle and corrosion resistance in processed portions becomes poor.

[0048]

A coated steel sheet according to the present invention that is produced by the above-described method and has a surface-treatment film may be further coated with a resin
5 film so as to have higher corrosion resistance.

[0049]

A surface-treatment film formed with a surface-treatment agent according to the present invention may be formed on a single surface or both surfaces of a coated
10 steel sheet.

[0050]

Hereinafter, effects of the present invention will be described. The components of a surface-treatment agent according to the present invention probably have the
15 following effects; however, the description of these effects does not limit the present invention at all.

A surface-treatment agent according to the present invention mainly contains the resin compound (A), the cationic urethane (B), and the silane coupling agent (C).
20 These main components form the skeleton of a film.

[0051]

By adjusting the pH of a surface-treatment agent such that the surface-treatment agent becomes weakly acidic, the surface-treatment agent containing the resin compound (A)
25 having a cationic functional group (general formula (II) or

(III)), the stability of the surface-treatment agent is enhanced and the storage stability of the surface-treatment agent is ensured. In addition, by making the resin compound (A) be cationic, the resin compound (A) does not dissolve in alkali and hence a film having alkali resistance is provided. In addition, by selecting bisphenol as the phenol skeleton of the resin compound (A), the resin compound (A) becomes less likely to dissolve in polar solvents (solvent resistance is imparted) to thereby provide enhanced adhesion and corrosion resistance.

[0052]

However, the resin compound (A) tends to turn yellow under heating (degradation of thermal yellowing resistance) and tends to provide a hard film. Accordingly, in the present invention, the cationic urethane (B) is further added to reduce hardness due to the phenolic resin to thereby ensure corrosion resistance in processed portions.

[0053]

Although the cationic urethane (B) has such an advantage, it provides a film that is likely to separate with polar solvents. Accordingly, in the present invention, the silane coupling agent (C) is further added for the purpose of ensuring solvent resistance (relative to polar solvents) and yellowing resistance. The silane coupling agent (C) produces active silanol groups (Si-OH) from end

alkoxy groups through hydrolysis and hence contributes to adhesion to a material (galvanized steel sheet) and an overcoat. In addition, a portion of the silane coupling agent (C) undergoes dehydration condensation to generate
5 siloxane bonds (Si-O-Si). The silane coupling agent (C) turns into a polymer by the formation of continuous chains of the siloxane bonds (formation of polysiloxane: -Si-O-Si-O-Si-). As a result, the silane coupling agent (C) has a structure with high stability and can impart corrosion
10 resistance, solvent resistance, and yellowing resistance to the film.

[0054]

As described above, by using the resin compound (A), the cationic urethane (B), and the silane coupling agent (C)
15 serving as main components with appropriate proportions, highly balanced various characteristics can be probably achieved. However, an agent that overcomes existing problems and achieves the newly found objects cannot be obtained with the main components only. To achieve the
20 objects, a surface-treatment agent according to the present invention contains, as essential components, the main components and the organic titanium chelate compound (D). The organic titanium chelate compound (D) probably functions as a catalyst promoting formation of polysiloxane in the
25 formation of a film by drying the surface-treatment agent.

As a result, the film has considerably enhanced alkali resistance, enhanced corrosion resistance after alkaline degreasing, enhanced solvent resistance, and enhanced paintability.

5 [0055]

To provide such an effect, a predetermined content of the organic titanium chelate compound (D) is needed, the predetermined content being determined in accordance with the content of the silane coupling agent (C). When the
10 content of the organic titanium chelate compound (D) is low, the desired effect is not provided; and when the content is excessive, the amount of polysiloxane becomes excessively large to provide a hard and brittle film and corrosion resistance in processed portions becomes poor. Although the
15 formation of polysiloxane promoted by the organic titanium chelate compound (D) ideally proceeds in the formation of the film, the organic titanium chelate compound (D) also promotes the formation of polysiloxane during storage of the surface-treatment agent. Accordingly, when the content of
20 the organic titanium chelate compound (D) is excessive, storage stability (suppression of an increase in viscosity and gelation) of the surface-treatment agent becomes poor and the surface-treatment agent after storage no longer has the quality thereof before the storage.

25 [0056]

A surface-treatment agent according to the present invention contains the tetravalent vanadyl compound (E) as another essential component. In the present invention, the tetravalent vanadyl compound (E) probably functions as a corrosion inhibitor (for example, passivation of zinc). In particular, vanadyl $[VO^{2+}]$ ions having a single oxygen are less likely to be released under a wet environment and remain in the film to provide the inhibitor effect.

Accordingly, the vanadyl ions probably enhance corrosion resistance in portions of a coated steel sheet where the coated steel sheet is subjected to strong processing such as bending and the surface-treatment film and the coated surface in the portions undergo ductile fracture; and corrosion resistance after alkaline degreasing. The inventors of the present invention consider that such an effect is provided only when the film skeleton having a cationic functional group is appropriate and the effect is probably achieved through synergistic effect between the film skeleton and Ti that is also present as a cation.

[EXAMPLES]

[0057]

Resin compounds (A) described in Table 1 (Table 1a and Table 1b), urethanes (B) described in Table 2, silane coupling agents (C) described in Table 3, titanium compounds (D) described in Table 4, vanadium compounds (E) described

in Table 5, wax (W) emulsions in Table 6 were appropriately mixed to prepare surface-treatment agents. For example, as for a surface-treatment agent in Example 1, mixing was performed so as to achieve a composition in Table 8; the pH of the mixture was adjusted to a value described in Table 8 with acetic acid and ammonia; and the surface-treatment agent was prepared with deionized water so as to have a dry solid content (drying at 110°C for 2 hours) of 10 mass%. All the other surface-treatment agents were also adjusted in terms of pH with acetic acid and ammonia and prepared so as to have a dry solid content of 10 mass%. The deionized water was an ion-exchanged water having an electrical conductivity of 10 $\mu\text{S}/\text{cm}$.

[0058]

Coated steel sheets described in Table 7 were used as base sheets to be treated. The surfaces of each coated steel sheet were subjected to an alkaline degreasing treatment, rinsed, and dried. A single surface of the coated steel sheet was coated with a surface-treatment agent described in Table 8 with a roll coater and dried at a temperature described in Table 8 under heating without being rinsed. Thus, a coated steel sheet having a surface-treatment film was produced. The coating weight of the surface-treatment film relative to a single surface was adjusted by changing the solid content (heating residue) of

the surface-treatment agent or coating conditions (roll separating force, rotational speed, and the like). The coating weight was determined by quantifying Si in the silane coupling agent (C) added with a fluorescent X-ray analysis apparatus and converting the Si quantity. The compositions of the surface-treatment agents and results of tests in terms of quality (corrosion resistance in a flat portion, corrosion resistance in a bent portion, corrosion resistance after alkaline degreasing, thermal discoloration resistance, paintability, paintability after alkaline degreasing, solvent resistance, storage stability, and lubricity) are described in Table 8. The qualities were evaluated under the following conditions.

[0059]

15 (1) Corrosion resistance

The samples were subjected to salt spray testing (JIS-Z-2371-2000) and were evaluated in terms of area percentage of white rust after a lapse of 120 hours. The following evaluation criteria were used.

20 Excellent: white-rust area percentage of 0%

Very Good: white-rust area percentage of less than 5%

Good: white-rust area percentage of 5% or more and less than 10%

Fair: white-rust area percentage of 10% or more and less than 20%

Poor: white-rust area percentage of 20% or more and less than 40%

Very poor: white-rust area percentage of 40% or more
[0060]

5 (2) Corrosion resistance in bent portion

Each sample was bent at 180° by being sandwiched between rods (formed of stainless steel) having a diameter of 2 mm and was squeezed with a vise. The bent sample was subjected to salt spray testing (JIS-Z-2371-2000) and was
10 evaluated in terms of generation of white rust in the outer (front) surface of the bent portion after a lapse of 72 hours. The following evaluation criteria were used.

Excellent: no rust in the bent portion

Very Good: rust area percentage of less than 5% in the bent
15 portion

Good: rust area percentage of 5% or more and less than 10% in the bent portion

Fair: rust area percentage of 10% or more and less than 40% in the bent portion

20 Poor: rust area percentage of 40% or more and less than 80% in the bent portion

Very poor: rust area percentage of 80% or more in the bent portion

[0061]

25 (3) Corrosion resistance after alkaline degreasing

An alkaline degreasing agent CL-N364S (manufactured by Nihon Parkerizing Co., LTD.) was dissolved at a concentration of 20 g/l in pure water and heated to 60°C. Each sample was immersed in this alkaline solution for 2 minutes, taken out from the solution, rinsed, and dried. The sample was subjected to salt spray testing (JIS-Z-2371-2000) and was evaluated in terms of area percentage of white rust after a lapse of 72 hours. The evaluation criteria described in (1) above were used.

10 [0062]

(4) Thermal discoloration resistance

Each sample was heated with an infrared image furnace for 30 seconds so that a sheet temperature may reach 500°C, held for 30 seconds, and allowed to naturally cool to room temperature. The appearance of a surface of the sample was visually inspected. The following evaluation criteria were used.

Excellent: no discoloration

Good: very slightly brown

20 Fair: discoloration to pale brown

Poor: discoloration to brown

[0063]

(5) Paintability

Each sample was painted with a DELICON (registered trademark) #700 (manufactured by Dai Nippon Toryo Company,

Limited), which is a melamine alkyd paint, baked at 130°C for 30 minutes to form a painted film having a thickness of 30 µm, immersed in boiling water for 2 hours, and immediately cut in a lattice pattern (10 × 10 squares,

5 pitch: 1 mm) to such a depth as to reach the base steel.

The sample was subjected to cupping by 5 mm with an Erichsen tester such that the cut portion was on the outer (front) side. An adhesive tape was affixed to the sample and

removed from the sample and delamination area percentage of
10 the painted film was determined. The evaluation criteria below were used. The Erichsen cupping conditions were compliance with JIS-Z-2247-2006 and the punch diameter was 20 mm, the die diameter was 27 mm, and the drawing width was 27 mm.

15 Excellent: no delamination

Very Good: delamination area of less than 3%

Good: delamination area of 3% or more and less than 10%

Fair: delamination area of 10% or more and less than 20%

Poor: delamination area of 20% or more and less than 50%

20 Very poor: delamination area of 50% or more

[0064]

(6) Paintability after alkaline degreasing

Each sample was subjected to alkaline degreasing as in

(3) above and subjected to the paintability test as in (5)

25 above. The same evaluation criteria as in (5) were used.

[0065]

(7) Solvent resistance

A gauze impregnated with methanol was pressed under a load of 4.90 N (500 gf) onto a surface of each sample and
5 rubbed against the surface in a reciprocating manner for ten cycles under the load. Tracks caused by the rubbing were evaluated by visual inspection. The following evaluation criteria were used.

Excellent: no tracks

10 Very Good: no tracks visible when viewed from above, but tracks slightly visible when viewed obliquely

Good: no tracks visible when viewed from above, but tracks clearly visible when viewed obliquely

Fair: tracks slightly visible when viewed from above

15 Poor: tracks clearly visible when viewed from above

Very poor: delamination of the film

[0066]

(8) Storage stability

The surface-treatment agents described in Table 8 were
20 stored in a constant temperature chamber at 40°C for 30 days. The surface-treatment agents were taken out and the appearance thereof was visually inspected and evaluated. The evaluation criteria below were used. Furthermore, coated steel sheets having surface-treatment films produced
25 with the surface-treatment agents stored under such

conditions were subjected to the tests (1) to (3) described above.

Excellent: no change

Good: very small amount of precipitation

5 Fair: small amount of precipitation or an increase in viscosity to some extent

Poor: large amount of precipitation or gelation

[0067]

(9) Lubricity

10 A disc-shaped specimen having a diameter of 100 mm was cut from each sample and formed into a cup under conditions: a punch diameter of 50 mm, a die diameter of 51.91 mm, and a blank holding force of 1 ton. The appearance of the drawn surface of the formed product (outer side surface of the
15 cup) was visually inspected and was evaluated in terms of how scratched it was and how blackened it was. The following evaluation criteria were used.

Excellent: almost no change over the entire surface, uniform appearance

20 Very Good: very slightly blackened, but uniform appearance

Good: slightly scratched and blackened and clearly nonuniform appearance

Fair: locally scratched and blackened and clearly nonuniform appearance

25 Poor: severely scratched and blackened mainly in corner

portions

Very poor: cracked and the forming was not achieved

[0068]

[Table 1a]

No.	Z group: general formula (II)				Average substitution number of Z group	n
	Y1		Y2			
	R1	R2	R1	R2		
A1	hydrogen	hydrogen	methyl	ethyl	0.4	5
A2	ethyl	methyl	hydrogen	propyl	0.7	3
A3	ethyl	propyl	hydrogen	ethyl	0.4	10
A4	hydroxyethyl	hydroxyethyl	hydroxyethyl	hydroxyethyl	0.5	5
A5	hydrogen	hydrogen	methyl	ethyl	<u>0.1</u>	5
A6	hydrogen	hydrogen	methyl	ethyl	<u>1.2</u>	5
A7	hydrogen	hydrogen	methyl	ethyl	0.4	<u>80</u>
A8	-C ₁₂ H ₂₃	methyl	hydrogen	hydrogen	0.5	5
A9	hydroxyethyl	hydroxyethyl	hydroxyethyl	hydroxyethyl	<u>0.1</u>	5
A10	hydroxyethyl	hydroxyethyl	hydroxyethyl	hydroxyethyl	<u>1.2</u>	5
A11	hydroxyethyl	hydroxyethyl	hydroxyethyl	hydroxyethyl	0.5	<u>70</u>
A12	-C ₁₂ H ₂₂ OH	methyl	hydrogen	hydrogen	0.5	5

※Groups represented by the general formula (II) were used as Z groups.

[Table 1b]

No.	Z group : general formula (III)						Average substitution number of Z group	n
	Y1			Y2				
	R3	R4	R5	R3	R4	R5		
A13	hydrogen	hydrogen	methyl	methyl	ethyl	methyl	0.4	5
A14	ethyl	methyl	hydrogen	hydrogen	propyl	hydrogen	0.7	3
A15	ethyl	propyl	methyl	hydrogen	ethyl	methyl	0.4	10
A16	hydroxyethyl	hydroxyethyl	hydrogen	hydroxyethyl	hydroxyethyl	hydrogen	0.5	5
A17	hydrogen	hydrogen	methyl	methyl	ethyl	methyl	0.1	5
A18	hydrogen	hydrogen	methyl	methyl	ethyl	methyl	1.2	5
A19	hydrogen	hydrogen	methyl	methyl	ethyl	methyl	0.4	80
A20	-C ₁₂ H ₂₃	methyl	hydrogen	hydrogen	hydrogen	hydrogen	0.5	5
A21	hydroxyethyl	hydroxyethyl	hydrogen	hydroxyethyl	hydroxyethyl	hydrogen	0.1	5
A22	hydroxyethyl	hydroxyethyl	hydrogen	hydroxyethyl	hydroxyethyl	hydrogen	1.2	5
A23	hydroxyethyl	hydroxyethyl	hydrogen	hydroxyethyl	hydroxyethyl	hydrogen	0.5	70
A24	-C ₁₂ H ₂₂ OH	methyl	hydrogen	hydrogen	hydrogen	hydrogen	0.5	5

※Groups represented by the general formula (III) were used as Z groups.

[0069]

[Table 2]

No.	Urethane resin (B)	Ionicity	Manufacturer
B1	ADEKA BONTIGHTER HUX-670	Cation	ADEKA CORPORATION
B2	SUPERFLEX 600	Cation	DAI-ICHI KOGYO SEIYAKU CO., LTD.
B3	PERMARIN UC-20	Cation	Sanyo Chemical Industries, Ltd.
B4	ADEKA BONTIGHTER UX-206	<u>Nonion</u>	ADEKA CORPORATION
B5	HYDRAN AP-10	<u>Anion</u>	DIC Corporation

[0070]

[Table 3]

No.	Silane coupling agent (C)
C1	3-mercaptopropyltrimethoxysilane
C2	N-(2-aminoethyl)-3-aminopropyltrimethoxysilane
C3	3-glycidoxypentyltrimethoxysilane
C4	3-methacryloxypropyltrimethoxysilane
C5	<u>vinyltrimethoxysilane</u>

[0071]

[Table 4]

No.	Ti compound (D)
D1	acetylacetonato titanium (Ti:12.5%)
D2	tetraacetylacetonato titanium (Ti:10.8%)
D3	<u>titanium nitrate (Ti:16.2%)</u>
D4	<u>fluorotitanic acid (Ti:29.2%)</u>

[0072]

[Table 5]

No.	V compound (E)
E1	vanadyl oxalate (V:32.9%)
E2	vanadyl acetylacetonate (V:19.2%)
E3	vanadyl sulfate (V:31.2%)
E4	ammonium metavanadate (V:43.5%)

[0073]

[Table 6]

No.	Wax (W)	Melting point (°C)	Solid content of dispersion(%)	Particle size (μm)
W1	polyethylene oxide wax	115	20	0.1
W2	microcrystalline wax	90	20	0.1
W3	paraffin wax	50	20	0.1

※These waxes were made to be emulsified with an emulsifying agent and used.

[0074]

[Table 7]

No.	Coated steel sheet	Coating weight (g/m^2)
GI	hot dip galvanized steel sheet	60
EG	electrogalvanized steel sheet	20
GA	galvannealed steel sheet	60
GF	hot dip Zn-5mass%Al-0.5mass%Mg alloy-coated steel sheet	90
GL	hot dip Zn-5.5mass%Al alloy-coated steel sheet	100

※Although both surfaces were coated, a coating weight relative to a single surface is described in the table.

[0075]

[Table 8-1]

No.		(A) Type		(B) Type		(C) Type		Parts by mass of Ti (D)		Parts by mass of V (E)		(W)		Acid component 1	
		Table 1	parts by mass	Table 2	parts by mass	Table 3	parts by mass	Type Table 4	parts by mass	Type Table 5	parts by mass	Type Table 6	parts by mass	Type	parts by mass
1	Invention example 1	A1	4	B1	16	C1	60	D1	1	E1	0.4	-	0	phosphoric acid	4
2	Invention example 2	A1	10	B1	10	C1	60	D1	1	E1	0.4	-	0	phosphoric acid	4
3	Invention example 3	A1	11	B1	9	C1	60	D1	1	E1	0.4	-	0	phosphoric acid	4
4	Comparative example 1	A1	14	B1	6	C1	60	D1	1	E1	0.4	-	0	phosphoric acid	4
5	Invention example 4	A1	0.5	B1	19.5	C1	60	D1	1	E1	0.4	-	0	phosphoric acid	4
6	Invention example 5	A1	0.5	B1	21.5	C1	58	D1	1	E1	0.4	-	0	phosphoric acid	4
7	Invention example 6	A1	0.5	B1	23.5	C1	56	D1	1	E1	0.4	-	0	phosphoric acid	4
8	Comparative example 2	A1	0.1	B1	25.9	C1	55	D1	1	E1	0.4	-	0	phosphoric acid	4
9	Comparative example 3	A1	4	B1	16	C1	60	D3	1	E1	0.4	-	0	phosphoric acid	4
10	Comparative example 4	A1	4	B1	16	C1	60	D4	1	E1	0.4	-	0	phosphoric acid	4
11	Comparative example 5	A1	4	B1	16	C1	60	D1	1	E1	0	-	0	phosphoric acid	4
12	Comparative example 6	A1	4	B1	16	C1	60	D1	1	E4	0.4	-	0	phosphoric acid	4
13	Comparative example 7	A1	29	B1	6	C1	65	D4	1.134	E1	0	-	0	nitric acid	10
14	Comparative example 8	A1	29	B1	6	C1	65	D4	1.134	E1	0	-	0	phosphoric acid	10
15	Comparative example 9	A1	20	B1	40	C2:C3=1:1	20	D4	1	E1	0.4	-	0	phosphoric acid	6
16	Invention example 7	A2	4	B1	16	C2	60	D1	1	E2	0.4	-	0	phosphoric acid	4
17	Invention example 8	A3	4	B1	16	C2	60	D2	1	E3	0.4	-	0	-	0
18	Invention example 9	A2	4	B1	19	C3	60	D1	1	E2	0.4	-	0	phosphoric acid	5
19	Invention example 10	A1	4	B1	19	C2:C3=1:1	60	D1	1	E3	0.4	-	0	-	0
20	Invention example 11	A1	4	B1	19	C1	60	D1:D4=10:1	1.1	E2	0.4	-	0	phosphoric acid	4
21	Comparative example 10	A1	19	B1	19	C1	45	D1	0.75	E2	0.3	-	0	phosphoric acid	4
22	Invention example 12	A1	12	B1	19	C1	52	D1	0.85	E2	0.34	-	0	phosphoric acid	4
23	Invention example 13	A1	4	B1	11	C1	68	D1	1.1	E2	0.44	-	0	phosphoric acid	4
24	Comparative example 11	A1	1	B1	10	C1	72	D1	1.2	E2	0.48	-	0	phosphoric acid	4
25	Comparative example 12	A1	4	B1	16	C1	60	D1	0.8	E2	0.32	-	0	phosphoric acid	4
26	Invention example 14	A1	4	B1	16	C1	60	D1	0.88	E2	0.35	-	0	phosphoric acid	4
27	Invention example 15	A1	4	B1	16	C1	60	D1	1.15	E2	0.46	-	0	phosphoric acid	4

[Table 8-2]

No.		(A) Type		(B) Type		(C) Type		Parts by mass of Ti (D)		Parts by mass of V (E)		(W)		Acid component 1	
		Table 1	parts by mass	Table 2	parts by mass	Table 3	parts by mass	Type Table 4	parts by mass	Type Table 5	parts by mass	Type Table 6	parts by mass	Type	parts by mass
28	Comparative example 13	A1	4	B1	16	C1	60	D1	1.25	E2	0.5	-	0	phosphoric acid	4
29	Comparative example 14	A1	4	B1	16	C1	60	D1	1	E2	0.24	-	0	phosphoric acid	4
30	Invention example 16	A1	4	B1	16	C1	60	D1	1	E2	0.33	-	0	phosphoric acid	4
31	Invention example 17	A1	4	B1	16	C1	60	D1	1	E2	0.49	-	0	phosphoric acid	4
32	Comparative example 15	A1	4	B1	16	C1	60	D1	1	E2	0.55	-	0	phosphoric acid	4
33	Invention example 18	A1	4	B1	16	C1	60	D1	1	E2	0.4	W1	6.1	phosphoric acid	4
34	Invention example 19	A1	4	B1	16	C1	60	D1	1	E2	0.4	W2	6.1	phosphoric acid	4
35	Invention example 20	A1	4	B1	16	C1	60	D1	1	E2	0.4	W3	6.1	phosphoric acid	4
36	Invention example 21	A1	4	B1	16	C1	60	D1	1	E2	0.4	W1	7.8	phosphoric acid	4
37	Invention example 22	A1	4	B1	16	C1	60	D1	1	E2	0.4	W1	5	phosphoric acid	4
38	Comparative example 16	A1	4	B1	16	C1	60	D1	1	E1	0.4	-	0	phosphoric acid	4
39	Comparative example 17	A1	4	B1	16	C1	60	D1	1	E1	0.4	-	0	phosphoric acid	4
40	Invention example 23	A1	4	B1	16	C1	60	D1	1	E1	0.4	-	0	phosphoric acid	4
41	Invention example 24	A1	4	B1	16	C1	60	D1	1	E1	0.4	-	0	phosphoric acid	4
42	Comparative example 18	A1	4	B1	16	C1	60	D1	1	E1	0.4	-	0	phosphoric acid	4
43	Comparative example 19	A1	4	B1	16	C1	60	D1	1	E1	0.4	-	0	phosphoric acid	4
44	Invention example 1A	A1	4	B1	16	C1	60	D1	1	E1	0.4	-	0	phosphoric acid	4
45	Invention example 25	A1	4	B1	16	C1	60	D1	1	E1	0.4	-	0	phosphoric acid	4
46	Invention example 26	A1	4	B1	16	C1	60	D1	1	E1	0.4	-	0	phosphoric acid	4
47	Invention example 27	A1	4	B1	16	C1	60	D1	1	E1	0.4	-	0	phosphoric acid	4
48	Invention example 28	A1	4	B1	16	C1	60	D1	1	E1	0.4	-	0	phosphoric acid	4
49	Invention example 2A	A1	4	B1	16	C1	60	D1	1	E1	0.4	-	0	phosphoric acid	4
50	Invention example 1B	A1	4	B1	16	C1	60	D1	1	E1	0.4	-	0	phosphoric acid	4
51	Invention example 29	A1	4	B1	16	C1	60	D1	1	E1	0.4	-	0	phosphoric acid	4
52	Invention example 30	A1	4	B1	16	C1	60	D1	1	E1	0.4	-	0	phosphoric acid	4
53	Invention example 2B	A1	4	B1	16	C1	60	D1	1	E1	0.4	-	0	phosphoric acid	4
54	Invention example 31	A4	4	B1	16	C1	60	D1	1	E1	0.4	-	0	phosphoric acid	4

[Table 8-3]

No.		(A) Type		(B) Type		(C) Type		Parts by mass of Ti		Parts by mass of V		(W)		Acid component 1	
		Table 1	parts by mass	Table 2	parts by mass	Table 3	parts by mass	Type 4	parts by mass	Type 5	parts by mass	Type 6	parts by mass	Type	parts by mass
55	Comparative example 20	A5	4	B1	16	C1	60	D1	1	E1	0.4	-	0	phosphoric acid	4
56	Comparative example 21	A6	4	B1	16	C1	60	D1	1	E1	0.4	-	0	phosphoric acid	4
57	Comparative example 22	A7	4	B1	16	C1	60	D1	1	E1	0.4	-	0	phosphoric acid	4
58	Comparative example 23	A8	4	B1	16	C1	60	D1	1	E1	0.4	-	0	phosphoric acid	4
59	Comparative example 24	A9	4	B1	16	C1	60	D1	1	E1	0.4	-	0	phosphoric acid	4
60	Comparative example 25	A10	4	B1	16	C1	60	D1	1	E1	0.4	-	0	phosphoric acid	4
61	Comparative example 26	A11	4	B1	16	C1	60	D1	1	E1	0.4	-	0	phosphoric acid	4
62	Comparative example 27	A12	4	B1	16	C1	60	D1	1	E1	0.4	-	0	phosphoric acid	4
63	Invention example 32	A13	4	B1	16	C1	60	D1	1	E1	0.4	-	0	phosphoric acid	4
64	Invention example 33	A14	4	B1	16	C1	60	D1	1	E1	0.4	-	0	phosphoric acid	4
65	Invention example 34	A15	4	B1	16	C1	60	D1	1	E1	0.4	-	0	phosphoric acid	4
66	Invention example 35	A16	4	B1	16	C1	60	D1	1	E1	0.4	-	0	phosphoric acid	4
67	Comparative example 28	A17	4	B1	16	C1	60	D1	1	E1	0.4	-	0	phosphoric acid	4
68	Comparative example 29	A18	4	B1	16	C1	60	D1	1	E1	0.4	-	0	phosphoric acid	4
69	Comparative example 30	A19	4	B1	16	C1	60	D1	1	E1	0.4	-	0	phosphoric acid	4
70	Comparative example 31	A20	4	B1	16	C1	60	D1	1	E1	0.4	-	0	phosphoric acid	4
71	Comparative example 32	A21	4	B1	16	C1	60	D1	1	E1	0.4	-	0	phosphoric acid	4
72	Comparative example 33	A22	4	B1	16	C1	60	D1	1	E1	0.4	-	0	phosphoric acid	4
73	Comparative example 34	A23	4	B1	16	C1	60	D1	1	E1	0.4	-	0	phosphoric acid	4
74	Comparative example 35	A24	4	B1	16	C1	60	D1	1	E1	0.4	-	0	phosphoric acid	4
75	Invention example 36	A1	4	B2	16	C1	60	D1	1	E1	0.4	-	0	phosphoric acid	4
76	Invention example 37	A1	4	B3	16	C1	60	D1	1	E1	0.4	-	0	phosphoric acid	4
77	Comparative example 36	A1	4	B4	16	C1	60	D1	1	E1	0.4	-	0	phosphoric acid	4
78	Comparative example 37	A1	4	B5	16	C1	60	D1	1	E1	0.4	-	0	phosphoric acid	4
79	Invention example 38	A1	4	B1	16	C4	60	D1	1	E1	0.4	-	0	phosphoric acid	4
80	Comparative example 38	A1	4	B1	16	C5	60	D1	1	E1	0.4	-	0	phosphoric acid	4
81	Invention example 39	A1	4	B1	16	C1	60	D1	1	E1	0.4	-	0	phosphoric acid	4

[Table 8-4]

No.		Acid component 2		pH	(X1)	(X2)	(X3)	(X4)	(X5)	PO ₄ / (a+b+c)	F/ (a+b+c)	Coated steel sheet	Drying temperature °C	Coating weight g/m ²	Remarks
		Type	parts by mass												
1	Invention example 1	-	0	4.5	0.20	0.75	60	0.40	0	0.050	0	GI	100	1.0	
2	Invention example 2	-	0	4.5	0.13	0.75	60	0.40	0	0.050	0	GI	100	1.0	
3	Invention example 3	-	0	4.5	0.11	0.75	60	0.40	0	0.050	0	GI	100	1.0	
4	Comparative example 1	-	0	4.5	0.08	0.75	60	0.40	0	0.050	0	GI	100	1.0	
5	Invention example 4	-	0	4.5	0.24	0.75	60	0.40	0	0.050	0	GI	100	1.0	
6	Invention example 5	-	0	4.5	0.27	0.73	58	0.40	0	0.050	0	GI	100	1.0	
7	Invention example 6	-	0	4.5	0.29	0.70	56	0.40	0	0.050	0	GI	100	1.0	
8	Comparative example 2	-	0	4.5	0.32	0.68	55	0.40	0	0.049	0	GI	100	1.0	
9	Comparative example 3	-	0	4.5	0.20	0.75	60	0.40	0	0.050	0	GI	100	1.0	
10	Comparative example 4	-	0	4.5	0.20	0.75	60	0.40	0	0.050	0.030	GI	100	1.0	
11	Comparative example 5	-	0	4.5	0.20	0.75	60	0.00	0	0.050	0	GI	100	1.0	
12	Comparative example 6	-	0	4.5	0.20	0.75	60	0.40	0	0.050	0	GI	100	1.0	
13	Comparative example 7	-	0	4.5	0.06	0.65	57	0.00	0	0.100	0.027	GI	100	1.0	Reference: Japanese Patent No. 3883831
14	Comparative example 8	-	0	4.5	0.06	0.65	57	0.00	0	0.100	0.027	GI	100	1.0	
15	Comparative example 9	-	0	4.5	0.50	0.25	20	0.40	0	0.075	0.030	GI	100	1.0	Reference: Japanese Unexamined Patent Application Publication No. 2006-152436
16	Invention example 7	-	0	4.5	0.20	0.75	60	0.40	0	0.050	0	GI	100	1.0	
17	Invention example 8	H ₂ ZrF ₆	0.5	4.5	0.20	0.75	60	0.40	0	0.000	0.003	EG	100	1.0	
18	Invention example 9	hydrofluoric acid	0.5	4.5	0.23	0.72	60	0.40	0	0.060	0.006	GA	100	1.0	
19	Invention example 10	hydrofluoric acid	0.5	4.5	0.23	0.72	60	0.40	0	0.000	0.006	GF	100	1.0	
20	Invention example 11	-	0	4.5	0.23	0.72	55	0.36	0	0.048	0.003	EG	100	1.0	
21	Comparative example 10	-	0	4.5	0.23	0.54	60	0.40	0	0.048	0	GI	100	1.0	
22	Invention example 12	-	0	4.5	0.23	0.63	61	0.40	0	0.048	0	GI	100	1.0	
23	Invention example 13	-	0	4.5	0.13	0.82	62	0.40	0	0.048	0	GI	100	1.0	
24	Comparative example 11	-	0	4.5	0.12	0.87	60	0.40	0	0.048	0	GI	100	1.0	
25	Comparative example 12	-	0	4.5	0.20	0.75	75	0.40	0	0.050	0	GI	100	1.0	
26	Invention example 14	-	0	4.5	0.20	0.75	68	0.40	0	0.050	0	GI	100	1.0	
27	Invention example 15	-	0	4.5	0.20	0.75	52	0.40	0	0.050	0	GI	100	1.0	

(X1) = (b)/(a+b+c), X2 = (c)/(a+b+c), X3 = (c)/Ti, X4 = V/Ti, X5 = (w)/(a+b)

[Table 8-5]

No.		Acid component 2		pH	(X1)	(X2)	(X3)	(X4)	(X5)	PO ₄ / (a+b+c)	F / (a+b+c)	Coated steel sheet	Drying temperature °C	Coating weight g/m ²	Remarks
		Type	parts by mass												
28	Comparative example 13	-	0	4.5	0.20	0.75	48	0.40	0	0.050	0	GI	100	1.0	
29	Comparative example 14	-	0	4.5	0.20	0.75	60	0.24	0	0.050	0	GI	100	1.0	
30	Invention example 16	-	0	4.5	0.20	0.75	60	0.33	0	0.050	0	GI	100	1.0	
31	Invention example 17	-	0	4.5	0.20	0.75	60	0.49	0	0.050	0	GI	100	1.0	
32	Comparative example 15	-	0	4.5	0.20	0.75	60	0.55	0	0.050	0	GI	100	1.0	
33	Invention example 18	-	0	4.5	0.20	0.75	60	0.40	0.31	0.050	0	GI	100	1.0	
34	Invention example 19	-	0	4.5	0.20	0.75	60	0.40	0.31	0.050	0	GI	100	1.0	
35	Invention example 20	-	0	4.5	0.20	0.75	60	0.40	0.31	0.050	0	GI	100	1.0	
36	Invention example 21	-	0	4.5	0.20	0.75	60	0.40	0.38	0.050	0	GI	100	1.0	
37	Invention example 22	-	0	4.5	0.20	0.75	60	0.40	0.25	0.050	0	GI	100	1.0	
38	Comparative example 16	-	0	3.0	0.20	0.75	60	0.40	0	0.050	0	GI	100	1.0	
39	Comparative example 17	-	0	3.4	0.20	0.75	60	0.40	0	0.050	0	GI	100	1.0	
40	Invention example 23	-	0	4.0	0.20	0.75	60	0.40	0	0.050	0	GI	100	1.0	
41	Invention example 24	-	0	5.0	0.20	0.75	60	0.40	0	0.050	0	GI	100	1.0	
42	Comparative example 18	-	0	5.5	0.20	0.75	60	0.40	0	0.050	0	GI	100	1.0	
43	Comparative example 19	-	0	6.0	0.20	0.75	60	0.40	0	0.050	0	GI	-	-	Invention examples according to Claims 1 and 2
44	Invention example 1A	-	0	4.5	0.20	0.75	60	0.40	0	0.050	0	GI	100	0.1	
45	Invention example 25	-	0	4.5	0.20	0.75	60	0.40	0	0.050	0	GI	100	0.3	
46	Invention example 26	-	0	4.5	0.20	0.75	60	0.40	0	0.050	0	GI	100	0.5	
47	Invention example 27	-	0	4.5	0.20	0.75	60	0.40	0	0.050	0	GI	100	1.3	
48	Invention example 28	-	0	4.5	0.20	0.75	60	0.40	0	0.050	0	GI	100	1.5	
49	Invention example 2A	-	0	4.5	0.20	0.75	60	0.40	0	0.050	0	GI	100	2.0	Invention examples according to Claims 1 and 2
50	Invention example 1B	-	0	4.5	0.20	0.75	60	0.40	0	0.050	0	GI	40	1.0	Invention examples according to Claims 1 and 2
51	Invention example 29	-	0	4.5	0.20	0.75	60	0.40	0	0.050	0	GI	60	1.0	
52	Invention example 30	-	0	4.5	0.20	0.75	60	0.40	0	0.050	0	GI	140	1.0	
53	Invention example 2B	-	0	4.5	0.20	0.75	60	0.40	0	0.050	0	GI	220	1.0	Invention examples according to Claims 1 and 2
54	Invention example 31	-	0	4.5	0.20	0.75	60	0.40	0	0.050	0	GI	100	1.0	

(※) X1=(b)/(a+b+c), X2=(c)/(a+b+c), X3=(c)/Ti, X4=V/Ti, X5=(w)/(a+b)

[Table 8-6]

No.		Acid component 2		pH	(X1)	(X2)	(X3)	(X4)	(X5)	PO ₄ / (a+b+c)	F / (a+b+c)	Coated steel sheet	Drying temperature °C	Coating weight g/m ²	Remarks
		Type	parts by mass												
55	Comparative example 20	-	0	4.5	0.20	0.75	60	0.40	0	0.050	0	GI	-	-	
56	Comparative example 21	-	0	4.5	0.20	0.75	60	0.40	0	0.050	0	GI	100	1.0	
57	Comparative example 22	-	0	4.5	0.20	0.75	60	0.40	0	0.050	0	GI	100	1.0	
58	Comparative example 23	-	0	4.5	0.20	0.75	60	0.40	0	0.050	0	GI	-	-	
59	Comparative example 24	-	0	4.5	0.20	0.75	60	0.40	0	0.050	0	GI	-	-	
60	Comparative example 25	-	0	4.5	0.20	0.75	60	0.40	0	0.050	0	GI	100	1.0	
61	Comparative example 26	-	0	4.5	0.20	0.75	60	0.40	0	0.050	0	GI	100	1.0	
62	Comparative example 27	-	0	4.5	0.20	0.75	60	0.40	0	0.050	0	GI	-	-	
63	Invention example 32	-	0	4.5	0.20	0.75	60	0.40	0	0.050	0	GI	100	1.0	
64	Invention example 33	-	0	4.5	0.20	0.75	60	0.40	0	0.050	0	GI	100	1.0	
65	Invention example 34	-	0	4.5	0.20	0.75	60	0.40	0	0.050	0	GI	100	1.0	
66	Invention example 35	-	0	4.5	0.20	0.75	60	0.40	0	0.050	0	GI	100	1.0	
67	Comparative example 28	-	0	4.5	0.20	0.75	60	0.40	0	0.050	0	GI	-	-	
68	Comparative example 29	-	0	4.5	0.20	0.75	60	0.40	0	0.050	0	GI	100	1.0	
69	Comparative example 30	-	0	4.5	0.20	0.75	60	0.40	0	0.050	0	GI	100	1.0	
70	Comparative example 31	-	0	4.5	0.20	0.75	60	0.40	0	0.050	0	GI	-	-	
71	Comparative example 32	-	0	4.5	0.20	0.75	60	0.40	0	0.050	0	GI	-	-	
72	Comparative example 33	-	0	4.5	0.20	0.75	60	0.40	0	0.050	0	GI	100	1.0	
73	Comparative example 34	-	0	4.5	0.20	0.75	60	0.40	0	0.050	0	GI	100	1.0	
74	Comparative example 35	-	0	4.5	0.20	0.75	60	0.40	0	0.050	0	GI	-	-	
75	Invention example 36	-	0	4.5	0.20	0.75	60	0.40	0	0.050	0	GI	100	1.0	
76	Invention example 37	-	0	4.5	0.20	0.75	60	0.40	0	0.050	0	GI	100	1.0	
77	Comparative example 36	-	0	4.5	0.20	0.75	60	0.40	0	0.050	0	GI	-	-	
78	Comparative example 37	-	0	4.5	0.20	0.75	60	0.40	0	0.050	0	GI	-	-	
79	Invention example 38	-	0	4.5	0.20	0.75	60	0.40	0	0.050	0	GI	100	1.0	
80	Comparative example 38	-	0	4.5	0.20	0.75	60	0.40	0	0.050	0	GI	100	1.0	
81	Invention example 39	-	0	4.5	0.20	0.75	60	0.40	0	0.050	0	GI	100	1.0	

(※) X1=(b)/(a+b+c), X2=(c)/(a+b+c), X3=(c)/Ti, X4=V/Ti, X5=(w)/(a+b)

[Table 8-7]

No.	Corrosion resistance			Thermal discoloration resistance (4)	Paintability		Solvent resistance (7)	(8)	Storage stability			Lubricity (9)
	(1) Flat portion	(2) Bent portion	(3) After degreasing		(5) Without degreasing	(6) After degreasing			Corrosion resistance			
									Appearance	Flat portion	Bent portion	
1	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Poor
2	Excellent	Very Good	Excellent	Good	Excellent	Excellent	Excellent	Excellent	Excellent	Very Good	Very Good	Very poor
3	Excellent	Fair	Excellent	Good	Excellent	Excellent	Excellent	Excellent	Excellent	Fair	Fair	Very poor
4	Excellent	Very poor	Excellent	Poor	Excellent	Excellent	Excellent	Excellent	Excellent	Good	Very poor	Very poor
5	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Very Good	Excellent	Excellent	Excellent	Excellent	Poor
6	Excellent	Excellent	Excellent	Excellent	Excellent	Very Good	Good	Excellent	Excellent	Excellent	Fair	Poor
7	Excellent	Excellent	Fair	Excellent	Excellent	Fair	Fair	Excellent	Excellent	Excellent	Good	Poor
8	Excellent	Excellent	Poor	Excellent	Excellent	Poor	Very poor	Excellent	Excellent	Very Good	Very poor	Poor
9	Excellent	Very poor	Very poor	Excellent	Good	Very poor	Very Good	Excellent	Excellent	Excellent	Very poor	Poor
10	Excellent	Very poor	Fair	Excellent	Excellent	Poor	Excellent	Excellent	Excellent	Excellent	Very poor	Poor
11	Good	Very poor	Very poor	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Good	Very poor	Poor
12	Excellent	Poor	Very poor	Excellent	Excellent	Very poor	Excellent	Excellent	Fair	Good	Very poor	Poor
13	Excellent	Very poor	Good	Excellent	Excellent	Good	Excellent	Excellent	Excellent	Poor	Very poor	Very poor
14	Excellent	Very poor	Good	Excellent	Excellent	Very Good	Excellent	Excellent	Excellent	Fair	Poor	Very poor
15	Excellent	Very poor	Poor	Fair	Excellent	Fair	Very poor	Excellent	Excellent	Fair	Very poor	Very poor
16	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Very poor	Poor
17	Excellent	Good	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Poor
18	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Poor
19	Excellent	Good	Good	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Good	Good	Poor
20	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Poor
21	Excellent	Good	Good	Fair	Very Good	Poor	Very poor	Excellent	Excellent	Fair	Fair	Poor
22	Excellent	Very Good	Very Good	Good	Excellent	Excellent	Excellent	Excellent	Excellent	Good	Good	Poor
23	Excellent	Very Good	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Fair	Fair	Very poor
24	Excellent	Very poor	Good	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Very poor	Very poor	Very poor
25	Poor	Poor	Very poor	Excellent	Very Good	Very poor	Very Good	Excellent	Excellent	Poor	Very poor	Poor
26	Good	Fair	Fair	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Good	Fair	Poor
27	Excellent	Fair	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Fair	Poor

[Table 8-8]

[Table 8-8]												
No.		Corrosion resistance			Thermal discoloration resistance (4)	Paintability		Solvent resistance (7)	Storage stability			Lubricity (9)
		(1)	(2)	(3)		(5)	(6)		(8)	Corrosion resistance		
										Flat portion	Bent portion	
28	Comparative example 13	Excellent	Very poor	Excellent	Excellent	Excellent	Excellent	Excellent	Fair	Good	Very poor	Poor
29	Comparative example 14	Very poor	Very poor	Very poor	Excellent	Excellent	Good	Good	Excellent	Very poor	Very poor	Poor
30	Invention example 16	Good	Fair	Fair	Excellent	Excellent	Excellent	Excellent	Excellent	Good	Fair	Poor
31	Invention example 17	Very Good	Fair	Fair	Excellent	Excellent	Good	Excellent	Excellent	Good	Fair	Poor
32	Comparative example 15	Excellent	Fair	Very poor	Excellent	Very poor	Good	Good	Excellent	Good	Very poor	Poor
33	Invention example 18	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent
34	Invention example 19	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent
35	Invention example 20	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Poor
36	Invention example 21	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent
37	Invention example 22	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Good
38	Comparative example 16	Poor	Very poor	Very poor	Excellent	Poor	Poor	Excellent	Excellent	Very poor	Very poor	Poor
39	Comparative example 17	Good	Poor	Poor	Excellent	Good	Good	Excellent	Excellent	Poor	Very poor	Poor
40	Invention example 23	Very Good	Very Good	Very Good	Excellent	Excellent	Excellent	Excellent	Excellent	Very Good	Good	Poor
41	Invention example 24	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Poor
42	Comparative example 18	Poor	Poor	Poor	Excellent	Good	Good	Excellent	Excellent	Poor	Poor	Poor
43	Comparative example 19	The test was terminated because the treatment solution gelled.										
44	Invention example 1A	Very poor	Very poor	Very poor	Excellent	Fair	Excellent	Excellent	Excellent	Very poor	Very poor	Poor
45	Invention example 25	Good	Fair	Fair	Excellent	Excellent	Excellent	Excellent	Excellent	Good	Fair	Poor
46	Invention example 26	Very Good	Fair	Fair	Excellent	Excellent	Excellent	Excellent	Excellent	Very Good	Fair	Poor
47	Invention example 27	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Very Good	Excellent	Excellent	Excellent	Poor
48	Invention example 28	Excellent	Excellent	Excellent	Good	Good	Good	Good	Excellent	Excellent	Excellent	Poor
49	Invention example 2A	Excellent	Good	Excellent	Good	Very poor	Poor	Poor	Excellent	Excellent	Excellent	Poor
50	Invention example 1B	Good	Good	Very poor	Excellent	Good	Poor	Poor	Good	Good	Very poor	Poor
51	Invention example 29	Very Good	Very Good	Very Good	Excellent	Good	Good	Good	Excellent	Very Good	Very Good	Poor
52	Invention example 30	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Poor
53	Invention example 2B	Excellent	Poor	Excellent	Poor	Poor	Excellent	Excellent	Excellent	Poor	Excellent	Poor
54	Invention example 31	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Good	Excellent	Poor

[0076]

As described in Table 8, all the test sheets produced with surface-treatment agents according to the present invention are excellent in terms of corrosion resistance (flat portion, processed portion, and after alkaline degreasing), thermal discoloration resistance, paintability (without degreasing and after degreasing), and solvent resistance. The surface-treatment agents according to the present invention after storage maintains excellent quality similar to that before storage.

[0077]

In contrast, in Comparative example 1 (No. 4) that does not satisfy the requirements of the present invention, since the content of the cationic urethane (B) was less than the lower limit of the range according to the present invention, sufficient corrosion resistance in a bent portion was not provided at all and corrosion resistance was degraded after storage. In Comparative example 2 (No. 8), since the content of the cationic urethane (B) was more than the upper limit of the range according to the present invention, the quality after alkaline degreasing was poor and sufficient solvent resistance was not provided. In Comparative example 3 (No. 9) and Comparative example 4 (No. 10), since organic titanium chelate compounds (D) according to the present invention were not added,

sufficient quality in terms of bent portions and after alkaline degreasing were not achieved.

[0078]

In Comparative example 5 (No. 11), Comparative example
5 7 (No. 13), and Comparative example 8 (No. 14) in which
tetravalent vanadyl compounds (E) were not added, sufficient
corrosion resistance in bent portions was also not achieved
and the quality after storage was degraded. In Comparative
example 6 (No. 12), since a pentavalent vanadyl compound was
10 used, sufficient corrosion resistance in a bent portion and
sufficient corrosion resistance after alkaline degreasing
were not achieved, and paintability after alkaline
degreasing was degraded. In Comparative example 9 (No. 15),
although the tetravalent vanadyl compound (E) was used, the
15 composition was not appropriate and hence a bent portion and
solvent resistance were not achieved and corrosion
resistance after storage was degraded. Note that
Comparative example 7 (No. 13) was tested with reference to
Japanese Patent No. 3883831; and Comparative example 9 (No.
20 15) was tested with reference to Japanese Unexamined Patent
Application Publication No. 2006-152436.

[0079]

In Comparative example 10 (No. 21), since the content
of the silane coupling agent (C) was less than the lower
25 limit of the range according to the present invention,

solvent resistance was poor; whereas, in Comparative example 11 (No. 24), since the content was more than the upper limit of the range according to the present invention, sufficient corrosion resistance in a bent portion was not provided and the solution after storage did not provide corrosion resistance. In Comparative example 12 (No. 25), since the content of the silane coupling agent (C) relative to titanium of the organic titanium chelate compound (D) was more than the upper limit of the range according to the present invention, corrosion resistance and paintability after alkaline degreasing were poor; whereas, in Comparative example 13 (No. 28), since the content was less than the lower limit of the range according to the present invention, sufficient corrosion resistance in a bent portion was not provided and the solution after storage did not provide sufficient corrosion resistance.

[0080]

In Comparative example 14 (No. 29), since the vanadium content of the tetravalent vanadyl compound (E) relative to titanium of the organic titanium chelate compound (D) was less than the lower limit of the range according to the present invention, sufficient corrosion resistance was not provided; whereas, in Comparative example 15 (No. 32), since the content was more than the upper limit of the range according to the present invention, corrosion resistance and

paintability after alkaline degreasing were poor. In Comparative examples 16 (No. 38), 17 (No. 39), 18 (No. 42), and 19 (No. 43) in which pH was not adjusted to be in the proper range, sufficient corrosion resistance was not achieved and storage stability was poor. In Comparative example 19 (No. 43) in which the pH was high, the agent gelated and the test was not performed.

[0081]

As for the resin compound (A), in Comparative examples 20 (No. 55), 24 (No. 59), 28 (No. 67), and 32 (No. 71), the average substitution number of the Z group was less than the lower limit of the range according to the present invention and hence unsolved matter was generated in the preparation of the surface-treatment agents; and, in Comparative examples 23 (No. 58), 27 (No. 62), 31 (No. 70), and 35 (No. 74), the number of carbon atoms of alkyl groups of the Z group was more than the upper limit of the range according to the present invention and hence unsolved matter was generated in the preparation of the surface-treatment agents. In Comparative examples 21 (No. 56), 25 (No. 60), 29 (No. 68), and 33 (No. 72), the average substitution number of the Z group was more than the upper limit of the range according to the present invention and hence the surface-treatment agents after storage did not maintain quality similar to that before storage. In Comparative examples 22 (No. 57),

26 (No. 61), 30 (No. 69), and 34 (No. 73), the average degree of polymerization of the Z group was more than the upper limit of the range according to the present invention and hence the surface-treatment agents after storage gelated.

5 [0082]

In Comparative example 36 (No. 77), since the urethane resin was the nonionic resin, the urethane resin aggregated in the preparation of the surface-treatment agent. In Comparative example 37 (No. 78), since the urethane resin
10 was the anionic resin, the urethane resin aggregated in the preparation of the surface-treatment agent. In Comparative example 38 (No. 80), the silane coupling agent did not satisfy the requirement of the present invention and hence sufficient corrosion resistance was not provided.

15 [0083]

Even when a surface-treatment agent according to the present invention is used, unless the appropriate coating weight and drying condition are satisfied, desired advantages are not provided. In Invention examples 1A (No.
20 44), 2A (No. 49), 1B (No. 50), and 2B (No. 53), surface-treatment agents according to Claims 1 and 2 of the present invention were used and were excellent in terms of thermal discoloration resistance and storage stability (appearance). However, in Invention example 1A (No. 44), since the coating
25 weight of the film was less than the lower limit of the

range according to Claim 3 of the present invention,
sufficient corrosion resistance was not provided. In
Invention example 2A (No. 49), since the coating weight of
the film was more than the upper limit of the range
5 according to Claim 3 of the present invention, paintability
was poor. In Invention example 1B (No. 50), since the
drying temperature was less than the lower limit of the
range according to Claim 3 of the present invention,
sufficient corrosion resistance was not provided. In
10 Invention example 2B (No. 53), since the drying temperature
was more than the upper limit of the range according to
Claim 3 of the present invention, corrosion resistance in a
bent portion and paintability were poor.

15 [Industrial Applicability]
[0084]

According to the present invention, surface-treated
coated steel sheets that are excellent in terms of corrosion
resistance (in particular, in bent portions), heat
20 resistance, paintability, and solvent resistance can be
provided with a treatment agent without using a chromate
treatment. In addition, such a treatment agent that has
excellent quality even after storage in the state of a one-
component agent also provides advantages of cost reduction
25 and waste reduction.

CLAIMS

[Claim 1]

A surface-treatment agent comprising:

(A) a resin compound (hereafter, referred to as "resin
5 compound (A)") having a bisphenol skeleton represented by a
general formula (I) below; (B) a cationic urethane resin
emulsion (hereafter, referred to as "cationic urethane (B)")
having at least one cationic functional group selected from
primary to tertiary amino groups and a quaternary ammonium
10 salt group;

(C) at least one silane coupling agent having at least one
reactive functional group selected from an active-hydrogen-
containing amino group, an epoxy group, a mercapto group,
and a methacryloxy group; (D) an organic titanium chelate
15 compound;

(E) a tetravalent vanadyl compound; and

(F) water,

wherein, a mass ratio $[(b)/\{(a) + (b) + (c)\}]$ of a
solid content of the cationic urethane (B) to a total of
20 solid contents of the resin compound (A), the cationic
urethane (B), and the silane coupling agent (C) is 0.1 to
0.3,

a mass ratio $[(c)/\{(a) + (b) + (c)\}]$ of the solid
content of the silane coupling agent (C) to the total of the
25 solid contents of the resin compound (A), the cationic


urethane (B), and the silane coupling agent (C) is 0.6 to 0.85,

a mass ratio $\{(c)/Ti\}$ of the solid content of the silane coupling agent (C) to a content of the organic
5 titanium chelate compound (D) in terms of titanium is 50 to 70,

a mass ratio (V/Ti) of a content of the tetravalent vanadyl compound (E) in terms of vanadium to the content of the organic titanium chelate compound (D) in terms of
10 titanium is 0.3 to 0.5,


the surface-treatment agent has a pH of 4 to 5,

in the formulae, (a) represents the solid content of the resin compound (A), (b) represents the solid content of the cationic urethane (B), (c) represents the solid content
15 of the silane coupling agent (C), Ti represents the content of the organic titanium chelate compound (D) in terms of titanium, and V represents the content of the tetravalent vanadyl compound (E) in terms of vanadium,
[Chemical formula 1]




where Y_1 and Y_2 bonded to benzene rings each independently represent hydrogen or a Z group represented by a general formula (II) or (III) below; an average substitution number of the Z group per benzene ring is 0.2 to 1.0; n represents an integer of 2 to 50, and

[Chemical formula 2]



[Chemical formula 3]



in the formulae (II) and (III), R₁, R₂, R₃, R₄, and R₅ each independently represent a hydrogen atom, an alkyl group having 1 to 10 carbon atoms, or a hydroxyalkyl group having 1 to 10 carbon atoms; and A⁻ represents a hydroxide ion or an acid ion.

[Claim 2]

The surface-treatment agent according to Claim 1, further comprising:

(W) a wax,

wherein a mass ratio [(w)/{(a) + (b)}] of a solid content of the wax (W) to a total of the solid contents of the resin compound (A) and the cationic urethane (B) is 0.2 to 0.4, and

in the formula, w represents the solid content of the wax (W), (a) represents the solid content of the resin compound (A), and (b) represents the solid content of the cationic urethane (B).

[Claim 3]

A method for producing a coated steel sheet, comprising applying the surface-treatment agent according to Claim 1 or 2 to a coated steel sheet, and drying the surface-treatment

agent at a sheet temperature of 50°C to 180°C to form a surface-treatment film having a coating weight of 0.2 to 1.8 g/m² on a surface of the steel sheet.

[Claim 4]

- 5 A coated steel sheet produced by the method for producing a coated steel sheet according to Claim 3.