

Description

This invention relates to compositions which are useful in medium voltage electrical insulation because of their resistance to heat and water trees.

Ethylene/propylene copolymers and terpolymers (EPRs) are currently being used for insulating medium voltage cables. These polymers are generally crosslinked using peroxides and are utilized in combination with various additives and fillers. As insulation for cables, the EPRs require a filler for reinforcement because of their lack of strength. A filler is also required for processing, e.g., in an extruder, since unfilled EPRs do not extrude smoothly.

It is desirable to add polyethylene glycol, a well known water tree growth inhibitor, to medium voltage insulation. Water trees occur when an organic polymeric insulation material is subjected to an electrical field over a long period of time in the presence of water in liquid or vapor form. They are called trees because they appear to have a trunk with branches. Water trees grow from points in the insulation where there are voids or contaminants such as metal, lint, or other foreign material. Since it is difficult to eliminate voids or extraneous matter from the insulation, water tree growth inhibitors have been developed. The aforementioned polyethylene glycol is one that is found to be superior in its inhibiting qualities. Unfortunately, polyethylene glycol is found to degrade EPRs when crosslinked specimens are exposed to accelerated heat aging tests at elevated temperatures.

US-A-4 305 849 relates to a composition for electrical insulation which comprises an optionally crosslinked polyolefin (e.g. homo- and copolymers of ethylene and propylene, polybutene, polyisobutylene and poly-4-methylpentene) and a small amount of polyethylene glycol of high molecular weight. In the examples polyethylene having a density of 0.92 g/cm³ is employed as polyolefin.

An object of this invention is to provide a heat and water tree resistant composition adapted for use in medium voltage electrical insulation, which has sufficient strength so as not to require fillers, will not be degraded by polyethylene glycol, and is otherwise equivalent in physical properties to the EPRs.

Other objects and advantages will become apparent hereinafter.

According to the present invention, the above object is met by a heat and water tree resistant composition comprising:

- (a) a copolymer of ethylene, at least one alpha-olefin having 4 to 8 carbon atoms and 0 to 15% by weight, based on the copolymer, of propylene, said copolymer having a density equal to or less than 0.89 gram per cubic centimeter; and
- (b) a polyethylene glycol having a molecular weight in the range of about 1000 to about 20,000 in an amount of about 0.1 to about 20 percent by weight based on the weight of the copolymer.

The ethylene/alpha olefin copolymer can be prepared by the process described in EP-A-120 501. The density of the copolymer is equal to or less than 0.89 gram per cubic centimeter and is preferably in the range of about 0.85 to 0.89 gram per cubic centimeter. The portion of the copolymer attributed to the alpha-olefin having 4 to 8 carbon atoms preferably is in the range of about 5 to about 50 percent by weight based on the weight of the copolymer and more preferably is in the range of about 15 to about 40 percent by weight. The balance of the copolymer is based on ethylene (and optionally propylene). Within the noted density range, the higher densities represent increased strength and are relatively less rubbery. These copolymers are considered to be soft polymers because they are semi-crystalline. They can also be described as rubber-like. Soft polymers can be processed on or in cool processing equipment, i.e., the copolymer mixes readily without the use of heat.

Examples of alpha-olefins having 4 to 8 carbon atoms are 1-butene, 1-hexene, and 1-octene. The copolymer can also be subjected to grafting, or the comonomers can be copolymerized, with a vinyl alkoxy silane to make them hydrolyzable.

The polyethylene glycol is a known water tree inhibitor described, for example, in US-A-4,612,139. It can have a molecular weight in the range of about 1000 to about 20,000, and at least 30 carbon atoms, preferably at least 80 carbon atoms. The polyethylene glycol is present in the insulation composition in an amount of about 0.1 to about 20 parts by weight based on 100 parts by weight of the base ethylene/alpha-olefin copolymer and is preferably present in an amount in the range of about 0.1 to about 2 parts by weight.

The ethylene/alpha-olefin copolymer having a density equal to or less than 0.89 g/cm³ can be advantageously blended with (i) polyethylenes having densities in the range of 0.91 to 0.93 g/cm³ prepared by conventional high pressure techniques; (ii) ethylene copolymers wherein at least one comonomer is a vinyl acid, a vinyl acid ester, or a derivative of either; (iii) ethylene/hydrolyzable silane copolymers; (iv) ethylene terpolymers based on at least two comonomers referred to in items (ii) and (iii); (v) ethylene terpolymers based on alpha-olefins having 3 to 8 carbon atoms; (vi) ethylene/propylene rubbers; (vii)

ethylene/propylene/diene monomer rubbers; and (viii) hydrolyzable graft polymers produced by grafting silane to any of items (i) to (vii).

The high pressure technique referred to in (i) is described in Introduction to Polymer Chemistry, Stille, Wiley and Sons, New York, 1982, at pages 149 to 153. The ethylene/silane copolymer can be prepared by the process described in US-A-3,225,018 and the terpolymer by the process described in US-A-4,291,136.

The polymers which are blended with the base ethylene/alpha-olefin copolymer can be blended in a weight ratio of polymer to copolymer of about 1:9 to about 9:1 and preferably in a weight ratio of about 7:3 to about 3:7.

Various conventional additives can be added in conventional amounts to the insulation compositions. Typical additives are antioxidants, ultraviolet absorbers, antistatic agents, pigments, dyes, fillers including carbon black and aluminum silicate, slip agents, fire retardants, stabilizers, crosslinking agents, halogen scavengers, smoke inhibitors, crosslinking boosters, processing aids, lubricants, plasticizers, and viscosity control agents. Fillers can be included in amounts of about 5 to about 60 percent by weight based on the weight of the total composition.

One additive of special interest as a substitute for the commonly used red lead oxide as a scavenger for residual halogen is a metal carboxylate, which, on reaction with a halogen, yields a water insoluble product. Examples of suitable metal carboxylates are dioctyltin maleate, dibutyltin dilaurate, stannous acetate, and stannous octoate.

The invention is illustrated by the following examples.

Examples 1 to 12

Each insulation composition is blended as follows: the components are charged into a mixer such as a Brabender or Banbury mixer. The mixture is fluxed at about 150 °C to 170 °C for about 3 minutes at about 60 rpm. The batch is discharged at about 160 °C and is homogenized on a two-roll mill, and removed from the two-roll mill as a sheet. Standard test specimens or slabs (150 millimeters X 150 millimeter X 1.9 millimeters thick) are cured, vulcanized, or crosslinked in accordance with ASTM D-15-72 ("Compound and Sample Preparation for Physical Testing of Rubber Products"). Dumbbell shaped test specimens are cut from the slabs for stress-strain testing in accordance with ASTM D-412-6B ("Tension Testing of Vulcanized Rubber"). ASTM D-573-673 ("Accelerated Aging of Vulcanized Rubber") is used to test the heat resistance of crosslinked specimens. Crosslinking of the test slabs is carried out for 40 minutes at 170 °C. Accelerated heat aging is conducted for 1, 2, and 3 weeks at 150 °C. The percent tensile strength and elongation retained after these aging periods is used as a measure of the heat resistance of the compositions. The higher the retention of properties, the better the heat resistance.

The components are as follows:

1. ethylene/propylene/1,4 hexadiene terpolymer rubber (ethylene portion approx. 74 weight percent or 81 mole percent)
2. ethylene/propylene/1,4 hexadiene terpolymer rubber (ethylene portion approx. 56 weight percent or 66 mole percent)
3. ethylene/propylene/ethylidene norbornene (ethylene portion approx. 50 weight percent or 64 mole percent)
4. ethylene/propylene copolymer rubber (ethylene portion approx. 65 weight percent or 73 mole percent)
5. ethylene/1-butene copolymer (1-butene portion approx. 26 weight percent, density 0.88)
6. ethylene/1-butene copolymer (1-butene portion approx. 18 weight percent, density 0.89)
7. polyethylene (density 0.92)
8. silane treated clay (aluminum silicate)(filler)
9. zinc oxide (pH modifier)
10. paraffin (lubricant)
11. gamma-methacryloxypropyltrimethoxy silane (coupling agent)
12. zinc 2-mercaptotoluimidazole (anti-oxidant)
13. low temperature reaction product of diphenylamine and acetone (anti-oxidant)
14. dicumyl peroxide (curing agent)
15. organosilane ester (cure booster)
16. red lead masterbatch (90% by weight Pb_3O_4 , 10% by weight EPR)(Lead oxide is used to scavenge residual halogen) (EPR - see item 4 above)
17. dioctyltin maleate (this compound is used to scavenge residual halogen)

18. polyethylene glycol (molecular weight = 20,000) (water tree inhibitor)

The stress-strain tests applied to the samples are as follows:

1. 100% modulus (psi) - ASTM 412. (1 psi = 0.00689 MPa)
2. 300% modulus (psi) - ASTM 412.
3. tensile strength (psi) - ASTM 412.
4. % elongation - ASTM 412
5. Shore A Hardness - ASTM 412
6. % tensile retained
7. % elongation retained

Note: Examples 1, 2, and 3 contain polyethylene glycol together with dioctyl tin maleate, red lead oxide, or a combination of both) The properties of the compositions of these (comparative) examples are severely deteriorated after aging for two weeks at 150 °C. The composition of (comparative) example 4, which is devoid of polyethylene glycol, ages satisfactorily. The compositions of examples 5 and 6, which contain both polyethylene glycol and dioctyltin maleate, show excellent heat aging.

The following Tables set forth the variables and results. Each example represents one test specimen. Table I gives the component proportions in each specimen. Table II sets forth the results of tests performed on specimens after the specimens are cured for 40 minutes at 170 °C. Table III sets forth the results of tests performed on specimens after the specimens are aged in an oven for one week at 150 °C. Table IV sets forth the results of tests performed on specimens after the specimens are aged in an oven for two weeks at 150 °C. Table V sets forth the results of tests performed on specimens after the specimens are aged in an oven for three weeks at 150 °C.

Table I

Examples 1* 2* 3* 4* 5. 6. 7* 8* 9* 10* 11. 12

Component
Number

1	-	-	-	-	-	50	-	-	-	-	-	-
2	-	-	-	-	-	-	50	-	-	-	-	-
3	50	50	50	50	-	-	-	50	-	-	-	-
4	-	-	-	-	-	-	-	-	50	-	-	-
5	-	-	-	-	-	50	-	-	-	50	-	-
6	-	-	-	-	50	-	-	-	-	-	50	-
7	50	50	50	50	50	50	50	50	50	50	50	50
8	30	30	30	30	30	30	30	30	30	30	30	30
9	5	5	5	5	5	5	5	5	5	5	5	5
10	3	3	3	3	3	3	3	3	3	3	3	3
11	1	1	1	1	1	1	1	1	1	1	1	1
12	2	2	2	2	2	2	2	2	2	2	2	2
13	1	1	1	1	1	1	1	1	1	1	1	1
14	2.6	2.6	2.6	2.6	2.6	2.6	2.6	2.6	2.6	2.6	2.6	2.6
15	-	-	-	-	-	-	0.7	0.7	0.7	0.7	0.7	0.7
16	-	-	5	-	-	-	5	5	5	5	5	5
17	0.3	0.3	-	0.3	0.3	0.3	0.3	0.3	0.3	0.3	0.3	0.3
18	0.7	0.7	0.7	-	0.7	0.7	0.7	0.7	0.7	0.7	0.7	0.7

Table II

Test
Number

1	970	1010	1030	985	1480	1290	1140	905	985	1050	1540	1450
2	1710	1780	1830	1790	2030	1670	1890	1460	1750	1610	2010	1990
3	2260	2030	2030	2290	2600	2220	2210	1740	2030	2240	2590	2590
4	410	350	340	400	480	510	410	430	350	480	510	490
5	93	94	94	93	98	97	96	92	93	95	95	98

* = comparative example

Table III

Examples 1* 2* 3* 4* 5* 6* 7* 8* 9* 10* 11 12

Test
Number

1	1080	1150	1150	1070	1570	1450	1290	1030	-	1170	1450	1610
2	1990	-	-	1970	2260	1930	2230	1740	-	1850	1970	2310
3	2170	1800	1800	2250	2550	2280	2360	1980	900	1920	2340	2630
4	330	230	200	350	420	480	340	400	40	340	480	410
5	94	94	94	93	98	97	97	94	94	95	98	98
6	96	88	81	98	98	102	117	113	44	85	90	101
7	80	65	58	87	87	94	83	93	11	70	94	83

Table IV

Test
Number

1	-	-	-	1150	1560	1430	-	1020	-	-	1420	1590
2	-	-	-	2130	2260	1900	-	-	-	-	1940	2240
3	895	805	855	2130	2380	2210	1070	1370	575	1010	2220	2590
4	70	10	10	300	350	480	10	20	<10	10	440	420
5	94	95	96	94	98	98	98	94	98	98	97	100
6	39	39	42	93	91	99	48	78	28	45	86	100
7	17	2	2	75	72	94	2	46	0	2	86	85

Table V

Test
Number

1	-	-	-	-	-	-	-	-	-	-	1410	1590
2	-	-	-	-	-	-	-	-	-	-	1900	2310
3	-	-	-	-	-	-	330	330	125	295	2100	2480
4	-	-	-	-	-	-	<10	<10	<10	<10	420	365
5	-	-	-	-	-	-	100	94	97	97	98	97
6	-	-	-	-	-	-	15	18	6	13	81	95
7	-	-	-	-	-	-	0	0	0	0	82	74

* = comparative example

Claims

1. A heat and water tree resistant composition comprising:

- a copolymer of ethylene, at least one alpha-olefin having 4 to 8 carbon atoms and 0 to 15% by weight, based on the copolymer, of propylene, said copolymer having a density equal to or less than 0.89 gram per cubic centimeter; and
- a polyethylene glycol having a molecular weight in the range of about 1000 to about 20,000 in an amount of about 0.1 to about 20 percent by weight based on the weight of the copolymer.

Table III

Examples 1* 2* 3* 4* 5* 6* 7* 8* 9* 10* 11 12

Test
Number

1	1080	1150	1150	1070	1570	1450	1290	1030	-	1170	1450	1610
2	1990	-	-	1970	2260	1930	2230	1740	-	1850	1970	2310
3	2170	1800	1800	2250	2550	2280	2360	1980	900	1920	2340	2630
4	330	230	200	350	420	480	340	400	40	340	480	410
5	94	94	94	93	98	97	97	94	94	95	98	98
6	96	88	81	98	98	102	117	113	44	85	90	101
7	80	65	58	87	87	94	83	93	11	70	94	83

Table IV

Test
Number

1	-	-	-	1150	1560	1430	-	1020	-	-	1420	1590
2	-	-	-	2130	2260	1900	-	-	-	-	1940	2240
3	895	805	855	2130	2380	2210	1070	1370	575	1010	2220	2590
4	70	10	10	300	350	480	10	20	<10	10	440	420
5	94	95	96	94	98	98	98	94	98	98	97	100
6	39	39	42	93	91	99	48	78	28	45	86	100
7	17	2	2	75	72	94	2	46	0	2	86	85

Table V

Test
Number

1	-	-	-	-	-	-	-	-	-	-	1410	1590
2	-	-	-	-	-	-	-	-	-	-	1900	2310
3	-	-	-	-	-	-	330	330	125	295	2100	2480
4	-	-	-	-	-	-	<10	<10	<10	<10	420	365
5	-	-	-	-	-	-	100	94	97	97	98	97
6	-	-	-	-	-	-	15	18	6	13	81	95
7	-	-	-	-	-	-	0	0	0	0	82	74

* = comparative example

Claims

1. A heat and water tree resistant composition comprising:

- a copolymer of ethylene, at least one alpha-olefin having 4 to 8 carbon atoms and 0 to 15% by weight, based on the copolymer, of propylene, said copolymer having a density equal to or less than 0.89 gram per cubic centimeter; and
- a polyethylene glycol having a molecular weight in the range of about 1000 to about 20,000 in an amount of about 0.1 to about 20 percent by weight based on the weight of the copolymer.



2. The composition defined in claim 1, wherein the density of the copolymer is in the range of 0.85 to 0.89 gram per cubic centimeter.
3. The composition defined in one or both of the claims 1 to 2, wherein the portion of the copolymer attributed to the alpha-olefin having 4 to 8 carbon atoms is in the range of about 5 to about 50 percent by weight based on the weight of the copolymer.
4. The composition defined in one or more of the claims 1 to 3, additionally containing a polymer selected from the following classes (i) to (viii):
 - (i) polyethylene having a density in the range of 0.91 to 0.93 gram per cubic centimeter;
 - (ii) ethylene copolymers wherein at least one comonomer is a vinyl acid, a vinyl acid ester, or a derivative of either;
 - (iii) ethylene/hydrolyzable silane copolymers;
 - (iv) ethylene terpolymers based on at least two comonomers referred to in items (ii) and (iii);
 - (v) ethylene terpolymers based on alpha-olefins having 3 to 8 carbon atoms;
 - (vi) ethylene/propylene rubbers;
 - (vii) ethylene/propylene/diene monomer rubbers; and
 - (viii) hydrolyzable graft polymers produced by grafting silane to any of polymers (i) to (vii); the polymers (i) to (viii) being present in the composition in a weight ratio polymers (i) to (viii): copolymer (a) as defined in any one of claims 1 to 3 of about 1:9 to about 9:1.
5. The composition defined in one or more of the claims 1 to 4, additionally containing a metal carboxylate, which, on reaction with a halogen, yields a water insoluble product.
6. The composition of claim 5, wherein said metal carboxylate is dioctyltin maleate.
7. The composition defined in one or more of the claims 1 to 6, wherein the alpha-olefin is 1-butene.
8. The composition defined in one or more of the claims 1 to 7, wherein the copolymer (a) is silane modified to provide a hydrolyzable copolymer.
9. The composition defined in one or more of the claims 1 to 8, additionally including filler in an amount of about 5 to about 60 percent by weight, based on the total weight of the composition.
10. Use of the composition according to any one of claims 1 to 9 in medium voltage electrical insulation.

Patentansprüche

1. Wärme- und Wasserbäumchen-beständige Zusammensetzung, umfassend:
 - (a) ein Copolymer von Ethylen, mindestens einem alpha-Olefin mit 4 bis 8 Kohlenstoffatomen und 0 bis 15 Gewichts-%, bezogen auf das Copolymer, Propylen, wobei das Copolymer eine Dichte aufweist, die gleich oder kleiner als 0,89 Gramm pro Kubikzentimeter ist; und
 - (b) ein Polyethylenglycol mit einem Molekulargewicht im Bereich von etwa 1000 bis etwa 20000 in einer Menge von etwa 0,1 bis etwa 20 Gewichtsprozent bezogen auf das Gewicht des Copolymeren.
2. Zusammensetzung nach Anspruch 1, in welcher die Dichte des Copolymeren im Bereich von 0,85 bis 0,89 Gramm pro Kubikzentimeter liegt.
3. Zusammensetzung nach einem oder beiden der Ansprüche 1 bis 2, in welcher der Teil des Copolymeren, der auf das alpha-Olefin mit 4 bis 8 Kohlenstoffatomen zurückgeht, im Bereich von etwa 5 bis etwa 50 Gewichtsprozent, bezogen auf das Gewicht des Copolymeren, liegt.
4. Zusammensetzung nach einem oder mehreren der Ansprüche 1 bis 3, zusätzlich enthaltend ein Polymer, das ausgewählt ist aus den folgenden Klassen (i) bis (viii):
 - (i) Polyethylen mit einer Dichte im Bereich von 0,91 bis 0,93 Gramm pro Kubikzentimeter;
 - (ii) Ethylen-Copolymere, in denen mindestens ein Comonomer eine Vinylsäure, ein Vinylsäureester oder ein Derivat derselben ist;
 - (iii) Ethylen/hydrolysierbares Silan-Copolymere;



- (iv) Ethylen-Terpolymere auf der Basis von mindestens zwei Comonomeren, auf die in (ii) und (iii) Bezug genommen wurde;
 (v) Ethylen-Terpolymere auf der Basis von alpha-Olefinen mit 3 bis 8 Kohlenstoffatomen;
 (vi) Ethylen/Propylen-Kautschuke;
 (vii) Ethylen/Propylen/Dien-Monomer-Kautschuke; und
 (viii) hydrolysierbare Pfropf-Polymere, hergestellt durch Pfröpfen von Silan auf irgendeines der Polymeren (i) bis (vii);
 wobei die Polymeren (i) bis (viii) in der Zusammensetzung in einem Gewichtsverhältnis von Polymere (i) bis (viii):Copolymer (a) wie in irgendeinem der Ansprüche 1 bis 3 definiert von etwa 1:9 bis etwa 9:1 vorliegen.
5. Zusammensetzung nach einem oder mehreren der Ansprüche 1 bis 4, zusätzlich ein Metallcarboxylat enthaltend, das bei der Reaktion mit einem Halogen ein wasserunlösliches Produkt liefert.
6. Zusammensetzung nach Anspruch 5, in welchem das Metallcarboxylat Dioctylzinnmaleat ist.
7. Zusammensetzung nach einem oder mehreren der Ansprüche 1 bis 6, in welchem das alpha-Olefin 1-Buten ist.
8. Zusammensetzung nach einem oder mehreren der Ansprüche 1 bis 7, in welchem das Copolymer (a) Silan-modifiziert ist, um ein hydrolysierbares Copolymer zu liefern.
9. Zusammensetzung nach einem oder mehreren der Ansprüche 1 bis 8, zusätzlich Füllstoff in einer Menge von etwa 5 bis etwa 60 Gewichtsprozent, bezogen auf das Gesamtgewicht der Zusammensetzung, einschließend.
10. Verwendung der Zusammensetzung nach irgendeinem der Ansprüche 1 bis 9 für elektrische Isolierung im mittleren Spannungsbereich.

30 Revendications

1. Composition résistante à la chaleur et à la formation d'arborescences d'eau, comprenant :
 (a) un copolymère d'éthylène, d'au moins une alpha-oléfine ayant 4 à 8 atomes de carbone et de 0 à 15 % en poids, sur la base du copolymère, de propylène, ledit copolymère ayant une masse volumique égale ou inférieure à 0,89 gramme par centimètre cube ; et
 (b) un polyéthylèneglycol ayant un poids moléculaire compris dans l'intervalle d'environ 1000 à environ 20 000 en une quantité d'environ 0,1 à environ 20 % en poids, sur la base du poids du copolymère.
2. Composition répondant à la définition suivant la revendication 1, dans laquelle la masse volumique du copolymère est comprise dans l'intervalle de 0,85 à 0,89 gramme par centimètre cube.
3. Composition répondant à la définition suivant l'une des, ou les deux, revendications 1 et 2, dans laquelle la portion du copolymère attribuée à l'alpha-oléfine ayant 4 à 8 atomes de carbone est présente en une quantité comprise dans l'intervalle d'environ 5 à environ 50 % en poids, sur la base du poids du copolymère.
4. Composition répondant à la définition suivant une ou plusieurs des revendications 1 à 3, contenant en outre un polymère choisi parmi les catégories (i) à (viii) suivantes :
 (i) un polyéthylène ayant une masse volumique comprise dans l'intervalle de 0,91 à 0,93 gramme par centimètre cube ;
 (ii) des copolymères d'éthylène dans lesquels au moins un comonomère est un acide vinylique, un ester d'acide vinylique ou un de leurs dérivés ;
 (iii) des copolymères éthylène/silane hydrolysable ;
 (iv) des terpolymères d'éthylène à base d'au moins deux comonomères mentionnés dans les paragraphes (ii) et (iii) ;
 (v) des terpolymères d'éthylène à base d'alpha-oléfines ayant 3 à 8 atomes de carbone ;
 (vi) des caoutchoucs éthylène/propylène ;



(vii) des caoutchoucs éthylène/propylène/monomère diénique ; et

(viii) des polymères greffés hydrolysables produits par greffage d'un silane sur l'un quelconque des polymères (i) à (vii) ;

les polymères (i) à (viii) étant présents dans la composition en un rapport pondéral polymères (i) à (viii) : copolymère (a) tel que défini dans l'une quelconque des revendications 1 à 3 compris dans l'intervalle d'environ 1:9 à environ 9:1.

- 5 5. Composition répondant à la définition suivant une ou plusieurs des revendications 1 à 4, contenant en outre un carboxylate métallique qui, par réaction avec un halogène, donne un produit insoluble dans l'eau.
- 10 6. Composition suivant la revendication 5, dans laquelle le carboxylate métallique est le maléate de dioctylétain.
- 15 7. Composition répondant à la définition suivant une ou plusieurs des revendications 1 à 6, dans laquelle l'alpha-oléfine est le 1-butène.
- 20 8. Composition répondant à la définition suivant une ou plusieurs des revendications 1 à 7, dans laquelle le copolymère (a) est un silane modifié de manière à former un copolymère hydrolysable.
9. Composition répondant à la définition suivant une ou plusieurs des revendications 1 à 8, comprenant en outre une charge en une quantité d'environ 5 à environ 60 % en poids, sur la base du poids total de la composition.
- 25 10. Utilisation de la composition suivant l'une quelconque des revendications 1 à 9, dans une isolation électrique à moyenne tension.

30

35

40

45

50

55

