

WO 94/17081

REPLACED SHEETS		SG
☒	Description : paged ...1... to paged ...22...	
☒	Claim(s) : paged ...23... to paged ...24...	
☐	Drawing(s) : paged to paged	
☒	Abstract : paged ...1... to paged ...1...	
DATE OF RECEIPT		

PCT/US94/00319

**POTASSIUM PARA-DIPHENYL
PHOSPHINO BENZENE SULFONATE LIGAND**

5 The present invention relates generally to a novel
ligand that is useful for hydroformylation of higher α -
olefins in an aqueous emulsion. The ligand is a
potassium para-diphenyl phosphino benzene sulfonate
which is synthesized rapidly and in extremely high
10 yields.

BACKGROUND OF THE INVENTION

Hydroformylation reactions involve the preparation
15 of oxygenated organic compounds by the reaction of
carbon monoxide and hydrogen (i.e., synthesis gas) with
carbon compounds containing olefinic unsaturation. The
reaction is typically performed in the presence of a
carbonylation catalyst and results in the formation of
20 compounds, for example, aldehydes, which have one or
more carbon atoms in their molecular structure than the
starting olefinic feedstock. By way of example, higher
alcohols may be produced by hydroformylation of
commercial C₆-C₁₂ olefin fractions to an aldehyde-
25 containing oxonation product, which on hydrogenation
yields the corresponding C₇-C₁₃ saturated alcohols.
The crude product of the hydroformylation reaction will

SUBSTITUTE SHEET (RULE 26)

This Sheet Has Been Replaced



contain catalyst, aldehydes, alcohols, unreacted olefin feed, synthesis gas and by-products.

A variety of transition metals catalyze the hydroformylation reaction, but only cobalt and rhodium carbonyl complexes are used in commercial plants. The reaction is highly exothermic, i.e., the heat release is approximately ca 125 kJ/mol (30 kcal/mol). The position of the formyl group in the aldehyde product depends upon the olefin type, the catalyst, the solvent, and the reaction conditions. Reaction conditions have some effect and, with an unmodified cobalt catalyst, the yield of straight chain product from a linear olefin is favored by higher carbon monoxide partial pressure. In the hydroformylation of terminal olefinic hydrocarbons, the use of a catalyst containing selected complexing ligands, e.g., tertiary phosphines, results in the predominant formation of the normal isomer.

20

In commercial operation, the aldehyde product is typically used as an intermediate which is converted by hydrogenation to an alcohol or by aldolization and hydrogenation to a higher alcohol. The aldol-hydrogenation route is used primarily for the

25



manufacture of 2-ethylhexanol from propylene that is converted to n-butyraldehyde.

Much research in the past 25 years has been
5 directed to improving reaction selectivity to the linear product. Introduction of an organophosphine ligand to form a complex, e.g., $\text{Co}(\text{CO})_6[\text{P}(\text{n-C}_4\text{H}_9)_3]_2$, significantly improves the selectivity to the straight-chain alcohol.

10

Recent developments of low pressure rhodium catalyst systems have been the subject of a considerable body of patent art and literature, and rhodium-triphenyl phosphine systems have been widely,
15 and successfully, used commercially for the hydroformylation of propylene feedstocks to produce butyraldehyde.

Homogeneous catalysts formed from ligated metal
20 atoms can perform very selective chemistries with high turnover rates. For example, rhodium complexes containing phosphine ligands have ideal properties as catalysts in the hydroformylation process used in making long chain aldehydes because of their propensity
25 to form the linear rather than branched isomers. The linear aldehydes which can be formed with rhodium



catalyst complexes are needed for formulating biodegradable detergents, plasticizers, specialty polymers, etc. Homogeneous rhodium catalyst complexes have a unique role in this chemistry in that they can
5 take a linear terminal olefin and convert it into a predominantly linear aldehyde.

A typical homogeneous rhodium complex catalyst is formed with triphenylphosphine ligands in the presence
10 of carbon monoxide and hydrogen. The rhodium bonds to the triphenylphosphine ligand through a phosphorous atom. A large number of complexes are formed between rhodium, triphenylphosphine, hydrogen, and carbon
15 monoxide, because they form loosely bound molecular species which are involved in multiple equilibria as they dissociate and recombine with ligands in solution. One of the complexes can be a very active catalyst for the hydroformylation reaction which converts linear
20 olefins into the next higher carbon number linear aldehydes by the addition of carbon monoxide and hydrogen. In addition, the catalyst converts some of the product aldehyde to dimer and trimer condensation products. The isomerization activity of the catalyst
25 in extremely undesirable in applications designed to produce long chain linear aldehydes. Linear aldehydes containing between 12 to 15 carbon are readily



hydrogenated to linear alcohols which are premium products for formulating biodegradable liquid detergents.

5 Others have synthesized high molecular weight phosphine ligands for use as homogeneous catalysts. High molecular weight polymeric phosphine ligands are synthesized by reacting polyvinylchloride, polychloroprene or brominated polystyrene with lithium
10 diphenylphosphide at 20°C to 25°C. These homogeneous catalysts containing bulky ligands are thought to be more easily separated from the reaction products by ultrafiltration. See Imyanitov et al., All-Union Scientific Research Institute of Petrochemical
15 Processes, Neftekhimiya, 32, No. 3:200-7 (May-June 1992).

One conventional rhodium ligand used in the hydroformylation of higher α -olefins, such as 1-
20 dodecene in an aqueous emulsion catalytic process, is sodium p-diphenyl phosphino benzoate, i.e., $\text{Ph}_2\text{P}(\text{p-C}_6\text{H}_4\text{COO}_3\text{Na})$. As discussed in Great Britain Patent Application No. 2,085,874, filed on August 21, 1981, this rhodium ligand complex is active at low
25 temperature and pressure, and gives a high selectivity to the normal isomer.



Still others have synthesized a rhodium ligand complex using a $\text{Ph}_2\text{P}(\text{m-C}_6\text{H}_4\text{SO}_3\text{Na})$ ligand as shown in Ahrland et al., "The relative Affinities of Coordinating Atoms for Silver Ion. Part II.¹ Nitrogen, Phosphorus, and Arsenic.²:", Chemical Society, 1958, pp. 276-288. The $\text{Ph}_2\text{P}(\text{m-C}_6\text{H}_4\text{SO}_3\text{Na})$ ligand was synthesized by slowly adding 10 grams of triphenylphosphine, with cooling, to a mixture of 20% $\text{SO}_3\text{-H}_2\text{SO}_4$ (19 c.c.) and 65% $\text{SO}_3\text{-H}_2\text{SO}_4$ (1 c.c.). The phosphine dissolved and the solution was heated on a water bath. The solution was tested at intervals by adding one drop to water (2-3 c.c.) until a test drop gave a clear or only slightly cloudy aqueous solution (1-2 hours depending on the acid strength). The acid solution was cooled, poured cautiously into water (200 c.c.) and neutralized with saturated sodium hydroxide solution. The product separated as fine, white shining leaves.

As demonstrated in comparative Example 3, the sodium m-diphenyl phosphino benzene sulfonate (i.e., $\text{Ph}_2\text{P}(\text{m-C}_6\text{H}_4\text{SO}_3\text{Na})$) ligand which was synthesized by direct sulfonation of triphenyl phosphine resulted in very low rates of reaction in the hydroformylation of 1-decene and a low selectivity to the desired normal isomer compared to the corresponding para substituted carboxylic or sulfonic acid ligands.



Sodium p-diphenyl phosphino sulfonate, i.e., $\text{Ph}_2\text{P}(\text{p-C}_6\text{H}_4\text{SO}_3\text{Na})$, was first synthesized by H. Schindlbauer (see H. Schindlbauer, Monatsh Chem, 96 (6), 1965, pp. 2051) from potassium diphenyl phosphide and p-chloro sodium benzoate by boiling at 67°C in tetrahydrofuran (THF) for 24 hours. This article describes the formation of a by-product, p-diphenyl phosphino benzene, i.e., $\text{Ph}_2\text{P}(\text{p-C}_6\text{H}_4\text{PPh}_2)$, resulting from displacement of the sulfonic group by the diphenyl phosphino group, but gives no yield for the sulfonic salt, i.e., $\text{Ph}_2\text{P}(\text{p-C}_6\text{H}_4\text{SO}_3\text{Na})$, which was identified by elemental analysis for phosphorus and sulfur but could not be recrystallized due to poor solubility

The present inventors have discovered that by using a lithium salt of the p-chloro benzene sulfonic acid, i.e., $\text{Cl}(\text{p-C}_6\text{H}_4\text{SO}_3\text{Li})$ in a reaction with potassium diphenyl phosphide enables the isolation and purification of the product compound in high yield and purity. Since the lithium salt is more soluble than the corresponding sodium salt in THF, the reaction proceeds in 0.5 hours in boiling THF which is substantially faster than the formation of $\text{Ph}_2\text{P}(\text{p-C}_6\text{H}_4\text{SO}_3\text{Na})$ from $\text{Cl}(\text{p-C}_6\text{H}_4\text{SO}_3\text{Na})$. Moreover, the potassium salt ($\text{Ph}_2\text{P}(\text{p-C}_6\text{H}_4\text{SO}_3\text{K})$) of the ligand as a result of a lithium/potassium salt exchange is obtained



in an approximate yield of 50%. Also, the potassium salt of the ligand was found to be less soluble in organic solvents than the conventional sodium salts, such that it was able to be recrystallized from EtOH.

- 5 The potassium salt was identified by elemental analysis, IR and ^{31}P NMR.

Conventional hydroformylation reactions take place in an aqueous emulsion, such as that described in Great Britain Application No. 2,085,874, filed August 21, 10 1981, in which the aqueous phase consists of a 1N NaHCO_3 solution, thus generating an excess of sodium cations. Therefore, since the potassium ligand salt is soluble in water it is consequently exchanged "in situ" 15 to the sodium salt. As such, when the $\text{Ph}_2\text{P}(\text{p-C}_6\text{H}_4\text{SO}_3\text{K})$ ligand complexed catalyst is used to hydroformylate 1-decene it exhibits comparable rates of conversion to both $\text{Ph}_2\text{P}(\text{p-C}_6\text{H}_4\text{SO}_3\text{Na})$ and $\text{Ph}_2\text{P}(\text{p-C}_6\text{H}_4\text{COO}_3\text{Na})$ ligands, and substantially higher rates of conversion than 20 $\text{Ph}_2\text{P}(\text{m-C}_6\text{H}_4\text{SO}_3\text{Na})$.

The present invention also provides many additional advantages which shall become apparent as described below.

25

This Sheet Has Been Replaced



SUMMARY OF THE INVENTION

A method for producing a potassium para-diphenyl phosphino sulfonate ligand by reacting potassium diphenyl phosphide with a lithium salt of para-chloro benzenesulfonic acid in the presence of at least one compound selected from the group consisting of: tetrahydrofuran, 1,4-dioxane and 2-ethoxyethyl ether, at a temperature in the range between about 65 to about 100°C for between about 0.25 to 1 hours.

10


This group VIII noble metal-ligand complex catalyst is preferably used in hydroformylation of olefins in the presence of synthesis gas. The present invention also encompasses a method for producing higher aldehydes and higher alcohols by hydroformylating an olefinic feedstock with synthesis gas in the presence of this novel Group VIII noble metal-ligand complex catalyst which forms a crude reaction product of an olefin feed, a hydroformylation reaction product and the Group VIII noble metal-ligand complex catalyst.

Other and further objects, advantages and features of the present invention will be understood by reference to the following specification.



DESCRIPTION OF THE PREFERRED EMBODIMENTS

Hydroformylation is a process of converting olefins to a product of one or more additional carbon numbers by the addition of carbon monoxide and hydrogen to the double bond(s) of the olefin in the presence of a catalyst at elevated temperatures and pressures. A typical hydroformylation process is demonstrated below:



At a temperature of 100°C and a pressure of 12.75 kg (150 lbs.) the normal to iso ratio using rhodium as the catalyst may be below 1 or even as high as 100, depending on the ligand, ratio of ligand to rhodium, etc. Homogeneous rhodium-ligand complex catalysts are able to take a linear terminal olefin and convert it into a predominantly linear aldehyde.



20 A potassium para-diphenyl phosphino sulfonate ligand is formed by reacting potassium diphenyl phosphide with a lithium salt of para-chloro benzenesulfonic acid in the presence of at least one compound selected from the group consisting of:

25 tetrahydrofuran, 1,4-dioxane and 2-ethoxyethyl ether, at a temperature in the range between about 65 to about 100°C for between about 0.25 to 1 hours.



The potassium diphenyl phosphide is produced from the reaction product of diphenyl chlorophosphine and potassium in the presence of at least one compound selected from the group consisting of: tetrahydrofuran, 1,4-dioxane and 2-ethoxyethyl ether, at a temperature in the range between about 65 to about 100°C for between about 0.25 to 1 hours.

The potassium para-diphenyl phosphino sulfonate ligand ($\text{Ph}_2\text{P}(\text{p-C}_6\text{H}_4\text{SO}_3\text{K})$) according to the present invention is preferably synthesized from potassium diphenyl phosphide (Ph_2PK) and the lithium salt of p-chloro benzenesulfonic acid ($\text{Cl}(\text{p-C}_6\text{H}_4\text{SO}_3\text{Li})$) by boiling in tetrahydrofuran (THF) for approximately 0.5 hours as shown in the below equations:



Due to Li/K salt exchange, the yield of potassium p-diphenyl phosphino sulfonate during the synthesis process is approximately 50%. The potassium ligand salt is soluble in water. The hydroformylation takes place in an aqueous emulsion in which the aqueous phase



consists of a 1N NaHCO_3 solution, thus giving an excess of sodium cations. The potassium salt of the ligand is consequently exchanged "in situ" with the sodium salt. The aqueous phase contains sodium bicarbonate and a
5 surfactant such as lauric acid in addition to the ligand-sodium salt.

This Group VIII metal-ligand complex catalyst is particularly useful in producing higher aldehydes and
10 higher alcohols which comprises hydroformylating an olefinic feedstock with synthesis gas in the presence of the Group VIII noble metal-ligand complex catalyst to form a crude reaction product comprised of an olefin feed, a hydroformylation reaction product and the Group
15 VIII noble metal-ligand complex catalyst.

In the below examples, the organic phase solution contains the olefin, e.g., 1-decene, the Rh catalyst precursor, a co-solvent such as i-PrOH and, as an
20 internal standard for gas chromatographic (GC) analysis, a non-reactive compound such as hexadecane. The two solutions are introduced in an autoclave and pressurized to 10 psig at room temperature with a mixture of carbon monoxide to hydrogen of 1:1. The
25 autoclave is heated at 80°C while the pressure is maintained at 150 psig. The reaction is monitored by



periodic GC analysis of samples taken from the organic phase.

EXAMPLE 1

5 **(Synthesis of $\text{Ph}_2\text{P}(\text{p-C}_6\text{H}_4\text{SO}_3\text{K})$)**

28.30 grams of diphenyl chlorophosphine were added to 10 grams of a finely dispersed suspension of potassium, the suspension of potassium was obtained under vigorous stirring in 400 ml of THF at 67°C in a nitrogen atmosphere, dropwise at a sufficient rate to maintain constant reflux without external heating. As the reaction proceeded, the potassium disappeared and Ph_2PK appeared as an intense purple compound. After 15 the diphenyl chlorophosphine had been completely added to the suspension of potassium, the solution was cooled to 45-50°C. Thereafter, 25.47 grams of a well dried p-chloro lithium sulfonate was added to the Ph_2PK under a nitrogen blanket. This solution was then heated to 20 reflux with stirring. The change in color from purple to light brown, which took place within 0.5 hours, indicated the disappearance of the potassium diphenyl phosphide. The solution was cooled, while stirring, to room temperature, and 250cc of water was added. The 25 mixture was extracted times with 100cc of ether. The aqueous solution was concentrated on the rotary



evaporator at 50-60°C to approximately half the original volume. A white precipitate appeared. The solution was cooled, filtered, washed with cold ethanol and dried under nitrogen to give 25 grams of product and a yield of 49% of $\text{Ph}_2\text{P}(\text{p-C}_6\text{H}_4\text{SO}_3\text{K})$.

The compound analysis for $\text{Ph}_2\text{P}(\text{p-C}_6\text{H}_4\text{SO}_3\text{K})$ having a molecular weight of 380 calculated for C=56.84, H=3.69, P=8.16, O=12/63, K=10.26 and S=8.42% found:
C=56.68, H=3.93, P=7.51, K=10.36, S=8.01%. ^{31}P NMR detected one peak of -3.6396 ppm (with 85% H_3PO_4 ext. reference). The IR=1210-1050, CM^{-1} for SO_3^- , 827 CM^{-1} 1,4 disubst. benzene, 1479, 750, 697 CM^{-1} for $(\text{C}_6\text{H}_5)_2\text{P}$.

The lithium p-chloro benzene sulfonate was obtained from the corresponding acid by exchange with LiOH in aqueous ethanol, neutralization of the excess LiOH with carbon dioxide, and drying ASTM/Toluene followed by high vacuum.

20

EXAMPLE 2

(Sodium p-Diphenyl Phosphino Benzoate Ligand)

2 grams of lauric acid, as surfactant, were added to an aqueous solution of which consisted of sodium p-diphenyl phosphino benzoate ($\text{Ph}_2\text{P}(\text{p-C}_6\text{H}_4\text{COO}_3\text{Na})$),



15

dissolved at approximately 70°C with stirring under nitrogen in 70 grams of 1N NaHCO₃ solution. The resulting clear solution was then introduced through a Hoke bomb to a 1 liter autoclave. To this solution, a mixture which consisted of 179.23 grams of 1-decene, 9.93 grams of hexadecane as an internal standard, 1.24E-01 grams of rhodium acetate dimer (i.e., RhII₂(OOCCH₃)₄ dimer) and 10 grams of i-PrOH as co-solvent were introduced through the Hoke bomb under a carbon monoxide/hydrogen pressure.

The autoclave was pressurized with a mixture of CO/H₂ in a ratio of 1:1 and at a pressure of 100 psig at room temperature. The contents were then heated to 80°C while the pressure was maintained at 150 psig. The reaction was monitored by periodic GC analysis of the organic layer. The data is set forth below in Table 1.

20

25

This Sheet Has Been Replaced



Table 1

5	Run No.	Ligand Type	Mole%				Ratio
			Time	Conversion	Selectivity		
			Hour	of 1-Decene	to Aldehyde	N/I	TON
	1	Ph ₂ P(p-C ₆ H ₄ SO ₃ Na)	0.50	5.26	76.00	15.87	239
	2	Ph ₂ P(p-C ₆ H ₄ SO ₃ Na)	1.00	13.59	86.56	15.94	345
	3	Ph ₂ P(p-C ₆ H ₄ SO ₃ Na)	2.00	21.50	88.83	15.69	172
	4	Ph ₂ P(p-C ₆ H ₄ SO ₃ Na)	3.00	31.47	91.24	15.14	213
10	5	Ph ₂ P(p-C ₆ H ₄ SO ₃ Na)	4.00	42.25	91.42	14.95	243

TON = Moles Conv. (Sel to Ald./100)/g.at. Rh Hr.

EXAMPLE 3

(Sodium m-Diphenyl Phosphino Benzene Sulfonate Ligand)

15

2 grams of lauric acid, as surfactant, were added to an aqueous solution of which consisted of sodium m-diphenyl phosphino benzene sulfonate (Ph₂P(m-C₆H₄SO₃Na)), dissolved at approximately 70°C with stirring under nitrogen in 70 grams of 1N NaHCO₃ solution. The resulting clear solution was then introduced through a Hoke bomb to a 1 liter autoclave. To this solution, a mixture which consisted of 181.56 grams of 1-decene, 12.20 grams of hexadecane as an internal standard, 1.22E-01 grams of RhII₂(OOCCH₃)₄ dimer and 1.0 grams of i-PrOH as co-solvent were introduced through the Hoke bomb under a carbon monoxide/hydrogen pressure.

20

25

This Sheet Has Been Replaced



The autoclave was pressurized with a mixture of CO/H₂ in a ratio of 1:1 and at a pressure of 100 psig at room temperature. The contents were then heated to 80°C while the pressure was maintained at 150 psig.

- 5 The reaction was monitored by periodic GC analysis of the organic layer. The data is set forth below in Table 2.

Table 2

10

Run No.	Ligand Type	Mole%		Selectivity to Aldehyde	Ratio N/I	Ratio TON
		Time Hour	Conversion of 1-Decene			
1	Ph ₂ P(m-C ₆ H ₄ SO ₃ Na)	0.50	0.55	34.18	13.35	25
15 2	Ph ₂ P(m-C ₆ H ₄ SO ₃ Na)	1.00	0.57	33.12	9.85	13
3	Ph ₂ P(m-C ₆ H ₄ SO ₃ Na)	2.00	0.78	41.04	6.82	9
4	Ph ₂ P(m-C ₆ H ₄ SO ₃ Na)	18.00	3.27	83.25	6.39	4

EXAMPLE 4

- 20 (Potassium p-Diphenyl Phosphino Benzene Sulfonate
Ligand)

2 grams of lauric acid, as surfactant, were added to an aqueous solution of which consisted of sodium p-
25 diphenyl phosphino benzene sulfonate (Ph₂P(p-C₆H₄SO₃K)), dissolved at approximately 70°C with stirring under nitrogen in 70.84 grams of 1N NaHCO₃ solution. The resulting clear solution was then



introduced through a Hoke bomb to a 1 liter autoclave. To this solution, a mixture which consisted of 180.13 grams of 1-decene, 10.34 grams of hexadecane as an internal standard, 1.44E-01 grams of rhodium carbonyl
5 acetyl acetonate ($\text{RhI}(\text{CO})_2(\text{C}_5\text{H}_7\text{O}_2)$) and 15 grams of i-
PrOH as co-solvent were introduced through the Hoke bomb under a carbon monoxide/hydrogen pressure.

The autoclave was pressurized with a mixture of
10 CO/H_2 in a ratio of 1:1 and at a pressure of 100 psig at room temperature. The contents were then heated to 80°C while the pressure was maintained at 150 psig. The reaction was monitored by periodic GC analysis of the organic layer. The data is set forth below in
15 Table 3.

Table 3

Run No.	Ligand Type	Mole%				
		Time Hour	Conversion of 1-Decene	Selectivity to Aldehyde	Ratio N/I	TON
1	$\text{Ph}_2\text{P}(\text{p-C}_6\text{H}_4\text{SO}_3\text{K})$	0.50	11.30	94.50	14.86	505
2	$\text{Ph}_2\text{P}(\text{p-C}_6\text{H}_4\text{SO}_3\text{K})$	1.00	16.62	94.52	13.56	238
3	$\text{Ph}_2\text{P}(\text{p-C}_6\text{H}_4\text{SO}_3\text{K})$	2.50	33.81	94.20	13.23	257
25 4	$\text{Ph}_2\text{P}(\text{p-C}_6\text{H}_4\text{SO}_3\text{K})$	4.00	49.00	94.47	13.06	225
5	$\text{Ph}_2\text{P}(\text{p-C}_6\text{H}_4\text{SO}_3\text{K})$	10.00	85.87	95.53	12.62	135

This Sheet Has Been Replaced



When Tables 1, 2 and 3 are compared it becomes abundantly clear that the rhodium hydroformylation of 1-decene with potassium p-diphenyl phosphine benzene sulfonate ($\text{Ph}_2\text{P}(\text{p-C}_6\text{H}_4\text{SO}_3\text{K})$) exhibited slightly higher rates of conversion as compared to $\text{Ph}_2\text{P}(\text{p-C}_6\text{H}_4\text{COO}_3\text{Na})$. For example, after 4 hours of reaction in the hydroformylation reactor the rhodium catalyst of the present invention having a $\text{Ph}_2\text{P}(\text{p-C}_6\text{H}_4\text{SO}_3\text{K})$ ligand converted approximately 49.00 mole percent of 1-decene to aldehyde, whereas the conventional rhodium catalyst with a $\text{Ph}_2\text{P}(\text{p-C}_6\text{H}_4\text{COO}_3\text{Na})$ ligand only converted approximately 42.25 mole percent. Furthermore, the $\text{Ph}_2\text{P}(\text{p-C}_6\text{H}_4\text{SO}_3\text{K})$ converted more than twenty times as much as the rhodium catalyst with a $\text{Ph}_2\text{P}(\text{m-C}_6\text{H}_4\text{SO}_3\text{Na})$ ligand. The rhodium catalyst with a $\text{Ph}_2\text{P}(\text{p-C}_6\text{H}_4\text{SO}_3\text{K})$ ligand also exhibited an increased selectivity to aldehydes verses the $\text{Ph}_2\text{P}(\text{p-C}_6\text{H}_4\text{COO}_3\text{Na})$ and $\text{Ph}_2\text{P}(\text{m-C}_6\text{H}_4\text{SO}_3\text{Na})$ ligands.

While we have shown and described several embodiments in accordance with our invention, it is to be clearly understood that the same are susceptible to numerous changes apparent to one skilled in the art. Therefore, we do not wish to be limited to the details shown and described but intend to show all changes and

This Sheet Has Been Replaced



SUBSTITUTE SHEET (RULE 26)

modifications which come within the scope of the
appended claims.

5

10

15

20

25

This Sheet Has Been Replaced



CLAIMS:

1. A method for producing a potassium para-diphenyl phosphino sulfonate ligand which comprises reacting potassium diphenyl phosphide with a lithium
5 salt of para-chloro benzenesulfonic acid.

2. The method according to claim 1 wherein said potassium diphenyl phosphide and lithium salt of para-chloro benzenesulfonic acid are reacted in the presence
10 of at least one compound selected from the group consisting of: tetrahydrofuran, 1,4-dioxane and 2-ethoxyethyl ether.

3. The method according to claim 1 wherein said
15 potassium diphenyl phosphide and lithium salt of para-chloro benzenesulfonic acid are reacted at a temperature in the range between about 65 to about 100°C.

20 4. The method according to claim 1 wherein said potassium diphenyl phosphide and lithium salt of para-chloro benzenesulfonic acid are reacted for between about 0.25 to about 1 hours.





5. The method according to claim 1 wherein said potassium diphenyl phosphide is produced from the reaction product of diphenyl chlorophosphine and potassium.

5

6. The method according to claim 5 wherein said diphenyl chlorophosphine and potassium are reacted in the presence of at least one compound selected from the group consisting of: tetrahydrofuran, 1,4-dioxane and
10 2-ethoxyethyl ether.

7. The method according to claim 5 wherein said diphenyl chlorophosphine and potassium are reacted at a temperature in the range between about 65 to about
15 100°C.

8. A Group VIII noble metal-ligand complex catalyst for use in hydroformylation of olefins in the presence of synthesis gas which comprises a Group VIII
20 noble metal complexed with a potassium para-diphenyl phosphino sulfonate ligand.

9. The catalyst according to claim 8 wherein said potassium diphenyl phosphino sulfonate ligand is
25 the reaction product of potassium diphenyl phosphide and a lithium salt of para-chloro benzenesulfonic acid.





10. The catalyst according to claim 9 wherein
said potassium diphenyl phosphide and lithium salt of
para-chloro benzenesulfonic acid are reacted in the
presence of at least one compound selected from the
5 group consisting of: tetrahydrofuran, 1,4-dioxane and
2-ethoxyethyl ether.

11. The catalyst according to claim 9 wherein
said potassium diphenyl phosphide and lithium salt of
10 para-chloro benzenesulfonic acid are heated at a
temperature in the range between about 65 to about
100°C.

12. The catalyst according to claim 9 wherein
15 said potassium diphenyl phosphide and lithium salt of
para-chloro benzenesulfonic acid are reacted for
between about 0.25 to about 1 hours.

13. The catalyst according to claim 9 wherein
20 said potassium diphenyl phosphide is produced from the
reaction product of diphenyl chlorophosphine and
potassium.






14. The catalyst according to claim 13 wherein
said diphenyl chlorophosphine and potassium are reacted
in the presence of at least one compound selected from
the group consisting of: tetrahydrofuran, 1,4-dioxane
5 and 2-ethoxyethyl ether.

15. The catalyst according to claim 13 wherein
said diphenyl chlorophosphine and potassium are reacted
at a temperature in the range between about 65 to about
10 100°C.

16. A method for producing higher aldehydes and
higher alcohols which comprises hydroformylating an
olefinic feedstock with synthesis gas in the presence
15 of a Group VIII noble metal-ligand complex catalyst to
form a crude reaction product comprised of an olefin
feed, a hydroformylation reaction product and a Group
VIII noble metal-ligand complex catalyst, wherein said
Group VIII noble metal-ligand complex catalyst is a
20 Group VIII noble metal complexed with a potassium para-
diphenyl phosphino sulfonate ligand.

17. The method according to claim 16 wherein said
potassium para-diphenyl phosphino sulfonate ligand is
25 the reaction product of potassium diphenyl phosphide
and a lithium salt of para-chloro benzenesulfonic acid.





18. The method according to claim 17 wherein said potassium diphenyl phosphide and lithium salt of para-chloro benzenesulfonic acid are reacted in the presence of at least one compound selected from the group
5 consisting of: tetrahydrofuran, 1,4-dioxane and 2-ethoxyethyl ether.

19. The method according to claim 17 wherein said potassium diphenyl phosphide and lithium salt of para-
10 chloro benzenesulfonic acid are heated at a temperature in the range between about 65 to about 100°C.

20. The method according to claim 17 wherein said potassium diphenyl phosphide and lithium salt of para-
15 chloro benzenesulfonic acid are reacted for between about 0.25 to about 100 hours.

21. The method according to claim 17 wherein said potassium diphenyl phosphide is produced from the
20 reaction product of diphenyl chlorophosphine and potassium.





22. The method according to claim 21 wherein said
diphenyl chlorophosphine and potassium are reacted in
the presence of at least one compound selected from the
group consisting of: tetrahydrofuran, 1,4-dioxane and
5 2-ethoxyethyl ether.

23. The method according to claim 21 wherein said
diphenyl chlorophosphine and potassium are reacted at a
temperature in the range between about 65 to about
10 100°C.

15

20

25

