


MONOAZO PIGMENTS

This invention relates to monoazo pigments and more particularly to orange pigments of the azo pyrazolone series.

The use of pigments for the colouring of plastics materials is well known. For the production of orange colorations, it has been traditional to employ inorganic pigments such as cadmiums, lead chromes and molybdate oranges but these are now being phased out because of environmental pressures. Organic pigments that have been proposed as replacements for these inorganic materials have not been found entirely satisfactory in all of the major polymer types, especially in respect of their heat stability.

It has now been found that certain organic pigments of the azo pyrazolone series are characterised by excellent heat stability, light stability, and bleed fastness when used in a wide range of plastics materials.

Accordingly, the invention provides an azo pyrazolone compound of the formula :



in the form of a salt.

The salts of the compounds of Formula 1 may exhibit polyphormism and, where this is the case, the various polymorphic forms are regarded as within the scope of the invention.


Particularly advantageous compounds of Formula 1 in terms of superior heat and light stability are compounds in which the sulphonic acid group of the naphthalene nucleus is present in the 4- or 6-position relative to the azo link and the sulphonic acid group of the benzene ring is present in the 3- or 4-position relative to the pyrazolyl group.



2

The salt of the azo pyrazolone compound of Formula 1 may be a metal salt, for example, an alkali metal, alkaline earth metal or heavy metal salt, or a salt of a nitrogenous base, for example a primary, secondary or tertiary amine or quaternary ammonium salt, particularly useful pigments being the salts of barium, strontium, manganese, magnesium, sodium and, especially, calcium.

The most preferred compounds of the invention have the formula :



wherein the sulphonate group of the naphthalene nucleus is in the 4- or 6-position relative to the azo group.

The azo pyrazolone compounds of the invention may be prepared by diazotising a naphthylamine sulphonic acid of the formula :



and coupling the resulting diazo compound with a sulphonated 3-methyl-1-phenylpyrazol-5-one of the formula :



and converting the resulting monoazo compound to the desired salt form.

The diazotisation and coupling reactions may be performed in a conventional manner appropriate to the classes of compound being used.

The preferred naphthylamine sulphonic acids for use in preparing the compounds of the invention are 1-naphthylamine-4-sulphonic acid and 1-naphthylamine-6-sulphonic acid whilst the preferred coupling components are 3-methyl-1-(4'-sulphophenyl)pyrazol-5-one and, especially 3-methyl-1-(3'-sulphophenyl)pyrazol-5-one.

It is often convenient to prepare the compound of Formula 1 in the form of a sodium salt and then convert the sodium salt to, for example, an alkaline earth or heavy metal lake by adding the required amount of a water-soluble alkaline earth metal or heavy metal salt, usually in the form of an aqueous solution.

Surface active agents and/or organic solvents may optionally be present during the synthesis of the compound of Formula 1 and/or during precipitation of the pigment.

The compounds of the invention, which may be subjected to conventional milling operations and/or thermal treatments in order to provide products of the desired particle size and/or crystal structure, are useful orange pigments which may be used in conventional manner. In particular, they may be used alone or in conjunction with other pigments for the coloration of plastics materials, for example polyvinyl chloride, polyolefins, polystyrene and ABS where they exhibit excellent properties. The compounds of the invention are also valuable for the pigmentation of surface coatings.

The invention is illustrated but not limited by the following Examples.

Example 1

1-Naphthylamine-6-sulphonic acid (4.46g), de-ionised water (50ml) and hydrochloric acid (5.1ml) were stirred together in a vessel surrounded by an ice-bath, followed by sufficient 48% sodium hydroxide solution to form a solution alkaline to Brilliant Yellow paper. The solution was then cooled to 0-5°C and a further amount (5.1ml) of hydrochloric acid was added. A solution of sodium nitrite (1.56g) in de-ionised water (5ml) was added all at once and the mixture was stirred at 0-5°C for 30 mins. Excess nitrite was then removed by adding a few ml of 10% sulphamic acid solution.

3-Methyl-1-(3'-sulphophenyl) pyrazol-5-one (5.4g) was added to de-ionised water (50ml) and the pH was adjusted to 6.5 by the addition of 48% sodium hydroxide solution. The solution was then stirred at 0-5°C and the diazo suspension

obtained as described above was added over 10 mins whilst maintaining the pH at 6.5 by the addition of 48% sodium hydroxide solution. The coupling mixture was then stirred overnight at room temperature.

The reaction mixture was then heated to 90°C and a solution of calcium chloride (32g CaCl_2 in 40ml water) was added all at once and the mixture stirred for a further 3 hours at 90°C. The mixture was then filtered hot and the product was washed chloride-free with de-ionised water (1000ml) and dried giving 7.3g of an orange solid.

Example 2

10 1-Naphthylamine-4-sulphonic acid, sodium salt (6.14g), deionised water (50ml) and hydrochloric acid (5.1ml) were stirred together in a vessel surrounded by an ice bath, followed by sufficient 48% sodium hydroxide solution to form a solution alkaline to Brilliant Yellow paper. The solution was then cooled to 0-5°C and a further amount (5.1ml) of hydrochloric acid was added. A solution of sodium nitrite (1.56g) in deionised water (5ml) was added all at once and the mixture was stirred at 0-5°C for 30 mins. Excess nitrite was then removed by adding a few ml of 10% sulphamic acid solution.

3-Methyl-1-(3'-sulphophenyl)pyrazol-5-one (6.08g) was added to deionised water (50ml) and the pH was adjusted to 6.5 by the addition of 48% sodium hydroxide solution. The solution was then stirred at 0-5°C and the diazo suspension obtained as described above was added over 10 mins whilst maintaining the pH at 6.5 by the addition of 48% sodium hydroxide solution. The coupling mixture was then stirred overnight at room temperature.

The reaction mixture was then heated to 90°C and a solution of calcium chloride (32g CaCl_2 in 40ml water) was added all at once and the mixture stirred for a further 3 hours at 90°C. The mixture was then filtered hot and the product was washed chloride-free with deionised water (1000ml) and dried giving 8.4g of an orange solid.

Example 3

30 1-Naphthylamine-4-sulphonic acid, sodium salt (5.74g), deionised water (50ml) and hydrochloric acid (5.1ml) were stirred together in a vessel surrounded by an ice bath, followed by sufficient 48% sodium hydroxide solution to form a solution alkaline to Brilliant Yellow paper. The solution was then cooled to 0-5°C and a further amount (5.1ml) of hydrochloric acid was added. A solution of sodium nitrite (1.56g) in deionised

water (5ml) was added all at once and the mixture was stirred at 0-5°C for 30 mins. Excess nitrite was then removed by adding a few ml of 10% sulphamic acid solution.

3-Methyl-1-(4'-sulphophenyl)pyrazol-5-one (5.6g) was added to deionised water (50ml) and the pH was adjusted to 6.5 by the addition of 48% sodium hydroxide solution. The solution was then stirred at 0-5°C and the diazo suspension obtained as described above was added over 10 mins whilst maintaining the pH at 6.5 by the addition of 48% sodium hydroxide solution. The coupling mixture was then stirred overnight at room temperature.

The reaction mixture was then heated to 90°C and a solution of calcium chloride (32g CaCl_2 in 40ml water) was added all at once and the mixture stirred for a further 3 hours at 90°C. The mixture was then filtered hot and the product was washed chloride-free with deionised water (1000ml) and dried giving 3.4g of an orange solid.



THIS SHEET HAS BEEN
REPLACED

PCT/GB95/02833


WO 96/22334

6

CLAIMS

1. An azo pyrazolone compound of the formula :

5



10

in the form of a salt.

- 15 2. A compound according to claim 1 wherein the sulphonic acid group in the naphthalene nucleus is in the 4- or 6- position relative to the azo link and the sulphonic acid group in the benzene ring is in the 3- or 4-position relative to the pyrazolyl group.


3. A compound according to claim 1 or claim 2 wherein the salt is a metal
20 salt or a salt of a nitrogenous base.

4. A compound according to claim 3 wherein the salt is a calcium salt.

5. A compound according to claim 4 having the formula :

25

30




This Sheet Has Been Replaced






wherein the sulphonate group in the naphthalene nucleus is in the 4- or 6-position relative to the azo link.

6. A method for the preparation of an azo pyrazolone compound as defined
5 in claim 1 which comprises diazotising a naphthylamine sulphonic acid of the formula :



10

and coupling the resulting diazo compound with a sulphonated 3-methyl-1-phenylpyrazol-5-one of the formula :



15

20

and converting the resulting monoazo compound to the desired salt form.

7. A method according to claim 6 wherein the naphthylamine sulphonic acid
comprises 1-naphthylamine-4-sulphonic acid and/or 1-naphthylamine-6-sulphonic acid.

25

8. A method according to claim 6 or claim 7 wherein the sulphonated 3-
methyl-1-phenylpyrazol-5-one comprises 3-methyl-1-(4'-sulphophenyl)pyrazol-5-one
and/or 3-methyl-1-(3'-sulphophenyl)pyrazol-5-one.

- 30 9. The use of an azo pyrazolone compound as defined in
claim 1 as a pigment.



1

MONOAZO PIGMENTS

8


1

INSERT → This invention relates to monoazo pigments and more particularly to orange pigments of the azo pyrazolone series.

The use of pigments for the colouring of plastics materials is well known. For the production of orange colorations, it has been traditional to employ inorganic pigments such as cadmiums, lead chromes and molybdate oranges but these are now being phased out because of environmental pressures. Organic pigments that have been proposed as replacements for these inorganic materials have not been found entirely satisfactory in all of the major polymer types, especially in respect of their heat stability.

10 It has now been found that certain organic pigments of the azo pyrazolone series are characterised by excellent heat stability, light stability, and bleed fastness when used in a wide range of plastics materials.

Accordingly, the invention provides an azo pyrazolone compound of the formula :




in the form of a salt.

25 The salts of the compounds of Formula 1 may exhibit polyphormism and, where this is the case, the various polymorphic forms are regarded as within the scope of the invention.

Particularly advantageous compounds of Formula 1 in terms of superior heat and light stability are compounds in which the sulphonic acid group of the naphthalene nucleus is present in the 4- or 6-position relative to the azo link and the sulphonic acid group of the benzene ring is present in the 3- or 4-position relative to the pyrazolyl group.

30




REVENDED SHEET

Insert for PCT/GB 95/02833

J. of Chromatography, 665, 197 (1994) discloses certain sulphonated azopyrazolones and the corresponding sodium and potassium salts.


European patent EP 0 225 553 discloses certain isomeric azopyrazolones as the calcium salts.






CLAIMS


1. An azo pyrazolone compound of the formula :



in the form of a salt except for




and



in the form of their sodium and potassium salts.


2. A compound according to claim 1 wherein the sulphonic acid group in the naphthalene nucleus is in the 4- or 8- position relative to the azo link and the sulphonic acid group in the benzene ring is in the 3- or 4-position relative to the pyrazolyl group.



AMENDED SHEET




3. A compound according to claim 1 or claim 2 wherein the salt is a metal salt or a salt of a nitrogenous base.
4. A compound according to claim 3 wherein the salt is a calcium salt.
5. A compound according to claim 4 having the formula :




wherein the sulphonate group in the naphthalene nucleus is in the 4- or 6-position relative to the azo link.


6. A method for the preparation of an azo pyrazolone compound as defined in claim 1 which comprises diazotising a naphthylamine sulphonic acid of the formula :



and coupling the resulting diazo compound with a sulphonated 3-methyl-1-phenylpyrazol-5-one of the formula :



AMENDED SHEET




and converting the resulting monoazo compound to the desired salt form.

7. A method according to claim 6 wherein the naphthylamine sulphonic acid comprises 1-naphthylamine-4-sulphonic acid and/or 1-naphthylamine-6-sulphonic acid.

8. A method according to claim 6 or claim 7 wherein the sulphonated 3-methyl-1-phenylpyrazol-5-one comprises 3-methyl-1-(4'-sulphophenyl)pyrazol-5-one and/or 3-methyl-1-(3'-sulphophenyl)pyrazol-5-one.

9. The use of an azo pyrazolone compound as defined in claim 1 as a pigment.



PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C09B 63/00, 29/50, 69/04		A1	(11) International Publication Number: WO 96/22334
			(43) International Publication Date: 25 July 1996 (25.07.96)
(21) International Application Number: PCT/GB95/02835		(81) Designated States: AL, AM, AT, AU, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IS, JP, KE, KG, KP, KR, KZ, LK, LR, LS, LT, LU, LV, MD, MG, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG , SI, SK, TJ, TM, TT, UA, UG, US, UZ, VN, ARIPO patent (KE, LS, MW, SD, SZ, UG), European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).	
(22) International Filing Date: 5 December 1995 (05.12.95)		Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>	
(30) Priority Data: 9501089.8 20 January 1995 (20.01.95) GB			
(71) Applicant (for all designated States except US): ZENECA LIMITED [GB/GB]; 15 Stanhope Gate, London W1Y 6LN (GB).			
(72) Inventors; and (75) Inventors/Applicants (for US only): CHORLTON, Alan, Patrick [GB/GB]; 22 Cote Green Road, Marple Bridge, Stockport, Cheshire SK6 5EW (GB). MASON, James [GB/GB]; 5 Pikehouse Cottages, Lightowlers Lane, Littleborough, Rochdale, Lancashire OL15 0LW (GB).			
(74) Agents: STEPHENSON, Kenneth; Zeneca Specialties, Intellectual Property Group, P.O. Box 42, Hexagon House, Blackley, Manchester M9 8ZS (GB) et al.			

(54) Title: MONOAZO PIGMENTS

(57) Abstract

An azo pyrazolone compound of formula (1) in the form of a salt, and its use as a pigment.

