

Description

This invention relates to the use of a matrix-enclosed magnetically responsive material for the manufacture of NMR imaging contrast agent.

In diagnostic medicine, contrast agents are today being used primarily in X-ray diagnostics where an increased contrast effect is obtained during examination of, for example, internal organs, such as the kidneys, the urinary tract, the digestive tract, the vascular system of the heart (angiography), etc. This contrast effect is based upon the fact that the contrast agent itself is less permeable to X-rays than the surrounding tissue, as a result of which a different blackening of the X-ray plate is obtained.

X-raying implies certain radiation hazards, but during angiography the risk of complications is associated in particular with the use of contrast agents.

In recent years, a number of new methods have been introduced in diagnostic imaging. One such method goes by the name NMR (Nuclear Magnetic Resonance) which provides information not only about the distribution of the water content in a specific tissue (in contradistinction to radiology which merely gives a measure of the transmissibility of the X-rays in a specific tissue), but also about the chemical tissue structure which is different in normal and pathological tissue.

In the NMR method, a strong and homogeneous magnetic field is applied across the tissue to be examined. By studying the so-called relaxation times of the protons of the molecules present, especially the protons of the water, it is possible to produce, via comprehensive and complex computer calculations, a visual image of the structure of the tissue concerned.

There is, however, an interest in being able to make a differential diagnosis between pieces of tissue having a high density of blood vessels and, alternatively, tissue having a low density of vessels. Such a situation, which has considerable clinical interest, occurs with the localisation of tumours which, in their periphery, have a higher density of vessels as compared with normal tissue.

One useful method in this context would be to inject into the vascular system a contrast agent comprising particles responsive to a magnetic field and showing changes in the above-mentioned relaxation times.

It may be noted that drug-targeting matrix bound magnetically responsive particles are described in WO-A-78/00005 and WO-A-83/01738 — these publications suggest that the magnetically responsive nature of the particles be utilized to enable the particles to be caused to congregate at desired sites there to release a biologically active agent.

However according to the present invention there is provided the use of magnetically responsive material for the manufacture of a diagnostic agent for use in a method of nuclear magnetic resonance imaging of a subject, said agent comprising particles of a matrix material having a diameter of up to 10 micrometers, for example at least 0.01 micrometer, and having enclosed therein said magnetically responsive material.

The magnetically responsive particles interfere with the above-mentioned homogeneous magnetic field in that there is formed, around each individual particle, a field gradient which in its turn changes the relaxation times.

Put more simply, this means that "black holes" are formed around each particle which may be visualised and thus give an impression of the vessel density in the tissue in question.

By labelling the particles with some gamma-radiating nuclide (for example technetium-99m) it is possible to localise the particles by means of a gamma camera and thereby also to combine such examination with the other technique referred to above.

When using the magnetically responsive material containing matrix particles, it is desirable, in order to achieve optimal conditions, to be able to vary the amount of magnetically responsive material, without affecting on that account the pharmacodynamic and circulatory characteristics of the particles. To be able to do this, one must use a technique which involves enclosing the responsive material in a matrix, preferably a matrix of spherical shape, and the matrix itself should satisfy the following criteria:

- biocompatible
- biologically degradable
- nonimmunogenic.

A matrix of this type normally is built up of some type of polymers which are held together by chemical bonds. Different types of polymers are available for making such matrices. However, the selection of polymers will be very limited if the above-mentioned criteria of the matrix are to be fulfilled.

One type of polymers that has proved useful in these contexts are the carbohydrates and their derivatives, especially those which occur naturally in the body.

Endogenous carbohydrates are represented by starch and glycogen, but dextran also may be included in this group because of its prolonged use as a blood substituent in medical service.

The production of a carbohydrate matrix satisfying these criteria is described in WO-A-83/01738, WO-A-83/03426 and WO-A-84/00294.

Another set of polymers that have proved to satisfy the said criteria are polyamino acids, such as proteins of the type albumin. The production of polyamino acid matrices is disclosed in US-A-424706.

Other parenterally-administrable, particulate, magnetically responsive material-containing agents are disclosed in WO-A-78/00005. This publication however suggests utilization of the magnetic

responsiveness for drug targetting by the application of an external magnetic field.

Further types of polymers are represented by synthetic polymers, such as acrylates, polystyrene etc. The production of matrices from synthetic polymers is well documented in the literature.

In this connection it is extremely advantageous if covalent cross-linking of the polymers can be avoided in the production of a useful matrix. For example, covalently cross-linked carbohydrate matrices have been found to produce transformed cells, in the form of granuloma, when used on humans (see Am.Surg. (1955) 142, 1045).

When using covalently cross-linked proteins, there is a risk of immunological reactions because the resulting derivatised protein is not recognised by the body's immunity system as a protein belonging to the body. There are, however, for specific systems no alternatives to the covalent cross-linking, especially when using synthetic polymers or combinations of different polymers and cross-linking agents in order to obtain a useful system. As an example, it is possible to cross-link acrylic polymers with starch and, alternatively, the cross-link starch with acrylates.

Another useful possibility which is described in the literature is the production of larger particles from smaller particles. For example, it is possible to produce, from 0.5 micrometer particles, conglomerates of larger particles, for example in the range of about 10 micrometers.

Another factor of importance to the injection of spherical particles into the vascular system is that the spheres have a size that prevents them from getting stuck in the capillary system of different tissues during the first passage. To prevent this, the particle must have a diameter below 1 micrometer (Chem. Pharm. Bull. (1975) 23, 1452) and a surface structure of hydrophilic character.

When particles are injected into the vascular system, all particles will have collected after a given period of time in the liver or spleen (the RES system) because the normal function of these organs is to purify the blood of foreign particles. At present, there is only one method described which is capable of collecting particles to organs other than those mentioned above, and this is by utilising magnetically responsive particles or spheres.

This is of particular interest in the context of this invention because spherical particles containing magnetically responsive substances can be used and be made to stop in different tissues by means of the external magnetic field. When the magnetically responsive particles then are stuck in the desired tissue, the tissue in question can simply be visualised by means of the NMR method.

The magnetically responsive material used according to the invention may consist, for example, of magnetite particles enclosed in the form of discrete particles of varying size, or in the form of complexed ions.

One conceivable matrix for use in the context of this invention consists of carbohydrates that have been stabilised by crystallization, which means that the type of chemical bonds holding the polymeric network together is not covalent in character, mainly hydrogen bonds, van der Waals forces or, in some cases, ion bonds.

As carbohydrates, use may be made of all conceivable variants, including carbohydrates of varying molecular weight and/or substituted or otherwise derivatised carbohydrates. For example, it may be mentioned that it is possible to produce and use magnetically responsive carbohydrate particles in which the carbohydrate is of starch origin and low-molecular of the type glucose, maltose, dextrans etc., and successively increasing molecular weight up to native potato starch having a molecular weight of several millions. The same molecular weight range is applicable to other carbohydrate groups, such as dextran or glycogen.

Another matrix for use according to the invention may consist of polyamino acids, such as the protein albumin in which the matrix is stabilised by heating and the cohering forces are not covalent in character, of the type hydrophobic interactions, hydrogen bonds, van der Waals forces or ion bonds. In a manner similar to what has been stated above, it is also possible to use synthetic polymers or combinations as matrix.

The following Example should not be regarded as restrictive and merely serves to illustrate the main features of the invention.

Example

Dextran spheres having a size of about 1 micrometer with enclosed magnetite particles (size 10—20 nm) were suspended in human serum. The relaxation times of the solution were measured with an NMR apparatus (Praxis II, Alnor Instrument AB, Nyköping) and compared with the relaxation times for the same serum without magnetically responsive dextran spheres. The following values of T_1 and T_2 , respectively, were obtained.

		T_1 (ms)	T_2 (ms)
	Serum without particles:	1660	400
5	Serum with particles: conc.:		
	0.05 mg/ml	1342	109
	0.1 mg/ml	1306	82.2
	0.2 mg/ml	1147	52.6
	0.5 mg/ml	968	30.7
	1.0 mg/ml	813	24.0
15	2.0 mg/ml	688	19.9
	4.0 mg/ml	691	22.9

Claims

1. Use of magnetically responsive material for the manufacture of a diagnostic agent for use in a method of nuclear magnetic resonance imaging of a subject, said agent comprising particles of a matrix material having a diameter of up to 10 micrometers and having enclosed therein said magnetically responsive material.

2. Use as claimed in claim 1 for the manufacture of a said agent wherein the diameter of said matrix material particles is at least 0.01 micrometer.

3. Use as claimed in claim 1 for the manufacture of a said agent wherein the diameter of said matrix material particles is at least 0.5 micrometers.

4. Use as claimed in any one of claims 1 to 3 for the manufacture of a said agent wherein the diameter of said matrix material particles is less than 1 micrometer.

5. Use as claimed in any one of claims 1 to 4 for the manufacture of a said agent wherein said particles of matrix material enclose particles of magnetite.

6. Use as claimed in claim 5 for the manufacture of a said agent wherein said particles of magnetite are 10 to 20 nanometers in size.

7. Use as claimed in any one of claims 1 to 6 for the manufacture of a said agent wherein said matrix material is a carbohydrate or a derivative thereof.

8. Use as claimed in claim 7 for the manufacture of a said agent wherein said matrix material is a material selected from starch and derivatives thereof, glycogen and dextran.

9. Use as claimed in claim 1 for the manufacture of a said agent comprising dextran spheres of about 1 micrometer diameter having enclosed therein magnetite particles of 10 to 20 nanometer size.

10. Use as claimed in any one of claims 1 to 9 for the manufacture of a said agent in a form adapted for injection into said subject's vascular system.

Patentansprüche

1. Verwendung eines magnetisch anregbaren Materials zur Herstellung eines diagnostischen Mittels für die Anwendung bei der Kernspin-Tomographie eines Patienten, wobei das Mittel Matrix-Partikel mit einem Durchmesser bis zu 10 µm umfaßt, worin das magnetisch anregbare Material enthalten ist.

2. Verwendung nach Anspruch 1, zur Herstellung des Mittels, worin der Durchmesser der Matrix-Partikel mindestens 0,01 µm beträgt.

3. Verwendung nach Anspruch 1 zur Herstellung des Mittels, worin der Durchmesser der Matrix-Partikel mindestens 0,5 µm beträgt.

4. Verwendung nach einem der Ansprüche 1 bis 3 zur Herstellung des Mittels, worin der Durchmesser der Matrix-Partikel weniger als 1 µm beträgt.

5. Verwendung nach einem der Ansprüche 1 bis 4 zur Herstellung des Mittels, worin die Matrix-Partikel Magnetit-Partikel enthalten.

6. Verwendung nach Anspruch 5 zur Herstellung des Mittels, worin die Magnetit-Partikel eine Größe von 10 bis 20 nm aufweisen.

7. Verwendung nach einem der Ansprüche 1 bis 6 zur Herstellung des Mittels, worin das Matrixmaterial ein Kohlenhydrat oder ein Derivat davon ist.

8. Verwendung nach Anspruch 7 zur Herstellung des Mittels, worin das Matrixmaterial unter Stärke und deren Derivaten, Glykogen und Dextran ausgewählt ist.



		T_1 (ms)	T_2 (ms)
	Serum without particles:	1660	400
5	Serum with particles: conc.:		
	0.05 mg/ml	1342	109
	0.1 mg/ml	1306	82.2
	0.2 mg/ml	1147	52.6
	0.5 mg/ml	968	30.7
	1.0 mg/ml	813	24.0
15	2.0 mg/ml	688	19.9
	4.0 mg/ml	691	22.9

Claims

1. Use of magnetically responsive material for the manufacture of a diagnostic agent for use in a method of nuclear magnetic resonance imaging of a subject, said agent comprising particles of a matrix material having a diameter of up to 10 micrometers and having enclosed therein said magnetically responsive material.

2. Use as claimed in claim 1 for the manufacture of a said agent wherein the diameter of said matrix material particles is at least 0.01 micrometer.

3. Use as claimed in claim 1 for the manufacture of a said agent wherein the diameter of said matrix material particles is at least 0.5 micrometers.

4. Use as claimed in any one of claims 1 to 3 for the manufacture of a said agent wherein the diameter of said matrix material particles is less than 1 micrometer.

5. Use as claimed in any one of claims 1 to 4 for the manufacture of a said agent wherein said particles of matrix material enclose particles of magnetite.

6. Use as claimed in claim 5 for the manufacture of a said agent wherein said particles of magnetite are 10 to 20 nanometers in size.

7. Use as claimed in any one of claims 1 to 6 for the manufacture of a said agent wherein said matrix material is a carbohydrate or a derivative thereof.

8. Use as claimed in claim 7 for the manufacture of a said agent wherein said matrix material is a material selected from starch and derivatives thereof, glycogen and dextran.

9. Use as claimed in claim 1 for the manufacture of a said agent comprising dextran spheres of about 1 micrometer diameter having enclosed therein magnetite particles of 10 to 20 nanometer size.

10. Use as claimed in any one of claims 1 to 9 for the manufacture of a said agent in a form adapted for injection into said subject's vascular system.

Patentansprüche

1. Verwendung eines magnetisch anregbaren Materials zur Herstellung eines diagnostischen Mittels für die Anwendung bei der Kernspin-Tomographie eines Patienten, wobei das Mittel Matrix-Partikel mit einem Durchmesser bis zu 10 μm umfaßt, worin das magnetisch anregbare Material enthalten ist.

2. Verwendung nach Anspruch 1, zur Herstellung des Mittels, worin der Durchmesser der Matrix-Partikel mindestens 0,01 μm beträgt.

3. Verwendung nach Anspruch 1 zur Herstellung des Mittels, worin der Durchmesser der Matrix-Partikel mindestens 0,5 μm beträgt.

4. Verwendung nach einem der Ansprüche 1 bis 3 zur Herstellung des Mittels, worin der Durchmesser der Matrix-Partikel weniger als 1 μm beträgt.

5. Verwendung nach einem der Ansprüche 1 bis 4 zur Herstellung des Mittels, worin die Matrix-Partikel Magnetit-Partikel enthalten.

6. Verwendung nach Anspruch 5 zur Herstellung des Mittels, worin die Magnetit-Partikel eine Größe von 10 bis 20 nm aufweisen.

7. Verwendung nach einem der Ansprüche 1 bis 6 zur Herstellung des Mittels, worin das Matrixmaterial ein Kohlenhydrat oder ein Derivat davon ist.

8. Verwendung nach Anspruch 7 zur Herstellung des Mittels, worin das Matrixmaterial unter Stärke und deren Derivaten, Glykogen und Dextran ausgewählt ist.

EP 0 166 755 B1

9. Verwendung nach Anspruch 1 zur Herstellung des Mittels, welches Dextran-Kügelchen von etwa 1 μm Durchmesser aufweist, worin Magnetit-Partikel von 10 bis 20 nm Größe eingeschlossen sind.

10. Verwendung nach einem der Ansprüche 1 bis 9 zur Herstellung des Mittels in einer Form, die sich zur Injektion in das vaskuläre System des Patienten eignet.

5

Revendications

1. Emploi d'une matière magnétiquement sensible pour la fabrication d'un agent diagnostique à utiliser dans un procédé d'imagerie à résonance magnétique nucléaire d'un sujet ou patient, l'agent en question comprenant des particules d'une matière constituant matrice, possédant un diamètre allant jusqu'à 10 micromètres et dans laquelle est incluse ladite matière magnétiquement sensible.

2. Emploi suivant la revendication 1 pour la fabrication d'un agent tel que précité, caractérisé en ce que le diamètre desdites particules de la matière constituant matrice atteint au moins 0,01 micromètre.

15 3. Emploi suivant la revendication 1 pour la fabrication d'un agent du genre précité, caractérisé en ce que le diamètre des particules de ladite matière constituant matrice atteint au moins 0,5 micromètre.

4. Emploi suivant l'une quelconque des revendications 1 à 3, pour la fabrication d'un agent tel que précité, caractérisé en ce que le diamètre des particules de ladite matière constituant matrice est inférieur à 1 micromètre.

20 5. Emploi suivant l'une quelconque des revendications 1 à 4, pour la fabrication d'un agent tel que précité, caractérisé en ce que lesdites particules de la matière constituant matrice enferment des particules de magnétite.

6. Emploi suivant la revendication 5, pour la fabrication d'un agent du genre précité, caractérisé en ce que lesdites particules de magnétite ont un calibre qui fluctue de 10 à 20 nanomètres.

25 7. Emploi suivant l'une quelconque des revendications 1 à 6, pour la fabrication d'un agent du genre précité, caractérisé en ce que la ladite matière constituant matrice est un hydrate de carbone ou glucide ou un dérive d'un tel composé.

8. Emploi suivant la revendication 7, pour la fabrication d'un agent tel que précité, caractérisé en ce que ladite matière constituant matrice est une matière choisie parmi l'amidon et les dérivés de ce dernier, le glycogène et le dextrane.

30 9. Emploi suivant la revendication 1, pour la fabrication d'un agent du genre précité, comprenant des sphères de dextrane d'un diamètre d'environ 1 micromètre, dans lesquelles sont incluses des particules de magnétite d'un calibre de 10 à 20 nanomètres.

10. Emploi suivant l'une quelconque des revendications 1 à 9, pour la fabrication d'un agent tel que précité, sous une forme adaptée à l'injection dans le système vasculaire du sujet ou patient.

35

40

45

50

55

60

65



* C L M S *