

Description

The present invention relates to crosslinkable organic polymer compositions. More particularly the present invention is concerned with compositions comprising crosslinkable copolymers which are prepared by copolymerising unsaturated organic monomers with unsaturated silane compounds containing hydrolysable groups.

It is known that organic polymers containing hydrolysable silane groups can be crosslinked by the action of water, preferably in the presence of a so-called silanol condensation catalyst. A number of methods are known for producing such crosslinkable organic polymers. One method comprises copolymerising unsaturated organic monomers with unsaturated silane compounds containing hydrolysable groups. Examples of this method are described in GB-A-2028831 and GB-A-2039513 which disclose the preparation of crosslinkable copolymers of ethylene and an ethylenically unsaturated silane compound by copolymerising the monomers at relatively high temperatures and pressures in the presence of a radical polymerisation initiator. Another example of this copolymerisation method is described in GB-A-1415194 which discloses the preparation of crosslinkable copolymer by contacting ethylene, optionally with other olefinically unsaturated comonomer, and a terminally unsaturated silane compound with certain defined Ziegler catalysts under polymerisation conditions which preferably employ relatively low temperatures and pressures.

It is also well-known that polymers crosslinkable by the action of water and a silanol condensation catalyst can be prepared by grafting an unsaturated silane compound on to a (preformed) polyolefin, but the present invention is not concerned with graft polymers of this type.

Crosslinkable organic copolymers having hydrolysable silane groups and made by the copolymerisation method (hereinafter referred to as "silyl copolymers") can be fabricated to form a large variety of useful articles by conventional techniques, for example, extrusion, injection moulding, blow-moulding and film-blowing processes. The crosslinking step is generally carried out subsequent to fabrication of the article because the crosslinked polymer cannot in general be satisfactorily thermoformed.

A problem encountered with silyl copolymers is that during storage or thermoforming operations the polymer can undergo premature crosslinking and this can lead to difficulties in the fabrication of articles from the polymer or to the production of articles having unsatisfactory physical and mechanical properties. The problem of crosslinking during storage may be reduced by ensuring that the silyl copolymers are maintained in a moisture-free environment and by keeping the silanol condensation catalyst (or other additives known to promote crosslinking) separate from the polymer until the fabrication step is preformed. A technique frequently employed in the art is to make up a concentrated masterbatch containing the silanol condensation catalyst and other additives if any, in an organic polymer which does not spontaneously crosslink and which is compatible with the silyl copolymer, and to blend this masterbatch with the silyl copolymer during or just prior to thermoforming of the desired article. The fabricated article is then exposed to water, steam or moist air to cause crosslinking.

Problems resulting from premature crosslinking during thermoforming are more difficult to overcome. One method of reducing premature crosslinking proposed in GE-A-1357549 is to mould or extrude articles from silyl copolymers (or alternatively from polymers grafted with hydrolysable silane compound) in the absence of the silanol condensation catalyst and then to contact the produced article with an aqueous dispersion or solution of a tin carboxylate to cause the crosslinking.

It is an object of the present invention to provide an improved crosslinkable silyl copolymer composition. It is a further object of the present invention to provide a crosslinkable silyl copolymer composition which exhibits a reduced tendency to undergo premature crosslinking during the fabrication of articles therefrom.

Accordingly, the present invention provides a crosslinkable composition comprising:-

(A) A silyl copolymer prepared by copolymerising ethylene and an unsaturated silane compound having one or more hydrolysable groups, optionally together with one or more other monomers copolymerisable therewith, and

(B) A silanol condensation catalyst comprising a dihydrocarbyl tin (IV) carboxylate compound characterised in that the carboxylate units in the tin compound are provided by a dicarboxylic acid.

The present invention further provides a process for preparing a crosslinkable composition by blending together components comprising:

(A) A silyl copolymer prepared by copolymerising ethylene and an unsaturated silane compound having one or more hydrolysable groups, optionally together with one or more other monomers copolymerisable therewith, and


(B) A silanol condensation catalyst comprising a dihydrocarbyl tin (IV) carboxylate compound charac-

terised in that the carboxylate units in the tin compound are provided by a dicarboxylic acid.

The carboxylate units in the tin compound are provided by a dicarboxylic acid having the general formula $\text{HOOC}\cdot\text{X}\cdot\text{COOH}$ wherein X is a divalent organic group which preferably contains 1-12, most preferably 1-6 carbon atoms. Examples of suitable divalent groups (X) are methylene, alkyl or aryl substituted methylene, polymethylene, alkyl or aryl substituted polymethylene, unsaturated straight or branched chain groups and substituted or unsubstituted phenylene groups. Examples of suitable dicarboxylic acids are oxalic, malic, maleic, fumaric, adipic, sebacic and phthalic acid. Maleic acid is particularly preferred.


The hydrocarbyl groups in the dihydrocarbyl tin (IV) compound can be the same or different and are preferably alkyl groups containing 1-6 carbon atoms. A particularly preferred dihydrocarbyl tin (IV) compound is dibutyl tin (IV) maleate.

The dihydrocarbyl tin compound can be a monomeric tin compound (i.e. a tin compound containing one atom of tin per molecule) or in the form of dimeric or polymeric tin compounds (i.e. compounds of tin containing two or more atoms of tin per molecule). The monomeric tin compounds can be, for example, cyclic diesters represented by the general formula:



20

or acyclic diesters represented by the general formula:



wherein R^1 , R^2 and R^3 are the same or different hydrocarbyl groups, preferably alkyl groups containing 1 to 6 carbon atoms and X is an organic divalent group as described above. The value of m is 0 or 1. The dimeric or polymeric tin compounds can be, for example, cyclic or acyclic compounds built up from units of the above monomeric tin compounds and linked together via the dicarboxylate and tin functions.

The dihydrocarbyl tin (IV) carboxylate employed in the present invention preferably contains less than 0.1 mole of free carboxylic acid groups per atom of tin and is most preferably substantially free from such uncombined carboxylic acid groups.

The manufacture of tin compounds of the type referred to above is well known from the prior art. They can be made, for example by reacting dicarboxylic acid esters (or half esters) with dihydrocarbyl tin dichlorides.

The quantity of the tin compound employed in the composition of the present invention is suitably in the range 0.001 to 3.0 moles, preferably 0.003 to 0.05 moles (based on atoms of tin) per mole of silyl units in the silyl copolymer. Generally speaking, the quantity of the tin compound is in the range 0.001 to 10% by weight, preferably 0.01 to 5% by weight, for example, 0.03 to 3% by weight based on the weight of the silyl copolymer in the composition.

The silyl copolymers employed in the present invention are prepared by copolymerising ethylene and an unsaturated compound having one or more hydrolysable groups, optionally together with one or more other monomers copolymerisable therewith.

The unsaturated silane compound copolymerised with the ethylene, is preferably a compound having the general formula $\text{R}^4\text{SiR}^5_n\text{Y}_{3-n}$ wherein R^4 represents an ethylenically unsaturated hydrocarbyl or hydrocarbyloxy group; R^5 represents an aliphatic saturated hydrocarbyl group; Y represents a hydrolysable organic group; and n represents zero, 1 or 2. R^4 can be, for example, vinyl, allyl, isopropenyl, butenyl, cyclohexenyl or gamma-methacryloxypropyl. Y can be, for example, methoxy, ethoxy, formyloxy, acetoxy, propionyloxy, alkylamino or arylamino. R^5 can be, for example, methyl, ethyl, propyl, hexyl, octyl, decyl or phenyl. R^4 is preferably a vinyl group, Y is preferably methoxy, ethoxy or acetoxy. Preferred unsaturated silane compounds for use in making the copolymer are vinyl trimethoxy silane, vinyl triethoxy silane and vinyl triacetoxy silane.

The silyl copolymer suitably contains 0.1-10 weight %, preferably 0.5 to 5 weight % of copolymerised units of the unsaturated silane compound (based on copolymer).

The one or more other optional monomers copolymerisable with the ethylene and the unsaturated silane compound can be selected from, for example, vinyl esters, alkyl (meth)acrylates, olefinically unsaturated carboxylic acids or derivatives thereof and vinyl ethers. Examples of suitable (optional) copolymerisable monomers are vinyl acetate, vinyl butyrate, vinyl pivalate, methyl acrylate, ethyl acrylate, butyl acrylate, methyl methacrylate, methacrylamide, methacrylonitrile, vinyl methyl ether and vinyl phenyl ether. The quantity of the optional copolymerisable monomer present in the silane copolymer can be, for example, up to 40 weight %, preferably up to 25 weight % of copolymer.

The silane copolymer is preferably prepared by free radical initiated copolymerisation of the monomers. Preferably the copolymerisation is carried out under high pressure, for example, 500 to 4000 bars and at a temperature in the range 150 to 400°C. These polymerisation conditions are well known in the manufacture of conventional low density polyethylene (including ethylene/vinyl acetate and ethylene/ethyl acrylate copolymers) using autoclave or tubular reactors and such conventional polymerisation conditions and apparatus can generally be employed in the manufacture of the silyl copolymer.

For further details of the production of silyl copolymers suitable for use in the present invention reference may be made to GB-A-2028831, GB-A-2039513, US-A-3225018 and US-A-3392156.

The tin compound can be incorporated into the crosslinkable composition of the present invention using any of the blending or mixing techniques employed in the art. For example the tin compound can be mixed directly with solid pellet or granular silyl copolymer, optionally with other additives, and then melt blended or directly extruded to give crosslinkable products. A preferred method for incorporating the tin compound into the silyl copolymer employs a masterbatch technique. For example the tin compound is compounded with a thermoplastic polymer to form a masterbatch concentrate and the latter is then blended with the silyl copolymer. Examples of thermoplastic polymers suitable for preparing the masterbatch are LDPE, LLDPE, ethylene/ethyl acrylate copolymer and ethylene vinyl acetate copolymer. The masterbatch concentrate can also contain other additives which it is desired to incorporate into the final composition.

The composition of the present invention can contain additives conventionally employed in the art. Examples of such additives are antioxidants, fillers, metal deactivators (e.g. salicylaldehyde oximes), lubricants, water-tree inhibitors, foaming agents, flame retardants and pigments. Additives of this type are conventionally incorporated into the composition either directly or by a masterbatching technique. The composition can also be blended with other compatible polymeric materials, for example, polyethylene, polypropylene, ethylene/ethyl acrylate copolymer and ethylene/1-olefin copolymer.

In a particularly preferred embodiment of the present invention, the crosslinkable composition comprises the defined silyl copolymer and the defined silanol condensation catalyst together with a phosphorus compound containing at least one P-R group wherein R is a hydrogen atom or an organic substituent bonded to P (phosphorus atom) via a carbon or oxygen atom and wherein the phosphorus is trivalent or pentavalent, preferably trivalent. Examples of suitable classes of phosphorus compounds are organic phosphites, organic phosphonites, organic phosphines and organic phosphine oxides. Preferred compounds are trialkyl phosphites, for example tributyl phosphite, tri-n-hexyl phosphite, tri-iso-octyl phosphite, trionyl phosphite and di-iso-octyl phosphite. When such phosphorus compounds are employed in the composition of the present invention they are suitably present in an amount in the range 0.001 to 3.0, preferably 0.003 to 0.05 moles of silyl units in the silyl copolymer. Such phosphorus compounds can be incorporated in the crosslinkable composition, for example, by direct blending with the crosslinkable copolymer. It is preferred to incorporate the phosphorus compound into a masterbatch, for example together with the silanol condensation catalyst.

In a further aspect of the present invention the defined silanol condensation catalyst is absorbed on to a porous particulate solid material prior to blending into the composition. Examples of suitable porous particulate solid materials include silica, silica-alumina, alumina, magnesium oxide, magnesium carbonate, calcium carbonate, calcium phosphate, kieselguhr, celite, charcoal, pumice, fullers earth and the like. Preferably such materials are finely divided, e.g. have a mean particle diameter of not greater than 20 microns.

The composition of the present invention can be used to manufacture crosslinked products using the technology known in the manufacture of articles from conventional silane grafted polymers or silyl copolymers of this type. For example, the composition can be used in blow-moulding, injection-moulding, film-blowing, calendaring, extrusion, roto-moulding and extrusion-coating techniques. The composition is particularly preferred for wire and cable coating applications. Wire and cable insulation produced by extrusion coating using the composition of the present invention exhibits improved surface finish.

Articles fabricated from the composition of the present invention can be readily crosslinked by exposure to water, steam or moist air and, in general, relatively fast rates of cure are obtained. The defined silanol condensation catalyst containing dicarboxylic acid functions is generally less easily leached from the composition by the action of water than is the case with conventional silanol condensation catalyst.

The invention is illustrated in the following Examples.

Example and Comparative Test

The following ingredients were compounded together to make a masterbatch using a Werner and

Pfleiderer® ZSK 30 twin screw extruder at a screw speed of 200 revolutions per minute. The total quantity of composition prepared in the Example and in the Test was 10 Kg per run. The extruder barrel temperature was about 140°C close to hopper zone, increasing to about 190°C at the extruder head. Extrusion was carried out to give a strand which was chopped to give the pelleted masterbatch.

	<u>Parts by weight</u>	
	<u>Example</u>	<u>Comparative Test</u>
Ethylene/ethyl acrylate copolymer	93.25	93
Conventional antioxidant	6.0	6.0
Dibutyl tin (IV) maleate	0.75	-
Dibutyl tin (IV) dilaurate	-	1.0

The pelleted masterbatch (5 parts by weight) was dry blended with 95 parts by weight of a silyl copolymer prepared by copolymerising ethylene with vinyl trimethoxy silane under high temperature and high pressure conditions using a free radical initiator. The silyl modified polymer contained 1.8 weight % of copolymerised vinyl trimethoxy silane, had a melt index (190°C, 2.16 Kg load) of 0.7 and a density of 923 Kg/m³.

The dry blend was fed into the hopper of a Gottfert® extruder equipped with 25 mm screw having L:D of 23:1 and a 5 cm slot-casting die having a 3 mm die gap to produce an extruded tape. The die temperature was 210°C and the screw speed was 40 RPM. The extrudate was collected on a conveyor belt moving at a rate such that the tape thickness was maintained at 1.5 plus or minus 0.1 mm. The extruder tape was cured by immersion for 1 hr in a water bath thermostatted at 80°C. Visual examination of the tape produced using the composition of the present invention (Example) showed the tape relatively free from surface imperfections and defects caused by premature crosslinking (i.e. crosslinking during extrusion). Tape having similar characteristics continued to be extruded even after 1 hours extrusion time. On the other hand, tape produced from the composition of the Comparative Test exhibited substantial surface irregularity caused by premature crosslinking in the extruder.

Measurement of surface irregularities using a Tallysurf® machine gave a value of 1.2 units for the "Example" tape and 1.8 units for the Comparative Test tape thus confirming the results of the visual examination.

Claims

1. A crosslinkable composition comprising:

(A) A silyl copolymer prepared by copolymerising ethylene and an unsaturated silane compound having one or more hydrolysable groups, optionally together with one or more other monomers copolymerisable therewith, and

(B) A silanol condensation catalyst comprising a dihydrocarbyl tin (IV) carboxylate compound characterised in that the carboxylate units in the tin compound are provided by a dicarboxylic acid.

2. A crosslinkable composition as claimed in Claim 1 wherein the carboxylate units in the tin compound are provided by a dicarboxylic acid having the general formula HOOC.X.COOH wherein X is a divalent organic group which preferably contains 1-12, most preferably 1-6 carbon atoms.

3. A crosslinkable composition as claimed in Claim 1 wherein the silanol condensation catalyst is dibutyl tin(IV) maleate.

4. A crosslinkable composition as claimed in any one of the preceding claims wherein the quantity of tin compound employed is in the range 0.01 to 5 % by weight based on the weight of silyl copolymer in the composition.

5. A crosslinkable composition as claimed in any one of the preceding claims wherein the unsaturated silane compound is vinyl trimethoxy silane, vinyl triethoxy silane or vinyl triacetoxysilane.

Pfleiderer® ZSK 30 twin screw extruder at a screw speed of 200 revolutions per minute. The total quantity of composition prepared in the Example and in the Test was 10 Kg per run. The extruder barrel temperature was about 140°C close to hopper zone, increasing to about 190°C at the extruder head. Extrusion was carried out to give a strand which was chopped to give the pelleted masterbatch.

5

	<u>Parts by weight</u>	
	<u>Example</u>	<u>Comparative Test</u>
Ethylene/ethyl acrylate copolymer	93.25	93
Conventional antioxidant	6.0	6.0
Dibutyl tin (IV) maleate	0.75	-
Dibutyl tin (IV) dilaurate	-	1.0

15

The pelleted masterbatch (5 parts by weight) was dry blended with 95 parts by weight of a silyl copolymer prepared by copolymerising ethylene with vinyl trimethoxy silane under high temperature and high pressure conditions using a free radical initiator. The silyl modified polymer contained 1.8 weight % of copolymerised vinyl trimethoxy silane, had a melt index (190°C, 2.16 Kg load) of 0.7 and a density of 923 Kg/m³.

20

The dry blend was fed into the hopper of a Gottfert® extruder equipped with 25 mm screw having L:D of 23:1 and a 5 cm slot-casting die having a 3 mm die gap to produce an extruded tape. The die temperature was 210°C and the screw speed was 40 RPM. The extrudate was collected on a conveyor belt moving at a rate such that the tape thickness was maintained at 1.5 plus or minus 0.1 mm. The extruder tape was cured by immersion for 1 hr in a water bath thermostatted at 80°C. Visual examination of the tape produced using the composition of the present invention (Example) showed the tape relatively free from surface imperfections and defects caused by premature crosslinking (i.e. crosslinking during extrusion). Tape having similar characteristics continued to be extruded even after 1 hours extrusion time. On the other hand, tape produced from the composition of the Comparative Test exhibited substantial surface irregularity caused by premature crosslinking in the extruder.

25

30

Measurement of surface irregularities using a Tallysurf® machine gave a value of 1.2 units for the "Example" tape and 1.8 units for the Comparative Test tape thus confirming the results of the visual examination.

35

Claims

40

1. A crosslinkable composition comprising:

(A) A silyl copolymer prepared by copolymerising ethylene and an unsaturated silane compound having one or more hydrolysable groups, optionally together with one or more other monomers copolymerisable therewith, and

(B) A silanol condensation catalyst comprising a dihydrocarbyl tin (IV) carboxylate compound characterised in that the carboxylate units in the tin compound are provided by a dicarboxylic acid.

45

2. A crosslinkable composition as claimed in Claim 1 wherein the carboxylate units in the tin compound are provided by a dicarboxylic acid having the general formula HOOC.X.COOH wherein X is a divalent organic group which preferably contains 1-12, most preferably 1-6 carbon atoms.

50

3. A crosslinkable composition as claimed in Claim 1 wherein the silanol condensation catalyst is dibutyl tin(IV) maleate.

55

4. A crosslinkable composition as claimed in any one of the preceding claims wherein the quantity of tin compound employed is in the range 0.01 to 5 % by weight based on the weight of silyl copolymer in the composition.

5. A crosslinkable composition as claimed in any one of the preceding claims wherein the unsaturated silane compound is vinyl trimethoxy silane, vinyl triethoxy silane or vinyl triacetoxy silane.



6. A crosslinkable composition as claimed in any one of the preceding claims wherein the silyl copolymer contains 0.5 to 5 weight % of copolymerised units of the unsaturated silane compound (based on copolymer).
- 5 7. A process for preparing a crosslinkable composition by blending together components comprising:
 (A) A silyl copolymer prepared by copolymerising ethylene and an unsaturated silane compound having one or more hydrolysable groups, optionally together with one or more other monomers copolymerisable therewith, and
 (B) A silanol condensation catalyst comprising a dihydrocarbyl tin (IV) carboxylate compound
 10 characterised in that the carboxylate units in the tin compound are provided by a dicarboxylic acid.
8. A process as claimed in Claim 7 wherein the defined silanol condensation catalyst is incorporated in the composition as a masterbatch concentrate prepared by compounding the silanol condensation catalyst with a thermoplastic polymer, optionally together with other additives.
- 15 9. A process for manufacturing crosslinked articles comprising extruding the composition claimed in any one of claims 1 to 6 to form a shaped article and treating the article with hot water or steam to cause crosslinking.
10. Extrusion coated wire or cable manufactured by the process of Claim 9.

Revendications

- 25 1. Composition réticulable comportant :
 (A) un copolymère de silyle préparé par copolymérisation de l'éthylène et d'un composé du silane insaturé ayant un ou plusieurs groupes hydrolysables, éventuellement avec un ou plusieurs autres monomères copolymérisables avec lui, et
 (B) un catalyseur de condensation du silanol constitué d'un composé carboxylate de dihydrocarbylé-
 30 tain (IV), caractérisée par le fait que les unités de carboxylate dans le composé d'étain sont fournies par un acide dicarboxylique.
2. Composition réticulable comme revendiqué dans la revendication 1, dans laquelle les unités de carboxylate dans le composé d'étain sont fournies par un acide dicarboxylique de formule générale
 35 HOOC.X.COOH où X est un groupe organique divalent qui contient de préférence 1-12, de plus grande préférence 1-6 atomes de carbone.
3. Composition réticulable comme revendiqué dans la revendication 1, dans laquelle le catalyseur de condensation du silanol est le maléate de dibutylétain (IV).
- 40 4. Composition réticulable comme revendiqué dans l'une quelconque des revendications précédentes, dans laquelle la quantité du composé d'étain employé est entre 0,01 et 5% en poids sur la base du poids du copolymère de silyle dans la composition.
- 45 5. Composition réticulable comme revendiqué dans l'une quelconque des revendications précédentes, dans laquelle le composé de silane insaturé est le vinyltriméthoxy-silane, le vinyltriéthoxy-silane ou le vinyltriacétoxy-silane.
- 50 6. Composition réticulable comme revendiqué dans l'une quelconque des revendications précédentes, dans laquelle le copolymère de silyle contient de 0,5 à 5 % en poids d'unités copolymérisées du composé de silane insaturé (sur la base du copolymère).
7. Procédé de préparation d'une composition réticulable en mélangeant ensemble des composants comportant :
 55 (A) un copolymère de silyle préparé par copolymérisation de l'éthylène et d'un composé du silane insaturé ayant un ou plusieurs groupes hydrolysables, éventuellement avec un ou plusieurs autres monomères copolymérisables avec lui, et
 (B) un catalyseur de condensation du silanol constitué d'un composé carboxylate de dihydrocarbylé-



tain (IV), caractérisée par le fait que les unités de carboxylate dans le composé d'étain sont fournies par un acide dicarboxylique.

8. Procédé comme revendiqué dans la revendication 7, dans lequel le catalyseur de condensation du silanol défini est incorporé dans la composition sous forme d'un concentré formant un mélange maître préparé en combinant le catalyseur de condensation du silanol avec un polymère thermoplastique, éventuellement avec d'autres additifs.
9. Procédé de fabrication d'articles réticulés comportant le fait d'extruder la composition revendiquée dans l'une quelconque des revendications 1 à 6 pour former un article conformé et de traiter l'article à l'eau chaude ou à la vapeur pour en provoquer la réticulation.
10. Fil métallique ou câble revêtu par extrusion, fabriqué par le procédé de la revendication 9.

Ansprüche

1. Vernetzbare Zusammensetzung, umfassend:
 - (A) ein Silylcopolymer, hergestellt durch Copolymerisieren von Ethylen und einer ungesättigten Silanverbindung mit einer oder mehreren hydrolysierbaren Gruppen, wahlweise gemeinsam mit einem oder mehreren anderen damit copolymerisierbaren Monomeren und
 - (B) einen Silanolkondensationskatalysator, umfassend eine Dihydrocarbylzinn(IV)-carboxylatverbindung, welche dadurch gekennzeichnet ist, daß die Carboxylateinheiten in der Zinnverbindung von einer Dicarbonsäure stammen.
2. Vernetzbare Zusammensetzung nach Anspruch 1, worin die Carboxylateinheiten in der Zinnverbindung von einer Dicarbonsäure stammen, welche die allgemeine Formel $\text{HOOC} \cdot \text{X} \cdot \text{COOH}$ besitzt, worin X eine zweiwertige organische Gruppe darstellt, welche vorzugsweise 1 bis 12, am stärksten bevorzugt 1 bis 6 Kohlenstoffatome enthält.
3. Vernetzbare Zusammensetzung nach Anspruch 1, worin der Silanolkondensationskatalysator Dibutylzinn(IV)maleat ist.
4. Vernetzbare Zusammensetzung nach einem der vorherstehenden Ansprüche, worin die angewandte Menge an Zinnverbindung im Bereich von 0,01 bis 5 Gew.-%, bezogen auf das Gewicht des Silylcopolymeren in der Zusammensetzung, beträgt.
5. Vernetzbare Zusammensetzung nach einem der vorherstehenden Ansprüche, worin die ungesättigte Silanverbindung Vinyltrimethoxysilan, Vinyltriethoxysilan oder Vinyltriacetoxysilan ist.
6. Vernetzbare Zusammensetzung nach einem der vorherstehenden Ansprüche, worin das Silylcopolymer 0,5 bis 5 Gew.-% an copolymerisierten Einheiten der ungesättigten Silanverbindung (bezogen auf das Copolymer) enthält.
7. Verfahren zur Herstellung einer vernetzbaren Zusammensetzung durch Zusammenmischen von Komponenten, welche:
 - (A) ein Silylcopolymer, hergestellt durch Copolymerisieren von Ethylen und einer ungesättigten Silanverbindung mit einer oder mehreren hydrolysierbaren Gruppen, wahlweise gemeinsam mit einem oder mehreren anderen damit copolymerisierbaren Monomeren und
 - (B) einen Silanolkondensationskatalysator, umfassend eine Dihydrocarbylzinn(IV)-carboxylatverbindung, welche dadurch gekennzeichnet ist, daß die Carboxylateinheiten in der Zinnverbindung von einer Dicarbonsäure stammen, umfassen.
8. Verfahren nach Anspruch 7, worin der definierte Silanolkondensationskatalysator in die Zusammensetzung als ein Vorgemischkonzentrat einverleibt wird, welches durch Compoundieren des Silanolkondensationskatalysators mit einem thermoplastischen Polymer, wahlweise gemeinsam mit anderen Additiven, hergestellt wird.



9. Verfahren zur Herstellung von vernetzten Gegenständen, umfassend das Extrudieren der Zusammensetzung nach einem der Ansprüche 1 bis 6, um einen geformten Gegenstand auszubilden, und das Behandeln des Gegenstandes mit heißem Wasser oder Dampf, um das Vernetzen hervorzurufen.

- 5 10. Extrusionsbeschichtete Drähte oder Kabel, hergestellt durch das Verfahren nach Anspruch 9.

10

15

20

25

30

35

45

50

55

