

HIGH PERFORMANCE ULTRACAPACITORS WITH CARBON NANOMATERIALS AND IONIC LIQUIDS

STATEMENT REGARDING FEDERALLY SPONSORED

5 RESEARCH OR DEVELOPMENT

The U.S. Government has a paid-up license in this invention and the right in limited circumstances to require the patent owner to license others on reasonable terms as provided for by the terms of Contract Nos. DE-FG02-05ER84218 and DE-FG02-07ER84688 awarded by the Department of Energy and OII-0610919 awarded by the
10 National Science Foundation.

FIELD OF THE INVENTION

The invention relates generally to electrochemical devices and particularly to ultracapacitors.

BACKGROUND OF THE INVENTION

15 High performance energy storage devices are critical in advanced transportation technologies, e.g., electrical vehicles (EVs) and hybrid electrical vehicles (HEVs). This is extremely useful in achieving better fuel economy, decreasing harmful emissions, and reducing our nation's reliance on foreign sources of petroleum.

Ultracapacitors (aka, supercapacitors, Electrical Double-Layer Capacitor
20 (EDLC), or electrochemical capacitors) are being developed as power assists for HEVs. Ultracapacitors are energy storage devices which combine the high-energy storage potential of batteries with the high-energy transfer rate and high recharging capabilities of capacitors. Ultracapacitors can have orders of magnitude more energy density than conventional capacitors and power density than batteries. Generally, ultracapacitors
25 have energy densities in the range of about 1 to about 10 Wh/kg, which is about one-tenth of that of secondary batteries, which have energy densities of about 20 to about 100 Wh/kg and power densities in the range of about 1000 to about 2000 W/kg, which is about ten times higher than those of secondary batteries, which have power densities in the range of about 50 to about 200 W/kg.

30 Energy storage in ultracapacitors can be either Faradaic or non-Faradaic. A common type of Faradaic ultracapacitor is a redox ultracapacitor in which electrons are transferred across the electrode interface. Such ultracapacitors are based on mixed metal oxides, such as ruthenium dioxide and other transition metal oxides. For reasons of high

cost, scarcity, and toxicity of suitable metal oxides, Faradaic ultracapacitors are generally not preferred in most applications. In non-Faradaic ultracapacitors, no electron transfer takes place across the electrode interface, and the storage of the electric charge and energy is electrostatic. Positive and negative charges accumulate electrostatically on the electrodes at the electrode-electrolyte interface. Electrical energy is stored in the electric double layer from charge separation, *i.e.*, the electrostatic force between an ionically conducting electrolyte and a conducting electrode. The ions displaced in forming the double layers are transferred between electrodes by diffusion through the electrolyte.

In both Faradaic and non-Faradaic ultracapacitor systems, capacitance is dependent on the characteristics of the electrode material. Ideally, the electrode material should be electrically conducting and have a porous structure. The characteristics of the porous structure, including pore size, pore size distribution, and pore volume fraction, can enable the formation of a large amount of surface area that can be used either for the development of the electrical double layer for static charge storage to provide non-Faradaic capacitance or for the reversible chemical redox reaction sites to provide Faradaic capacitance.

A major obstacle to the applications of ultracapacitors to advanced HEVs is the limited performance (energy and power densities), unsafe operation, and short cycle life of ultracapacitors. These parameters are strongly determined by the poor properties of the currently employed electrode materials (*e.g.*, low electrolyte accessibility and low capacitance) and electrolytes (*e.g.*, narrow electrochemical window, flammability, toxicity, volatility, thermal instability, and electrolyte depletion).

There is thus a need for an ultracapacitor capable of providing high energy and power densities, safe operation, and long cycle lives. This will need improved properties for both the electrode and electrolyte materials over those employed in current ultracapacitor technology.

SUMMARY OF THE INVENTION

These and other needs are addressed by the various embodiments and configurations of the present invention. The present invention is directed generally to the use of Carbon NanoTubes (CNTs) and/or ionic liquid/polymer structures in various electrochemical devices, particularly ultracapacitors.

In a first embodiment of the present invention, an ultracapacitor is provided that includes:

(a) first and second electrodes, the first and second oppositely charged electrodes primarily comprising carbon nanotubes; and

5 (b) an electrolyte material, comprising oppositely charged ions, in contact with first ends of the first and second electrodes, with most, if not all, of the first ends of the carbon nanotubes being open to permit the charged ions to access interior surfaces of the nanotubes and the sizes of the ions being less than interior diameters of the carbon nanotubes.

10 The carbon nanotubes are preferably aligned nanotubes having lengths of about 75 microns or longer, inter-carbon nanotube spacings ranging from about 5 to about 1,000 nm, and diameters ranging from about 0.25 to about 250 nm.

Use of perpendicularly aligned CNTs as electrode materials can significantly improve capacitor performance. Perpendicularly aligned CNTs can provide an enhanced
15 specific surface area, improved charge transport capability, and excellent electrolyte accessibility, making them ideal electrode materials for high performance ultracapacitors.

Compared to randomly entangled CNTs, aligned CNTs can be better synthesized for ultracapacitor applications. Randomly entangled CNT-based electrodes are
20 commonly prepared by blending the CNTs with an insulating polymer binder (at 5~10 wt%), *e.g.*, poly(vinylidene fluoride), polytetrafluoroethylene, or poly(vinylidene chloride). The use of an insulating polymer can lower electrical conductivity of the resulting electrodes, leading to low performance for the capacitors. In contrast, aligned CNTs can be grown as a film perpendicularly on a substrate, including metal substrates,
25 without a polymer binder being required, thereby ensuring high electrical conductivity for the electrode. The aligned CNT structure should provide improved charge transport properties, as each of the constituent aligned CNTs can be connected directly onto a common electrode to maximize the charge mobility, *i.e.*, participation of each individual tube in the charge/discharge of the capacitor. This indicates a combined charge capacity
30 from all individual tubes of the aligned CNT electrode, and thus enhanced energy density for the capacitor. In turn, the stored energy can be delivered rapidly through each

individual tube of the electrode, thereby providing excellent power density for the capacitor.

Compared to randomly entangled CNTs, aligned CNTs can have better defined pore structures and higher specific surface areas. The surface area of randomly entangled CNTs is determined by the open space between entangled fibrils. Similarly, the surface area of aligned CNTs is determined by the open space between highly aligned tubes. The inter-CNT open space is in the range of tens of nanometers, indicating high mesoporosity and electrolyte accessibility. The aligned structure can provide a well-defined surface area for each of the constituent CNTs to be accessible to the electrolyte molecules, resulting in higher surface area for aligned CNTs. Moreover, under appropriate plasma conditions, the top end-caps of aligned CNTs can be properly opened without any observable structural change for the sidewalls. Once opened, the aligned structure allows access to the inner cavity of each of the constituent aligned CNTs collectively through a conducting substrate, thereby introducing additional mesoporosity to the electrode. The diameters of the opened tubes (up to tens of nanometers) are commonly larger than the sizes (ionic diameters) of the charged electrolyte ions. The well-defined alignment, in connection with the tip-opened structure, can impart to the aligned CNTs a higher specific surface area than that of randomly entangled CNTs. Higher specific surface area in turn translates into enhanced energy density for ultracapacitors.

Mesoporosity can be important to realizing high capacitance for the electrode and high performance for the ultracapacitor. As will be appreciated, the capacitance of conventional carbon-based electrodes decreases gradually with increasing discharging current density. This is so because currents, which are too large, may block the entrances of the micropores. Therefore, the energy stored can be withdrawn only at limited discharge rates and at low frequencies or by Direct Current (“DC”) techniques. In contrast, due to the high mesoporosity and enhanced electrolyte accessibility of aligned CNTs, fast charge injection and withdrawal are feasible for CNTs, meaning high capacitance at high frequencies. In other words, the overall enhanced mesoporosity (from both internal and external walls of tubes) and electrolyte accessibility of aligned CNTs can result in even higher capacitance and performance than capacitors fabricated from randomly entangled CNTs.

In a second embodiment, an ultracapacitor is provided that includes:

- (a) first and second carbon-based electrodes; and
- (b) a solid-phase electrolyte material comprising an ionic liquid and a polymer host, the polymer host forming a self-supporting film comprising the ionic liquid.

5 Preferably, the ionic liquid includes one or more cations selected from the group consisting essentially of pyridinium, pyridazinium, pyrimidinium, pyrazinium, imidazolium, pyrazolium, thiazolium, oxazolium, triazolium, ammonium, pyrrolidinium, pyrrolinium, pyrrolium, piperidinium, phosphonium, and mixtures thereof and one or
10 more anions selected from the group consisting essentially of F^- ; Cl^- ; Br^- ; I^- ; NO_3^- ; $N(CN)_2^-$; BF_4^- ; ClO_4^- ; PF_6^- ; RSO_3^- ; $RCOO^-$; where R is an alkyl group, substituted alkyl group, or phenyl group; $(CF_3)_2PF_4^-$, $(CF_3)_3PF_3^-$, $(CF_3)_4PF_2^-$, $(CF_3)_5PF^-$, $(CF_3)_6P^-$, $(CF_2SO_3^-)_2$, $(CF_2CF_2SO_3^-)_2$, $(CF_3SO_2^-)_2N^-$, $CF_3CF_2(CF_3)_2CO^-$, $(CF_3SO_2^-)_2CH^-$, $(SF_5)_3C^-$, $(CF_3SO_2)_3C^-$, $[O(CF_3)_2C_2(CF_3)_2O]_2PO^-$, $(CF_3(CF_2)_7$
15 SO_3^- , and mixtures thereof.

Preferably, the polymer host is selected from the group consisting essentially of homopolymers and copolymers of polyolefins, polystyrenes, polyvinyls, polyacrylics, polyhalo-olefins, polydienes, polyoxides/esters/acetal, polysulfides, polyester/thioesters, polyamides/thioamides, polyurethanes/thiourethanes,
20 polyureas/thioureas, polyimides/thioimides, polyanhydrides/thianhydrides, polycarbonates/thiocarbonates, polyimines, polysiloxanes/silanes, polyphosphazenes, polyketones/thioketones, polysulfones/sulfoxides/sulfonates/sulfoamides, polyphenylenes, and mixtures thereof.

The solid-phase electrolyte material can include a substantially nonconductive,
25 inorganic filler having a surface area of at least about $10\text{ m}^2/\text{g}$, a maximum dimension of about 50 micrometers, and an average pore size of less than about 10 micrometers.

In a third embodiment, a method is provided that includes the steps:

- (a) contacting a polymer host with an organic solvent to form a first composition;
- (b) contacting an ionic liquid with the first composition; and
- (c) removing at least most of the organic solvent from the first composition to
30 form a freestanding film comprising the polymer host and ionic liquid.

The polymer host is dissolved substantially in the first composition, and the organic solvent is removed from the first composition by heating the first composition to a selected temperature under a vacuum. The selected temperature is preferably higher than a boiling point of the solvent but lower than decomposition temperatures of the ionic liquid and polymer host.

In a fourth embodiment, a method is provided that includes the steps:

- (a) first forming a self-supporting polymer film comprising a host polymer.
- (b) second contacting the film with an ionic liquid; and
- (c) heating the film and ionic liquid, while in contact with one another, to a selected temperature above a glass transition temperature of the polymer host but below decomposition temperatures of the ionic liquid and polymer host to impregnate the polymer film with the ionic liquid.

The present invention can provide a number of advantages depending on the particular configuration. For example, the combination of an ionic liquid and a polymer host can provide environmentally friendly solid-state electrolytes suitable for use in high performance and stable electrochemical devices. Environmentally stable ionic liquids can have attractive properties, including high ionic conductivity, large electrochemical window, excellent thermal and chemical stability, non-volatility, non-flammability, non-toxicity, and negligible electrolyte depletion and are readily combinable with well-developed Gel Polymer Electrolyte (GPE) technology to provide an environmentally friendly, solid-state, Ionic Liquid-incorporated, Gel Polymer Electrolyte (ILGPE). Being solid-state, ILGPEs can possess distinct advantages over liquid electrolytes, including reduced reactivity, reduced leakage, improved safety, better shape flexibility, better processing characteristics, and better manufacturing integrity. In a conventional GPE, an organic solvent is needed as the plasticizer. In an ILGPE, the ionic liquid acts as both the salt and the solvent (plasticizer) without a conventional organic solvent. Absence of the environmentally unstable organic solvents in the ILGPE ensures the improved stability of ILGPEs over conventional GPEs. The combination of the unique properties of aligned CNTs (*e.g.*, high electrical conductivity, high specific surface area, high charge transport capability, and high electrolyte accessibility) as electrodes with the unique properties of environmentally friendly ionic liquids (*e.g.*, high ionic conductivity, large electrochemical window, excellent thermal stability, non-volatility, non-flammability, non-toxicity, and negligible electrolyte depletion) as electrolytes can

overcome the limitations of currently available ultracapacitors, achieve high performance and long cycle life, and are capable of delivering high power pulses that can satisfy the requirements for Hybrid Electric Vehicles (HEVs).

5 These and other advantages will be apparent from the disclosure of the invention(s) contained herein.

As used herein, the term "a" or "an" entity refers to one or more of that entity. As such, the terms "a" (or "an"), "one or more" and "at least one" can be used interchangeably herein. It is also to be noted that the terms "comprising", "including", and "having" can be used interchangeably.

10 "Alkyl" refers to monovalent alkyl groups preferably having from 1 to 8 carbon atoms and more preferably 1 to 6 carbon atoms. An alkyl group is typically a paraffinic hydrocarbon group, which may be derived from an alkane by dropping one hydrogen from the formula. Examples are methyl, ethyl, n-propyl, iso-propyl, n-butyl, iso-butyl, n-hexyl, and the like.

15 "Aryl" refers to an unsaturated aromatic carbocyclic group of from 6 to 14 carbon atoms having a single ring (for example phenyl) or multiple condensed rings (for example naphthyl or anthryl). Preferred aryls include phenyl, naphthyl, and the like.

The terms "at least one", "one or more", and "and/or" are open-ended expressions that are both conjunctive and disjunctive in operation. For example, each of
20 the expressions "at least one of A, B and C", "at least one of A, B, or C", "one or more of A, B, and C", "one or more of A, B, or C" and "A, B, and/or C" means A alone, B alone, C alone, A and B together, A and C together, B and C together, or A, B and C together.

An ionic liquid is generally understood to be a liquid composed almost entirely, if not completely, of ions. An ionic liquid commonly acts as both a salt and solvent or is
25 said to be 100% salt and 100% solvent. Ionic liquids are liquid even at low temperatures (<100 degrees Celsius), cannot decompose at high temperatures (> 400 degrees Celsius), and have relatively high viscosities.

"Polymer" refers to both polymers and copolymers. Copolymers include all polymers having more than one monomer type. Copolymers therefore include
30 terpolymers, tetrapolymers, and other polymers with multiple monomer types.

The preceding is a simplified summary of the invention to provide an understanding of some aspects of the invention. This summary is neither an extensive nor exhaustive overview of the invention and its various embodiments. It is intended

neither to identify key or critical elements of the invention nor to delineate the scope of the invention but to present selected concepts of the invention in a simplified form as an introduction to the more detailed description presented below. As will be appreciated, other embodiments of the invention are possible utilizing, alone or in combination, one or more of the features set forth above or described in detail below.

BRIEF DESCRIPTION OF THE DRAWINGS

Fig. 1 is a side view of an ultracapacitor according to an embodiment of the present invention;

Fig. 2 is an exploded view of a portion of an electrode of Fig. 1;

Fig. 3 is a Scanning Electron Microscope (SEM) image of perpendicularly aligned CNTs;

Fig. 4 is a high magnification SEM image of perpendicularly aligned CNTs of Fig. 3;

Fig. 5 is an SEM of randomly entangled CNTs;

Fig. 6 is an SEM of aligned CNTs after plasma-treatment to open the top end-caps of the CNTs;

Fig. 7 is an SEM of aligned CNTs before plasma-treatment showing the occluded top end-caps of the CNTs;

Fig. 8 is an exploded view of a portion of the ILGPE layer of Fig. 1;

Fig. 9 shows examples of ionic liquids based on various monocations;

Fig. 10 shows examples of ionic liquids based on various polycations;

Fig. 11 shows examples of polymer hosts;

Fig. 12 is a flowchart of a method to produce an ILGPE layer according to an embodiment of the invention;

Fig. 13 is a flowchart of a method to produce an ILGPE layer according to an embodiment of the invention;

Fig. 14 is a flowchart of a method to produce an ILGPE layer according to an embodiment of the invention;

Fig. 15 is a flowchart of a method to produce an ILGPE layer according to an embodiment of the invention;

Fig. 16 is a voltammogram of a PVdF-HFP/[EMIM][Tf₂N]/Zeolite film sandwiched between two stainless steel electrodes (the voltammogram being obtained by voltage scanning from 0 to 4.5 V at a scan rate of 20 mV/s);

Fig. 17 is a $Z' \sim Z''$ plot of a PVdF-HFP/[EMIM][Tf₂N]/Zeolite film sandwiched between two stainless steel electrodes (with the frequency range being 0.1 ~ 500K Hz and amplitude of sine wave being 5 mV);

Fig. 18 is a TGA graph of a PVdF-HFP/[EMIM][Tf₂N]/zeolite film (the
5 measurements being made in a N₂ purge);

Figs. 19A and B are, respectively, cyclic voltammogram and $Z' \sim Z''$ plot of an ultracapacitor fabricated from two activated carbon electrodes with aluminum foil as the current collector and a PVdF-HFP/[EMIM][Tf₂N]/Zeolite ILGPE (the thickness and density of the carbon layer of the electrode being 100 μm and 6 mg/cm^2 , respectively;
10 the effective size of the capacitor being $2 \times 2 \text{ cm}^2$, the scan rate for cyclic voltammetry being 20 mV/s, and the frequency range and amplitude of sine wave for AC impedance spectroscopy being 1mm Hz ~ 100 KHz and 5 mV, respectively;

Figs. 20A and B are, respectively, a galvanostatic charge/discharge of the same capacitor used in Figs. 19A and B obtained at the rate of 10 mA/cm^2 . and a Ragone plot
15 of the same capacitor obtained from charge/discharge testing at different rates of 2 ~ 50 mA/cm^2 ;

Figs. 21A and B are cyclic voltammograms of capacitors fabricated from [EMIM][Tf₂N]-containing ILGPEs (indicated on the graph) (with the voltage range being 0 ~ 3 V (Fig. 21A) and 0 ~ 4 V (Fig. 21B) and the scan rate being 20 mV/s);

Fig. 22 shows AC impedance spectra of the same capacitors used in Figs. 19A
20 and B (the spectra being recorded for all capacitors at open-circuit, using an AC voltage amplitude of 5mV and a frequency range of 1 mHz - 100 kHz);

Figs. 23A-C are galvanostatic charge/discharge profiles of the same capacitors used in Figs. 19A-B (with the charge/discharge current density being 10 mA/cm^2 and
25 cut-off voltage being 2.0V/4.0V);

Fig. 24 presents Ragone plots of the same capacitors used in Figs. 19A-B (with the charge/discharge current density being 2 ~ 50 mA/cm^2 and cut-off voltage being 2.0V/4.0V);

Figs. 25A-B present galvanostatic charge/discharge cycle life tests of a capacitor
30 fabricated from a PVdF-HFP/[EMIM][Tf₂N]/Zeolite ILGPE and two carbon electrodes (with the current density being 20 mA/cm^2 and cut-off voltage being 1.5V/3.0V);

Figs 26A-B are cyclic voltammograms obtained in [EMIM][Tf₂N] for aligned CNT electrodes without (a) and with (b) plasma etching on the CNT film (the scan rate being 20 mV/s and capacitance being indicated in the CVs);

Fig. 27 is a table listing ionic liquid structures and characteristics;

5 Fig. 28 provides Ragone plots of AC/IL and CNT/IL capacitors (with the charge/discharge current density being 2 ~ 50 mA/cm²);

Fig. 29 is a plot of capacitance (bottom) obtained in [EMIM][Tf₂N] for aligned CNT electrodes without and with plasma etching on one side and two sides of the CNT film;

10 Fig. 30 is a plot of capacitance versus scan rate showing the effect of scan rate on capacitance of aligned CNT electrodes obtained in different ionic liquids (data being from Figs. 28A-D);

Fig. 31 is a plot of Z'' against Z' providing AC impedance spectra obtained for aligned CNT electrodes in [EMIM][BF₄] (a), [EMIM][Tf₂N] (b), and [EMIM][CF₃SO₃] (c) and for an activated carbon electrode in [EMIM][Tf₂N] (d) (with AC voltage amplitude being 5mV, frequency range being 100K Hz-1 mHz, and the activated carbon electrode having a specific surface area of 1000~2000 m²/g and a thickness of 150μm);

15 Figs. 32A-C are CVs of aligned CNT electrodes obtained in [EMIM][BF₄] (Fig. 32A), [EMIM][Tf₂N] (Fig. 32B), and [EMIM][CF₃SO₃] (Fig. 32C) (with scan rate increasing from 5, 20, 50, to 100 mV/s as indicated by arrows);

Figs. 33A-B provide CVs (Fig. 33A) and capacitance (Fig. 33B) obtained for an activated carbon electrode in [EMIM][Tf₂N] (with scan rate increasing from 5, 20, 50, to 100 mV/s as indicated by arrows);

25 Figs. 34A-B provide CVs of an ultracapacitor fabricated from activated carbon electrodes and [EMIM][Tf₂N], AC/IL capacitor (with Fig. 34A being from 0~3V and Fig. 34B being from 0~4V and the scan rate increasing from 5, 20, 50, 100, to 200 mV/s as indicated by arrows);

30 Figs. 35A-B are CVs of an ultracapacitor fabricated from aligned CNT electrodes and [EMIM][Tf₂N], CNT/IL capacitor (with Fig. 35A being from 0~3V and Fig. 35B being from 0~4V and the scan rate increasing from 5, 20, 50, 100, to 200 mV/s as indicated by arrows);

Figs. 36A-B provide AC impedance spectra obtained for an AC/IL capacitor (a) and a CNT/IL capacitor (b) (the spectra being recorded for all capacitors at open-circuit AC voltage amplitude of 5mV and a frequency range of 100K Hz-1 mHz); and

5 Figs. 37A-C provide galvanostatic charge/discharge curves obtained for an AC/IL capacitor (Fig. 37A) and for a CNT/IL capacitor (Figs. 37B and C) (with the current density being 10 mA/cm² and cut-off voltage for charge/discharge being 2.0/4.0V (Figs. 37A and C) and 1.5/3V (Fig. 37B)).

DETAILED DESCRIPTION

10 An electrochemical device according to a first embodiment of the present invention is shown in Fig. 1. The device is a Faradaic or non-Faradaic ultracapacitor 100 comprising first and second current collectors 104a,b, anode 108, cathode 112, and Ionic Liquid-incorporated Gel Polymer Electrolyte (ILGPE) 116 positioned between the anode 108 and cathode 112. As will be appreciated, the ultracapacitor can be of other designs, including, without limitation, stacked and spiral-wound configurations. Additionally, the
15 anode and cathodes can act both as electrode and current collector, thus, eliminating the need for separate current collectors.

The first and second conductive collectors 104a,b are any highly conductive or superconductive material. Examples include conductive metals (*e.g.*, copper, aluminum, nickel, and stainless steel), superconductive ceramics, and the like.

20 The anode 108 and cathode 112 electrodes can be any material having relatively high degrees of electrolyte accessibility and high capacitance. The electrodes can be, for example, high-surface-area activated carbons or carbon nanotubes, transition metal oxides, and electroactive polymers. As noted, in carbon-based ultracapacitors the charge is stored in an electrical double layer formed at the interface between the electrolyte and
25 electrode (*i.e.*, double layer capacitance).

In a particularly preferred configuration, the electrodes are formed primarily from aligned or nonaligned single- or multi-walled carbon nanotubes, with aligned carbon nanotubes being preferred. Even more preferably, at least about 75% by volume of each electrode is formed from CNTs. The electrodes can also be formed by mixing CNTs
30 with high surface area activated carbons (ACs), forming the CNT/AC composite electrodes that combine the advantages of high electrolyte accessibility of CNTs and high surface area of ACs. This can deduce a high capacitance for the composite

electrodes. Moreover, an ionic liquid can be further introduced into this two-component system to fabricate a CNT/AC/IL composite electrode. Presence of the ionic liquid in the resultant three-component composite electrode can provide a facilitated ion transport pathway so as to further improve capacitance and charge delivery capability for the electrode. Carbon nanotubes are generally categorized as Single-Wall carbon NanoTubes (SWNT) and Multi-Wall carbon NanoTubes (MWNT). SWNT are fullerenes consisting essentially of sp^2 -hybridized carbon typically arranged in hexagons and pentagons. These carbon cylindrical structures, known commonly as "buckytubes," have extraordinary properties, including both high electrical and thermal conductivity, as well as high strength and stiffness. Multi-wall carbon nanotubes are nested single-wall carbon cylinders formed by rolling up additional graphene tubes around a core of an SWNT and possess some properties similar to single-wall carbon nanotubes.

Morphologically, CNTs can be produced in randomly entangled and aligned forms. By way of illustration, aligned CNTs 200 are depicted in Figs. 2 - 4. As can be seen from this figures, the longitudinal axes of the individual CNTs are substantially parallel to one another along substantially their entire lengths very much like the fibers on a brush. The longitudinal axes are normal or perpendicular to the planar interface between the electrode and ILGPE 116. In contrast, Fig. 5 shows randomly entangled CNTs 500 in which the longitudinal axes of the individual CNTs are not substantially parallel to one another along their entire lengths. SWNTs and MWNTs can provide high electrical conductivity, high surface area, high mesoporosity, and high electrolyte accessibility. As will be appreciated, mesopores (2 to 50 nm) are accessible by organic electrolytes and contribute the most to capacitance in an EDLC. While not wishing to be bound by any theory, it is believed that aligned or patterned CNTs (due to their well-defined spacing between tubes) are even more accessible by electrolytes, particularly organic electrolytes.

Compared to high-surface-area activated carbons, CNTs possess moderate specific surface area ($\sim 400 \text{ m}^2/\text{g}$ for randomly entangled CNTs). Nevertheless, much higher capacitance (up to 200 F/g) has been demonstrated for CNTs, in contrast to that of only tens of F/g for good activated carbons. Based on the commonly realizable charge densities of $20\sim 50 \mu\text{F}/\text{cm}^2$ for activated carbon-based EDLCs, the capacitance for CNT-

based EDLCs (using a CNT specific surface area of about $357 \text{ m}^2/\text{g}$) is normally at least about 70 F/g and more preferably ranges from about 71 to about 200 F/g.

To provide optimal results, the ends or tips of the CNTs are preferably removed by etching to “open up” the interior of the CNTs to the electrolyte, thereby effectively doubling the electrolyte-accessible surface area of the CNT-based electrode. Etching also purifies CNTs by eliminating residual catalysts. With etching CNTs can have an electrolyte-accessible surface area of at least about $800 \text{ m}^2/\text{g}$. Fig. 7 depicts CNTs prior to etching, and shows that the tips or ends are occluded. Fig. 6 shows CNTs after etching and shows that the ends or tips of the CNTs are opened. In the absence of etching, CNTs display low capacitance and impurity peaks due to the presence of residual catalysts. To provide effective electrolyte access, the diameters of the CNTs must exceed the molecular size(s) of the cations and anions in the electrolyte. In multi-layered CNTs, the annular space between the inner and outer CNT walls, or difference between the outer CNT diameter and inner CNT diameter, preferably is larger than the molecular size(s) of the cations and anions. Preferably at least one and more preferably both of the upper and lower surfaces 204 and 208 of each electrode are etched to remove substantially the tips or ends of at least most of the CNTs. Although etching one surface can increase the capacitance, it fails to remove substantially completely catalysts remaining from CNT fabrication. Etching both surfaces can not only further increase the capacitance but also remove, substantially completely, catalysts and other impurities.

The lengths of the CNTs influences the overall specific surface area of the CNTs and charge storage capability (capacitance) of the electrodes. The lengths “L” of the CNTs, or thickness of each electrode, preferably are at least about 75 microns and more preferably range from about 150 to about 200 microns. The inter-CNT spacing preferably ranges from about 5 to about 1,000 nanometers and even more preferably from about 10 to 500 of nanometers. The CNT diameter preferably ranges from about 5 to about 250 nm and even more preferably from about 10 to about 100 nm.

Carbon nanotubes can be made by known methods, such as by gas-phase synthesis from high temperature, high pressure carbon monoxide, catalytic vapor deposition using carbon-containing feedstocks and metal catalyst particles, laser ablation, the arc method, or any other method for synthesizing single-wall carbon nanotubes. Preferred methods are chemical vapor deposition to grow random CNTs and plasma-

enhanced chemical vapor deposition to grow aligned CNTs. The carbon nanotubes can be used as synthesized or after purification. Metals, such as Group VIB and/or VIIIB, are possible catalysts for the synthesis of carbon nanotubes. In one configuration, the CNTs are grown directly on conductive substrates, which are later used as the current collectors in the ultracapacitor.

Returning to Figs. 1 and 8, the ILGPE layer 116 includes an electrolyte, preferably an ionic liquid, 800 and a microporous and permeable polymer host 804. The polymer host 804 provides a structurally stable and solid carrier for the ionic liquid, thereby providing a solid-state ultracapacitor. The thickness of the layer 116 preferably is at least about 5 microns and preferably ranges from about 10 to about 200 microns. Alternatively, the layer 116 can be replaced by electrolytes other than ionic liquids, with or without the polymer host 804.

The ionic liquid can be any suitable electrochemically stable, water miscible and immiscible (with immiscible being preferred) ionic liquid having a relatively low melting point (*e.g.*, preferably less than about 100 degrees Celsius and more preferably no more than about -10 degrees Celsius), a relatively high decomposition temperature (*e.g.*, preferably greater than about 200 degrees Celsius and even more preferably greater than about 300 degrees Celsius), a low viscosity (*e.g.*, preferably no more than about 200Cp and even more preferably ranging from about 5 to about 150 Cp), a relatively high ionic conductivity (*e.g.*, preferably at least about 0.1, more preferably at least about 1, and even more preferably ranging from about 1 to about 100 mS/cm) and a wide electrochemical window (*e.g.*, preferably at least about 2 Volts, more preferably at least about 3 Volts, and even more preferably ranging from about 3.5 to about 10 Volts).

Fig. 9 shows examples of suitable ionic liquids based on various monocations, while Fig. 10 shows examples of suitable ionic liquids based on polycations. The R₁, R₂, R₃, R₄, R₅, and R₆ of the cationic components are identical or different and are preferably selected from the group consisting essentially of:

- (a) a hydrogen (-H)
- (b) a halogen (-Cl, -Br, -I, or -F)
- (c) a hydroxyl (-OH)
- (d) an amine (-NH₂)
- (e) a thiol (-SH)

- (f) a C₁ to C₂₅ straight-chain, branched aliphatic hydrocarbon radical
- (g) a C₅ to C₃₀ cycloaliphatic hydrocarbon radical
- (h) a C₆ to C₃₀ aromatic hydrocarbon radical
- (i) a C₇ to C₄₀ alkylaryl radical
- 5 (j) a C₂ to C₂₅ linear or branched aliphatic hydrocarbon radical having interruption by one or more heteroatoms, such as, oxygen, nitrogen or sulfur
- (k) a C₂ to C₂₅ linear or branched aliphatic hydrocarbon radical having interruption by one or more functionalities selected from the group
- 10 consisting essentially of:
- a carbonyl (–C(O)–)
 - an ester (–C(O)O–)
 - an amide (–C(O)NR'–), where R' selected from the group consisting essentially of hydrogen, C₁-C₁₂ straight-chain, branched
 - 15 or cyclic alkane or alkene
 - a sulfonate (–S(O)₂O–)
 - a sulfonamide (–S(O)₂NR'–), where R' selected from the group consisting essentially of hydrogen, C₁-C₁₂ straight-chain, branched
 - or cyclic alkane or alkene
- 20 (l) a C₂ to C₂₅ linear or branched aliphatic hydrocarbon radical terminally functionalized by Cl, Br, F, I, NH, OH, NH₂, NHCH₃ or SH
- (m) a C₅ to C₃₀ cycloaliphatic hydrocarbon radical having at least one heteroatom selected from the group consisting essentially of O, N, S, and optionally substituted with at least one of the following Cl, Br, F, I, NH,
- 25 OH, NH₂, NHCH₃ or SH
- (n) a C₇ to C₄₀ alkylaryl radical heteroatom selected from the group consisting essentially of O, N, S, and optionally substituted with at least one of the following
- a C₂ to C₂₅ straight-chain, branched hydrocarbon radical
 - 30 substituted with at least one of the following Cl, Br, F, I, NH, OH, NH₂, NHCH₃ or SH

- 5
- b. a C₅ to C₃₀ cycloaliphatic hydrocarbon radical substituted with at least one of the following Cl, Br, F, I, NH, OH, NH₂, NHCH₃ or SH
 - c. a hydroxyl
 - d. an amine
 - e. a thiol
- (o) a polyether of the type $-O-(R_7-O)_n-R_8$ or block or random type $-O-(R_7-O)_n-(R_7'-O)_m-R_8$ where
- 10
- a. R₇ is a linear or branched hydrocarbon radical having from 2 to 4 carbon atoms
 - b. R_{7'} is a linear or branched hydrocarbon radical having from 2 to 4 carbon atoms
 - c. n is from 1 to 40
 - d. R₈ is hydrogen, or a C₅ to C₃₀ straight-chain or branched
- 15
- hydrocarbon radical, or a C₅ to C₃₀ cycloaliphatic hydrocarbon radical, or a C₆ to C₃₀ aromatic hydrocarbon radical, or a C₇ to C₄₀ alkylaryl radical
- (p) a polyether of the type $-O-(R_7-O)_n-C(O)-R_8$ or block or random type $-O-(R_7-O)_n-(R_7'-O)_m-C(O)-R_8$ where
- 20
- a. R₇ is a linear or branched hydrocarbon radical having from 2 to 4 carbon atoms
 - b. R_{7'} is a linear or branched hydrocarbon radical having from 2 to 4 carbon atoms
 - c. n is from 1 to 40
 - d. R₈ is hydrogen, or a C₅ to C₃₀ straight-chain or branched
- 25
- hydrocarbon radical, or a C₅ to C₃₀ cycloaliphatic hydrocarbon radical, or a C₆ to C₃₀ aromatic hydrocarbon radical, or a C₇ to C₄₀ alkylaryl radical.

The anionic component is preferably selected from the group consisting essentially of:

- 30
- (a) halides, i.e., chloride, bromide, and iodide, preferably iodide
 - (b) phosphates
 - (c) halophosphates, preferably hexafluorophosphate

- (d) alkylated phosphates
- (e) nitrate
- (f) sulfates, i.e., hydrogen-sulfate
- (g) alkyl sulfates, preferably octyl sulfate
- 5 (h) aryl sulfates
- (i) perfluorinated alkyl sulfates
- (j) perfluorinated alkyl ether sulfates
- (k) halogenated alkyl sulfates
- (l) perfluorinated aryl sulfates
- 10 (m) perfluorinated aryl ether sulfates
- (n) sulfonates
- (o) alkylsulfonates
- (p) arylsulfonates
- (q) perfluorinated alkyl- and arylsulfonates, preferably triflate (or
- 15 trifluoromethane sulfonate)
- (r) perfluorinated alkyl ether and aryl ether sulfonates
- (s) halogenated alkyl- and arylsulfonates,
- (t) perchlorate
- (u) tetrachloroaluminate
- 20 (v) tetrafluoroborate
- (w) alkylated borates, preferably $B(C_2H_5)_3C_6H_{13}^-$
- (x) tosylate
- (y) saccharinate
- (z) alkyl carboxylates, and
- 25 (aa) bis(perfluoroalkylsulfonyl)amide anions, preferably the
- bis(trifluoromethylsulfonyl)amide anion, or is
- (bb) a mixture of two or more of these anionic species.

In one preferred embodiment of the polymer composition of the invention, the ionic liquid has halogen-free anions selected from the group consisting essentially of

30 phosphate, alkyl phosphates, nitrate, sulfate, alkyl sulfates, aryl sulfates, sulfonate, alkylsulfonates, arylsulfonates, alkyl borates, tosylate, saccharinate, and alkyl carboxylates, particular preference being given to alkyl sulfates, in particular octyl sulfate, and to tosylate.

In another preferred embodiment of the polymer composition of the invention, the ionic liquid has various anions and/or cations. The ionic liquids used by way of example as plasticizers may therefore be used individually or in a mixture in the polymer composition of the invention.

- 5 Ionic liquids based on polycations are formed when monocations are joined together; Fig. 10 shows monocations joined to form polycationic ring structures, where A_1 and A_2 are alkylene groups and substituted alkylene groups. The anion X^- includes, without limitation, but is not limited to, F^- ; Cl^- ; Br^- ; I^- ; NO_3^- ; BF_4^- ; $N(CN)_2^-$; BF_4^- ; ClO_4^- ; PF_6^- ; RSO_3^- ; $RCOO^-$, where R is an alkyl group; substituted alkyl group; phenyl
- 10 group; $(CF_3)_2PF_4^-$, $(CF_3)_3PF_3^-$, $(CF_3)_4PF_2^-$, $(CF_3)_5PF^-$, $(CF_3)_6P^-$, $(CF_2SO_3^-)_2$, $(CF_2CF_2SO_3^-)_2$, $(CF_3SO_2^-)_2N^-$, $CF_3CF_2(CF_3)_2CO^-$, $(CF_3SO_2^-)_2CH^-$, $(SF_5)_3C^-$, $(CF_3SO_2^-)_3C^-$, $[O(CF_3)_2C_2(CF_3)_2O]_2PO^-$, and $CF_3(CF_2)_7SO_3^-$. Preferably, the ionic liquid is a composition having at least one cation selected from the group consisting essentially of pyridinium, pyridazinium, pyrimidinium, pyrazinium,
- 15 imidazolium, pyrazolium, thiazolium, oxazolium, triazolium, ammonium, pyrrolidinium, pyrrolinium, pyrrolium, and piperidinium and at least one anion selected from the group consisting essentially of F^- ; Cl^- ; Br^- ; I^- ; NO_3^- ; $N(CN)_2^-$; BF_4^- ; ClO_4^- ; PF_6^- ; RSO_3^- ; $RCOO^-$; where R is an alkyl group, substituted alkyl group, or phenyl group;
- 20 $(CF_3)_2PF_4^-$, $(CF_3)_3PF_3^-$, $(CF_3)_4PF_2^-$, $(CF_3)_5PF^-$, $(CF_3)_6P^-$, $(CF_2SO_3^-)_2$, $(CF_2CF_2SO_3^-)_2$, $(CF_3SO_2^-)_2N^-$, $CF_3CF_2(CF_3)_2CO^-$, $(CF_3SO_2^-)_2CH^-$, $(SF_5)_3C^-$, $(CF_3SO_2^-)_3C^-$, $[O(CF_3)_2C_2(CF_3)_2O]_2PO^-$, and $(CF_3(CF_2)_7SO_3^-)$. Particularly preferred ionic liquids include 1-ethyl-3-methylimidazolium bis(trifluoromethylsulfonyl)imide ([EMIM][Tf₂N]).

- 25 The polymer host can be any thermoplastic or thermosetting polymer having a melting point of at least about 60 degrees Celsius and a high solubility in a selected low boiling point (organic) solvent. When thermosetting polymers are used, the polymer preferably cross-links at a temperature below the decomposition temperature of the ionic liquid and/or in response to ultraviolet light or heat. Thermosetting polymers, when cross-linked, form three-dimensional polymer networks through which the ionic liquid

can move. Cross-linked polymers do not crystallize and have the advantage of superior dimensional stability and mechanical strength. When thermoplastic polymers are used, the polymer preferably melts at a temperature above the decomposition temperature of the ionic liquid.

- 5 The polymer host can be any suitable high molecular weight polymer. Examples of suitable host polymers include homopolymers and copolymers of polyolefins, polystyrenes, polyvinyls, polyacrylics, polyhalo-olefins, polydienes, polyoxides/esters/acetals, polysulfides, polyesters/thioesters, polyamides/thioamides, polyurethanes/thiourethanes, polyureas/thioureas, polyimides/thioimides, 10 polyanhydrides/thianhydrides, polycarbonates/thiocarbonates, polyimines, polysiloxanes/silanes, polyphosphazenes, polyketones/thioketones, polysulfones/sulfoxides/sulfonates/sulfoamides, polyphenylenes, and mixtures thereof.

Preferred polymers are semicrystalline or amorphous polymers having no ionic groups. Examples of suitable host polymers are shown in Fig. 11. Particularly preferred 15 host polymers include:

- Polyoxides formed by the homo- or co-polymerization of alkylene oxides, $R'R''C(O)CR'''R''''$, where R' , R'' , R''' , and R'''' can separately be hydrogen and/or a C_1 - C_{18} linear or branch alkyl group, or a C_2 - C_{26} cyclic alkyl and/or aryl group, wherein the cyclic or aryl group can contain at least 20 hetero atom selected from the group consisting essentially of O, N and S and wherein the cyclic and/or acyclic alkyl group can be saturated or unsaturated. Preferred the linear or branched alkyl groups are C_1 - C_4 . The most preferred polyoxide is poly(ethylene oxide) (PEO).
- Polyacrylics formed by the homo- or co-polymerization of:
 - 25 ○ acrylic acid or its derivatives: $R'R''C=CR'''C(=O)OR''''$, and/or $R'R''C=CR'''C(=O)SR''''$, and/or $R'R''C=CR'''C(=O)NR''''R''''$; and/or
 - acrylonitrile, $R'R''C=CR'''CN$,
 where R' , R'' , R''' , R'''' , and R''''' can be hydrogen and/or a C_1 - C_{18} linear 30 or branch alkyl group, or a C_2 - C_{26} cyclic alkyl and/or aryl group, wherein the cyclic or aryl group can contain at least hetero atom selected from the group consisting essentially of O, N and S, and wherein the cyclic and acyclic alkyl

group may be saturated or unsaturated. Preferred linear or branched alkyl groups are C₁-C₁₂, and the more preferred are C₁-C₆ linear or branched alkyl groups. The most preferred are methyl methacrylate homopolymer and acrylonitrile homopolymer.

- 5 • Polyhalo-olefins formed by the homo- or co-polymerization of halogenated olefins, R'R''C=CR'''R''', where R', R'', R''', and R'''' that can independently be:
- a hydrogen,
 - a halogen,
 - 10 ○ a C₁-C₁₈ linear or branched, saturated or unsaturated, alkyl group that may be partially or fully halogenated,
 - a C₂-C₂₆ cyclic, saturated or unsaturated, alkyl group and/or aryl group, the cyclic alkyl or aryl group may be partially or fully halogenated.

15 A preferred linear or branched alkyl group is C₁-C₁₂ that can be partially or fully halogenated. The more preferred halogen is fluoride and the more preferred linear or branched alkyl group is C₁-C₁₂ that can be halogenated, wherein the alkyl group may be partially or fully halogenated. The most preferred are poly(vinylidene fluoride) where R' and R'' are hydrogen and R''' and R'''' are fluoride, and poly(vinylidene fluoride-co-

20 hexafluoropropylene), a co-polymer wherein one component is R' and R'' are hydrogen and R''' and R'''' are fluoride and the other component is R', R'', R''' are fluoride and R'''' is trifluoromethyl.

For any polymer formula "N" refers to the number of repeating units in the

25 polymer chain and typically is at least 25 and even more typically ranges from 50 to 50,000. "X" and "Y" is an integer value preferably in the range of 3 to 1,000. "X" and "Y" may, of course, have different values.

Particularly preferred polymer hosts include poly(ethylene oxide) (PEO), polyacrylonitrile (PAN), poly(methyl methacrylate) (PMMA), poly(vinylidene fluoride)

30 (PVdF), and poly(vinylidene fluoride-co-hexafluoropropylene) (PVdF-HFP), with PAN and PVdF-HFP being even more preferred. PAN and PVdF, have relatively high thermal stability. In addition, PVdF-based polymer electrolytes are highly anodically stable due

to the strongly electron-withdrawing functional group –C–F. PVdF co-polymerized with hexafluoropropylene (PVdF-HFP), can be used to improve the gel properties of the polymer electrolytes because of its greater solubility in organic solvents, lower crystallinity, and lower glass transition temperature than the PVdF polymer alone in the
5 gel.

In a preferred polymer composition, the mass ratios of ionic liquid to polymer host range from about 0.1:1 to about 1:1 and even more preferably from about 0.1:1 to about 10:1. Stated another way, the ILGPE layer 116 preferably comprises from about 9 to about 50 and even more preferably from about 9 to about 90 wt.% ionic liquid, with
10 the remainder being the polymer host.

The ionic liquid can include additives to provide more desirable electrochemical properties. By way of example, viscosity reducers can be added to the ionic liquid to lower viscosity and increase ionic conductivity for ILGPEs. Examples of potential viscosity reducers include propylene carbonate, ethylene carbonate, dimethylformamide,
15 and acetonitrile.

In an alternative configuration, the layer 116 includes an inorganic filler in addition to the ionic liquid and polymer host. The filler increases the mechanical strength of the ILGPE layer 116 and decreases the level of crystallinity of the polymer host. Introduction of inorganic fillers disrupts polymer chain packing (and crystallinity)
20 and thus enhances ionic conductivities for the ILGPE layer 116. The filler preferably has a high surface area (*e.g.*, preferably a surface area of at least about 10 and more preferably ranging from about 10 to about 500 m²/g) and electrochemical inertness (*e.g.*, is insulative or nonconductive) to avoid shorting the opposing electrodes. Preferred fillers include zeolites, metal oxides such as ZrO₂, TiO₂, and Al₂O₃, hydrophobic
25 fumed silica, fiberglass, silicates, cellulosic materials, lignin, diatomaceous earth, and mixtures thereof. At least most of the filler particles, and more preferably at least about 80% of the particles, have a particle size preferably not greater than about 50 microns. The particles have a preferred maximum dimension of about 50 micrometers, more preferably about 25 micrometer, even more preferably about 10 micrometers, and even
30 more preferably about 5 micrometers and a preferred average pore size of less than about 10 micrometers and more preferably of no more than about 5 micrometers. The pores preferably constitute from about 25 to about 95 percent by volume of the microporous

material. Preferably, the layer 116 comprises from about 9 to about 90 wt.% ionic liquid and from about 9 to about 90 wt.% polymer host, and from about 1 to about 10 wt.% of the filler particles.

5 The ILGPE layer 116 can have desirable properties. By way of example, the ionic conductivity of the layer 116 is preferably at least about 5 mS/cm at about 50 degrees Celsius and more preferably ranges from about 5 to about 50 mS/cm at about 50 degrees Celsius.

The various methods of manufacturing the ILGPE layer 116 will now be discussed.

10 Fig. 12 illustrates a method of manufacturing the layer 116 according to an embodiment of the invention. This method is hereinafter referred to as the ionic liquid-polymer gellation method.

In step 1200, the polymer host (preferably in powder form) is dissolved in a low-boiling point solvent under magnetic stirring. To effect rapid dissolution, the average or
15 mean particle size of the host preferably is no more than about 50 micrometers. The polymer host can be precipitated, spray-dried, or milled.

The solvent, or swelling agent, is preferably an organic solvent for the polymer host. The solvent preferably has a low boiling point, which is more preferably no more than about 200 degrees Celsius and even more preferably ranges from about 50 to about
20 200 degrees Celsius. Particularly preferred solvents include pyrrolidinone, acetone, dimethylformamide, acetonitrile, and tetrahydrofuran.

In step 1204 when the polymer host is fully dissolved in the solvent, the viscous solution is mixed with an appropriate amount of an ionic liquid under magnetic stirring to allow the gellation of polymer with the ionic liquid. As will be appreciated,
25 “gellation” of the polymer refers to the polymer chains being placed in a more disordered state, thereby occupying a greater volume than the volume of the undissolved, more highly ordered polymer host before step 1200.

In step 1208, the resultant mixture is processed by solution casting on a selected substrate, such as a glass plate.

30 In step 1212, the solvent cast mixture is heated under a dynamic vacuum to evaporate at least most, if not all, of the low boiling-point solvent to form an ILGPE layer 116. This heating process is preferably performed at a temperature higher than the

boiling point of the low-boiling point solvent but lower than the decomposition temperature of the ionic liquid and polymer host. The freestanding and self-supporting ILGPE film can be easily peeled off from the substrate for later assembly of the ultracapacitor.

5 Fig. 13 illustrates a method of manufacturing the layer 116 according to another embodiment of the invention. This method is hereinafter referred to as the ionic liquid-inorganic-polymer composite method. In this method, inorganic particulate fillers are introduced into the ILGPE to enhance the mechanical strength of the ILGPE system. Further, introduction of inorganic fillers can also decrease the level of polymer
10 crystallinity and thus enhance ionic conductivities for the polymer composite electrolytes.

 Similar to the ionic liquid-polymer gelation method described above, a polymer solution is prepared, in step 1300, by dissolving a polymer host in a low-boiling point solvent.

15 In step 1304, the resultant solution is mixed with an ionic liquid and an appropriate amount of inorganic particulate filler (appropriately in fine powder form) under magnetic stirring, ensuring the complete dispersion of the filler powder in the solution and the gelation of polymer with the ionic liquid.

 In step 1308, the resultant mixture is processed by solution casting on a selected
20 non-adhesive substrate.

 In step 1312, the solvent-cast film is heated under dynamic vacuum to evaporate at least most, if not all, of the low boiling point solvent to form an inorganic filler-embodied ILGPE film. This heating process is preferably performed at a temperature higher than the boiling point of the low-boiling point solvent but lower than the
25 decomposition temperatures of the ionic liquid and polymer host. The obtained ILGPE layer 116 can be peeled off easily from the substrate for later assembly of the ultracapacitor.

 In either of the above methods, when the polymer host is a thermosetting polymer the polymer is cross-linked while in the presence of the ionic liquid and/or filler. To
30 produce such ILGPEs, appropriate monomers are mixed with the selected ionic liquid, followed by cross-linking reactions. The ionic liquid molecules are trapped in the resulting cross-linked polymer structures. Suitable plasticizers and cross-linking agents

may be added to the mixture. For the cross-linking step, several methods, such as ultraviolet (UV) irradiation, electron-beam irradiation, and thermal polymerization, can be selected to initiate cross-linking.

Exemplary cross-linking monomers include acrylate monomers (e.g., ethylene glycol diacrylate, polyethylene glycol diacrylate, trimethylolpropane triacrylate, vinyl acetate, and divinyl adipate, 1,6-hexanediol diacrylate, 1,9-nonanediol diacrylate, 2-butyl-2-ethyl-1,3-propanediol diacrylate, 2-hydroxy 3-phenyloxy propyl acrylate, 2-hydroxyethyl acrylate, 2-hydroxypropyl acrylate, butoxy ethyl acrylate, behenyl acrylate, diacrylate of ethylene oxide modified bisphenol A, dipentaerythritol hexaacrylate, neopentyl glycol diacrylate, ethoxy diethyleneglycol acrylate, hexyl polyethyleneglycol acrylate, diethylene glycol diacrylate, isoamyl acrylate, isobornyl acrylate, lauryl acrylate, methoxy triethyleneglycol acrylate, neopentyl glycol diacrylate, tetraethylene glycol di(chloroacrylate), neopentyl glycol benzoate acrylate, PEG#200 diacrylate, PEG#400 diacrylate, PEG#600 diacrylate, perfluorooctylethyl acrylate, triethylene glycol diacrylate, phenoxy ethyl acrylate, diglycerol diacrylate, trimethylolpropane triacrylate, tetraethylene glycol diacrylate, phenoxy polyethyleneglycol acrylate, atearyl acrylate, tetrahydro furfuryl acrylate, triethyleneglycol diacrylate, triethyleneglycol diacrylate, trimethylpropane triacrylate, trimethylpropane benzoate acrylate, 2-ethylhexyl acrylate, butyl acrylate, can combinations thereof), methacrylate monomers (e.g., methyl methacrylate, ethylene glycol dimethacrylate, diglycerol tetramethacrylate, butylene glycol dimethacrylate, polyethylene glycol dimethacrylate, hexamethylene glycol dimethacrylate, diethylene glycol dimethacrylate, triethylene glycol dimethacrylate, tetraethylene glycol dimethacrylate, di(pentamethylene glycol) dimethacrylate, and combinations thereof)

Fig. 14 shows a further method according to an embodiment of the invention. In this method known as the ionic liquid-inorganic-polymer composite method, a pre-made microporous and permeable polymer separator is impregnated with a selected ionic liquid. The dispersion of the ionic liquid in the polymer composition occurs by means of diffusion. Preference is given to impregnation of polymer powders by an ionic liquid, and particular preference to impregnation of films, fibers, foams, or injection moldings, using auxiliaries, e.g., solvent.

Any microporous polymer membrane that is permeable to the selected ionic liquid may be employed. Examples of suitable membranes include battery and ultracapacitor separators, such as those sold by PPG Industries Inc. under the tradename Teslin™ (a microporous, highly filled polyethylene matrix sheet material),

5 EXCELLERATOR PTFE separators sold by W. L. Gore & Associates, Inc., Daramic Industrial CL™ (a microporous, highly filled polyethylene matrix sheet material) sold by Daramic, Inc., Solufill™ and Solupor™, both sold by DSM Solutech of the Netherlands and Teijin Fibers Limited of Japan, Tyvek™ (spun bonded polyethylene fibers) sold by E.I. du Pont de Nemours and Company, and the battery separator membranes sold by

10 Celgard, or by Daramic, Inc. under the tradename Artisyn™. Artisyn™ is an uncoated, mono-layer, highly filled polyolefin sheet. Other preformed microporous and permeable organic membranes, such polymer membrane separators designed for energy storage applications (*i.e.*, batteries and ultracapacitors), may also be employed.

In step 1400, the preformed, microporous and permeable polymer membrane is

15 contacted with the ionic liquid by placing the membrane in a bath of the ionic liquid.

In step 1404, the polymer membrane, while contacted with the ionic liquid or ionic liquid/solvent mixture, is heated at a temperature above the glass transition temperature of the polymer host in the membrane but below the decomposition temperatures of the ionic liquid and polymer host to directly swell/gell the polymer host

20 and form the ILGPE layer 116. Preferably, the temperature to which the membrane is heated is at least about 50 and more preferably ranges from about 50 to about 200 degrees Celsius. Swelling/gellation of the polymer membrane by the ionic liquid is enhanced at an elevated temperature and under dynamic vacuum. The vacuum is preferably at a pressure of no more than about -0.1 atm and more preferably ranges from

25 about -0.1 to about -1 atm. The vacuum can improve the uptaking of ionic liquid in the polymer network and thus enhance ionic conductivity of the resulting ILGPEs. Use of the dynamic vacuum can help the penetration of the ionic liquid into the depth of the polymer network and thus enhance ionic conductivity of the resulting ILGPEs.

In step 1408, the resultant ILGPE membrane is removed from the ionic liquid and

30 the excess ionic liquid on the membrane is removed, such as by hanging the membrane for a few minutes.

Fig. 15 depicts the process for assembling an ultracapacitor according to an embodiment of the invention.

In step 1500, the aligned CNTs are formed by known techniques to form the anode and cathode electrode layers 108 and 112.

5 In step 1504, the layers 108 and 112 are etched by suitable techniques to open up one or both of the ends of at least most of the CNTs. Etching can be performed by (oxygen) plasma etching and/or chemical etching techniques, with plasma etching being preferred.

10 In step 1508, the ultracapacitor is assembled by sandwiching the anode and cathode electrodes 108 and 112 and ILGPE layer 116 between current collectors 104a and b. Typically, the current collectors are sputter-coated onto the anode and cathode and a dry transfer method is used to transfer aligned CNTs from the substrate on which they are grown.

15 The ultracapacitors can have highly attractive properties. By way of example, the power density of the ultracapacitors can be at least about 10 kW/kg with an energy density of at least about 10 Wh/kg.

EXPERIMENTAL

20 An example of an ILGPE layer 116 was manufactured by the process of Fig. 12 using PVdF-HFP/[EMIM][Tf₂N]. PVdF-HFP was the polymer host, 1-methyl-2-pyrrolidinone (NMP) the low-boiling point solvent, and [EMIM][Tf₂N] the ionic liquid. PVdF-HFP is one of the polymers that have been most frequently used in conventional gel polymer electrolytes owing to its relatively high thermal stability. PVdF-based polymer electrolytes are expected to have high anodic stability due to the strong electron-withdrawing functional group –C–F. Furthermore, PVdF co-polymerized with
25 hexafluoropropylene (PVdF-HFP), can be used to improve the gel properties of the polymer electrolytes because of its greater solubility in organic solvents, lower crystallinity, and lower glass transition temperature than the PVdF polymer alone in the gel. First, 0.34 g of PVdF-HFP powder was dissolved in 1.7 ml of NMP under magnetic stirring for three hours. The resultant viscous polymer solution was then mixed with 0.8
30 ml of [EMIM][Tf₂N] under magnetic stirring for two hours to complete the polymer gellation with the ionic liquid. 0.4 ml of the obtained homogeneous polymer-solvent-ionic liquid mixture was then poured onto a piece of glass slide (6.25 cm²). Heating this

solution-containing glass slide at 110⁰C under dynamic vacuum (22 InHg) for fifteen hours completely evaporated the solvent NMP and formed a uniform and transparent PVdF-HFP/[EMIM][Tf₂N] film.

5 An example of an ILGPE layer 116 was manufactured by the technique of Fig. 13 using PVdF-HFP/[EMIM][Tf₂N]/Zeolite. Zeolite was the inorganic particulate filler. First, 0.34 g of PVdF-HFP powder was dissolved in 1.7 ml of NMP under magnetic stirring for three hours. The resultant viscous polymer solution was then mixed with 0.02 g of zeolite and 0.8 ml of [EMIM][Tf₂N] under magnetic stirring for two hours to complete the dispersion of zeolite powder in the solution and the gellation of the polymer
10 with the ionic liquid. 0.4 ml of the obtained homogeneous polymer-solvent-ionic liquid mixture was then poured onto a piece of glass slide (6.25 cm²). Heating this solution-containing glass slide at 110⁰C under dynamic vacuum (22 InHg) for fifteen hours completely evaporated the solvent NMP and formed a uniform and light brown PVdF-HFP/[EMIM][Tf₂N]/Zeolite film. The PVdF-HFP/[EMIM][Tf₂N]/Zeolite composite
15 ILGPE was a light brown rubbery film and was mechanically stronger than the ILGPE without zeolite. The zeolite was found to be uniformly distributed within the polymer gel. In this fashion, addition of inorganic particulate fillers to improve the mechanical strength of ILGPEs was demonstrated. Addition of zeolites into a conventional gel polymer electrolyte system consisting essentially of polyacrylonitrile, propylene
20 carbonate / ethylene carbonate, and LiAsF₆ resulted in the increase of ionic conductivity from 10⁻³ to 10⁻² S/cm, which is the highest so far in the field of polymer electrolytes.

An example of an ILGPE layer 116 was manufactured by the process of Fig. 14 using PTFE/[EMIM][Tf₂N] by directly gelling poly(tetrafluoroethylene) (PTFE) membrane (thickness: 23 μm, pore size: 0.05 - 15 μm, porosity: 50 - 70 %) obtained
25 from W.L. Gore & Associates with [EMIM][Tf₂N]. This was done by soaking a piece of PTFE membrane (2 × 2 cm²) in a 4 cm-diameter aluminum pan containing 0.5 ml [EMIM][Tf₂N], followed by heating the membrane (in the ionic liquid) at 110⁰C and under dynamic vacuum (22 InHg) for fifteen hours. The obtained ILGPE membrane was then taken out from the ionic liquid and hung for five minutes to exclude the excess of
30 the ionic liquid. Incorporation of ionic liquids into the polymer membrane can be improved by imbibing it at elevated temperature and under reduced pressure. This helps swelling/gelling the polymer membrane, enhancing the uptake of ionic liquid into the

polymer network, and thus increasing ionic conductivity for the resultant ILGPEs (up to 10^{-3} S/cm even at room temperature). Use of the dynamic vacuum can help the penetration of the ionic liquid into the depth of the membrane's pore network and thus enhance ionic conductivity of the resulting ILGPEs. Ionic conductivity of the resultant PTFE/[EMIM][Tf₂N] was 1.1×10^{-3} S/cm. As a comparison, a lower ionic conductivity of 5×10^{-4} S/cm was observed for the PTFE/[EMIM][Tf₂N] prepared using the similar procedure but without the use of heating during the gelling / swelling of polymer membrane with ionic liquid. This demonstrates the importance of an elevated temperature in improving the swelling of the polymer and the uptaking of the ionic liquid and thus the ionic conductivity of the ILGPE.

Electrochemical window, ionic conductivity, and thermal stability are important properties of electrolytes in determining the performance and lifetime of an electrochemical device. These properties were measured for a variety of ILGPEs. Electrochemical characterization included measurements of the ionic conductivity and electrochemical windows of ILGPEs by AC impedance spectroscopy using a cell that sandwiched the ILGPE film between two stainless steel electrodes. The cell consisted of two identical stainless steel electrodes (2cm $\times$ 2 cm for each) and a plastic spacer having a circular cut-out area of 0.785 cm² and a thickness of 0.0245 cm. Ionic conductivity of ILGPEs was measured by AC impedance spectroscopy with an AC voltage amplitude of 5 mV and a frequency range of 500 kHz $\sim$ 0.1 Hz. The real resistance Z' at the imaginary resistance $Z'' = 0$ was used to calculate ionic conductivity of the ILGPE according to $\sigma = t / (SZ')$ (t and S are thickness and area of the electrolyte between the two electrodes). The electrochemical window was measured by linear sweep voltammetry.

Ionic conductivities of a number of ILGPEs were measured. The results are summarized in Table 1 below in comparison with those of pure ionic liquids. It can be seen that ionic conductivities of all ILGPEs are lower than the pure ionic liquids. This is associated with the relatively slower ion movement in a gel polymer matrix than in the pure liquid form. Nevertheless, all ILGPEs show a reasonable conductivity of >1 mS/cm, which is believed to be sufficient for the fabrication of electrochemical devices. From the AC impedance spectra, a high ionic conductivity of $1 \sim 3.5 \times 10^{-3}$ S/cm was calculated for all ILGPEs tested.

Incorporation of zeolite in the PVdF-HFP/[EMIM][BF₄] system resulted in a further decrease of ionic conductivity for the resultant composite. Figs. 16-17 show the result for PVdF-HFP/[EMIM][Tf₂N]/Zeolite as the example. The polymer-ionic liquid-filler mixture solution of the PVdF-HFP/[EMIM][BF₄]/zeolite system was not as homogeneous as the PVdF-HFP/[EMIM][Tf₂N]/zeolite system. This may reflect a phase separation existing between the hydrophilic ionic liquid ([EMIM][BF₄]) and the hydrophobic filler (zeolite), hindering the ion movement and thus decreasing the ionic conductivity. By contrast, addition of zeolite in PVdF-HFP/[EMIM][Tf₂N] did not significantly change the ionic conductivity (but enhanced the mechanical strength) for the resulting composite ILGPE. Hydrophobicity of both the ionic liquid and the filler should be responsible for this observation, providing greater homogeneity of the mixture. Further optimization of the inorganic filler concentration in the composite system should lead to the improvement of conductivity.

The electrochemical windows of the ILGPEs were measured by linear sweep voltammetry. The results are summarized in Table 1 below. Fig.16 shows the voltammogram of PVdF-HFP/[EMIM][Tf₂N]/Zeolite as the example. As can be seen, upon the voltage scanning from 0 to 4.5 V, breakdown of the electrolyte begins at a voltage higher than 4.10 V. Below 4.10 V, the electrolyte is electrochemically stable, indicating a wide electrochemical window of 4.10 V of the PVdF-HFP/[EMIM][Tf₂N]/zeolite. All ILGPEs tested have a wide electrochemical window of 4 V or higher, showing their high electrochemical stability. This will allow the operation of ultracapacitors with a high cell voltage and thus high energy storage capacity for the ultracapacitors.

Table 1. Ionic conductivities and electrochemical windows of pure ionic liquids and ILGPEs.

Ionic liquid or resulting ILGPE	Ionic conductivity (mS/cm)	Electrochemical window (V)
[EMIM][BF ₄] (pure ionic liquid)	7.56	4.05
PVdF-HFP/[EMIM][BF ₄] (1 : 2.5)	3.44	4.02
PVdF-HFP/[EMIM][BF ₄]/Zeolite (1 : 2.5 : 0.06)	2.41	4.02
PTFE/[EMIM][BF ₄]	1.20	4.03
[EMIM][Tf ₂ N] (pure ionic liquid)	4.85	4.28
PVdF-HFP/[EMIM][Tf ₂ N] (1 : 2.5)	1.54	4.10
PVdF-HFP/[EMIM][Tf ₂ N]/Zeolite (1 : 2.5 : 0.06)	1.52	4.10
PTFE/[Tf ₂ N]	1.10	4.15

Thermal properties of ILGPEs were screened by performing selected measurements using Differential Scanning Calorimetry (DSC) and Thermal Gravimetric Analysis (TGA). Different instruments were used with common samples in order to identify any instrumental artifacts—none were determined to exist. The DSC was performed using either a TA DSC Q1000 or a PE Pyris 1 DSC. These measurements were made using “crimped” Al pans. The DSC was run to a maximum of 200°C with a low temperature (using liquid N₂) of 0°C or (-100°C for a few samples). Sample size was typically ~ 25 mg and runs had one heating cycle from room temperature, then a cooling cycle to 0°C (or lower), and then a final heating cycle using a 10°C/min ramp with a 1 minute hold at the end points. The TGA was performed using either a Sieko TG/DTA200 or a TA TGA Q500. In either case, the purge gas was N₂, the sample size was ~ 7 - 10 mg (Pt pans), and the TGA was performed between 30 - 700 °C using a 60 minute hold at the starting (for baseline stabilization) and end points and a heating rate of 5°C/min.

With respect to the calorimetry (DSC) results, it was found that during the first heating cycle a small, broad endotherm occurred between 80-120°C. This would be consistent with the TGA results and could be water being evaporated or, alternatively, a low order structural re-arrangement. The cooling cycle generated a small, broad exotherm usually in the range of 40-70°C. The second heating cycle was generally consistent with the first one. No glass transition-type events were identified. The ILGPE's based on the imbibed Gore-Tex[®] membrane (PTFE) were different than the others in that a small transition (perhaps the crystallization of PTFE) was identified and the broad endotherm between 80-120°C wasn't discerned—probably due to less water and no NMP, and consistent with the lowest mass loss (0.4%) observed in the TGA measurements. In general, the heat capacity of the samples decreased continuously as the temperature increased between 80 – 200°C. In general, the DSC measurements indicate some variations in the thermal transitions depending on whether the matrix was PVdF-HFP, PVdF-HFP + zeolite, or PTFE. The presence of the zeolite resulted in bimodal transitions and long continuous changes in the heat capacity as the temperature increased.

Thermal stability of ILGPEs was measured by thermogravimetric analysis (TGA) (mass loss resulting from increasing temperature) by measuring the weight loss of the gel with increasing temperature. Fig. 18 shows the TGA result of PVdF-

HFP/[EMIM][Tf₂N]/zeolite as an example. These indicated three main mass loss regimes. The first regime was between 30°C and 160°C, with the main transition occurring in the range of 80 to 110°C. In this transition ~0.4 to 5% of mass (depending on the specific sample) was lost. This transition is probably absorbed water and residual NMP solvent. A second regime occurs between 250 to 460°C. In this transition, the majority of mass is lost, with the total mass loss being on the order of 60-85% at this point. This transition is probably the breakdown (pyrolysis) and volatilization of the ionic liquids in each of the samples. The final regime is >450°C. In this transition, most of the remaining mass is released and is probably due to the breakdown (pyrolysis) of the polymer. The results showed that the main thermal decomposition/pyrolysis of these ILGPEs occurs in the range of 250-450°C with the majority above 350°C, indicating the high thermal stability of these ILGPEs.

These results support the contention that ILGPEs, especially [EMIM][Tf₂N] containing ILGPEs, are highly thermally stable gel polymer electrolytes and can be used at an elevated temperature up to 350°C. High thermal stability of these ILGPEs ensures the long lifetime and duration of electrochemical devices. Considering the commonly used operation temperature of about 60°C for HEVs, these ILGPEs are highly suitable for ultracapacitors for vehicular applications.

Application of ILGPEs to electrochemical devices was demonstrated by their use in the fabrication of ultracapacitors. The ultracapacitor was fabricated by sandwiching a piece of ILGPE with two identical activated carbon electrodes. Any type of ILGPEs discussed above can be used to fabricate the ultracapacitor. Each electrode had a size of 1.5 cm × 1.5 cm. Prior to use, the aluminum foil current collector of the electrode assembly was attached onto a polypropylene plate with epoxy. To ensure the good contact and low interfacial resistance between the electrode and the ILGPE of the capacitor, the electrodes were pretreated with the ionic liquid [EMIM][Tf₂N] prior to capacitor assembly. This was done by putting a small amount of ionic liquid on the electrodes and then placing the ionic liquid-containing electrodes under dynamic vacuum for two hours. The ionic liquid that was used for ILGPE synthesis was employed for electrode pretreatment. By doing this, gas bubbles were excluded from the depth of electrodes, and the ionic liquid can penetrate into the bulk of the electrode materials. Subsequently, the ultracapacitor was assembled by sandwiching the ILGPE with the two

ionic liquid-pretreated electrodes. Edges of the capacitor were sealed with epoxy. For PVdF-HFP/[EMIM][Tf₂N] and PVdF-HFP/[EMIM][Tf₂N]/Zeolite, one piece of the ILGPE (thickness: ~100 μm) was used directly as a separator for capacitor fabrication. However, four pieces of PTFE/[EMIM][Tf₂N] (thickness: 23 μm for each) needed to be stacked together to form the capacitor separator for that material. This minimized the difference in separator thickness between different capacitors. Capacitor testing included cyclic voltammetry, AC impedance spectroscopy, and galvanostatic charge/discharge.

Cyclic voltammogram of an ultracapacitor fabricated from two activated carbon electrodes and a PVdF-HFP/[EMIM][Tf₂N]/Zeolite ILGPE shows a rectangle shape (Fig. 19A, top), typical for a capacitor. Also, a cell voltage of up to 4 V can be determined from the cyclic voltammogram. Further, in the AC impedance measurement (Fig. 19B, bottom), capacitive behavior characterized by a nearly vertical line of the Z' ~ Z'' plot for the same cell has been confirmed. From the Z' ~ Z'' plot, a low effective series resistance (ESR) of about 5 Ω of the capacitor was determined, indicating the high conductivity of the ILGPE used and the low interfacial resistance between the electrode and the ILGPE.

Galvanostatic charge/discharge behavior of the same capacitor was investigated at different rates. An example charge/discharge curve obtained at the rate of 10 mA/cm² is shown in Fig. 20A (top). From the straight line portion of the discharge curve, energy density and power density of the capacitor at different rates were obtained (Fig. 20B (bottom)). In the range of discharge times of 3 ~ 30 seconds (the typical discharge time for HEVs), corresponding to the discharge rates of 10 ~ 40 mA/cm², a maximum energy density up to 20 Wh/kg and a maximum power density up to 7000 W/kg have been achieved.

As part of synthesis of ILGPEs, a preliminary screening of ionic liquids was performed in terms of their capacitor performance relative to the most frequently used conventional organic electrolyte (1M Et₄NBF₄/acetonitrile). Several ionic liquids covering the imidazolium, phosphonium, ammonium, and pyrrolidinium groups were tested. All ionic liquid-incorporated capacitors showed a classic rectangle-shaped cyclic voltammogram similar to that of the acetonitrile electrolyte-based capacitor. Better performance (energy and power densities) was obtained for the imidazolium group, which is believed to be due to their relatively higher ionic conductivity and lower viscosity than other groups. Electrolyte properties of imidazolium ionic liquids, 1-ethyl-

3-methylimidazolium tetrafluoroborate ([EMIM][BF₄]), 1-ethyl-3-methylimidazolium trifluoromethanesulfonate ([EMIM][CF₃SO₃]), and 1-ethyl-3-methylimidazolium bis(trifluoromethylsulfonyl)imide ([EMIM][Tf₂N]), in comparison with those of the acetonitrile electrolyte, as well as the performance of capacitors fabricated from these electrolytes are summarized in Table 2.

Table 2. Properties and capacitor performance of imidazolium ionic liquids and acetonitrile electrolyte

Electrolyte	Electrolyte property		Capacitor performance		
	Ionic conductivity (S/cm)	Viscosity (cp, at 20°C)	Maximum cell voltage (V)	Energy density (Wh/kg)	Power density (W/kg)
[EMIM][BF ₄]	7.56	151.7	4.0	20.4	2302.8
[EMIM][CF ₃ SO ₃]	4.54	51.7	4.0	10.0	2108.1
[EMIM][Tf ₂ N]	4.85	28.0	4.0	27.5	2316.5
1M Et ₄ NBF ₄ /acetonitrile	15.45	~2	2.3	7.8	1418.3

Maximum cell voltage was determined by cyclic voltammetry (scan rate: 20 mV/s). Energy and power densities were determined by galvanostatic charge/discharge (current density: 10 mA/cm²). Cut-off voltage for charge/discharge: 2.0V/4.0V for ionic liquid capacitors, 1.15V/2.3V for acetonitrile capacitor.

Capacitors incorporating imidazolium ionic liquids showed higher performance than the acetonitrile capacitor. This was mainly due to the wider electrochemical window of the ionic liquids, thus allowing higher cell voltages for the capacitor. Having the highest ionic conductivity, but also highest viscosity in the imidazolium group, [EMIM][BF₄] exhibited a moderate performance. Lower viscosity and ionic conductivity provided lower performance for [EMIM][CF₃SO₃]. The highest performance was achieved for [EMIM][Tf₂N], the ionic liquid that had the lowest viscosity among all ionic liquids reported so far. This implies that viscosity of an ionic liquid plays a more important role than its conductivity in determining capacitor performance. It is likely that the lower viscosity of an ionic liquid reduces the interfacial resistance between the electrode and the electrolyte, facilitating the ion transport into and out of the electrical double layer, and thus enhancing the performance for a capacitor.

Testing demonstrated that capacitors incorporating [EMIM][Tf₂N]-containing ILGPEs showed better performance than those incorporating [EMIM][BF₄]-containing ones, which is consistent with the results observed for capacitors fabricated from the liquid form of ionic liquids (Table 2). This indicates that regardless of the form (either liquid or polymer gel) of the electrolyte, viscosity of an ionic liquid plays a more important role than its ionic conductivity in influencing capacitor performance. Having lower viscosity, [EMIM][Tf₂N] based ILGPE electrolytes produced higher performance

for the capacitors. Because of its highest capacitor performance, [EMIM][Tf₂N] was selected as the primary ionic liquid for the synthesis of ILGPEs. Moreover, combining these electrokinetic attributes with the attractive properties including water immiscibility and high decomposition temperature (400⁰C), [EMIM][Tf₂N] promises to be a good electrolyte for ultracapacitors for vehicular applications.

The capacitors showed well-defined cyclic voltammograms characterized with a rectangle shape (Fig. 21 A (left)), indicating their typical capacitor behavior. Maximum cell voltages of these capacitors were determined to be 4 V (Fig. 21B (right)), consistent with electrochemical windows of ILGPEs (Table 1). Shape and current magnitude of voltammograms of these ILGPE-incorporated capacitors were similar to those (not shown) of the capacitors fabricated from the liquid form of the ionic liquid [EMIM][Tf₂N], suggesting that the ionic liquid functions well in the polymer network of an ILGPE in the capacitor. Capacitive behavior of these ILGPE-incorporated capacitors can be confirmed by AC impedance spectra (Fig. 22), showing nearly-vertical lines at low frequencies, typical phenomenon for capacitors.

Furthermore, these ILGPE-incorporated capacitors were subjected to galvanostatic charge/discharge tests at different current densities of 2 - 50 mA/cm². Figs. 23 A-C show the charge/discharge curves of capacitors obtained at 10 mA/cm². They are similar to that (not shown) of a capacitor fabricated from the liquid form of ionic liquid EMIM][Tf₂N]. From linear portion of the discharge curves, energy and power densities for all capacitors were calculated and summarized in Table 3 below. As can be seen, relatively lower performances were obtained for ILGPE-incorporated capacitors. This should be associated with the relatively lower ionic conductivity of ILGPEs compared to that of pure ionic liquids (Table1) and the more difficult transport of electrolyte ions within a solid-state polymer network of the ILGPE and/or between the ILGPE and the electrode. Nevertheless, these figures-of-merit are still promising for solid-state-electrolyte-based capacitors, especially when considering the overall advantages of the solid-state electrolytes over liquid ones such as reduced reactivity, reduced leakage, improved safety, better shape flexibility, better processing characteristics, and better manufacturing integrity.

Table 3. Performance of capacitors fabricated from [EMIM][Tf₂N] in liquid form and in polymer gels.

Electrolyte	Energy density (Wh/kg)	Power density (W/kg)
[EMIM][Tf ₂ N] (pure ionic liquid)	27.5	2316.5
PTFE/[EMIM][Tf ₂ N]	16.7	2277.3
PVdF-HFP/[EMIM][Tf ₂ N]	13.3	2280.0
PVdF-HFP/[EMIM][Tf ₂ N]/zeolite	20.2	2272.5

Capacitor performance was obtained at the current density of 10 mA/cm². Cut-off voltage: 2.0V/4.0V.

5 Typical Ragone plots of ILGPE-incorporated capacitors obtained using the current densities of 2 - 50 mA/cm² are shown in Fig. 24. Upon discharge at the highest rate of 50 mA/cm², resulting in a very short discharge period of 0.8 - 1.5 seconds, very high power densities of 9,000 ~ 9,900 W/kg were obtained for these capacitors. Practically, regarding the discharge times of 3 - 30 seconds (the typical range for HEVs),
10 a maximum energy density and a maximum power density were obtained (Table 4). It should be noted that the present research was focused on the synthesis of ILGPEs and demonstration of their application in ultracapacitors. Optimization of electrode materials and capacitor packaging materials was not studied. Capacitor performance for the ILGPEs was evaluated based on the mass of the active material (carbon) of electrodes
15 rather than overall weight of the packaged capacitor. Based on a simplified estimation method, the active-material-based performances can be converted (multiplying by a factor of 0.35) to the performances for a packaged capacitor (Table 4). The results exceed the performance metrics (4 - 5 Wh/kg, 1,000 - 1,800 W/kg) of currently available ultracapacitors. Again, the wider electrochemical window of ionic liquids over
20 conventional organic electrolytes, and thus the larger maximum cell voltages for such capacitors, is the primary cause for this observation.

Table 4. Maximum energy and power densities of ultracapacitors fabricated from ILGPEs.

ILGPE	Maximum energy density (Wh/kg)	Maximum power density (Wh/kg)	Maximum energy density for packaged cell* (Wh/kg)	Maximum power density for packaged cell* (Wh/kg)
PTFE/[EMIM][Tf ₂ N]	17	8120	6	2842
PVdF-HFP/[EMIM][Tf ₂ N]	15	7000	5	2450
PVdF-HFP/[EMIM][Tf ₂ N]/zeolite	20	7791	7	2727

25 *Estimated by multiplying the active-material-based performances by a factor of 0.35

Finally, we performed a preliminary cycle life test for an ILGPE-incorporated capacitor. Based on the fact that all capacitors made in the current work were fabricated in ambient air, the presence of moisture and oxygen in the cell may limit the maximum cell voltage of the capacitor. Therefore, for the proof-of-concept, we cycled the capacitor using a relatively low voltage of 3 V. As shown in Fig. 25, after an initial decrease of ~20% in the first 2000 cycles, the energy remained stable. The power was fairly stable over the entire time tested. The test was stopped at the 100,000th cycle. The excellent cycle life achieved indicates the possibly longer cycles of the ILGPE-based capacitors. Moreover, careful fabrication of capacitors in a dry glove box will allow the capacitors to be cycled to a higher cell voltage of 4 V.

The above promising results prompted the construction of prototype ultracapacitors using plasma-etched, aligned CNTs as the electrodes and selected ionic liquids as the electrolyte. Activated carbon (AC) electrodes and the same ionic liquids were used to fabricate capacitors as reference for evaluating the CNT capacitors.

Aligned CNT arrays were synthesized by vacuum chemical vapor deposition on SiO₂/Si wafers as described elsewhere. Controlling the reaction time and pressure during synthesis of aligned CNTs, properties of the nanotubes could be adjusted. For the ultracapacitor study in this work, aligned CNT film electrodes with the nanotube specifications of the tube length of 150 ~ 200 μm , tube diameter of 10 ~ 15 nm, and spacing of tens to hundreds of nanometers were obtained. A gold layer was deposited to the (upper) tube tips of the aligned CNT film and the resulting CNT / gold assembly was physically removed from the silicon wafer using a commercially available double-sided conducting tape. Finally, water or oxygen plasma etching was applied on the CNT film. After the plasma etching, the amorphous carbon layer that covers the CNT film can be properly removed without damaging the CNTs. Prolonged plasma treatment was able to cause a controllable disintegration of the graphitic structure, leading to the opening of some CNT end-caps.

Electrochemical and capacitive behavior of aligned CNT electrodes in ionic liquids was investigated using a PGSTAT30 potentiostat purchased from Eco Chemie B.V. The measurements were performed in a three-electrode electrochemical cell consisting essentially of the aligned CNT electrode ($0.5 \times 0.5 \text{ cm}^2$) as the working electrode, a platinum wire (1.5 mm diameter) as the auxiliary electrode, and a silver wire

(1.5 mm diameter) as the quasi-reference electrode. Investigation was also performed for an activated carbon electrode (specific surface area: 1000 ~ 2000 m²/g, thickness: 150 μm) that is currently employed for commercial supercapacitors. Ionic liquids 1-ethyl-3-methylimidazolium tetrafluoroborate ([EMIM][BF₄]), 1-ethyl-3-methylimidazolium trifluoromethanesulfonate ([EMIM][CF₃SO₃]), and 1-ethyl-3-methylimidazoliumbis(trifluoromethylsulfonyl)imide ([EMIM][Tf₂N]) were purchased from Sigma-Aldrich.

Electrochemical and capacitive behavior of the aligned CNTs in the ionic liquid was determined by the properties of both the aligned CNTs and the ionic liquids. First of all, plasma etching was demonstrated to be important in improving the charge capacity and charge storage/delivery capability for the aligned CNT electrodes. Without etching, the CNT electrode showed a low current (Fig. 26). After etching, the current magnitude of the CNT electrode increased significantly. It has been demonstrated previously that plasma etching can properly remove the amorphous carbon layer that covers the CNT film without damaging the CNTs. Electrochemically, this indicates the exposure of the open (loosely-packed) nanostructure of the CNTs to the electrolyte. Consequently, well-defined spacing (tens to hundreds of nanometers) of the CNTs ensures an intimate contact between the nanotubes and the electrolyte ions resulting in improved capacitance for the CNT electrode. Further, prolonged plasma treatment was able to cause a controllable disintegration of the graphitic structure, leading to the opening of some CNTs on the end-caps. Given the fact that diameters (10 ~ 15 nm) of these tubes are larger than the ionic diameters of the ionic liquids (see table of Fig. 27), the internal walls of the opened tubes of the CNTs are electrochemically accessible to the electrolyte. These factors resulted in an enhanced overall surface area and enhanced electrolyte accessibility and thus improved capacitance for the CNT electrode from 35 F/g to 440 F/g, after etching, clearly demonstrating the significant enhancement of plasma etching.

Furthermore, the results demonstrated that the plasma etching technique is also useful in removing loosely-bonded catalysts from the CNT film surface. As shown in (Fig. 6), after etching, an open (loosely-packed) nanostructure has been achieved for the CNT film. Thus, well-defined spacing ensures an intimate contact between the CNTs and the electrolyte ions, resulting in improved capacitance for the CNT electrode. Further, prolonged plasma treatment was able to cause a controllable disintegration of

the graphitic structure, leading to the opening of some CNTs on the end-caps. Given the fact that diameters (10 ~ 15 nm) of these tubes are larger than the ionic diameters of the ionic liquids (Fig. 27), the internal walls of the opened tubes of the CNTs can be electrochemically accessible to the electrolyte. This improves the overall specific surface area and introduces additional charge capacity to the electrode. Moreover, etching on both sides of the CNT film can further improve the charge capacity for the CNT electrode. As shown in Fig. 29, after etching on both sides, the CNT electrode shows a capacitance two times higher than that of a one-side etched electrode and more than ten times higher than that of an untreated electrode, clearly demonstrating the significance of etching. Without etching, the appearance of some CV peaks of a CNT electrode (Fig. 26A) may be attributed to the presence of residual catalyst materials in the CNTs. Etching effectively removes these loosely-bonded catalysts from the CNTs and thus ensures a stable electrochemical behavior for the CNT electrode. Therefore, plasma etching was used for preparing all of the aligned CNT film electrodes in the following work.

Electrolyte choice is another important factor in determining the electrochemical and capacitive behavior of the CNTs. Among five groups of ionic liquids (imidazolium, pyridinium, pyrrolidinium, phosphonium, and ammonium), the imidazolium group was selected because of its relatively higher ionic conductivity and lower viscosity (two important properties for electrochemical applications). Further, in the imidazolium group, three ionic liquids (having the best combination of large electrochemical window, high ionic conductivity, and low viscosity) that have been tested in the above ultracapacitor research, were selected. Physical properties of these ionic liquids are summarized in Fig. 27.

Similar butterfly-shape CVs were obtained for aligned CNT electrodes in all three ionic liquids (Fig. 32). Capacitive behavior of CNTs was determined by the combined effect of viscosity, ionic conductivity, and ion size of the ionic liquids. For example, [EMIM][BF₄] has the highest viscosity, thus, its higher ionic conductivity and smaller anion size (Fig. 27) is important in facilitating the transport of ions into the double layer of the CNT electrode. In contrast, the most important factor of [EMIM][Tf₂N] is its low viscosity, the lowest among all three ionic liquids. Low viscosity of [EMIM][Tf₂N] offsets the negative effect from its relatively lower ionic conductivity and the larger anion size. With moderate viscosity and anion size, [EMIM][CF₃SO₃] also

produced a similar capacitance for CNTs. However, the less symmetric CV and the slower transient response at both ends of the CV in [EMIM][CF₃SO₃] suggest a slow charge/discharge process of CNTs in this ionic liquid. Due to this slow process, a pronounced decrease in capacitance of CNTs has been observed in [EMIM][CF₃SO₃] upon the increase of scan rate. In contrast, a fairly stable capacitance was observed for the CNTs in [EMIM][BF₄] and [EMIM][CF₃SO₃] upon increasing the scan rate up to 100 mV/s, indicating the fast charge/discharge process of CNTs in these two ionic liquids (Fig. 30).

Capacitive behavior of CNTs in these ionic liquids was also investigated using AC impedance spectroscopy (Fig. 31). CNTs show a vertical line at low frequencies in all ionic liquids, a typical capacitive phenomenon, indicating that all ionic liquids functioned well as electrolytes for the CNTs. Steeper lines obtained in [EMIM][BF₄] and [EMIM][Tf₂N] suggest the better capacitive performance of CNTs in these two ionic liquids (Table 5). However, the more shallowly sloping line in [EMIM][CF₃SO₃] indicates its relatively poor capacitive behavior. At high frequencies, a 45° Warburg region, the consequence of the distributed resistance in a porous electrode, was observed for all ionic liquids. This 45° Warburg region expands following an order of [EMIM][BF₄] < [EMIM][Tf₂N] < [EMIM][CF₃SO₃], indicating the increase of the distributed resistance of the CNTs in these ionic liquids according to this order. In the cell set-up for this experiment, it was difficult to maintain a constant distance between the CNT electrode and the Pt wire auxiliary electrode, making it difficult to compare ESR (effective series resistance, *i.e.*, the combination of electrolyte resistance, electrode resistance, and contact resistance) in different ionic liquids. However, EDR, the equivalent distributed resistance related to ion transport at the electrode interface, is a good indicator to measure the ion transport behavior at the electrode/electrolyte interface of the CNTs in different ionic liquids. A low EDR would be expected for a fast/easy ion transport at the electrode/electrolyte interface. This suggests that the ease of ion transport at the CNT/ionic liquid interface follows the order of [EMIM][BF₄] > [EMIM][Tf₂N] > [EMIM][CF₃SO₃] (Table 5). Accordingly, a higher ionic resistance (interfacial resistance between the electrode and the ionic liquid) due to the slower/more difficult transport of ions at the CNTs is confirmed in [EMIM][CF₃SO₃]. This will result in a low charge storage/ delivery capability for the CNTs in this ionic liquid. Moreover, a frequency “knee” can be used to evaluate the frequency dependence of a capacitor

material. At a frequency higher than the “knee”, the real part of the impedance is frequency dependent and very small capacitance will be obtained. At a frequency below this value, the resistance changes weakly with frequency and the capacitor behavior tends to approach that of a pure capacitance. The knee frequency decreases following the order of [EMIM][BF₄] > [EMIM][Tf₂N] > [EMIM][CF₃SO₃], suggesting the capacitive behavior of the CNTs in these ionic liquids decreases according to this order. Having the lowest knee frequency, [EMIM][CF₃SO₃] produces the smallest capacitive property for the CNTs.

Poor capacitive performance of [EMIM][CF₃SO₃] determined by AC impedance spectroscopy is consistent with the less symmetric CV and the slower transient response at both ends of the CV (Fig. 32C) and the decrease in capacitance of CNTs at a high scan rate (Fig. 30).

Table 5. Capacitive behavior of aligned CNTs and activated carbon (AC) in different ionic liquids

Sample	EDR (Ω)	Knee frequency (Hz)	Line slope at low frequencies
CNTs in [EMIM][BF ₄]	4.6	0.87	25.2
CNTs in [EMIM][Tf ₂ N]	8.2	0.60	24.3
CNTs in [EMIM][CF ₃ SO ₃]	84.5	0.13	4.0
AC in [EMIM][Tf ₂ N]	39.3	0.02	9.4

In short, determined by the low EDR, high knee frequency, and high low-frequency line slope, capacitive performance of the aligned CNT electrodes in these ionic liquids can be decided to be [EMIM][BF₄] > [EMIM][Tf₂N] > [EMIM][CF₃SO₃]. However, considering the overall requirements of high performance, safe operation, and long cycle life for ultracapacitors, [EMIM][BF₄], may not be the good choice due to its water miscibility and relatively narrow electrochemical window. Instead, [EMIM][Tf₂N] has been determined to be the best ionic liquid because of its large electrochemical window, low viscosity, water immiscibility, and high decomposition temperature, ensuring high performance and long cycle life for the resulting ultracapacitors.

[EMIM][Tf₂N] demonstrates superior electrochemical and capacitive performance of aligned CNTs over the currently employed activated carbon electrode materials. Fast charge/discharge process and thus a high capacitance (Figs. 32A-C) of aligned CNTs remained upon the fast potential cycling (up to 100 mV/s). However, at a scan rate higher than 5 mV/s, the typical rectangle-shape of an activated carbon electrode

disappeared accompanying with the rapid decrease of its capacitance (Figs. 33A-B), indicating a slow charge/discharge process for activated carbons in the ionic liquid. A very high capacitance (~430 F/g) has been achieved for aligned CNTs in [EMIM][Tf₂N], which is much higher than that (~50 F/g) of the activated carbons. Although they have a high surface area (1000 ~ 2000 m²/g), low mesoporosity and thus low electrolyte accessibility of activated carbons is likely responsible for this observation. Again, poor capacitive behavior of the activated carbon can be confirmed by its higher EDR, lower knee frequency, and smaller low-frequency line slope comparing to those of the aligned CNTs (Table 5).

These results prove the concept that superior electrical properties and porosity of aligned CNTs can be utilized to produce high electrochemical and capacitive performance for the CNTs in ionic liquids. It should be mentioned that the relatively high viscosity of ionic liquids comparing to conventional aqueous and organic electrolytes is disadvantageous for electrochemical applications (including ultracapacitors). However, the discovery here indicates that, with their unique properties, aligned CNTs are ideal materials to overcome this problem. Also, the capacitance obtained in ionic liquids for these aligned CNTs is higher than that obtained in 1 M H₂SO₄ for a similar electrode material, namely, a CNT array electrode prepared by chemical vapor deposition in the template of porous alumina. This demonstrates that the template-free synthesis and the plasma etching (opening) procedure employed in this project are better approaches to prepare CNTs with highly aligned and open structures and high surface area, ensuring their higher capacitance (even in ionic liquids).

In conclusion, the template-free synthesis approach was used to obtain highly aligned CNTs for ultracapacitor applications. High alignment of nanotubes and well-defined spacing between the tubes provide the CNTs with a high surface area and high electrolyte accessibility, ensuring a high capacitance, fast charge/discharge process, and excellent capacitive behavior for the CNT film electrode in the ionic liquids. Plasma etching has been demonstrated to be very useful in removing the amorphous carbon layer from the top surface of the CNT film and in opening end-caps of the CNTs, enhancing the overall specific surface area of the CNT film and the electrolyte accessibility of the CNTs from both the external and internal surfaces so as to significantly improve the capacitance of the CNT film electrodes. In the optimized ionic liquid, [EMIM][Tf₂N],

the optimized aligned CNTs film electrode (two-side etched) shows a much higher capacitance (430 F/g vs. 50 F/g) and faster charge/discharge process than an activated carbon electrode.

Finally, the CNT capacitors (CNT/IL) were compared to AC capacitors (AC/IL) using the same ionic liquids. Both capacitors showed well-defined rectangle-shape CVs (Figs. 34A-B and Figs. 35A-B). Due to the large electrochemical window of the ionic liquid employed, a large cell voltage of 4V was observed for both capacitors.

Charging/discharging the AC/IL capacitor with an increased scan rate from 5 to 20 mV/s resulted in an increased current. However, further increase of the scan rate (> 20 mV/s)

did not lead to the increase of the current as expected. Instead, a fairly unchanged current and a shrunk CV (shown by arrows) were observed, indicating poor charge storage/delivery capability and slow charge/discharge process of the AC/IL capacitor (Figs. 34A-B). This should be attributed to the low electrolyte accessibility and poor capacitive behavior of the activated carbons. In contrast, the CNT/IL capacitor shows an

increased current (shown by arrows) and remains the well-defined rectangle CV upon charging/discharging up to 200 mV/s (Figs. 35A-B), indicating its excellent charge storage/delivery capability and fast charge/discharge process. Moreover, upon cycling to 4 V, the CNT/IL capacitor showed an additional redox process at around 2 V. This may be due to the presence of the trace amount of firmly-bonded catalysts in the CNTs,

whose electroactivity can be triggered upon charging the capacitor to a high voltage. It is likely that, different from the loosely-bonded catalysts, the firmly-bonded catalysts cannot be removed from the CNTs by plasma etching. Importantly, this additional redox process is fast and reversible, introducing additional pseudocapacitance and thus charge storage capacity to the capacitor.

Capacitive behavior of these capacitors was further investigated by AC impedance spectroscopy, showing vertical lines at low frequencies for both capacitors (Fig. 36). From the AC impedance spectra, capacitive behavior parameters of capacitors are summarized as in Table 6. As can be seen, a similar ESR was observed for both capacitors, suggesting the similar electrical conductivity of the two types of electrode materials employed. However, the AC/IL capacitor shows a very high EDR and an expanded 45° Warburg region, indicating a high interfacial resistance and a slow/difficult transport of electrolyte ions at the electrode/electrolyte interface of the capacitor. Poor

capacitive behavior of this capacitor can be confirmed by its small slope of the low-frequency line and a very small knee frequency.

Table 6. Capacitive behavior and performance of ultracapacitors.

Electrode material of ultracapacitor	ESR (Ω)	EDR (Ω)	Line slope at low frequencies	Knee frequency (Hz)	$E_{\max}$ (Wh/kg)	$P_{\max}$ (kW/kg)	$E_{\max}$ (Wh/kg)*	$P_{\max}$ (kW/kg)*
Activated carbon	1.55	8.2	10.1	0.09	19.6	6.3	6.9	2.2
Aligned CNTs	1.51	0.5	14.1	54.3	148.1	315	51.8	110.3

*Performance of packaged cells, estimated by multiplying the active-material-based performances by a factor of 0.35

In contrast to the AC/IL capacitor, excellent capacitive behavior was obtained for the CNT/IL capacitor. This can be clearly supported by its much lower EDR, larger slope of the low-frequency line, and higher knee frequency than those of the AC/IL capacitor (Table 6). Highly aligned and open structures and excellent electrolyte accessibility of the aligned CNTs are responsible for these findings. We noticed that the knee frequency of our CNT/IL capacitor (54 Hz) is also much higher than that of most commercially available ultracapacitors (usually < 1 Hz), including those specially designed for high power applications, suggesting that most of the stored energy of the CNT/IL capacitor is accessible at frequencies as high as 54 Hz. This larger frequency response means better power performance in demand applications.

Furthermore, these capacitors were subjected to galvanostatic charge/discharge tests at a range of different current densities. As an example, the charge/discharge curves obtained at a moderate current density of 10 mA/cm² are shown in Figs. 37A-C. As can be seen, a slow discharge process was obtained for the AC/IL capacitor evidenced by a bent discharge curve and the uncertainty of defining a discharge straight line. Again, high interfacial resistance and slow/difficult ion transport at the interface between the activated carbon and the ionic liquid are responsible for this problem. In contrast, the CNT/IL capacitor can be charged/discharged rapidly. The well-defined discharge straight line clearly demonstrates that the stored energy of the capacitor can be delivered rapidly. Increasing the cell voltage from 3 V to 4 V resulted in a relatively slow charge process for the capacitor. This is believed to be due to the introduction of the redox process at a high voltage (as discussed above for Figs. 35A-B). Nevertheless, due to the preferable nanostructures of the aligned CNTs, the stored energy still can be delivered rapidly. Importantly, use of the high capacitor voltage and the introduction of

pseudo-capacitance to the CNTs can further enhance performance of the capacitor (Fig. 28).

From the discharge curves obtained at different current densities, energy and power densities were calculated for these two capacitors and are presented in Ragone plots (Fig. 28). For the AC/IL capacitor, upon the increase of the power density, the energy density decreases, a typical phenomena for most conventional ultracapacitors. This means that, to achieve a high power for the capacitor, its energy storage capacity will decrease rapidly. This has long been a problem for conventional ultracapacitors. In contrast, the CNT/IL capacitor shows a high power density at a high energy density, indicating that the high energy stored in CNTs can be delivered very rapidly to achieve a high power. For example, a high energy density of 100 Wh/kg can be maintained at a power density as high as 100 kW/kg. Unique properties of aligned CNTs discussed above are responsible for this significance. From these results, maximum energy density ($E_{\max}$) and maximum power density ($P_{\max}$) of the capacitors are obtained and included in Table 6. It should be stressed that energy and power densities of the CNT/IL ultracapacitor are also higher than those CNT ultracapacitors (aqueous electrolyte-based) reported in the literature. This should be due to the use of not only highly aligned CNT electrodes but also high-electrochemical window ionic liquids in the present project. Indeed, as proposed and demonstrated, this combination of the unique properties of aligned CNTs with those of ionic liquids is an innovative aspect of the work and holds the potential to revolutionize ultracapacitor technology.

A number of variations and modifications of the invention can be used. It would be possible to provide for some features of the invention without providing others.

For example in one alternative embodiment, the solvent or swelling agent, which in this instance is identical with the ionic liquid, remains in the ILGPE composition. This is particularly advantageous for multiphase polymer systems in which, for example, only one of the polymeric components is compatible with the ionic liquid. An additional result can be novel properties for the multiphase system, preferably at the phase boundaries. Another possible use of the ILGPE composition in which the ionic liquid remains present is the dissolving or solvating of one polymer component of a multiphase system, where another polymer component is incompatible with the simple ionic liquid. Through mixing or kneading of this multiphase system it is possible for the ionic liquid to migrate into the phase which is incompatible with the simple ionic liquid.

In another embodiment, the dispersion of the ionic liquid in the polymer composition takes place by means of a mixing process. Here, the ionic liquid is brought into contact with, and then thoroughly mixed with, the molten phase of the polymer host. Another method brings the ionic liquid into contact with the solid phase of the polymeric component, melts the polymer host, and then thoroughly mixes the ionic liquid and polymer host. One way of achieving this is to use mechanical mixing of the polymer host and the ionic liquid by means of an extruder or stirrer at appropriate temperatures, and preference is given to mixing of the individual components of the ILGPE composition in a single- or twin-screw kneader, the polymer host being molten. It is also possible for the polymer host to become dissolved in the ionic liquid at relatively high temperatures during the mixing process, or for both the polymer host and the ionic liquid to be dissolved in a solvent. In one embodiment, the polymer host, which comprises precipitated, spray-dried, or (low-temperature-)milled polymer, for example, is mixed with the ionic liquid, where appropriate via addition of a solvent which can dissolve the ionic liquid but cannot dissolve the polymeric component, thus giving homogeneous dispersion of the ionic liquid in the polymer composition of the invention.

In other embodiments, the ultracapacitors of the present invention are used in applications other than hybrid electric vehicles. For example, in consumer electronics, they can be used for notebook computers, cellular telephones, pagers, videocameras, and hand-held tools. In medical electronics, they can be used for portable defibrillators, drug delivery units, and neurological stimulators. In the military and defense, the ultracapacitors can be used in specialized mobile power applications such as communication devices, unmanned aerial vehicles, spacecraft probes, and missile systems. Environmentally friendly solid-state ILGPEs can benefit a wide range of other electrochemical devices (such as batteries, electrochromic devices, sensors, photoelectrochemical solar cells, and light emitting electrochemical cells) with high performance and extended lifetimes.

The present invention, in various embodiments, includes components, methods, processes, systems and/or apparatus substantially as depicted and described herein, including various embodiments, subcombinations, and subsets thereof. Those of skill in the art will understand how to make and use the present invention after understanding the present disclosure. The present invention, in various embodiments, includes providing


devices and processes in the absence of items not depicted and/or described herein or in various embodiments hereof, including in the absence of such items as may have been used in previous devices or processes, e.g., for improving performance, achieving ease and/or reducing cost of implementation.

5 The foregoing discussion of the invention has been presented for purposes of illustration and description. The foregoing is not intended to limit the invention to the form or forms disclosed herein. In the foregoing Detailed Description for example, various features of the invention are grouped together in one or more embodiments for the purpose of streamlining the disclosure. The features of the embodiments of the
10 invention may be combined in alternate embodiments other than those discussed above. This method of disclosure is not to be interpreted as reflecting an intention that the claimed invention requires more features than are expressly recited in each claim. Rather, as the following claims reflect, inventive aspects lie in less than all features of a single foregoing disclosed embodiment. Thus, the following claims are hereby
15 incorporated into this Detailed Description, with each claim standing on its own as a separate preferred embodiment of the invention.

 Moreover, though the description of the invention has included description of one or more embodiments and certain variations and modifications, other variations, combinations, and modifications are within the scope of the invention, e.g., as may be
20 within the skill and knowledge of those in the art, after understanding the present disclosure. It is intended to obtain rights which include alternative embodiments to the extent permitted, including alternate, interchangeable and/or equivalent structures, functions, ranges or steps to those claimed, whether or not such alternate, interchangeable and/or equivalent structures, functions, ranges or steps are disclosed
25 herein, and without intending to publicly dedicate any patentable subject matter.

What is claimed is:

1. An ultracapacitor, comprising:
 - (a) first and second electrodes, the first and second oppositely charged electrodes
5 primarily comprising carbon nanotubes; and
 - (b) an electrolyte material, comprising oppositely charged ions, in contact with first ends of the first and second electrodes, wherein at least most of the first ends of the carbon nanotubes are open to permit the ions to access interior surfaces of the nanotubes, wherein the sizes of the ions are less than interior diameters of the carbon nanotubes.
- 10 2. The ultracapacitor of claim 1, wherein longitudinal axes of at least most of the carbon nanotubes are substantially parallel to one another along substantially the entire length of the nanotube and wherein at least most of the carbon nanotubes are carbon nanotubes.
- 15 3. The ultracapacitor of claim 1, wherein at least most of the opposing second ends of the carbon nanotubes in the first and second electrodes are open.
4. The ultracapacitor of claim 1, wherein at least most of the carbon nanotubes have lengths of at least about 75 microns, inter-carbon nanotube spacings ranging from about 5 to about 1,000 nm, and diameters ranging from about 0.25 to about 250 nm.
- 20 5. The ultracapacitor of claim 1, wherein the electrolyte material comprises an ionic liquid and polymer host in the form of a self-supporting film, wherein the ionic liquid has a melting point of no more than about 100 degrees Celsius, a decomposition temperature of at least about 200 degrees Celsius, a viscosity of no more than about 200 Cp, an ionic conductivity of at least about 0.1 mS/cm, and an electrochemical window of
25 at least about 2 Volts.
6. The ultracapacitor of claim 5, wherein:
 - (I) the ionic liquid comprises:
 - (A) at least one cation selected from the group consisting essentially of the following compounds and mixtures thereof:



5 wherein R₁, R₂, R₃, R₄, R₅, and R₆ of the cationic components are identical or different and are selected from the group consisting essentially of:

- (i) a hydrogen;
- (ii) a halogen;
- (iii) a hydroxyl;
- 10 (iv) an amine;
- (v) a thiol;
- (vi) a C₁ to C₂₅ straight-chain, branched aliphatic hydrocarbon radical;
- (vii) a C₅ to C₃₀ cycloaliphatic hydrocarbon radical;
- (viii) a C₆ to C₃₀ aromatic hydrocarbon radical;
- 15 (ix) a C₇ to C₄₀ alkylaryl radical;
- (x) a C₂ to C₂₅ linear or branched aliphatic hydrocarbon radical having interruption by one or more heteroatoms, such as, oxygen, nitrogen or sulfur;
- (xi) a C₂ to C₂₅ linear or branched aliphatic hydrocarbon radical having
- 20 interruption by one or more functionalities selected from the group consisting essentially of:
 - (a') a carbonyl;
 - (b') an ester;

- (c') an amide, where R' selected from the group consisting essentially of hydrogen, C₁-C₁₂ straight-chain, branched or cyclic alkane or alkene;
- (d') a sulfonate;
- 5 (e') a sulfonamide, where R' selected from the group consisting essentially of hydrogen, C₁-C₁₂ straight-chain, branched or cyclic alkane or alkene;
- (xii) a C₂ to C₂₅ linear or branched aliphatic hydrocarbon radical terminally functionalized by Cl, Br, F, I, NH, OH, NH₂, NHCH₃ or SH;
- 10 (xiii) a C₅ to C₃₀ cycloaliphatic hydrocarbon radical having at least one heteroatom selected from the group consisting essentially of O, N, S, and optionally substituted with at least one of the following Cl, Br, F, I, NH, OH, NH₂, NHCH₃ or SH;
- (xiv) a C₇ to C₄₀ alkylaryl radical heteroatom selected from the group consisting essentially of O, N, S, and optionally substituted with at least one of the following:
- 15 (a'') a C₂ to C₂₅ straight-chain, branched hydrocarbon radical substituted with at least one of the following Cl, Br, F, I, NH, OH, NH₂, NHCH₃ or SH;
- 20 (b'') a C₅ to C₃₀ cycloaliphatic hydrocarbon radical substituted with at least one of the following Cl, Br, F, I, NH, OH, NH₂, NHCH₃ or SH
- (c'') a hydroxyl;
- (d'') an amine;
- (e'') a thiol;
- 25 (xv) a polyether of the type -O-(R₇-O)_n-R₈ or block or random type -O-(R₇-O)_n-(R_{7'}-O)_m-R₈, wherein at least of the following is true:
- (a''') R₇ is a linear or branched hydrocarbon radical having from 2 to 4 carbon atoms;
- 30 (b''') R_{7'} is a linear or branched hydrocarbon radical having from 2 to 4 carbon atoms; and
- (c''') wherein n is from 1 to 40; and

- (d''') R_8 is hydrogen, or a C_5 to C_{30} straight-chain or branched hydrocarbon radical, or a C_5 to C_{30} cycloaliphatic hydrocarbon radical, or a C_6 to C_{30} aromatic hydrocarbon radical, or a C_7 to C_{40} alkylaryl radical; and
- 5 (xvi) a polyether of the type $-O-(R_7-O)_n-C(O)-R_8$ or block or random type $-O-(R_7-O)_n-(R_7'-O)_m-C(O)-R_8$, wherein at least of the following is true:
- (a''') R_7 is a linear or branched hydrocarbon radical having from 2 to 4 carbon atoms;
- 10 (b''') R_7' is a linear or branched hydrocarbon radical having from 2 to 4 carbon atoms; and
- (c''') wherein n is from 1 to 40; and
- (d''') R_8 is hydrogen, or a C_5 to C_{30} straight-chain or branched hydrocarbon radical, or a C_5 to C_{30} cycloaliphatic hydrocarbon radical, or a C_6 to C_{30} aromatic hydrocarbon radical, or a C_7 to
- 15 C_{40} alkylaryl radical; and
- (B) at least one anion selected from the group consisting essentially of F^- ; Cl^- ; Br^- ; I^- ; NO_3^- ; $N(CN)_2^-$; BF_4^- ; ClO_4^- ; PF_6^- ; RSO_3^- ; $RCOO^-$; where R is an alkyl group, substituted alkyl group, or phenyl group; $(CF_3)_2PF_4^-$, $(CF_3)_3PF_3^-$,
- 20 $(CF_3)_4PF_2^-$, $(CF_3)_5PF^-$, $(CF_3)_6P^-$, $(CF_2SO_3^-)_2$, $(CF_2CF_2SO_3^-)_2$, $(CF_3SO_2^-)_2N^-$, $CF_3CF_2(CF_3)_2CO^-$, $(CF_3SO_2^-)_2CH^-$, $(SF_5)_3C^-$, $(CF_3SO_2)_3C^-$, $[O(CF_3)_2C_2(CF_3)_2O]_2PO^-$, $(CF_3(CF_2)_7SO_3^-$, and mixtures thereof; and
- (II) wherein the polymer host is selected from the group consisting essentially of homopolymers and copolymers of polyolefins, polystyrenes, polyvinyls, polyacrylics,
- 25 polyhalo-olefins, polydienes, polyoxides/esters/acetal, polysulfides, polyesters/thioesters, polyamides/thioamides, polyurethanes/thiourethanes, polyureas/thioureas, polyimides/thioimides, polyanhydrides/thianhydrides, polycarbonates/thiocarbonates, polyimines, polysiloxanes/silanes, polyphosphazenes, polyketones/thioketones, polysulfones/sulfoxides/sulfonates/sulfoamides, polyphenylenes,
- 30 and mixtures thereof.

7. The ultracapacitor of claim 5, wherein the electrolyte material further comprises an inorganic filler, wherein at least most of the filler particles have a surface area of at least about 10 m²/g, a maximum dimension of about 50 micrometers, and an average pore size of less than about 10 micrometers.

5 8. An ultracapacitor, comprising:


- (a) first and second electrodes comprising etched carbon nanotubes; and
- (b) a solid-phase electrolyte material comprising an ionic liquid and a polymer host, the polymer host forming a self-supporting film comprising the ionic liquid.

9. The ultracapacitor of claim 8, wherein the ionic liquid has a melting point of no more than about 100 degrees Celsius, a decomposition temperature of at least about 200 degrees Celsius, a viscosity of no more than about 200 Cp, an ionic conductivity of at least about 0.1mS/cm, and an electrochemical window of at least about 2 Volts.

10. The ultracapacitor of claim 9, wherein:

(I) the ionic liquid comprises:

15 (A) at least one cation selected from the group consisting essentially of the following compounds and mixtures thereof:



20 wherein R₁, R₂, R₃, R₄, R₅, and R₆ of the cationic components are identical or different and are selected from the group consisting essentially of:

- (i) a hydrogen;
- (ii) a halogen;
- (iii) a hydroxyl;

- (iv) an amine;
- (v) a thiol;
- (vi) a C₁ to C₂₅ straight-chain, branched aliphatic hydrocarbon radical;
- (vii) a C₅ to C₃₀ cycloaliphatic hydrocarbon radical;
- 5 (viii) a C₆ to C₃₀ aromatic hydrocarbon radical;
- (ix) a C₇ to C₄₀ alkylaryl radical;
- (x) a C₂ to C₂₅ linear or branched aliphatic hydrocarbon radical having
interruption by one or more heteroatoms, such as, oxygen, nitrogen or
sulfur;
- 10 (xi) a C₂ to C₂₅ linear or branched aliphatic hydrocarbon radical having
interruption by one or more functionalities selected from the group
consisting essentially of:
 - (a') a carbonyl;
 - (b') an ester;
 - 15 (c') an amide, where R' selected from the group consisting
essentially of hydrogen, C₁-C₁₂ straight-chain, branched or
cyclic alkane or alkene;
 - (d') a sulfonate;
 - (e') a sulfonamide, where R' selected from the group consisting
20 essentially of hydrogen, C₁-C₁₂ straight-chain, branched or
cyclic alkane or alkene;
- (xii) a C₂ to C₂₅ linear or branched aliphatic hydrocarbon radical terminally
functionalized by Cl, Br, F, I, NH, OH, NH₂, NHCH₃ or SH;
- (xiii) a C₅ to C₃₀ cycloaliphatic hydrocarbon radical having at least one
25 heteroatom selected from the group consisting essentially of O, N, S,
and optionally substituted with at least one of the following Cl, Br, F, I,
NH, OH, NH₂, NHCH₃ or SH;
- (xiv) a C₇ to C₄₀ alkylaryl radical heteroatom selected from the group
consisting essentially of O, N, S, and optionally substituted with at least
30 one of the following:
 - (a'') a C₂ to C₂₅ straight-chain, branched hydrocarbon radical
substituted with at least one of the following Cl, Br, F, I, NH, OH,
NH₂, NHCH₃ or SH;

- (b'') a C₅ to C₃₀ cycloaliphatic hydrocarbon radical substituted with at least one of the following Cl, Br, F, I, NH, OH, NH₂, NHCH₃ or SH
- (c'') a hydroxyl;
- (d'') an amine;
- 5 (e'') a thiol;
- (xv) a polyether of the type $-O-(R_7-O)_n-R_8$ or block or random type $-O-(R_7-O)_n-(R_{7'}-O)_m-R_8$, wherein at least of the following is true:
- (a''') R₇ is a linear or branched hydrocarbon radical having from 2 to
- 10 4 carbon atoms;
- (b''') R_{7'} is a linear or branched hydrocarbon radical having from 2 to 4 carbon atoms; and
- (c''') wherein n is from 1 to 40; and
- (d''') R₈ is hydrogen, or a C₅ to C₃₀ straight-chain or branched
- 15 hydrocarbon radical, or a C₅ to C₃₀ cycloaliphatic hydrocarbon radical, or a C₆ to C₃₀ aromatic hydrocarbon radical, or a C₇ to C₄₀ alkylaryl radical; and
- (xvi) a polyether of the type $-O-(R_7-O)_n-C(O)-R_8$ or block or random type $-O-(R_7-O)_n-(R_{7'}-O)_m-C(O)-R_8$, wherein at least of the
- 20 following is true:
- (a''') R₇ is a linear or branched hydrocarbon radical having from 2 to 4 carbon atoms;
- (b''') R_{7'} is a linear or branched hydrocarbon radical having from 2 to 4 carbon atoms; and
- 25 (c''') wherein n is from 1 to 40; and
- (d''') R₈ is hydrogen, or a C₅ to C₃₀ straight-chain or branched hydrocarbon radical, or a C₅ to C₃₀ cycloaliphatic hydrocarbon radical, or a C₆ to C₃₀ aromatic hydrocarbon radical, or a C₇ to C₄₀ alkylaryl radical; and
- 30 (B) at least one anion selected from the group consisting essentially of F⁻; Cl⁻, Br⁻; I⁻; NO₃⁻; N(CN)₂⁻; BF₄⁻; ClO₄⁻; PF₆⁻; RSO₃⁻; RCOO⁻; where R is an alkyl group, substituted alkyl group, or phenyl group; (CF₃)₂PF₄⁻, (CF₃)₃PF₃⁻,

(CF₃)₄PF₂⁻, (CF₃)₅PF⁻, (CF₃)₆P⁻, (CF₂SO₃⁻)₂, (CF₂CF₂SO₃⁻)₂, (CF₃SO₂⁻)₂N⁻, CF₃CF₂(CF₃)₂CO⁻, (CF₃SO₂⁻)₂CH⁻, (SF₅)₃C⁻, (CF₃SO₂)₃C⁻,
[O(CF₃)₂C₂(CF₃)₂O]₂PO⁻, (CF₃(CF₂)₇ SO₃⁻, and mixtures thereof; and

(II) wherein the polymer host is selected from the group consisting essentially of
5 homopolymers and copolymers of polyolefins, polystyrenes, polyvinyls, polyacrylics, polyhalo-olefins, polydienes, polyoxides/esters/acetal, polysulfides, polyesters/thioesters, polyamides/thioamides, polyurethanes/thiourethanes, polyureas/thioureas, polyimides/thioimides, polyanhydrides/thianhydrides, polycarbonates/thiocarbonates, polyimines, polysiloxanes/silanes, polyphosphazenes,
10 polyketones/thioketones, polysulfones/sulfoxides/sulfonates/sulfoamides, polyphenylenes, and mixtures thereof.

11. The ultracapacitor of claim 9, wherein the polymer host is selected from the group consisting essentially of homopolymers and copolymers of polyolefins, polystyrenes, polyvinyls, polyacrylics, polyhalo-olefins, polydienes,
15 polyoxides/esters/acetal, polysulfides, polyesters/thioesters, polyamides/thioamides, polyurethanes/thiourethanes, polyureas/thioureas, polyimides/thioimides, polyanhydrides/thianhydrides, polycarbonates/thiocarbonates, polyimines, polysiloxanes/silanes, polyphosphazenes, polyketones/thioketones, polysulfones/sulfoxides/sulfonates/sulfoamides, polyphenylenes, and mixtures thereof.

20 12. The ultracapacitor of claim 8, wherein the solid-phase electrolyte material comprises a substantially nonconductive, inorganic filler, wherein at least most of the filler particles have a surface area of at least about 10 m²/g, a maximum dimension of about 50 micrometers, and an average pore size of less than about 10 micrometers.

25 13. The ultracapacitor of claim 8, wherein a molar ratio of ionic liquid to polymer host ranges from about 0.1:1 to about 10:1.

14. The ultracapacitor of claim 8, wherein the first and second carbon-based electrodes are primarily comprised of carbon nanotubes, wherein at least most of the first ends of the carbon nanotubes are open to permit the ions to access interior surfaces of the nanotubes, and wherein the sizes of the cations and anions in the ionic liquid are less
30 than interior diameters of the carbon nanotubes.

15. The ultracapacitor of claim 14, wherein at least most of the carbon nanotubes are aligned carbon nanotubes.

16. A method, comprising:

(a) contacting a polymer host with an organic solvent to form a first composition;


(b) contacting an ionic liquid with the first composition; and
 (c) removing at least most of the organic solvent from the first composition to form a free-standing film comprising the polymer host and ionic liquid.

17. The method of claim 16, wherein the polymer host is dissolved substantially in the first composition, wherein the organic solvent is removed from the first composition by heating the first composition to a selected temperature under a vacuum, wherein the selected temperature is higher than a boiling point of the solvent but lower than decomposition temperatures of the ionic liquid and polymer host, and wherein the first composition is spread onto a substrate during step (c).

18. The method of claim 16, wherein:

(I) the ionic liquid comprises:

(A) at least one cation selected from the group consisting essentially of the following compounds and mixtures thereof:



wherein R_1 , R_2 , R_3 , R_4 , R_5 , and R_6 of the cationic components are identical or different and are selected from the group consisting essentially of:

- (i) a hydrogen;
- (ii) a halogen;
- (iii) a hydroxyl;
- (iv) an amine;
- (v) a thiol;

- (vi) a C₁ to C₂₅ straight-chain, branched aliphatic hydrocarbon radical;
- (vii) a C₅ to C₃₀ cycloaliphatic hydrocarbon radical;
- (viii) a C₆ to C₃₀ aromatic hydrocarbon radical;
- (ix) a C₇ to C₄₀ alkylaryl radical;
- 5 (x) a C₂ to C₂₅ linear or branched aliphatic hydrocarbon radical having interruption by one or more heteroatoms, such as, oxygen, nitrogen or sulfur;
- (xi) a C₂ to C₂₅ linear or branched aliphatic hydrocarbon radical having interruption by one or more functionalities selected from the group consisting essentially of:
 - 10 (a') a carbonyl;
 - (b') an ester;
 - (c') an amide, where R' selected from the group consisting essentially of hydrogen, C₁-C₁₂ straight-chain, branched or
 - 15 cyclic alkane or alkene;
 - (d') a sulfonate;
 - (e') a sulfonamide, where R' selected from the group consisting essentially of hydrogen, C₁-C₁₂ straight-chain, branched or cyclic alkane or alkene;
- 20 (xii) a C₂ to C₂₅ linear or branched aliphatic hydrocarbon radical terminally functionalized by Cl, Br, F, I, NH, OH, NH₂, NHCH₃ or SH;
- (xiii) a C₅ to C₃₀ cycloaliphatic hydrocarbon radical having at least one heteroatom selected from the group consisting essentially of O, N, S, and optionally substituted with at least one of the following Cl, Br, F, I,
 - 25 NH, OH, NH₂, NHCH₃ or SH;
- (xiv) a C₇ to C₄₀ alkylaryl radical heteroatom selected from the group consisting essentially of O, N, S, and optionally substituted with at least one of the following:
 - (a'') a C₂ to C₂₅ straight-chain, branched hydrocarbon radical
 - 30 substituted with at least one of the following Cl, Br, F, I, NH, OH, NH₂, NHCH₃ or SH;
 - (b'') a C₅ to C₃₀ cycloaliphatic hydrocarbon radical substituted with at least one of the following Cl, Br, F, I, NH, OH, NH₂, NHCH₃ or SH

- (c'') a hydroxyl;
 (d'') an amine;
 (e'') a thiol;
- (xv) a polyether of the type $-O-(-R_7-O-)_n-R_8$ or block or random type
 $-O-(-R_7-O-)_n-(-R_{7'}-O-)_m-R_8$, wherein at least of the following is
 true:
- (a''') R_7 is a linear or branched hydrocarbon radical having from 2 to
 4 carbon atoms;
 (b''') $R_{7'}$ is a linear or branched hydrocarbon radical having from 2 to
 4 carbon atoms; and
 (c''') wherein n is from 1 to 40; and
 (d''') R_8 is hydrogen, or a C_5 to C_{30} straight-chain or branched
 hydrocarbon radical, or a C_5 to C_{30} cycloaliphatic hydrocarbon
 radical, or a C_6 to C_{30} aromatic hydrocarbon radical, or a C_7 to
 C_{40} alkylaryl radical; and
- (xvi) a polyether of the type $-O-(-R_7-O-)_n-C(O)-R_8$ or block or random
 type $-O-(-R_7-O-)_n-(-R_{7'}-O-)_m-C(O)-R_8$, wherein at least of the
 following is true:
- (a''') R_7 is a linear or branched hydrocarbon radical having from 2 to
 4 carbon atoms;
 (b''') $R_{7'}$ is a linear or branched hydrocarbon radical having from 2
 to 4 carbon atoms; and
 (c''') wherein n is from 1 to 40; and
 (d''') R_8 is hydrogen, or a C_5 to C_{30} straight-chain or branched
 hydrocarbon radical, or a C_5 to C_{30} cycloaliphatic hydrocarbon
 radical, or a C_6 to C_{30} aromatic hydrocarbon radical, or a C_7 to
 C_{40} alkylaryl radical; and
- (B) at least one anion selected from the group consisting essentially of F^- ; Cl^- ; Br^- ;
 I^- ; NO_3^- ; $N(CN)_2^-$; BF_4^- ; ClO_4^- ; PF_6^- ; RSO_3^- ; $RCOO^-$; where R is an alkyl
 group, substituted alkyl group, or phenyl group; $(CF_3)_2PF_4^-$, $(CF_3)_3PF_3^-$,
 $(CF_3)_4PF_2^-$, $(CF_3)_5PF^-$, $(CF_3)_6P^-$, $(CF_2SO_3^-)_2$, $(CF_2CF_2SO_3^-)_2$, $(CF_3SO_2^-$

)₂N⁻, CF₃CF₂(CF₃)₂CO⁻, (CF₃SO₂)₂CH⁻, (SF₅)₃C⁻, (CF₃SO₂)₃C⁻,

[O(CF₃)₂C₂(CF₃)₂O]₂PO⁻, (CF₃(CF₂)₇ SO₃)⁻, and mixtures thereof; and

(II) wherein the polymer host is selected from the group consisting essentially of homopolymers and copolymers of polyolefins, polystyrenes, polyvinyls, polyacrylics, polyhalo-olefins, polydienes, polyoxides/esters/acetal, polysulfides, polyesters/thioesters, polyamides/thioamides, polyurethanes/thiourethanes, polyureas/thioureas, polyimides/thioimides, polyanhydrides/thianhydrides, polycarbonates/thiocarbonates, polyimines, polysiloxanes/silanes, polyphosphazenes, polyketones/thioketones, polysulfones/sulfoxides/sulfonates/sulfoamides, polyphylenes, and mixtures thereof.

19. The method of claim 16, wherein the ionic liquid has a melting point of no more than about 100 degrees Celsius, a decomposition temperature of at least about 200 degrees Celsius, a viscosity of no more than about 200 Cp, an ionic conductivity of at least about 0.1 mS/cm, and an electrochemical window of at least about 2 Volts.

20. The method of claim 16, wherein in step (b) the first composition further comprises a substantially nonconductive, inorganic filler and wherein at least most of the filler particles have a surface area of at least about 10 m²/g, a maximum dimension of about 50 micrometers, and an average pore size of less than about 10 micrometers.

21. A method, comprising:


(a) first forming a self-supporting polymer film comprising a host polymer;
(b) second contacting the film with an ionic liquid; and
(c) heating the film and ionic liquid, while in contact with one another, to a selected temperature above a glass transition temperature of the polymer host but below decomposition temperatures of the ionic liquid and polymer host to impregnate the polymer film with the ionic liquid.

22. The method of claim 21, wherein the self-supporting polymer film comprises a substantially nonconductive, inorganic filler and wherein at least most of the filler particles have a surface area of at least about 10 m²/g, a maximum dimension of about 50 micrometers, and an average pore size of less than about 10 micrometers.

23. The method of claim 21, wherein:

(I) the ionic liquid comprises:

(A) at least one cation selected from the group consisting essentially of the following compounds and mixtures thereof:



wherein R₁, R₂, R₃, R₄, R₅, and R₆ of the cationic components are identical or different

5 and are selected from the group consisting essentially of:

- (i) a hydrogen;
- (ii) a halogen;
- (iii) a hydroxyl;
- (iv) an amine;
- 10 (v) a thiol;
- (vi) a C₁ to C₂₅ straight-chain, branched aliphatic hydrocarbon radical;
- (vii) a C₅ to C₃₀ cycloaliphatic hydrocarbon radical;
- (viii) a C₆ to C₃₀ aromatic hydrocarbon radical;
- (ix) a C₇ to C₄₀ alkylaryl radical;
- 15 (x) a C₂ to C₂₅ linear or branched aliphatic hydrocarbon radical having interruption by one or more heteroatoms, such as, oxygen, nitrogen or sulfur;
- (xi) a C₂ to C₂₅ linear or branched aliphatic hydrocarbon radical having interruption by one or more functionalities selected from the group consisting essentially of:
- 20 (a') a carbonyl;
- (b') an ester;

- (c') an amide, where R' selected from the group consisting essentially of hydrogen, C₁-C₁₂ straight-chain, branched or cyclic alkane or alkene;
- (d') a sulfonate;
- 5 (e') a sulfonamide, where R' selected from the group consisting essentially of hydrogen, C₁-C₁₂ straight-chain, branched or cyclic alkane or alkene;
- (xii) a C₂ to C₂₅ linear or branched aliphatic hydrocarbon radical terminally functionalized by Cl, Br, F, I, NH, OH, NH₂, NHCH₃ or SH;
- 10 (xiii) a C₅ to C₃₀ cycloaliphatic hydrocarbon radical having at least one heteroatom selected from the group consisting essentially of O, N, S, and optionally substituted with at least one of the following Cl, Br, F, I, NH, OH, NH₂, NHCH₃ or SH;
- (xiv) a C₇ to C₄₀ alkylaryl radical heteroatom selected from the group consisting essentially of O, N, S, and optionally substituted with at least one of the following:
- 15 (a'') a C₂ to C₂₅ straight-chain, branched hydrocarbon radical substituted with at least one of the following Cl, Br, F, I, NH, OH, NH₂, NHCH₃ or SH;
- 20 (b'') a C₅ to C₃₀ cycloaliphatic hydrocarbon radical substituted with at least one of the following Cl, Br, F, I, NH, OH, NH₂, NHCH₃ or SH
- (c'') a hydroxyl;
- (d'') an amine;
- (e'') a thiol;
- 25 (xv) a polyether of the type -O-(R₇-O)_n-R₈ or block or random type -O-(R₇-O)_n-(R_{7'}-O)_m-R₈, wherein at least of the following is true:
- (a''') R₇ is a linear or branched hydrocarbon radical having from 2 to 4 carbon atoms;
- 30 (b''') R_{7'} is a linear or branched hydrocarbon radical having from 2 to 4 carbon atoms; and
- (c''') wherein n is from 1 to 40; and

- (d''') R_8 is hydrogen, or a C_5 to C_{30} straight-chain or branched hydrocarbon radical, or a C_5 to C_{30} cycloaliphatic hydrocarbon radical, or a C_6 to C_{30} aromatic hydrocarbon radical, or a C_7 to C_{40} alkylaryl radical; and
- 5 (xvi) a polyether of the type $-O-(R_7-O)_n-C(O)-R_8$ or block or random type $-O-(R_7-O)_n-(R_7'-O)_m-C(O)-R_8$, wherein at least of the following is true:
- (a''') R_7 is a linear or branched hydrocarbon radical having from 2 to 4 carbon atoms;
- 10 (b''') R_7' is a linear or branched hydrocarbon radical having from 2 to 4 carbon atoms; and
- (c''') wherein n is from 1 to 40; and
- (d''') R_8 is hydrogen, or a C_5 to C_{30} straight-chain or branched hydrocarbon radical, or a C_5 to C_{30} cycloaliphatic hydrocarbon radical, or a C_6 to C_{30} aromatic hydrocarbon radical, or a C_7 to
- 15 C_{40} alkylaryl radical; and
- (B) at least one anion selected from the group consisting essentially of F^- ; Cl^- ; Br^- ; I^- ; NO_3^- ; $N(CN)_2^-$; BF_4^- ; ClO_4^- ; PF_6^- ; RSO_3^- ; $RCOO^-$; where R is an alkyl group, substituted alkyl group, or phenyl group; $(CF_3)_2PF_4^-$, $(CF_3)_3PF_3^-$,
- 20 $(CF_3)_4PF_2^-$, $(CF_3)_5PF^-$, $(CF_3)_6P^-$, $(CF_2SO_3^-)_2$, $(CF_2CF_2SO_3^-)_2$, $(CF_3SO_2^-)_2N^-$, $CF_3CF_2(CF_3)_2CO^-$, $(CF_3SO_2^-)_2CH^-$, $(SF_5)_3C^-$, $(CF_3SO_2)_3C^-$, $[O(CF_3)_2C_2(CF_3)_2O]_2PO^-$, $(CF_3(CF_2)_7SO_3^-$, and mixtures thereof; and
- (II) wherein the polymer host is selected from the group consisting essentially of homopolymers and copolymers of polyolefins, polystyrenes, polyvinyls, polyacrylics,
- 25 polyhalo-olefins, polydienes, polyoxides/esters/acetal, polysulfides, polyesters/thioesters, polyamides/thioamides, polyurethanes/thiourethanes, polyureas/thioureas, polyimides/thioimides, polyanhydrides/thianhydrides, polycarbonates/thiocarbonates, polyimines, polysiloxanes/silanes, polyphosphazenes, polyketones/thioketones, polysulfones/sulfoxides/sulfonates/sulfoamides, polyphenylenes,
- 30 and mixtures thereof.