



- (51) **International Patent Classification:**
C03C 17/36 (2006.01)
- (21) **International Application Number:**
PCT/EP2014/061096
- (22) **International Filing Date:**
28 May 2014 (28.05.2014)
- (25) **Filing Language:** English
- (26) **Publication Language:** English
- (30) **Priority Data:**
BE 2013/0385 30 May 2013 (30.05.2013) BE
13197207.7 13 December 2013 (13.12.2013) EP
- (71) **Applicant:** AGC GLASS EUROPE [BE/BE]; Avenue Jean Monnet, 4, B-1348 Louvain-La-Neuve (BE).
- (72) **Inventors:** MAHIEU, Stijn; Vijverstraat, 32, B-9920 Lovendegem (BE). BAUDOUIN, Anne-Christine; Place de l'Esquerre, 37, B-1348 Louvain-La-Neuve (BE). HAUPTMANN, Marc; Wilselsesteenweg 179, B-3010 Kessel-Lo (BE). DEPAUW, Jean-Michel; Rue Eugène Toussaint, 5, B-1083 Bruxelles (BE).
- (74) **Agent:** LARANGÉ, Françoise; AGC Glass Europe, Technology Center, IP Department, Rue Louis Blériot, 12, B-6041 Gosselies (BE).
- (81) **Designated States** (*unless otherwise indicated, for every kind of national protection available*): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM,

DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, JP, KE, KG, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

- (84) **Designated States** (*unless otherwise indicated, for every kind of regional protection available*): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

Declarations under Rule 4.17:

— *of inventorship (Rule 4.17(iv))*

Published:

- *with international search report (Art. 21(3))*
- *before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments (Rule 48.2(h))*

- (88) **Date of publication of the international search report:**
22 January 2015

(54) **Title:** LOW-EMISSIVITY AND ANTI-SOLAR GLAZING

(57) **Abstract:** The invention relates to low-emissivity and anti-solar glazing systems that change only very little in properties when they are subjected to a heat treatment. They comprise a stack of thin layers comprising an alternating arrangement of n infrared radiation reflecting functional layers and $n + 1$ dielectric coatings, and a barrier layer directly superposed on the last functional layer furthest away from the substrate, characterised in that: (i) the first dielectric coating closest to the substrate comprises a layer made from an oxide, in direct contact with the substrate, (ii) the internal dielectric coating or coatings surrounded by two functional layers comprise a layer made from a silicon nitride or a silicon oxide with a thickness greater than 5 nm surrounded on both sides by layers made from an oxide other than silicon oxide with thicknesses greater than 5 nm, (iii) the barrier layer is based on zinc oxide or consists of an indium oxide possibly doped with tin, and (iv) the last dielectric coating furthest away from the substrate comprises, in order starting from the substrate: a layer made from an oxide other than silicon oxide with a thickness greater than 3 nm and a layer made from a silicon nitride or a silicon oxide with a thickness greater than 10 nm.

