



Description:

The invention relates to a galvanic cell comprising an outer metallic jar which on its outside has an insulating and decorative layer.

5 Galvanic cells which are mainly used in electrically operated appliances have an electrically insulated jacket and two contacts which, as a rule, are situated opposite one another. The electric circuit of the electrical appliance is closed via the contact areas. The
10 insulation situated between the contact areas is intended to prevent inadvertent discharge of the cells. Thus, for example, many electrical appliances are fitted with a spiral spring as the electrical contact area, the jacket-type insulation protecting the two cell terminals against
15 short-circuiting by inadvertent canting of said spiral spring. The insulating casing of the galvanic cells further protects the cells against environmental influences which lead to scratches, spots or traces of corrosion on the cell jar. The insulating casing of the
20 galvanic cells is also provided with inscriptions and advertising material. On the one hand, this decor comprises information on the electrochemical system used, the cell size, the cell voltage, the manufacturer, the country of origin and the guarantee period, but it is
25 also intended to provide, by the way it is designed, an appropriate advertising message.

The documents DE 1671802 and DE 2845242 disclose metallic casings for galvanic cells, which on their outside have a decorative layer. These metallic casings
30 are primarily employed for galvanic cells of the Leclanché type, to prevent electrolyte from escaping after the cells have been completely discharged. In the case of galvanic cells of the Leclanché type it is possible, as complete discharge of the cells is
35 approached, for holes to be formed in the zinc anode designed as the jar. To protect the cells of the above-mentioned type from leaking, they are provided, an insulating layer being interposed, with a metallic jacket which is provided with a decorative layer. The above-



described jacketing technique is also employed in galvanic cells of the alkali-manganese type. To increase the capacity of the cells, the film labels or adhesive labels disclosed by the documents US 4,869,978, WO/1983⁵ and
5 US 4,801,514 have been used, for some time now, for the purpose of electrical insulation and as decor, since it is thus possible to reduce the thickness of the casing. Keeping the dimensions of the galvanic cell constant it is thereby possible to use a larger cell vessel and thus
10 to introduce more active compound into the cells. The known methods for electrically insulating jacketing of galvanic cells constitute a significant cost factor, and the battery manufacturers are also interested in reducing the thickness of the insulating layer.

15 The object of the invention is to specify galvanic cells and methods for fabricating them, which dispense with the known expensive methods for jacketing of the galvanic cells.

 The object is achieved, according to the invention,
20 tion, by a galvanic cell comprising an outer metallic jar, where the insulating and decorative layer has been applied directly onto the metallic jar by means of a printing and/or coating process.

 The galvanic cells are advantageously fabricated
25 by the insulating and decorative layer being applied prior to the metallic jar being shaped. In a further development of the invention the galvanic cells are fabricated by at least the insulating layer being applied onto the prefabricated metallic jar. A further refinement
30 of the invention consists in the insulating and decorative layer being applied onto the metallic jar of the completed galvanic cell, i.e. onto galvanic cells which have been filled with active materials and sealed. In the process, the galvanic cells are fabricated by way of the
35 insulating layer being applied by electrophoretic coating, spray coating, powder coating, knife application methods or dipping processes and the decorative layer being applied by printing processes such as distortion printing (i.e. printing which takes into account later



deformation of the article during processing), flatbed screen printing, rotary screen printing, offset printing or pad printing. Preference is given to the use of UV-curable coatings. The use of such coatings enables high
5 fabrication cycle rates and reduces the risk of damage to
the cells, since no heat treatment of the cells is
required for efficient curing of the coating layer. The novel galvanic cells and the methods for fabricating them have the following advantages:

- 10 1. A continuous production which can be carried out at high speed
2. Savings in material costs by eliminating the plastic film label
- 15 3. Simplification of the fabrication steps by virtue of reduced fabrication depth, since prefabrication of the printed film tape, cutting and application steps and transport and storage are omitted
- 20 4. Achieving a higher cell capacity, since the coating of the jar is thinner than a film label and as a result a larger cell jar with a greater available volume can be utilized for electrochemically active material
5. High flexibility in choosing the cell design

25 The invention is illustrated by means of the following examples:

Example 1

30 Completed cells were provided, in a flatbed screen printing single step, with the insulating and decorative layer by direct printing of the rotating metallic jar. Printing was carried out with a conventional printing ink, set to a very high viscosity and based on polyacrylates or polyurethanes. Drying was effected by a stream of warm air at about 60°C. A layer



thickness of the dry printing ink of from 10 to 20 μm afforded adequate insulation resistance.

Example 2

To base-coat completed cells, they were spray-coated with epoxy resin, polyurethane resin or a polyacrylate as the insulating layer. The precoated cell jars were then provided with the decorative layer by means of flatbed printing in accordance with Example 1. The printing ink used was a UV-curable coating which cures within seconds. The coating attains an insulation resistance which is comparable to that of adhesive labels.

Example 3

Prior to completion of the cells, the metallic jars were provided, in accordance with Example 2, with a base coat serving as the insulating layer. The decorative layer was applied onto these precoated cells by rotary offset printing, using conventional printing inks. A layer thickness of about 20 μm afforded an insulation resistance which met practical requirements.

20 Example 4

A cell jar is spray-coated with a resilient, abrasion-resistant base coat. This is followed by baking at 180°C. The jars obtained are used for cell fabrication in the same way as uncoated jar bulk material. The coating involving baking and the resilience of the coating layer prevent the coating from spalling off in the bead zone at the bead. Subsequent application of the decor by offset printing is carried out using a UV-curable coating system (layer thickness typically from 1 to 5 μm). This can be concluded by the application of a clear-varnish topcoat (layer thickness typically from 10 to 30 μm). The use of a UV coating has the advantage that curing does not require the cell to be subjected to thermal stress.

35 Example 5

A UV-curable base coat (e.g. 20 μm) is applied onto the finished cell by roller printing. This is followed by application of the decorative layer (usually 2-10 μm) by offset printing, up to seven colors being

customary and possible within one operation. A topcoat layer, in the form of a likewise UV-curable system, is applied at the end for the purpose of additional mechanical protection and to increase the gloss.

5 Example 6

10 A 2-component coating system is applied by spray coating onto the finished cell. Subsequent formation of the decor is effected by offset printing with a UV-curable coating. Additional roller coating is carried out with a UV-curable clear coating, said clear coating containing UV-absorbing or fluorescing components. An advantage of this is that a cell thus printed can be recognized and sorted by scanner systems.

This Sheet Has Been Replaced



THIS SHEET HAS BEEN
REPLACED



Claims

1. A galvanic cell comprising an outer metallic jar which on the outside has an insulating and a decorative layer, wherein the insulating and decorative layer has
5 been applied directly onto the metallic jar by means of a printing and/or coating process.
2. A method for fabricating a cell as claimed in claim 1, wherein the insulating and decorative layer is applied onto the metallic material prior to the metallic
10 jar being shaped.
3. A method for fabricating a cell as claimed in claim 1, wherein at least the insulating layer is applied onto the prefabricated metallic jar.
4. A method for fabricating a cell as claimed in
15 claim 1, wherein the insulating and decorative layer is applied onto the metallic jar of the completed galvanic cell.
5. The method as claimed in any one of claims 2 to 4, wherein the insulating layer is applied by electrophoretic coating, spray coating, powder coating, knife
20 application methods or dipping processes and the decorative layer is applied by printing processes such as distortion printing, flatbed screen printing, rotary screen printing, offset printing or pad printing.
- 25 6. A galvanic cell as claimed in claim 1, wherein
the insulating layer and the decorative layer is a UV-
curable coating.

THIS SHEET HAS BEEN
REPLACED