


Claims

1. A composition (PC1) comprising
 - a) a multistage polymer (MP1) comprising
 - 5 a1) one stage (A1) comprising a polymer (A1) having a glass transition temperature of less than 10°C
 - a2) one stage (A2) comprising a polymer (A1) having a glass transition temperature of at least 60°C and
 - b) a thermoplastic polymer (B1) having a glass transition
10 temperature of at least 30°C and
 - c) a component (LC1) comprising a compound (C1) with at least two polymerizable groups (PG1) and (PG2)characterized in that the polymer (B1) has a mass average molecular weight Mw of between 10 000g/mol and 500 000g/mol and
15 that the component b) represents at most 40wt% of a composition based on a), and b) only and the sum of components a) and b) is between 0.5phr and 100phr for 100phr of component c).
2. The composition according to claim 1, characterized in that
20 the polymer (B1) is a (meth)acrylic polymer.
3. The composition according to claim 1 or 2, characterized in that the polymer (B1) comprises at least 70wt% monomers chosen from C1 to C12 alkyl (meth)acrylates.
- 25 4. The composition according to any of claims 1 to 3, characterized in that the sum of components a) and b) is between 1phr and 15phr for 100phr of component c).
- 30 5. The composition according to any of claims 1 to 3, characterized in that the sum of components a) and b) is between 15phr and 100phr for 100phr of component c).
- 35 6. The composition according to any of claims 1 to 3, characterized in that the sum of components a) and b) is between 21phr and 100phr for 100phr of component c).

7. The composition according to any of claims 1 to 3, characterized in that the sum of components a) and b) is between 50phr and phr for 100phr of component c).
- 5 8. The composition according to any of claims 1 to 7, characterized in that the composition (PC1) is liquid having a viscosity between 1mPa*s and 1000Pa*s at 25°C.
9. The composition according to any of claims 1 to 8, characterized in that the multistage polymer (MP1) is a core/shell particle having a weight average particle size between 15nm and 900nm.
- 10 10. The composition according to any of claims 1 to 9, characterized in that the the mass average molecular weight Mw of polymer (B1) is between 15 000g/mol and 150 000g/mol.
- 15 11. The composition according to any of claims 1 to 9, characterized in that the the mass average molecular weight Mw of polymer (B1) is between 30 000g/mol and 200 000g/mol.
- 20 12. The composition according to any of claims 1 to 11, characterized in that the the polymer (B1) comprises a functional comonomer having the formula (1)



(1)

- 25 wherein R₁ is chosen from H or CH₃ and R₂ is H or an aliphatic or aromatic radical having at least one atom that is not C or H.
- 30 13. The composition according to any of claims 1 to 12, characterized in that the component (LC1) is a liquid having a viscosity between 0.5mPa*s and 10Pa*s at 25°C.

14. The composition according to any of claims 1 to 13, characterized in that component (LC1) additionally comprises a monomer (M1) or a mixture of monomers (Mx).
- 5 15. The composition according to claim 14, characterized in that the monomer (M1) or the mixture of monomers (Mx) is chosen from (meth)acrylic monomers, allyl monomers or styrenic monomers.
- 10 16. The composition according to claim 14, characterized in that the monomer (M1) or the mixture of monomers (Mx) is chosen from alkyl (meth)acrylates that have an alkyl group containing 1 to 10 carbon atoms, hydroxyethyl (meth)acrylate, as well as bifunctional (meth)acrylates such as butanediol di (meth)
15 acrylate, 1,6-hexanediol di(meth)acrylate and di (meth)acrylates having a glycol structure, and polyfunctional (meth)acrylates such as trimethylolpropane tri (meth)acrylate.
- 20 17. The composition according to claim 14, characterized in that the monomer (M1) or the mixture of monomers (Mx) comprises no styrene.
- 25 18. The composition according to claim 14, characterized in that the monomer (M1) or the mixture of monomers (Mx) comprises no styrene based monomers.
- 30 19. The composition according to any of claims 1 to 18, characterized in that the two polymerizable groups (PG1) and (PG2) of compound (C1) are carbon double bonds.
20. The composition according to any of claims 1 to 18, characterized in that the two polymerizable groups (PG1) and (PG2) of compound (C1) are α,β -unsaturated carbonyl groups.
- 35 21. The composition according to any of claims 1 to 18, characterized in that the two polymerizable groups (PG1) and (PG2) of compound (C1) are chosen from an acrylate group, a

methacrylate group or a condensation product comprising maleic acid or itaconic acid or fumaric acid.

22. The composition according to any of claims 1 to 18,
5 characterized in that the compound (C1) is a vinyl ester or an unsaturated polyester.

23. The composition according to any of claims 1 to 18,
10 characterized in that the compound (C1) is a vinyl ester.

24. The composition according to any of claims 1 to 18,
characterized in that the compound (C1) is an unsaturated polyester.

15 25. The composition according to any of claims 1 to 7, characterized in that the component b) represents between 10wt% and 20wt% of a composition based on a) and b) only.

20 26. A method for manufacturing a composition (PC1) according to any of claims 1 to 25 comprising the steps of

i) providing a composition (Ci) comprising

a) a multistage polymer (MP1) comprising

a1) one stage (A1) comprising a polymer (A1) having a glass transition temperature of less than 10°C

25 a2) one stage (A2) comprising a polymer (A2) having a glass transition temperature of at least 60°C and

b) a thermoplastic polymer (B1) having a glass transition temperature of at least 30°C and a mass average molecular weight Mw of between 10 000g/mol and
30 500 000g/mol so that the component b) represents at most 40wt% of a composition based on a) and b);

and

ii) mixing the composition (Ci) with a composition (Ciia) comprising at least one other component or compound present
35 in the composition (PC1); and

iii) optionally mixing the composition obtained in step ii) with the other components or compounds present in the composition (PC1) that have not been added yet in step ii).

27. A method for manufacturing the composition (PC1) according to any of claims 1 to 25 comprising the steps of
- i) providing a polymeric composition (Ci) comprising
 - 5 a) a multistage polymer (MP1) comprising
 - a1) one stage (A1) comprising a polymer (A1) having a glass transition temperature of less than 10°C
 - a2) one stage (A2) comprising a polymer (A2) having a glass transition temperature of at least 60°C and
 - 10 b) a thermoplastic polymer (B1) having a glass transition temperature of at least 30°C and a mass average molecular weight Mw of between 10 000g/mol and 500 000g/mol so that the component b) represents at most 40wt% of a composition based on a) and b),
 - 15 ii) providing a composition (Ciib) comprising c) a component (LC1) comprising a compound (C1) with at least two polymerizable groups (PG1) and (PG2),
 - iii) mixing the compositions (Ci) and (Ciib) comprising the components a), b) and c) in a ratio that the sum of components
 - 20 a) and b) is between 0.5phr and 100phr for 100phr of component c).
28. A method for reducing the preparation time of a composition (PC1) comprising the steps of
- 25 i) providing a polymeric composition (Ci) comprising
 - a) a multistage polymer (MP1) comprising
 - a1) one stage (A1) comprising a polymer (A1) having a glass transition temperature of less than 10°C
 - a2) one stage (A2) comprising a polymer (A2) having a
 - 30 glass transition temperature of at least 60°C and
 - b) a thermoplastic polymer (B1) having a glass transition temperature of at least 30°C and a mass average molecular weight Mw of between 10 000g/mol and 500 000g/mol so that the component b) represents at
 - 35 most 40wt% of a composition based on a) and b),

- ii) providing a composition (Ciib) comprising c) a component (LC1) comprising a compound (C1) with at least two polymerizable groups (PG1) and (PG2),
iii) mixing the compositions (Ci) and (Ciib) comprising the components a), b) and c) in a ratio so that the sum of components a) and b) is between 0.5 and 100phr for 100phr of component c).

29. The method according to any of claims 26 to 28, characterized in that the composition (Ciia) and (Ciib) comprises:

- a polyepoxide or
- a polyepoxid and organic acid with a double bond or
- a vinylester or
- a vinylester and monomer (M1) or the mixture of monomers (Mx)
- unsaturated polyester or
- unsaturated polyester and monomer (M1) or the mixture of monomers (Mx).

30. The method according to any of claims 26 to 28, characterized in that the composition (Ciia) and (Ciib) comprises a polyepoxide.

31. The method according to any of claims 26 to 28, characterized in that the composition (Ciia) and (Ciib) comprises a polyepoxid and organic acid with a double bond.

32. The method according to any of claims 26 to 28, characterized in that the composition (Ciia) and (Ciib) comprises a vinylester.

33. The method according to any of claims 26 to 28, characterized in that the composition (Ciia) and (Ciib) comprises a vinylester and monomer (M1) or the mixture of monomers (Mx).

34. The method according to any of claims 26 to 28, characterized in that the composition (Ciia) and (Ciib) comprises an unsaturated polyester.
- 5 35. The method according to any of claims 26 to 28, characterized in that the composition (Ciia) and (Ciib) comprises an unsaturated polyester and monomer (M1) or the mixture of monomers (Mx).
- 10 36. The method according to any of claims 29 or 31 or 33 or 35, characterized in that the monomer (M1) or the mixture of monomers (Mx) is chosen from (meth)acrylic monomers, allyl monomers or styrenic monomers.
- 15 37. The method according to any of claims 29 or 31 or 33 or 35, characterized in that the monomer (M1) or the mixture of monomers (Mx) comprises no styrene based monomers.
- 20 38. The method according to any of claims 29 or 31 or 33 or 35, characterized in that the monomer (M1) or the mixture of monomers (Mx) is chosen from alkyl (meth)acrylates that have an alkyl group containing 1 to 10 carbon atoms, and hydroxyethyl (meth)acrylate, as well as bifunctional (meth)acrylates such as butanediol di (meth) acrylate, 1,6-hexanediol di(meth)acrylate and di (meth) acrylates having a glycol structure, and polyfunctional (meth)acrylates such as trimethylolpropane tri (meth) acrylate.
- 25 39. A method for manufacturing the composition (PC1) according to any of claims 1 to 25 comprising the steps of
- 30 i) providing a polymeric composition comprising
- a) a multistage polymer (MP1) comprising
- a1) one stage (A1) comprising a polymer (A1) having a glass transition temperature of less than 10°C
- 35 a2) one stage (A2) comprising a polymer (A2) having a glass transition temperature of at least 60°C and

- b) a thermoplastic polymer (B1) having a glass transition temperature of at least 30°C,
ii) providing c) a component (LC1) comprising a compound (C1) with at least two polymerizable groups (PG1) and (PG2),
5 iii) mixing the components a), b) and c).
40. The method according to any of claims 26 to 39, characterized in that in step iii) ratio of sum of components a) and b) is between 15phr and 100phr for 100phr of component c).
10
41. The method according to any of claims 26 to 39, characterized in that in step iii) ratio of sum of components a) and b) is between 21phr and 100phr for 100phr of component c).
- 15 42. The method according to any of claims 26 to 29, characterized in that in step iii) ratio of sum of components a) and b) is between 50phr and 100phr for 100phr of component c).
- 20 43. The method according to any of claims 26 to 42, characterized in that the step iii) the mixing is made at a temperature between 0°C and 50°C.
- 25 44. The method according to any of claims 26 to 42, characterized in that the step iii) the mixing is made at a temperature between 10°C and 30°C.
- 30 45. The method according to any of claims 26 to 44, characterized in that the multistage polymer (MP1) provided is in form of a polymer powder having a total intruded volume of at least 1.2 ml/g as measured by mercury porosimetry.
- 35 46. The method according to any of claims 26 to 44, characterized in that the multistage polymer (MP1) provided is in form of a polymer powder having a total intruded volume between 1.2ml/g and 10ml/g as measured by mercury porosimetry.
47. The method according to any of claims 26 to 46, characterized in that the multistage polymer (MP1) provided is in form of a

polymer powder having relative incremental intrusion of the polymer powder for a pore size above 10 μ m of at most 85%.

48. Use of the composition according to any of claims 1 to 25 or
5 obtained by the method according to any of claims 26 to 47 to prepare an impact modified polymeric composition (PC2).

49. A polymeric composition (PC2) comprising
a) a multistage polymer (MP1) comprising
10 a1) one stage (A1) comprising a polymer (A1) having a glass transition temperature of less than 10°C,
a2) one stage (A2) comprising a polymer (A2) having a glass transition temperature of at least 60°C and
b) a thermoplastic polymer (B1) having a glass transition
15 temperature of at least 30°C and
c) a polymer (P2) comprising units from a compound (C1) with at least two polymerizable groups (PG1) and (PG2), characterized in that the polymer (B1) has a mass average molecular weight Mw of between 10 000g/mol and 500 000g/mol
20 and that the component b) represents at most 40wt% of a composition based on a), and b) only and the sum of components a) and b) is between 0.5phr and 100phr for 100phr of component c).

25 50. The polymeric composition (PC2) according to claim 49, characterized that the polymer (P2) is a thermoset polymer.

51. The polymeric composition (PC2) according to claim 49 or 50, characterized that the polymeric composition (PC2) comprises
30 other components as fibers or mineral fillers.

52. Use of the polymeric composition (PC2) according to claim 49 or 50 or 51 as an adhesive and more preferably a structural adhesive or in a polymeric composite; or in applications as
35 coating, decorative casting, flooring, polymer concrete, solid surfaces, artificial marble, or in marine applications, building and construction, wind energy applications.