

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C04B 35/628, 35/468, H01G 4/12	A1	(11) International Publication Number: WO 99/67189 (43) International Publication Date: 29 December 1999 (29.12.99)
(21) International Application Number: PCT/US99/13980 (22) International Filing Date: 21 June 1999 (21.06.99) (30) Priority Data: 60/090,408 23 June 1998 (23.06.98) US 60/096,668 14 August 1998 (14.08.98) US (71) Applicant: CABOT CORPORATION [US/US]; 75 State Street, Boston, MA 02109-1806 (US). (72) Inventors: MILLER, David, V.; 5787 Fresh Meadow Drive, Macungie, PA 18062 (US). VENIGALLA, Sridhar; 5354 Princeton Road, Macungie, PA 18062 (US). CLANCY, Donald, J.; 1296 Vale Circle, Pottstown, PA 19464 (US). (74) Agent: LANDO, Michelle, B.; Cabot Corporation, 157 Concord Road, P.O. Box 7001, Billerica, MA 01821-7001 (US).	(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>	
(54) Title: BARIUM TITANATE DISPERSIONS		
(57) Abstract		
The invention provides slurries, dispersions, or slips of barium titanate-based particles in a non-aqueous medium and methods of their production. The particles have a coating comprising a metal oxide, metal hydrous oxide, metal hydroxide or organic acid salt of a metal other than barium or titanium. At least 90 percent of the particles have a particle size less than 0.9 micrometer when the coated particles are dispersed by high shear mixing.		