

A process and device for the manufacture of mouldings and mouldings that are manufactured in accordance with that process

Abstract

A measured amount of a material that is crosslinkable by impingement of a suitable form of energy, especially UV light (3), is introduced into a two-part mould (1) of which the cavity (15) determines the shape of a moulding (CL) to be produced. The two mould halves (11, 12) are held a small distance from one another so that a thin annular gap (16) is formed between them, which gap is in communication with the mould cavity (15) and through which gap excess material can escape. The crosslinking is triggered by impingement of the selected form of energy, the impingement being spatially restricted to the cavity (15) by suitable masking (21) so that material disposed outside the mould cavity is not crosslinked. In that manner mouldings are obtained that do not require subsequent mechanical processing, and the mould is reusable. The process is especially, but not, however, exclusively, suitable for the manufacture of contact lenses.

(Fig. 1)

