

ABSTRACT

The present invention relates to a low-temperature curable clear coating composition comprising: an acrylic resin; a first polyester resin; a second polyester resin; and an isocyanate-based curing agent, wherein the first polyester resin has a hydroxyl value of 240 to 320 mg KOH/g, and the second polyester resin has a hydroxyl value of 100 to 180 mg KOH/g.

No Figure