CLAIMS

1. A method, comprising:

forming two vertical transport field effect transistors stacked one atop the other and separated by a resistive random access memory structure, wherein the resistive random access memory structure comprises faceted epitaxy defined by pointed tips, wherein the pointed tips of the faceted epitaxy extend vertically toward each other, wherein the faceted epitaxy is between the two vertical transport field effect transistors, wherein the two vertical transport field effect transistors comprise a source, a channel, and a drain, wherein a contact layer of the resistive random access memory structure functions as the drain of the two vertical transport field effect transistors.

2. The method of claim 1, wherein forming the two vertical transport field effect transistors further comprises:

forming a first source and a second source, wherein the first source is a bottom source and the second source is a top source; and

forming a gate conductor layer surrounding the channel.

3. The method of claim 1, wherein the resistive random access memory structure further comprises;

a metal layer in direct contact with each of the pointed tips of the faceted epitaxy; and

two electrodes, the two electrodes in direct contact with the metal layer.

4. A structure, comprising:

a first vertical field effect transistor, the first vertical field effect transistor comprises a first source, a first channel, and a drain, the first channel separates the first source from the drain;

a second vertical field effect transistor stacked above the first vertical field effect transistor, the second vertical field effect transistor comprises a second source, a second channel and the drain, the second channel separates the second source from the drain; and

a two resistive random access memory structure between the first vertical field effect transistor and the second vertical field effect transistor, the two resistive random access memory structure functioning as the drain of the first and the second vertical transport field effect transistors, wherein the two resistive random access memory structure includes <111> plane bound faceted epitaxy defined by two pointed shape tips, wherein the two pointed shape tips of the faceted epitaxy extend vertically toward each other.

5. The structure of claim 4, wherein the two resistive random access memory structure further comprises:

a metal layer in direct contact with each of the two pointed shape tips of the faceted epitaxy; and

two electrodes in direct contact with the metal layer.

6. The structure of claim 4 or 5, wherein the faceted epitaxy is doped with a dopant and has a doping level of $4x10^{20}cm^{-3}$ to $1.5x10^{21}cm^{-3}$.

7. The structure of claim 6, wherein the dopant is phosphorus or arsenic.

8. The structure of claim 4, wherein the first and the second vertical field effect transistors are n-type vertical field effect transistors.

9. The structure of claim 4, wherein the first and the second vertical field effect transistors are p-type vertical field effect transistors.

10. The structure of claim 4, wherein the first source and the second source have a doping level of $4x10^{20}cm^{-3}$ to $1.5x10^{21}cm^{-3}$.

11. A structure comprising:

a first vertical field effect transistor, the first vertical field effect transistor comprises a first source, a first channel, and a drain, the first channel separates the first source from the drain;

a second vertical field effect transistor stacked above the first vertical field effect transistor, the second vertical field effect transistor comprises a second source, a second channel and the drain, the second channel separates the second source from the drain;

a two resistive random access memory structure between the first vertical field effect transistor and the second vertical field effect transistor, the two resistive random access memory structure functions as the drain of the first and the second vertical transport field effect transistors, wherein the two resistive random access memory structure includes <111> plane bound faceted epitaxy defined by two pointed shape tips, wherein the two pointed shape tips of the faceted epitaxy extend vertically toward each other; and

a gate conductor layer surrounding the first and second channels, wherein the gate conductor layer is separated from the first and second channels by a gate dielectric layer.

12. The structure of claim 11, wherein the two resistive random access memory structure further comprises:

a metal layer, the metal layer is in direct contact with the two pointed shape tips of the faceted epitaxy; and

two electrodes, the two electrodes are in direct contact with the metal layer.

13. The structure of claim 11 or 12, wherein the faceted epitaxy is doped with a dopant and has a doping level of $4x10^{20}cm^{-3}$ to $1.5x10^{21}cm^{-3}$.

14. The structure of claim 13, wherein the dopant is phosphorus or arsenic.

15. The structure of claim 11, wherein the first and the second vertical field effect transistors are n-type vertical field effect transistors.

16. The structure of claim 11, wherein the first and the second vertical field effect transistors are p-type vertical field effect transistors.

17. The structure of claim 11, wherein the first source and the second source have a doping level of $4x10^{20}cm^{-3}$ to $1.5x10^{21}cm^{-3}$.

18. The structure of claim 11, wherein the first source is doped with phosphorus or boron and the second source is doped with phosphorus.