


Pigment compositions, a process for the colouration of paints, printing inks and bulk polymers with these pigment compositions and paints, printing inks and bulk polymers coloured by this process


The invention relates to solid pigment compositions comprising a mixture of a pigment and a thermoplastic resin. Such compositions may be used to incorporate pigment into substrates such as paints, printing inks and bulk polymers, and enable the pigment to be more evenly dispersed in the substrate than if the pigment alone were to be added to the substrate.

The present invention provides a solid pigment composition comprising an intimate mixture of a pigment and a copolymer of a compound of formula I



in which

R is C_{4-8} alkyl, or C_{4-8} cycloalkyl and a lesser amount of a compound of formula II,



in which

R_1 is hydrogen or methyl,


R_2 is hydrogen or C_{1-8} alkyl

R_3 is C_{1-8} alkyl, or

R_2 and R_3 together with the nitrogen atom to which they are attached form a heterocyclic 5- or 6-membered ring which may contain an oxygen or a further nitrogen atom, and

A is a straight or branched chain C_{2-8} alkylene group.

All alkyl groups of more than 2 carbon atoms may be either straight-chain or branched. In the compound of formula I, R is preferably a butyl or cyclohexyl group. More preferably the compound of formula I is isobutyl methacrylate. In the compound of formula II, R_1 is preferably methyl, and R_2 and R_3 as alkyl are preferably C_{1-4} alkyl, more preferably methyl. Where R_2 and R_3 together with the nitrogen atom to which they are attached form a heterocyclic ring, this is preferably a morpholine or piperidine ring. Most preferably, both R_2 and R_3 are methyl. The group A is preferably



or



The preferred compound of formula II is 2-dimethylaminoethyl methacrylate.

The copolymer suitably has a reduced viscosity, as herein defined, of 5—25 ml/g, corres-

ponding approximately to an average molecular weight of 10,000 to 80,000, and a $T_{\lambda\text{max}}$ temperature, as herein defined, above 45°C .

One suitable class of copolymers based on isobutylmethacrylate have molecular weights of 15,000 to 25,000, a melting point range of $80-120^\circ\text{C}$, preferably $92-100^\circ\text{C}$ and an acid number of 0. The weight percentage of comonomer II in the copolymer is preferably 1—10%, more preferably 2—6%, particularly 3%.

The copolymer may also contain up to 10% by weight of one or more additional comonomers capable of free-radical polymerisation, for example vinyl-substituted heterocyclic compounds such as vinylpyridine, vinylimidazole and vinylpyrrolidone; vinyl esters of fatty acids, for example vinyl acetate; vinyl halides, for example vinylidenechloride; vinyl aromatics, for example styrene and vinyltoluene; α -olefins and/or dienes. The amount of any additional comonomer which is present should not be so great as to adversely affect the desirable properties of the final pigment preparation, such as its capability of being ground to a fine powder and its compatibility with a wide range of substrates. Preferably, the weight percentage of any additional comonomer present is no greater than the weight percentage of the comonomer of formula II, and more preferably only comonomers of formulae I and II are present.

The reduced viscosity of a polymer,

$$\frac{\eta_{\text{sp}}}{c}$$

is the specific viscosity η_{sp} of a polymer solution divided by the concentration of the solution expressed as g/ml. The specific viscosity is given by

$$\eta_{\text{sp}} = \frac{t - t_0}{t_0}$$

where t is the time required for a polymer solution to flow through a capillary viscometer at a given temperature and t_0 is the time required for the pure solvent at the same temperature. Although

$$\frac{\eta_{\text{sp}}}{c}$$

is not independent of concentration, it is relatively constant at low concentrations, where $\eta_{\text{sp}} = 0.1$ to 0.2 .

The temperature $T_{\lambda\text{max}}$ is the temperature of maximum vibrational damping of the polymer as

measured by D.I.N. (Deutsche Industrienorm) 53445 or I.S.O. DR 533.

The copolymer may be prepared by conventional addition polymerisation methods, using an initiator such as a peroxide or an azo compound in the proportion of 0.05% to 1% by weight. A suitable initiator is 2,2'-azobis(isobutyronitrile). The polymerisation is carried out in the presence of a chain transfer agent to keep the molecular weight of the copolymer low. Suitable chain transfer agents are mercapto compounds such as 2-mercaptoethanol, used in quantities of up to 2% by weight. A suitable polymerisation process is to seal the mixture of monomers, initiator and chain transfer agent into a flat bag or tube of plastic film and to heat this container in a water bath, for example at 50—100°C. The high surface-to-volume ratio of such a container gives good heat transfer and prevents overheating of the reaction mixture during polymerisation. When polymerisation is complete, the product may be removed from the container and milled to give a granulate or powder.

The intimate mixture of pigment and copolymer is obtained in conventional manner by melt blending or by dissolving the copolymer in a suitable solvent, adding the pigment and removing the solvent by evaporation. The pigment composition according to the invention may contain from 10 to 95% by weight of pigment, preferably 30—80% pigment.

Compositions containing relatively small amounts of pigment are suitably prepared by melt blending in appropriate equipment for example a kneader, roll mill or extruder, and will consist of a continuous matrix of copolymer containing a dispersion of pigment particles. If melt blending is carried out in a roll mill or kneader, the molten mass may be extruded and granulated, or may be allowed to solidify and then ground to a powder.

Alternatively, the pigment may be dispersed in a solution of the copolymer in a suitable solvent, for example in a sand or ball mill, or a blender. The solution may then be dried directly, or a pigment-solvent suspension may be precipitated with water, filtered and dried. Solution techniques may be necessary in order to prepare compositions having high pigment content; according to the pigment content the compositions may consist of a dispersion of pigment particles in a more or less continuous copolymer matrix, or of pigment particles or clumps of particles coated with copolymer.

The pigment composition according to the invention may contain inorganic pigments for example titanium dioxide, iron oxide, chromium oxide and lead chromate or organic pigments, for example those of the azo-, bisazo-, phthalocyanine-, naphthol AS-, benzidine-, isoindolinone-, quinacridone-, dioxazine-, thioindigo- and perylene-types. Mixtures of pigments of one or more types may be used. Essentially all pigments capable of being used

for the mass dyeing of polymer substrates may be used in the present pigment compositions.

In addition to pigments the composition may contain other solid additives, for example fillers such as calcium carbonate or silica.

The pigment compositions of the present invention are compatible with a very wide range of polymers, may be easily incorporated into different types of substrates, and give notably high colour yields in the final products.

The following examples, in which all parts are by weight and all temperatures in degrees Centigrade, illustrate the invention:

Preparation of copolymer

Copolymer 1

A mixture of 97 parts isobutyl methacrylate, 3 parts 2-dimethylaminoethyl methacrylate, 0.2 parts azoisobutyronitrile (AIBN) and 1.3 parts 2-mercaptoethanol is polymerised in a tube of plastic film in a water bath at 50° for 24 hours. The solid product is cured at 100° for 8 hours to reduce the residual monomer content. The polymer had a reduced viscosity (measured at 20° in chloroform) of 8 ml/g.

Copolymer 2

A mixture of 90 parts cyclohexyl methacrylate, 10 parts 2-dimethylaminoethyl methacrylate 0.1 parts AIBN and 1.8 parts 2-mercaptoethanol is polymerised and cured as described for copolymer 1 above. The product had a reduced viscosity of 7 ml/g.

Copolymer 3

A mixture of 96 parts isobutyl methacrylate, 4 parts 2-(4-morpholinyl)ethyl methacrylate, 0.1 part AIBN and 1.6 parts 2-mercaptoethanol is polymerised as described for copolymer 1 above. The product had a reduced viscosity of 8 ml/g.

Copolymer 4

A mixture of 89 parts cyclohexyl methacrylate, 1 part methacrylic acid, 10 parts 2-dimethylaminoethyl methacrylate, 0.1 part AIBN and 2.0 parts 2-mercaptoethanol is polymerised as described for copolymer 1. The product had a reduced viscosity of 6 ml/g.

Preparation of pigment composition

Example 1

50 Parts C.I. Pigment Blue 15:3 are blended with 50 parts of copolymer 1 in a Turbula mixer for 1 hour. The blend is then fed to a mixing extruder at 110°, and the extrudate coarsely granulated then finely ground in a Kolloplex mill.

The product is a 50% pigment composition in powder form, which is very easily incorporated into paints and printing inks and is suitable for the mass dyeing of polyacrylonitrile, polystyrene, ABS, styrene/acrylonitrile polymers, PVC and polyolefins.

Examples 2—4

Copolymer 1 in Example 1 is replaced by copolymers 2—4.

Example 5

30 Parts C.I. Pigment Violet 23 and 70 parts of copolymer 1 are blended in a Turbula mixer for 1 hour, and worked up as described in Example 1 to give a pigment composition containing 30% pigment, which is readily incorporable into the substrates described in Example 1.

Example 6—8

Copolymer 1 in Example 4 is replaced by copolymers 2—4.

Example 9


36 Parts C.I. Pigment Green 7 are stirred into a solution of 24 parts of copolymer 1 and 110 parts isobutanol and are ground in a horizontal ball mill until the pigment is completely dispersed. After that the solvent is eliminated by steam-distillation. The precipitate is washed, dried and if required pulverized in known manner. The product contains 60% pigment, which is readily incorporable into the substrates described in Example 1.

Example 10

50 Parts C.I. Pigment Blue 15:3 are added to a solution of 50 parts copolymer 1 in 100 parts methyl ethyl ketone, and dispersed by mixing in a dissolver. After removal of the solvent by evaporation, the residue is pulverized in a Kolloplex mill. The resulting pigment composition contains 50% pigment, can readily be incorporated into paints and printing inks using normal mixing equipment and can be used for mass dyeing of the substrates described in Example 1.


Claims

1. A solid pigment composition comprising an intimate mixture of a pigment and a copolymer of a compound of formula I



in which

R is C₄₋₈ alkyl, or C₄₋₈ cycloalkyl and a lesser amount of a compound of formula II,



in which

R₁ is hydrogen or methyl,
R₂ is hydrogen or C₁₋₆ alkyl
R₃ is C₁₋₆ alkyl, or

R₂ and R₃ together with the nitrogen atom to which they are attached form a heterocyclic 5- or 6-membered ring which may contain an oxygen or a further nitrogen atom, and

A is a straight or branched chain C₂₋₆ alkylene group.

2. A composition as claimed in Claim 1 in which R in formula I is butyl or cyclohexyl.

3. A composition as claimed in Claim 1 or Claim 2 in which, in formula II, R₁ is methyl; R₂ and R₃ are each methyl or together with the nitrogen atom to which they are attached, form a morpholine or piperidine ring, and A is



or



4. A composition as claimed in any one of the preceding claims in which the copolymer is a copolymer of isobutyl methacrylate and 2-dimethylaminoethyl methacrylate.

5. A composition as claimed in any one of the preceding claims in which the copolymer has a reduced viscosity, as herein defined, of 5—25 ml/g, an average molecular weight of 10,000 to 80,000 and a T_{max} temperature, as herein defined, above 45°C.

6. A composition as claimed in any one of Claims 1 to 4 in which the copolymer is based on isobutyl methacrylate and has a molecular weight of 15,000 to 25,000, a melting point range of 80—120°C and an acid number of 0.

7. A composition as claimed in any one of the preceding claims in which the copolymer contains from 1 to 10% by weight of the compound of formula II.


8. A composition as claimed in any one of the preceding claims containing 30—60% by weight of pigment.

9. A process for the colouration of paints, printing inks and bulk polymers comprising the step of mixing the substrate with a pigment composition as claimed in Claim 1.

10. A dispersion of a pigment in a solution of a copolymer as defined in Claim 1, in a solvent.

Patentansprüche

1. Feste Pigmentzubereitungen enthaltend eine innige Mischung eines Pigmentes und eines Copolymeren einer Verbindung der Formel I



worin

R Alkyl (C₄₋₈) oder Cycloalkyl (C₄₋₈) bedeuten mit einer kleineren Menge einer Verbindung der Formel II

Examples 2—4

Copolymer 1 in Example 1 is replaced by copolymers 2—4.

Example 5

30 Parts C.I. Pigment Violet 23 and 70 parts of copolymer 1 are blended in a Turbula mixer for 1 hour, and worked up as described in Example 1 to give a pigment composition containing 30% pigment, which is readily incorporable into the substrates described in Example 1.

Example 6—8

Copolymer 1 in Example 4 is replaced by copolymers 2—4.

Example 9


36 Parts C.I. Pigment Green 7 are stirred into a solution of 24 parts of copolymer 1 and 110 parts isobutanol and are ground in a horizontal ball mill until the pigment is completely dispersed. After that the solvent is eliminated by steam-distillation. The precipitate is washed, dried and if required pulverized in known manner. The product contains 60% pigment, which is readily incorporable into the substrates described in Example 1.

Example 10

50 Parts C.I. Pigment Blue 15:3 are added to a solution of 50 parts copolymer 1 in 100 parts methyl ethyl ketone, and dispersed by mixing in a dissolver. After removal of the solvent by evaporation, the residue is pulverized in a Kolloplex mill. The resulting pigment composition contains 50% pigment, can readily be incorporated into paints and printing inks using normal mixing equipment and can be used for mass dyeing of the substrates described in Example 1.


Claims

1. A solid pigment composition comprising an intimate mixture of a pigment and a copolymer of a compound of formula I



in which

R is C_{4-8} alkyl, or C_{4-8} cycloalkyl and a lesser amount of a compound of formula II,



in which

R_1 is hydrogen or methyl,

R_2 is hydrogen or C_{1-8} alkyl

R_3 is C_{1-8} alkyl, or

R_2 and R_3 together with the nitrogen atom to which they are attached form a heterocyclic 5- or 6-membered ring which may contain an oxygen or a further nitrogen atom, and

A is a straight or branched chain C_{2-8} alkylene group.

2. A composition as claimed in Claim 1 in which R in formula I is butyl or cyclohexyl.

3. A composition as claimed in Claim 1 or Claim 2 in which, in formula II, R_1 is methyl; R_2 and R_3 are each methyl or together with the nitrogen atom to which they are attached, form a morpholine or piperidine ring, and A is



or



4. A composition as claimed in any one of the preceding claims in which the copolymer is a copolymer of isobutyl methacrylate and 2-dimethylaminoethyl methacrylate.

5. A composition as claimed in any one of the preceding claims in which the copolymer has a reduced viscosity, as herein defined, of 5—25 ml/g, an average molecular weight of 10,000 to 80,000 and a T_{max} temperature, as herein defined, above 45°C .

6. A composition as claimed in any one of Claims 1 to 4 in which the copolymer is based on isobutyl methacrylate and has a molecular weight of 15,000 to 25,000, a melting point range of $80-120^\circ\text{C}$ and an acid number of 0.

7. A composition as claimed in any one of the preceding claims in which the copolymer contains from 1 to 10% by weight of the compound of formula II.


8. A composition as claimed in any one of the preceding claims containing 30—60% by weight of pigment.

9. A process for the colouration of paints, printing inks and bulk polymers comprising the step of mixing the substrate with a pigment composition as claimed in Claim 1.

10. A dispersion of a pigment in a solution of a copolymer as defined in Claim 1, in a solvent.

Patentansprüche


1. Feste Pigmentzubereitungen enthaltend eine innige Mischung eines Pigmentes und eines Copolymeren einer Verbindung der Formel I



worin

R Alkyl (C_{4-8}) oder Cycloalkyl (C_{4-8}) bedeuten mit einer kleineren Menge einer Verbindung der Formel II





R₁ Wasserstoff oder Methyl
R₂ Wasserstoff oder Alkyl (C₁₋₆)
R₃ Alkyl (C₁₋₆) oder

R₂ und R₃ zusammen mit dem Stickstoffatom an welches sie gebunden sind einen heterocyclischen 5- oder 5-gliedrigen Ring der ein Sauerstoffatom oder ein weiteres Stickstoffatom aufweisen kann, und

A eine geradkettige oder verzweigte Alkyl(en)(C₂₋₉) kette bedeuten.

2. Zubereitung nach Patentanspruch 1, dadurch gekennzeichnet, dass R in der Formel I Butyl oder Cyclohexyl bedeutet.

3. Zubereitung nach Patentanspruch 1 oder Patentanspruch 2, dadurch gekennzeichnet, dass in der Verbindung der Formel II R₁ Methyl und R₂ und R₃ Methyl oder zusammen mit dem Stickstoffatom an welches sie gebunden sind einen Morphin- oder Piperidinring, und A



oder



bedeuten.

4. Zubereitung nach einem der Patentansprüche 1—3, dadurch gekennzeichnet, dass das Copolymere aus Isobutylmethacrylat und 2-Dimethylaminoäthylmethacrylat besteht.

5. Zubereitung nach einem der Patentansprüche 1—4, dadurch gekennzeichnet, dass die copolymere Verbindung eine verminderte Viskosität, wie definiert, von 5—25 mVg, ein durchschnittliches Molekulargewicht von 10,000—80,000 und eine T_{max} Temperatur, wie definiert, oberhalb 45°C aufweist.

6. Zubereitung nach einem der Patentansprüche 1—4, dadurch gekennzeichnet, dass das Copolymere auf der Basis von Isobutylmethacrylat aufgebaut ist, eine Molekulargewicht von 15,000—25,000, ein Schmelzpunktsintervall von 80—120°C und eine Säurezahl von Null aufweist.

7. Zubereitung nach einem der Patentansprüche 1—6, dadurch gekennzeichnet, dass der prozentuale Gewichtsanteil des Comonomeren der Formel II im Copolymeren 1—10% beträgt.


8. Zubereitung nach einem der Patentansprüche 1—7, dadurch gekennzeichnet, dass diese 30—60% Pigment enthält.

9. Verfahren zum Färben von Anstrichstoffen, Drucktinten und Polymermassen, dadurch gekennzeichnet, dass man diese Substrate mit einer Zubereitung nach Patentanspruch 1 mischt.

10. Eine Dispersion eines Pigmentes in einer Lösung des Copolymeren nach Patentanspruch 1 in einem Lösungsmittel.


Revendications

1. Une composition pigmentaire solide comprenant un mélange intime d'un pigment et d'un copolymère d'un composé de formule I



dans laquelle

R signifie un groupe alkyle en C₄—C₆ ou cycloalkyle en C₄—C₆, et une quantité moindre d'un composé de formule II



dans laquelle

R₁ signifie l'hydrogène ou un groupe méthyle, R₂ signifie l'hydrogène ou un groupe alkyle en C₁—C₆,


R₃ signifie un groupe alkyle en C₁—C₆, ou bien R₂ et R₃ ensemble avec l'atome d'azote auquel ils sont attachés, forment un noyau hétérocyclique à 5 ou 6 chaînons qui peut contenir un atome d'oxygène ou un atome d'azote supplémentaire, et

A signifie un groupe alkylène en C₂—C₆ à chaîne linéaire ou ramifiée.

2. Une composition selon la revendication 1, caractérisée en ce que R dans la formule I signifie un groupe butyle ou cyclohexyle.

3. Une composition selon la revendication 1 ou 2, caractérisée en ce que dans la formule II,

R₁ signifie un groupe méthyle, R₂ et R₃ signifient chacun un groupe méthyle ou ensemble avec l'atome d'azote auquel ils sont liés, forment un noyau morpholine ou pipéridine, et A signifie



ou



4. Une composition selon l'une quelconque des revendications précédentes, caractérisée en ce que le copolymère est un copolymère de méthacrylate d'isobutyle et de méthacrylate de 2-diméthylaminoéthyle.

5. Une composition selon l'une quelconque des revendications précédentes, caractérisée en



15

9

0022 746

10

ce que le copolymère a une viscosité relative, comme définie ici, de 5—25 ml/g, un poids moléculaire moyen de 10 000 à 80 000 et une température T_{Amax} comme définie ici, supérieure à 45°C.

6. Une composition selon l'une quelconque des revendications 1 à 4, caractérisée en ce que le copolymère est à base de méthacrylate d'isobutyle et possède un poids moléculaire de 15 000 à 25 000, un point de fusion de l'ordre de 80 à 120°C et un indice d'acide de 0.

7. Une composition selon l'une quelconque des revendications précédentes, caractérisée en

ce que la copolymère contient de 1 à 10% en poids du composé de formule II.

8. Une composition selon l'une quelconque des revendications précédentes, caractérisée en ce qu'elle contient de 30 à 60% en poids de pigment.

9. Un procédé pour la coloration des peintures, encres d'impression et polymères masse, comprenant l'étape de mélanger le substrat avec une composition pigmentaire selon la revendication 1.

10. Une dispersion d'un pigment dans une solution d'un copolymère selon la revendication 1, dans un solvant.

5

10

15

20

25

30

35

40

45

50

55

60

65

6

