CLAIMS

1. A clear coating composition, comprising a silicone-modified polyester polyol resin, an acrylic polyol resin, a polyester resin and an isocyanate resin,

wherein the silicone-modified polyester polyol resin has a hydroxyl value of 200 to 300 mgKOH/g, an acid value of 1 mgKOH/g to 20 mgKOH/g, a number average molecular weight of 100 to 2,000 g/mol, and a glass transition temperature of greater than 0°C to 20°C or less and

the polyester resin has a hydroxyl value of 200 to 320 mgKOH/g, an acid value of 15 to 25 mgKOH/g, and a number average molecular weight of 200 to 600 g/mol.

2. The clear coating composition according to claim 1, wherein the acrylic polyol resin has a hydroxyl value of 80 to 200 mgKOH/g, an acid value of greater than 0 mgKOH/g and 30 mgKOH/g or less, a number average molecular weight of 1,000 to 10,000 g/mol, and a glass transition temperature of greater than 0°C and 70°C or less.

3. The clear coating composition according to claim 1, wherein the clear coating composition comprises 1 to 30 parts by weight of the silicone-modified polyester polyol resin, 1 to 30 parts by weight of the acrylic polyol resin, 5 to 40 parts by weight of the polyester resin, and 10 to 40 parts by weight of the isocyanate resin.