

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
10 March 2022 (10.03.2022)

WIPO | PCT

(10) International Publication Number
WO 2022/051698 A8

(51) International Patent Classification:

A61F 2/06 (2013.01) A61F 2/82 (2013.01)

(21) International Application Number:

PCT/US2021/049182

(22) International Filing Date:

06 September 2021 (06.09.2021)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

63/075,242 07 September 2020 (07.09.2020) US
17/467,340 06 September 2021 (06.09.2021) US

(71) Applicant: **FRONTIER BIO CORPORATION**
[US/US]; 8000 Edgewater Dr., Ste 200, Oakland, CA 94621 (US).


(72) Inventor: **BENNETT, Eric**; 8000 Edgewater Dr., Ste 200, Oakland, CA 94621 (US).

(74) Agent: **LOVELESS, Ryan, S.**; Loveless Law Group PLLC, 4760 Preston Road, Suite 244-357, Frisco, TX 75034 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DJ, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, IT, JO, JP, KE, KG, KH, KN, KP, KR, KW, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, WS, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK,

(54) Title: SYSTEM AND METHOD FOR CREATING AN OBJECT WITH A CONDUIT WITH PARTICULAR VASCULAR APPLICATIONS



Two 3-D printed mold pieces (A) are compressed together (B) and molten gallium is cast into the cavity. The solidified gallium (C) is removed from the mold and nanofibers are electrospun onto it (D). The gallium is melted out, leaving only the hollow nanofibrous scaffold (E) in the desired shape which is then seeded with cells and matured (F) in a bioreactor.

FIG. 1

(57) Abstract: According to an embodiment of the disclosure, a method of creating an object with a conduit is disclosed. A material is deposited on a sacrificial collector; and, the sacrificial collector is then removed to create the object with the conduit. Both the object and the sacrificial collector can approximate the shape of desired blood vessel. The method can also include a 3-D printing of the desired shape of the mold and utilization of Gallium as the sacrificial collector. The sacrificial object is created by insertion of the gallium in the mold. After removal of the gallium from the mold, fibers are electrospun onto the gallium. The gallium is removed through melting - leaving a scaffold, the object with the conduit. In addition to the gallium, an extra sacrificial layer of a water-soluble material may be utilized.

[Continued on next page]

EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV,
MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM,
TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW,
KM, ML, MR, NE, SN, TD, TG).

Published:

— *with international search report (Art. 21(3))*

(48) Date of publication of this corrected version:

02 March 2023 (02.03.2023)

(15) Information about Correction:

see Notice of 02 March 2023 (02.03.2023)