

- 1 -

CASTING STEEL STRIP

TECHNICAL FIELD

5 This invention relates to the casting of steel strip in a twin roll caster.

10 In a twin roll caster molten metal is introduced between a pair of contra-rotated horizontal casting rolls which are cooled so that metal shells solidify on the moving roll surfaces and are brought together at the nip between them to produce a solidified strip product delivered downwardly from the nip between the rolls. The term "nip" is used herein to refer to the general region at which the rolls are closest together. The molten metal may be poured from a ladle into a smaller vessel from 15 which it flows through a metal delivery nozzle located above the nip so as to direct it into the nip between the rolls, so forming a casting pool of molten metal supported on the casting surfaces of the rolls immediately above the nip and extending along the length of the nip. This 20 casting pool is usually confined between side plates or dams held in sliding engagement with end surfaces of the rolls so as to dam the two ends of the casting pool against outflow, although alternative means such as electromagnetic barriers have also been proposed.

25 When casting steel strip in a twin roll caster the casting pool will generally be at a temperature in excess of 1550°C and it is necessary to achieve very rapid and even cooling of the molten steel over the casting surfaces of the rolls in order to obtain solidification in 30 the short period of exposure of each point on the casting surfaces to the molten steel casting pool during each revolution of the casting rolls. As described in United States Patent 5,720,336 the heat flux on solidification can be dramatically affected by the nature of the metal 35 oxides which are deposited on the casting roll surfaces from the steel slag which forms on the casting pool during the casting process. Specifically heat flux on

- 2 -

solidification can be greatly enhanced if the metal oxides thus deposited on the casting surfaces are in liquid form at the casting temperature thus ensuring that the casting surfaces are each covered by a layer of material which is at least partially liquid at the solidification temperature of the steel. The oxides solidify with the steel to form oxide inclusions in the steel strip but it is most important that they remain in liquid form at the initial solidification temperature of the steel so that they do not deposit as solid particles on the casting surfaces prior to solidification of the steel and thereby inhibit heat transfer to the molten steel.

DISCLOSURE OF THE INVENTION

Based on experience in casting low carbon steel strip in a twin roll caster and analyzing the oxide inclusions formed when casting steels of differing compositions, we have discovered that the heat fluxes at the casting surfaces are governed by the melting point of inclusions produced from two sources, namely (a) those produced during solidification at the meniscus on initial solidification of the steel on the casting surfaces and (b) those produced during deoxidation of liquid steel in the ladle.

In the solidification of the strip on the casting rolls, the solidification inclusions are localized at the surfaces of the strip. On the other hand, the deoxidation inclusions formed in the ladle are distributed throughout the strip and are markedly coarser than the solidification inclusions. Both sources of inclusions are important to the casting of the strip, and for better casting conditions, the melting points of the inclusions produced from both sources should be low.

The disclosure of United States Patent 5,720,336 was concerned exclusively with the inclusions generated during the solidification. It was assumed in that disclosure that the presence of Al_2O_3 in the slag is

- 3 -

necessarily detrimental and should be minimized or counteracted by calcium treatment. However, we have now found, to the contrary, that the presence of controlled amounts of Al_2O_3 in the deoxidation inclusions can be

5 highly beneficial in ensuring that the inclusions remain molten until the surrounding steel melt has solidified during casting. With manganese/silicon killed steel, the inclusion melting point is very sensitive to changes in the ratio of manganese oxides to silicon oxides, and for

10 some such ratios, the inclusion melting point may be quite high, e.g., greater than 1700°C , which can prevent the formation of a satisfactory liquid film on the casting roll surfaces and may lead to clogging of flow passages in the molten steel delivery system. The deliberate

15 generation of Al_2O_3 in the deoxidation inclusions so as to produce a three phase oxide system comprising MnO , SiO_2 and Al_2O_3 can reduce the sensitivity of the inclusion melting point to changes in the MnO/SiO_2 ratios, and can actually reduce the melting point of the inclusions. The present

20 invention accordingly provides for casting low carbon steel in a twin roll caster which allows for the formation of deoxidation inclusions including Al_2O_3 .

According to the invention there is provided a method of casting low carbon steel strip comprising:

25 assembling a pair of casting rolls forming a nip between the rolls;

forming a molten steel having a slag of iron, manganese, silicon and aluminum oxides producing in a steel strip $\text{MnO}.\text{SiO}_2.\text{Al}_2\text{O}_3$ inclusions having a ratio of

30 MnO/SiO_2 in the range of 0.2 to 1.6 and Al_2O_3 content less than 45%; and

introducing the molten steel between the pair of casting rolls to form a casting pool of molten steel supported on casting surfaces of the rolls above the nip;

35 and

counter rotating the casting rolls to produce a solidified steel strip delivered downwardly from the nip.

- 4 -

The Al_2O_3 content in the inclusions in the molten steel is such as to permit the formation of liquid inclusions. The resulting Al_2O_3 content in the strip formed from the molten steel may range up to a maximum
5 percentage of $35 + 2.9 (R - 0.2)$, where R is the MnO/SiO_2 ratio of the inclusions. The Al_2O_3 content of the resulting strip may be in the range 10% to 30% over a wide range of MnO/SiO_2 ratios. The inclusions may contain at least 3% Al_2O_3 .

10 The inclusions may be dispersed generally throughout the strip and the majority range in a size from 2 to 12 microns.

The invention also provides a cast low carbon steel strip of less than 5mm thickness comprising
15 solidified steel phases and distributed generally throughout the strip solidified $\text{MnO} \cdot \text{SiO}_2 \cdot \text{Al}_2\text{O}_3$ inclusions having an MnO/SiO_2 ratio in the range 0.2 to 1.6 and an Al_2O_3 content in the range 3% to 45%. The deoxidation inclusions may have a size range of 2 to 12 microns.

20 A novel low carbon steel strip may be produced described by the above method by which it is produced.

BRIEF DESCRIPTION OF THE DRAWINGS

In order that the invention may be more fully
25 explained, results of experimental work carried out to date will be described with reference to the accompanying drawings in which:

Figure 1 is a plan view of a continuous strip caster which is operable in accordance with the invention;

30 Figure 2 is a side elevation of the strip caster shown in Figure 1;

Figure 3 is a vertical cross-section on the line 3-3 in Figure 1;

35 Figure 4 is a vertical cross-section on the line 4-4 in Figure 1;

Figure 5 is a vertical cross-section on the line 5-5 in Figure 1;

- 5 -

Figure 6 illustrates the effect of MnO/SiO_2 ratios on inclusion melting point;

Figure 7 illustrates MnO/SiO_2 ratios obtained from inclusion analysis carried out on samples taken from various locations in a strip caster during the casting of low carbon steel strip;

Figure 8 illustrates the effect on inclusion melting point by the addition of Al_2O_3 at varying contents; and

Figure 9 illustrates how Al_2O_3 levels may be adjusted within a safe operating region when casting low carbon steel in order to keep the melting point of the oxide inclusions below a casting temperature of about $1580^\circ\text{C}.$;

Figure 10 is a micrograph of an illustrative $\text{MnO}.\text{SiO}_2.\text{Al}_2\text{O}_3$ inclusion of 9.3 microns in diameter;

Figure 11 is a micrograph of an illustrative $\text{MnO}.\text{SiO}_2.\text{Al}_2\text{O}_3$ inclusion of 5.6 microns in diameter;

Figure 12 is a micrograph of an illustrative $\text{MnO}.\text{SiO}_2.\text{Al}_2\text{O}_3$ inclusion of 4.1 microns in diameter;

Figure 13 is an x-ray spectrum of the illustrative $\text{MnO}.\text{SiO}_2.\text{Al}_2\text{O}_3$ inclusion of Figure 10;

Figure 14 is an x-ray spectrum of the illustrative $\text{MnO}.\text{SiO}_2.\text{Al}_2\text{O}_3$ inclusion of Figure 11; and

Figure 15 is an x-ray spectrum of the illustrative $\text{MnO}.\text{SiO}_2.\text{Al}_2\text{O}_3$ inclusion of Figure 12.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENT

Figures 1 to 5 illustrate a twin roll continuous strip caster which has been operated in accordance with the present invention. This caster comprises a main machine frame 11 which stands up from the factory floor 12. Frame 11 supports a casting roll carriage 13 which is horizontally movable between an assembly station 14 and a casting station 15. Carriage 13 carries a pair of parallel casting rolls 16 to which molten metal is supplied during a casting operation from a 35 ladle 17

- 6 -

via a tundish 18 and delivery nozzle 19 to create a casting pool 30. Casting rolls 16 are water cooled so that shells solidify on the moving roll surfaces 16A and are brought together at the nip between them to produce a solidified strip product 20 at the roll outlet. This product 20 is fed to a standard coiler 21 and may subsequently be transferred to a second coiler 22. A receptacle 23 is mounted on the machine frame adjacent the casting station and molten metal can be diverted into this receptacle via an overflow spout 24 on the tundish or by withdrawal of an emergency plug 25 at one side of the tundish if there is a severe malformation of product or other malfunction during a casting operation.

Roll carriage 13 comprises a carriage frame 31 mounted by wheels 32 on rails 33 extending along part of the main machine frame 11 whereby roll carriage 13 as a whole is mounted for movement along the rails 33. Carriage frame 31 carries a pair of roll cradles 34 in which the rolls 16 are rotatably mounted. Roll cradles 34 are mounted on the carriage frame 31 by inter-engaging complementary slide members 35, 36 to allow the cradles to be moved on the carriage under the influence of hydraulic cylinder units 37, 38 to adjust the nip between die casting rolls 16 and to enable the rolls to be rapidly moved apart for a short time interval when it is required to form a transverse line of weakness across the strip as will be explained in more detail below. The carriage is movable as a whole along the rails 33 by actuation of a double acting hydraulic piston and cylinder unit 39, connected between a drive bracket 40 on the roll carriage and the main machine frame so as to be actuable to move the roll carriage between the assembly station 14 and casting station 15 and vice versa.

Casting rolls 16 are contra rotated through drive shafts 41 from an electric motor and transmission mounted on carriage frame 31. Rolls 16 have copper peripheral walls formed with a series of longitudinally extending and

- 7 -

circumferentially spaced water cooling passages supplied with cooling water through the roll ends from water supply ducts in the roll drive shafts 41 which are connected to water supply hoses 42 through rotary glands 43. The roll
5 may typically be about 500 mm in diameter and up to 2000 mm, long in order to produce 2000 mm wide strip product.

Ladle 17 is of entirely conventional construction and is supported via a yoke 45 on an overhead crane whence
10 it can be brought into position from a hot metal receiving station. The ladle is fitted with a stopper rod 46 actuatable by a servo cylinder to allow molten metal to flow from the ladle through an outlet nozzle 47 and refractory shroud 48 into tundish 18.

15 Tundish 18 is also of conventional construction. It is formed as a wide dish made of a refractory material such as magnesium oxide (MgO). One side of the tundish receives molten metal from the ladle and is provided with the aforesaid overflow 24 and emergency plug 25. The
20 other side of the tundish is provided with a series of longitudinally spaced metal outlet openings 52. The lower part of the tundish carries mounting brackets 53 for mounting the tundish onto the roll carriage frame 31 and provided with apertures to receive indexing pegs 54 on the
25 carriage frame so as to accurately locate the tundish.

Delivery nozzle 19 is formed as an elongate body made of a refractory material such as alumina graphite. Its lower part is tapered so as to converge inwardly and downwardly so that it can project into the nip between
30 casting rolls 16. It is provided with a mounting bracket 60 whereby to support it on the roll carriage frame and its upper part is formed with outwardly projecting side flanges 55 which locate on the mounting bracket.

Nozzle 19 may have a series of horizontally
35 spaced generally vertically extending flow passages to produce a suitably low velocity discharge of metal throughout the width of the rolls and to deliver the

- 8 -

molten metal into the nip between the rolls without direct impingement on the roll surfaces at which initial solidification occurs. Alternatively, the nozzle may have a single continuous slot outlet to deliver a low velocity
5 curtain of molten metal directly into the nip between the rolls and/or it may be immersed in the molten metal pool.

The pool is confined at the ends of the rolls by a pair of side closure plates 56 which are held against stepped ends 57 of the rolls when the roll carriage is at
10 the casting station. Side closure plates 56 are made of a strong refractory material, for example boron nitride, and have scalloped side edges 81 to match the curvature of the stepped ends 57 of the rolls. The side plates can be mounted in plate holders 82 which are movable at the
15 casting station by actuation of a pair of hydraulic cylinder units 83 to bring the side plates into engagement with the stepped ends of the casting rolls to form end closures for the molten pool of metal formed on the casting rolls during a casting operation.

20 During a casting operation the ladle stopper rod 46 is actuated to allow molten metal to pour from the ladle to the tundish through the metal delivery nozzle whence it flows to the casting rolls. The clean head end of the strip product 20 is guided by actuation of an apron
25 table 96 to the jaws of the coiler 21. Apron table 96 hangs from pivot mountings 97 on the main frame and can be swung toward the coiler by actuation of an hydraulic cylinder unit 98 after the clean head end has been formed. Table 96 may operate against an upper strip guide flap 99
30 actuated by a piston and a cylinder unit 101 and the strip product 20 may be confined between a pair of vertical side rollers 102. After the head end has been guided in to the jaws of the coiler, the coiler is rotated to coil the strip product 20 and the apron table is allowed to swing
35 back to its inoperative position where it simply hangs from the machine frame clear of the product which is taken directly onto the coiler 21. The resulting strip

- 9 -

product 20 may be subsequently transferred to coiler 22 to produce a final coil for transport away from the caster.

Full particulars of a twin roll caster of the kind illustrated in FIGS. 1 to 5 are more fully described in our U.S. Pat. Nos. 5,184,668 and 5,277,243 and International Patent Application PCT/AU93/00593.

Extensive casting of manganese silicon killed low carbon steel strip in a twin roll caster has shown that the melting point of deoxidation inclusions is very sensitive to changes in the MnO/SiO₂ ratios for those inclusions. This is illustrated in Figure 6 which plots variations in inclusion melting point against the relevant MnO/SiO₂ ratios. When casting low carbon steel strip the casting temperature is about 1580°C. It will be seen from Figure 6 that over a certain range of MnO/SiO₂ ratios the inclusion melting point is much higher than this casting temperature and may be in excess of 1700°C. With such high melting points it is not possible to satisfy the requirement of ensuring the maintenance of a liquid film on the casting roll surfaces, and steel of this composition may not be castable. Furthermore, clogging of flow passages in the delivery nozzle and other parts of the steel delivery system can become a problem.

Although manganese and silicon levels in the steel can be adjusted with a view to producing the desired MnO/SiO₂ ratios, experience has shown that it is very difficult to ensure that the desired MnO/SiO₂ ratios are in fact achieved and maintained in practice in a commercial plant. For example, we have determined that a steel composition having a manganese content of 0.6% and a silicon content of 0.3% is a desirable chemistry and based on equilibrium calculations should produce a MnO/SiO₂ ratio greater than 1.2. However, our experience in operating a commercial roll casting plant has shown that much lower MnO/SiO₂ ratios are obtained. This is illustrated by Figure 7 in which MnO/SiO₂ ratios obtained from inclusion analysis carried out on steel samples taken at various

- 10 -

locations in a commercial scale strip caster during casting of M06 steel strip, the various locations being identified as follows:

- .5 L1: ladle
- T1, T2, T3: a tundish which receives metal
 from the ladle.
- TP2, TP3: a transition piece below the
 tundish.
- 10 S, 1, 2: successive parts of the formed
 strip.

 It will be seen from Figure 7 that the measured
MnO/SiO₂ ratios are all considerably lower than the
15 calculated expected ratio of more than 1.2. Moreover
small changes in MnO/SiO₂ ratio, for example a reduction
from 0.9 to 0.8, can increase the melting point
considerably as seen in Figure 6. Also, during steel
transfer operation from the ladle to the mould, steel
20 exposure to air will cause re-oxidation which will tend to
further reduce the MnO/SiO₂ ratios (Si has more affinity
for oxygen compared to Mn for oxygen, and therefore, more
SiO₂ will be formed, lowering the ratio). This effect can
clearly be seen in Figure 7 where the MnO/SiO₂ ratios in
25 the tundish (T1, T2, T3), transition piece (TP2, TP3) and
strip (S, 1, 2) are lower than in the ladle (L1).

 We have found that by introducing controlled
alumina levels, MnO.SiO₂.Al₂O₃ based inclusions can produce
the following benefits: lower inclusion melting point
30 (particularly at lower values of MnO/SiO₂ ratios); and
reduced sensitivity of inclusion melting point to changes
in MnO/SiO₂ ratios.

 These benefits are illustrated by Figure 8, which
plots measured values of inclusion melting point for
35 differing MnO/SiO₂ ratios with varying Al₂O₃ content in the
inclusions. These results show that low carbon steel of
varying MnO/SiO₂ ratios can be made castable with proper

- 11 -

control of Al_2O_3 levels. This is further shown by Figure 9 which shows the range of Al_2O_3 contents for varying MnO/SiO_2 ratios which will ensure an inclusion melting point of less than 1580°C , which is a typical casting temperature for a silicon manganese killed low carbon steel. It will be seen that the upper limit of Al_2O_3 content ranges from about 35% for an MnO/SiO_2 ratio of 0.2 to about 39% for an MnO/SiO_2 ratio of 1.6. The increase of this maximum is approximately linear and the upper limit or maximum Al_2O_3 content can therefore be expressed as $35+2.9 (R-0.2)$.

For MnO/SiO_2 ratios of less than about 0.9 it is essential to include Al_2O_3 to ensure an inclusion melting point less than 1580°C . A minimum of about 3% Al_2O_3 is essential and a reasonable minimum would be of the order of 10% Al_2O_3 . For MnO/SiO_2 ratios above 0.9, it may be theoretically possible to operate with negligible Al_2O_3 content. However, as previously explained, the MnO/SiO_2 ratios actually obtained in a commercial plant can vary from the theoretical, calculated expected values and can change at various locations through the strip caster. Moreover the melting point can be very sensitive to minor changes in this ratio. Accordingly it is desirable to control the Al_2O_3 level to produce an Al_2O_3 content of at least 3% for all silicon manganese killed low carbon steels.

The solidification inclusions formed at the meniscus level of the pool on initial solidification become localized on the surface of the final strip product and can be removed by scaling or pickling. The deoxidation inclusions on the other hand are distributed generally throughout the strip. They are coarser than the solidification inclusions and are generally in the size range 2 to 12 microns. They can readily be detected by SEM or other techniques.

FIGS. 10-12 are SEM micrographs of illustrative $\text{MnO}.\text{SiO}_2.\text{Al}_2\text{O}_3$ inclusions from one heat showing the

- 12 -

measured inclusion size. Each micrograph represents a 61 x 500 μm section of strip 20 magnified to show $\text{MnO.SiO}_2.\text{Al}_2\text{O}_3$ inclusions 7, 8, and 9, respectively. The magnification and scale of the micrograph is shown on each Figure. $\text{MnO.SiO}_2.\text{Al}_2\text{O}_3$ inclusion 7 has a diameter of about 9.3 microns, $\text{MnO.SiO}_2.\text{Al}_2\text{O}_3$ inclusion 8 has a diameter of about 5.6 microns, and $\text{MnO.SiO}_2.\text{Al}_2\text{O}_3$ inclusion 9 has a diameter of about 4.1 microns.

By bombarding the illustrative $\text{MnO.SiO}_2.\text{Al}_2\text{O}_3$ inclusions 7, 8, 9 with an electron beam, x-rays are emitted from the inclusions thereby creating respective spectra as shown in FIGS. 13-15. The x-axis of the spectra shows the x-ray energy in Kev and the y-axis shows the number of counts measured at the different energy levels over the x-ray energy spectra. Because each oxide in the inclusion has a signature x-ray emission characteristic over the spectrum, the composition of each inclusion 7, 8, 9 may be determined, after taking into account atom interaction corrections familiar to those skilled in the art.

For $\text{MnO.SiO}_2.\text{Al}_2\text{O}_3$ inclusion 7 of FIG. 10 of 9.3 microns in diameter, the corresponding histogram FIG. 13 shows the oxide composition and oxide distribution of the inclusion to be:

Oxide	Measured Percent by Wt.	Normalised Percent by Wt.
MgO	1.06	1.11
Al_2O_3	41.13	43.19
SiO_2	26.91	28.26
SO	0.82	0.86
CaO	1.61	1.69
TiO_2	1.17	1.23
MnO	21.19	22.25
FeO	1.30	1.37
Total		99.96

- 13 -

For $\text{MnO}.\text{SiO}_2.\text{Al}_2\text{O}_3$ inclusion 8 of FIG. 11 of 5.6 microns in diameter, the corresponding histogram FIG. 14 shows the oxide composition and oxide distribution to be:

Oxide	Measured Percent by Wt.	Normalised Percent by Wt.
MgO	0.65	0.68
Al_2O_3	38.02	39.92
SiO_2	27.32	28.69
SO	0.73	0.77
CaO	0.34	0.36
TiO_2	1.15	1.21
MnO	25.11	26.37
FeO	1.70	1.79
Total		99.79

5

For $\text{MnO}.\text{SiO}_2.\text{Al}_2\text{O}_3$ inclusion 9 of FIG. 12 of 4.1 microns in diameter, the corresponding histogram FIG. 14 shows the oxide composition and oxide distribution of the inclusion to be:

10

Oxide	Measured Percent by Wt.	Normalised Percent by Wt.
MgO	0.35	0.38
Al_2O_3	32.54	35.14
SiO_2	28.26	30.52
SO	0.70	0.76
CaO	0.56	0.60
TiO_2	1.07	1.16
MnO	26.35	28.46
FeO	2.69	2.91
Total		99.93

These measurements show that inclusions 7, 8 and 9 have Al_2O_3 content less than about 45 % and are of different sizes between 2 and 12 microns in diameter. Also, the measured ratios of these MnO/SiO_2 illustrative

15

- 14 -

MnO.SiO₂.Al₂O₃ inclusions is 0.79 for inclusion 7, 0.92 for inclusion 8 and 0.93 for inclusion 9.

Although the invention has been illustrated and described in detail in the foregoing drawings and
5 description with reference to several embodiments, it should be understood that the description is illustrative and not restrictive in character, and that the invention is not limited to the disclosed embodiments. Rather, the
10 present invention covers all variations, modifications and equivalent structures that come within the scope and spirit of the invention. Additional features of the invention will become apparent to those skilled in the art upon consideration of the detailed description, which
15 exemplifies the best mode of carrying out the invention as presently perceived. Many modifications may be made to the present invention as described above without departing from the spirit and scope of the invention.

- 15 -

CLAIMS:

1. A method of casting low carbon steel strip comprising:

5 assembling a pair of casting rolls forming a nip between the rolls;

forming a molten steel having a slag of iron, manganese, silicon and aluminum oxides producing in a steel strip $\text{MnO} \cdot \text{SiO}_2 \cdot \text{Al}_2\text{O}_3$ inclusions having a ratio of MnO/SiO_2 in the range of 0.2 to 1.6 and Al_2O_3 content less than 45%;

10 introducing the molten steel between the pair of casting rolls to form a casting pool of molten steel supported on casting surfaces of the rolls above the nip; and

15 counter rotating the casting rolls to produce the solidified steel strip delivered downwardly from the nip between the casting rolls.

20 2. The method of Claim 1 wherein the Al_2O_3 content is up to a percentage of $35 + 2.9 (R - 0.2)$, where R is the MnO/SiO_2 ratio of the inclusions.

25 3. The method of Claim 1 wherein the $\text{MnO} \cdot \text{SiO}_2 \cdot \text{Al}_2\text{O}_3$ inclusions contain at least 3% Al_2O_3 .

4. The method of Claim 1 wherein the Al_2O_3 content of the $\text{MnO} \cdot \text{SiO}_2 \cdot \text{Al}_2\text{O}_3$ inclusions is in the range 10% to 30%.

30 5. The method of Claim 1 wherein $\text{MnO} \cdot \text{SiO}_2 \cdot \text{Al}_2\text{O}_3$ inclusions are dispersed through the strip.

6. The method of Claim 1 wherein the majority of the $\text{MnO} \cdot \text{SiO}_2 \cdot \text{Al}_2\text{O}_3$ inclusions range in size from 2 to 12 microns in diameter.

- 16 -

7. A cast low carbon steel strip made by a method comprising the steps of:
assembling a pair of casting rolls forming a nip between the rolls;
5 forming a molten steel having a slag of iron, manganese, silicon and aluminum oxides producing in a steel strip $\text{MnO} \cdot \text{SiO}_2 \cdot \text{Al}_2\text{O}_3$ inclusions having a ratio of MnO/SiO_2 in the range of 0.2 to 1.6 and Al_2O_3 content less than 45%;
10 introducing the molten steel between the pair of the casting rolls to form a casting pool of molten steel supported on casting surfaces of the rolls above the nip; and
counter rotating the casting rolls to produce a
15 solidified steel strip delivered downwardly from the nip between the casting rolls.
8. The cast low carbon steel strip of Claim 7 wherein the Al_2O_3 content is up to a percentage of $35 + 2.9$
20 $(R - 0.2)$, where R is the MnO/SiO_2 ratio of the inclusions.
9. The cast low carbon steel strip of Claim 7 wherein the $\text{MnO} \cdot \text{SiO}_2 \cdot \text{Al}_2\text{O}_3$ inclusions may contain at least 3% Al_2O_3 .
25
10. The cast low carbon steel strip of Claim 7 wherein the Al_2O_3 content of the $\text{MnO} \cdot \text{SiO}_2 \cdot \text{Al}_2\text{O}_3$ inclusions is in the range 10% to 30%.
- 30 11. The cast low carbon steel strip of Claim 7 wherein $\text{MnO} \cdot \text{SiO}_2 \cdot \text{Al}_2\text{O}_3$ inclusions are dispersed through the strip.
12. The cast low carbon steel strip of Claim 7
35 wherein the majority of $\text{MnO} \cdot \text{SiO}_2 \cdot \text{Al}_2\text{O}_3$ inclusions range in size from 2 to 12 microns in diameter.