

DESCRIPTION

Title of Invention

POLYESTER RESIN FOR ANTIFOULING COATING MATERIAL,
METHOD FOR PRODUCING SAME, ANTIFOULING COATING
5 MATERIAL COMPOSITION, ANTIFOULING COATING FILM,
AND ANTIFOULING BASE

Technical Field

[0001] The present invention relates to a polyester resin for an antifouling coating material and to a method for producing it, to an
10 antifouling coating material composition comprising the polyester resin, and to an antifouling coating film and antifouling base using the antifouling coating material composition.

Background Art

[0002] The surfaces of base materials that are subjected to underwater
15 conditions for long periods, in ships, underwater structures, fishing nets and the like, are prone to attachment of various types of aquatic creatures including animal life such as oysters, mussels and barnacles or plant life such as laver, as well as bacteria. Proliferation of these aquatic creatures on base surfaces can produce increased ship surface
20 roughness, and can thus lower speed and increase fuel consumption, while also potentially resulting in damage as anticorrosive coating films provided on base surfaces can become damaged, reducing the strength and function of underwater structures or notably shortening their life. In addition, aquatic creatures adhere to and proliferate on
25 fishing nets such as aquaculture nets and fixed shore nets, often causing serious problems such as oxygen deficient mortality of fish catches due

to mesh obstruction. Furthermore, adhesion of aquatic creatures to seawater plumbing pipes for thermal power and nuclear power plants, and their proliferation, can create hindrances to the plumbing circulation of cooling water. Much research and development has
5 been devoted to antifouling coating materials designed to be coated onto base surfaces to prevent adhesion of aquatic creatures.

[0003] For example, patent literature 1 discloses a hydrolyzable polyester resin for an antifouling coating material, comprising a specific dicarboxylic acid component and a specific glycol component,
10 and having improved resistance to seawater and solubility.

[0004] Furthermore, in light of revised air pollution prevention laws and environmental problems, there has been demand in the field of antifouling coating materials for reducing volatile organic compound (VOC) contents of coating materials, in addition to providing
15 prolonged antifouling performance (long-term antifouling properties) and reducing re-coating operations.

[0005] For example, patent literature 2 discloses a two-pack reactive antifouling coating material composition comprising a polyester resin having a specific acid value and hydroxyl value for the solid portion, in
20 order to achieve both low VOC and a long-term antifouling property.

Citation List

Patent Literature

[0006] Patent Literature 1: Japanese Unexamined Patent Application Publication No. 2010-95585

25 Patent Literature 2: Japanese Patent Publication No. 4621901

Summary of Invention

Technical Problem

[0007] With conventional antifouling coating materials such as described in patent literature 1, it is necessary to use a large amount of solvent in order to obtain a viscosity suitable for coating.

5 Consequently, the coating materials that can be provided for practical use have high VOC contents and therefore low environmental friendliness.

Antifouling coating material compositions exhibiting low VOC have also been developed, but because curing is slow compared to
10 conventional antifouling coating materials, and depressions and the like form in the coating films when they are contacted with blocks, they have been difficult to use for coating steps in new shipbuilding operations that require contact with blocks, and when launching is initiated before the coatings have been sufficiently hardened, problems
15 such as depressions and warping or peeling have occurred when the ships are pushed by tugboats or contacted with docks during berthing.

In patent literature 2 mentioned above there is described a two-pack reactive hydrolyzable antifouling coating material composition using a reactive polyester resin, but there has been room for improvement in
20 that with two-pack reactive types, the environmental temperature has a major effect on the reactivity/drying property, the reactivity being lowered when the environmental temperature is low, and in that two-pack reactive compositions require more processing steps during coating (effort for can opening and stirring), and more time and labor
25 are necessary for coating operations compared to one-pack coating materials.

[0008] It is an object of the present invention, which has been accomplished in light of the aforementioned problems of the prior art, to provide a polyester resin for an antifouling coating material that has improved storage stability while maintaining low VOC, thereby
5 allowing preparation in a one-pack form, and that allows increased curability to be achieved and can provide a satisfactory antifouling property and coating property for prolonged periods, as well as a method for producing it, and an antifouling coating material composition.

10 **Solution to Problem**

[0009] The invention relates to the following.

[1] A polyester resin for an antifouling coating material obtained by reacting a (a) trihydric or greater alcohol, a (b) dibasic acid or its anhydride and a (c) divalent alcohol, and then further reacting with an
15 (d) alicyclic dibasic acid or its anhydride.

[2] The polyester resin for an antifouling coating material according to [1], wherein the (d) alicyclic dibasic acid or its anhydride is an alicyclic dibasic acid anhydride.

[3] The polyester resin for an antifouling coating material according to
20 [1] or [2], wherein the (d) alicyclic dibasic acid or its anhydride comprises hexahydrophthalic anhydride.

[4] The polyester resin for an antifouling coating material according to any one of [1] to [3], wherein the (a) trihydric or greater alcohol comprises one or more of glycerin and trimethylolpropane.


25 [5] The polyester resin for an antifouling coating material according to any one of [1] to [4], which comprises one or more of an alicyclic

dibasic acid anhydride and an aromatic dibasic acid anhydride as the (b) dibasic acid or its anhydride.

[6] The polyester resin for an antifouling coating material according to any one of [1] to [4], wherein the (c) divalent alcohol is a branched
5 alkylene glycol.

[7] A polyester resin for an antifouling coating material comprising a compound having the structure represented by formula (1).

[Chemical Formula 1]



10 [In formula (1), R^1 is selected from among C3-24 trivalent or tetravalent hydrocarbon groups, R^2 and R^3 are selected from among C2-34 divalent hydrocarbon groups, R^4 is selected from among C3-24 divalent alicyclic hydrocarbon groups, and n represents an integer of 3 or 4.]

15 [8] The polyester resin for an antifouling coating material according to any one of [1] to [7], wherein the acid value of the solid portion is 50 to 250 mgKOH/g.

[9] A method for producing a polyester resin for an antifouling coating material, comprising a first step of reacting a (a) trihydric or greater
20 alcohol, a (b) dibasic acid or its anhydride and a (c) divalent alcohol, and a second step of further reacting an (d) alicyclic dibasic acid or its anhydride after the first step.

[10] The method for producing a polyester resin for an antifouling coating material according to [9], wherein the (d) alicyclic dibasic acid
25 or its anhydride is an alicyclic dibasic acid anhydride.

[11] The method for producing a polyester resin for an antifouling

coating material according to [9] or [10], wherein the (d) alicyclic dibasic acid or its anhydride comprises hexahydrophthalic anhydride.

[12] The method for producing a polyester resin for an antifouling coating material according to any one of [9] to [11], wherein the (a)
5 trihydric or greater alcohol comprises one or more of glycerin and trimethylolpropane.

[13] The method for producing a polyester resin for an antifouling coating material according to any one of [9] to [12], wherein the polyester resin comprises one or more of an alicyclic dibasic acid
10 anhydride and an aromatic dibasic acid anhydride as the (b) dibasic acid or its anhydride.

[14] The method for producing a polyester resin for an antifouling coating material according to any one of [9] to [13], wherein the (c) divalent alcohol is a branched alkylene glycol.

15 [15] A coating composition comprising the polyester resin according to any one of [1] to [8].

[16] An antifouling coating material composition comprising the polyester resin according to any one of [1] to [8].

[17] The antifouling coating material composition according to [16],
20 further comprising a polyvalent metal compound.

[18] The antifouling coating material composition according to [17], wherein the polyvalent metal compound is at least one compound selected from the group consisting of oxides, hydroxides, halides and carbonates of divalent or trivalent metals.

25 [19] The antifouling coating material composition according to [17] or [18], wherein the polyvalent metal compound is zinc oxide.

[20] The antifouling coating material composition according to any one of [17] to [19], wherein the polyvalent metal compound content is 10 to 700 parts by mass with respect to 100 parts by mass of the polyester resin.

5 [21] The antifouling coating material composition according to any one of [16] to [20], further comprising a rosin and/or rosin derivative.

[22] The antifouling coating material composition according to any one of [16] to [21], further comprising an antifouling agent.

10 [23] The antifouling coating material composition according to any one of [16] to [22], further comprising a plasticizer.

[24] The antifouling coating material composition according to any one of [16] to [23], further comprising an extender pigment (excluding said polyvalent metal compound).

15 [25] The antifouling coating material composition according to any one of [16] to [24], further comprising a pigment dispersant.

[26] The antifouling coating material composition according to any one of [16] to [25], further comprising a color pigment.

[27] The antifouling coating material composition according to any one of [16] to [26], further comprising a dehydrating agent.

20 [28] The antifouling coating material composition according to any one of [16] to [27], further comprising a volatile organic compound, wherein the volatile organic compound content is no greater than 400 g/L.

25 [29] An antifouling coating film obtained by curing the antifouling coating material composition according to any one of [16] to [28].

[30] An antifouling base obtained by coating or impregnating a base

with the antifouling coating material composition according to any one of [16] to [28], and curing the coating composition that has been coated onto or impregnated into the base to form an antifouling coating film on the base.

- 5 [31] A method for producing an antifouling base comprising:
coating or impregnating a base with the antifouling coating material composition according to any one of [16] to [28], and
curing the coating composition that has been coated onto or impregnated into the base to form an antifouling coating film on the
10 base.

Advantageous Effects of Invention

- [0010] According to the invention it has become possible to provide a polyester resin for an antifouling coating material with excellent storage stability and curability, to be used in an antifouling coating
15 material that requires improved curability and low VOC, as well as a method for producing it.

- Also according to the invention, it is possible to provide a low-VOC high solid-type hydrolyzable antifouling coating material composition with satisfactory balance between the various aspects of performance,
20 while having minimal environmental load and minimal effects on the human body and low VOC.

Furthermore, according to the invention it is possible to provide an antifouling coating film with an excellent long-term antifouling property and excellent mechanical strength.

- 25 In addition, according to the invention it is possible to provide an antifouling base that can prevent fouling of the base surfaces of

underwater structures, ship outer plates, fishing nets, fishing gear base materials and the like, for prolonged periods.


Description of Embodiments

[0011] Preferred embodiments of the invention will now be described
5 in detail.

[0012] <(A) Polyester resin>

The polyester resin for an antifouling coating material of this embodiment (hereunder referred to as "(A) polyester resin" comprises a compound with the structure represented by the following formula (1).

10 [0013] [Chemical Formula 2]



[In formula (1), R^1 is selected from among C3-24 trivalent or tetravalent hydrocarbon groups, R^2 and R^3 are selected from among C2-34 divalent hydrocarbon groups, R^4 is selected from among C3-24
15 divalent alicyclic hydrocarbon groups, and n represents an integer of 3 or 4.]

[0014] R^1 is a trivalent or tetravalent hydrocarbon group. There is no particular restriction on the number of carbon atoms, but it is preferably 3 to 24 and more preferably 3 to 8, in consideration of ease of synthesis
20 and availability of starting materials. The compound may also have a substituent such as sulfonic acid group.

R^2 and R^3 are not particularly restricted, but divalent hydrocarbon groups with 2 to 34 carbon atoms are preferred, and 2 to 8 carbon atoms are more preferred, in consideration of ease of synthesis and
25 availability of starting materials. The compound may also have a substituent such as sulfonic acid group. Also, the n R^2 groups and n

R^3 groups may be the same or different.

The R^4 group is a divalent alicyclic hydrocarbon group. There is no particular restriction on the number of carbon atoms, but it is preferably 3 to 24, more preferably 3 to 12 and even more preferably 6 to 7, in
5 consideration of ease of synthesis and availability of starting materials. The compound may also have a substituent such as sulfonic acid group. The $n R^4$ groups may be the same or different.

The number n is 3 or 4, and is preferably 3 from the viewpoint of resin viscosity.

10 [0015] The polyester resin of this embodiment is obtained by reacting a (a) trihydric or greater alcohol (hereunder referred to as "component (a)"), a (b) dibasic acid or its anhydride (hereunder referred to as "component (b)") and a (c) divalent alcohol (hereunder referred to as "component (c)"), and then further reacting an (d) alicyclic dibasic acid
15 or its anhydride (hereunder referred to as "component (d)"). This yields a polyester resin including a compound having the structure represented by formula (1) above.

The R^1 group in formula (1) derives from component (a), R^2 derives from component (b), R^3 derives from component (c) and R^4 derives
20 from component (d). Also, by conducting reaction with component (d) after components (a) to (c) have been reacted in the first stage, it is possible to obtain a polyester resin having an alicyclic structure derived from component (d) on the end, which structure is presumed to increase resin compatibility.

25 For synthesis using components (a) to (c) in the first stage (first step), the (c) divalent alcohol is added in a greater amount than necessary to

produce the desired polyester polyol structure, and preferably the process is controlled for a theoretical solid portion hydroxyl value in a range of ± 12 mgKOH/g, as derived from this structure, and reaction is conducted to an acid value of 1 mgKOH/g or lower. If the hydroxyl value is within this range, it will prevent the compound from having a high molecular weight and will allow resin viscosity increase to be inhibited, so that a polyester resin suitable for a low VOC, high solid hydrolyzable antifouling coating material composition can be obtained. Also, if the acid value is 1 mgKOH/g or lower, there will be less unreacted component (b) and reduced clouding of the resin solution. Furthermore, addition reaction with component (d) in the second stage will be facilitated, and it will be easier to obtain rosin compatibility. Also, the reaction temperature for component (d) in the second stage (second step) is preferably 100°C to 140°C. If the temperature is no higher than 140°C, it will be possible to inhibit production of polyesters with structures other than formula (1), by esterification reaction that is not based simply on addition reaction of component (d). On the other hand, if the temperature is 100°C or higher, the reaction of component (d) will proceed more readily and synthesis will be possible within a short period of time.

[0016] The (a) trihydric or greater alcohol may be an alcohol having 3 or more hydroxyl groups in the molecule, examples of which include polyfunctional polyhydroxy compounds such as glycerin, trimethylolethane, trimethylolpropane, trimethylolbutane, hexanetriol and pentaerythritol. The number of carbon atoms is preferably 3-24 and more preferably 3-8. From the viewpoint of material cost,

glycerin or trimethylolpropane is preferred.

[0017] The (b) dibasic acid or its anhydride is an acid with two or more ionizable hydrogen atoms in the molecule, or an anhydride thereof, examples of which include aliphatic dibasic acids, alicyclic dibasic acids, aromatic dibasic acids and their anhydrides. Specific examples for the aliphatic dibasic acid or its anhydride include malonic acid, maleic acid, fumaric acid, glutaric acid, succinic acid, adipic acid, pimelic acid, suberic acid, azelaic acid, sebacic acid, 1,9-nonamethylenedicarboxylic acid, 1,10-decamethylenedicarboxylic acid, 1,11-undecamethylenedicarboxylic acid and 1,12-dodecamethylenedicarboxylic acid, and their anhydrides. Specific examples for the alicyclic dibasic acid or its anhydride include 1,2-cyclohexanedicarboxylic acid, 1,3-cyclohexanedicarboxylic acid, 1,4-cyclohexanedicarboxylic acid, 1,4-decahydronaphthalenedicarboxylic acid, 1,5-decahydronaphthalenedicarboxylic acid, 2,6-decahydronaphthalenedicarboxylic acid and 2,7-decahydronaphthalenedicarboxylic acid, and their anhydrides. Further, specific examples for the aromatic dibasic acid or its anhydride include orthophthalic acid, isophthalic acid, terephthalic acid, naphthalenedicarboxylic acid, anthracenedicarboxylic acid, dimer acid, hydrogenated dimer acid and phenanthrenedicarboxylic acid, as well as their anhydrides. These may naturally be used in various derivative forms (for example, dimethyl carboxylate ester or sodium-5-sulfoisophthalic acid), and two or more different ones may also be used as mixtures. The number of carbon atoms is preferably 2-34 and more preferably 2-8. From the viewpoint of curability of the coating film

there are preferred alicyclic dibasic acids and aromatic dibasic acids, which are dibasic acids having ring structures, as well as their anhydrides, with phthalic anhydride being more preferred.

[0018] The (c) divalent alcohol is an alcohol having two hydroxyl
5 groups in the molecule. Specific examples include ethylene glycol, 1,2-propylene glycol, 1,3-propylene glycol, 1,2-butanediol, 1,3-butanediol, 2-methyl-1,3-propanediol, 1,4-butanediol, neopentyl glycol, 1,5-pentanediol, 3-methyl-1,5-pentanediol, 1,6-hexanediol, 2,2,4-trimethyl-1,3-pentanediol, 2-ethyl-1,3-hexanediol, 2-methyl-1,8-
10 octanediol, 1,9-nonanediol, 1,10-decanediol and 1,12-octadecanediol. The number of carbon atoms is preferably 2-24, more preferably 2-12 and even more preferably 2-8. From the viewpoint of solubility of the synthesized ester, a branched alkylene glycol is preferred. Propylene glycol is preferred in consideration of availability of starting materials.

15 [0019] The (d) alicyclic dibasic acid or its anhydride is an acid having an alicyclic structure and two ionizable hydrogen atoms in the molecule, or an anhydride thereof. Specific examples include 1,2-cyclohexanedicarboxylic acid, 1,3-cyclohexanedicarboxylic acid, 1,4-cyclohexanedicarboxylic acid, 1,4-decahydronaphthalenedicarboxylic
20 acid, 1,5-decahydronaphthalenedicarboxylic acid, 2,6-decahydronaphthalenedicarboxylic acid and 2,7-decahydronaphthalenedicarboxylic acid, and their acid anhydrides. The number of carbon atoms is preferably 3-24, more preferably 3-12 and even more preferably 3-8. Hexahydrophthalic anhydride is
25 preferred from the viewpoint of ease of synthesis.

[0020] There are no particular restrictions on the mixing proportions of

the components, but component (b) is preferably used at 0.5 to 8.0 with respect to 1 as component (a) as molar ratio in consideration of coating film flexibility, and more preferably 2 to 4 from the viewpoint of coating material viscosity. Also, component (c) is preferably used at
5 0.5 to 8 with respect to 1 as component (a), and more preferably at 2 to 4 from the viewpoint of coating material viscosity. Furthermore, component (d) is preferably used at 1 to 5 with respect to 1 as component (a), and more preferably at 2 to 4 from the viewpoint of curability of the coating material and compatibility with the rosin resin
10 used for pigment dispersion.

[0021] The weight-average molecular weight of the (A) polyester resin is preferably no greater than 8000, more preferably no greater than 4000 and even more preferably no greater than 2000. If the weight-average molecular weight is no greater than 2000, excessive increase in
15 viscosity of the final coating material will be prevented and it will be possible to reduce the amount of VOC necessary for dilution with solvent to a coatable viscosity.

[0022] The weight-average molecular weight and number-average molecular weight of the (A) polyester resin are the values obtained by
20 measurement by gel permeation chromatography (GPC) and calculation using a standard polystyrene calibration curve. The GPC conditions for molecular weight measurement were as follows.

<GPC conditions>

Pump: L-6200 by Hitachi, Co., Ltd.

25 Columns: Gel packs GL-420, GL-430 and GL-440 by Hitachi Chemical Co., Ltd.

Eluent: tetrahydrofuran

[0023] The acid value of the solid portion of the (A) polyester resin is preferably 50 to 250 mgKOH/g, more preferably 80 to 200 mgKOH/g and even more preferably 100 to 150 mgKOH/g. If the acid value of
5 the solid portion is at least 50 mgKOH/g, reaction with the polyvalent metal compound will readily proceed and the drying property will be superior, while an acid value of no greater than 250 mgKOH/g will prevent reaction with the polyvalent metal compound during mixing, that results in high viscosity of the coating material, so that day-to-day
10 viscosity increase can be prevented.

The acid value of the solid portion of the polyester resin of this embodiment may be measured by titration using potassium hydroxide (KOH).

[0024] The hydroxyl value of the solid portion of the (A) polyester
15 resin is preferably no greater than 100 mgKOH/g, more preferably no greater than 50 mgKOH/g, even more preferably no greater than 20 mgKOH/g and most preferably no greater than 10 mgKOH/g. By limiting the hydroxyl value of the solid portion to no greater than 100 mgKOH/g, it will be easier to obtain compatibility with the rosin and
20 petroleum resin used in the coating material, the coating film appearance will be superior and the water resistance of the coating film will be excellent.

[0025] To obtain a solid portion acid value for the (A) polyester resin within the range specified above, there may be applied a method of
25 introducing a carboxylic acid at the ends using a dibasic acid, or a method of introducing a carboxylic acid at the ends using a polybasic

acid. More specifically, the acid value of the solid portion can also be modified to within the aforementioned range by adjusting the contents for the first step, adjusting the extent of esterification reaction or adding a polybasic acid anhydride (such as trimellitic anhydride) after the first step. So long as it is after the first step, the addition reaction of the polybasic acid anhydride may be before the second step, during the second step or after the second step, and it may also be used in combination with an alicyclic dibasic anhydride used in the second step. A method of introducing a polybasic acid by the first step may also be employed, but introduction by addition after polyester synthesis allows easier control of the reaction with less gelling and viscosity increase.

[0026] Low molecularization of the polyester for viscosity reduction will tend to increase the hydroxyl groups, and in such cases a monocarboxylic acid such as benzoic acid may be used for reaction with the hydroxyl groups during the first step, to adjust the hydroxyl value.

[0027] The (A) polyester resin may be used as a solution dissolved in a solvent (hereunder also referred to as "(A) polyester resin solution"). Examples for the solvent to be used include the same ones provided as examples for the (F) solvent for the antifouling coating material composition described hereunder.

The (A) polyester resin solution may also comprise a non-reacting starting material.

[0028] The viscosity of the (A) polyester resin solution at 25°C is preferably no higher than 3000 mPa·s, more preferably no higher than 2000 mPa·s and even more preferably no higher than 1000 mPa·s. If

the viscosity is no higher than 3000 mPa·s, it will be easier to prepare an antifouling coating material composition that is coatable even when the volatile organic compound (VOC) content is 400 g/L or lower.

[0029] [Antifouling coating material composition]

- 5 The antifouling coating material composition of this embodiment comprises the aforementioned (A) polyester resin. The other components that may be included in the antifouling coating material composition will now be described.

<(B) Polyvalent metal compound>

- 10 The antifouling coating material composition of this embodiment may further comprise a polyvalent metal compound.

The polyvalent metal compound functions by reacting with the carboxyl groups of the (A) polyester resin.

- [0030] Reaction between the (A) polyester resin and the polyvalent metal compound can form a metal salt crosslinked structure (for example, $\text{-COO}^- \cdots \text{M}^{2+} \cdots \text{OOC-}$) by a -COO^- group as the residue after dissociation of the hydrogen ion from the carboxyl group of the (A) polyester resin and the metal ion M^{x+} of the polyvalent metal compound (where x is the valency of the metal element M).
- 15
- 20 The metal salt crosslinked structure is readily hydrolyzed, allowing stable hydrolysis to be exhibited. The (A) polyester resin of this embodiment has excellent reactivity with polyvalent metal compounds, and also excellent compatibility with various resins. Because the (A) polyester resin of this embodiment has excellent reactivity with
- 25
- polyvalent metal compounds, it rapidly forms stable metal salts. Furthermore, since the (A) polyester resin of this embodiment has

- excellent compatibility with combined resins, there are no storage stability problems such as viscosity increase or formation of precipitates or coarse grains, and the coating film can exhibit grinding and cleaning properties for prolonged periods. Consequently, the (A)
- 5 polyester resin of this embodiment can yield a coating film with excellent long-term antifouling properties and excellent flexibility. If the polyester resin has an appropriate molecular weight, (a weight-average molecular weight of no greater than 10,000 for this embodiment), it will be possible to obtain a practical coating material
- 10 viscosity even when the VOC value is set to 400 g/L or lower.
- Polyvalent metals include copper, zinc, magnesium, calcium, germanium, aluminum, cobalt, iron and titanium, among which zinc, copper, germanium, magnesium, calcium, cobalt and aluminum are preferred, and zinc is especially preferred.
- 15 Polyvalent metal compounds include inorganic acid salts of polyvalent metal such as oxides, hydroxides, halides, carbonates and sulfates, or their organic acid salts such as acetates or salicylates, with oxides, hydroxides and carbonates being preferred, and oxides and hydroxides being more preferred.
- 20 Preferred polyvalent metal compounds are oxides of one or more polyvalent metals selected from the group consisting of zinc, copper, germanium, magnesium, calcium and cobalt, with zinc oxide being especially preferred from the viewpoint of high reactivity.
- [0031] Zinc oxide may be used in forms with various different particle
- 25 diameters. Using zinc oxide fine particles is preferred over using zinc oxide with large particle diameters, because reaction between the

carboxyl groups of (A) polyester resin and the zinc oxide will be accelerated, while the coating film hardness will also be increased in a shorter period of time and damage resistance of the coating film will be exhibited early.

- 5 [0032] The polyvalent metal compound content in the antifouling coating material composition of this embodiment is an amount of preferably 10 to 700 parts by mass and even more preferably 50 to 500 parts by mass with respect to 100 parts by mass of the (A) polyester resin solution. If it is less than 10 parts by mass, poor curability and
10 poor coated film strength will tend to result. If it is greater than 700 parts by mass, the coating properties such as crack resistance will tend to be poor.

[0033] <(C) Rosin and rosin derivative>

- The antifouling coating material composition of this embodiment may
15 further comprise a rosin and/or a rosin derivative. Rosins include gum rosin, wood rosin and tall oil rosin. Rosin derivatives include hydrogenated rosins, polymerized rosins, maleinized rosins, aldehyde-modified rosins, rosin metal salts and rosin amines. The rosin and/or its derivative used may be a single type or a mixture of two or more
20 types.

- [0034] The content of the rosin and/or rosin derivative in the antifouling coating material composition of this embodiment is preferably 0.5 to 300 parts by mass, even more preferably 0.5 to 250 parts by mass and most preferably 0.5 to 200 parts by mass, with
25 respect to 100 parts by mass of the (A) polyester resin solution. At less than 0.5 part by mass the coating material viscosity will tend to

increase, and at greater than 300 parts by mass the physical properties may be impaired, including cracking, and the like.

[0035] <(D) Antifouling agent>

The antifouling coating material composition of this embodiment may
5 further comprise an antifouling agent (hereunder also referred to as
"(D) antifouling agent"). The (D) antifouling agent may be either an
organic or an inorganic antifouling agent, and cuprous oxide, metal
pyrithiones such as copper pyrithione (Copper Omadine) and zinc
pyrithione (Zinc Omadine), or 4,5-dichloro-2-n-octyl-4-isothiazolin-3-
10 one, 2-methylthio-4-t-butylamino-6-cyclopropylamino-s-triazine, 2-(p-
parachlorophenyl)-3-cyano-4-bromo-5-trifluoromethylpyrrole,
medetomidine, N,N'-dimethyl-N'-tolyl-(N-
fluorodichloromethylthio)sulfamide, pyridine-triphenylborane and the
like may be used.

15 [0036] In the antifouling coating material composition of this
embodiment, the (D) antifouling agent is preferably used in an amount
of 10 to 1000 parts by mass and more preferably 100 to 800 parts by
mass with respect to 100 parts by mass of the (A) polyester resin
solution.

20 [0037] Also, cuprous oxide exhibits stable antifouling performance,
from the viewpoint of its antifouling property against a wide range of
organisms, and it exhibits its antifouling property in antifouling coating
films in a variety of sea regions.

[0038] In the antifouling coating material composition of this
25 embodiment, the cuprous oxide is used at 50 to 1000 parts by mass and
more preferably 50 to 800 parts by mass with respect to 100 parts by

mass of the polyester resin.

[0039] <(E) Other additives>

The antifouling coating material composition of this embodiment may also comprise at least one type of additive selected from the group
5 consisting of plasticizers (e1), extender pigments (excluding polyvalent metal compounds) (e2), pigment dispersants (e3), color pigments (e4), anti-running agents (e5), anti-settling agents (e6) and dehydrating agents (e7) (hereunder referred to collectively as "additive (E)").

[0040] The plasticizers (e1), extender pigments (e2) (excluding
10 polyvalent metal compounds), pigment dispersants (e3), color pigments (e4), anti-running agents (e5), anti-settling agents (e6) and dehydrating agents (e7) will now be explained in detail.

[0041] (e1) Plasticizers

Plasticizers (e1) include chlorinated paraffins, petroleum resins, ketone
15 resins, TCP (tricresyl phosphate), polyvinyl ethyl ethers and dialkyl phthalates. The antifouling coating material composition of this embodiment preferably includes a plasticizer (e1) from the viewpoint of increasing the crack resistance of the coating film (antifouling coating film) formed from the antifouling coating material composition.
20 As chlorinated paraffins there may be used straight-chain or branched ones that are either liquid or solid (powder) at room temperature, but the average number of carbons is usually preferred to be 8 to 30 and more preferably 10 to 26, and preferably the number-average molecular weight is generally 200-1200 and more preferably 300 to 1100, the
25 viscosity is generally at least 1 (poise/25°C) and preferably 1.2 or greater (poise/25°C), and the specific gravity is generally 1.05 to

1.80/25°C and more preferably 1.10 to 1.70/25°C. Using a chlorinated paraffin with this specified number of carbon atoms will allow a coating film with low cracking and peeling to be obtained from the resulting antifouling coating material composition. If the
5 chlorinated paraffin has less than 8 carbon atoms the effect of inhibiting cracking may be insufficient, while if it has more than 30 carbon atoms the expendability (regenerability) of the obtained coating film surface may be poor and the antifouling property inferior. The degree of chlorination (chlorine content) of the chlorinated paraffin is
10 usually preferred to be 35% to 75% and more preferably 35% to 65%. Using a chlorinated paraffin with this specified degree of chlorination will allow a coating film with low cracking and peeling to be obtained from the resulting antifouling coating material composition. Such chlorinated paraffins include TOYOPARAX 150 and TOYOPARAX
15 A-70, by Tosoh Corp. As petroleum resins there may be used, specifically, C5, C9, styrene-based and dicyclopentadiene-based compounds, as well as their hydrogenated forms, with commercial products including QUINTONE 1500 and QUINTONE 1700 by Zeon Corp. Preferred among these are chlorinated paraffins, petroleum
20 resins and ketone resins. These plasticizers may be used either alone or in combinations of two or more.

[0042] The plasticizer (e1) is preferably included at 0.1 to 300 parts by mass, more preferably 0.1 to 200 parts by mass and most preferably 0.1 to 150 parts by mass, with respect to 100 parts by mass of the (A)
25 polyester resin solution.

[0043] (e2) Extender pigments

Extender pigments (e2) (excluding polyvalent metal compounds) include talc, silica, mica, clay, potassium feldspar, and calcium carbonate, kaolin and alumina white that are also used as anti-settling agents and white carbon, aluminum hydroxide, magnesium carbonate, 5 barium carbonate and barium sulfate that are also used as delustering agents, among which extender pigments selected from the group consisting of talc, silica, mica, clay, calcium carbonate, kaolin, barium sulfate and potassium feldspar are preferred. Extender pigments are pigments with a low refractive index that when kneaded with oils or 10 varnishes are transparent and do not hide coated surfaces, and an extender pigment (e2) is preferably added to the antifouling coating material composition of this embodiment from the viewpoint of improving the coating properties, including crack resistance.

[0044] The extender pigment (e2) is preferably included at 0.1 to 500 15 parts by mass and more preferably 50 to 300 parts by mass with respect to 100 parts by mass of the (A) polyester resin solution.

[0045] (e3) Pigment dispersants

As pigment dispersants (e3) there may be used conventionally known organic and inorganic dispersing agents. Organic pigment dispersants 20 include aliphatic amines and organic acids (DUOMEEN TDO by Lion Corp., and DISPERBYK101 by BYK Chemie).

[0046] The pigment dispersant (e3) is preferably included at 0.01 to 100 parts by mass and more preferably 0.01 to 50 parts by mass with respect to 100 parts by mass of the (A) polyester resin solution.

25 [0047] (e4) Color pigments

As color pigments (e4) there may be used conventionally known

organic and inorganic pigments. Organic pigments include carbon black, naphthol red, phthalocyanine blue and the like. Examples of inorganic pigments include bengala (iron oxide red), baryta powder, titanium white and yellow iron oxide. Various coloring agents such
5 as dyes may also be added. The antifouling coating material composition of this embodiment preferably contains a color pigment (e4) from the viewpoint of discretionary adjustment of the color tone of the antifouling coating film obtained from the composition.

[0048] The color pigment (e4) is preferably included at 0.01 to 100
10 parts by mass and more preferably 0.01 to 10 parts by mass with respect to 100 parts by mass of the (A) polyester resin solution.

[0049] (e5) Anti-running agents (also known as "anti-sagging agents")
Anti-running agents (e5) include amide waxes, hydrogenated castor oil waxes and polyamide waxes, and mixtures of both, and synthetic fine
15 silica powder, with polyamide waxes and synthetic fine silica powder being preferred. Commercial products include DISPARLON A630-20XC by Kusumoto Chemicals, Ltd., and ASAT-250F by Itoh Oil Chemicals Co., Ltd. The antifouling coating material composition of this embodiment preferably contains an anti-running agent (e5) from
20 the viewpoint of allowing adjustment of the anti-running property during coating.

[0050] The anti-running agent (e5) is preferably included at 0.1 to 100 parts by mass and more preferably 0.1 to 50 parts by mass with respect to 100 parts by mass of the (A) polyester resin solution.

25 [0051] (e6) Anti-settling agents

Anti-settling agents (e6) include organic clay-based Al, Ca and Zn

amine salts, polyethylene waxes and polyethylene oxide-based waxes, with polyethylene oxide-based waxes being preferred. Commercial products include DISPARLON 4200-20X by Kusumoto Chemicals, Ltd. The antifouling coating material composition of this
5 embodiment preferably contains an anti-settling agent (e6) from the viewpoint of preventing deposition of the solvent insolubles during the storage period and improving the stirrability.

[0052] The anti-settling agent (e6) is preferably included at 0.1 to 100 parts by mass and more preferably 0.1 to 50 parts by mass with respect
10 to 100 parts by mass of the (A) polyester resin solution.

[0053] (e7) Dehydrating agent

The dehydrating agent (e7) used may be a publicly known one, such as gypsum or ethyl silicate. Commercial products include gypsum such as "Calcined Plaster FT-2" by Noritake Co., Ltd., and ethyl silicates
15 such as Ethyl Silicate 28 by Colcoat Co., Ltd.

[0054] The dehydrating agent (e7) is preferably included at 0.01 to 100 parts by mass and more preferably 0.01 to 50 parts by mass with respect to 100 parts by mass of the (A) polyester resin solution.

[0055] <(F) Solvent>

20 The antifouling coating material composition of this embodiment may further comprise a solvent (F). Publicly known solvents with a wide range of boiling points may be used as the solvent (F), and specifically there may be mentioned aliphatic solvents such as terpene; aromatic solvents such as toluene, xylene; alcohol-based solvents such as
25 isopropyl alcohol, n-butyl alcohol and isobutyl alcohol; esteric solvents such as ethyl acetate and butyl acetate; ketone-based solvents such as

methylethyl ketone, methyl isobutyl ketone (MIBK) and methyl amyl ketone; and ether-based or ether ester-based solvents such as ethyleneglycol monomethyl ether, ethyleneglycol monobutyl ether, propyleneglycol monomethyl ether and propyleneglycol monomethyl ether acetate; among which xylene, methyl isobutyl ketone and propyleneglycol monomethyl ether are preferred. These solvents may be used as single compounds or as combinations of two or more compounds.

The volatile organic compound (VOC) content of the antifouling coating material composition of this embodiment is preferably no greater than 400 g/L and more preferably 100 to 350 g/L. A VOC content of no greater than 400 g/L can minimize environmental load and effects on the human body. The VOC is the value determined under the measuring conditions explained in the Examples section.

In the antifouling coating material composition of this embodiment, the viscosity is preferably 5 to 20 dPa·s, and for coating manageability (spray manageability and running resistance), it is more preferably 8 to 20 dPa·s and even more preferably 10 to 20 dPa·s.

[0056] The antifouling coating material composition of this embodiment can be produced by stirring and mixing the aforementioned components that have been previously prepared. The stirring and mixing may be accomplished using a known mixer/stirrer such as a high-speed dispersion mixer, sand grinding mill, basket mill, ball mill, triple roll, Ross mixer, planetary mixer, universal Shinagawa mixer or the like.

[0057] [Antifouling coating film, antifouling base, and method for

producing antifouling base]

The antifouling coating film of this embodiment is obtained by curing the antifouling coating material composition of the embodiment described above. The antifouling base of this embodiment is obtained
5 by coating or impregnating a base with the antifouling coating material composition of this embodiment, and curing the coating composition that has been coated onto or impregnated into the base, to form an antifouling coating film on the base. Also, the method for producing an antifouling base according to this embodiment is one in which a
10 base is coated or impregnated with the antifouling coating material composition of this embodiment, and the coating composition that has been coated onto the base or the coating composition that has been impregnated into the base is cured, to form an antifouling coating film on the base.

[0058] There are no particular restrictions on the base material that is
15 the target of the method of preventing fouling, but it is preferably an underwater structure, ship, fishing net or fishing gear item. For example, the antifouling coating material composition may be applied once or several times by a common method onto the surface of
20 underwater structures such as plumbing drains in thermal power or nuclear power plants, sludge diffusion-blocking films for various ocean civil engineering works such as coastal roads, undersea tunnels, harbor facilities, canals/water channels or the like, or molded articles of ships, fishery materials (for example, ropes, fishing nets, fishing gears, floats
25 and buoys) and the like, to obtain antifouling coating film-coated ships or underwater structures with excellent antifouling properties, allowing

sustained release of antifouling agent components for prolonged periods, and exhibiting excellent crack resistance with suitable flexibility even when thickly coated.

[0059] That is, an antifouling coating film obtained by coating and
5 curing the antifouling coating material composition of this embodiment
on the surface of a molded article exhibits excellent antifouling
properties that allow long-term and continuous prevention of adhesion
of aquatic creatures such as sea lettuce, barnacles, green laver, serpula,
oysters and *Bugula neritina*. Satisfactory adhesion occurs especially
10 for material surfaces when the materials of ships and the like are FRP,
steel, wood or aluminum alloy. In addition, coating the antifouling
coating material composition of this embodiment onto the surface of an
underwater structure can prevent adhesion of marine organisms and
maintain the function of the structure for prolonged periods, while
15 coating onto a fishing net can prevent obstruction of the fishing net
mesh and lower the risk of environmental pollution.

[0060] The antifouling coating material composition of this
embodiment may be coated directly onto a fishing net, or it may be
coated onto the surface of a ship or underwater structure whose base
20 layer material has already been coated with a rust-preventive agent or
primer. Furthermore, the antifouling coating material composition of
this embodiment may be applied as an overcoat for repair on the
surface of a ship, especially an FRP ship, or an underwater structure
that has already been coated with a conventional antifouling coating
25 material or that has already been coated with an antifouling coating
material composition according to this embodiment. There are no

particular restrictions on the thickness of the antifouling coating film formed in this manner on the surface of a ship, underwater structure or the like, and it may be about 30-250 μm /application, for example.

[0061] The antifouling coating film of this embodiment, obtained as
5 described above, is the cured product of the antifouling coating material composition of this embodiment, and therefore the risk of environmental pollution is low and it exhibits an excellent long-term antifouling property against adhesion of organisms onto a broad range of ships and underwater structures.

10 [0062] As explained above, this embodiment can provide a low-VOC hydrolyzable antifouling coating material composition capable of forming an antifouling coating film having low environmental load and excellent antifouling properties, and superior uniform expendability of the coated film, whereby the coating film undergoes uniform wear at a
15 constant rate over long periods, and excellent maintenance of long-term antifouling performance of the coated film, allowing superior antifouling performance to be maintained for prolonged periods and making it suitable for sea going vessels, as well as an antifouling coating film, and ships, underwater structures, fishing gear or fishing
20 nets coated with the antifouling coating film.

Examples

[0063] The present invention will now be explained in greater detail based on examples and comparative examples, with the understanding that these examples are in no way limitative on the invention. The
25 "parts" and "%" values in the examples and comparative examples refer to "parts by mass" and "mass%", respectively.

[0064] <Production of (A) polyester resin>

(Example 1: Production of polyester resin solution (a-1))

Into a reactor equipped with a stirrer, condenser and thermometer there were charged 92 parts of glycerin as a (a) trihydric or greater alcohol, 444 parts of phthalic anhydride as a (b) dibasic acid or its anhydride, 228 parts of propylene glycol as a (c) divalent alcohol and 0.05 part of tetrabutyl titanate as a catalyst, and esterification reaction was conducted from 140°C to 190°C over a period of 4 hours. The system interior was then gradually reduced in pressure to 100 mmHg over a period of 2 hours, and polycondensation reaction was conducted at 190°C for 20 hours. During the reaction, the generated water was removed by reflux dewatering, the acid value was measured by KOH titration and the hydroxyl value was measured by acetylation, the mixture was cooled to 120°C when the acid value of the solid portion fell below 1 mgKOH/g, and then 439 parts of hexahydrophthalic anhydride was charged in as a (d) alicyclic dibasic acid or its anhydride for reaction for 2 hours. After cooling the reaction mixture, it was diluted with n-butyl acetate to obtain polyester resin solution (a-1) having a nonvolatile content of 65%, an acid value of 88 mgKOH/g (135 mgKOH/g as solid portion), a hydroxyl value of 5 mgKOH/g (7.7 mgKOH/g as solid portion), a viscosity of 1000 mPa·s and a weight-average molecular weight of 1,000.

[0065] (Examples 2 to 7 and 26 to 31: Production of polyester resin solutions (a-2) to (a-7) and (a-13) to (a-18))

Polyester resin solutions (a-2) to (a-7) and (a-13) to (a-18) were obtained in the same manner as Production Example 1, except for

changing the types and amounts of starting materials as shown in Table 1.

[0066] (Comparative Examples 1 to 5)

Polyester resin solutions (a-8) to (a-12) were obtained in the same
5 manner as Production Example 1, except for changing the types and amounts of starting materials as shown in Table 2.

[0067] (Comparative Example 6: Production of polyester resin solution (b-1))

After mixing 280 parts of isophthalic acid, 430 parts of sebacic acid, 12
10 parts of trimethylolpropane, 70 parts of propylene glycol, 238 parts of neopentyl glycol, 90 parts of ethylene glycol and 165 parts of benzoic acid in a 2 L four-necked flask, the mixture was reacted at 220°C for 6 hours in the presence of nitrogen gas (esterification reaction). The water generated was removed by reflux dewatering and, measuring the
15 acid value by KOH titration and the hydroxyl value by the acetylation method, the reaction was suspended when the acid value of the solid portion reached 43 mgKOH/g and the hydroxyl value of the solid portion reached 60 mgKOH/g. The mixture was then cooled to 170°C, 178 parts of trimellitic anhydride was added, the mixture was thermally
20 insulated for 2 hours, addition reaction was conducted, and the reaction was suspended when the acid value of the solid portion reached 108 mgKOH/g and the hydroxyl value of the solid portion reached 10 mgKOH/g. After cooling, it was diluted with methyl isobutyl ketone, to obtain polyester resin solution (b-1) having a heating residue of
25 65.0%, an acid value of 70 mgKOH/g (108 mgKOH/g as solid portion), a hydroxyl value of 7 mgKOH/g (10 mgKOH/g as solid portion), a

viscosity of 240 mPa·s and a weight-average molecular weight of 1,790.
[0068] <Evaluation of resin properties>

The following evaluation was conducted for polyester resin solutions (a-1) to (a-7) and (a-13) to (a-18) obtained in Examples 1 to 7 and 26 to 31, and polyester resin solutions (a-8) to (a-12) and (b-1) obtained in Comparative Examples 1 to 6. The obtained results are shown in Tables 1 to 3.

(1) GPC;

The weight-average molecular weight and number-average molecular weight were measured by GPC using a standard polystyrene calibration curve, under the following conditions.

(GPC measuring conditions)

Apparatus: L-6200 by Hitachi Co., Ltd.

Columns: Gel packs GL-420, GL-430 and GL-440 by Hitachi Chemical Co., Ltd.

Eluent: THF

Flow rate: 2.0 ml/min

(2) Heating residue (mass NV);

After weighing out 1.5 g of polyester resin solution into a flat-bottom dish, a wire of known mass was used for even spreading and the solution was dried at 135°C for 1 hour, after which the masses of the residue and wire were measured and the heating residue (mass%) was calculated.

The term "heating residue" has the same definition as "nonvolatile content" mentioned above.

(3) Acid value;

After weighing out the polyester resin (solid portion or solution) into an Erlenmeyer flask, approximately 30 ml of a solvent (isopropyl alcohol/toluene = 1/2 (volume ratio)) was added to dissolve it. Next, about 2-3 drops of an indicator (1% phenolphthalein/ethyl alcohol solution) was added and titration was performed with a 0.1 mol/l potassium hydroxide solution (alcoholic), with the end point defined as disappearance of faint crimson color, after which calculation was performed by the following formula.

$$\text{Acid value (mgKOH/g)} = F \times V/S$$

10 F: Coefficient of 0.1 mol/l potassium hydroxide solution (reagent factor $\times 5.61$)

V: Titer of 0.1 mol/l potassium hydroxide solution (ml)

S: Sampling amount (g)

(4) Hydroxyl value;

15 The polyester resin (solid portion or solution) was weighed out into an Erlenmeyer flask, and 5 ml of an acetylating agent (acetic anhydride 20 g, with pyridine added to 100 ml) was precisely added thereto to dissolve it. After warming for 30 minutes on a hot plate heated to approximately 120°C, 1.2 ml of purified water was added, and the mixture was gently shaken and again warmed for 5 minutes. After cooling to room temperature, about 20 ml of a solvent (isopropyl alcohol/toluene = 1/2 (volume ratio)) and about 2-3 drops of an indicator (1% phenolphthalein/ethyl alcohol solution) were added and titration was performed with a 0.5 mol/l potassium hydroxide solution (alcoholic), with the end point defined as disappearance of faint crimson color, after which calculation was performed by the following

25

formula. A blank test was conducted in parallel with this test, and calculation was performed by the following formula.

$$\text{Hydroxyl value (mgKOH/g)} = (A-B) \times F/S + C$$

A: Titer of 0.5 mol/l potassium hydroxide solution (ml) for blank test

5 B: Titer of 0.5 mol/l potassium hydroxide solution (ml) for main test

F: Coefficient of 0.5 mol/l potassium hydroxide solution (reagent factor $\times 28.05$)

S: Sampling amount (g)

C: Acid value of sample (mgKOH/g)

10 (5) Viscosity;

The viscosity of the polyester resin solution was measured using a Brookfield viscometer at 25°C.

(Viscosity measuring conditions)

Temperature: 25°C

15 Cone shape: No.2 rotor

Sample volume: Approximately 200 ml

Rotational speed: 30 rpm

Time from initial rotation to measurement: 3 minutes

(6) Evaluation of rosin compatibility;

20 After mixing the polyester resin solution with WW rosin resin in a solid ratio of 1:1, the mixture was coated onto a glass plate with a film applicator (clearance: 0.3 mm) and dried at 23°C for 24 hours, after which the outer appearance was observed. In Tables 1 to 3, "A" represents compatibility and "B" represents no compatibility
25 (separation).

(7) Coating film curability;

A mixture of 50 parts of the polyester resin solution and 25 parts of zinc oxide was dispersed for 30 minutes using a pigment disperser (paint shaker). The coating material obtained in this manner was used for coating onto a glass plate to a dry thickness of 100 μm , and the
5 cured state of the coating film after standing at 25°C for 24 hours was evaluated by finger contact. In Tables 1 to 3, "VG" means no tack and no warping of the coating film, "G" means no tack but some warping of the coating film, and "P" means tack.

[0069] [Table 1]

			Example 1	Example 2	Example 3	Example 4	Example 5	Example 6	Example 7	Example 26	Example 27	Example 28	Example 29	Example 30	Example 31	
			Polyester resin solution (a-1)	Polyester resin solution (a-2)	Polyester resin solution (a-3)	Polyester resin solution (a-4)	Polyester resin solution (a-5)	Polyester resin solution (a-6)	Polyester resin solution (a-7)	Polyester resin solution (a-13)	Polyester resin solution (a-14)	Polyester resin solution (a-15)	Polyester resin solution (a-16)	Polyester resin solution (a-17)	Polyester resin solution (a-18)	
Monomer composition	Component (a)	Glycerin	92	92	92	92	92	92	-	-	92	92	92	92	92	
		Trimethylolpropane	-	-	-	-	-	-	134	-	-	-	-	-	-	-
		Pentaerythritol	-	-	-	-	-	-	-	136	-	-	-	-	-	-
	Component (b)	Hexahydrophthalic anhydride	-	-	-	-	462	-	-	-	-	-	-	-	-	-
		Phthalic anhydride	444	-	-	444	-	444	444	592	-	-	-	444	444	444
		Isophthalic acid	-	498	-	-	-	-	-	-	-	-	-	-	-	-
		Terephthalic acid	-	-	-	-	-	-	-	-	498	-	-	-	-	-
		1,4-Cyclohexanedicarboxylic acid	-	-	-	-	-	-	-	-	-	-	516	-	-	-
		Adipic acid	-	-	438	-	-	-	-	-	-	-	-	-	-	-
	Component (c)	Ethylene glycol	-	-	-	-	-	-	-	-	-	-	-	186	-	-
		Propylene glycol	228	228	228	-	228	228	228	304	228	228	-	-	-	-
		1,3-Butanediol	-	-	-	270	-	-	-	-	-	-	-	-	-	-
		Neopentyl glycol	-	-	-	-	-	-	-	-	-	-	-	-	312	-
		1,4-Cyclohexanedimethanol	-	-	-	-	-	-	-	-	-	-	-	-	-	432
	Component (d)	Hexahydrophthalic anhydride	439	439	439	439	439	-	439	439	439	439	439	439	439	439
		Methylhexahydrophthalic anhydride	-	-	-	-	-	479	-	-	-	-	-	-	-	-
Catalyst			0.05	0.05	0.05	0.05	0.05	0.05	0.05	0.05	0.05	0.05	0.05	0.05	0.05	
Mean number of functional groups (designed value)			3	3	3	3	3	3	3	4	3	3	3	3	3	
Resin properties	Heating residue (%)		65	65	65	65	65	65	65	65	65	65	65	65	65	
	Acid value (mgKOH/g)		88	89	87	87	88	86	86	77	92	90	97	79	78	
	Hydroxyl value (mgKOH/g)		5	5	6	5	6	5	5	35	5	6	7	10	9	
	Viscosity (mPa·s)		1000	990	1050	800	980	1200	1000	2680	930	700	830	1160	1840	
	Num. average mol. wt. (Mn)		1000	1000	980	1050	1020	1050	1040	1150	1000	1020	920	1100	1230	
	Wt. average mol. wt. (Mw)		1680	1700	1670	1790	1720	1780	1750	2370	1750	1750	1270	1740	2060	
Resin compatibility			A	A	A	A	A	A	A	A	A	A	A	A	A	
Coating film curability			VG	VG	G	VG	VG	VG	VG	G	VG	G	G	VG	VG	

[0070] [Table 2]

			Comp. Ex. 1	Comp. Ex. 2	Comp. Ex. 3	Comp. Ex. 4	Comp. Ex. 5
			Polyester resin solution (a-8)	Polyester resin solution (a-9)	Polyester resin solution (a-10)	Polyester resin solution (a-11)	Polyester resin solution (a-12)
Monomer composition	Component (a)	Glycerin	-	92	92	92	92
	Component (b)	Hexahydrophthalic anhydride	-	-	-	462	-
		Phthalic anhydride	296	444	444	-	444
	Component (c)	Propylene glycol	228	228	228	228	228
	Component (d)	Hexahydrophthalic anhydride	293	-	-	-	-
	Component (d')	Phthalic anhydride	-	422	-	422	211
		Succinic anhydride	-	-	285	-	-
		Maleic anhydride	-	-	-	-	140
Catalyst		0.05	0.05	0.05	0.05	0.05	
Mean number of functional groups (designed)		2	3	3	3	3	
Resin properties	Heating residue (%)		65	65	65	65	65
	Acid value (mgKOH/g)		87	90	103	87	91
	Hydroxyl value (mgKOH/g)		6	6	5	6	6
	Viscosity (mPa·s)		150	1500	900	1000	2000
	Num. average mol. wt. (Mn)		800	1030	950	980	1000
	Wt. average mol. wt. (Mw)		1120	1800	1520	1750	1850
Rosin compatibility		A	B	B	B	B	
Coating film curability		P	VG	VG	VG	VG	

[0071] [Table 3]

			Comp. Ex. 6 Polyester resin solution (b-1)
Monomer composition	Polyhydric alcohol	Trimethylolpropane	12
		Propylene glycol	70
		Ethylene glycol	90
		Neopentyl glycol	238
	Polybasic acid	Isophthalic acid	280
		Sebacic acid	430
		Benzoic acid	165
		Trimellitic anhydride	178
Catalyst			0.05
Mean number of functional groups (designed)			1.7
Resin properties	Heating residue (%)		65
	Acid value (mgKOH/g)		70
	Hydroxyl value (mgKOH/g)		5
	Viscosity (mPa·s)		240
	Num. average mol. wt. (Mn)		900
	Wt. average mol. wt. (Mw)		1790
Rosin compatibility			A
Coating film curability			P

5

[0072] <Modification of antifouling coating material composition>

(Example 8)

The antifouling coating material composition was modified in the

following manner.

First, xylene (10.5 parts), methyl isobutyl ketone (2 parts), WW rosin (5.5 parts), TCP (5 parts), polyester resin solution (a-1) (8 parts), BYK-101 (0.3 part) and Ethyl Silicate 28 (0.3 part) were combined in a 1000 ml plastic container, and agitated with a paint shaker to uniform dissolution.

Next, TTK Talc (4 parts), zinc oxide (6 parts), NOVAPERM RED F5RK (0.6 part), Cuprous Oxide NC-803 (48 parts), 2-methylthio-4-t-butylamino-6-cyclopropylamino-s-triazine (2.5 parts), iron oxide red 404 (2.3 parts), Titanium White R-5N (2 parts), Calcined Plaster (1 part) and Disperlon 603-20X (2 parts) were combined, glass beads (200 parts) were added, and the mixture was dispersed for 1 hour.

This was filtered with a 80 mesh filter screen to prepare an antifouling coating material composition.

[0073] (Examples 9 to 25, Comparative Examples 7 to 23)

Antifouling coating material compositions for Examples 9 to 25 and Comparative Examples 7 to 23 were prepared in the same manner as Example 8, except that the compounding ingredients and amounts were changed as shown in Tables 4 and 5.

[0074] <Evaluation of physical properties of antifouling coating material compositions>

The physical properties of the antifouling coating material compositions of Examples 8 to 25 and Comparative Examples 7 to 23, and the coating films formed using them, were evaluated in the following manner. The obtained results are shown in Tables 6 and 7.

(1) Measurement of volatile organic compound (VOC) mass;

The volatile organic compound mass was calculated by the following formula, using the values for the coating material specific gravity and mass NV.

$$\text{VOC (g/L)} = \text{Coating material specific gravity} \times 1000 \times (100 - \text{mass NV})/100$$

(2) Specific gravity;

The mass of the antifouling coating material composition filling a specific gravity cup with an internal volume of 100 ml was measured at 25°C to determine the specific gravity (coating material specific gravity) (g/cm³).

(3) Heating residue (mass NV);

After weighing out 1 g of antifouling coating material composition into a flat-bottom dish, a wire of known mass was used for even spreading and the solution was dried at 125°C for 1 hour, after which the masses of the residue and wire were measured and the heating residue (mass%) was calculated.

(4) Measurement of antifouling coating material composition viscosity;

The viscosity of the antifouling coating material composition at 23°C was measured using a Rion viscometer (VISCOTESTER VT-04F by Rion Co., Ltd., for high viscosity, No.1 rotor).

(5) Storage stability test;

The antifouling coating material composition was allowed to stand in a thermostat at 50°C, and the state of the coating material (viscosity, film tension, and presence of precipitates or coarse grains) was confirmed once a month, taking note of the change of state from immediately after preparation.

The "film tension" was evaluated as "G" for no film tension, or "P" for film tension. Also, the "presence of precipitates or coarse grains" was evaluated as "G" for no observation of precipitates or coarse grains, or "P" for observation of precipitates or coarse grains.

5 (6) Antifouling coating film expendability test

An applicator was used for coating of $50 \times 50 \times 1.5$ mm hard vinyl chloride sheets with the antifouling coating material composition to a dry film thickness of $150 \mu\text{m}$, and the coatings were allowed to dry indoors for 7 days at room temperature (approximately 20°C), to
10 prepare test sheets.

Each test sheet was attached to the side of a rotating drum set in a thermostatic bath containing 25°C seawater, which was rotated at a circumferential speed of 15 knots, and the antifouling coating film expendability (film thickness reduction) was measured each month.

15 (7) Antifouling coating film stationary antifouling property test

A $100 \times 300 \times 3.2$ mm sand blast-treated steel sheet was coated with an epoxy-based coating material ("BANNOH 500" by Chugoku Marine Paints, Ltd.) to a dry film thickness of $150 \mu\text{m}$ and an epoxy-based binder coating material ("BANNOH 500N", product of Chugoku
20 Marine Paints, Ltd.) to a dry film thickness of $100 \mu\text{m}$, in that order with an interval of 1 day between them. After allowing one more day to elapse, the surface of the coating film formed from the epoxy-based binder coating material was coated with the antifouling coating material composition to a dry film thickness of $150 \mu\text{m}$, to prepare a
25 test sheet.

Each test sheet was dried at 23°C for 7 days and then stationarily

submerged in Nagasaki Bay, Nagasaki Prefecture, and the area of adhering organisms was visually examined each month and evaluated on the following scale.

<Evaluation scale>

- 5 0: No adhesion of aquatic organisms
 - 0.5: More than 0% and no greater than 10% adhesion area of aquatic organisms
 - 1: More than 10% and no greater than 20% adhesion area of aquatic organisms
 - 10 2: More than 20% and no greater than 30% adhesion area of aquatic organisms
 - 3: More than 30% and no greater than 40% adhesion area of aquatic organisms
 - 4: More than 40% and no greater than 50% adhesion area of aquatic organisms
 - 15 5: More than 50% adhesion area of aquatic organisms
- [0075] [Table 4]

Name	Example																		
	8	9	10	11	12	13	14	15	16	17	18	19	20	21	22	23	24	25	
Polyester resin solution (a-1)	8	8	8	8	-	-	-	-	-	-	9.5	6.5	9	9	9	-	11.5	7	
Polyester resin solution (a-2)	-	-	-	-	8	-	-	-	-	-	-	-	-	-	-	9	-	-	
Polyester resin solution (a-3)	-	-	-	-	-	8	-	-	-	-	-	-	-	-	-	-	-	-	
Polyester resin solution (a-4)	-	-	-	-	-	-	8	-	-	-	-	-	-	-	-	-	-	-	
Polyester resin solution (a-5)	-	-	-	-	-	-	-	8	-	-	-	-	-	-	-	-	-	-	
Polyester resin solution (a-6)	-	-	-	-	-	-	-	-	8	-	-	-	-	-	-	-	-	-	
Polyester resin solution (a-7)	-	-	-	-	-	-	-	-	-	8	-	-	-	-	-	-	-	-	
TCP (Tricresyl phosphate)	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	
WW resin	5.5	5.5	5.5	5.5	5.5	5.5	5.5	5.5	5.5	5.5	5.5	4	7	9	9	9	9	11	
Xylene	10.5	10.5	6	10.5	10.5	10.5	10.5	10.5	10.5	10.5	10.5	10.5	16.5	16.5	16.5	16.5	16.5	16.5	
MIBK	2	2	2	2	2	2	2	2	2	2	2	2	3	3	3	3	3	3	
Cuprous oxide NC-803	48	48	48	48	48	48	48	48	48	48	48	48	-	-	-	-	-	-	
Disparton A603-20X	2	2	2	2	2	2	2	2	2	2	2	2	2	2	2	2	2	2	
Calcined Plaster FT-2	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	
Disperbyk-101 (BYK-101)	0.3	0.3	0.3	0.3	0.3	0.3	0.3	0.3	0.3	0.3	0.3	0.3	0.5	0.5	0.5	0.5	0.5	0.5	
TTK Talc	4	4.5	4	4	4	4	4	4	4	4	4	4	7	7	7	7	7	7	
Potassium feldspar	-	-	-	-	-	-	-	-	-	-	-	-	4	4	4	4	4	4	
Titanium white R-5N	2	2	2	2	2	2	2	2	2	2	2	2	3	3	3	3	3	3	
Zinc oxide	6	6	6	6	6	6	6	6	6	6	6	6	25	25	25	25	25	25	
Zinc Oxadine	-	-	-	-	-	-	-	-	-	-	-	-	8	8	8	8	8	8	
2-Methylthio-4-t-butylamino-6-cyclopropylamino-s-triazine	2.5	-	-	-	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	3	-	-	-	-	-	
Copper Oxadine	-	2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
4,5-Dichloro-2-n-octyl-4-isothiazolin-3-one	-	-	7	-	-	-	-	-	-	-	-	-	-	3	-	-	-	-	
2-(p-Chlorophenyl)-3-cyano-4-bromo-5-trifluoromethylpyrrole	-	-	-	2.5	-	-	-	-	-	-	-	-	-	-	-	3	3	3	
Pyridine-triphenylborane	-	-	-	-	-	-	-	-	-	-	-	-	-	-	3	-	-	-	
Bengala 404	2.3	2.3	2.3	2.3	2.3	2.3	2.3	2.3	2.3	2.3	2.3	2.3	3	3	3	3	3	3	
NOVAPERM RED F5RK	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.5	0.5	0.5	0.5	0.5	0.5	
Ethyl Silicate 28	0.3	0.3	0.3	0.3	0.3	0.3	0.3	0.3	0.3	0.3	0.3	0.3	0.5	0.5	0.5	0.5	0.5	0.5	
[Total]	100	100	100	100	100	100	100	100	100	100	100	100	100	100	100	100	100	100	

[0076] [Table 5]

Name	Comp. Ex.																	
	7	8	9	10	11	12	13	14	15	16	17	18	19	20	21	22	23	
Polyester resin solution (a-8)	8	8	8	8	-	-	-	-	-	9.5	6.5	9	9	9	-	11.5	7	
Polyester resin solution (a-9)	-	-	-	-	8	-	-	-	-	-	-	-	-	-	9	-	-	
Polyester resin solution (a-10)	-	-	-	-	-	8	-	-	-	-	-	-	-	-	-	-	-	
Polyester resin solution (a-11)	-	-	-	-	-	-	8	-	-	-	-	-	-	-	-	-	-	
Polyester resin solution (a-12)	-	-	-	-	-	-	-	8	-	-	-	-	-	-	-	-	-	
Polyester resin solution (b-1)	-	-	-	-	-	-	-	-	8	-	-	-	-	-	-	-	-	
TCP (Tricresyl phosphite)	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	
WW resin	5.5	5.5	5.5	5.5	5.5	5.5	5.5	5.5	5.5	4	7	9	9	9	9	6.5	11	
Xylene	10.5	10.5	6	10.5	10.5	10.5	10.5	10.5	10.5	10.5	10.5	16.5	16.5	16.5	16.5	16.5	16.5	
MIBK	2	2	2	2	2	2	2	2	2	2	2	3	3	3	3	3	3	
Cuprous oxide NC-803	48	48	48	48	48	48	48	48	48	48	48	-	-	-	-	-	-	
Disparion A603-20X	2	2	2	2	2	2	2	2	2	2	2	2	2	2	2	2	2	
Calcined Plaster FT-2	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	
Disperbyk-101 (BYK-101)	0.3	0.3	0.3	0.3	0.3	0.3	0.3	0.3	0.3	0.3	0.3	0.5	0.5	0.5	0.5	0.5	0.5	
TTK Talc	4	4.5	4	4	4	4	4	4	4	4	4	7	7	7	7	7	7	
Potassium feldspar	-	-	-	-	-	-	-	-	-	-	-	4	4	4	4	4	4	
Titanium white R-5N	2	2	2	2	2	2	2	2	2	2	2	3	3	3	3	3	3	
Zinc oxide	6	6	6	6	6	6	6	6	6	6	6	25	25	25	25	25	25	
Zinc Oxadine	-	-	-	-	-	-	-	-	-	-	-	8	8	8	8	8	8	
2-Methylthio-4-t-butylamino-6-cyclopropylamino-s-triazine	2.5	-	-	-	2.5	2.5	2.5	2.5	2.5	2.5	2.5	3	-	-	-	-	-	
Copper Oxadine	-	2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
4,5-Dichloro-2-n-octyl-4-isothiazolin-3-one	-	-	7	-	-	-	-	-	-	-	-	-	-	3	-	-	-	
2-(p-Chlorophenyl)-3-cyano-4-bromo-5-trifluoromethylpyrrole	-	-	-	2.5	-	-	-	-	-	-	-	-	-	-	3	3	3	
Pyridine-triphenylborane	-	-	-	-	-	-	-	-	-	-	-	-	-	3	-	-	-	
Bengala 404	2.3	2.3	2.3	2.3	2.3	2.3	2.3	2.3	2.3	2.3	2.3	3	3	3	3	3	3	
NOVAPERM RED F5RK	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.5	0.5	0.5	0.5	0.5	0.5	
Ethyl Silicate 28	0.3	0.3	0.3	0.3	0.3	0.3	0.3	0.3	0.3	0.3	0.3	0.5	0.5	0.5	0.5	0.5	0.5	
[Total]	100	100	100	100	100	100	100	100	100	100	100	100	100	100	100	100	100	

[0077] [Table 6]

	Name	Example																							
		8	9	10	11	12	13	14	15	16	17	18	19	20	21	22	23	24	25						
Property	Specific gravity	2.05	2.08	2.04	2.07	2.05	2.05	2.05	2.05	2.05	2.05	2.04	2.05	1.55	1.55	1.56	1.56	1.55	1.55						
	Heating residue (wt%)	82.9	82.9	82.5	82.9	82.9	82.9	82.9	82.9	82.9	82.9	82.4	83.5	75.5	75.5	75.5	75.5	74.6	76.2						
	VOC (g/L)	347	353	354	352	347	347	347	347	347	347	348	337	377	377	377	381	381	390	366					
Storage stability (viscosity: dPa·s)	Initial	Viscosity	15	14	15	15	12	12	13	13	13	14	10	16	17	18	18	19	15						
		Film tension	G	G	G	G	G	G	G	G	G	G	G	G	G	G	G	G	G						
		Precipitates, coarse grains	G	G	G	G	G	G	G	G	G	G	G	G	G	G	G	G	G						
	1 month, 50°C	Viscosity	15	14	16	15	12	12	13	14	14	13	14	11	17	18	18	18	19	15					
		Film tension	G	G	G	G	G	G	G	G	G	G	G	G	G	G	G	G	G						
		Precipitates, coarse grains	G	G	G	G	G	G	G	G	G	G	G	G	G	G	G	G	G						
	2 month, 50°C	Viscosity	15	15	16	16	13	12	13	14	14	14	15	11	18	18	18	18	19	16					
		Film tension	G	G	G	G	G	G	G	G	G	G	G	G	G	G	G	G	G						
	Precipitates, coarse grains	G	G	G	G	G	G	G	G	G	G	G	G	G	G	G	G	G							
Coated film expendability (µm, cumulative value) (25°C/15 knots)	1 month	9.8	7.7	11.2	13.3	8.7	9.3	10.3	9.5	12.3	11.1	12.3	9.6	13.4	11.2	13.3	10.4	8.9	12.3						
	2 month	13.3	14.5	17.8	18.7	13.5	14.5	15.6	13.3	17.8	17.8	19.8	14.5	22.5	18.7	19.8	18.8	15.6	18.7						
	3 month	21.8	19.8	24.5	23.4	21.5	21.4	21.4	18.8	22.3	26.7	27.6	20.9	29.8	24.5	27.6	26.7	23.4	24.5						
	4 month	29.8	26.5	32.6	31.5	27.8	27.8	28.8	24.5	29.8	32.5	35.6	27.8	36.7	31.6	33.7	33.4	31.3	30.7						
	5 month	35.4	33.5	39.8	38.8	33.5	35.6	35.6	30.6	35.6	39.8	41.3	34.5	43.8	39.8	40.8	41.3	39.8	38.9						
	6 month	41.5	43.3	48.7	44.5	40.8	44.3	44.4	38.9	43.3	47.3	50.6	43.2	52.3	47.6	49.8	50.6	46.7	45.6						
Stationary antifouling property	1 month	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0						
	2 month	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0						
	3 month	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0						
	4 month	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5						
	5 month	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5						
	6 month	0.5	0.5	1	1	1	0.5	1	0.5	1	1	1	0.5	0.5	0.5	0.5	0.5	1	0.5	1					

[0078] [Table 7]

	Name	Comp. Ex.																	
		7	8	9	10	11	12	13	14	15	16	17	18	19	20	21	22	23	
Property	Specific gravity	2.05	2.08	2.04	2.07	2.05	2.05	2.05	2.05	2.05	2.04	2.05	1.55	1.55	1.56	1.56	1.55	1.55	
	Heating residue (wt%)	82.9	82.9	82.5	82.9	82.9	82.9	82.9	82.9	82.9	82.4	83.5	75.5	75.5	75.5	75.5	74.6	76.2	
	VOC (g/L)	347	353	354	352	347	347	347	347	347	358	337	377	377	381	381	390	366	
Storage stability (viscosity: dPa·s)	Initial	Viscosity	8	11	13	11	12	12	10	9	9	11	11	18	20	18	17	16	18
		Film tension	G	G	G	G	G	G	G	G	G	G	G	G	G	G	G	G	G
		Precipitates, coarse grains	G	G	G	G	G	G	G	G	G	G	G	G	G	G	G	G	G
	1 month, 50°C	Viscosity	23	24	26	19	23	24	19	21	17	19	22	35	31	38	29	25	29
		Film tension	P	P	P	P	P	P	P	P	P	P	P	P	P	P	P	P	P
		Precipitates, coarse grains	P	P	P	P	P	P	P	P	P	P	P	P	P	P	P	P	P
	2 month, 50°C	Viscosity	25	28	31	29	29	32	27	29	26	34	32	43	39	47	43	48	53
		Film tension	P	P	P	P	P	P	P	P	P	P	P	P	P	P	P	P	P
		Precipitates, coarse grains	P	P	P	P	P	P	P	P	P	P	P	P	P	P	P	P	P
Coated film expendability (µm, cumulative value) (25°C/15 knots)	1 month	10.5	8.7	9.8	11.1	10.6	8.9	7.8	12.3	11.3	9.3	8.6	10.8	12.3	11.3	8.6	12.3	9.8	
	2 month	13.3	10.3	11.1	14.5	14.3	12.3	10.4	15.6	15.7	13.3	12.4	14.5	17.8	15.6	12.1	16.7	14.1	
	3 month	16.7	13.3	13.4	17.7	17.7	15.6	12.3	19.9	20.7	18.8	17.8	18.9	22.3	21.4	15.5	19.4	18.8	
	4 month	19.8	16.7	16.7	20.1	22.4	18.8	15.4	24.5	25.4	22.5	22.4	23.4	27.8	26.5	18.7	25.7	23.5	
	5 month	22.3	20.4	19.7	23.4	26.7	22.3	18.9	28	29.7	25.8	29.8	29.8	33.3	31.6	22.3	30.5	28.9	
	6 month	24.5	23.3	21.2	26.5	30.1	25.9	22.2	31.3	33.3	29.7	31.2	35.6	40.7	37.6	26.7	35.9	34.5	
Stationary antifouling property	1 month	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	
	2 month	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	
	3 month	0	0	0.5	0	0	0.5	0	0	0	0.5	0	0	0.5	0.5	0.5	0	0	
	4 month	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5	
	5 month	1	0.5	1	0.5	0.5	0.5	1	0.5	0.5	1	0.5	1	1	1	1	1	1	
	6 month	2	1	2	1	1	1	2	1	1	1	1	1	1	1	1	1	1	


[0079] The details for some of the starting materials used in the examples and comparative examples are shown in Table 8.

[0080] [Table 8]

Product name	Maker	Type	Solid portion
TTK Talc	Fukuoka Talc	Extender pigment	100
Zinc oxide (mean particle diameter: 0.2-3 μm)	Kyushu Hokusui Chem.	Extender pigment	100
NOVAPERM RED F5RK	Clariant North America	Organic red pigment	100
Zinc Omadine	Arch Chem.	Organic antifouling agent	100
Copper Omadine	Arch Chem.	Organic antifouling agent	100
Bengala 404	Toda Indus.	Coloring pigment	100
TCP (Tricresyl phosphate)	Kyowa Hakko Indus.	Plasticizer	100
Potassium feldspar	KINSEI MATIC	Potassium feldspar	100
Titanium white R-5N	Sakai Chemical	Coloring pigment	100
4,5-Dichloro-2-n-octyl-4-isothiazolin-3-one	Rohm & Haas	Organic antifouling agent	30
WW rosin		Solid resin	100
BYK-101	BYK CHEMICAL	Pigment dispersant	100
2-Methylthio-4-t-butylamino-6-cyclopropylamino-s-triazine	Ciba	Organic antifouling agent	100
N,N'-Dimethyl-N'-tolyl-(N-fluorodichloromethylthio)sulfamide	Bayer, Japan	Organic antifouling agent	100
2-(p-Chlorophenyl)-3-cyano-4-bromo-5-trifluoromethylpyrrole	JANSSEN	Organic antifouling agent	100
Pyridine-triphenylborane	Hokko Chem. Indus.	Organic antifouling agent	100
Medetomidine	i-Tech	Organic antifouling agent	100
Cuprous oxide NC-803	NC Tech.	Inorganic antifouling agent	100
Dis603-20XC	Kusumoto Chem.	Anti-running agent	20

CLAIMS

1. A polyester resin for an antifouling coating material obtained by reacting a (a) trihydric or greater alcohol, a (b) dibasic acid or its anhydride and a (c) divalent alcohol, and then further reacting with an
5 (d) alicyclic dibasic acid or its anhydride.
2. The polyester resin for an antifouling coating material according to claim 1, wherein the (d) alicyclic dibasic acid or its anhydride is an alicyclic dibasic acid anhydride.
3. The polyester resin for an antifouling coating material according to
10 claim 1 or 2, wherein the (d) alicyclic dibasic acid or its anhydride comprises hexahydrophthalic anhydride.
4. The polyester resin for an antifouling coating material according to any one of claims 1 to 3, wherein the (a) trihydric or greater alcohol comprises one or more of glycerin and trimethylolpropane.
- 15 5. The polyester resin for an antifouling coating material according to any one of claims 1 to 4, which comprises one or more of an alicyclic dibasic acid anhydride and an aromatic dibasic acid anhydride as the (b) dibasic acid or its anhydride.
6. The polyester resin for an antifouling coating material according to
20 any one of claims 1 to 4, wherein the (c) divalent alcohol is a branched alkylene glycol.
7. A polyester resin for an antifouling coating material, comprising a compound having the structure represented by formula (1):



- 25 wherein R^1 is selected from among C3-24 trivalent or tetravalent hydrocarbon groups, R^2 and R^3 are selected from among C2-34

divalent hydrocarbon groups, R^4 is selected from among C3-24
divalent alicyclic hydrocarbon groups, and n represents an integer of 3
or 4.

8. The polyester resin for an antifouling coating material according to
5 any one of claims 1 to 7, wherein the acid value of the solid portion is
50 to 250 mgKOH/g.

9. A method for producing a polyester resin for an antifouling coating
material, comprising a first step of reacting a (a) trihydric or greater
alcohol, a (b) dibasic acid or its anhydride and a (c) divalent alcohol,
10 and a second step of further reacting an (d) alicyclic dibasic acid or its
anhydride after the first step.

10. The method for producing a polyester resin for an antifouling
coating material according to claim 9, wherein the (d) alicyclic dibasic
acid or its anhydride is an alicyclic dibasic acid anhydride.

11. The method for producing a polyester resin for an antifouling
15 coating material according to claim 9 or 10, wherein the (d) alicyclic
dibasic acid or its anhydride comprises hexahydrophthalic anhydride.

12. The method for producing a polyester resin for an antifouling
coating material according to any one of claims 9 to 11, wherein the (a)
20 trihydric or greater alcohol comprises one or more of glycerin and
trimethylolpropane.

13. The method for producing a polyester resin for an antifouling
coating material according to any one of claims 9 to 12, wherein the
polyester resin comprises one or more of an alicyclic dibasic acid
25 anhydride and an aromatic dibasic acid anhydride as the (b) dibasic
acid or its anhydride.

14. The method for producing a polyester resin for an antifouling coating material according to any one of claims 9 to 13, wherein the (c) divalent alcohol is a branched alkylene glycol.
15. A coating composition comprising the polyester resin according to
5 any one of claims 1 to 8.
16. An antifouling coating material composition comprising the polyester resin according to any one of claims 1 to 8.
17. The antifouling coating material composition according to claim 16, further comprising a polyvalent metal compound.
- 10 18. The antifouling coating material composition according to claim 17, wherein the polyvalent metal compound is at least one compound selected from the group consisting of oxides, hydroxides, halides and carbonates of divalent or trivalent metals.
19. The antifouling coating material composition according to claim 17
15 or 18, wherein the polyvalent metal compound is zinc oxide.
20. The antifouling coating material composition according to any one of claims 17 to 19, wherein the polyvalent metal compound content is 10 to 700 parts by mass with respect to 100 parts by mass of the polyester resin.
- 20 21. The antifouling coating material composition according to any one of claims 16 to 20, further comprising a rosin and/or a rosin derivative.
22. The antifouling coating material composition according to any one of claims 16 to 21, further comprising an antifouling agent.
23. The antifouling coating material composition according to any one
25 of claims 16 to 22, further comprising a plasticizer.
24. The antifouling coating material composition according to any one

of claims 16 to 23, further comprising an extender pigment (excluding said polyvalent metal compound).

25. The antifouling coating material composition according to any one of claims 16 to 24, further comprising a pigment dispersant.

5 26. The antifouling coating material composition according to any one of claims 16 to 25, further comprising a color pigment.

27. The antifouling coating material composition according to any one of claims 16 to 26, further comprising a dehydrating agent.

10 28. The antifouling coating material composition according to any one of claims 16 to 27, further comprising a volatile organic compound, wherein the volatile organic compound content is no greater than 400 g/L.

29. An antifouling coating film obtained by curing the antifouling coating material composition according to any one of claims 16 to 28.

15 30. An antifouling base obtained by coating or impregnating a base with the antifouling coating material composition according to any one of claims 16 to 28, and curing the coating composition that has been coated onto or impregnated into the base to form an antifouling coating film on the base.

20 31. A method for producing an antifouling base comprising:

coating or impregnating a base with the antifouling coating material composition according to any one of claims 16 to 28, and

curing the coating composition that has been coated onto or impregnated into the base to form an antifouling coating film on the

25 base.