

## ABSTRACT

5 A multi-layer direct blow bottle in which a metallic layer containing a metal pigment having an average thickness of not more than 1  $\mu\text{m}$  dispersed in a resin is formed at a position where it is visible from the outer surface side. This bottle is decorated metallic by extremely inexpensive means and gives an excellent metallic appearance stably.