



G00002

PERPENDICULAR MAGNETIC RECORDING MEDIA

BACKGROUND OF THE INVENTION

1. Field of the Invention

The present invention relates to perpendicular magnetic recording media, and more particularly, to a perpendicular magnetic recording medium with an increased recording density.



159159

2. Description of the Related Art

Perpendicular magnetic recording media generally have high recording density, as compared to longitudinal magnetic recording mechanism. Hence, recent hard disk drives (HDDs) use perpendicular magnetic recording media to obtain a high recording density. Perpendicular magnetic recording media have a magnetization that is perpendicular to the main plane of the media. The recording density of such perpendicular magnetic recording media is greatly affected by the properties of a perpendicular magnetic recording layer and by an underlayer which perpendicularly orients a magnetization in a magnetic recording layer.

FIG. 1 shows the layer structure of a conventional perpendicular magnetic recording medium having a single magnetic layer. FIGS. 2 and 3 show the later structures of conventional perpendicular magnetic recording media having two magnetic layers.

Referring to FIG. 1, a perpendicular magnetic recording layer 13, where information is recorded, is placed over the upper surface of a substrate 11. A perpendicular orientation underlayer 12 for perpendicularly orienting the magnetization of the perpendicular magnetic recording layer 13 is placed between the substrate 11 and the perpendicular magnetic recording layer 13. A protection layer 14 is formed on the perpendicular magnetic recording layer 13 to protect the perpendicular magnetic recording layer 13. A lubricating layer 15 is formed on the protection layer 14 to reduce abrasion of a magnetic head of an HDD and the protection layer 14 due to collision and sliding of the protective layer 14 and the magnetic head.

Referring to FIG. 2, a perpendicular magnetic recording layer 23, where information is recorded, is placed over the upper surface of a substrate 21. A soft material layer 22, which forms a magnetic path of a perpendicular magnetic field

generated by a magnetic head of an HDD, is placed between the substrate 21 and the perpendicular magnetic recording layer 23. A protection layer 24 and a lubricating layer 25 are sequentially formed on the perpendicular magnetic recording layer 23.

5 Referring to FIG. 3, a perpendicular magnetic recording layer 224, where information is recorded, is placed over the upper surface of a substrate 221. A perpendicular orientation underlayer 223 and a soft material layer 222 are placed between the substrate 221 and the perpendicular magnetic recording layer 224. A protection layer 225 and a lubricating layer 226 are sequentially formed on the
10 perpendicular magnetic recording layer 224.

The types and composition ratio of elements that form each of the perpendicular magnetic recording layers 13, 23, and 224 greatly affect the types and structures of the corresponding perpendicular orientation underlayers 12 and 223 and the soft magnetic layer 22. An existing perpendicular orientation underlayer
15 formed of Ti or Pt is greatly affected by the characteristics of a perpendicular magnetic recording layer. If a perpendicular orientation underlayer is formed of Ti, a thick initial growth film is formed between the perpendicular magnetic layer and the Ti perpendicular orientation underlayer due to the difference in the crystal lattice constant between them. Thus, the orientation characteristic of the perpendicular
20 magnetic recording layer is deteriorated. A perpendicular orientation underlayer formed of Pt has an excellent perpendicular crystal orientation because it has a small difference in the lattice constant from the perpendicular magnetic recording layer. However, the excellent perpendicular crystal orientation shown in some perpendicular magnetic recording layers causes crystal grains to be enlarged and
25 exchanged coupling to be increased, thereby degrading a signal-to-noise ratio (SNR) upon information recording/writing.

SUMMARY OF THE INVENTION

The present invention provides a perpendicular magnetic recording medium
30 which has an increased recording density by improving perpendicular orientation properties.

According to an aspect of the present invention, there is provided a perpendicular magnetic recording medium in which a perpendicular magnetic recording layer is placed on a substrate and a multi-layered perpendicular orientation

underlayer is placed between the substrate and the perpendicular magnetic recording layer and having first through third underlayers each made of Pt.

In the perpendicular magnetic recording medium, at least one of the first and third underlayers is formed of any of Pt and a Pt alloy, and the second underlayer is formed of any of Ti and a Ti alloy.

Also, in an embodiment of the perpendicular magnetic recording medium, a soft magnetic layer is placed between the perpendicular orientation layer and the substrate.

BRIEF DESCRIPTION OF THE DRAWINGS

The above and other features and advantages of the present invention will become more apparent by describing in detail exemplary embodiments thereof with reference to the attached drawings in which:

FIG. 1 shows the layer structure of a conventional perpendicular magnetic recording medium with a single magnetic layer;

FIG. 2 shows the layer structure of a conventional perpendicular magnetic recording medium with two magnetic layers;

FIG. 3 shows the layer structure of another conventional perpendicular magnetic recording medium with two magnetic layers;

FIG. 4 shows the layer structure of a perpendicular magnetic recording medium according to a first embodiment of the present invention;

FIG. 5 shows the layer structure of a perpendicular magnetic recording medium according to a second embodiment of the present invention;

FIG. 6 shows magnetic hysteresis loops of a perpendicular magnetic recording medium according to the present invention; and

FIG. 7 is a graph showing the size of grains and a perpendicular orientation characteristic of a perpendicular magnetic recording medium according to the present invention.

DETAILED DESCRIPTION OF THE INVENTION

A perpendicular magnetic recording medium according to a first embodiment of the present invention shown in FIG. 4 has a single magnetic layer. A perpendicular magnetic recording medium according to a second embodiment of the present invention shown in FIG. 5 has two magnetic layers.

Referring to FIG. 4, first, second, and third underlayers 301, 302, and 303 are sequentially formed on the upper surface of a substrate 300. A perpendicular magnetic recording layer 304, where information is recorded, is formed on the third underlayer 303. As in conventional magnetic recording media, a protection layer 305 and a lubricating layer 306 are formed on the perpendicular magnetic recording layer 304.

Referring to FIG. 5, in contrast with the first embodiment of FIG. 4, a soft magnetic layer 401 is first formed on the upper surface of a substrate 400. Next, first, second, and third underlayers 402, 403, and 404 are sequentially formed on the soft magnetic layer 401. A perpendicular magnetic recording layer 405, where information is recorded, is formed on the third underlayer 404. As in conventional magnetic recording media, a protection layer 406 and a lubricating layer 407 are formed on the perpendicular magnetic recording layer 405.

In the perpendicular magnetic recording media according to the present invention, the three underlayers 301, 302, and 303 (or 402, 403, and 404) are used to form a perpendicular orientation underlayer to improve the perpendicular orientation of the perpendicular magnetic recording layer 304 (or 405).

The first underlayers 301 and 402 and the third underlayers 303 and 404 are mainly formed of Pt, and the second underlayers 302 and 403 are mainly formed of Ti.

If a single Pt underlayer is used as a perpendicular orientation underlayer, some perpendicular magnetic recording layers increase exchange coupling and enlarge crystal grains. Thus, noise upon information recording/writing is increased, and electrical characteristics, such as, a coercive force or a second-quadrant hysteresis loop inclination, are deteriorated. These problems are mainly due to the thickness of the Pt underlayer. If the Pt underlayer is thick, the crystal grains of the Pt underlayer are enlarged. Accordingly, the crystal grains of the perpendicular magnetic recording layer are enlarged, and exchange coupling increases.

A thin Pt underlayer decreases the size of crystal grains and an exchange coupling of the perpendicular magnetic recording layer and also provides an excellent perpendicular orientation. However, if the Pt underlayer is too thin, it cannot form a complete layer structure, and accordingly it is difficult to be used.

In the present invention, in order to overcome the defects of the single Pt underlayer and form a perpendicular orientation underlayer with excellent properties,

a first Pt thin underlayer is deposited to obtain stability. Next, a very thin second underlayer is deposited using Ti or the like to prevent crystal grains from being enlarged and to have the properties of the first Pt underlayer. Finally, a third Pt underlayer is deposited to provide excellent magnetic characteristics to a perpendicular magnetic recording layer and reduce the size of crystal grains and an exchange coupling effect. Therefore, a thermally-stable perpendicular magnetic recording medium with an excellent SNR can be obtained.

FIG. 6 shows the magnetic hysteresis loop of a perpendicular magnetic recording layer having a three-layered perpendicular orientation underlayer according to the present invention and the magnetic hysteresis loops of two conventional perpendicular magnetic recording media having single-layered perpendicular orientation underlayers made of Pt and Ti.

As shown in FIG. 6, the perpendicular magnetic recording layer having a three-layered perpendicular orientation underlayer according to the present invention has a higher coercive force value (H_c), a higher nucleation field value (H_n), and a higher squareness value (SQ) than those of the two conventional perpendicular magnetic recording media. Consequently, the perpendicular magnetic recording layer having a three-layered perpendicular orientation underlayer according to the present invention can provide an excellent thermal stability and a low exchange coupling.

FIG. 7 shows the size of crystal grains and the crystal orientation of perpendicular magnetic recording media having a three-layered perpendicular orientation underlayer according to the present invention. It can be seen from FIG. 7 that the perpendicular magnetic recording media according to the present invention have similar-sized crystal gains to those of two conventional perpendicular magnetic recording media and an excellent perpendicular orientation. As a result, the perpendicular magnetic recording media according to the present invention can achieve high-density recording with a high SNR.

While the present invention has been particularly shown and described with reference to exemplary embodiments thereof, it will be understood by those of ordinary skill in the art that various changes in form and details may be made therein without departing from the spirit and scope of the present invention as defined by the following claims.

As described above, due to the use of a three-layered perpendicular orientation underlayer, an excellent perpendicular orientation and a consistent crystal lattice of a Pt underlayer can be obtained. Also, the perpendicular orientation underlayer has small crystal grains. Thus, the perpendicular orientation underlayer having excellent perpendicular orientation and small crystal grains enables a perpendicular magnetic recording layer to have a good thermal stability, a high recording density, and a high SNR.

5

What is claimed is:

1. A perpendicular magnetic recording medium comprising:
 a perpendicular magnetic recording layer placed over a substrate; and
 a multi-layered perpendicular orientation underlayer placed between the
 5 substrate and the perpendicular magnetic recording layer and having first through
 third underlayers each made of Pt.

2. The perpendicular magnetic recording medium of claim 1, wherein at
 10 leas one of the first and third underlayers is formed of any of Pt and a Pt alloy, and
 the second underlayer is formed of any of Ti and a Ti alloy.

3. The perpendicular magnetic recording medium of claim 1, wherein a
 soft magnetic layer is placed between the perpendicular orientation layer and the
 substrate.

4. The perpendicular magnetic recording medium of claim 2, wherein a
 soft magnetic layer is placed between the perpendicular orientation layer and the
 substrate.