

This invention relates to polymeric film structures of improved opacity; more particularly, this invention relates to pigmented such films; and to their manufacture.

U.S. Patent 4,377,616 discloses an opaque, biaxially oriented polymeric film structure of lustrous satin appearance comprising:

a core thermoplastic polymer matrix material within which is located a strata of voids;

positioned at least substantially within at least a substantial number of each of said voids, is at least one spherical void-initiating solid particle which is phase distinct and incompatible with said matrix material, the void-space occupied by said particle being substantially less than the volume of said void, with one generally cross-sectional dimension of said particle at least approximating a corresponding cross-sectional dimension of said void;

void-free, transparent, thermoplastic skin layers adhering to the surfaces of said core layer, said skin layers being of a thickness such that the outer surfaces thereof do not, at least substantially, manifest the surface irregularities of said core layer;

the population of voids in said core being such as to cause a degree of opacity of less than 70% light transmissions;

said structure having a 45° gloss measurement greater than 100%.

It also discloses that from 1 to 3% by weight of the core of an opacifying pigment may be incorporated: titania is specifically exemplified.

This invention seeks to provide film structures of enhanced opacity.

opacity and lustrous satin appearance which comprises:

- (a) a voided core layer comprising a matrix of (i) a thermoplastic polymeric material in which are dispersed (ii) void-initiating solid particles which are phase-distinct from the thermoplastic polymeric material of the matrix and about which particles are located opacifying voids and a minor amount (iii) of a light absorbing pigment; and
- (b) at least one transparent skin layer adhering to the surface of the voided core layer comprising a thermoplastic polymeric material and being thick enough substantially to prevent the asperities of the core layer from being manifest, the light transmission of the structure being less than about 15%, and the structure having a gloss measurement greater than 80%.

According to a further aspect of this invention, there is also provided a process for the preparation of a film structure as herein defined, which process comprises:

- mixing a major proportion of (i) with a minor proportion of (ii) which preferably has a higher melting point and/or higher glass transition temperature than (i);

- heating the mixture to a temperature above the melting point of (i);

- uniformly dispersing (ii) throughout (i) preferably as microspheres;

- uniformly dispersing a minor amount, suitably from 2 to 12 wt. %, preferably greater than 3 to 10 wt. %, especially 4 to 9 wt. %, of (iii) therein; and

- forming a biaxially-oriented core layer (a) having adhering to at least one surface of (a) a transparent skin layer (b), the biaxial orientation having been effected at a temperature and deformation ratio effective to form opacifying voids in the core layer.

exist between the thickness dimension of the core and the thickness dimension of the skin layer or layers which can be transparent or pigmented for further augmented opacity. It is preferred that the core thickness be from about 30, preferably from 40, to about 85% of the overall structure. This, in combination with the population and configuration of the voids in a structure at least about 0.5 mils thick, will materially contribute to the overall degree of opacity of the structure. Likewise, by maintaining the skin thickness within a particular range in relation to the overall structure and to the thickness of the core layer, the overall combination results in the unique film combination. It is preferred that the combined skin thickness be about 15 to about 70% of the overall film structure. It is important that the skin layers be sufficiently thick so that the outer surfaces thereof do not manifest the irregularities or surface projections of the core material. It is understood that the film structure may consist (100%) entirely of the described core or it may consist of the core and one layer or the core and multiple layers.

It is preferred that the average diameter of the void-initiating particles be from about 0.1 to about 10 microns. These particles may be of any desired shape although it is preferred that they be substantially spherical in shape. This does not mean that every void is the same size. It means that, generally speaking, each void tends to be of like shape when like particles are used, even though they vary in dimensions. Ideally, these voids assume a shape defined by two opposed and edge contacting concave disks.

Experience has shown that optimum characteristics of opacity and satin-like appearance is obtained when the two average major void dimensions are greater than about 30 microns.

The void-initiating particle material, as indicated above, should be incompatible with the core material, at least at the temperature of biaxial orientation.

From this it is to be understood that the voids create the matrix configuration. The term "strata" is intended to convey the understanding that there are a large number of voids creating the matrix and the voids themselves are oriented so that the two major dimensions are aligned in correspondence with the direction of orientation of the polymeric film structure. After each void has been formed through the initiation of the described particle, the particle generally contributes little else to the system. This is because its refractive index can be close enough to the matrix material that it makes no contribution to opacity. When this is the case, the opacity is principally a function of the light scattering effect which occurs because of the existence of the voids in the system.

When light absorbent colored pigment is added to the expanded layer of a film an unexpected increase in opacity occurs. Usually from 3 to about 10 wt.% or more and preferably 4 to about 8% of light absorbing pigment is added. With 2% pigment in a nonexpanded film a light transmission (LT) of 46% is obtained. Placing 2% pigment in the nonexpanded skin of an expanded core film yields a LT of 18%, placing the same amount of pigment in the expanded core with nonpigmented skins yields a LT of 10% or a decrease of 8 LT units. (Also note that at a 4% pigment loading when pigment is placed in the skin only a 6 unit decrease in LT is seen but when the same amount is placed in the expanded core a 7 LT unit decrease is observed.) It is clear, therefore, that a lot more pigment is required in the skin only to achieve opacity comparable to that obtained for a specific pigment concentration in the core.

The concentration of pigment in each case is based on the total weight of the sample. Any suitable light absorbent colored pigment may be used, e.g., brown, green, black, red or blue, etc. Such pigments may be selected from those conventionally used in the dyeing and/or coloring of synthetic resins, industrial coatings and paints, and may be organic or inorganic.

are disclosed in Vol. 17, pages 788-889, Kirk Othmer Encyclopedia of Chemical Technology, 3rd Edition C 1982. Some exemplary pigments are carbon black, brown iron oxide iron blue, etc. Accordingly, light absorbing pigments as used herein are understood to mean "colored" light absorbing pigments.

When pigments such as TiO_2 are used they function primarily to mask contact clarities, since they are primarily light reflecting pigments, and as such can add little to the measured opacity of the film structure. It is noted that the greatest degree of opacity is achieved by using an expanded film, a light absorbent colored pigment and a cavitated core. The pigment material is present in such a particle size, shape and amount that it does not, in any material sense, by itself contribute any void initiation.

A typical void of the core is defined as having major dimensions X and Y and minor dimension Z, where dimension X is aligned with machine direction orientation, dimension Y is aligned with transverse direction orientation and dimension Z approximately corresponds to the cross-sectional dimension of the spherical particle which initiated the void.

It is a necessary part of the present invention that orientation conditions be such that the X and Y dimensions of the voids of the core be major dimensions in comparison to the Z dimension. Thus, while the Z dimension generally approximates the cross-sectional dimension of the spherical particle initiating the void, the X and Y dimensions must be significantly greater.

By way of illustration, room temperature biaxial orientation of a polypropylene matrix containing polybutylene terephthalate (PBT) spheres of the size and amount contemplated herein, could not produce the claimed structure. Either void splitting will occur, or, voids of insignificant size would result. As shown in the examples, infra, polypropylene must be oriented at a temperature significantly higher than its glass transition temperature. The

significant degree. If this is accomplished, optimum physical characteristics, including low water vapor transmission rates and a high degree of light scattering is obtained without void splitting or film fibrillating.

As indicated above, the matrix polymer and the void initiating particle must be incompatible and this term is used in the sense that the materials are two distinct phases. The spherical void initiating particles constitute a dispersed phase throughout the lower melting polymer which polymer will, ultimately, upon orientation, become a void filled matrix with the spherical particles positioned somewhere in the voids.

As a result of the biaxial orientation of the film structure described herein, in addition to opacifying the core layer of the structure, the orientation improves other physical properties of the composite layers such as, flex-cracking resistance, Elmendorff tear strength, elongation, tensile strength, impact strength and cold strength properties. The resulting film can have, in addition to a rich, high quality appearance and excellent opacifying characteristics, low water vapor transmission rate characteristics and low oxygen transmission rate characteristics. This makes the film ideally suited for packaging food products, including liquids. The film also has attractive utility as a decorative wrap material.

It is believed that because of the comparative sphericity of the void-initiating particles, the voids are closed cells. This means that there is virtually no path open from one side of the core to the other through which liquid or gas can traverse.

The void-initiating particles can be organic or inorganic, preferably, they are substantially spherical in shape and within the preferred particle size range so as to initiate the formation of a void, which in a significant number of cases, has a lens-like shape, that is, a lens of the biconvex shape. When a polymeric material is contemplated as the void-initiating particle, it can be a polymer

point than the core polymer and be incompatible and capable of assuming a dispersed phase of small particles as the temperature of the co-melted mix is reduced. It is also contemplated that the void initiating particles can be preformed and then uniformly dispersed into a melt of, e.g., polypropylene. This has the advantage of not having to subject the matrix polymer to the temperature of a much higher melting polymer. In this manner, any thermal degradation of the matrix polymer is avoided.

It is believed that because of the number, the shape and the orientation strata-wise of matrix voids, a significantly enhanced light scattering effect is obtained by virtue of the present invention. This effect is further enhanced or magnified by the use of the two transparent skin layers of the size relationship mentioned above.

When preformed spheres, for example, are employed, it is the shape and size of the sphere that is important rather than the chemical nature of the material, per se. Thus, solid or hollow organic or inorganic spheres of any type can be employed. The light scattered in a particular void is additionally either absorbed or reflected by the void initiating sphere and the light absorbing pigment. Inorganic materials include solid or hollow preformed glass spheres, metal beads or spheres, ceramic spheres, etc. In fact, any material which can be formed into spheres or other suitable shape without causing thermal degradation to the core material is contemplated.

Examples of a thermoplastic resin which can be the dispersed phase within the matrix material, are the polyesters, such as polybutylene terephthalate and polyethylene terephthalate, polycarbonates, polysulfones, acetals, acrylic resins, nylon, etc.

By the technique of the present invention, light transmission through the film structures contemplated herein can be reduced to about 15% or less. This would be true in a film having an overall thickness of at least 1.5 mils where the core portion of this is at least 60% and the individual skin layers are 20%.

size range from about 0.75 to about 4 microns. The void initiating particles can be present in up to about 20% by weight of the core layer prior to orientation, a preferred range being from 2 to about 7 percent by weight. As stated hereinabove, the light absorbing colored pigment particles can be present in up to about 12% of the core material with a preferred range being from 4 to about 9 wt.% of the core. The pigment particles may be of any size insufficient to cause cavitation. Accordingly, the pigment particles occupy substantially less space than the void-initiating particles. The pigment particles may be conveniently added to the core only, to the skins only or to one skin only, or to any combination of the above, preferably, they are added to the core only.

For convenience and more precise control of the formulation and character of the core layer, a master batch technique can be employed either in the case of forming the spherical particles in situ or in adding preformed spheres to the molten core matrix material. After the formation of a master batch, appropriate dilution of this system can be made by adding additional thermoplastic core matrix material until the desired proportions are obtained.

The core material and the skin material may be coextruded. Thereafter, biaxial orientation is carried out to an extent and at a temperature calculated to obtain the maximum degree of opacity without any significant sacrifice in the physical characteristics, including appearance, of the film structure. Obviously, as the materials employed change, the conditions of biaxial orientation will change. By way of exemplification, when employing polypropylene as the material of the core matrix and of the transparent skin layers, and when employing PBT as the void initiating particles, a machine direction orientation of from 4 to 8 times and a transverse direction orientation of from about 4 to 10 times, at a drawing temperature of from 100°C to 170°C to yield a

the same, or of different, polymeric material.

In the following Examples, characteristics of the film were measured by ASTM method D 1003-61 entitled "Test for Haze and Luminous Transmittance of Transparent Plastics".

EXAMPLE 1

An isotactic polypropylene (MP 165°C and a melt flow rate of 4.5) containing 1.4% TiO_2 by weight (light reflecting pigment) was melt extruded in an extruder provided with a screw of L/D ratio of 20/1. The extruder temperature profiles ranged from 190°C to 220°C. The extrudate was quenched and subsequently biaxially oriented five by nine times using a commercially available sequential biaxially orienting apparatus. The MD orientation temperature ranged from 105°C to 135°C and those of TD were from 150°C to 170°C.

The resulting 1.5 mil film had a 72% light transmission and a gloss of 70%.

EXAMPLE 2

The procedure of Example 1 was followed except that 2.8 weight percent TiO_2 based on the total structure was added.

The resulting 1.5 mil film had a 62% light transmission.

EXAMPLE 3

The procedure of Example 1 was repeated except that various levels of light absorbing brown colored pigments were added to the isotactic polypropylene in place of the TiO_2 .

Table 1 summarizes the results showing % light transmission on various colored pigment (brown, brown iron oxide) loading amounts.

TABLE 1

<u>Pigment Loading Amount, wt.%</u>	<u>Light Transmission</u>
1.4	59
2.8	37
4.4	25
8.8	8

melt flow rate of 4.5), PBT (6 parts, MP 227°C) and 2% TiO_2 was melted in an extruder provided with a screw of L/D ratio of 20/1. A second extruder was in association with this first mentioned extruder and supplied with the same polypropylene but without the PBT and TiO_2 present. A melt coextrusion was carried out while maintaining the barrel temperature for the core material ranging from 190° to 220°C. The barrel temperature for the polypropylene to be extruded as the skin layers was maintained at 220°C. A three-layer film structure was coextruded with a core thickness 70% of the total extruded thickness. The skin layers were each approximately 15% of the total thickness. The unoriented film measured approximately 40 mils in thickness. This sheet was subsequently oriented five by nine times using a commercially available sequential biaxially orienting apparatus.

The resulting 1.5 mil film structure had a 26% light transmission and a gloss of 115%.

The TiO_2 aids in increasing the contact opacity of the film but does not measurably aid in the measured opacity at lower levels of TiO_2 . Opacities of from 72% light transmission to about 26% light transmission have been achieved using core formulations containing from about 87 to 96% polypropylene and from 3 to 10% PBT and from about 1 to about 3% TiO_2 .

EXAMPLE 5

The procedure of Example 4 was repeated except that various levels of light absorbing colored pigment (brown iron oxide) were added in the skin resin.

The resulting % light transmission on the pigment loading amount based on total film structure is listed in Table 2.

1.9	19
2.8	17
4.2	11

EXAMPLE 6

The procedure of Example 4 was followed except that various levels of the light absorbing colored pigment were added to the core formulation. The % light transmission on the pigment loading amount based on total film structure is summarized in Table 3.

TABLE 3

<u>Pigment Loading Amount, Wt.%</u>	<u>% Light Transmission</u>
1.4	13
2.8	7
4.2	3

The data disclosed hereinabove reveal without question the surprising and unexpected increase in opacity or decrease in light transmission of light absorbing pigments versus prior art light reflecting pigments. For example, various loading amounts and locations of light absorbing pigments in accordance with the invention and a prior art light reflecting pigment were compared. The results whether it is light reflecting or absorbing reveal that the location of the pigment, whether it is light reflecting or absorbing, greatly determines its opacifying effect.

The data clearly show the differences and unexpected superiority of light absorbing pigment versus light reflecting pigment. The light absorbing pigment is unquestionably more effective than the light reflecting TiO_2 for light blockage. Examples 1 and 2 are of uncavitated film structure with minor amounts of TiO_2 ; Example 3 is of the same film containing various levels of colored pigment

superior opacity. Note Example 2 which provide a LT of 62% at 2.8% TiO_2 and Item 2 of Table 1 where the pigment in accordance with the invention provides an LT of 37% at 2.8%.

Examples 4, 5 and 6 are various cavitated film structures containing light absorbing pigment as disclosed herein, Examples 4 and 6 were core only pigment, and Example 5 was skin only pigment. At 4.2%, pigment loading the core only pigment film structure permitted almost 75% less light transmission. In comparison with the uncavitated film structure at 2.8% pigment, the cavitated pigment core (Table 3) permitted about 5 times less light transmission than did the non-cavitated core of Example 3 (Table 1). The magnitude of the change in light transmission for light reflecting pigment and skin versus expanded core pigment is highly significant and quite unexpected.

1. An opaque, biaxially-oriented, polymeric film structure which comprises:

- (a) a voided core layer comprising a matrix of (i) a thermoplastic polymeric material in which are dispersed (ii) void-initiating solid particles which are phase-distinct from the thermoplastic polymeric material of the matrix and about which particles are located opacifying voids and a minor amount (iii) of a light absorbing pigment; and
- (b) at least one transparent skin layer adhering to the surface of the voided core layer comprising a thermoplastic polymeric material and being thick enough substantially to prevent the asperities of the core layer from being manifest, the light transmission of the structure being less than about 15%.

2. A film structure according to claim 1 wherein the thermoplastic polymeric material (i) of the matrix comprises a polyolefin.

3. A film structure according to claim 2 wherein the polyolefin comprises polypropylene.

4. A film structure according to any preceding claim wherein the void-initiating solid particles (ii) comprise an organic or inorganic material.

5. A film structure according to claim 4 wherein the material comprises a polymeric material.

6. A film structure according to claim 5 wherein the organic polymeric material comprises a polyester.

7. A film structure according to claim 6 wherein the polyester comprises polybutylene terephthalate.

8. A film structure according to any preceding claim wherein the void-initiating solid particles (ii) are substantially spherical.

9. A film structure according to any preceding claim wherein the void-initiating solid particles (ii) have an average particle size from 0.5 to 10 micrometres.

red coloured pigment.

11. A film structure according to claim 10 wherein the pigment is a brown pigment.

12. A film structure according to any preceding claim wherein the light absorbing pigment (iii) has an average particle size insufficient to cause voiding of the core layer.

13. A film structure according to any preceding claim wherein the light absorbing pigment (iii) is present in the core layer only.

14. A film structure according to any preceding claim wherein the light absorbing pigment (iii) is present in an amount from 2 to 12 wt. % of the core.

15. A film structure according to any preceding claim wherein at least one skin layer (b) comprises the same polymeric material as the voided core layer (a).

16. A film structure according to any preceding claim wherein the thickness of the voided core layer (a) comprises from 30 to 85% of the thickness of the structure.

17. A process for the preparation of a film structure according to any preceding claim, which process comprises:

mixing a major proportion of (i) with a minor proportion of (ii);

heating the mixture to a temperature above the melting point of (i);

uniformly dispersing (ii) throughout (i);

uniformly dispersing a minor amount of (iii) therein; and

forming a biaxially-oriented core layer (a) having adhering to at least one surface of (a) a transparent skin layer (b), the biaxial orientation having been effected at a temperature and deformation ratio effective to form opacifying voids in the core layer.

18. A process according to claim 17 wherein (i) and (ii) are melted together.

20. A process according to any of claims 17 to 19 wherein the biaxial orientation is effected after the adhesion of (b) and (a).

21. A process according to any of claims 17 to 20 wherein the orientation in both directions is effected concurrently.

22. A process according to any of claims 17 to 21 wherein the orientation is effected at a temperature above 100°C.

23. A modified film structure according to any of claims 1 to 14 wherein the skin layer (b) is absent.

24. A modified film structure according to any of claims 1 to 15 wherein the skin layer (b) does not prevent the asperities of the core layer from being manifest.

An opaque, biaxially oriented film structure is described which comprises:

an expanded thermoplastic polymer matrix core layer within which is located a minor amount of a light-absorbing pigment and a strata of voids; positioned at least substantially within at least a substantial number of said voids is at least one void-initiating particle which is phase distinct and incompatible with the matrix material, the void space occupied by said particle being substantially less than the volume of said void, with one generally cross-sectional dimension of said particle, at least approximating a corresponding cross-sectional dimension of said void; the population of voids in said core and the thickness of said core being such as to cause a degree of opacity of less than 15% light transmission; and

at least one void-free thermoplastic skin layer affixed to a surface of the core layer, said skin layer(s) being of a thickness such that the outer surfaces thereof do not, at least substantially, manifest the surface irregularities of said core layer.