

Catalyst, process for producing the catalyst and
process for preparing vinyl acetate using the catalyst

The present invention relates to a catalyst comprising
5 palladium and/or its compounds, gold and/or its
compounds and also at least one alkali metal compound,
a process for producing it and its use for preparing
vinyl acetate in the gas phase from acetic acid,
ethylene and oxygen or oxygen-containing gases.

10

It is known from the prior art that vinyl acetate can
be prepared in the gas phase from ethylene, oxygen and
acetic acid in the presence of catalysts which comprise
palladium, gold and alkali metal compounds on a porous
15 support material (such as silicon dioxide).

The distribution of the noble metals on the support
material is of particular importance for the activity
and selectivity of these catalysts. Since the reactants
20 in the reaction to be catalyzed cannot readily diffuse
into the intermediate or inner regions of the porous
support material, the reaction takes place essentially
only on the outermost or surface regions of the
catalyst. Thus, the metal components present in the
25 interior or in the intermediate regions of the support
do not contribute significantly to the reaction
mechanism, which leads to a reduction in productivity
of the catalyst based on the weight of the noble
metals.

30

In the development of effective catalysts for vinyl
acetate production, efforts have therefore been
directed at providing catalysts in which the
catalytically active noble metals are present in a
35 shell on the support particles while the core of the
support particles is largely free of noble metals. Such
catalysts can in principle be produced by impregnation
of the support material with soluble noble metal
compounds, subsequent precipitation of insoluble noble

metal compounds on the support by addition of alkaline compounds and final reduction to the noble metals.

US-A-4,048,096 describes a process for producing a
5 palladium-, gold- and potassium-containing catalyst for
vinyl acetate production. The catalyst support is first
impregnated with a solution comprising a mixture of the
dissolved palladium and gold salts. It is essential to
that invention that the solution has the same volume as
10 the pores of the support material in the dry state.
During the impregnation step, the support particles are
kept in motion in a rotating vessel. Without prior
drying of the impregnated support, the noble metal
salts on the support particles are subsequently
15 converted into insoluble compounds by addition of
alkalis and are thus fixed to the support particles.
The palladium and gold compounds are reduced to the
corresponding metals by a final treatment with a
reducing agent. Application of an alkali metal compound
20 in a further impregnation step gives a catalyst which
has the desired shell structure and comprises palladium
and gold in a thickness of 0.5 mm on the surface of the
support material.

25 US-A-3,775,342 also describes the production of a
palladium-, gold- and potassium-containing catalyst for
vinyl acetate production. In this process, the support
material is treated in any order with two solutions of
which one comprises the dissolved palladium and gold
30 salts and the other an alkaline substance. After
treatment with the first solution, the support is dried
in an intermediate step before being brought into
contact with the second solution. The volume of both
solutions corresponds to the pore volume of the support
35 material.

Furthermore, US-A-5,332,710 discloses the production of
a catalyst for preparing vinyl acetate, in which the
insoluble noble metal salts are likewise precipitated

on the support particles by addition of alkalis. For this purpose, the support particles are immersed in the alkaline solution and are subjected to rotary motion from the commencement of the precipitation for at least
5 half an hour in a drum. This process is known as "rotation-immersion".

In the preparation of vinyl acetate, the catalysts produced as described in the abovementioned process
10 frequently lead to undesirably high formation of degradation products and by-products, e.g. carbon dioxide, thus adversely affecting activity and selectivity of the overall reaction.

15 In view of the fact that vinyl acetate is a volume product produced on a large industrial scale, it is an object of the present invention to provide a catalyst which has a further improved activity and selectivity in the preparation of vinyl acetate in the gas phase.

20

The invention provides a process for producing a catalyst for the preparation of vinyl acetate in the gas phase from ethylene, acetic acid and oxygen or oxygen-containing gases, which catalyst comprises
25 palladium and/or its compounds, gold and/or its compounds and also alkali metal compounds on a particulate, porous support and is produced by

- a) impregnating the support with soluble palladium and gold compounds,
- 30 b) converting the soluble palladium and gold compounds into insoluble palladium and gold compounds by addition of an alkaline solution to the support,
- c) reducing the insoluble palladium and gold
35 compounds on the support by means of a reducing agent in the liquid or gaseous phase,
- d) impregnating the support with at least one soluble alkali metal compound and

e) finally drying the support at a maximum of 150°C.

In this process, the catalyst is brought into contact with at least one peroxidic compound in step b).

5

The invention also provides a catalyst for preparing vinyl acetate in the gas phase from ethylene, acetic acid and oxygen or oxygen-containing gases, which comprises palladium and/or its compounds, gold and/or
10 its compounds and also alkali metal compounds on a particulate, porous support and is obtainable by the above-described process.

The invention further provides a process for preparing
15 vinyl acetate in the gas phase from ethylene, acetic acid and oxygen and/or oxygen-containing gases in the presence of a catalyst obtainable by the above-described process.

20 In the preparation of vinyl acetate, the catalysts of the invention surprisingly lead both to an improved activity and to a higher selectivity of the reaction.

The support particles of the catalyst of the invention
25 can have any geometric shape, for example spheres, pellets, cylinders, rings or stars with a regular or irregular configuration. The dimensions of the support particles, i.e. the diameter or the length and thickness are generally from 1 to 10 mm, in particular
30 from 3 to 9 mm. Preference is given to using spherical support particles having a diameter of from 4 to 8 mm.

Supports which can be used are the known inert support materials such as silica, aluminum oxide, alumino-
35 silicates, silicates, titanium oxide, zirconium oxide, titanates, silicon carbide and carbon. Other suitable support materials are the pyrogenic silicas obtained by flame hydrolysis of silicon tetrachloride or the pyrogenic $\text{SiO}_2\text{-M}_x\text{O}_y$ mixtures obtained by flame

hydrolysis of silicon tetrachloride and another metal chloride such as aluminum chloride (US-A-3,939,199 and EP-A-0 723 810). Preference is given to using silica (SiO_2), baddeleyite (ZrO_2) and $\text{SiO}_2\text{-Al}_2\text{O}_3$ mixtures as support material. In the case of the pyrogenic support materials, the pressed bodies described in DE-A-38 03 895 and DE-A-39 12 504 are particularly suitable.

To be suitable as support material, it is critical that the material retains its mechanical strength under the reaction conditions of the catalytic process for preparing vinyl acetate, in particular in the presence of acetic acid.

Particularly suitable supports are those of the above-mentioned type having a specific surface area of from 50 to $400 \text{ m}^2/\text{g}$ (measured by the BET method) and a mean pore radius of from 50 to $2000 \text{ \AA}$ (measured by means of mercury porosimetry).

In step a) of the process of the invention, the impregnation step, the support particles are impregnated with the soluble palladium and gold compounds. Suitable palladium and gold compounds are all salts and complexes which are soluble in the solvents described below, can be precipitated as hydroxide or oxide and in the finished catalyst, possibly after a washing step, leave no materials which impair the performance of the catalyst.

Examples of suitable palladium compounds are palladium(II) chloride, sodium and potassium chloropalladate(II), palladium(II) nitrate, nitrite, sulfate, oxalate, acetylacetonate or acetoacetate and hydrated palladium(II) oxide. It is also possible to use palladium salts of aliphatic monocarboxylic acids having from 2 to 5 carbon atoms, preferably palladium(II) acetate. Gold(III) chloride, gold(III) acetate, tetrachloroauric(III) acid and its alkali

metal salts can be used as soluble gold compounds. In general, these compounds are used in such amounts that the finished catalyst comprises from 2 to 14 g/l, preferably from 4 to 8 g/l, of palladium and from 1 to 5 8 g/l, preferably from 2 to 5 g/l, of gold.

Suitable solvents for the palladium and gold compounds and also for the alkali metal compounds to be applied in step d) are all compounds in which the salts chosen
10 are soluble and which are easy to remove again in an optional drying step after the impregnation. Particularly suitable solvents are water and unsubstituted carboxylic acids having from 2 to 10 carbon atoms, e.g. acetic acid, propionic acid, n- and
15 iso-butyric acid and n- and iso-valeric acids. Owing to its favorable physical properties and also for economic reasons, the preferred carboxylic acid is acetic acid. It is advantageous to use an additional solvent when the palladium and gold compounds are not sufficiently
20 soluble in the carboxylic acid used. Thus, for example, palladium(II) chloride dissolves significantly better in aqueous acetic acid than in glacial acetic acid. Suitable additional solvents are those which are inert and at the same time are miscible with the carboxylic
25 acid, e.g. water, ethers such as tetrahydrofuran or dioxane and hydrocarbons such as benzene.

In the impregnation of the support material, it is possible to use a plurality of salts of each of the
30 metals to be applied, but preference is given to using only one salt per metal.

The impregnation of the support material with the soluble palladium and gold compounds in step a) can be
35 carried out using a solution which simultaneously comprises all soluble palladium and gold compounds. Here, the support material can be impregnated once or a plurality of times with this solution. Since the amount of palladium and gold compounds used should be

identical in single and multiple impregnation, the total volume of the solution should be divided appropriately in the case of multiple impregnation. Preference is given to a single impregnation with the
5 total volume of the solution.

In an alternative embodiment, the impregnation of the support material can also be carried out using two separate solutions of which one contains the palladium
10 compounds and the other contains the gold compounds. In this case, the two solutions can be brought into contact with the support material either simultaneously or else in any order. In the latter case, the support has to be dried after impregnation with the first
15 solution.

For effective impregnation, the total volume of the noble metal salt solution or of the two noble metal salt solutions should be about 90-100%, preferably 95-
20 100% and in particular 98-99%, of the pore volume of the support material in the dry state. In practice, it is also possible to cover the support particles with an excess of the noble metal salt solution and subsequently to pour away or filter off the excess
25 solution. However, preference is given to adding only the above-described amount of solution corresponding approximately to the pore volume of the catalyst support.

30 It has been found to be advantageous to keep the support particles in motion during the impregnation to achieve intimate mixing. This can be done by means of a rotating or shaken flask or a mixing drum. The rotational speed or in general terms the intensity of
35 the motion should be sufficient to achieve complete wetting of the support particles with the impregnation solution but must not be so great that appreciable abrasion of the support material occurs.

The catalyst can subsequently be dried at temperatures of at most 150°C, preferably 80-150°C and in particular 100-150°C. This drying procedure can be carried out, for example, in a stream of hot air in a fan-forced drier or else in a drying oven in a stream of inert gas, in particular a stream of nitrogen or carbon dioxide. Drying is carried out at atmospheric pressure or under reduced pressure, preferably 0.01-0.08 MPa.

10 In step b), the fixing step, the soluble palladium and gold compounds present on the support particles are converted into insoluble compounds by means of an alkaline solution and are thus fixed to the support. It is assumed that the insoluble compounds are the hydroxides and/or oxides of the noble metals.

Suitable alkaline solutions are all solutions which are able to convert the soluble palladium and gold compounds into insoluble compounds. Examples of alkaline reagents which can be used are alkali metal hydroxides, alkali metal silicates and alkali metal carbonates. Preference is given to an aqueous solution of the alkali metal hydroxides, in particular of potassium or sodium hydroxide. Solutions containing boron compounds can also be used as alkaline solutions. Here, aqueous solutions of sodium tetraborate decahydrate (borax), potassium tetraborate or mixtures of alkali metal hydroxide and boric acid are particularly suitable. The alkaline solution can have buffer properties.

The amount of alkaline compound present in the aqueous solution is advantageously selected so that it is at least sufficient for the stoichiometric reaction with the soluble palladium and gold compounds applied. However, it is also possible to use an excess of the alkaline compound, usually 1-10 times the stoichiometrically required amount.

It is essential to the process of the invention that the catalyst is brought into contact with at least one peroxidic compound in step b).

5 This peroxidic compound can be, for example, a perborate, preferably sodium perborate, a percarbonate, preferably sodium percarbonate, a peroxodisulfate, preferably sodium peroxodisulfate, or hydrogen peroxide.

10

One possible embodiment comprises adding the peroxidic compound to the alkaline solution which already comprises one of the abovementioned alkaline substances, preferably an alkali metal hydroxide. In an
15 alternative embodiment, a second, separate solution comprising the peroxidic compound can be used in step b) is addition to the alkaline solution. In this case, the impregnated catalyst support, as described below, is first brought into contact with the alkaline
20 solution and subsequently treated with the aqueous solution of the peroxidic compound before the reduction is carried out in step c). Since some of the peroxidic compounds mentioned are themselves alkaline, e.g. the perborates and percarbonates, it is also possible, in a
25 third and preferred embodiment, for the alkaline solution to be used in step b) to comprise only the peroxidic compound which is simultaneously alkaline.

It has been found to be useful to heat the solution
30 which comprises the peroxidic compounds to a maximum of 90°C, preferably to 60-85°C, before addition to the impregnated catalyst support.

In all three embodiments, the peroxidic compound is
35 used in a 1-20-fold, preferably 5-10-fold, excess based on the concentration of the noble metal salt. It is found that contact of the impregnated catalyst support with at least one peroxidic compound in the fixing step b) leads to some reduction of the noble metals.

Two methods I and II which are suitable for carrying out the fixing step b) and can be employed in the production of the catalyst of the invention are described below.

5

In method I, the support material impregnated in step a) is placed for a sufficient time in an alkaline solution whose concentration is such that the desired, insoluble noble metal compounds are precipitated. In addition, the volume of the alkaline solution is selected so that it is sufficient to completely cover and immerse the impregnated support particles. Furthermore, the impregnated support particles immersed in the alkaline solution are subjected to rotary motion commencing with the precipitation of the insoluble palladium and gold compounds for at least half an hour, preferably one hour and at most up to 4 hours. This fixing method is known as "rotation-immersion" and is described in detail in US-A-5,332,710, which is hereby incorporated by reference.

15
20

In this variant I, the additional treatment of the catalyst support with the peroxidic compound can be carried out as described in the three abovementioned embodiments.

25

If the method II described below is employed for fixing the palladium and gold compounds to the support particles, the support which has been impregnated in step a) should be dried before the fixing step b).

30

In method II, the fixing step b) comprises at least two separate stages of treatment with the alkaline fixing solution. In the first fixing stage, the impregnated and then dried support is brought into contact with the alkaline fixing solution. The volume of this first fixing solution corresponds to the pore volume and thus the absorptive capacity of the support material in the dry state. The amount of alkaline compounds present

35

therein should be such that the molar ratio of alkali metal from the alkaline compound to anions from the soluble metal salt is in the range from 0.7:1 to 2:1. For absorption on the support particles, the alkaline
5 fixing solution is poured onto the support particles and they are then left to stand for up to 24 hours, preferably 2-8 hours.

In this method II, the second fixing stage can be
10 carried out in two variants A) and B). In both variants, the molar ratio of the alkali metal from the alkaline compound to the anion from the metal salt is from about 0.2:1 to 2:1 in the fixing solution.

In variant A) of method II, the undried support
15 particles are brought into contact with the second fixing solution whose volume should at least just cover the supports. For absorption on the support particles, the alkaline fixing solution is poured onto the support particles and they are then left to stand for up to 16
20 hours, but at least 2 hours and preferably at least 4 hours.

In variant B), the support material after contact with the first fixing solution is, in the second step,
25 treated by the rotation-immersion process of US-A-5,332,710. Here, the support material is immersed in the alkaline fixing solution of the second step and at the same time subjected to rotary motion. This rotation should continue for at least half an hour,
30 preferably one hour and at most up to 4 hours.

Regardless of whether variant A) or B) is employed, the treatment in the second fixing step can be equivalent to the treatment in the first stage in that a fixing
35 solution of the same concentration is used and the volume of the second fixing solution likewise corresponds to the pore volume and thus the absorptive capacity of the support material in the dry state. The total molar ration of alkali metal to anion from the

metal salt for both fixing stages together is preferably in the range from 1.1:1 to 3.3:1.

5 In method II, the additional treatment of the catalyst support with the peroxidic compound can in principle be carried out in either of the two fixing stages, but it is preferably carried out in the second fixing stage as described in the three abovementioned embodiments.

10 After the fixing step of method I or the last fixing step of method II, the supports can be washed with water, preferably with distilled water, to remove any interfering anions, e.g. chlorides, which originate from the impregnation step, have been set free by the
15 precipitation of the noble metals and are still present on the support material. This washing procedure also removes any excess of alkaline compound which may still be present.

20 The catalyst can then be dried at temperatures of at most 150°C, preferably 80-150°C and in particular 100-150°C. This drying procedure can be carried out, for example, in a stream of hot air in a fan-forced drier or else in a drying oven in a stream of inert
25 gas, in particular in a stream of nitrogen or carbon dioxide. Drying is carried out at atmospheric pressure or under reduced pressure, preferably 0.01-0.08 MPa.

Such a drying procedure is advantageous at this point
30 particularly when the reduction step c) described below is carried out in the gas phase. In contrast, prior drying is not necessary if the reduction is carried out in the liquid phase.

35 In step c), the support together with the insoluble palladium and gold compounds deposited thereon is treated with a reducing agent in order to convert the precipitated palladium and gold compounds into the metallic form. This reduction can be carried out in the

liquid phase at a temperature of 0-90°C, preferably 15-25°C. The reducing agent used here is, for example, hydrazine, formic acid or an alkali metal borohydride, preferably sodium borohydride. As an alternative, it is
5 also possible to carry out the reduction in the gas phase using hydrogen, ethylene, propylene, isobutylene, butylene or other olefins as reducing agent. In this case, it is advantageous to carry out the reaction at an increased temperature of 40-260°C, preferably
10 70-200°C. It is also advantageous to dilute the reducing agent with an inert gas. The inert gas used can be, for example, nitrogen, carbon dioxide or a noble gas. Such a reducing agent/inert gas mixture usually contains 0.01-50% by volume, preferably 0.5-20%
15 by volume, of reducing agent.

Regardless of whether the reduction is carried out in the liquid or gas phase, the reducing agent should be added in an excess, based on the catalyst to be
20 reduced, so as to ensure that all the insoluble noble metal compound is converted into the metallic form.

After the reduction, the support particles can be washed again once or a plurality of times, preferably
25 with distilled water, to remove interfering anions, e.g. chlorides, and residues of the alkaline solution used. The washing procedure can also serve to remove residues of the reducing agent from step c).

30 Subsequently, the catalyst is dried again under drying conditions which should be similar to those of a drying step after the fixing step b).

Finally, the addition of at least one alkali metal
35 compound is necessary. The catalyst is therefore impregnated with an aqueous solution of an alkali metal compound in step d). Alkali metal compounds which can be used are sodium, potassium, rubidium or cesium compounds; preference is given to potassium compounds.

Suitable anions of these alkali metal compounds are, in particular, carboxylates, especially acetates or propionates. Particular preference is given to using potassium acetate. However, it is also possible to use compounds which liberate alkali metal acetates under the reaction conditions, i.e. the alkali metal hydroxides, oxides or carbonates when acetic acid is used as solvent. This impregnation is carried out, in principle, in the same way as the impregnation of the support material in step a). The solvents which can be used are subject to the same conditions and definitions as in the case of the solutions in impregnation step a). The alkali metal compound is used in such an amount that the catalyst after the drying step described below contains 0.1-10% by weight of alkali metal, preferably 1-4% by weight of alkali metal, in particular potassium, based on the total mass of the catalyst.

Finally, the catalyst is, in step e), dried at temperatures of at most 150°C, preferably 80-150°C and in particular 100-150°C. This drying procedure can be carried out, for example, in a stream of hot air in a fan-forced drier or else in a drying oven in a stream of inert gas, in particular in a stream of nitrogen or carbon dioxide. Drying is carried out at atmospheric pressure or under reduced pressure, preferably 0.01-0.08 MPa.

The catalyst obtainable by steps a) to e) of the process of the invention and the treatment with the peroxidic compounds essential to the invention in step b) comprises, based on the total mass of the catalyst, 0.2-2.5% by weight, preferably 0.6-1.5% by weight, of palladium, 0.2-2.5% by weight, preferably 0.3-1.0% by weight, of gold and 0.1-10% by weight of alkali metal, preferably 1.0-4.0% by weight of alkali metal, in particular potassium.

Vinyl acetate is prepared by passing acetic acid, ethylene and oxygen or oxygen-containing gases at temperatures of from 100 to 220°C, preferably from 120 to 200°C, and pressures of from 0.1 to 2.5 MPa, preferably from 0.1 to 2 MPa, over the catalyst of the invention. Unreacted components can be circulated. In some cases, dilution with inert gases such as nitrogen or carbon dioxide is also advantageous. Carbon dioxide is particularly suitable for dilution in a circulation mode of operation since it is in any case formed during the reaction.

It has been found to be useful to carry out the preparation of the vinyl acetate in a stirred reactor, a Berty reactor, in circulation mode in the gas phase at a constant oxygen conversion of about 45%. The reactor is first charged with the catalyst. Subsequently, a measured amount of acetic acid and also ethylene and oxygen diluted with nitrogen is introduced and the temperature is increased to the desired value by means of a heating mantle. The reaction is usually stopped after about 18 hours, as long it has been possible to set a temperature at which the oxygen conversion is constant at 45%. The composition of the product mixture is determined by means of gas chromatography.

The higher selectivity and activity achievable using the catalysts of the invention can in practice be utilized in two ways:

Firstly, to produce a larger amount of vinyl acetate per unit volume and unit time in existing plants while retaining all other reaction conditions. Owing to the higher selectivity, the product mixture taken from the reactor has a higher proportion of vinyl acetate and contains less by-products, in particular carbon dioxide. In this way, the work-up, i.e. the isolation of the vinyl acetate, is made easier because, for example, the amount of carbon dioxide to be separated

off is lower and accordingly the loss of entrained ethylene associated with the removal of carbon dioxide drops. This leads to a saving in starting material. The principles of the work-up of the product mixture after the preparation of vinyl acetate are described, for example, in EP-A-0 423 658.

The second possible way of utilizing the improved properties of the catalysts of the invention is to lower the reaction temperature in the preparation of vinyl acetate while maintaining the same space-time yield. A lower reaction temperature in turn has a positive effect on the total operational life of the catalyst.

15

Examples:

The catalysts in Examples 1-5 are produced using silica based on bentonite as support material. This is the KA-160 support from Süd-Chemie; spheres having a diameter of 7 mm are employed in Examples 1-4 and 6-8 and spheres having a diameter of 5 mm are employed in Example 5.

25 Example 1

5.37 g (0.0164 mol) of K_2PdCl_4 and 3.36 g (0.0089 mol) of $KAuCl_4$ are together dissolved in 80 ml of demineralized water. All of this solution is, with gentle motion, applied to 131 g of the support material. The support which has been pretreated in this way is placed in a solution of 18.31 g (0.12 mol) of sodium perborate tetrahydrate ($NaBO_3 \cdot 4H_2O$) in 300 ml of distilled water and the total reaction mixture is rotated on a rotary evaporator at a speed of 5 revolutions per minute for 3.5 hours at 85°C to complete the reaction. The reaction mixture is allowed to stand for about 12 hours and then washed free of chloride with demineralized water. The freedom from

chloride is checked by means of the silver nitrate test for chloride ions in aqueous solution. The material is then dried for 2 hours at 100°C. It can be shown by photoelectron spectroscopy that after this step the noble metal shell formed comprises metallic gold and palladium in the oxidation state +2. Subsequently, the noble metals are reduced completely using diluted ethylene (5% in nitrogen). For this purpose, the gas mixture is passed over the catalyst for 5 hours at 150°C. 10 g of potassium acetate are then dissolved in 75 ml of distilled water and added a little at a time to the catalyst and the latter is dried once more for 2 hours at 100°C.

Example 2

5.37 g (0.0164 mol) of K_2PdCl_4 and 1.92 g (0.0051 mol) of $KAuCl_4$ are together dissolved in 80 ml of demineralized water. All of this solution is, with gentle motion, applied to 131 g of the support material. The support which has been pretreated in this way is placed in a solution of 14.92 g (0.097 mol) of sodium perborate tetrahydrate ($NaBO_3 \cdot 4H_2O$) in 300 ml of distilled water and the total reaction mixture is rotated on a rotary evaporator at a speed of 5 revolutions per minute for 3.5 hours at 85°C to complete the reaction. The reaction mixture is allowed to stand for about 12 hours and is then washed free of chloride with demineralized water.

The further procedure is as described in Example 1.

Example 3

12.88 g (0.0349 mol) of K_2PdCl_4 and 4.6 g (0.0122 mol) of $KAuCl_4$ are together dissolved in 192 ml of demineralized water. All of this solution is, with gentle motion, applied to 314.4 g of the support material. The support which has been pretreated in this way is placed in a solution of 35.8 g (0.23 mol) of

sodium perborate tetrahydrate ($\text{NaBO}_3 \cdot 4\text{H}_2\text{O}$) in 720 ml of distilled water and the total reaction mixture is rotated on a rotary evaporator at a speed of 5 revolutions per minute for 3.5 hours at 85°C to complete the reaction. The reaction mixture is allowed to stand for about 12 hours and is then washed free of chloride with distilled water.

The further procedure is as described in Example 1.

10 Example 4

12.88 g (0.0349 mol) of K_2PdCl_4 and 8.06 g (0.0214 mol) of KAuCl_4 are together dissolved in 192 ml of demineralized water. All of this solution is, with gentle motion, applied to 314.4 g of the support material. The support which has been pretreated in this way is placed in a solution of 35.8 g (0.23 mol) of sodium perborate tetrahydrate ($\text{NaBO}_3 \cdot 4\text{H}_2\text{O}$) in 720 ml of distilled water and the total reaction mixture is rotated on a rotary evaporator at a speed of 5 revolutions per minute for 3.5 hours at 85°C to complete the reaction. The reaction mixture is allowed to stand for about 12 hours and is then washed free of chloride with distilled water.

25 The further procedure is as described in Example 1.

Example 5

5.37 g (0.0164 mol) of K_2PdCl_4 and 3.36 g (0.0089 mol) of KAuCl_4 are together dissolved in 90 ml of demineralized water. All of this solution is, with gentle motion, applied to 147.5 g of the support material. The support which has been pretreated in this way is placed in a solution of 18.31 g (0.12 mol) of sodium perborate tetrahydrate ($\text{NaBO}_3 \cdot 4\text{H}_2\text{O}$) in 300 ml of distilled water and the total reaction mixture is rotated on a rotary evaporator at a speed of 5 revolutions per minute for 3.5 hours at 85°C to complete the reaction. The reaction mixture is allowed

5 to stand for about 12 hours and is then washed free of chloride with distilled water.

The further procedure is as described in Example 1.

Example 6

10

7.67 g (0.0235 mol) of K_2PdCl_4 and 3.84 g (0.0102 mol) of $KAuCl_4$ are together dissolved in 90 ml of demineralized water. All of this solution is, with gentle motion, applied to 133.75 g of the support material. The support which has been pretreated in this way is placed in a solution of 23.85 g (0.16 mol) of sodium perborate tetrahydrate ($NaBO_3 \cdot 4H_2O$) in 300 ml of distilled water and the total reaction mixture is rotated on a rotary evaporator at a speed of 5 revolutions per minute for 3.5 hours at 85°C to complete the reaction. The reaction mixture is allowed to stand for about 12 hours and is then washed free of chloride with distilled water.

15

20

The further procedure is as described in Example 1.

25

Example 7

2.69 g (0.0082 mol) of K_2PdCl_4 and 0.96 g (0.0025 mol) of $KAuCl_4$ are together dissolved in 40 ml of demineralized water. All of this solution is, with gentle motion, applied to 65.5 g of the support material. The support which has been pretreated in this way is placed in a solution of 1.89 g (0.034 mol) of potassium hydroxide in 150 ml of distilled water and is rotated in this solution on a rotary evaporator at a speed of 5 revolutions per minute for 2.5 hours at room

30

35

temperature. Then the reaction mixture is allowed to
5 stand for about 12 hours. Then the support is separated
from the KOH-solution. The wet support material is
subsequently brought into contact with 150 ml of an
aqueous solution which contains 18.84 g (0.12 mol) of
sodium percarbonate and which has been heated at first
10 to 60°C. Then, the reaction mixture is heated
immediately on a water bath to 85°C to complete the
reaction.

Subsequently, the total reaction mixture is rotated on
15 a rotary evaporator at a speed of 5 revolutions per
minute for 3.5 hours at 85°C to complete the reaction.

The reaction mixture is allowed to stand for about 12 hours and is then washed free of chloride with demineralized water.

The further procedure is as described in Example 1.

5

Example 8

2.69 g (0.0082 mol) of K_2PdCl_4 and 0.96 g (0.0025 mol) of $KAuCl_4$ are together dissolved in 40 ml of demineralized water. All of this solution is, with gentle motion, applied to 65.5 g of the support material. The support which has been pretreated in this way is placed in a solution of 1.15 g (0.029 mol) of sodium hydroxide and 9.94 g of a 30% strength hydrogen peroxide solution (corresponds to 0.088 mol (2.98 g) of hydrogen peroxide) in 150 ml of distilled water and the total reaction mixture is rotated on a rotary evaporator at a speed of 5 revolutions per minute for 3.5 hours at 85°C to complete the reaction. The reaction mixture is allowed to stand for about 12 hours and is then washed free of chloride with demineralized water.

The further procedure is as described in Example 1.

25 Comparative example

5.37 g (0.0164 mol) of K_2PdCl_4 and 1.92 g (0.0051 mol) of $KAuCl_4$ are together dissolved in 87 ml of demineralized water. All of this solution is, with gentle motion, applied to 133.75 g of the support material. The support which has been pretreated in this way is placed in a solution of 19.22 g (0.05 mol) of sodium tetraborate decahydrate ($Na_2B_4O_7 \cdot 10H_2O$) in 300 ml of distilled water and the total reaction mixture is rotated on a rotary evaporator at a speed of 5 revolutions per minute for 3.5 hours at 85°C to complete the reaction. The reaction mixture is allowed to stand for about 12 hours and is then washed free of chloride with demineralized water.

The further procedure is as described in Example 1.

To examine the performance of the catalysts described in the preparation of vinyl acetate, tests are carried out in a Berty reactor. The results are summarized in the table:

Example	Activity of the catalyst	CO ₂ selectivity in % based on the amount of ethylene reacted
1	3.2	9.6
2	2.5	10.8
3	2.4	11.4
4	3.0	10.7
5	2.8	10.0
6	3.8	10.7
7	1.6	8.6
8	2.3	10.0
Comparative	2.1	12.4

To determine the activity of the catalyst, the temperature in the middle of the wall of the Berty reactor used for testing is recorded at a constant oxygen conversion of about 45%. Low wall temperatures at a constant oxygen conversion mean a relatively high catalyst activity.

Claims:

1. A process for producing a catalyst for the preparation of vinyl acetate in the gas phase from ethylene, acetic acid and oxygen or oxygen-containing gases, which catalyst comprises palladium and/or its compounds, gold and/or its compounds and also alkali metal compounds on a particulate, porous support and is produced by
- impregnating the support with soluble palladium and gold compounds,
 - converting the soluble palladium and gold compounds into insoluble palladium and gold compounds by addition of an alkaline solution to the support,
 - reducing the insoluble palladium and gold compounds on the support by means of a reducing agent in the liquid or gaseous phase,
 - impregnating the support with at least one soluble alkali metal compound and
 - finally drying the support at a maximum of 150°C,
- wherein the catalyst is brought into contact with at least one peroxidic compound in step b).
2. The process as claimed in claim 1, wherein the peroxidic compound is a perborate, preferably sodium perborate, a percarbonate, preferably sodium percarbonate, a peroxodisulfate, preferably sodium peroxodisulfate, or hydrogen peroxide.
3. The process as claimed in claim 1 or 2, wherein the peroxidic compound(s) is/are added to the alkaline solution of step b) which already comprises an alkaline substance, preferably an alkali metal hydroxide.



4. The process as claimed in claim 1 or 2, wherein a second, separate solution comprising the peroxidic compound(s) is used in step b) in addition to the alkaline solution.
- 5
5. The process as claimed in claim 4, wherein the impregnated catalyst support is first brought into contact with the alkaline solution and subsequently treated with the aqueous solution of the peroxidic compound(s).
- 10
6. The process as claimed in claim 1 or 2, wherein, if a perborate or percarbonate is used as peroxidic compound, the alkaline solution used in step b) comprises only the peroxidic compound(s).
- 15
7. The process as claimed in one or more of claims 1-6, wherein the solution which comprises the peroxidic compound(s) is heated to a maximum of 90°C, preferably to 60-85°C, before addition to the impregnated catalyst support.
- 20
8. The process as claimed in one or more of claims 1-7, wherein the peroxidic compound is used in a 1-20-fold, preferably 5-10-fold, excess, based on the concentration of the noble metal salts.
- 25
9. The process as claimed in one or more of claims 1-8, wherein, in step c), the insoluble palladium and gold compounds on the support are treated either in the liquid phase at a temperature of 0-90°C, preferably 15-25°C, with hydrazine, formic acid or an alkali metal borohydride, preferably sodium borohydride, as reducing agent; or else in the gas phase at a temperature of 40-260°C, preferably 70-200°C, using hydrogen, ethylene, propylene, isobutylene or butylene as reducing agent.
- 30
- 35



10. The process as claimed in one or more of claims 1-9, wherein the support is impregnated in step d) with an aqueous solution of an alkali metal compound, preferably an alkali metal carboxylate, in particular potassium acetate.
11. A catalyst for preparing vinyl acetate in the gas phase from ethylene, acetic acid and oxygen or oxygen-containing gases, which comprises palladium and/or its compounds, gold and/or its compounds and also alkali metal compounds on a particulate, porous support and is obtainable by the process as claimed in any of claims 1-10.
12. A catalyst as claimed in claim 11 comprising, based on the total mass of the catalyst, 0.2-2.5% by weight, preferably 0.6-1.5% by weight, of palladium, 0.2-2.5% by weight, preferably 0.3-1.0% by weight, of gold, 0.1-10% by weight of alkali metal, preferably 1.0-4.0% by weight of alkali metal, in particular potassium.
13. A process for preparing vinyl acetate in the gas phase from ethylene, acetic acid and oxygen and/or oxygen-containing gases in the presence of the catalyst as claimed in claim 8 or 9.
14. The process as claimed in claim 13 carried out at temperatures of from 100 to 220°C, preferably from 120 to 200°C, and pressures of from 0.1 to 2.5 MPa, preferably from 0.1 to 2 MPa.

