

CLEANING COMPOSITIONS

Background of the Invention

1. Field of the Invention

This invention relates to cleaning compositions which will replace cleaning agents containing an organic solvent including flon and the like.

2. Description of the Related Art

In manufacturing various parts such as metal parts, plated and coated parts, and electronic and semiconductor parts, flon containing solvents such as flon 113, and organic solvents such as trichloroethane, trichlorethylene, tetrachloroethylene, and carbon tetrachloride are widely used as cleaning agents for eliminating oil stains and the like.

The above organic solvent containing cleaning agents are also used as dewatering cleaning agents after having washed various parts with water in order to avoid the following problems that are associated with direct drying of water present on an object to be cleaned:

- (1) Heating (100°C or more) which entails energy loss;
- (2) Reducing in productivity due to time taken in drying;
- (3) Likely deformation of the object to be cleaned due to heating (thermal expansion that exceeds the tolerance); and
- (4) Increase in space for installing a cleaning system including a cooler and a heat shielding unit.

The term "dewatering cleaning agent" is used herein to

This Sheet Has Been Replaced



1

REPLACED SHEETS SG

☒ Description	: paged 1	to paged 38
☒ Claim(s)	: paged 39	to paged 42
☒ Drawing(s)	: paged 111	to paged -
☒ Abstract	: paged 43	to paged 44

denote a cleaning agent into which an object to be cleaned, which has been washed with water, is immersed or with which the object is rinsed by shower thereby to have water present on the object, substituted by itself and then vaporized by air at room temperature or heated to 60°C or less so that the object can be dried.

However, ever since it has been found that the destruction of the ozone layer by discharge of flon affects seriously the human body and the ecological system, the use of flons such as flon 12 and flon 113 whose ozone destruction coefficients are high is on the gradual decline on a global scale for an eventual total ban.

Stricter regulations are imposed also on chlorine containing organic solvents such as trichloroethylene and tetrachloroethylene which are presumed to induce soil and underwater contaminations and the like.

Flons whose ozone destruction coefficients are lower than the currently used flon containing solvents are being developed, some of which are under fabrication on a commercial basis. However, these new developments are not so welcome because they still are destroyers of the ozone layer.

What gradually attracts attention as a replacement for the above organic solvents is a surfactant-based water system cleaning agent which is free from environmental destruction and contamination. However, cleaning agents containing only surfactants are not satisfactory in penetrability, thereby not cleaning, e.g., stains penetrated into narrow portions and medium to high viscous, persistently sticky oil stains.

denote a cleaning agent into which an object to be cleaned, which has been washed with water, is immersed or with which the object is rinsed by shower thereby to have water present on the object, substituted by itself and then vaporized by air at room temperature or heated to 60°C or less so that the object can be dried.

However, ever since it has been found that the destruction of the ozone layer by discharge of flon affects seriously the human body and the ecological system, the use of flons such as flon 12 and flon 113 whose ozone destruction coefficients are high is on the gradual decline on a global scale for an eventual total ban.

Stricter regulations are imposed also on chlorine containing organic solvents such as trichloroethylene and tetrachloroethylene which are presumed to induce soil and underwater contaminations and the like.

Flons whose ozone destruction coefficients are lower than the currently used flon containing solvents are being developed, some of which are under fabrication on a commercial basis. However, these new developments are not so welcome because they still are destroyers of the ozone layer.

What gradually attracts attention as a replacement for the above organic solvents is a surfactant-based water system cleaning agent which is free from environmental destruction and contamination. However, cleaning agents containing only surfactants are not satisfactory in penetrability, thereby not cleaning, e.g., stains penetrated into narrow portions and medium to high viscous, persistently sticky oil stains.



isopropyl alcohol has a flash point of 11.7°C , which is lower than room temperature, and this involves some danger of fires under ordinary handling conditions. In addition, isopropyl alcohol is highly compatible with water, so that the initial dewatering property is ensured, but its repetitive use causes dissolved water to be present again. As a result its dewatering property will be impaired on a long-term basis. To refine isopropyl alcohol for reuse by removing water from the water containing isopropyl alcohol, a tremendous equipment investment is required. That isopropyl alcohol is toxic to the human body is another factor that tends to keep it from using.

The use of hydrocarbon and higher alcohols which have higher flash points than room temperature allows a comparatively easy removal of water, but their low volatility prevents drying themselves at low temperatures, e.g., 60°C or less, thereby making them unsuitable for applications to dewatering cleaning agents.

Therefore, an object of the invention is to provide water system cleaning compositions which have cleaning capability equivalent to that of organic solvent containing cleaning agents including such as flon and which are stable as water system cleaning agents and free from environmental destruction and contamination.

Another object of the invention is to provide dewatering compositions which have the substituting and drying properties equivalent to those of organic solvent containing dewatering cleaning agents, which have few risks of fires and which are free from environmental destruction.




isopropyl alcohol has a flash point of 11.7°C , which is lower than room temperature, and this involves some danger of fires under ordinary handling conditions. In addition, isopropyl alcohol is highly compatible with water, so that the initial dewatering property is ensured, but its repetitive use causes dissolved water to be present again. As a result its dewatering property will be impaired on a long-term basis. To refine isopropyl alcohol for reuse by removing water from the water containing isopropyl alcohol, a tremendous equipment investment is required. That isopropyl alcohol is toxic to the human body is another factor that tends to keep it from being used.

The use of hydrocarbon and higher alcohols which have higher flash points than room temperature allows a comparatively easy removal of water, but their low volatility prevents drying themselves at low temperatures, e.g., 60°C or less, thereby making them unsuitable for applications to dewatering cleaning agents.

Therefore, an object of the invention is to provide water system cleaning compositions which have cleaning capability equivalent to that of organic solvent containing cleaning agents including such as flon and which are stable as water system cleaning agents and free from environmental destruction and contamination.

Another object of the invention is to provide dewatering compositions which have the substituting and drying properties equivalent to those of organic solvent containing dewatering cleaning agents, which have few risks of fires and which are free from environmental destruction.



isopropyl alcohol has a flash point of 11.7°C , which is lower than room temperature, and this involves some danger of fires under ordinary handling conditions. In addition, isopropyl alcohol is highly compatible with water, so that the initial dewatering property is ensured, but its repetitive use causes dissolved water to be present again. As a result its dewatering property will be impaired on a long-term basis. To refine isopropyl alcohol for reuse by removing water from the water containing isopropyl alcohol, a tremendous equipment investment is required. That isopropyl alcohol is toxic to the human body is another factor that tends to keep it from using.

The use of hydrocarbon and higher alcohols which have higher flash points than room temperature allows a comparatively easy removal of water, but their low volatility prevents drying themselves at low temperatures, e.g., 60°C or less, thereby making them unsuitable for applications to dewatering cleaning agents.


Therefore, an object of the invention is to provide water system cleaning compositions which have cleaning capability equivalent to that of organic solvent containing cleaning agents including such as flon and which are stable as water system cleaning agents and free from environmental destruction and contamination.

Another object of the invention is to provide dewatering compositions which have the substituting and drying properties equivalent to those of organic solvent containing dewatering cleaning agents, which have few risks of fires and which are free from environmental destruction.




11. *Chrysomelidae* (10 spp.)

the group consisting of straight chain polydiorganosiloxane represented by a general formula:



(wherein R¹ is an organic group of single valence substituted by the same or different group or unsubstituted, and l is an integer from 0 to 5), and cyclic polydiorganosiloxane represented by a general formula:



(wherein R¹ is an organic group of single valence substituted by the same of different group of unsubstituted, and m is an integer from 3 to 7).

Each of such low molecular weight polyorganosiloxanes exhibits powerful penetrability to stains and satisfactory substituting property with water alone, making itself a feature component of the invention. Reference character R¹ in formulas (I) and (II) denotes a substituted or unsubstituted organic group of single valence including: a single-valence unsubstituted hydrocarbon group such as an alkyl group such as a methyl group, an ethyl group, a propyl group, and a butyl group and a phenyl group; and a single-valence substituted hydrocarbon group such



as a trifluoromethyl group. As the R¹ which is placed at an end of formula (I), an amino group, an amide group, an acrylic acid ester group, and a mercaptan group are typical organic groups; however, the methyl group is most preferable from the viewpoint of stability, and maintainability of volatility, and the like.

The cleaning compositions of the invention may roughly be classified into two groups: a water system cleaning agent and a dewatering cleaning agent.

For use as a water system cleaning agent, suitable low molecular weight polyorganosiloxanes include: octamethylcyclotetrasiloxane, decamethylcyclopentasiloxane and mixtures thereof, each having a cyclic structure; and octamethyltrisiloxane and decamethyltetrasiloxane, each having a straight chain structure, from the viewpoint of penetrability and cleaning capability. In regions where the water system cleaning composition has a strong alkaline property from the viewpoint of stability of polysiloxane, the low molecular weight polyorganosiloxane having a straight chain structure which is represented by formula (I) is preferable.

For use as a dewatering cleaning agent, low molecular weight polyorganosiloxanes having a cyclic structure are preferable from the viewpoint of substituting property with water and penetrability and the like, octamethylcyclotetrasiloxane, decamethylcyclopentasiloxane, and mixtures thereof are more preferable.

A case in which the cleaning compositions of the invention are used as water system cleaning agents will now be described.

Although the low molecular weight polyorganosiloxanes

represented by formulas (I) and (II) exhibit powerful penetrability to stains, each composition is not compatible with water singly nor is it soluble and stably dispersive in water so that it is likely to have phase separation in water. That is, it is proposed to use them in combination with polyoxyalkylene group containing polyorganosiloxane having in a single molecule at least one siloxy unit represented by a general formula:



(wherein R² is an alkyl or phenyl group and A is a polyoxyalkylene group). As a result of such use in combination, the low molecular weight polyorganosiloxanes, providing stable dispersion in water, exhibit strong penetrability to stains. In addition, the use of a surfactant in combination with the compositions may improve their cleaning property.

Thus, preferable compositions for a water system cleaning agent of the invention contain the low molecular weight polyorganosiloxane represented by formula (I) or (II); the polyoxyalkylene group containing polyorganosiloxane having at least one siloxy unit represented by formula (III) in a single molecular; a surfactant; and water.


The polyoxyalkylene group containing polyorganosiloxane exhibits affinity for water owing to its polyoxyalkylene group bonded with the silicon atom, thus not only being a component for a stable water system dispersed solution or aqueous solution but also acting as an agent for eliminating stains by penetrating into the interface between the stains and a substrate which is



made of, e.g., a metal and which has the stains deposited thereon, and as an antifoaming agent as well.

Such a polyoxyalkylene group containing polyorganosiloxane can be prepared by hydrosilyl group containing polyorganosiloxane and a polyoxyalkylene compound having an unsaturated group at the end to interact with each other for addition under the presence of a platinum containing catalyzer.

An example of the polyoxyalkylene group denoted by reference character A in formula (III) is, e.g., a single-valence group represented by the formula:



(wherein R^3 is a two-valence group selected from the group consisting of an alkylene group having from 1 to 8 carbon atoms, a β -hydroxypropyleneoxyalkylene group and a polymethylene oxyalkylene group, both having from 4 to 11 carbon atoms; R^4 is an alkylene group having from 2 to 4 carbon atoms; R^5 is an end group selected from a hydrogen atom and a single-valence organic group; and n is a positive integer).

Siloxane that forms a main component of the polyoxyalkylene group containing polyorganosiloxane is not particularly limited. The organic group that is to be bonded with the silicon atom of the siloxane is basically a methyl group, but may also contain a single-valence hydrocarbon group such as an ethyl-group, a propyl group, a butyl group, a phenyl group, or a single-valence substituted hydrocarbon group such as a trifluoromethyl group as long as the advantages of the invention can remain harmless therefrom.

Also, the molecular weight of the siloxane is not




particularly limited nor is that of a single polyoxyalkylene group. Although they are large values, the addition of a surfactant thereto and the like allows the composition to be made sufficiently water soluble or stably water dispersive. However, it is practically preferable to limit the molecular weight of the single polyoxyalkylene group in the order of 100 to 5000. For a polyoxyalkylene chain, it is preferable to adjust its oxyethylene component to 40 mol % or more in the total polyoxyalkylene.

While the amount of the polyoxyalkylene group is not particularly limited, it is more preferable to limit it within 5 mol % or more of the total organic groups bonded with silicon atoms of the polyorganosiloxane from the standpoint of system stability.

Exemplary polyoxyalkylene group containing polyorganosiloxanes include:

a chain polysiloxane represented by the formula:




(wherein p, q, r, and s are positive integers); and

a cyclic polysiloxane represented by the formula:

This Sheet Has Been Replaced





(wherein t, u, and v are positive integers).

The surfactant serves as a component for dissolving, emulsifying, and stabilizing the stains removed by the low molecular weight polyorganosiloxanes or polyoxyalkylene group containing polyorganosiloxanes.

Such surfactants can be classified by the activation chemical structure into the following types: cationic, anionic, nonionic, amphoteric, and combined types. The invention may be applied to all the above types of surfactants. However, to obtain the advantage from their combination with the polyoxyalkylene group containing polyorganosiloxane, it is preferable to use anionic, nonionic, or amphoteric surfactants. Particularly, the use of the polyoxyalkylene group containing polyorganosiloxane in combination with either anionic/nonionic surfactants or amphoteric/nonionic surfactants provides a remarkable synergetic effect in improving the cleaning property and penetrability of the low molecular weight polyorganosiloxanes or the polyoxyalkylene group containing polyorganosiloxanes.

Exemplary suitable surfactants to be applied to the invention include: anionic surfactants such as polyoxyalkylene alkylether sulfonates and phosphoric esters; nonionic surfactants such as polyalcohol fatty acid esters, polyoxyalkylene fatty acid esters, and polyoxyalkylene alkylethers; amphoteric surfactants



such as imidazolin derivatives; and cationic surfactants such as alkylamine salts, alkyl quaternary ammonium salts. In addition thereto, terpene containing compounds which are rarely present in the form of a single substance and extracted from natural substances as well as higher fatty acid esters may also be applied. It is also possible to use synthetic compounds in which part of the chemical structure of each compound is substituted by a fluorine or silicon atom.

While the composition ratio of the above-mentioned quaternary water system cleaning agent is not particularly limited, it is preferable to blend 10 to 1000 parts by weight of a surfactant to 100 parts by weight of the polyoxyalkylene group containing polyorganosiloxane, and 1000 parts by weight or less of the low molecular weight polyorganosiloxane to 100 parts by weight of a total combination of the above surfactant(s) and the polyoxyalkylene containing polyorganosiloxane. Too small an amount of the surfactant reduces the cleaning capability, while too large an amount impairs the penetrability. Too large an amount of the low molecular weight polyorganosiloxane not only makes the system difficult to disperse but also reduces stability as a water system composition. A preferable fraction of the surfactant is 30 to 700 parts by weight, or, more preferably, 50 to 300 parts by weight, to 100 parts by weight of the polyoxyalkylene group containing polyorganosiloxane. A more preferable fraction of the low molecular weight polyorganosiloxane is between 10 and 1000 part by weight. While the fraction of water in the quaternary water system cleaning agent is not particularly limited either, it is preferable to



have water 40 wt.% or more or, more preferably, 70 to 99.5 wt.% to the total composition from a stability viewpoint.

By the way, the polyoxyalkylene group containing polyorganosiloxane having in a single molecule at least one siloxy unit represented by formula (III) penetrates, as described above, into the interface between the stains and the substrate made of, e.g., a metal to which the stains adhere to "peel off" the stains. Thus, even a tertiary composition consisting of the polyoxyalkylene group containing polyorganosiloxane, a surfactant, and water may serve as a viable water system cleaning agent. In this case, the fractions of the quaternary water system cleaning agent will apply to the tertiary composition.

The fractions of the tertiary or quaternary water system cleaning agents may be so designed that the value to be obtained by a canvas method at room temperature for evaluating penetrability will be 15 or less, 10 or less, or 5 or less. For the evaluation, the canvas method specified as a fiber/textile test method by Japanese Industrial Standards (JIS) is adopted. Since the cleaning property of these water system cleaning agents depends on the pH value of the solution itself, it is desirable to adjust the pH value to the alkali region. The pH value is more preferably be between 8 to 14.

The tertiary or quaternary cleaning agents can be prepared easily by blending and stirring the above-mentioned polyoxyalkylene group containing polyorganosiloxane, a surfactant, water, or further the low molecular weight polyorganosiloxane represented by formula (I) or (II), where necessary. The use of a known dispersing device will help obtain

a water system cleaning agent with ease.

The water system cleaning agents such as described above may have additives to be applied to ordinary water-soluble cleaning agents such as pH modifiers, adsorbents, solid particles, synthetic builders, rust preventives, and antistatic agents mixed as cleaning assistants or post-cleaning added-value improving agents and the like, depending on the property, amount, adhering state, cleaning condition, and the like of a stain. Such an addition may play an important part depending on their application.

The water system cleaning agents of the invention may be applied to metals, ceramics, plastics, and the like. More specifically, they may be applied to metallic parts, surface treated parts, electronic and semiconductor parts, electric and precision machinery parts, optical parts, glass and ceramic parts, and the like. An exemplary general-purpose cleaning process usually involves cleaning of any of the above-described parts by such a process as ultrasonic process, mechanical stirring and spraying, and thereafter, washing by water (preferably by pure water or ion-exchanged water), and is dewatered by drying the part with heated air or a like process. The cleaning composition in which the stain separated from the part is present is treated by, e.g., separating the stain through a filter or the like and thereafter by being subjected to a general waste water treatment process, thereby allowing the composition to be unhazardous and pollution-free easily.

According to the water system cleaning agent of the invention, the powerful penetrating property of the low molecular



weight polyorganosiloxane represented by formula (I) or (II) for the interface between the stains and the substrate as well as the cleaning capability of the surfactant(s) to the stains provides a cleaning performance equivalent to that of the conventionally used flon containing cleaning agents. The use of the polyoxyalkylene group containing polyorganosiloxane in combination with the water system cleaning agents of the invention allows satisfactory dispersing property in water. In addition, when applied as a tertiary composition consisting of the polyoxyalkylene group containing polyorganosiloxane, the surfactant, and water, the cleaning agent of the invention exhibits excellent cleaning property by the penetrating capability of the polyoxyalkylene group containing polyorganosiloxane with respect to the stain. Being a water system agent, it will bring no risk of environmental destruction and pollution. Thus, it can be said from the above that the water system cleaning agent of the invention can be an attractive replacement for cleaning agents based on organic solvents containing flon and other substances which have considered hazardous.

A case in which a cleaning composition of the invention is used as a dewatering cleaning agent will now be described.

Here, the term "dewatering agent" is only so named after "water," which is a typical liquid capable of being substituted by the low molecular weight polyorganosiloxanes, and the cleaning compositions of the invention may also be used as "liquid removing" agents in substituting and cleaning liquids other than water. The applicable liquids may be those which are insoluble



or difficult to be dissolved in the low molecular weight polyorganosiloxanes and whose surface tensions are larger than those of the low molecular weight polyorganosiloxanes. The "water" to be cleaned may include liquids using water as a dispersion medium such as mixtures of water and alcohols and liquids in which various substances are dissolved.

The low molecular weight polyorganosiloxane represented by formula (I) or (II) can be, as described previously, substituted by water alone, thus allowing itself to be easily vaporized and dried by hot air below 60°C.

Such a dewatering cleaning agent may consist substantially of the low molecular weight polyorganosiloxane and with it a satisfactory effect can be obtained. However, its cleaning and dewatering properties and the like will be further improved by forming it into a composition having the low molecular weight polyorganosiloxane mixed with a surfactant and/or a hydrophilic solvent.

The above-mentioned surfactants contribute to improving particularly the cleaning and dewatering property, and suitable surfactants to be applied to the invention include: anionic surfactants such as polyoxyalkylene alkylether sulfonates and phosphoric esters; nonionic surfactants such as polyalcohol fatty acid esters, polyoxyalkylene fatty acid esters, and polyoxyalkylene alkylethers; amphoteric surfactants such as imidazolin derivatives; and cationic surfactants such as alkylamine salts, alkyl quaternary ammonium salts. In addition thereto, terpene containing compounds which are rarely present in the form of a single substance and extracted from natural



substances as well as higher fatty acid esters may also be applied. It is also possible to use synthetic compounds in which part of the chemical structure of each compound is substituted by a fluorine or silicon atom. However, it is more preferable to use nonionic surfactants if the effect as a dewatering cleaning agent used in combination with the low molecular weight polyorganosiloxane is to be further improved.

While the composition ratio of the surfactant is not particularly limited, it is desirable to have 20 parts by weight or less, or, more preferably, 3 parts by weight or less, of the surfactant to 100 parts by weight of low molecular weight polyorganosiloxane.

A suitable hydrophilic solvent may be one compatible with the low molecular weight polyorganosiloxanes, and more particularly, one whose flash point is 40°C or more from the practical viewpoint. The hydrophilic solvent contributes to improving substituting property by water.

Suitable hydrophilic solvents include: polyalcohols and their derivatives such as ethylene glycol monomethyl ethers, ethylene glycol monoethyl ethers, ethylene glycol monopropyl ethers, ethylene glycol monobutyl ethers, ethylene glycol monobutyl ether acetates, diethylene glycol monobutyl ethers.

Particularly preferable are diethylene glycol monobutyl ethers from the viewpoint of its compatibility with the low molecular weight polyorganosiloxanes and safety to the human body and the like. Since these compounds exhibit improved properties when coexisting with the low molecular weight polyorganosiloxanes, a composition only using this combination may allow substitution




by water and drying.

While the composition ratio of the hydrophilic solvent is not particularly limited, it is preferable to have 100 parts by weight or less or, more preferably, 50 parts by weight or less of the hydrophilic solvent mixed with 100 parts by weight of the low molecular weight polyorganosiloxane.

The dewatering cleaning agents of the invention may be applied to metals, ceramics, plastics, and the like. More specifically, they may be applied to metallic parts, surface treated parts, electronic and semiconductor parts, electric and precision machinery parts, optical parts, glass and ceramic parts, and the like. An exemplary general-purpose cleaning process usually involves immersing of any of the above-described parts or spraying a dewatering cleaning agent of the invention onto the part to substitute it by water and drying by blowing hot air and the like. The immersing and spraying processes may be accompanied by an ultrasonic process and mechanical stirring.

The dewatering cleaning agents of the invention, exhibiting a powerful dewatering property, can not only provide cleaning and water-substituting effects equivalent to those of conventional cleaning agents containing flon and the like but also allow various materials to be stably cleaned with their low eroding action. In addition, containing no element halogen such as chlorine and bromine in general, the dewatering cleaning agents of the invention have few risk of destroying or polluting the environment. Thus, it can be said that the dewatering cleaning agents of the invention will be a viable replacement for the conventional organic solvent containing dewatering cleaning



agents such as flon, which have been imposing the environmental problems.

Brief Description of the Drawings

Fig. 1 is a diagram showing an exemplary construction of a cleaning system using a dewatering cleaning agent of the invention.


Detailed Description of the Preferred Embodiments

The invention will now be described with reference to examples in which a cleaning composition of the invention is applied to water system cleaning agents.


Example 1

Two kinds (A1 and A2) of polyoxyalkylene group containing polyorganosiloxane, each represented by formula (V) and (VI), were prepared.


This Sheet Has Been Replaced



A1:



A2:



Then, the polyoxyalkylene denatured silicone (A1) represented by formula (V), polyoxyalkylene denatured silicone (A2) represented by formula (VI), sodium laurate (B1) and polyoxyethylene octylphenyl ether (B2) (20 moles of polyoxyethylene), both serving as surfactants, and water were weighed so that their ratio by weight will be 5 : 5 : 4 : 4 : 82. Thereafter, these components were charged into a homogenizing mixer for blending to obtain a water system cleaning composition P1.

Example 2

The polyoxyalkylene group containing polyorganosiloxane (A1), the sodium laurate (B1) and polyoxyethylene octylphenyl ether (B2), both serving as surfactants, and water were weighed



so that they satisfy the composition ratio specified in Table 1. Then, a water system cleaning composition P2 was obtained as in Example 1.

Examples 3 to 5

The polyoxyalkylene group containing polyorganosiloxanes (A1) and (A2), dioctyl sodium sulfosuccinate (B3) that serves as a surfactant in addition to the surfactants (B1) and (B2), octamethyl tetrasiloxane (D1) and octamethyl trisiloxane (D2), both as low molecular weight polyorganosiloxanes, and water were selectively mixed to prepare water system cleaning compositions P3 to P5 having composition ratios specified in Table 1 in the same manner as that in Example 1.

Comparative examples 1 to 3

Three kinds of water system cleaning compositions were prepared in a manner similar to that of each of the above examples except that no polyoxyalkylene group containing polyorganosiloxane was mixed.

The properties as a cleaning agent were evaluated as to the water system cleaning compositions of Examples 1 to 5 and Comparative examples 1 to 3 by the following methods. The result is also shown in Table 1.

(1) Penetration test

Measurements were made based on the JIS-specified canvas method. The smaller value means better penetrating property; i.e., the composition is more effective in cleaning smaller parts.

(2) Cleaning property test

A sample is prepared by applying a spindle oil over a steel



strip and baking it at 135°C for 48 hours. The property is evaluated by the time spent for cleaning the oil baked on the sample (by ultrasonic cleaning). The smaller the value is, the better the cleaning property becomes.

(3) Stability test

Each composition was contained in a transparent bottle of 200 ml sealed thereafter and then heated at 50°C for 6 hours. After being gradually cooled from 50 to 25°C, its appearance in the bottle is observed.

This Sheet Has Been Replaced



Table 1

		Examples						Comparative examples		
		1	2	3	4	5		1	2	3
Composition ratio (wt.%)	Polyoxyalkylene	5	0.5	1.0	-	10		-	-	-
	Denatured silicone	5	-	-	1.0	-		-	-	-
	Surfactant	4	0.8	0.3	0.3	4		1.2	0.8	0.8
		4	0.7	0.4	0.5	-		0.8	0.7	0.7
		-	-	-	-	0.5		-	0.5	-
	Water	82	98	98	98	82		98	98	98
	Low molecular weight polyorganosiloxane	-	-	-	0.2	3.5		-	-	0.5
		-	-	0.3	-	-		-	-	-
	Penetrability (Canvas method, in second)	7	8	4	3	2		25	22	18
Evaluation result	Cleaning property (in minute)	14	14	12	11	7		22	23	17
	Stability	ST	ST	ST	ST	ST		ST	ST	SEP

Note: ST: stable
SEP: separated

This Sheet Has Been Replaced



As is apparent from the result shown in Table 1, the water system cleaning agent of the invention exhibits excellent cleaning capability and penetrability, attesting to its availability as a replacement for the conventional solvent based cleaning agents containing flon and the like. With its stability, it is considered a highly practical product. In contradistinction thereto, the water system cleaning agents according to Comparative examples were satisfactory neither in cleaning capability nor in penetrability.

An exemplary process employed to clean a specific part using a water system cleaning agent of the invention will now be described.

Example 6

In fabricating a liquid crystal device, a liquid crystal cell is evacuated to a high vacuum degree and a liquid crystal material is sealed in a device. In this case, the evacuation is carried out by a high performance diffusion vacuum pump. Since the diffused oil enters into the vacuum system in the form of mist, the pump must be cleaned often to remove the oil.


In this example, the water system cleaning agent of the invention was used in lieu of a conventional triethane cleaning agent.

A pump part made of a stainless steel SUS304 and a Ni-plated stainless steel SUS304 material having an adhesion of Silicon Oil F-4 (trademark of Shinetsu Chemical) as a diffusion oil was cleaned.

The composition ratio of the used water system cleaning agent is as shown below.



That is, in 80 wt.% of ion-exchanged water being sufficiently stirred at ambient temperature. 6 wt.% of the polyoxyalkylene group containing polyorganosiloxane having the following chemical structure was gradually added to obtain an achromatic translucent homogenous solution.



On the other hand, as a surfactant, a mixture of 8 wt.% of special nonionic Adecanol B-4001 (trademark of Asahi Electrochemical) and 6 wt.% of anionic TWA-2023 (trademark of Ipposha Oil and Grease) of sulfuric acid ester PURLONIC structure was added to the above water/siloxane solution.

After diluting the water system cleaning agent thus obtained was diluted by ion-exchanged water at an arbitrary ratio, Silicone Oil F-4 was cleaned using the diluted cleaning agents. As a result, the pump part was satisfactorily cleaned: through immersion by stirring for 1 minute in a 1/10 diluted cleaning agent at ambient temperature; through immersion by oscillating for 1 minute in a 1/30 diluted cleaning agent at 40°C or through 1 minute ultrasonic cleaning at 20°C in the same cleaning agent; and through 1 minute ultrasonic cleaning in a 1/50 diluted cleaning agent at 50°C, respectively.

For comparison, the pump part was similarly cleaned with compositions containing only surfactant(s) and no polyoxyalkylene group containing polyorganosiloxane. Silicone Oil was not



removed sufficiently with 10 or more minute immersion ultrasonic cleaning in a 1/10 diluted composition at ambient temperature. To remove Silicone Oil with this composition, it took more than 5 minutes at 65°C or more.

It is understood from this data that the cleaning agent that incorporates the polyoxyalkylene group containing polyorganosiloxane of the invention exhibits an outstanding cleaning property.

Example 7


The polyoxyalkylene group containing polyorganosiloxanes and the low molecular weight polyorganosiloxanes of the invention contribute to significantly improve the cleaning capability of commercially available water-soluble cleaning agents.

An aqueous solution of Chemiclean MS-109 (trademark of Sanyo Kasei Kogyo), which is a surfactant containing, low foaming, rust preventive cleaning agent, is typically used to clean mechanical and metallic parts. Blending 3 wt.% of the polyoxyalkylene denatured silicon (A1) represented by formula (V) in Example 1, 5 wt.% of cyclic hexamethylcyclotrisiloxane, 17 wt.% of ion-exchanged water with 65 wt.% of the above aqueous solution, a new cleaning composition was prepared.

This new cleaning composition was 1/20 diluted by ion-exchanged water and its cleaning property was evaluated by the following method. The result is shown in Table 2. For comparison, the evaluation result of 1/20 diluted Chemiclean MS-109 was also shown.

Test Method

(1) Cleaning test - 1



The following contaminants were applied to a degreased aluminum plate (AC-4A) by immersing, dried by blowing, and immersed while stirred (400 rpm) in respective cleaning agents (1/20 diluted) for 15 seconds to 1 minute. Then, after immersed in water, the aluminum plate was dried by blowing. Each contaminant was transferred on white paper through an adhesive tape for reflectance measurement by a colorimeter thereby to calculate the cleaning rate.

Contaminant:

Spindle oil	78%
Fatty acid ester	15%
Chlorinated paraffin	5%
Carbon black	2%

$$\text{Cleaning rate (\%)} = (R_w - R_s) / (R_o - R_s)$$

R_o : Reflectance of the original white paper

R_s : Reflectance of the standard contaminated plate

R_w : Reflectance of the contaminated plate after
cleaned

(2) Cleaning test - 2


A contaminant was prepared by adding 2% of carbon black to a water-soluble machining oil (emulsive), and the test was performed in a manner similar to that of Cleaning test - 1. Its cleaning rate was similarly calculated.

This Sheet Has Been Replaced


Table 2

	Immersion time (second)	Cleaning rate (%)	
		Invention	MS-109
Cleaning test - 1	15	72.4	59.0
	30	86.5	65.2
	60	100.0	67.8
Cleaning test - 2	15	81.7	58.0
	30	93.8	71.0

This Sheet Has Been Replaced



Similar tests were conducted on EP-680 (trademark of E.P. Japan) which is a commercially available supereffective cleaning solution and water system cleaning agent; Banrise D-20 (trademark of Joban Chemical Industries) which is an emulsive degreased cleaning agent; and Hikari Ace (trademark of Shoko Trade) which is a powerful special cleaning agent. As a result, these cleaning agents, when used in combination of the polyoxyalkylene group containing polyorganosiloxane and the low molecular weight polyorganosiloxane of the invention, exhibited a significantly improved cleaning property.

Example 8


The water system cleaning agent of the invention exhibits remarkable effect on cleaning of fluxes used in mounting electronic parts on printed boards. The flux comes roughly in two types: rosin containing and water-soluble. A specific example of cleaning rosin containing fluxes, which is said to be a difficult task, will now be described.

As a step prior to soldering a part on a printed board, a WW rosin ester was put on a part and immersed in a solder bath at 230 to 250°C and then the part was mounted. It was observed that the flux was completely removed when the printed board was shower-rinsed for 35°C for 45 seconds using a water system cleaning agent described below.

The water system cleaning composition used here is prepared by blending 2 wt.% of the polyoxyalkylene group containing polyorganosiloxane represented by formula (VII), 3 wt.% of Senkanol FM (trademark of Nippon Senka), which is an amphoteric surfactant, 5 wt.% of Nikkol CMT-30 (trademark of Nippon



Surfactant), which is a sodium-N-COCOIL methyl taurine containing nonionic surfactant, and adding ion-exchanged water to prepare 100 wt. % of the composition.



When acceleration aging tests which guarantees US MIL-P-14256C standard, surface insulation resistance tests, ion residual tests and the like were conducted on the above composition which was 1/10 diluted by ion-exchanged water, the results were satisfactory.

Examples in which cleaning compositions of the invention were applied to dewatering cleaning agents will now be described.
Examples 9 to 17

Octamethyltrisiloxane (E1), octamethyltetrasiloxane (E2), and decamethylpentasiloxane (E3) were prepared as low molecular weight polyorganosiloxanes; polyoxyethylene oleyl ether (F1) (P.O.E = 6 moles), and polyoxyethylene octylphenyl ether (F2) (P.O.E = 10 moles) as surfactants; and diethylene glycol monobutyl ether (G1) as a hydrophilic solvent were prepared.

These components were selected and blended so that the composition ratio shown in Table 3 were satisfied to obtain respective dewatering cleaning agents.

Comparative examples 4 to 8

This Sheet Has Been Replaced



Flon 113, methylene chloride, isopropyl alcohol, and ethanol were prepared as conventional dewatering cleaning agents to obtain 5 types of dewatering cleaning agents whose composition ratios were as shown in Table 3.

The properties of Examples 9 to 17 and Comparative examples 4 to 8 were evaluated by the following methods. The result is also shown in Table 3.

(1) Dewatering property

Various pieces (a stainless steel strip, a ceramic piece, a polycarbonate piece, a Ni-plated steel strip) were immersed in each dewatering cleaning agent after washed by water. In examples 13 to 15, each piece was then rinsed by the low molecular weight polyorganosiloxane blended to prepare each dewatering cleaning agent. Thereafter, each piece was dried in an oven at 50°C. The water marks (a stain by impurities dissolved in water) after drying each piece was observed visibly and by a scanning electron microscope and evaluated in accordance with the following criteria.

XX: Not evaluable due to erosion of the piece during dewatering.

X: Water marks were visibly observed.

o: No water marks were visibly observed.

⊙: No water marks whose size is 50 μm or more were observed by the scanning electron microscope.

(2) Continuous dewatering property

A continuous dewatering test with a frequency of 50 times were conducted on a stainless steel strip and the appearance of the strip was evaluated in a manner similar to that of item (1).



(3) Drying property

The stainless steel strip was immersed in each dewatering cleaning agent and dried in the oven at 50°C. During the drying process, the strip was touched by a finger to see the drying condition every 5 minutes and the time required for drying was recorded on a 5-minute basis.

This Sheet Has Been Replaced



Table 3

			Examples														Comparative examples							
			9	10	11	12	13	14	15	16	17	4	5	6	7	8								
Composition ratio (parts by weight)	Low molecular weight polyorganosiloxane	E1	100	-	-	50	100	-	-	-	-	-	-	-	-	-	-	-	-	-				
		E2	-	100	50	50	-	100	100	100	-	50	-	-	-	-	-	-	-	-				
		E3	-	-	50	-	-	-	-	-	100	-	-	-	-	-	-	-	-	-				
	Surfactant	F1	-	-	-	-	0.3	0.3	-	-	-	-	-	-	-	-	-	-	-	-				
F2		-	-	-	-	-	-	0.2	-	-	-	-	-	-	-	-	-	-	-					
	Hydrophilic solvent	C1	-	-	-	-	-	-	-	10	20	-	-	-	-	-	-	-	-	-				
		Methylene chloride Freon 113 Ethanol Isopropyl alcohol	-	-	-	-	-	-	-	-	-	-	50	100	-	-	-	-	-	-				
			-	-	-	-	-	-	-	-	-	-	-	-	100	96	-	-	-	-				
			-	-	-	-	-	-	-	-	-	-	-	-	-	-	4	-	-	-				
Dewatering property	Stainless steel Ceramics Polycarbonate Ni plated strip	-	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙					
		⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙					
		⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙					
		⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙					
Continuous dewatering property		⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙					
Drying property (50°C in oven in minute)		10	5	10	10	10	5	5	10	15	5	5	<5	<5	<5	<5	<5	<5	<5					

Note: * Solvent cracks occurred.

This Sheet Has Been Replaced



As is apparent from the results shown in Table 3, the dewatering cleaning agents of the invention, exhibiting satisfactory dewatering property, can be a viable substitute for organic solvent containing flon and the like based cleaning agents.

Dewatering cleaning agents containing methylene chloride or isopropyl alcohol (Comparative examples 4 and 5) rust and erode metal films and plastics. In contradistinction thereto, the dewatering cleaning agents of the invention are stable to metal films and plastics and exhibit satisfactory dewatering property even to ceramics which have large surface roughness values, thereby ensuring their reliability when applied to parts including metal, plated, electronic, semiconductor, plastic, and ceramic parts. The dewatering cleaning agent containing isopropyl alcohol permitted water to be dissolved therein, thereby causing water to present on the part again.

Moreover, it is understood that mixing of surfactants and hydrophilic solvents with the dewatering cleaning agents of the invention improved the dewatering property, thereby attesting to their industrial applicability.

An exemplary cleaning system using a dewatering cleaning agent of the invention will now be described with reference to Fig. 1.

A cleaning system shown in Fig. 1 consists roughly of a cleaning/water-substituting process A and a rinsing/dewatering process B.

The cleaning/water-substituting process A, which is the first process involves a first cleaning vessel 1 and a second



cleaning vessel 2, each serving both as a separator through sedimentation and a separator through overflow, and a dewatering vessel 3. The first and second cleaning vessels 1 and 2 communicate with each other through a drain line 2a and an overflow line 2b. The first and second cleaning vessels 1 and 2 are operated together with ultrasonic, oscillating, mechanical stirring, cleaning agent heating, and brushing processes and the like, if necessary.

The first and second cleaning vessels 1 and 2 respectively contain a cleaning agent D1 composed of a low molecular weight polyorganosiloxane and a surfactant, which is one of the dewatering cleaning agents of the invention. The surfactant containing cleaning agent D1 may be so prepared that its specific gravity is smaller than that of water and larger than that of an oily stain. Therefore, water Y introduced by an object to be cleaned X is separated by being sedimentated at the bottom of the surfactant containing cleaning agent D1 that has been charged in the first and second cleaning vessels 1 and 2. If an oily stain Z is present on the object X, the oily stain Z is separated by floating upward in the surfactant containing cleaning agent D1 in the first and second cleaning vessels 1 and 2.

The water Y separated by being sedimentated in the second cleaning vessel 2 is intermittently discharged to the first cleaning vessel 1 through a drain line 2a while the water Y separated by being sedimentated in the first cleaning vessel 1 is intermittently discharged to a cleaning agent recycling mechanism C (described later) through a drain line 4. A drain line 3a connected to the drainage vessel 3 is also connected to



the cleaning agent recycling mechanism C.

The oily stain Z separated by floating in the first and second vessels 1 and 2 is discharged outside while continuously overflow through an overflow line 5 connected to the first cleaning vessel 1.

The surfactant containing cleaning agent D1 charged in the first and second cleaning vessels 1 and 2 is continuously circulated through a filter 6 that serves to remove solid particles, H₂O particles, undissolved substances, and the like contained in the cleaning agent D1.

The rinsing/dewatering process B, which is the second process, involves a third cleaning vessel 7 and a shower rinse vessel 8. Below the shower rinse vessel 8 is a buffer tank 9 that communicates with the third cleaning vessel 7 through a drain line 9a and an overflow line 9b. The third cleaning vessel 7 is also operated together with ultrasonic, oscillating, mechanical stirring, cleaning agent heating, and brushing processes and the like, if necessary.

The third cleaning vessel 7 contains a cleaning agent D2 consisting only of a silicone composition identical to the low molecular weight polyorganosiloxane used in the first process A. The cleaning agent D2 may be so prepared that its specific gravity is smaller than that of water and larger than that of an oily stain. Therefore, as in the first process A, water Y is separated by being sedimentated at the bottom of the cleaning agent D2 and the oily stain Z is separated by floating upward in the cleaning agent D2.

The water Y separated by being sedimentated in the third



cleaning vessel 7 is intermittently discharged to the cleaning agent recycling mechanism C through a drain line 10 while the oily stain Z separated by floating in the third cleaning vessel 7 is discharged outside through an overflow line 11.

The cleaning agent D2 charged in the third cleaning vessel 7 is continuously circulated through a filter 12 that serves to remove solid particles, H₂O particles, undissolved substances, and the like contained in the cleaning agent D2.

The object to be cleaned X undergoes the first process A and then the second process B, cleaned and dewatered, and then dried by a fan forced drier (not shown) to complete the cleaning process.

The cleaning agent used in the cleaning system is subjected to the following recycling process.

As described above, the drain lines 4, 3a, 10 of the first, second, and third cleaning vessels 1, 2, and 7, and the dewatering vessel 3 are connected to the cleaning agent recycling mechanism C. The cleaning agent D1 or D2 contained in each cleaning vessel is constantly cleaned by the filters 6 and 12. However, when heavily contaminated, the cleaning agent is introduced to the cleaning agent recycling mechanism C through drain lines 4 and 10 by a conveyer pump 13 for fractional distillation. The cleaning agent D1 deposited in the dewatering vessel 3 is also supplied intermittently to the cleaning agent recycling mechanism C.

At the cleaning agent recycling mechanism C, the introduced cleaning agent is separated into liquid components and solid components by a filter 14, and only the liquid components are



forwarded to a distiller 15 with the solid components being destroyed. The distiller 15 separates various components, water, oily stains in the cleaning agent utilizing the difference in their boiling points. Water and the like that remain in the distiller 15 are further separated by a decanter 16.

Since the cleaning agent D1 is an agent having a surfactant added to the cleaning agent D2 that contains only the low molecular weight polyorganosiloxane, the low molecular weight polyorganosiloxane, i.e., the cleaning agent D2, can be extracted from both cleaning agents D1 and D2, thereby allowing the cleaning agent D2 to be recycled. The components other than the recycled cleaning agent D2, i.e., the surfactant, water, and the like will be destroyed.

The recycled cleaning agent D2 is forwarded to a mixer 18 from which the cleaning agent D1 is supplied to the shower rinse vessel 8, the third cleaning vessel 7, or the second cleaning vessel 2 through a line 17.

In the shower rinse vessel 8, a shower rinsing process is conducted using only the recycled cleaning agent D2 or a cleaning agent D2 newly introduced through a cleaning agent supply line 19, both being free from impurities.

The mixer 18 mixes the recycled or new cleaning agent D2 with the surfactant newly supplied from a surfactant supply line 20 to prepare a new cleaning agent D1. The new cleaning agent D1 is supplied to the second cleaning vessel 2, if necessary.

With the cleaning system of such construction as described above, the dewatering cleaning agents of the invention can be used efficiently and effectively enjoying the advantage of



excellent cleaning properties.

Industrial Applicability

As described in the foregoing pages, the cleaning compositions of the invention, when used as water system cleaning agents, exhibit a cleaning effect equivalent to that of conventional flon containing cleaning agents and an excellent stability as a water system with no risk of enviromental destruction and pollution, thereby making a viable replacement for the organic solvent based cleaning agents including flon and the like which have environmental disadvantages. In addition, the cleaning compositions of the invention, when used as dewatering cleaning agents, provide a powerful dewatering property with no risk of environmental destruction and pollution, thereby serving a viable replacement for the organic solvent based dewatering cleaning agents including flon and the like which have environmental disadvantages.

This Sheet Has Been Replaced






5

CLAIMS:

1. A non-aqueous cleaning composition capable of cleaning an object, the composition comprising at least one low molecular weight polyorganosiloxane of formula (II):-



... (II)

(wherein R^1 is an organic group of single valence substituted by the same or different group or unsubstituted, and m is an integer from 3 to 7).

2. A non-aqueous cleaning composition according to claim 1, consisting essentially of said low molecular weight polyorganosiloxane of formula (II).
3. A non-aqueous cleaning composition according to claim 2, further comprising a surfactant and/or a hydrophilic solvent.
4. A non-aqueous cleaning composition according to claim 3, comprising at least said surfactant, the surfactant being selected from anionic surfactants, nonionic surfactants, amphoteric surfactants, and cationic surfactants.
5. A non-aqueous cleaning composition according to claim 4, wherein the surfactant is an anionic surfactant selected from polyoxyalkylene alkylether sulphonates and phosphoric esters.
6. A non-aqueous cleaning composition according to claim 4, wherein the surfactant is a nonionic surfactant selected from polyalcohol fatty acid esters, polyoxyalkylene fatty acid esters and polyoxyalkylene alkylethers.

This Sheet Has Been Replaced





7. A non-aqueous composition according to claim 4, wherein the surfactant is an imidazoline derivative amphoteric surfactant.

8. A non-aqueous cleaning composition according to claim 4, wherein the surfactant is a cationic surfactant selected from alkylamine salts and alkyl quaternary ammonium salts.

9. A non-aqueous cleaning composition according to claim 4, wherein the surfactant is a terpene-containing compound or a higher fatty acid ester.

10. A non-aqueous cleaning composition according to any of claims 4-9, wherein the amount of the surfactant is 20 parts by weight or less relative to 100 parts by weight of the polyorganosiloxane of formula (II).

11. A non-aqueous cleaning composition according to any of claims 4-9, wherein the amount of the surfactant is 3 parts by weight or less relative to 100 parts by weight of the polyorganosiloxane of formula (II).

12. A non-aqueous cleaning composition according to claim 3, wherein said hydrophilic solvent has a flash point of 40°C or more.

13. A non-aqueous cleaning composition according to claims or claim 12, comprising at least said hydrophilic solvent, the hydrophilic solvent being selected from polyalcohols and their derivatives.

14. A non-aqueous cleaning composition according to claim 13, wherein the hydrophilic solvent is selected from polyalcohols and their derivatives selected from ethylene glycol monomethyl ethers, ethylene glycol monoethyl ethers, ethylene glycol

This Sheet Has Been Replaced





monopropyl ethers, ethylene glycol monobutyl ethers, ethylene glycol monobutyl ether acetates and diethylene glycol monobutyl ethers.

15. A non-aqueous cleaning composition according to claim 13 or claim 14, wherein the amount of the hydrophilic solvent is 100 parts by weight or less relative to 100 parts by weight of the polyorganosiloxane of formula (II).

16. A non-aqueous cleaning composition according to any of claims 13-15, wherein the amount of the hydrophilic solvent is 50 parts by weight or less relative to 100 parts by weight of the polyorganosiloxane of formula (II).

17. A method of cleaning an object, the method comprising treating the object with a non-aqueous cleaning composition according to any preceding claim.

18. A method according to claim 17, wherein the object to be cleaned comprises at least one material selected from a metal material, a ceramic material and a plastics material.

19. A method according to claim 18, wherein the material is in the form of at least one part selected from a metallic part, a surface-treated part, an electronic part, an electrical part, a semiconductor part, a precision machinery part, an optical part, a glass part, a ceramic part and a plastic part.

20. A method according to any of claims 17-19, wherein the step of treatment with said non-aqueous cleaning composition involves immersion of the object in, or spraying the object with, the non-aqueous cleaning composition.

21. A method according to claim 20, wherein the immersion or spraying process in the treatment step are accompanied by ultrasonic agitation and mechanical stirring.





22. A method according to any of claims 17-21, further comprising the step of drying the object after the step of treatment with said non-aqueous cleaning composition.

23. A method according to any of claims 17-22, further comprising the steps of:-
a cleaning step of dewatering and cleaning an object to be cleaned by a cleaning vessel containing the non-aqueous cleaning composition of formula (II), and
a rinsing step of rinsing and cleaning said object to be cleaned after the dewatering and cleaning by a plurality of rinsing cleaning vessels in sequence, each of the rinsing cleaning vessels containing a rinsing cleaning agent, the rinsing cleaning vessels being connected such that said rinsing cleaning agent is transmitted in sequence in the direction opposite to that of transmitting said object to be cleaned,

wherein said rinsing step is conducted while a rinsing cleaning waste liquid is recovered from the most downstream rinsing cleaning vessel of said plurality of rinsing cleaning vessels, the recovered rinsing cleaning waste liquid is distilled so as to be recycled, and the recycled rinsing cleaning agent is re-supplied to the most upstream rinsing cleaning vessel.

24. A method according to claim 23, wherein said rinsing cleaning waste liquid is filtered as a pre-treatment for the distillation.


25. A method according to claim 23, wherein the cleaning waste liquid of the cleaning step is recovered from the cleaning vessel and the recovered cleaning waste liquid is distilled to recycle said low molecular weight polyorganosiloxane of formula (II).

This Sheet Has Been Replaced




Abstract of the Disclosure

A cleaning composition comprising at least one low molecular weight polyorganosiloxane selected from the group consisting of straight chain polydiorganosiloxane represented by a general formula:



(wherein R^1 is an organic group of single valence substituted by the same or different group or unsubstituted, and 1 is an integer from 0 to 5), and cyclic polydiorganosiloxane represented by a general formula:



(wherein R^1 is an organic group of single valence substituted by the same or different group or unsubstituted, and m is an integer from 3 to 7). To use it as a water system cleaning agent, polyoxyalkylene group containing polyorganosiloxane, a surfactant, and water are additionally mixed. Accordingly, a cleaning effect free from environmental destruction and contamination, equivalent to flon containing cleaning agents, and satisfactorily stable in terms of dispersion as a water system cleaning agent can be obtained. In addition, to use as a dewatering cleaning agent, the low molecular weight polyorganosiloxane is additionally mixed alone or with a surfactant and/or a hydrophilic solvent. Accordingly, cleaning


This Sheet Has Been Replaced



and water substituting properties equivalent to flon containing dewatering cleaning agents and environmental safety can be obtained.

This Sheet Has Been Replaced





This Sheet Has Been Replaced



20 FEB 1997

☒ Description : paged 1 to paged 30
☒ Claim(s) : paged 31 to paged 34
☒ Drawing(s) : paged 1 to paged 1
☒ Abstract : paged 35 to paged 36

DATE OF RECEIPT 20 FEB 1997

Background of the Invention

Field of the Invention


This invention relates to cleaning compositions which will replace cleaning agents containing an organic solvent including flon and the like.

Description of the Related Art

In manufacturing various parts such as metal parts, plated and coated parts, and electronic and semiconductor parts, flon containing solvents such as flon 113, and organic solvents such as trichloroethane, trichlorethylene, tetrachloroethylene, and carbon tetrachloride are widely used as cleaning agents for eliminating oil stains and the like. The above organic solvent containing cleaning agents are also used as dewatering cleaning agents after having washed various parts with water in order to avoid the following problems that are associated with direct drying of water present on an object to be cleaned:

- (1) Heating (100°C or more) which entails energy loss;
- (2) Reducing in productivity due to time taken in drying;
- (3) Likely deformation of the object to be cleaned due to heating (thermal expansion that exceeds the tolerance); and
- 4) Increase in space for installing a cleaning system including a cooler and a heat shielding unit.

The term "dewatering cleaning agent" is used herein to denote a cleaning agent into which an object to be cleaned, which has been washed with water, is immersed or with which the object is rinsed by shower thereby to have water present on the object substituted by itself and then vaporized by air at room temperature or heated to 60°C or less so that the object can be dried.



However, ever since it has been found that the destruction of the ozone layer by discharge of flon affects seriously the human body and the ecological system, the use of flons such as flon 12 and flon 113 whose ozone destruction coefficients are high is on the gradual decline on a global scale for an eventual total ban.

Stricter regulations are imposed also on chlorine containing organic solvents such as trichloroethylene and tetrachloroethylene which are presumed to induce soil and underwater contaminations and the like.

Flons whose ozone destruction coefficients are lower than the currently used flon containing solvents are being developed, some of which are under fabrication on a commercial basis. However, these new developments are not so welcome because they still are destroyers of the ozone layer.

What gradually attracts attention as a replacement for the above organic solvents is a surfactant-based water system cleaning agent which is free from environmental destruction and contamination. However, cleaning agents containing only surfactants are not satisfactory in penetrability, thereby not cleaning, e.g., stains penetrated into narrow portions and medium to high viscous, persistently sticky oil stains.

Japanese Patent Publication No. 50463/1988 discloses a method of cleaning woven materials by using silicone containing compounds. According to the disclosure, a liquid cleaning composition containing an effective amount of cyclic siloxane having 4 to 6 silicon atoms is used. However, the liquid cleaning compositions including the above silicone containing compound are not suitable for use not only in general industrial products due to their being specifically prepared for woven materials, but also in systems using water (hereinafter referred to as "water system") due to their being based on a single cyclic siloxane or the mixture of a cyclic siloxane and an organic solvent. Further, such compositions are not so dispersive in water that the addition of a surfactant thereto does not assist in blending them homogeneously, thereby causing phase separation immediately. Thus, they are not adapted for use as water system cleaning agents.

20 FEB 1997

On the other hand, Japanese Patent Laid Open No. 56203/1978 recites an aerosol aqueous cleaning composition containing a chain polydimethylsiloxane having 2 to 3 silicon atoms in a single molecular. Since its content is limited to about 0.02 to 0.1 wt.%, no such advantage as improving the cleaning property of water system cleaning compositions is disclosed.

Under such circumstances, the development of highperformance water system cleaning agents free from environmental problems is strongly called for.

In the meantime, the use of lower alcohols such as isopropyl alcohol is under study for a new development that can replace the above-mentioned organic solvents for dewatering. However, isopropyl alcohol has a flash point of 11.7°C, which is lower than room temperature, and this involves some danger of fires under ordinary handling conditions. In addition, isopropyl alcohol is highly compatible with water, so that the initial dewatering property is ensured, but its repetitive use causes dissolved water to be present again. As a result its dewatering property will be impaired on a long-term basis. To refine isopropyl alcohol for reuse by removing water from the water containing isopropyl alcohol, a tremendous equipment investment is required. That isopropyl alcohol is toxin to the human body is another factor that tends to keep it from using.


The use of hydrocarbon and higher alcohols which have higher flash points than room temperature allows a comparatively easy removal of water, but their low volatility prevents drying themselves at low temperatures, e.g., 60°C or less, thereby making them unsuitable for applications to dewatering cleaning agents.

Therefore, an object of the invention is to provide water system cleaning compositions which have cleaning capability equivalent to that of organic solvent containing cleaning agents including such as flon and which are stable as water system cleaning agents and free from environmental destruction and contamination.


Another object of the invention is to provide dewatering compositions which have the substituting and drying properties equivalent to those of organic solvent containing dewatering cleaning agents, which have few risks of fires and which are free from environmental destruction.

Summary of the Invention

A cleaning agent composition of the invention comprises at least one low molecular weight polyorganosiloxane selected from the group consisting of straight chain polydiorganosiloxane represented by a general formula:




(wherein R¹ is an organic group of single valence substituted by the same or different group or unsubstituted, and 1 is an integer from 0 to 5), and cyclic polydiorganosiloxane represented by a general formula:



(wherein R¹ is an organic group of single valence substituted by the same or different group or unsubstituted, and m is an integer from 3 to 7).

Each of such low molecular weight polyorganosiloxanes exhibits powerful penetrability to stains and satisfactory substituting property with water alone, making itself a feature component of the invention. Reference character R¹ in formulas (I) and (II) denotes a substituted or unsubstituted organic group of single valence including: a single-valence unsubstituted hydrocarbon group such as an alkyl group such as a methyl group, an ethyl group, a propyl group, and a butyl group and a phenyl group; and a single-valence substituted hydrocarbon group such as a trifluoromethyl group. As the R¹ which is placed at an end of formula (I), an amino group, an amide group, an acrylic acid ester group, and a mercaptan group are typical organic groups; however, the methyl



group is most preferable from the viewpoint of stability, and maintainability of volatility, and the like.



The cleaning compositions of the invention may roughly be classified into two groups: a water system cleaning agent and a dewatering cleaning agent.

For use as a water system cleaning agent, suitable low molecular weight polyorganosiloxanes include: octamethylcyclotetrasiloxane, decamethylcyclopentasiloxane and mixtures thereof, each having a cyclic structure; and octamethyltrisiloxane and decamethyltetrasiloxane, each having a straight chain structure, from the viewpoint of penetrability and cleaning capability. In regions where the water system cleaning composition has a strong alkaline property from the viewpoint of stability of polysiloxane, the low molecular weight polyorganosiloxane having a straight chain structure which is represented by formula (I) is preferable.

For use as a dewatering cleaning agent, low molecular weight polyorganosiloxanes having a cyclic structure are preferable from the viewpoint of substituting property with water and penetrability and the like, octamethylcyclotetrasiloxane, decamethylcyclopentasiloxane, and mixtures thereof are more preferable.

A case in which the cleaning compositions of the invention are used as water system cleaning agents will now be described.

Although the low molecular weight polyorganosiloxanes represented by formulas (I) and (II) exhibit powerful penetrability to stains, each composition is not compatible with water singly nor is it soluble and stably dispersive in water so that it is likely to have phase separation in water. That is, it is proposed to use them in combination with polyoxyalkylene group containing polyorganosiloxane having in a single molecule at least one siloxy unit represented by a general formula:



..... (III)


(wherein R^2 is an alkyl or phenyl group and A is a polyoxyalkylene group). As a result of such use in combination, the low molecular weight polyorganosiloxanes, providing stable dispersion in water, exhibit strong penetrability to stains. In addition, the use of a surfactant in combination with the compositions may improve their cleaning property.

Thus, preferable compositions for a water system cleaning agent of the invention contain the low molecular weight polyorganosiloxane represented by formula (I) or (II); the polyoxyalkylene group containing polyorganosiloxane having at least one siloxy unit represented by formula (III) in a single molecular; a surfactant; and water.

The polyoxyalkylene group containing polyorganosiloxane exhibits affinity for water owing to its polyoxyalkylene group bonded with the silicon atom, thus not only being a component for a stable water system dispersed solution or aqueous solution but also acting as an agent for eliminating stains by penetrating into the interface between the stains and a substrate which is made of, e.g., a metal and which has the stains deposited thereon, and as an antifoaming agent as well.

Such a polyoxyalkylene group containing polyorganosiloxane can be prepared by hydrosilyl group containing polyorganosiloxane and a polyoxyalkylene compound having an unsaturated group at the end to interact with each other for addition under the presence of a platinum containing catalyzer.

An example of the polyoxyalkylene group denoted by reference character A in formula (III) is, e.g., a single-valence group represented by the formula:



20 FEB 1997

(wherein R^3 is a two-valance group selected from the group consisting of an alkylene group having from 1 to 8 carbon atoms, a β -hydroxypropyleneoxyalkylene group and a polymethylene oxyalkylene group, both having from 4 to 11 carbon atoms; R^4 is an alkylene group having from 2 to 4 carbon atoms; R^5 is an end group selected from a hydrogen atom and a single-valence organic group; and n is a positive integer).

Siloxane that forms a main component of the polyoxyalkylene group containing polyorganosiloxane is not particularly limited. The organic group that is to be bonded with the silicon atom of the siloxane is basically a methyl group, but may also contain a single-valence hydrocarbon group such as an ethyl group, a propyl group, a butyl group, a phenyl group, or a single-valence substituted hydrocarbon group such as a trifluoromethyl group as long as the advantages of the invention can remain harmless therefrom.


Also, the molecular weight of the siloxane is not particularly limited nor is that of a single polyoxyalkylene group. Although they are large values, the addition of a surfactant thereto and the like allows the composition to be made sufficiently water soluble or stably water dispersive. However, it is practically preferable to limit the molecular weight of the single polyoxyalkylene group in the order of 100 to 5000. For a polyoxyalkylene chain, it is preferable to adjust its oxyethylene component to 40 mol % or more in the total polyoxyalkylene.

While the amount of the polyoxyalkylene group is not particularly limited, it is more preferable to limit it within 5 mol % or more of the total organic groups bonded with silicon atoms of the polyorganosiloxane from the standpoint of system stability.


Exemplary polyoxyalkylene group containing polyorganosiloxanes include:

a chain polysiloxane represented by the formula:

20 FEB 1997



(wherein p, q, r, and s are positive integers); and a cyclic polysiloxane represented by the formula:



(wherein t, u, and v are positive integers).

The surfactant serves as a component for dissolving, emulsifying, and stabilizing the stains removed by the low molecular weight polyorganosiloxanes or polyoxyalkylene group containing polyorganosiloxanes.

Such surfactants can be classified by the activation chemical structure into the following types: cationic, anionic, nonionic, amphoteric, and combined types. The invention may be applied to all the above types of surfactants. However, to obtain the advantage from their combination

20 FEB 1997

with the polyoxyalkylene group containing polyorganosiloxane, it is preferable to use anionic, nonionic, or amphoteric surfactants. Particularly, the use of the polyoxyalkylene group containing polyorganosiloxane in combination with either anionic/nonionic surfactants or amphoteric/nonionic surfactants provides a remarkable synergetic effect in improving the cleaning property and penetrability of the low molecular weight polyorganosiloxanes or the polyoxyalkylene group containing polyorganosiloxanes.

Exemplary suitable surfactants to be applied to the invention include: anionic surfactants such as polyoxyalkylene alkylether sulfonates and phosphoric esters; nonionic surfactants such as polyalcohol fatty acid esters, polyoxyalkylene fatty acid esters, and polyoxyalkylene alkylethers; amphoteric surfactants such as imidazolin derivatives; and cationic surfactants such as alkylamine salts, alkyl quaternary ammonium salts. In addition thereto, terpene containing compounds which are rarely present in the form of a single substance and extracted from natural substances as well as higher fatty acid esters may also be applied. It is also possible to use synthetic compounds in which part of the chemical structure of each compound is substituted by a fluorine or silicon atom.

While the composition ratio of the above-mentioned quaternary water system cleaning agent is not particularly limited, it is preferable to blend 10 to 1000 parts by weight of a surfactant to 100 parts by weight of the polyoxyalkylene group containing polyorganosiloxane, and 1000 parts by weight or less of the low molecular weight polyorganosiloxane to 100 parts by weight of a total combination of the above surfactant(s) and the polyoxyalkylene containing polyorganosiloxane. Too small an amount of the surfactant reduces the cleaning capability, while too large an amount impairs the penetrability. Too large an amount of the low molecular weight polyorganosiloxane not only makes the system difficult to disperse but also reduces stability as a water system composition. A preferable fraction of the surfactant is 30 to 700 parts by weight, or, more preferably, 50 to 300 parts by weight, to 100 parts by weight of the polyoxyalkylene group containing polyorganosiloxane. A more preferable fraction of the low molecular weight polyorganosiloxane is between 10 and 1000 part by weight. While the fraction of water in the quaternary water system cleaning agent is not particularly limited either, it is preferable to have water 40 wt.% or more or, more preferably, 70 to 99.5 wt.% to the total composition from a stability viewpoint.

By the way, the polyoxyalkylene group containing polyorganosiloxane having in a single molecule at least one siloxy unit represented by formula (III) penetrates, as described above, into the interface between the stains and the substrate made of, e.g., a metal to which the stains adhere to "peel off" the stains. Thus, even a tertiary composition consisting of the polyoxyalkylene group containing polyorganosiloxane, a surfactant, and water may serve as a viable water system cleaning agent. In this case, the fractions of the quaternary water system cleaning agent will apply to the tertiary composition.

The fractions of the tertiary or quaternary water system cleaning agents may be so designed that the value to be obtained by a canvas method at room temperature for evaluating penetrability will be 15 or less, 10 or less, or 5 or less. For the evaluation, the canvas method specified as a fiber/textile test method by Japanese Industrial Standards (JIS) is adopted. Since the cleaning property of these water system cleaning agents depends on the pH value of the solution itself, it is desirable to adjust the pH value to the alkali region. The pH value is more preferably between 8 to 14.

The tertiary or quaternary cleaning agents can be prepared easily by blending and stirring the above-mentioned polyoxyalkylene group containing polyorganosiloxane, a surfactant, water, or further the low molecular weight polyorganosiloxane represented by formula (I) or (II), where necessary. The use of a known dispersing device will help obtain a water system cleaning agent with ease.

The water system cleaning agents such as described above may have additives to be applied to ordinary water-soluble cleaning agents such as pH modifiers, adsorbents, solid particles, synthetic builders, rust preventives, and antistatic agents mixed as cleaning assistants or post-cleaning added-value improving agents and the like, depending on the property, amount, adhering state, cleaning condition, and the like of a stain. Such an addition may play an important part depending on their application.

The water system cleaning agents of the invention may be applied to metals, ceramics, plastics, and the like. More specifically, they may be applied to metallic parts, surface treated parts, electronic and semiconductor parts, electric and precision machinery parts, optical parts, glass and ceramic parts, and the like. An exemplary general-purpose cleaning process usually

20 FEB 1997

involves cleaning of any of the above-described parts by such a process as ultrasonic process, mechanical stirring and spraying, and thereafter, washing by water (preferably by pure water or ion-exchanged water), and is dewatered by drying the part with heated air or a like process. The cleaning composition in which the stain separated from the part is present is treated by, e.g., separating the stain through a filter or the like and thereafter by being subjected to a general waste water treatment process, thereby allowing the composition to be unhazardous and pollution-free easily.

According to the water system cleaning agent of the invention, the powerful penetrating property of the low molecular weight polyorganosiloxane represented by formula (I) or (II) for the interface between the stains and the substrate as well as the cleaning capability of the surfactant(s) to the stains provides a cleaning performance equivalent to that of the conventionally used flon containing cleaning agents. The use of the polyoxyalkylene group containing polyorganosiloxane in combination with the water system cleaning agents of the invention allows satisfactory dispersing property in water. In addition, when applied as a tertiary composition consisting of the polyoxyalkylene group containing polyorganosiloxane, the surfactant, and water, the cleaning agent of the invention exhibits excellent cleaning property by the penetrating capability of the polyoxyalkylene group containing polyorganosiloxane with respect to the stain. Being a water system agent, it will bring no risk of environmental destruction and pollution. Thus, it can be said from the above that the water system cleaning agent of the invention can be an attractive replacement for cleaning agents based on organic solvents containing flon and other substances which have considered hazardous.

A case in which a cleaning composition of the invention is used as a dewatering cleaning agent will now be described.

Here, the term "dewatering agent" is only so named after "water", which is a typical liquid capable of being substituted by the low molecular weight polyorganosiloxanes, and the cleaning compositions of the invention may also be used as "liquid removing" agents in substituting and cleaning liquids other than water. The applicable liquids may be those which are insoluble or difficult to be dissolved in the low molecular weight polyorganosiloxanes and whose surface tensions are larger than those of the low molecular weight polyorganosiloxanes. The "water" to

be cleaned may include liquids using water as a dispersion medium such as mixtures of water and alcohols and liquids in which various substances are dissolved.

The low molecular weight polyorganosiloxane represented by formula (I) or (II) can be, as described previously, substituted by water alone, thus allowing itself to be easily vaporized and dried by hot air below 60°C.

Such a dewatering cleaning agent may consist substantially of the low molecular weight polyorganosiloxane and with it a satisfactory effect can be obtained. However, its cleaning and dewatering properties and the like will be further improved by forming it into a composition having the low molecular weight polyorganosiloxane mixed with a surfactant and/or a hydrophilic solvent.

The above-mentioned surfactants contribute to improving particularly the cleaning and dewatering property, and suitable surfactants to be applied to the invention include: anionic surfactants such as polyoxyalkylene alkylether sulfonates and phosphoric esters; nonionic surfactants such as polyalcohol fatty acid esters, polyoxyalkylene fatty acid esters, and polyoxyalkylene alkylethers; amphoteric surfactants such as imidazolin derivatives; and cationic surfactants such as alkylamine salts, alkyl quaternary ammonium salts. In addition thereto, terpene containing compounds which are rarely present in the form of a single substance and extracted from natural substances as well as higher fatty acid esters may also be applied. It is also possible to use synthetic compounds in which part of the chemical structure of each compound is substituted by a fluorine or silicon atom. However, it is more preferable to use nonionic surfactants if the effect as a dewatering cleaning agent used in combination with the low molecular weight polyorganosiloxane is to be further improved.

While the composition ratio of the surfactant is not particularly limited, it is desirable to have 20 parts by weight or less, or, more preferably, 3 parts by weight or less, of the surfactant to 100 parts by weight of low molecular weight polyorganosiloxane.

A suitable hydrophilic solvent may be one compatible with the low molecular weight polyorganosiloxanes, and more particularly, one whose flash point is 40°C or more from the

20 FEB 1997

practical viewpoint. The hydrophilic solvent contributes to improving substituting property by water.

Suitable hydrophilic solvents include: polyalcohols and their derivatives such as ethylene glycol monomethyl ethers, ethylene glycol monoethyl ethers, ethylene glycol monopropyl ethers, ethylene glycol monobutyl ethers, ethylene glycol monobutyl ether acetates, diethylene glycol monobutyl ethers. Particularly preferable are diethylene glycol monobutyl ethers from the viewpoint of its compatibility with the low molecular weight polyorganosiloxanes and safety to the human body and the like. Since these compounds exhibit improved properties when coexisting with the low molecular weight polyorganosiloxanes, a composition only using this combination may allow substitution by water and drying.

While the composition ratio of the hydrophilic solvent is not particularly limited, it is preferable to have 100 parts by weight or less or, more preferably, 50 parts by weight or less of the hydrophilic solvent mixed with 100 parts by weight of the low molecular weight polyorganosiloxane.

The dewatering cleaning agents of the invention may be applied to metals, ceramics, plastics, and the like. More specifically, they may be applied to metallic parts, surface treated parts, electronic and semiconductor parts, electric and precision machinery parts, optical parts, glass and ceramic parts, and the like. An exemplary general-purpose cleaning process usually involves immersing of any of the above-described parts or spraying a dewatering cleaning agent of the invention onto the part to substitute it by water and drying by blowing hot air and the like. The immersing and spraying processes may be accompanied by an ultrasonic process and mechanical stirring.

The dewatering cleaning agents of the invention, exhibiting a powerful dewatering property, can not only provide cleaning and water-substituting effects equivalent to those of conventional cleaning agents containing flon and the like but also allow various materials to be stably cleaned with their low eroding action. In addition, containing no element halogen such as chlorine and bromine in general, the dewatering cleaning agents of the invention have few risk of destroying or polluting the environment. Thus, it can be said that the dewatering cleaning agents of the

invention will be a viable replacement for the conventional organic solvent containing dewatering cleaning agents such as flon, which have been imposing the environmental problems.

Brief Description of the Drawings

Fig. 1 is a diagram showing an exemplary construction of a cleaning system using a dewatering cleaning agent of the invention.


Detailed Description of the Preferred Embodiments


The invention will now be described with reference to examples in which a cleaning composition of the invention is applied to water system cleaning agents.

Example 1


Two kinds (A1 and A2) of polyoxyalkylene group containing polyorganosiloxane, each represented by formula (V) and (VI), were prepared.

A1:





A2:



Then, the polyoxyalkylene denatured silicone (A1) represented by formula (V), polyoxyalkylene denatured silicone (A2) represented by formula (VI), sodium laurate (B1) and polyoxyethylene octylphenyl ether (B2) (20 moles of polyoxyethylene), both serving as surfactants, and water were weighed so that their ratio by weight will be 5 : 5 : 4 : 4 : 82. Thereafter, these components were charged into a homogenizing mixer for blending to obtain a water system cleaning composition P1.

Example 2

The polyoxyalkylene group containing polyorganosiloxane (A1), the sodium laurate (B1) and polyoxyethylene octylphenyl ether (B2), both serving as surfactants, and water were weighed so that they satisfy the composition ratio specified in Table 1. Then, a water system cleaning composition P2 was obtained as in Example 1.

Examples 3 to 5

The polyoxyalkylene group containing polyorganosiloxanes (A1) and (A2), dioctyl sodium sulfosuccinate (B3) that serves as a surfactant in addition to the surfactants (B1) and (B2) octamethyl tetrasiloxane (D1) and octamethyl trisiloxane (D2), both as low molecular weight

20 FEB 1997

polyorganosiloxanes, and water were selectively mixed to prepare water system cleaning compositions P3 to P5 having composition ratios specified in Table 1 in the same manner as that in Example 1.

Comparative examples 1 to 3

Three kinds of water system cleaning compositions were prepared in a manner similar to that of each of the above examples except that no polyoxyalkylene group containing polyorganosiloxane was mixed.

The properties as a cleaning agent were evaluated as to the water system cleaning compositions of Examples 1 to 5 and Comparative examples 1 to 3 by the following methods. The result is also shown in Table 1.

(1) Penetration test

Measurements were made based on the JIS-specified canvas method. The smaller value means better penetrating property; i.e., the composition is more effective *in* cleaning smaller parts.

(2) Cleaning property test

A sample is prepared by applying a spindle oil over a steel strip and baking it at 135°C for 48 hours. The property is evaluated by the time spent for cleaning the oil baked on the sample (by ultrasonic cleaning). The smaller the value is, the better the cleaning property becomes.

(3) Stability test


Each composition was contained in a transparent bottle of 200 ml sealed thereafter and then heated at 50°C for 6 hours. After being gradually cooled from 50 to 25°C, its appearance in the bottle is observed.

Table 1

Composition ratio (wt.%)	Examples										Comparative Examples		
	1	2	3	4	5	1	2	3			1	2	3
Polyoxyalkylene	A1	5	0.5	1.0	-	10	-	-	-	-	-	-	-
Denatured silicone	A2	5	-	-	1.0	-	-	-	-	-	-	-	-
Surfactant	B1	4	0.8	0.3	0.3	4	1.2	0.8	0.8	0.8	0.8	0.8	0.8
	B2	4	0.7	0.4	0.5	-	0.8	0.7	0.7	0.7	0.7	0.7	0.7
	B3	-	-	-	-	0.5	-	0.5	-	-	-	0.5	-
Water		82	98	98	98	82	98	98	98	98	98	98	98
Low molecular weight	D1	-	-	-	0.2	3.5	-	-	-	-	-	-	0.5
Polyorganosiloxane	D2	-	-	0.3	-	-	-	-	-	-	-	-	-
Evaluation result	7	8	4	3	2	25	22	22	18				
penetrability (Canvas method, in second													
Cleaning property (in minute) stability													
	14	14	12	11	7	22	23	17					
	ST	ST	ST	ST	ST	ST	ST	ST	SEP				

Note: ST: stable

SEP: separated



As is apparent from the result shown in Table 1, the water system cleaning agent of the invention exhibits excellent cleaning capability and penetrability, attesting to its availability as a replacement for the conventional solvent based cleaning agents containing flon and the like. With its stability, it is considered a highly practical product. In contradistinction thereto, the water system cleaning agents according to Comparative examples were satisfactory neither in cleaning capability nor in penetrability.

An exemplary process employed to clean a specific part using a water system cleaning agent of the invention will now be described.

Example 6

In fabricating a liquid crystal device, a liquid crystal cell is evacuated to a high vacuum degree and a liquid crystal material is sealed in a device. In this case, the evacuation is carried out by a high performance diffusion vacuum pump. Since the diffused oil enters into the vacuum system in the form of mist, the pump must be cleaned often to remove the oil.


In this example, the water system cleaning agent of the invention was used in lieu of a conventional triethane cleaning agent.

A pump part made of a stainless steel SUS304 and a Ni-plated stainless steel SUS304 material having an adhesion of Silicon Oil F-4 (trademark of Shinetsu Chemical) as a diffusion oil was cleaned.

The composition ratio of the used water system cleaning agent is as shown below.

That is, in 80 wt.% of ion-exchanged water being sufficiently stirred at ambient temperature, 6 wt.% of the polyoxyalkylene group containing polyorganosiloxane having the following chemical structure was gradually added to obtain an achromatic translucent homogenous solution.

20 FEB 1997




On the other hand, as a surfactant, a mixture of 8 wt.% of special nonionic Adecanol B-4001 (trademark of Asahi Electrochemical) and 6 wt.% of anionic TWA-2023 (trademark of Ipposha Oil and Grease) of sulfuric acid ester PURLONIC structure was added to the above water/siloxane solution.

After diluting the water system cleaning agent thus obtained was diluted by ion-exchanged water at an arbitrary ratio, Silicone Oil F-4 was cleaned using the diluted cleaning agents. As a result, the pump part was satisfactorily cleaned: through immersion by stirring for 1 minute in a 1/10 diluted cleaning agent at ambient temperature; through immersion by oscillating for 1 minute in a 1/30 diluted cleaning agent at 40°C or through 1 minute ultrasonic cleaning at 20°C in the same cleaning agent; and through 1 minute ultrasonic cleaning in a 1/50 diluted cleaning agent at 50°C, respectively.

For comparison, the pump part was similarly cleaned with compositions containing only surfactant(s) and no polyoxyalkylene group containing polyorganosiloxane. Silicone Oil was not removed sufficiently with 10 or more minute immersion ultrasonic cleaning in a 1/10 diluted composition at ambient temperature. To remove Silicone Oil with this composition, it took more than 5 minutes at 65°C or more.

It is understood from this data that the cleaning agent that incorporates the polyoxyalkylene group containing polyorganosiloxane of the invention exhibits an outstanding cleaning property.



Example 7

20

The polyoxyalkylene group containing polyorganosiloxanes and the low molecular weight polyorganosiloxanes of the invention contribute to significantly improve the cleaning capability of commercially available water-soluble cleaning agents.

An aqueous solution of Chemiclean MS-109 (trademark of Sanyo Kasei Kogyo), which is a surfactant containing, low foaming, rust preventive cleaning agent, is typically used to clean mechanical and metallic parts. Blending 3 wt.% of the polyoxyalkylene denatured silicon (A1) represented by formula (V) in Example 1, 5 wt.% of cyclic hexamethylcyclotrisiloxane, 17 wt.% of ionexchanged water with 65 wt.% of the above aqueous solution, a new cleaning composition was prepared.

This new cleaning composition was 1/20 diluted by ionexchanged water and its cleaning property was evaluated by the following method. The result is shown in Table 2, For comparison, the evaluation result of 1/20 diluted Chemiclean MS109 was also shown.


Test Method

(1) Cleaning test - 1

The following contaminants were applied to a degreased aluminum plate (AC-4A) by immersing, dried by blowing, and immersed while stirred (400 rpm) in respective cleaning agents (1/20 diluted) for 15 seconds to 1 minute. Then, after immersed in water, the aluminum plate was dried by blowing. Each contaminant was transferred on white paper through an adhesive tape for reflectance measurement by a colorimeter thereby to calculate the cleaning rate.

Contaminant:

Spindle oil	78%
Fatty acid ester	15%
Chlorinated paraffin	5%



Carbon black 2%

Cleaning rate (%) = $R_w - R_s / R_o - R_s$

R_o : Reflectance of the original white paper

R_s : Reflectance of the standard contaminated plate

R_w : Reflectance of the contaminated plate after cleaned

(2) Cleaning test - 2

A contaminant was prepared by adding 2% of carbon black to a water-soluble machining oil (emulsive), and the test was performed in a manner similar to that of Cleaning test - 1. Its cleaning rate was similarly calculated.

Table 2

	Immersion time (second)	Cleaning rate (%)	
		Invention	MS-109
Cleaning test - 1	15	72.4	59.0
	30	86.5	65.2
	60	100.0	67.8
Cleaning test - 2	15	81.7	58.0
	30	93.8	71.0

Similar tests were conducted on EP-680 (trademark of B.P. Japan) which is a commercially available supereffective cleaning solution and water system cleaning agent; Banrise D-20 (trademark of Joban Chemical Industries) which is an emulsive degreased cleaning agent; and Hikari Ace (trademark of Shoko Trade) which is a powerful special cleaning agent. As a result, these cleaning agents, when used in combination of the polyoxyalkylene group containing polyorganosiloxane and the low molecular weight polyorganosiloxane of the invention, exhibited a significantly improved cleaning property.

20 FEB 1997


Example 8


The water system cleaning agent of the invention exhibits remarkable effect on cleaning of fluxes used in mounting electronic parts on printed boards. The flux comes roughly in two types: rosin containing and water-soluble. A specific example of cleaning rosin containing fluxes, which is said to be a difficult task, will now be described.

As a step prior to soldering a part on a printed board, a WW rosin ester was put on a part and immersed in a solder bath at 230 to 250°C and then the part was mounted. It was observed that the flux was completely removed when the printed board was shower-rinsed for 35°C for 45 seconds using a water system cleaning agent described below.

The water system cleaning composition used here is prepared by blending 2 wt. % of the polyoxyalkylene group containing polyorganosiloxane represented by formula (VII), 3 wt.% of Senkanol FM (trademark of Nippon Senka), which is an amphoteric surfactant, 5 wt.% of Nikkol CMT-30 (trademark of Nippon

Surfactant), which is a sodium-N-COCOIL methyl taurine containing nonionic surfactant, and adding ion-exchanged water to prepare 100 wt.% of the composition.





When acceleration aging tests which guarantees US MIL-F14256C standard, surface insulation resistance tests, ion residual tests and the like were conducted on the above composition which was 1/10 diluted by ion-exchanged water, the results were satisfactory.

Examples in which cleaning compositions of the invention were applied to dewatering cleaning agents will now be described.

Examples 9 to 17

Octamethyltrisiloxane (E1), octamethyltetrasiloxane (E2), and decamethylpentasiloxane (E3) were prepared as low molecular weight polyorganosiloxanes; polyoxyethylene oleyl ether (F1) (P.O.E = 6 moles), and polyoxyethylene octylphenyl ether (F2) (P.O.E. = 10 moles) as surfactants; and diethylene glycol monobutyl ether (G1) as a hydrophilic solvent were prepared.

These components were selected and blended so that the composition ratio shown in Table 3 were satisfied to obtain respective dewatering cleaning agents.


Comparative examples 4 to 8

Flon 113, methylene chloride, isopropyl alcohol, and ethanol were prepared as conventional dewatering cleaning agents to obtain 5 types of dewatering cleaning agents whose composition ratios were as shown in Table 3.

The properties of Examples 9 to 17 and Comparative examples 4 to 8 were evaluated by the following methods. The result is also shown in Table 3.

(1) Dewatering property

Various pieces (a stainless steel strip, a ceramic piece, a polycarbonate piece, a Ni-plated steel strip) were immersed in each dewatering cleaning agent after washed by water. In examples 13 to 15, each piece was then rinsed by the low molecular weight polyorganosiloxane blended to prepare each dewatering cleaning agent. Thereafter, each piece was dried in an oven at 50°C. The



water marks (a stain by impurities dissolved in water) after drying each piece was observed visibly and by a scanning electron microscope and evaluated in accordance with the following criteria.

XX: Not evaluable due to erosion of the piece during dewatering.

X: Water marks were visibly observed.

o: No water marks were visibly observed.

⊙: No water marks whose size is 50 μm or more were observed by the scanning electron microscope.

(2) Continuous dewatering property

A continuous dewatering test with a frequency of 50 times were conducted on a stainless steel strip and the appearance of the strip was evaluated in a manner similar to that of item (1).

(3) Drying property

The stainless steel strip was immersed in each dewatering cleaning agent and dried in the oven at 50°C. During the drying process, the strip was touched by a finger to see the drying condition every 5 minutes and the time required for drying was recorded on a 5-minute basis.

Table 3


Examples

Comparative Examples

Composition ratio (Parts by weight)	9	10	11	12	13	14	15	16	17	4	5	6	7	8
Low molecular weight	E1	100	-	50	100	-	-	-	-	-	-	-	-	-
Polyorganosiloxane	E2	-	100	50	50	100	100	100	-	50	-	-	-	-
	E3	-	-	50	-	-	-	-	100	-	-	-	-	-
Surfactant	F1	-	-	-	0.3	0.3	-	-	-	-	-	-	-	-
	F2	-	-	-	-	-	0.2	-	-	-	-	-	-	-
Hydrophilic solvent	C1	-	-	-	-	-	-	10	20	-	-	-	-	-
Methylene chloride	-	-	-	-	-	-	-	-	-	50	100	-	-	-
Freon 113	-	-	-	-	-	-	-	-	-	-	-	100	96	-
Ethanol	-	-	-	-	-	-	-	-	-	-	-	-	4	-
Isopropyl alcohol	-	-	-	-	-	-	-	-	-	-	-	-	-	100
Stainless steel	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	○	○	⊙	⊙	⊙
Dewatering property														
Ceramics	○	○	○	○	⊙	⊙	⊙	⊙	⊙	x	x	○	⊙	⊙
Polycarbonate	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	xx	xx	⊙	⊙	xx*
Ni plated strip	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	⊙	xx	xx	⊙	⊙	⊙

	Comparative Examples															
	Examples	9	10	11	12	13	14	15	16	17	4	5	6	7	8	
Continuous dewatering property	①	①	①	①	①	①	①	①	①	①	0	0	①	①	①	
Drying property (50°C in oven in minute)	10	5	5	10	10	10	5	5	10	15	5	5	<5	<5	<5	

Note: * Solvent cracks occurred.



20 FEB 1997

As is apparent from the result shown in Table 3, the dewatering cleaning agents of the invention, exhibiting satisfactory dewatering property, can be a viable substitute for organic solvent containing flon and the like based cleaning agents.

Dewatering cleaning agents containing methylene chloride or isopropyl alcohol (Comparative examples 4 and 5) rust and erode metal films and plastics. In contradistinction thereto, the dewatering cleaning agents of the invention are stable to metal films and plastics and exhibit satisfactory dewatering property even to ceramics which have large surface roughness values, thereby ensuring their reliability when applied to parts including metal, plated, electronic, semiconductor, plastic, and ceramic parts. The dewatering cleaning agent containing isopropyl alcohol permitted water to be dissolved therein, thereby causing water to present on the part again.


Moreover, it is understood that mixing of surfactants and hydrophilic solvents with the dewatering cleaning agents of the invention improved the dewatering property, thereby attesting to their industrial applicability.

An exemplary cleaning system using a dewatering cleaning agent of the invention will now be described with reference to Fig. 1.

A cleaning system shown in Fig. 1 consists roughly of a cleaning /water-substituting process A and a rinsing/dewatering process B.

The cleaning/water-substituting process A, which is the first process involves a first cleaning vessel 1 and a second cleaning vessel 2, each serving both as a separator through sedimentation and a separator through overflow, and a dewatering vessel 3. The first and second cleaning vessels 1 and 2 communicate with each other through a drain line 2a and an overflow line 2b. The first and second cleaning vessels 1 and 2 are operated together with ultrasonic, oscillating, mechanical stirring, cleaning agent heating, and brushing processes and the like if necessary.

The first and second cleaning vessels 1 and 2 respectively contain a cleaning agent D1 composed of a low molecular weight polyorganosiloxane and a surfactant, which is one of the dewatering cleaning agents of the invention. The surfactant containing cleaning agent D1 may be so prepared that its specific gravity is smaller than that of water and larger than that of an oily stain.



Therefore, water Y introduced by an object to be cleaned X is separated by being sedimentated at the bottom of the surfactant containing cleaning agent D1 that has been charged in the first and second cleaning vessels 1 and 2. If an oily stain Z is present on the object X, the oily stain Z is separated by floating upward in the surfactant containing cleaning agent D1 in the first and second cleaning vessels 1 and 2.

The water Y separated by being sedimentated in the second cleaning vessel 2 is intermittently discharged to the first cleaning vessel 1 through a drain line 2a while the water Y separated by being desimentated in the first cleaning vessel 1 is intermittently discharged to a cleaning agent recycling mechanism C (described later) through a drain line 4. A drain line 3a connected to the drainage vessel 3 is also connected to the cleaning agent recycling mechanism C.

The oily stain Z separated by floating in the first and second vessels 1 and 2 is discharged outside while continuously overflowed through an overflow line 5 connected to the first cleaning vessel 1.

The surfactant containing cleaning agent D1 charged in the first and second cleaning vessels 1 and 2 is continuously circulated through a filter 6 that serves to remove solid particles, H₂O particles, undissolved substances and the like contained in the cleaning agent D1.

The rinsing/dewatering process B, which is the second process, involves a third cleaning vessel 7 and a shower rinse vessel 8. Below the shower rinse vessel 8 is a buffer tank 9 that communicates with the third cleaning vessel 7 through a drain line 9a and an overflow line 9b. The third cleaning vessel 7 is also operated together with ultrasonic, oscillating, mechanical stirring, cleaning agent heating, and brushing processes and the like, if necessary.

The third cleaning vessel 7 contains a cleaning agent D2 consisting only of a silicone composition identical to the low molecular weight polyorganosiloxane used in the first process A. The cleaning agent D2 may be so prepared that its specific gravity is smaller than that of water and larger than that of an oily stain. Therefore, as in the first process A, water Y is separated by being sedimentated at the bottom of the cleaning agent D2 and the oily stain Z is separated by floating upward in the cleaning agent D2.

20 FEB 1997

The water Y separated by being sedimentated in the third cleaning vessel 7 is intermittently discharged to the cleaning agent recycling mechanism C through a drain line 10 while the oily stain Z separated by floating in the third cleaning vessel 7 is discharged outside through an overflow line 11.

The cleaning agent D2 charged in the third cleaning vessel 7 is continuously circulated through a filter 12 that serves to remove solid particles, H₂O particles, undissolved substances, and the like contained in the cleaning agent D2.

The object to be cleaned X undergoes the first process A and then the second process B, cleaned and dewatered, and then dried by a fan forced drier (not shown) to complete the cleaning process.

The cleaning agent used in the cleaning system is subjected to the following recycling process.

As described above, the drain lines 4, 3a, 10 of the first, second, and third cleaning vessels 1, 2, and 7, and the dewatering vessel 3 are connected to the cleaning agent recycling mechanism C. The cleaning agent D1 or D2 contained in each cleaning vessel is constantly cleaned by the filters 6 and 12. However, when heavily contaminated, the cleaning agent is introduced to the cleaning agent recycling mechanism C through drain lines 4 and 10 by a conveyer pump 13 for fractional distillation. The cleaning agent D1 deposited in the dewatering vessel 3 is also supplied intermittently to the cleaning agent recycling mechanism C.

At the cleaning agent recycling mechanism C, the introduced cleaning agent is separated into liquid components and solid components by a filter 14, and only the liquid components are forwarded to a distiller 15 with the solid components being destroyed. The distiller 15 separates various components, water, oily stains in the cleaning agent utilizing the difference in their boiling points. Water and the like that remain in the distiller 15 are further separated by a decanter 16.

Since the cleaning agent D1 is an agent having a surfactant added to the cleaning agent D2 that contains only the low molecular weight polyorganosiloxane, the low molecular weight

20 FEB 1997

polyorganosiloxane, i.e., the cleaning agent D2, can be extracted from both cleaning agents D1 and D2, thereby allowing the cleaning agent D2 to be recycled. The components other than the recycled cleaning agent D2, i.e., the surfactant, water, and the like will be destroyed.

The recycled cleaning agent D2 is forwarded to a mixer 18 from which the cleaning agent D1 is supplied to the shower rinse vessel 8, the third cleaning vessel 7, or the second cleaning vessel 2 through a line 17.

In the shower rinse vessel 8, a shower rinsing process is conducted using only the recycled cleaning agent D2 or a cleaning agent D2 newly introduced through a cleaning agent supply line 19, both being free from impurities.


The mixer 18 mixes the recycled or new cleaning agent D2 with the surfactant newly supplied from a surfactant supply line 20 to prepare a new cleaning agent D1. The new cleaning agent D1 is supplied to the second cleaning vessel 2, if necessary.

With the cleaning system of such construction as described above, the dewatering cleaning agents of the invention can be used efficiently and effectively enjoying the advantage of excellent cleaning properties.

Industrial Applicability

As described in the foregoing pages, the cleaning compositions of the invention, when used as water system cleaning agents, exhibit a cleaning effect equivalent to that of conventional flon containing cleaning agents and an excellent stability as a water system with no risk of environmental destruction and pollution, thereby making a viable replacement for the organic solvent based cleaning agents including flon and the like which have environmental disadvantages. In addition, the cleaning compositions of the invention, when used as dewatering cleaning agents, provide a powerful dewatering property with no risk of environmental destruction and pollution, thereby serving a viable replacement for the organic solvent based dewatering cleaning agents including flon and the like which have environmental disadvantages.


CLAIMS:



31




A non-aqueous cleaning composition capable of cleaning an object, the composition comprising at least one low molecular weight polyorganosiloxane of formula (II):




(wherein R¹ is an organic group of single valence substituted by the same or different group or unsubstituted, and m is an integer from 3 to 7).


2. A non-aqueous cleaning composition according to claim 1, consisting essentially of said low molecular weight polyorganosiloxane of formula (II).
3. A non-aqueous cleaning composition according to claim 2, further comprising a surfactant and/or a hydrophilic solvent.
4. A non-aqueous cleaning composition according to claim 3, comprising at least said surfactant, the surfactant being selected from anionic surfactants, nonionic surfactants, amphoteric surfactants, and cationic surfactants.
5. A non-aqueous cleaning composition according to claim 4, wherein the surfactant is an anionic surfactant selected from polyoxyalkylene alkylether sulphonates and phosphoric esters.
6. A non-aqueous cleaning composition according to claim 4, wherein the surfactant is a nonionic surfactant selected from polyalcohol fatty acid esters, polyoxyalkylene fatty acid esters and polyoxyalkylene alkylethers.



7. A non-aqueous composition according to claim 4, wherein the surfactant is an imidazoline derivative amphoteric surfactant.
8. A non-aqueous cleaning composition according to claim 4, wherein the surfactant is a cationic surfactant selected from alkylamine salts and alkyl quaternary ammonium salts.
9. A non-aqueous cleaning composition according to claim 4, wherein the surfactant is a terpene-containing compound or a higher fatty acid ester.
10. A non-aqueous cleaning composition according to any of claims 4-9, wherein the amount of the surfactant is 20 parts by weight or less relative to 100 parts by weight of the polyorganosiloxane of formula (II).
11. A non-aqueous cleaning composition according to any of claims 4-9, wherein the amount of the surfactant is 3 parts by weight or less relative to 100 parts by weight of the polyorganosiloxane of formula (II).
12. A non-aqueous cleaning composition according to claim 3, wherein said hydrophilic solvent has a flash point of 40°C or more.
13. A non-aqueous cleaning composition according to claims or claim 12, comprising at least said hydrophilic solvent, the hydrophilic solvent being selected from polyalcohols and their derivatives.
14. A non-aqueous cleaning composition according to claim 13, wherein the hydrophilic solvent is selected from polyalcohols and their derivatives selected from ethylene glycol monomethyl ethers, ethylene glycol monoethyl ethers, ethylene glycol monopropyl ethers, ethylene glycol monobutyl ethers, ethylene glycol monobutyl ether acetates and diethylene glycol monobutyl ethers.



15. A non-aqueous cleaning composition according to claim 13 or claim 14, wherein the amount of the hydrophilic solvent is 100 parts by weight or less relative to 100 parts by weight of the polyorganosiloxane of formula (II).
16. A non-aqueous cleaning composition according to any of claims 13-15, wherein the amount of the hydrophilic solvent is 50 parts by weight or less relative to 100 parts by weight of the polyorganosiloxane of formula (II).
17. A method of cleaning an object, the method comprising treating the object with a non-aqueous cleaning composition according to any preceding claim.
18. A method according to claim 17, wherein the object to be cleaned comprises at least one material selected from a metal material, a ceramic material and a plastics material.
19. A method according to claim 18, wherein the material is in the form of at least one part selected from a metallic part, a surface-treated part, an electronic part, an electrical part, a semiconductor part, a precision machinery part, an optical part, a glass part, a ceramic part and a plastic part.
20. A method according to any of claims 17-19, wherein the step of treatment with said non-aqueous cleaning composition involves immersion of the object in, or spraying the object with, the non-aqueous cleaning composition.
21. A method according to claim 20, wherein the immersion or spraying process in the treatment step are accompanied by ultrasonic agitation and mechanical stirring.
22. A method according to any of claims 17-21, further comprising the step of drying the object after the step of treatment with said non-aqueous cleaning composition.
23. A method according to any of claims 17-22, further comprising the steps of:



a cleaning step of dewatering and cleaning an object to be cleaned by a cleaning vessel containing the non-aqueous cleaning composition of formula (II), and

a rinsing step of rinsing and cleaning said object to be cleaned after the dewatering and cleaning by a plurality of rinsing cleaning vessels in sequence, each of the rinsing cleaning vessels containing a rinsing cleaning agent, the rinsing cleaning vessels being connected such that said rinsing cleaning agent is transmitted in sequence in the direction opposite to that of transmitting said object to be cleaned,

wherein said rinsing step is conducted while a rinsing cleaning waste liquid is recovered from the most downstream rinsing cleaning vessel of said plurality of rinsing cleaning vessels, the recovered rinsing cleaning waste liquid is distilled so as to be recycled, and the recycled rinsing cleaning agent is re-supplied to the most upstream rinsing cleaning vessel.

24. A method according to claim 23, wherein said rinsing cleaning waste liquid is filtered as a pre-treatment for the distillation.

25. A method according to claim 23, wherein the cleaning waste liquid of the cleaning step is recovered from the cleaning vessel and the recovered cleaning waste liquid is distilled to recycle said low molecular weight polyorganosiloxane of formula (II).


CLEANING COMPOSITIONS

REPLACEMENT SHEET


20 FEB 1997

ABSTRACT OF THE DISCLOSURE


A cleaning composition comprising at least one low molecular weight polyorganosiloxane selected from the group consisting of straight chain polydiorganosiloxane represented by a general formula:



(wherein R^1 is an organic group of single valence substituted by the same or different group or unsubstituted, and 1 is an integer from 0 to 5), and cyclic polydiorganosiloxane represented by a general formula:



(wherein R^1 is an organic group of single valence substituted by the same or different group or unsubstituted, and m is an integer from 3 to 7). To use it as a water system cleaning agent, polyoxyalkylene group containing polyorganosiloxane, a surfactant, and water are additionally mixed. Accordingly, a cleaning effect free from environmental destruction and contamination, equivalent to flon containing cleaning agents, and satisfactorily stable in terms of dispersion as a water system cleaning agent can be obtained. In addition, to use as a dewatering cleaning agent, the low molecular weight polyorganosiloxane is additionally mixed alone or with a surfactant and/or a hydrophilic



solvent. Accordingly, cleaning and water substituting properties equivalent to flon containing dewatering agents and environmental safety can be obtained.

