



159159

VEHICLE FOR APPLYING CHEMICAL COMPOUNDS ON WOOD

FIELD OF THE INVENTION

This invention is generally related to the treatment of
5 woods by means of applying chemical compounds. The invention
specifically refers to a vehicle that is useful for applying
chemical compounds on woods.

BACKGROUND OF THE INVENTION

Various harmful biological agents are known that are
10 capable of attacking wood, causing significant damage. Among
said biological agents harmful for wood are insects, for
example beetles (a term which includes various species of
wood-eating insects whose larvae gnaw and bore wood),
termites, moths, etc., and fungi, for example *Poria vaillantii*
15 Fr., *Coniophora cerebella* Duey, *Merulius lacrymans* Wulf,
Lentinus lepideus Fr., *Lenzites sepiaria* Wulf, *Chaetomium*
globosum Kunz, etc.

The products normally used for treating and conserving
wood generally comprise one or more active substances that are
20 effective against the harmful biological agents to be
eliminated, for example one or more insecticides and/or
fungicides, and a vehicle for introducing said active
substances into the tunnels and cavities generated in the wood
by the action of said harmful biological agents.

25 The number of vehicles that are effective as active
substance carriers inside the wood is currently very limited.
Among those vehicles normally used in products for treating
and conserving wood are water, inorganic arsenic derivatives,
pentachlorophenol and creosote.

30 Water is the most commonly used carrier. However, it
scarcely penetrates the wood, so the active substances applied
to the wood using said vehicle therefore do not suitably
penetrate it, remaining on the surface, thereby significantly
reducing the effectiveness of said active substances.

35 The other vehicles have a very slight wood penetration



G00002

index, generally comprised between 2 and 6 mm after 24 hours. In soft and porous woods, penetration indices of the vehicle of up to 6 mm are obtained, whereas in hard and not porous woods, the vehicles penetrate between 2 and 3 mm during a 24
 5 hour time period.

Therefore, there is a necessity to find new vehicles that are useful for applying chemical compounds on woods which advantageously have a high wood penetration index.

The invention provides a solution to the existing
 10 necessity that comprises the development of a new vehicle for applying chemical compounds on woods, comprising a mixture of several components. Said vehicle has a high wood penetration index, determined by means of a trial comprising the application of the vehicle at a point on the wood, allowing
 15 the vehicle to act for a period of time, and determining the advance of the vehicle front by means of cutting the wood and measuring the advance of the vehicle front.

A vehicle such as the one provided by this invention is useful for treating woods, specifically for treating and
 20 preventing damage caused by the attack of biological agents that are harmful for wood.

An object of this invention is constituted of said vehicle for applying chemical compounds on woods.

An additional object of this invention is constituted of
 25 a composition comprising said vehicle together with at least one chemical compound.

Another additional object of this invention is constituted of a method for treating wood, comprising applying said composition in a sufficient quantity to the wood to be
 30 treated.

DETAILED DESCRIPTION OF THE INVENTION

The invention provides a vehicle that is useful for applying chemical compounds on woods, heretofore vehicle of the invention, comprising:

35 Components Percentage by weight regarding total (%)

	Toluene	40-70
	Xylene	6-40
	Benzophenone	3-18
	Butyl glycol	2-9
5	Cetyl acetate	1-7
	Methanol	0.3-4

All the components constituting the vehicle of the invention are commercial products. In the sense used in this description, the term "benzophenone" includes both
 10 benzophenone (diphenylmethanone) and the hydroxylated or methoxylated derivatives thereof [see for example The Merck Index, 11th Edition, 1989]. Likewise, the term "butyl" includes any of the butyl isomers.

In a particular embodiment, the vehicle of the invention
 15 has the following composition:

	<u>Components</u>	<u>Percentage by weight regarding total (%)</u>
	Toluene	64
	Xylene	16
	Benzophenone	10
20	Butyl glycol	5
	Cetyl acetate	4
	Methanol	1

The vehicle of the invention can be easily prepared by means of a process that comprises mixing the components in the
 25 desired proportions.

Several trials have clearly shown the high penetration index of the vehicle of the invention in different woods [see Example 1], it can therefore be used for applying chemical compounds on woods, for example, chemical compounds useful for
 30 treating woods, specifically for treating and preventing damage caused by the attack of biological agents that are harmful for wood [see Example 2].

The invention also provides a composition, heretofore composition of the invention, comprising at least one chemical
 35 compound and a vehicle of the invention. The vehicle of the

invention can be present in the composition of the invention in a widely variable quantity; for example, the composition of the invention may contain between 0.1 and 99.9% by weight of the vehicle of the invention, the rest being constituted of said compound or chemical compounds, in which case said chemical compounds can be present in any weight ratio that is suitable among them. The composition of the invention can be easily obtained by mixing the vehicle of the invention with said compound or chemical compound in the suitable weight ratio. The composition of the invention is in liquid form, for example in a solution or dispersion.

In a particular embodiment of the invention, the composition of the invention is a composition that is useful for treating wood, comprising one or more chemical compounds that are useful for treating wood, in addition to the vehicle of the invention. In another more specific embodiment of the invention, the composition of the invention is an insecticide and/or fungicide composition, useful for treating and/or preventing damage caused by insects and/or fungi which attack wood, comprising one or more insecticides and/or one or more fungicides, in addition to the vehicle of the invention. Among those insecticides and/or fungicides that may be present in the composition of the invention, the following are included: chlorpyrifos, fipronil, silafluofen, acetamiprid, etofenprox, tripropyl isocyanurate, fenobucarb, hexaflumuron, fenitrothion, esfenvalerate, imidacloprid, difluobenzuron, lambda-cyhalothrin, clothalonil, propiconazole and the mixtures thereof. In this case, the composition of the invention is useful for inhibiting the development of biological agents that are harmful for wood, such as insects, for example, beetles, termites, moths, etc., and fungi, for example, *Poria vaillantii* Fr., *Coniophora cerebella* Duey, *Merulius lacrymans* Wulf, *Lentinus lepideus* Fr., *Lenzites sepiaria* Wulf, *Chaetomium globosum* Kunz, etc.

The wood penetration index obtained with the composition

of the invention generally corresponds to that of the vehicle used. Said penetration index may vary, depending on the type of wood as well as the degree of humidity thereof.

The invention also provides a method for treating wood which comprises applying a composition of the invention to the wood to be treated in a sufficient quantity so as to obtain the desired effect. In the sense used in this description, the expression "applying a composition of the invention to the wood to be treated" includes applying the composition of the invention on the surface to the wood to be treated as well as introducing the composition of the invention, by any suitable means, into the tunnels and cavities generated in the wood by the action of, for example, harmful biological agents.

The following examples serve to illustrate the invention and must not be considered limiting for the scope thereof.

EXAMPLE 1

Determination of the wood penetration index of a vehicle

1.1 Materials and method

The method used for determining the wood penetration index of a vehicle consists of applying a determined quantity of the vehicle to be tested (between 3 and 10 ml) at a point (origin) of the surface of the wood, allowing the vehicle to act for a determined time period (between 1-23 minutes), and measuring the advance of the vehicle front by means of cutting the wood and measuring the advance of the vehicle front inside the wood from the origin.

The woods used were representative of a broad spectrum of woods, from very soft and porous woods to very hard and not porous woods. The woods that were specifically tested were the following: poplar, scots pine, walnut, cedar and beech wood. The woods were shaped into 20 x 7 x 7 cm pieces.

The vehicles tested were those whose compositions are described below. As the trials were being carried out and results were being obtained, the products were selected and

those which resulted to be ineffective for the desired objective were discarded. Thus the composition of the vehicle of the invention was obtained.

I. Combinations of 2 different components:

- 5 1) Ethylene glycol/toluene
 2) benzophenone-2/ethyl ether
 3) disodium phosphate/monoxinol-9
 4) butyl glycol/acetylene
 5) methanol/benzol
- 10 6) dodecyl diamino ethyl/xylene
 7) sodium sulphate/cetyl acetate
 8) sodium hydroxide/methylene chloride

For each combination, different concentrations were tested (in each case comprised between 0.5 and 80% by weight regarding the total) of each one of the components present in each combination. The remainder up to 100% was composed of the other component.

II. Combinations of 3 different components:

- 20
- 1) cetyl acetate/sodium hydroxide/monoxinol-9
 - 2) butyl glycol/ethyl ether/disodium phosphate
 - 3) acetylene/dodecyl diamino ethyl/toluene
 - 4) benzol/methylene chloride/sodium sulphate
 - 5) benzophenone-2/acetylene/monoxinol-9
 - 6) xylene/ethylene glycol/methanol

25 For each combination, different concentrations were tested (in each case comprised between 0.5 and 80% by weight regarding the total) of each one of the components present in each combination. The remainder up to 100% was composed of the other components.

30 III. Combinations of 4 different components:

- 1) ethyl ether/methanol/butyl glycol/sodium hydroxide
- 2) sodium sulphate/xylene/methylene chloride/ benzol
- 3) dodecyl diamino ethyl/cetyl acetate/disodium phosphate /acetylene
- 4) benzophene-2/ethylene glycol/monoxinol-9/toluene

5) xylene/ethylene glycol/methanol

For each combination, different concentrations were tested (in each case comprised between 0.5 and 80% by weight regarding the total) of each one of the components present in each combination. The remainder up to 100% was composed of the other components.

IV. Combinations of 5 different components:

- 1) methanol/acetylene/ethylene glycol/benzol/disodium phosphate
- 10 2) xylene/methylene chloride/dodecyl diamino ethyl/sodium sulphate/monoxinol-9
- 3) benzophenone-2/sodium hydroxide/methanol/cetyl acetate/ethyl ether
- 15 4) acetylene/disodium sulphate/butyl glycol/methylene chloride/toluene

For each combination, different concentrations were tested (in each case comprised between 0.5 and 80% by weight regarding the total) of each one of the components present in each combination. The remainder up to 100% was composed of the other components.

V. Combinations of 6 different compounds:

- 1) toluene/ethyl ether/ethylene glycol/methanol/monoxinol-9/acetylene
- 25 2) sodium hydroxide/cetyl acetate/sodium sulphate/xylene/dodecyl diamino ethyl/benzol
- 3) benzophenone-2/methylene chloride/disodium phosphate/butyl glycol/acetylene/sodium hydroxide
- 4) toluene/xylene/benzophenone-2/butyl glycol/cetyl acetate/methanol

30 For each combination, different concentrations were tested (in each case comprised between 0.5 and 80% by weight regarding the total) of each one of the components present in each combination. The remainder up to 100% was composed of the other components.

In general, the best results, expressed as the measurement (in mm) of the advance of the vehicle front, were obtained with a vehicle whose composition contained 6 different components, specifically with a composition of type V.4 composed of toluene, xylene, benzophenone-2, butyl glycol, cetyl acetate and methanol. Specifically, with a vehicle having Composition A: 64% toluene, 16% xylene, 10% benzophenone-2, 5% butyl glycol, 4% cetyl acetate and 1% methanol, where all the percentages are by weight regarding the total, the results that were obtained are included in Table 1.

Table 1
Penetration index (PI) of composition A
on different woods

Wood	Quantity (ml)	Time (min)	PI (mm)
Poplar	3	1	10
Poplar	6	2.5	15
Poplar	10	6	20
Scots pine	3	2	10
Scots pine	6	5	15
Scots pine	10	10	20
Walnut	3	6	10
Walnut	6	14	15
Walnut	10	20	20
Cedar	3	8	10
Cedar	6	17	15
Cedar	10	23	20
Beech	3	8	10
Beech	6	17	15
Beech	10	23	20

Further trials carried out with compositions containing one or more insecticides and/or fungicides together with a vehicle provided by this invention clearly showed that the

penetration index of the composition was the same as that of the vehicle [without active substance(s)].

EXAMPLE 2

Insecticide composition and effectiveness trials

5 An insecticide composition was prepared, heretofore Composition B, which exhibited the following composition:

Fenitrothion	25% (total weight/volume)
Esfenvalerate	2% (total weight/volume)
Vehicle*	remainder up to 100%

10 * The vehicle composition was the following: 64% toluene, 16% xylene, 10% benzophenone-2, 5% butyl glycol, 4% cetyl acetate and 1% methanol, where all the rates are by weight with regard to the total weight [corresponds to Composition A mentioned in Example 1].

15 The density of the insecticide composition was 0.9 g/ml.

The insecticide composition was obtained by adding fenitrothion and esfenvalerate, in suitable amounts, to the vehicle obtained previously by means of mixing its components in the suitable amounts.

20 In order to evaluate the effectiveness of said insecticide composition [Composition B], which contained a vehicle provided by this invention, the following trials were carried out:

2.1 Determination of the preventive effectiveness
25 against termites; and

2.2 Determination of the threshold of preventive effectiveness against termites

2.1 Determination of the preventive effectiveness against termites

30 2.1.1 Brushing

2.1.1.1 Materials and methods

The tested insecticide composition is Composition B. No solvent was used to dissolve the insecticide composition. Pure gelatin was used for clogging up to the heads of the test
35 tubes, as indicated by the standard.

The biological material used was *Reticulitermes lucifugus* Rossi.

The trial standard was UNE standard 56411:1992 (*Una Norma Española- A Spanish Standard*) (EN 118:1990) "Wood
5 protectors. Determination of preventive effectiveness against *Reticulitermes santonensis* of Feytaud. Laboratory method."

The trial was carried out on wood test tubes obtained from *Pinus sylvestris* L. originating from the Valsain mountain, in accordance with the requirements of the standard.

10 The minimum dose obtained by means of treatment by brushing, as indicated by the standard, was 43.05 ml/m².

2.1.1.2 Treatment

On the 10 March of 2000, the minimum possible amount of insecticide composition (43.05 ml/m²), with a tolerance of
15 $\pm 5\%$, was applied by brushing on one of the sides of the test tube, checking by means of weighing that the desired amount had been applied, thus obtaining the insecticide composition absorptions and retentions that are included in Table 2.

After treatment, the test specimen were left to dry and
20 were treated in an air conditioned chamber at a temperature of $20 \pm 2^\circ\text{C}$ and a relative humidity of $65 \pm 5\%$ for 7 weeks, prior to putting them in contact with the insect colonies. The termite colonies were put in contact with the test tube using a polyurethane foam on the 3 of May of 2000, and the test
25 apparatuses were placed in a chamber at a temperature of $27 \pm 2^\circ\text{C}$ and a relative humidity of $75 \pm 5\%$ for 8 weeks.

The final examination was carried out on the 26 of June of 2000. The attacks of the test tubes were evaluated as per the following scale:

- 30 0: No sign of attack
 1: Tentative attack
 2: Light attack
 3: Medium attack
 4: Strong attack

35 The results obtained are included in Table 2.

Table 2
Preventive effectiveness against termites (UNE 56411:1992)
Unaged test tubes. Brushed

Test specimen number	Tested doses				Examination results		Degree of attack
	Theoretical doses		Applied Doses		Survival		
	g/m ²	ml/m ²	g/m ²	ml/m ²	O (%)	S and N (n)	(0-4)
1	12.0-15.0	13.33-16.66	38.75	43.05	0	0-0	0
3			38.75	43.05	0	0-0	0
4			38.75	43.05	3	0-0	0
5			38.75	43.05	1	0-0	0
7			40.00	44.44	0	0-0	0
9			40.00	44.44	2	0-0	0
T1	Untreated samples		-	-	91	0-2	4
T2			-	-	96	1-2	4
T3			-	-	97	1-3	4

5 [O: workers; S: soldiers; N: nymphs; n: number]

The results obtained clearly show that the tested insecticide composition (Composition B) is effective against termites for surface treatments by means of a method providing a dose of approximately 43 ml/m² on the wood that is actually treated. To evaluate the possibility that the effectiveness threshold is below the tested dose (43 ml/m²), several trials were carried out using a treatment method based on spraying the insecticide composition on the wood to be treated.

2.1.2 Spraying

15

2.1.2.1 Materials and methods

The tested insecticide composition is Composition B. No solvent was used to dissolve the insecticide composition. Pure gelatin was used for clogging up to the heads of the test tubes, as indicated by the standard.

20

The biological material used was *Reticulitermes lucifugus* Rossi (the termite species conventionally existing

in Spain).

The trial standard was the UNE standard 56411:1992 (EN 118:1990) "Wood protectors. Determination of preventive efficacy against *Reticulitermes santonensis* of Feytaud. Laboratory method."

The trial was carried out on wood test specimen obtained from *Pinus sylvestris* L. originating from the Burgui mountain (Navarra), in accordance with the requirements of the standard.

The tested insecticide composition concentrations were the following: 13.33 ml/m² and 16.66 ml/m². The insecticide composition was applied by means of spraying.

2.1.2.2 Treatment

On the 20 of June of 2000, the indicated doses of insecticide composition, with a tolerance of $\pm 5\%$, were applied by spraying on one of the sides of the test specimen, checking by means of weighing that the desired amounts had been applied, thus obtaining the insecticide composition absorptions and retentions that are included in Tables 3 and 4.

After treatment, the test tubes were left to dry and were treated in an air conditioned chamber at a temperature of $20 \pm 2^\circ\text{C}$ and a relative humidity of $65 \pm 5\%$ for 10 weeks prior to putting them in contact with the insect colonies or aging them.

In order to age the test tubes, the latter were subjected to an aging trial by evaporation for 12 weeks, as per the methodology indicated in the UNE standard 56406:1992 [Wood protectors. Accelerated aging trials of treated woods prior to biological trials. Evaporation test].

The termite colonies were put in contact with the test specimen using a polyurethane foam on the 27 of July of 2000 (for the unaged test specimen) and on the 30 of October of 2000 (for the test specimen subjected to aging by evaporation), and the test devices were placed in a chamber at

a temperature of $27 \pm 2^\circ\text{C}$ and a relative humidity of $75 \pm 5\%$ for 8 weeks.

The final examination was carried out on the 24 of October of 2000 (for the unaged test specimen) and on the 2 of January of 2001 (for the test specimen subjected to aging by evaporation). The attacks of the test specimen were evaluated as per the following scale:

- 0: No sign of attack
- 1: Tentative attack
- 10 2: Light attack
- 3: Medium attack
- 4: Strong attack

The results obtained are included in Tables 3 and 4.

Table 3

15 Preventive effectiveness against termites (UNE 56411:1992)

Unaged test specimen. Spraying

Test specimen number	Tested doses				Examination results		Degree of attack (0-4)
	Theoretical doses		Applied doses		Survival		
	g/m ²	ml/m ²	g/m ²	ml/m ²	O (%)	S and N (n)	
1	12.0-15.0	13.33-16.66	16.16	17.95	0	0-0	0
3			14.98	16.64	0	0-0	0
4			15.05	16.72	0	0-0	0
5			13.75	15.27	0	0-0	0
7			16.33	18.14	0	0-0	0
9			15.03	16.70	0	0-0	0
TA	Untreated samples		-	-	83	1-1	4
TB			-	-	86	2-1	4
TB'			-	-	87	1-1	4

[O: workers; S: soldiers; N: nymphs; n: number]

Table 4
Preventive efficacy against termites (UNE 56411:1992)
Aged test specimen (EN 73). Spraying

5

Test specimen number	Tested doses				Examination results		Degree of attack (0-4)
	Theoretical doses		Applied doses		Survival		
	g/m ²	ml/m ²	g/m ²	ml/m ²	O (%)	S and N (n)	
1'	12.0-15.0	13.33-16.66	16.16	17.95	0	0-0	0
3'			14.98	16.64	0	0-0	0
4'			15.05	16.72	0	0-0	0
5'			13.75	15.27	0	0-0	0
7'			16.33	18.14	0	0-0	0
9'			15.03	16.70	0	0-0	0
TA'	Untreated samples		-	-	94	2-1	4
TB'			-	-	86	3-2	4
TB			-	-	91	2-1	4

[O: workers; S: soldiers; N: nymphs; n: number]

The results obtained clearly show that the tested insecticide composition (Composition B) is effective against termites for surface treatments by means of a method providing a dose between 13.33 and 16.66 ml/m² on the wood that is actually treated. Given that the product has shown to be effective at the lowest dose of 13.33 ml/m², it is likely that it is effective at doses that are lower than those specified.

2.2 Determination of the threshold of preventive effectiveness against termites

15

2.2.1 Materials and Method

The tested insecticide composition is Composition B.

The biological material used was *R. lucifugus* Rossi (the termite species normally existing in Spain).

20

The trial standard was the UNE standard 56410:1992 (EN

117:1990) "Wood protectors. Determination of the threshold of preventive efficacy against *Reticulitermes santonensis* of Feytaud. Laboratory method."

5 The trial was carried out on wood test specimen obtained from *Pinus sylvestris* L. originating from the Burgui mountain (Navarra), in accordance with the requirements of the standard.

To dilute the insecticide composition, xylene was used. The tested concentrations were the following: 0%, 0.01%,
10 0.023%, 0.045%, 0.065% and 0.085%.

2.2.2 Treatment

On the 16 of June of 2000, the impregnation of the test specimen was carried by atmospheric pressure vacuum, as indicated by the standard, thus obtaining the insecticide
15 composition absorptions and retentions that are included in Tables 5 and 6.

After treatment, the test specimen were left to dry and were treated in an air conditioned chamber at a temperature of $20\pm 2^{\circ}\text{C}$ and a relative humidity of $65\pm 5\%$ for 6 weeks prior to
20 putting them in contact with the insect colonies or aging them.

To age the test specimen, once the latter are treated, they are subjected to an aging trial by evaporation for 12 weeks, as per the methodology indicated in the UNE standard
25 56406:1992.

The termite colonies were put in contact with the test specimen by using a polyurethane foam on the 27 of July of 2000 (for the unaged test specimen) and on the 30 of October of 2000 (for the test specimen subjected to aging by
30 evaporation), and the test devices were placed in a chamber at a temperature of $27\pm 2^{\circ}\text{C}$ and a relative humidity of $75\pm 5\%$ for 8 weeks.

The final examination was carried out on the 18 of September of 2000 for the unaged test specimen and on the 2 of
35 January of 2001 for the test specimen subjected to aging by

evaporation. The attacks of the specimen were evaluated as per the following scale:

- 0: No sign of attack
- 1: Tentative attack
- 5 2: Light attack
- 3: Medium attack
- 4: Strong attack

The results obtained are included in Tables 5 and 6. These results clearly show that the tested insecticide composition (Composition B) is effective against termites for deep treatments by a process providing a retention of approximately 0.04 kg/m³ on the wood that is actually impregnated. Given that the product has proven to be effective at the lowest dose (0.01%), it is likely that the effectiveness threshold is below the specified retention.

Table 5
Threshold of preventive efficacy against termites (UNE 56410:1992)
Unaged test specimen

Tested concentrations (%)	Test specimen no.	Solution discharge ($m_1 - m_0$) (g)	Product retention		Visual examination (0-4)	Surviving termites		
			Test specimen (kg/m^3)	Mean (kg/m^3)		O (%)	S (n)	N (n)
Xylene (0)	X ₂	7.65	0	0.00	4	228	2	1
	X ₃	8.01	0		4	226	1	2
	X ₈	7.93	0		4	231	1	2
0.01	1	7.33	0.04	0.04	1	0	0	0
	2	7.27	0.04		1	1	0	1
	6	7.24	0.04		0	5	0	1
0.023	13	8.23	0.10	0.10	1	0	0	0
	14	7.80	0.10		1	0	0	1
	17	7.93	0.10		0	0	0	0
0.045	33	7.38	0.18	0.18	1	0	0	0
	34	7.68	0.18		1	0	0	0
	36	7.48	0.18		1	0	0	0

Table 5 (continuation)

Tested concentrations (%)	Test specimen no.	Solution discharge ($m_1 - m_0$) (g)	Product retention		Visual examination (0-4)	Surviving termites		
			Test specimen (kg/m^3)	Mean (kg/m^3)		O (%)	S (n)	N (n)
0.064	38	8.05	0.27	0.28	1	0	0	0
	39	8.01	0.27		1	0	0	1
	40	8.41	0.29		1	0	0	0
0.085	49	9.41	0.42	0.42	1	0	0	0
	50	9.45	0.42		0	0	0	0
	51	9.46	0.42		1	0	0	0
Test solutions	T1	-	-	-	4	239	2	1
	T2	-	-	-	4	226	1	1
	T3	-	-	-	4	232	2	2

[O: Workers; S: Soldiers; N: Nymphs; n: number]

Table 6
Threshold of preventive effectiveness against termites (UNE 56410:1992)
Aged test specimen (EN 73)

Tested concentrations (%)	Test specimen no.	Solution charge (m ₁ -m ₀) (g)	Product retention		Visual examination (0-4)	Surviving termites		
			Test specimen (kg/m ³)	Measurement (kg/m ³)		O (%)	S (n)	N (n)
Xylene (0)	X ₁	7.22	0	0.00	4	195	1	2
	X ₁₀	8.02	0		4	210	0	3
	X ₁₂	7.56	0		4	219	0	3
0.01	7	7.33	0.04	0.04	0	0	0	0
	8	7.64	0.04		0	0	0	0
	9	7.51	0.04		0	1	0	2
0.023	19	8.09	0.10	0.10	0	0	0	0
	22	7.76	0.10		0	0	0	2
	23	7.26	0.09		0	0	0	0
0.045	26	7.70	0.19	0.19	0	0	0	0
	27	7.84	0.20		1	0	0	0
	32	7.59	0.19		0	0	0	0

Table 6 (continuation)

Tested concentrations (%)	Test specimen no.	Solution charge ($m_1 - m_0$) (g)	Product retention		Visual examination (0-4)	Surviving termites		
			Test specimen (kg/m^3)	Measurement (kg/m^2)		O (%)	S (n)	S (n)
0.064	38	8.07	0.28	0.28	1	0	0	0
	39	7.90	0.27		0	0	0	1
	40	8.22	0.28		1	0	0	0
0.085	49	9.34	0.42	0.42	1	0	0	0
	51	9.37	0.42		1	0	0	0
	52	9.35	0.42		0	0	0	0
Test solutions	T1	-	-	-	4	95	1	3
	T2	-	-	-	4	88	2	2
	T3	-	-	-	4	89	1	3

[O: Workers; S: Soldiers; N: Nymphs; n: number]

CLAIMS

1. Vehicle that is useful for applying chemical compounds on woods, comprising the following composition:

	<u>Components</u>	<u>Percentage by weight regarding total (%)</u>
5	Toluene	40-70
	Xylene	6-40
	Benzophenone	3-18
	Butyl glycol	2- 9
	Cetyl acetate	1- 7
10	Methanol	0.3-4

2. Vehicle according to claim 1, comprising the following composition:

	<u>Components</u>	<u>Percentage by weight regarding total (%)</u>
	Toluene	64
15	Xylene	16
	Benzophenone	10
	Butyl glycol	5
	Cetyl acetate	4
	Methanol	1

20 3. Composition comprising at least one chemical compound and a vehicle according to any of claims 1 or 2.

4. Composition according to claim 3, wherein said chemical compound comprises one or more insecticides and/or one or more fungicides.

25 5. Composition according to claim 4, wherein said chemical compound is selected from chlorpyrifos, fipronil, silafluofen, acetamiprid, etofenprox, tripropyl isocianurate, fenobucarb, hexaflumuron, fenitrothion, esfenvalerate, imidacloprid, difluobenzuron, lambda-cyhalothrin, clothalonil,
30 propiconazole and the mixtures thereof.

6. Method for treating wood which comprises applying a composition according to any of claims 3 to 5 to the wood to be treated.

7. Method according to claim 6, for treating and/or
35 preventing the damage caused by biological agents that are

harmful for wood, which comprises applying a composition according to any of claims 4 or 5 to the wood to be treated.