

ABSORBENT CORE FOR DISPOSABLE ABSORBENT ARTICLES

FIELD OF THE INVENTION

The present invention relates to an absorbent core for disposable absorbent articles, such as diapers, which provides the articles with an improved fit in dry and wet state (i.e. when loaded with bodily fluids) and an improved liquid transportation.

BACKGROUND OF THE INVENTION

Disposable absorbent articles for receiving and retaining bodily discharges such as urine or feces are well known in the art. Examples of these include disposable diapers, training pants and adult incontinence articles. Typically, disposable diapers comprise a liquid pervious topsheet that faces the wearer's body, a liquid impervious backsheet that faces the wearer's clothing and an absorbent core interposed between the liquid pervious topsheet and the backsheet.

Since their introduction into the market place, disposable diapers have continued to improve regarding comfort, fit and functionalities.

An important component of disposable absorbent articles is the absorbent core structure. The absorbent core structure typically includes absorbent polymer material, such as hydrogel-forming polymer material, also referred to as absorbent gelling material, AGM, or super-absorbent polymer, SAP. This absorbent polymer material ensures that large amounts of bodily fluids, e.g. urine, can be absorbed by the absorbent article during its use and be locked away, thus providing low rewet and good skin dryness.

Traditionally, the absorbent polymer material is incorporated into the absorbent core structure with cellulose or cellulosic fibres. However, over the past years, significant effort has been spent to make thinner absorbent core structures which can still acquire and store large quantities of discharged body fluids, in particular urine. Hereto, it has been proposed to reduce or eliminate these cellulose fibres from the absorbent core structures. To maintain the mechanical stability of the absorbent core structures, small quantities of thermoplastic adhesive material, such as fibrous thermoplastic adhesive material, may be added to stabilize the absorbent polymer material. Resultantly, absorbent structures having the required permeability/porosity, reduced gel-blocking, and that form stable structures in use or transport are provided.

However, it was found that some absorbent core structures with reduced cellulose fibre content, whilst being very thin when not loaded with bodily fluids, may have an increased

stiffness when partially loaded or fully loaded, especially in those regions which comprise most of the absorbent capacity of the absorbent article, such as the front region and crotch region of the diaper. Increased stiffness is not desirable since it reduces the absorbent article's ability to conform to the body of the wearer once worn. Furthermore, it was also found that some absorbent core structures which comprise absorbent polymer particles of high absorption capacity swell significantly upon loading with body exudates. As a result, the volume of the absorbent article may increase significantly during use, especially in these regions which comprise most of the absorbent capacity of the absorbent article, such as the front region and crotch region of the diaper. Such an increase in volume may render the disposable article uncomfortable for the wearer. It was also found that some of these absorbent core structures with reduced cellulose fibre content may have a reduced void volume which impacts negatively the liquid acquisition speed.

Therefore there is still a need for absorbent articles having good liquid handling properties and having an increased flexibility during the whole use of the article and which deliver, in particular a better fit in the wet state.

SUMMARY OF THE INVENTION

The present invention relates to an absorbent core for disposable absorbent articles, such as diapers. The absorbent core comprises at least a first and a second absorbent structures which comprise respectively a substrate layer and an absorbent layer comprising absorbent polymer particles, and optionally cellulose, supported by the substrate layer. Each absorbent layer has a transverse and longitudinal dimension, a pair of opposing longitudinal edges extending in its longitudinal dimension, a pair of opposing transverse edges extending in its transverse dimension and a front, crotch and back regions arranged sequentially in the longitudinal dimension. A plane perpendicular to the central longitudinal axis of the absorbent layer delimits two longitudinal regions. The absorbent layer of the first absorbent structure comprises two or more channels substantially free of said absorbent polymeric particles extending through the thickness of the absorbent layer whereas the second absorbent structure is free of channels. Each longitudinal portion of the absorbent layer comprises at least one channel extending in the longitudinal dimension of the absorbent layer. The channels have a width of at least 3 mm or of at least 4% of the transverse dimension of the absorbent layer and are at least present in the crotch region or front region. The absorbent layer of said first absorbent structure is free of channels extending up to the longitudinal and transverse edges of said absorbent layer.

The present invention also relates to a disposable diaper comprising an absorbent core as disclosed above and herein below.

BRIEF DESCRIPTION OF THE DRAWINGS

Figure 1 is a plan view of a disposable diaper.

Figure 2 is a perspective view of an absorbent structure comprising an absorbent layer free of channels.

Figure 3A is a perspective view of the absorbent layer with two longitudinal channels.

Figure 3B is a perspective view of an absorbent layer comprising an absorbent layer with four longitudinal channels.

Figure 4A is a perspective view of an absorbent layer comprising two longitudinal channels in the crotch region.

Figure 4B is a perspective view of an absorbent layer comprising two longitudinal channels in the front region.

Figure 4C is a perspective view of an absorbent layer comprising two longitudinal channels at least present in the crotch region and two longitudinal channels in the front region.

Figure 4D is a perspective view of an absorbent layer comprising two longitudinal channels at least present in the crotch region, two longitudinal channels in the front region and two longitudinal channels in back front region.

Figures 5A to 5E are schematic representations of channels.

Figure 6A is a top view of an absorbent structure comprising an absorbent layer with four longitudinal channels.

Figure 6B is a perspective view of the absorbent structure of figure 6A.

Figures 7 to 9 are schematic cross-sections of an absorbent core taken in the transverse dimension.

Figure 10 is a schematic representation of a process for making an absorbent structure comprising an absorbent layer with channels.

DETAILED DESCRIPTION OF THE INVENTION

Definitions

"Absorbent article" refers to devices that absorb and contain body exudates, and, more specifically, refers to devices that are placed against or in proximity to the body of the wearer to

absorb and contain the various exudates discharged from the body. Absorbent articles may include diapers, training pants, adult incontinence undergarments, feminine hygiene products.

As used herein "diapers" refers to devices which are intended to be placed against the skin of a wearer to absorb and contain the various exudates discharged from the body. Diapers are generally worn by infants and incontinent persons about the lower torso so as to encircle the waist and legs of the wearer. Examples of diapers include infant or adult diapers and pant-like diapers such as training pants.

"Training pant", as used herein, refers to disposable garments having a waist opening and leg openings designed for infant or adult wearers. A pant may be placed in position on the wearer by inserting the wearer's legs into the leg openings and sliding the pant into position about a wearer's lower torso. A pant may be preformed by any suitable technique including, but not limited to, joining together portions of the article using refastenable and/or non-refastenable bonds (e.g., seam, weld, adhesive, cohesive bond, fastener, etc.). A pant may be preformed anywhere along the circumference of the article (e.g., side fastened, front waist fastened).

"Disposable" is used herein to describe articles that are generally not intended to be laundered or otherwise restored or reused (i.e., they are intended to be discarded after a single use and, may be recycled, composted or otherwise disposed of in an environmentally compatible manner).

As used herein "absorbent core" refers to a component of an absorbent article typically disposed between a topsheet and backsheet of an absorbent article. The absorbent core comprises at least two absorbent structures and optionally further layers, such as for instance a cover layer.

As used herein "absorbent structure" refers to a three dimensional structure useful to absorb and contain liquids, such as urine. The absorbent structure is part of the absorbent core of an absorbent article, i.e. an absorbent component of the absorbent core, as will be further described herein.

"Absorbent polymer particles" as used herein refers to substantially water-insoluble polymer particles that can absorb at least 10 times their weight of a 0.9% saline solution in demineralized water as measured using the Centrifuge Retention Capacity test (Edana 441.2-01).

"Nonwoven material" as used herein refers to a manufactured web of directionally or randomly orientated fibers, excluding paper and products which are woven, knitted, tufted, stitch-bonded incorporating binding yarns or filaments, or felted by wet-milling, whether or not additionally needled. Nonwoven materials and processes for making them are known in the art.

Generally, processes for making nonwoven materials comprise laying fibers onto a forming surface, which may comprise spunlaying, meltblowing, carding, airlaying, wetlaying, coform and combinations thereof. The fibers may be of natural or man-made origin and may be staple fibers or continuous filaments or be formed in situ.

The term “basis weight” as used herein refers to the mass of a material per unit area, i.e. the mass of absorbent polymer particles per unit area, e.g. gram per square meter (gsm).

In the following description of the invention, the surface of an absorbent article, or of an element thereof, which faces in use in the direction of the wearer, is called the “wearer-facing surface”. Conversely, the surface facing in use in the direction of the garment is called the “garment-facing surface”. The absorbent article, as well as any element thereof, such as, for example the absorbent structure, has therefore a wearer-facing surface and a garment-facing surface.

“Hot melt adhesive” as used herein refers to adhesives in alignment with the description given in “Adhesion and Adhesives Technology: An Introduction” by Alphonsus V. Pocius (Hanser publishers Munich, 1997). Therein a hot melt is defined as an adhesive applied from the melt and gaining strength upon solidification.

Unless specified otherwise, the longitudinal dimension or length of an absorbent layer as used herein is to be understood as the average length.

Unless specified otherwise, the transverse dimension or width of an absorbent layer as used herein is to be understood as the average width.

DISPOSABLE ABSORBENT ARTICLES

The disposable absorbent article is a device that absorbs and contains body exudates. It may include diapers, training pants, adult incontinence undergarments, feminine hygiene products. Typically, the disposable article comprises a topsheet, a backsheet and an absorbent core in-between.

An exemplary embodiment of a disposable absorbent article is disposable diaper such as illustrated in figure 1.

The disposable diaper **1** has a longitudinal dimension (along a longitudinal axis **A**) and a transverse dimension (along a transverse axis **B**) perpendicular thereto.

One end portion of the diaper is configured as a front waist region **2** (which is the front one third of the article, having one third of the length of the article). The opposite end portion is

configured as a back waist region **3** (which is the back one third of the article, having one third of the length of the article). An intermediate portion of the diaper is configured as a crotch region **4** (which is the centre one third of the article). The crotch region extends longitudinally between the front and back waist regions. The crotch region is that portion of the diaper which, when the diaper is worn, is generally positioned between the wearer's legs.

The diaper typically comprises a topsheet **5**, a backsheet **6** and an absorbent core **7** disposed therebetween.

The topsheet may be liquid pervious. The topsheet may be at least partially hydrophilic. So-called apertured topsheets may also be used. Topsheets with one or more (large) openings may also be used. The topsheet may also include a skin care composition, e.g., a lotion. The topsheet may be fully or partially elasticized or may be foreshortened to provide a void space between the topsheet and the absorbent core. Exemplary structures including elasticized or foreshortened topsheets are described in more detail in U.S. Pat. No. 5,037,416 entitled "Disposable Absorbent Article Having Elastically Extensible Topsheet" issued to Allen et al. on Aug. 6, 1991; and U.S. Pat. No. 5,269,775 entitled "Trisection Topsheets for Disposable Absorbent Articles and Disposable Absorbent Articles Having Such Trisection Topsheets" issued to Freeland et al. on Dec. 14, 1993.

The backsheet may be vapor pervious but liquid impervious. The backsheet may be used to prevent the fluids absorbed and contained in the absorbent core from wetting materials that contact the absorbent article such as underpants, pants, pyjamas, undergarments, and shirts or jackets, thereby acting as a barrier to fluid transport. In certain embodiments, the backsheet may be substantially impervious to liquids (e.g., urine) and comprise a laminate of a nonwoven and a thin plastic film such as a thermoplastic film having a thickness of about 0.012 mm (0.5 mil) to about 0.051 mm (2.0 mils). Suitable backsheet films include those manufactured by Tredegar Industries Inc. of Terre Haute, Ind. and sold under the trade names X15306, X10962, and X10964. Other suitable backsheet materials may include breathable materials that permit vapors to escape from the diaper while still preventing liquid exudates from passing through the backsheet. Exemplary breathable materials may include materials such as woven webs, nonwoven webs, composite materials such as film-coated nonwoven webs, and microporous films such as manufactured by Mitsui Toatsu Co., of Japan under the designation ESPOIR NO and by EXXON Chemical Co., of Bay City, Tex., under the designation EXXAIRE. Suitable breathable composite materials comprising polymer blends are available from Clopay Corporation, Cincinnati, Ohio under the name HYTREL blend P18-3097. Such breathable

composite materials are described in greater detail in PCT Application No. WO 95/16746, published on Jun. 22, 1995 in the name of E. I. DuPont. Other breathable backsheets including nonwoven webs and apertured formed films are described in U.S. Pat. No. 5,571,096 issued to Dobrin et al. on Nov. 5, 1996.

The absorbent core **7** is disposed between the topsheet and the backsheet of the absorbent article. The absorbent core comprises at least two absorbent structures that will be described in further details herein below.

The diaper may further comprise a front and back waist band and/ or a fastening system, typically joined to the waistband, as known in the art. Preferred fastening systems comprise fastening tabs **8** and landing zones **9**, wherein the fastening tabs are attached or joined to the back waist region of the diaper and the landing zones are part of the front waist region of the diaper. The diaper may also have leg cuffs **10** and/ or barrier cuffs, such as elasticized barrier cuffs **11**. Suitable cuffs are described, for example, in U.S. 3,860,003; U.S. 4,808,178 and 4,909; U.S. 4,695,278 and 4,795,454.

As illustrated in figure 1, the absorbent core may comprise an acquisition system comprising an upper acquisition layer **12** and a lower acquisition layer **13** and optionally a core cover **14**.

Processes for assembling the diaper include conventional techniques known in the art for constructing and configuring disposable absorbent articles. For example, the backsheet and/or the topsheet can be joined to the absorbent core or to each other by a uniform continuous layer of adhesive, a patterned layer of adhesive, or an array of separate lines, spirals, or spots of adhesive. Adhesives which have been found to be satisfactory are manufactured by H. B. Fuller Company of St. Paul, Minnesota under the designation HL-1258 or H-2031. While the topsheet, the backsheet, and the absorbent core may be assembled in a variety of well-known configurations, preferred diaper configurations are described generally in U.S. Pat. No. 5,554,145 entitled "Absorbent Article With Multiple Zone Structural Elastic-Like Film Web Extensible Waist Feature" issued to Roe et al. on Sep. 10, 1996; U.S. Pat. No. 5,569,234 entitled "Disposable Pull-On Pant" issued to Buell et al. on Oct. 29, 1996; and U.S. Pat. No. 6,004,306 entitled "Absorbent Article With Multi-Directional Extensible Side Panels" issued to Robles et al. on Dec. 21, 1999.

ABSORBENT CORE

As indicated above, the absorbent core comprises at least two absorbent structures that absorb and contain liquids, such as urine, of which at least one comprises channels and at least one is free of channels.

“Absorbent structure” as used herein refers to a three-dimensional structure comprising one absorbent layer comprising absorbent polymer particles, and optionally cellulose, supported by a substrate layer

“Channels” as used herein refer to discrete portions of the absorbent layer extending through the thickness of an absorbent layer which are substantially free of absorbent polymer particles, i.e. no absorbent polymer particles are intentionally present in such a channel of an absorbent structure. However, it should be understood that, accidentally, a small, negligible amount of absorbent polymer particles may be present in the channel, which does not contribute to the overall functionality (e.g. absorbency of the absorbent structure). The channels are also preferably free of cellulose. Typically, the channels possess two transverse edges (in the shortest dimension) and two longitudinal edges (in the longest dimension) running between the transverse edges. The transverse edges of the channels may be straight (i.e. perpendicular to the longitudinal side edges), angled or curved. The channels have an average width **w** of at least 3 mm (the average of a channel is defined as the average distance between the longitudinal side edges) or at least 4% of the average width of the absorbent layer. In some embodiments, the longitudinal channels may have complex shapes: the channels may not end with a straight, angled or curved traverse edge but may have one or more ramifications at their end edges. The ramifications also possess longitudinal edges and one transverse edge. The channels, as well as their ramifications, have an average width **w** of at least 3 mm.

ABSORBENT STRUCTURE

An absorbent structure **15** is a three-dimensional structure comprising a substrate layer **16** and an absorbent layer **17** comprising absorbent polymer particles **50**, and optionally cellulose, supported by, and preferably immobilized on, said substrate layer **16**. Examples of absorbent structures are illustrated in figures 2, 3A, 6A and 6B.

The substrate layer has a longitudinal dimension extending in the longitudinal dimension of the diaper and a transverse dimension extending in the transverse dimension of the diaper.

The absorbent layer has a longitudinal dimension **M** extending in the longitudinal dimension of the diaper (i.e. the absorbent layer has a length **M**) and a transverse dimension **N** extending in the transverse dimension of the diaper (i.e. the absorbent layer has a width **N**). The absorbent layer **17** possesses a central longitudinal axis **x**, a central transverse axis **y**

perpendicular to said central longitudinal axis **x**, a pair of opposing longitudinal edges **18** extending in the longitudinal dimension of the disposable absorbent article, such as a disposable diaper and a pair of opposing transverse edges **19** extending in the transverse dimension of the disposable absorbent article, such as a disposable diaper. The longitudinal edges or transverse edges of the absorbent layer may be parallel respectively to the central longitudinal axis or central transverse axis (as shown in figures 2, 3A, 6A and 6B) or they may follow the general direction of these axes while not being strictly parallel, e.g. they may be curvilinear as for instance to provide for a narrower transverse dimension in the crotch region (as shown in figures 3B, 4A to 4D).

The central longitudinal axis **x** of the absorbent layer **17** delimits two regions of the absorbent layer referred herein as longitudinal regions **20** (the plane perpendicular to the central longitudinal axis divides the absorbent layer **17** in two longitudinal regions **20** disposed on either side of said plane).

One end portion of the absorbent layer is configured as a front region **21** (which is the region oriented toward the front waist region of the disposable diaper) which makes up 25% of the longitudinal dimension **M** of the absorbent layer. The opposite end region is configured as a back region **22** (which is the region oriented toward the back waist region of the diaper) which makes up 25% of the longitudinal dimension **M** of the absorbent layer. An intermediate portion of the absorbent layer is configured as a crotch region **23** which makes up 50% of the longitudinal dimension **M** of the absorbent layer. The front, crotch and back regions are arranged sequentially in the longitudinal dimension of the absorbent layer.

The substrate layer of the absorbent structure may be any material capable to support the absorbent polymer particles. Typically, it is a web or sheet material, such as foam, film woven and/or nonwoven material. "Nonwoven material" as used herein refers to a manufactured web of directionally or randomly orientated fibers, bonded by friction, and/or cohesion and/or adhesion, excluding paper and products which are woven, knitted, tufted, stitch-bonded incorporating binding yarns or filaments, or felted by wet-milling, whether or not additionally needled. Nonwoven materials and processes for making them are known in the art. Generally, processes for making nonwoven materials comprise two steps: fiber laying onto a forming surface and fiber bonding. The fiber laying step may comprise spunlaying, meltblowing, carding, airlaying, wetlaying, coform and combinations thereof. The fiber bonding step may comprise hydroentanglement, cold calendering, hot calendering, through air thermal bonding, chemical bonding, needle punching, and combinations thereof. The nonwoven material may be a laminate.

The laminate may comprise spunbond layer(s) (S), and/or meltblown layer(s) (M), and/or carded layer(s) (C). Suitable laminates include, but are not limited to, SS, SSS, SMS or SMMS. The nonwoven material may have a basis weight from about 5 to 100g/m², or from about 10 to 40 g/m², or from about 10 to 30 g/m². Woven or nonwoven materials may comprise natural fibers or synthetic fibers or combinations thereof. Examples of natural fibers may include cellulosic natural fibers, such as fibers from hardwood sources, softwood sources, or other non-wood plants. The natural fibers may comprise cellulose, starch and combinations thereof. The synthetic fibers can be any material, such as, but not limited to, those selected from the group consisting of polyolefins (polypropylene and polypropylene copolymers, polyethylene and polyethylene copolymers), polyesters (e.g., polyethylene terephthalate), polyethers, polyamides, polyesteramides, polyvinylalcohols, polyhydroxyalkanoates, polysaccharides, and combinations thereof. Further, the synthetic fibers can be a single component (i.e. a single synthetic material or a mixture that makes up the entire fiber), bi-component (i.e. the fiber is divided into regions, the regions including two or more different synthetic materials or mixtures thereof and may include co-extruded fibers and core and sheath fibers) and combinations thereof. Bi-component fibers can be used as a component fiber of the nonwoven material, and/or they may be present to act as a binder for the other fibers present in the nonwoven material. Any or all of the fibers may be treated before, during, or after manufacture to change any desired properties of the fibers.

The substrate layer **16** and the absorbent layer **17** may be coextensive or the substrate layer **16** may be slightly longer and wider than the absorbent layer **17** (as shown in figures 2, 3B, 6A and 6B).

The absorbent layer **17** comprises absorbent polymer particles **50**. The absorbent polymer particles may be used alone or in combination with other materials. In some embodiments, the absorbent layer comprises absorbent polymer particles combined with cellulose. "Cellulose" as used herein refers to comminuted wood pulp in the form of fibers, typically also referred in the art as "air-felt". In some embodiments, the absorbent layer comprises more than 70%, or more than 80%, or more than 90%, or more than 95%, or even 100% by weight of absorbent polymer particles. In some embodiments, the absorbent layer comprises absorbent polymer particles and less than 5% by weight of cellulose, more typically less than 2% by weight of cellulose and most typically the absorbent layer is cellulose free. The resulting absorbent structures have a reduced thickness in the dry state compared to conventional absorbent structure comprising cellulosic fibers. The reduced thickness helps to improve the fit and comfort of the absorbent article for the wearer.

The absorbent polymer particles, and cellulose when present, may be immobilized on the substrate layer, such as for example by a thermoplastic adhesive material.

Typically the absorbent polymer particles suitable for use in the absorbent layer can comprise any absorbent polymer particles known from superabsorbent literature, for example such as described in *Modern Superabsorbent Polymer Technology*, F.L. Buchholz, A.T. Graham, Wiley 1998.

The absorbent polymer particles may be spherical, spherical-like or irregular shaped particles, such as Vienna-sausage shaped particles, or ellipsoid shaped particles of the kind typically obtained from inverse phase suspension polymerizations. The particles can also be optionally agglomerated at least to some extent to form larger irregular particles.

The absorbent polymer particles can be selected among polyacrylates and polyacrylate based materials that are internally and/or surface cross-linked, such as for example partially neutralized cross-linked polyacrylates or acid polyacrylate. Examples of absorbent polymer particles suitable in the present invention are described for instance in the PCT Patent Application WO 07/047598, WO 07/046052, WO2009/155265 and WO2009/155264.

The absorbent polymer particles are preferably internally cross-linked, i.e. the polymerization is carried out in the presence of compounds having two or more polymerizable groups which can be free-radically copolymerized into the polymer network. Useful crosslinkers include for example ethylene glycol dimethacrylate, diethylene glycol diacrylate, allyl methacrylate, trimethylolpropane triacrylate, triallylamine, tetraallyloxyethane as described in EP-A 530 438, di- and triacrylates as described in EP-A 547 847, EP-A 559 476, EP-A 632 068, WO 93/21237, WO 03/104299, WO 03/104300, WO 03/104301 and in DE-A 103 31 450, mixed acrylates which, as well as acrylate groups, include further ethylenically unsaturated groups, as described in DE-A 103 31 456 and DE-A 103 55 401, or crosslinker mixtures as described for example in DE-A 195 43 368, DE-A 196 46 484, WO 90/15830 and WO 02/32962 as well as cross-linkers described in WO2009/155265.

The absorbent polymer particles may be externally cross-linked (post cross-linked). Useful post-crosslinkers include compounds including two or more groups capable of forming covalent bonds with the carboxylate groups of the polymers. Useful compounds include for example alkoxysilyl compounds, polyaziridines, polyamines, polyamidoamines, di- or polyglycidyl compounds as described in EP-A 083 022, EP-A 543 303 and EP-A 937 736, polyhydric alcohols as described in DE-C 33 14 019, cyclic carbonates as described in DE-A 40 20 780, 2-oxazolidone and its derivatives, such as N-(2-hydroxyethyl)-2-oxazolidone as

described in DE-A 198 07 502, bis- and poly-2-oxazolidones as described in DE-A 198 07 992, 2-oxotetrahydro-1,3-oxazine and its derivatives as described in DE-A 198 54 573, N-acyl-2-oxazolidones as described in DE-A 198 54 574, cyclic ureas as described in DE-A 102 04 937, bicyclic amide acetals as described in DE-A 103 34 584, oxetane and cyclic ureas as described in EP-A 1 199 327 and morpholine-2,3-dione and its derivatives as described in WO 03/031482.

The absorbent polymer particles may have surface modifications, such as being coated or partially coated with a coating agent. Examples of coated absorbent polymer particles are disclosed in WO2009/155265. The coating agent may be such that it renders the absorbent polymer particles more hydrophilic. The coating agent may be a polymer, such as an elastic polymer or a film-forming polymer or an elastic film-forming polymer, which forms an elastomeric (elastic) film coating on the particle. The coating may be a homogeneous and/or uniform coating on the surface of the absorbent polymer particles. The coating agent may be applied at a level of from 0.1% to 5%, or from 0.2% to 1% by weight of the surface-modified absorbent polymer particles.

Typically, the absorbent polymer particles can have a selected particle size distribution. For example, the absorbent polymer particles may have a particle size distribution in the range from 45 μm to 4000 μm , more specifically from 45 μm to about 1000 μm , or from about 100 μm to about 850 μm , or from about 100 μm to about 600 μm . The particle size distribution of a material in particulate form can be determined as it is known in the art, for example by means of dry sieve analysis (EDANA 420.02 "Particle Size distribution"). Optical methods, e.g. based on light scattering and image analysis techniques, can also be used.

An absorbent structure comprising a substrate layer and an absorbent layer free of channels, such as shown in figure 2, is referred herein as an "absorbent structure free of channels".

An absorbent structure comprising a substrate layer, an absorbent layer with channels **26**, such as shown in figures 3A, 3B, 4A to 4D, 6A and 6B, is referred herein as an "absorbent structure with channels".

At least one of the absorbent structures of the absorbent core comprises channels **26**. More specifically, in embodiments where the absorbent core comprises two absorbent structures, one of them comprises channels and one of them is free of channels. In embodiments where the absorbent core comprises more than two absorbent structures, such as three or four absorbent structures, the further absorbent structures may comprise channels or be free of channels.

The “absorbent structure with channels” comprises at least two longitudinal channels **26** which extend through the thickness of the absorbent layer in the longitudinal dimension of the absorbent layer and which are distributed in the absorbent layer such that each longitudinal portion **20** of the absorbent layer comprises at least one channel **26**. The channels are at least present in the crotch region and/or front region of the absorbent layer. By extending in the longitudinal dimension of the absorbent layer, it is meant that the channels extend essentially in the longitudinal dimension, i.e. they extend more in the longitudinal dimension than in the transverse dimension, for instance at least twice as much in the longitudinal dimension than in the transverse dimension.

In the following, when applicable, the description applies to each channel taken independently. For example, by “two longitudinal channels may extend over a distance **L** which is at least 15%” is meant that each of the two longitudinal channels may extend over a distance **L** which is at least 15%...”. The channels may be the same or different.

In some embodiments, such as shown in figures 3A and 4A, the absorbent layer **17** may comprise two longitudinal channels **26** at least present in the crotch region. By at least present in the crotch region, it is meant that the channels may extend from the crotch region up the front region and/or back region. The two longitudinal channels may extend over a distance **L** which is at least 15%, or at least 20% or at least 30% and up to 50%, or up to 70% or up 90% of the longitudinal dimension of the absorbent layer (i.e. they may extend over a distance **L** which is at least 15%, or at least 20% or at least 30% and up to 50%, or up to 70% or up 90% of the length **M** of the absorbent layer). In some embodiments, such as shown in figure 4A, the longitudinal main channels may be present only in the crotch region. When present only in the crotch region, the longitudinal channels may extend over the whole longitudinal dimension of the crotch region, i.e. 50% of the longitudinal dimension of the absorbent layer, or they may extend in only part of the crotch region, i.e. from at least 15% to 40%, or to 45% or to less than 50% of the longitudinal dimension of the absorbent layer (i.e. they may extend over a distance **L** which is at least 15% and up to 50% of the length **M** of the absorbent layer). In some embodiments, the two longitudinal channels **26** may be present in the crotch region, or part thereof, and part of the front region and/or part of the back region. For instance, in some embodiments, the longitudinal channels may be present in the front and crotch regions, i.e. the channels extend through the crotch region (or part thereof) and part of the front region. In these embodiments, the longitudinal channels may extend up to 70% of the longitudinal dimension of the absorbent layer, typically from 15%, or from 20% or from 30% to 70% of the longitudinal dimension of the absorbent layer

(i.e. they may extend over a distance **L** which is up to 70% of the length **M** of the absorbent layer). In some embodiments, the longitudinal channels may be present in the back and crotch regions, i.e. the channels extend through the crotch region (or part thereof) and part of the back region. In these embodiments, the longitudinal channels may extend up to 70% of the longitudinal dimension **M** of the absorbent layer, typically from 15%, or from 20% or from 30% to 70% of the longitudinal dimension of the absorbent layer (i.e. they may extend over a distance **L** which is up to 70% of the length **M** of the absorbent layer). In some embodiments, the longitudinal channels may be present in the front, crotch and back regions. In these embodiments, the longitudinal channels may extend up to 90% of the longitudinal dimension **M** of the absorbent layer, typically from 55% or from 60% to 70% , or to 80% of the longitudinal dimension of the absorbent layer (i.e. they may extend over a distance **L** which is up to 90% of the length **M** of the absorbent layer).

The two longitudinal channels are typically separated in the crotch region by a distance **D** of at least 5%, or at least 10%, or at least 20%, or at least 25% of the transverse dimension (width) of the absorbent layer in said crotch region. It was found that when such a distance **D** is present between the two longitudinal channels, the disposable diaper takes a desirable bucket shape which improves the fit of the diaper. In some embodiments, the longitudinal channels may be separated in the crotch region by a distance of at least 10 mm, or at least 15 mm, or at least 20 mm, or at least 30 mm. In some embodiments, the distance separating the longitudinal channels in the crotch region is from 20 to 30 mm.

In some embodiments, such as illustrated for example in figure 4B, the longitudinal channels may be present only in the front region of the absorbent layer. In these embodiments, the longitudinal channels may extend over a distance **L** which is less than 25% of the longitudinal dimension **M** of the absorbent layer, typically from 15%, or from 17%, or from 20% to less than 25% of the longitudinal dimension of the absorbent layer.

The longitudinal main channels **26** do not extend up to the transverse edges **19** of the absorbent layer **17**, i.e. from one transverse edge to the other. Typically, the absorbent layer comprises, along each transverse edge and immediately adjacent to said edge, a strip free of channels which extends in the transverse dimension of the absorbent layer from one longitudinal edge to the other (shown for instance in figure 3A). Said strips have respectively a width **F'** or **G'** which is at least 5% of the longitudinal dimension of the absorbent layer (i.e. a width **F'** or **G'** which is at least 5% of the length **M** of the absorbent layer). In other words, the smallest distance **F'** or **G'** between the edge of a channel and the transverse edge of the absorbent layer is

at least 5% of the longitudinal dimension **M** of the absorbent layer. In some embodiments, the width **F'** or **G'** is at least from 5% to 15%, or to 10% of the longitudinal dimension of the absorbent layer.

Furthermore, in order to reduce the risk of fluid leakages and run-off, the longitudinal main channels do not extend up to the longitudinal edges **18** of the absorbent layer **17**. Typically, the absorbent layer comprises, along each longitudinal edge and immediately adjacent to said edge, a strip free of channel which extends in the longitudinal dimension of the absorbent layer from one transverse edge to the other. Said strips have respectively a width **I' or F'** which is at least 5%, or at least 10%, or at least 12% to 25% of the transverse dimension **N** of the absorbent layer in a given region (i.e. a width **I' or F'** which is at least 5% of the width **N** of the absorbent layer in a given region). In other words, the minimum distance **I'** or **F'** between the edge of a channel and the longitudinal edge of the absorbent layer is at least from 5% to 25% of the transverse dimension of the absorbent layer. For example, the distance **I'** or **F'** in the crotch region may correspond to at least 5%, or to at least 10% or at least 12 % of the transverse dimension of the absorbent layer in said crotch region. In some embodiments, the distance **I'** and/or **F'** is of 10 mm, or 15 mm or 20 mm.

The longitudinal channels **26** may be mirror images of one another with respect to the central longitudinal axis **x** of the absorbent layer, i.e. the longitudinal channel in one longitudinal region **20** may be mirror image of the longitudinal channel in the other longitudinal region of the absorbent layer **17**.

The longitudinal channels may be straight channels running parallel to the longitudinal axis of the absorbent layer (as shown schematically in figure 5A). Straight channels act as folding lines in the absorbent structure which contribute to provide a desirable bucket shape to the diaper once worn. The disposable absorbent article, such as diaper, once worn conforms to the inside of the wearer's tight. As a result, a U-like shape is achieved which minimizes leakage and increases comfort. These channels also improve fluid transportation within the absorbent structure and therefore contribute to fast insult acquisition.

Alternatively, the longitudinal channels may be curved, as shown in figure 5B. Curved channels act as folding lines in the absorbent structure which assist the absorbent structure in following the morphology of the absorbent article's wearer, i.e. the channels constrain the product to take a U-like shape when the diaper is worn and compressed by the wearer's tights. Thus, the channels provide a comfortable and superior fit in addition to permitting improved liquid transportation.

The longitudinal channels may be oblique channels, as shown in figure 5C, i.e. straight channels oriented under an angle θ of up to 30 degrees, or up to 20 degrees or up to 10 degrees with respect to the longitudinal central axis of the absorbent structure.

In some other alternatives, the longitudinal channels may be angled channels, as shown in figure 5D. Angled channels are channels made of two or more portions connected under an angle σ to one another. Typically, angled channels are made of two portions connected under an angle σ of at least 150 degrees, or at least 160 degrees or at least 170 degrees.

In some embodiments, the longitudinal channels may be so-called “ramified” channels, i.e. channels having at least one extremity which does not end with a straight, angled or curved transverse edge **28** but with a ramification **29**. The ramification **29** may form an angle α of up to 30 degrees, or up to 20 degrees or up to 10 degrees with respect to the longitudinal central axis of the channel.

The longitudinal channels **26** may have an average width **w** of from 3 mm to 15 mm, or from 4 mm to 14 mm or from 5 mm to 12 mm (the average width of a channel is the average distance between its longitudinal side edges **27**). The average width of the channels may be at least 4% of the width of the absorbent layer, or at least 7% and up to 15%, or 20% or 25%. In some embodiments, the longitudinal channels may have an average width **w** of from 3 mm to 18 mm, or from 5 mm to 15 mm or from 6 to 10 mm. The ramifications **29**, as well, have an average width **w** of at least 3 mm or be at least 4% of the width of the absorbent layer, or at least 7% and up to 15%, or 20% or 25% (average distance between the longitudinal edges **27'** of the ramifications **29**).

The absorbent layer may comprise two or more longitudinal channels as disclosed above. Exemplary absorbent structures comprising more than two longitudinal channels are illustrated in figures 3B, 4C and 4D, 6A and 6B. In some embodiments, the absorbent layer may comprise 3, 4, 5, 6, 8 or even 10 channels. Preferably, the absorbent layer comprises an even number of longitudinal channels, which are preferably equally distributed in the two longitudinal regions of the absorbent layer.

In some embodiments, such as shown in figures 3B, 6A and 6B, the absorbent layer may comprise four longitudinal channels **26** at least present in the crotch region. The four longitudinal channels may be independently as disclosed above in respect of the two longitudinal channels at least present in the crotch region. In some embodiments, further longitudinal channels may be present in the back and/or front region. In some embodiments, it may be preferred that the maximal number of channels in the crotch region is such that the sum of the width of the channels is less than 50% of the transverse dimension **N** of the absorbent layer in the crotch region.

In some embodiments, such as shown in figure 4C, the absorbent layer **17** may comprise two longitudinal channels **26** at least present in the crotch region and two longitudinal channels **26** in the front region. By at least present in the crotch region, it is meant that said channels may extend from the crotch region up the front region and/or back region. The two longitudinal channels at least present in the crotch region may extend over a distance **L** which is at least 15%, or at least 20% or at least 30% of the longitudinal dimension **M** of the absorbent layer and up to 90% of the longitudinal dimension of the absorbent layer (the two longitudinal channels at least present in the crotch region may be as described above). The two longitudinal channels in the front region may extend over a distance which is at least 15% to 20% of the longitudinal dimension **M** of the absorbent layer. The two longitudinal channels in the crotch region may be curved channels whereas the two longitudinal channels in the front region may be oblique channels. Preferably, the channels in one of the longitudinal region are mirror images of each other in the other longitudinal region.

In some other embodiments, such as shown in figure 4D, the absorbent layer **17** may comprise two longitudinal channels **26** in the crotch region, two longitudinal channels **26** in the front region and two longitudinal channels **26** in the back region. The two longitudinal channels in the crotch region may extend across at least 15%, or at least 20% or at least 30% of the longitudinal dimension **M** of the absorbent layer. The longitudinal channels in the front region and back regions may extend across at least 15% to 20% of the longitudinal dimension **M** of the absorbent layer. The two longitudinal channels in the crotch region may be curved channels whereas the longitudinal channels in the front region and back region may be oblique channels. Preferably, the channels in one of the longitudinal regions are mirror images of each other in the other longitudinal region.

Typically, the channels are distributed such that along each transverse edge of the absorbent layer and immediately adjacent to said edge, the strip which extends in the transverse dimension of the absorbent layer from one longitudinal edge to the other over a distance **F'** or **G'** remains free of channels (as disclosed above in respect of the longitudinal channels distribution).

Typically, the channels are distributed such that along each longitudinal edge and immediately adjacent to said edge, the strip which extends in the longitudinal dimension of the absorbent layer from one transverse edge to the other over a distance **H'** or **I'** remains free of channels (as disclosed above in respect of the longitudinal channels distribution).

The two or more longitudinal channels may be distributed in the absorbent layer such that a strip extending along the central longitudinal axis of the absorbent layer (and including said axis) from one transverse edge to the other one, and having a width **D'** of at least 5%, or at least 10% and up to 60%, or up to 70%, or up to 75% of the transverse dimension **N** of the absorbent layer remains free of channels (as shown in figure 4D). The absorbent polymer particles are preferably continuously present in said strip. For example, said strip may have a width **D'** of at least 5 mm, or at least 10 mm, or at least 15 mm or at least 20 mm and up to 70 mm or up to 40 mm. The absence of channels in said strip is advantageous since it prevents the diaper from taking an inverted V-shape configuration once worn. Inverted V-shape configuration increases the risk of fluid leakages. In some embodiments, the average basis weight of absorbent polymer particles in said strip is high, i.e. at least 350 gsm and up to 1000 gsm, or for example from 450 gsm to 750 gsm.

The absorbent structure may also comprise one or more channels that extend in the transverse dimension of the absorbent layer, provided the absorbent layer does not comprise any such channels in the crotch region. Channels extending in the transverse dimension in the crotch region would transport liquids to the transverse edges and would increase undesirably the risk of fluid leakages and/or run off. However, such channels may be present in the front region and/or back region of the absorbent layer. In some embodiments, the absorbent structure does not comprise any such channels.

As disclosed in respect of the longitudinal channels, the transverse channels may be straight channels parallel to the transverse central axis of the absorbent structure (as shown in figure 5A), curved channels (as shown in figure 5B), angled channels (as shown in figure 5D),

oblique channels (as shown in figure 5C) or ramified channels (as shown in figure 5E). The transverse channels may have an average width w of from 3 mm to 15 mm, or from 4 mm to 14 mm or from 5 mm to 12 mm. In some embodiments, the transverse channels may have an average width of from 6 to 10 mm.

In some embodiment herein, it may be preferred that the region **30** of the absorbent layer immediately adjacent the channels (as shown in figure 4C) and extending over a distance k of at least 3 mm, or of at least 5 mm, or of at least 7 mm from the edges of the channels comprises absorbent polymer particles present substantially continuously. Preferably, in these regions **30**, the average basis weight of absorbent polymer particles is high, i.e. at least 350 gsm, at least 400 gsm, or at least 500 gsm or at least 600 gsm.

The channels are preferably permanent. By permanent, it is meant that the integrity of the channels is at least partially maintained both in dry state and wet state, i.e. the channels are resistant to frictions caused by movements of the diaper's wearer and resist wetting by bodily fluids, such as urine. Permanent channels are obtained by immobilizing the absorbent polymer particles on the substrate layer, such as by applying a thermoplastic adhesive material over the absorbent layer. Alternatively, the channels may be made permanent by folding the substrate layer into the channels or allowing the substrate layer to enter the channels so as to immobilize the absorbent polymer particles as will be described in further details herein below. Alternatively, the channels can be made permanent by allowing a further substrate layer, such as the core cover when present, to fold into the channels, i.e. undulate into the channels.

The Wet Channel Integrity Test described below can be used to test if channels are permanent following wet saturation and to what extent.

Wet Channel Integrity Test

This test is designed to check the integrity of a channel following wet saturation. The test can be performed directly on a absorbent structure or on a absorbent core containing the absorbent structure.

1. The length (in millimeters) of the channel is measured in the dry state (if the channel is not straight, the curvilinear length through the middle of the channel is measured).
2. The absorbent structure or core is then immersed in 5 liters of synthetic urine "Saline", with a concentration of 9.00 g NaCl per 1000 ml solution prepared by dissolving the appropriate amount of sodium chloride in distilled water. The temperature of the solution must be 20 +/- 5 °C.

3. After 1 minute in the saline, the absorbent structure or core is removed and held vertically by one end for 5 seconds to drain, then extended flat on a horizontal surface with the garment-facing side down, if this side is recognizable. If the absorbent structure or core comprises stretch elements, the absorbent structure or core is pulled taut in both X and Y dimensions so that no contraction is observed. The extremes/edges of the absorbent structure or core are fixed to the horizontal surface, so that no contraction can happen.
4. The absorbent structure or core is covered with a suitably weighted rigid plate, with dimensions as follows: length equal to the extended length of the absorbent structure or core, and width equal to the maximum absorbent structure or core width in the cross direction.
5. A pressure of 18.0 kPa is applied for 30 seconds over the area of the rigid plate above mentioned. Pressure is calculated on the basis of overall area encompassed by the rigid plate. Pressure is achieved by placing additional weights in the geometric center of the rigid plate, such that the combined weight of the rigid plate and the additional weights result in a pressure of 18.0 kPa over the total area of the rigid plate.
6. After 30 seconds, the additional weights and the rigid plate are removed.
7. Immediately afterwards, the cumulative length of the portions of the channel which remained intact is measured (in millimeters; if the channel is not straight, the curvilinear length through the middle of the channel is measured). If no portions of the channel remained intact then the channel is not permanent.
8. The percentage of integrity of the permanent channel is calculated by dividing the cumulative length of the portions of the channel which remained intact by the length of the channel in the dry state, and then multiplying the quotient by 100.

Advantageously, a permanent channel according to the invention has a percentage of integrity of at least 20%, or 30%, or 40%, or 50%, or 60, or 70%, or 80%, or 90% following this test.

When the absorbent structure comprises absorbent polymer particles and cellulose, it may be preferred that the channels are also free of such cellulose.

The absorbent layer of the “absorbent structure free of channels” may comprise absorbent polymer particles, and optionally cellulose, distributed on the substrate layer such as to form a continuous layer, i.e. an uninterrupted layer of absorbent polymeric particles and cellulose when present. Alternatively, the absorbent layer may comprise absorbent polymer particles, and optionally cellulose, distributed on the substrate layer such as to form a discontinuous layer. In some embodiments, the absorbent layer is cellulose free. In these embodiments, the absorbent polymer particle and cellulose when present, may be deposited on the substrate layer in clusters of particles (and cellulose when present), thus forming a discontinuous layer or an interrupted

layer of absorbent polymer particles (and cellulose when present). The clusters of absorbent polymer particles (and cellulose when present) may have a variety of shape including, but not limited to, circular, oval, square, rectangular, triangular and the like. Suitable methods for depositing particles in cluster of particles are disclosed in EP 1621167 A2, EP 1913914 A2 and EP 2238953 A2. Typically, absorbent polymer particles are deposited on the substrate layer in clusters of particles when two such absorbent structures, i.e. of which one comprising channels, are combined to form an absorbent core. The two absorbent structures are combined such that the resulting absorbent core comprises absorbent polymer particles substantially continuously distributed between the two substrate layers, except where channels present. “Substantially continuously distributed” as used herein indicates that the first substrate layer and second substrate layer are separated by a multiplicity of absorbent polymer particles. It is recognized that there may be minor incidental contact areas between the first substrate layer and second substrate layer within the absorbent particulate polymer material area (i.e. area between the two substrate layers). Incidental contact areas between the first substrate and second substrate may be intentional or unintentional (e.g. manufacturing artifacts) but do not form geometries such as pillows, pockets, tubes, quilted patterns and the like.

The absorbent layer of the “absorbent structure with channels” may comprise absorbent polymer particles, and optionally cellulose, distributed on the substrate layer such as to form as a continuous layer, i.e. an uninterrupted layer of absorbent polymeric particles and cellulose when present, which nevertheless comprises regions substantially free of absorbent polymer particles. These discrete regions substantially free of absorbent polymer particles correspond to the channels of the absorbent structure. Alternatively, the “absorbent layer with channels” may comprise absorbent polymer particles, and cellulose when present, distributed on the substrate layer such as to form a discontinuous layer as disclosed above which nevertheless comprises discrete regions substantially free of clusters of absorbent polymer particles and cellulose when present.

The absorbent polymer particles and optionally cellulose may be immobilized on the substrate layer. Immobilization may be achieved by applying a thermoplastic adhesive material which holds and immobilizes the absorbent polymer particles on the substrate layer. Some thermoplastic adhesive material may also penetrate into the layer of absorbent polymer particles and into the substrate layer to provide further immobilization and affixation. The thermoplastic adhesive material does not only help in immobilizing the absorbent polymer particles on the substrate layer but also helps in maintaining the integrity of the channels, when present. The

thermoplastic adhesive material avoids that a significant amount of absorbent polymer particles migrates into the channels.

The thermoplastic adhesive material may be applied as a continuous layer (i.e. uniformly) over the absorbent layer. In some embodiments, the thermoplastic adhesive material contacts the absorbent polymer particles (and cellulose when present) and part of the substrate layer when the absorbent polymer particles (and cellulose when present) are deposited in clusters.

In some embodiments, the thermoplastic adhesive material may be applied as a fibrous layer forming a fibrous network over the absorbent layer. The thermoplastic adhesive fibrous layer may be at least partially in contact with the absorbent polymer particles (and cellulose when present) and partially in contact with the substrate layer of the absorbent structure when the absorbent polymer particles (and cellulose when present) are deposited in clusters. Thereby, the thermoplastic adhesive material may provide cavities to cover the absorbent polymer particles, and thereby immobilizes this material and the channels when present.

Thermoplastic adhesive materials suitable for immobilizing the absorbent polymer particles typically combine good cohesion and good adhesion behavior. Good adhesion promotes good contact between the thermoplastic adhesive material and the absorbent polymer particles and the substrate layer. Good cohesion reduces the likelihood that the adhesive breaks, in particular in response to external forces, and namely in response to strain. When the absorbent structure/core absorbs liquid, the absorbent polymer particles swell and subject the thermoplastic adhesive material to external forces. The thermoplastic adhesive material may allow for such swelling, without breaking and without imparting too many compressive forces, which would restrain the absorbent polymer particles from swelling.

Thermoplastic adhesive materials suitable for use in the present invention includes hot melt adhesives comprising at least a thermoplastic polymer in combination with a plasticizer and other thermoplastic diluents such as tackifying resins and additives such as antioxidants. Exemplary suitable hot melt adhesive materials are described in EP 1447067 A2. In some embodiments, the thermoplastic polymer has a molecular weight (M_w) of more than 10,000 and a glass transition temperature (T_g) below room temperature or $-6\text{ }^{\circ}\text{C} > T_g < 16\text{ }^{\circ}\text{C}$. In certain embodiments, the concentrations of the polymer in a hot melt are in the range of about 20 to about 40% by weight. In certain embodiments, thermoplastic polymers may be water insensitive. Exemplary polymers are (styrenic) block copolymers including A-B-A triblock structures, A-B diblock structures and (A-B) $_n$ radial block copolymer structures wherein the A blocks are non-elastomeric polymer blocks, typically comprising polystyrene, and the B blocks

are unsaturated conjugated diene or (partly) hydrogenated versions of such. The B block is typically isoprene, butadiene, ethylene/butylene (hydrogenated butadiene), ethylene/propylene (hydrogenated isoprene), and mixtures thereof.

Other suitable thermoplastic polymers that may be employed are metallocene polyolefins, which are ethylene polymers prepared using single-site or metallocene catalysts. Therein, at least one comonomer can be polymerized with ethylene to make a copolymer, terpolymer or higher order polymer. Also applicable are amorphous polyolefins or amorphous polyalphaolefins (APAO) which are homopolymers, copolymers or terpolymers of C2 to C8 alpha olefins.

The thermoplastic adhesive material, typically a hot-melt adhesive material, is generally present in the form of fibres, i.e. the hot melt adhesive can be fiberized. In some embodiments, the thermoplastic adhesive material forms a fibrous network over the absorbent polymer particles. Typically, the fibres can have an average thickness from about 1 μm to about 100 μm , or from about 25 μm to about 75 μm , and an average length from about 5 mm to about 50 cm. In particular the layer of hot melt adhesive material can be provided such as to comprise a net-like structure. In certain embodiments the thermoplastic adhesive material is applied at an amount of from 0.5 to 30 g/m^2 , or from 1 to 15 g/m^2 , or from 1 and 10 g/m^2 or even from 1.5 and 5 g/m^2 per substrate layer.

A typical parameter for a hot melt adhesive suitable for use in the present invention can be a loss angle $\tan \Delta$ at 60°C of below the value of 1, or below the value of 0.5. The loss angle $\tan \Delta$ at 60°C is correlated with the liquid character of an adhesive at elevated ambient temperatures. The lower $\tan \Delta$, the more an adhesive behaves like a solid rather than a liquid, i.e. the lower its tendency to flow or to migrate and the lower the tendency of an adhesive superstructure as described herein to deteriorate or even to collapse over time. This value is hence particularly important if the absorbent article is used in a hot climate.

It may be beneficial, e.g. for process reasons and/or performance reasons, that the thermoplastic adhesive material has a viscosity of between 800 and 4000 mPa·s, or from 1000 mPa·s or 1200 mPa·s or from 1600 mPa·s to 3200 mPa·s or to 3000 mPa·s or to 2800 mPa·s or to 2500 mPa·s, at 175°C, as measurable by ASTM D3236-88, using spindle 27, 20 pmp, 20 minutes preheating at the temperature, and stirring for 10 min.

The thermoplastic adhesive material may have a softening point of between 60°C and 150°C, or between 75°C and 135°C, or between 90°C and 130°C, or between 100°C and 115°C, as can be determined with ASTM E28-99 (Herzog method; using glycerine).

In one embodiment herein, the thermoplastic adhesive component may be hydrophilic, having a contact angle of less than 90°, or less than 80° or less than 75° or less than 70°, as measurable with ASTM D 5725-99.

In some embodiments, the absorbent structure may also comprise an adhesive material deposited on the substrate before application of the absorbent polymer particles on the substrate layer, referred herein as the auxiliary adhesive. The auxiliary adhesive may enhance the immobilization of the absorbent polymer particles on the substrate layer. It may be a thermoplastic adhesive material, and comprise the same thermoplastic adhesive material as described hereinabove or it may be different. An example of commercially available adhesive is H.B. Fuller Co. (St. Paul, MN) Product No. HL-1620-B. The thermoplastic adhesive material may be applied to the substrate layer by any suitable means.

At least a first absorbent structure with channels and at least a second absorbent structure free of channels are combined to form an absorbent core.

The absorbent core may further comprise a cover layer. The cover layer may be a separate layer or it may be unitary with the substrate layer. In such a case, the substrate layer supporting the absorbent polymer particles is folded to form a top and bottom layer which encloses the absorbent polymer particles. The cover layer may be provided of the same material as the substrate layer, or may be provided of a different material. The layers may be bonded together at about the periphery to enclose the absorbent polymer particles therein, e.g. by adhesive bonding and/or heat bonding. In some embodiments, the core cover may undulate into the channels.

In some embodiments, the absorbent core may comprise an acquisition system which is disposed between the topsheet and the wearer facing side of the absorbent structure. The acquisition system may serve as a temporary reservoir for liquid until the absorbent structure can absorb the liquid. The acquisition system may comprise a single layer or multiple layers, such as an upper acquisition layer facing towards the wearer's skin and a lower acquisition layer facing the garment of the wearer. The acquisition system may be in direct contact with the absorbent structure. In these embodiments, the acquisition system may fill in the channels or part thereof. In some embodiments, the acquisition system may be placed on top of the core cover when present. In embodiments wherein the core cover or substrate layer folds into the channels, i.e. undulates into the channels, the acquisition system may fill in the channels or part thereof. In some embodiments, the acquisition system, or one layer thereof, may be bonded to the core cover or substrate layer which undulates into the channels thus providing an undulating profile to said acquisition system.

In a certain embodiment, the acquisition system may comprise chemically cross-linked cellulosic fibers. Such cross-linked cellulosic fibers may have desirable absorbency properties. Exemplary chemically cross-linked cellulosic fibers are disclosed in US Patent No. 5,137,537. In certain embodiments, the chemically cross-linked cellulosic fibers are cross-linked with between about 0.5 mole % and about 10.0 mole % of a C₂ to C₉ polycarboxylic cross-linking agent or between about 1.5 mole % and about 6.0 mole % of a C₂ to C₉ polycarboxylic cross-linking agent based on glucose unit. Citric acid is an exemplary cross-linking agent. In other embodiments, polyacrylic acids may be used. Further, according to certain embodiments, the cross-linked cellulosic fibers have a water retention value of about 25 to about 60, or about 28 to about 50, or about 30 to about 45. A method for determining water retention value is disclosed in US Patent No. 5,137,537. According to certain embodiments, the cross-linked cellulosic fibers may be crimped, twisted, or curled, or a combination thereof including crimped, twisted, and curled.

In a certain embodiment, one or both of the upper and lower acquisition layers may comprise a non-woven, which may be hydrophilic. Further, according to a certain embodiment, one or both of the upper and lower acquisition layers may comprise the chemically cross-linked cellulosic fibers, which may or may not form part of a nonwoven material. According to an exemplary embodiment, the upper acquisition layer may comprise a nonwoven, without the cross-linked cellulosic fibers, and the lower acquisition layer may comprise the chemically cross-linked cellulosic fibers. Further, according to an embodiment, the lower acquisition layer may comprise the chemically cross-linked cellulosic fibers mixed with other fibers such as natural or synthetic polymeric fibers. According to exemplary embodiments, such other natural or synthetic polymeric fibers may include high surface area fibers, thermoplastic binding fibers, polyethylene fibers, polypropylene fibers, PET fibers, rayon fibers, lyocell fibers, and mixtures thereof. Suitable non-woven materials for the upper and lower acquisition layers include, but are not limited to SMS material, comprising a spunbonded, a melt-blown and a further spunbonded layer. In certain embodiments, permanently hydrophilic non-wovens, and in particular, nonwovens with durably hydrophilic coatings are desirable. Another suitable embodiment comprises a SMMS-structure. In certain embodiments, the non-wovens are porous.

Figures 7 to 9 illustrate embodiments wherein a first absorbent structure **15** with channels **26** is combined with a second absorbent structure **15'** free of channels. In the embodiment shown in figure 7, the thermoplastic adhesive material **40** of the first absorbent structure **15** directly contacts the thermoplastic adhesive material **40'** of the second absorbent structure **15'** whereas in figures 8 and 9, the second absorbent structure **15'** does not comprise any such

thermoplastic adhesive material **40'** (however, it may be present to immobilize the absorbent layer on the substrate layer). An auxiliary adhesive **60** may be present on the substrate layer of the first and/or second absorbent structure for further immobilization of the absorbent polymer particles **50** (as shown in figure 7). In some embodiments, the substrate layer **16** of the first absorbent structure **15** may undulate into the channels **26** of the first absorbent structure (as shown in figures 8 and 9). The absorbent core may further comprise an acquisition system as disclosed above **70** that penetrates and fill in the channels (however in some embodiments, the acquisition system does not fill in the channels). Figure 9 shows an embodiment wherein the acquisition system **70** comprises a first layer **12** and second layer **13**, wherein the second layer fills in the channels.

In some embodiments, the absorbent structure with channels may be closer to the wearer in use than the absorbent structure(s) without channels.

In some embodiments, the absorbent structure with channels may be closer to the garment in use than the absorbent structure(s) without channels.

In some embodiments, the absorbent polymer particles, and optionally cellulose, may be distributed evenly in the longitudinal and/or transverse dimensions of the absorbent layers irrespective of whether the absorbent layer is a continuous layer or a discontinuous layer of absorbent polymer particles, and optionally cellulose, as described above to provide an absorbent core having an even distribution of absorbent polymer particles. The average basis weight of absorbent polymer particles may depend on the particular diaper in which it may be incorporated. In some embodiments, the average basis weight of absorbent polymer particles in the absorbent core may be from 350 gsm to 1500 gsm. The amount of absorbent polymeric particles in the respective region is calculated by determining the weight of absorbent polymeric material in this region and dividing it by the total surface area of the region (hence, the average amount is taken).

In some embodiments, the absorbent polymer particles, and optionally cellulose, may be distributed unevenly in the longitudinal and/or transverse dimension of at least one of the absorbent layers to provide a profiled absorbent core. For example, the crotch region of the absorbent structure/core may comprise a higher amount of absorbent polymer particles per area compared to the front and back regions of the absorbent structure/core. In some embodiment, the front half of the absorbent core comprises most of the absorbent capacity, i.e. it may comprise more than about 60% of the absorbent polymer particles, or more than about 65%, or more than 70%, based on the total weight of absorbent polymer particles in the absorbent core.

In some embodiments, the absorbent core can be made by combining or superposing one or more absorbent structures comprising channels as described above with an absorbent structure free of channels. In some embodiments, the absorbent core can be made by combining or superposing one absorbent structure comprising channels as described above with one or more absorbent structure free of channels. The absorbent structures may all comprise less than 5% by weight of cellulose, or less than 2% by weight of cellulose or be cellulose free or only some of them may comprise less than 5% by weight of cellulose, or less than 2% by weight of cellulose or be cellulose free.

In some embodiments where the absorbent core comprises two absorbent structures comprising channels as described above combined with an absorbent structure free of channels, the absorbent structures comprising channels may be combined such that the absorbent layer, or the thermoplastic adhesive material when present, of the one absorbent structure directly contacts the absorbent layer, or the thermoplastic adhesive material when present, of the other absorbent structure. It may be that the channels of one absorbent structure substantially superpose the channels of the adjacent absorbent structure. The resulting absorbent core is a laminate of absorbent structures with channels, wherein the channels extend substantially through the thickness of two of the combined absorbent structures (by substantially as used herein it is meant that the thicknesses of the substrate layer are hereby neglected). In some embodiments, it may be that the channels of one absorbent structure do not superpose the channels of the adjacent absorbent structure but are complementary with the channels of the adjacent structure. By complementary it is meant that the channels of one of the absorbent structure form an extension of the channels of the other absorbent structure. The absorbent structure free of channels may be combined with said two absorbent structures such as to be the absorbent structure the closer to the backsheet or to the topsheet of the diaper.

METHOD OF MAKING THE ABSORBENT CORE

The absorbent structure free of channels herein may be made by any method comprising the step of depositing absorbent polymer particles and optionally cellulose in form of an absorbent layer on a substrate layer.

The absorbent structure having channels herein may be made by any method comprising the step of depositing absorbent polymer particles and optionally cellulose to form an absorbent layer onto a substrate layer, for example by placing first said substrate layer onto raised portions in the shape and dimensions of said channels to be produced and then depositing said absorbent

polymer particles and optionally cellulose thereon; thereby, the absorbent polymer particles and optionally cellulose does not remain onto said raised portions, but only on the remaining portions of the substrate layer.

In some embodiments, the absorbent structure with the substrate layer with therein two or more channels with substantially no absorbent material is for example obtainable by a method comprising the steps of:

- a) providing a feeder for feeding said absorbent material (absorbent polymer particles and optionally cellulose) to a first moving endless surface, such as a hopper;
- b) providing a transfer means for transferring a substrate layer to a second moving endless surface;
- c) providing a first moving endless surface, having one or more absorbent layer-forming reservoirs with a longitudinal dimension and averaged length, a perpendicular transverse dimension and average width, and, perpendicular to both, a depth dimension and average depth, and a void volume for receiving said absorbent material therein, said reservoir(s) comprising one or more substantially longitudinally extending raised strips, not having a void volume, for example each having an average width **W** of at least 4% or at least 5% of the average width of the reservoir, and an average length **L** of at least 5% and at the most 30% of the average longitudinal dimension of the reservoir; said reservoir(s) being for transferring said absorbent material to said second moving endless surface adjacent and in proximity thereto;
- d) providing a second moving surface, having an outer shell that has one or more air permeable or partially air permeable receptacles with for receiving said substrate layer thereon or therein, with a receiving area and with one or more substantially longitudinally extending mating strips that may be air impermeable, and having each an average width of for example **W'** of at least 2.5 mm, preferably from 0.5 x **W** to 1.2 x **W**, an average length of for example **L'** being from about 0.8 x **L** to 1.2 x **L**;

whereby said air-permeable outer shell is connected to one or more secondary vacuum systems for facilitating retention of the substrate layer and/or said absorbent material thereon, and

whereby, in a meeting point, said first moving endless surface and said outer shell are at least partially adjacent to one another and in close proximity of one another during transfer of said absorbent material and such that each mating strip is substantially completely adjacent and in close proximity to a raised strip during transfer of said absorbent material;

- e) feeding with said feeder an absorbent material to said first moving endless surface, in at least said reservoir (s) thereof;
- f) optionally, removing any absorbent material on said raised strips (s);
- g) simultaneously, transferring said substrate layer to said second moving endless surface, onto or into said receptacle(s);
- h) selectively transferring in said meeting point, said absorbent material with said first moving endless surface only to said part of the supporting sheet that is on or in said receiving area of said receptacle.

Said reservoir(s) may be formed by of a multitude of grooves and/ or cavities with a void volume, for receiving said absorbent material therein. In some embodiments, the average width **W** of (each) strip is preferably at least 6 mm, or for example at least 7 mm, and/or at least at least 7%, or for example at least 10% of the average width of the respective reservoir.

Said grooves and/ or cavities may each for example have a maximum dimension in transverse direction which is at least 3 mm, and whereby the shortest distance between directly neighboring cavities and /or grooves in substantially transverse dimension, is less than 5 mm. Cavities and/ or grooves that are directly adjacent a raised strip may have a volume that is more than the volume of one or more, or all of their neighboring cavities or grooves, that are not directly adjacent said strip or another strip (thus further removed from a strip).

Said first moving endless surface's reservoir may be at least partially air permeable and said first moving endless surface may have a cylindrical surface with said reservoirs, rotatably moving around a stator, comprising a vacuum chamber; said second moving surface's outershell may be cylindrical, rotatably moving around a stator, comprising a secondary vacuum chamber connected to said secondary vacuum system.

An absorbent structure obtained by said method can then be combined with an absorbent structure free of channels.

The method may further comprise the optional step of i) applying an adhesive material to the absorbent structure of step h; and/ or applying an adhesive material (i.e. a second adhesive material) to said substrate layer, prior or step f, or simultaneously therewith, but in any event prior to step g).

Step i) 1) may involve straying said first adhesive material in the form of fibers onto said absorbent layer, or part thereof, for example substantially continuously, so it is also present in said channels.

Step i) 2) may involve slot coating or spray-coating the supporting sheet, either continuously, or for example in a pattern corresponding to the channel pattern.

The dimensions and values disclosed herein are not to be understood as being strictly limited to the exact numerical values recited. Instead, unless otherwise specified, each such dimension is intended to mean both the recited value and a functionally equivalent range surrounding that value. For example, a dimension disclosed as “40 mm” is intended to mean “about 40 mm.”

All documents cited in the Detailed Description of the Invention are, in relevant part, incorporated herein by reference; the citation of any document is not to be construed as an admission that it is prior art with respect to the present invention. To the extent that any meaning or definition of a term in this document conflicts with any meaning or definition of the same term in a document incorporated by reference, the meaning or definition assigned to that term in this document shall govern.

While particular embodiments of the present invention have been illustrated and described, it would be obvious to those skilled in the art that various other changes and modifications can be made without departing from the spirit and scope of the invention. It is therefore intended to cover in the appended claims all such changes and modifications that are within the scope of this invention.

CLAIMS

What is claimed:

1. An absorbent core (7) comprising at least a first and second absorbent structures (15, 15') comprising respectively a substrate layer (16, 16') and an absorbent layer (17, 17') comprising absorbent polymer particles (50, 50'), and optionally cellulose, supported by said substrate layer, each of said absorbent layer having:
 - i. a transverse and longitudinal dimension (M, N);
 - ii. a pair of opposing longitudinal edges (18) extending in said longitudinal dimension ;
 - iii. a pair of opposing transverse edges (19) extending in said transverse dimension;
 - iv. a front, crotch and back regions (21, 23, 22) arranged sequentially in said longitudinal dimension;
 - v. two longitudinal portions delimited by a plane perpendicular to the central longitudinal axis of said absorbent layer;wherein the absorbent layer of said first absorbent structure comprises two or more channels (26) having a width of at least 3 mm, or of at least 4% of the transverse dimension of the absorbent layer, which are substantially free of said absorbent polymeric particles and which extend through the thickness of said absorbent layer; and
wherein the absorbent layer (17') of said second absorbent structure (15') is free of said channels, and
wherein each longitudinal portion of said absorbent layer of said first absorbent structure comprises at least one longitudinal channel (26) extending in the longitudinal dimension of the absorbent layer and being at least present in said crotch region and/or front region with the proviso that said absorbent layer is free of channels extending up to the longitudinal and transverse edges of said absorbent layer.
2. An absorbent core according to claim 1 wherein said first and/or second absorbent structure comprises an absorbent layer which comprises less than 5% by weight of cellulose.

3. An absorbent core according to claim 1 or 2 wherein each of said longitudinal channels extends across from 15% to 90% of the longitudinal dimension of said absorbent layer.
4. An absorbent core according to any of the preceding claims wherein the absorbent layer of said first absorbent structure comprises four longitudinal channels, two of said channels being in the front region of said absorbent layer and two of said channels being in the crotch region of said absorbent layer.
5. An absorbent core according to any of claims 1, 2 or 3 wherein the absorbent layer of said first absorbent structure comprises six longitudinal channels, two of said channels being in the front region of said absorbent layer, two of said channels being in the crotch region of said absorbent layer and two of said channels being in the back region of said absorbent layer.
6. An absorbent core according to any of the preceding claims wherein said longitudinal channels in said crotch region are separated by a distance of at least 10% of the transverse dimension of the absorbent layer in said crotch region.
7. An absorbent core according to any of the preceding claims wherein the absorbent layer of said first absorbent structure further comprises transverse channels having a width of at least 3 mm which are substantially free of said absorbent polymer particles in the front region or back region of said absorbent layer.
8. An absorbent core according to any of the preceding claims wherein said channels are straight channels, oblique channels, curved channels, angled channels, ramified channels and combinations thereof.
9. An absorbent core according to any of the preceding claims wherein said absorbent polymer particles are immobilized on said substrate layer by a thermoplastic adhesive material.

10. An absorbent core according to any of the preceding claims wherein said channels have a width of from 6 to 10 mm.
11. An absorbent core according to any of the preceding claims wherein the substrate layer of said first absorbent structure undulates into the channels.
12. An absorbent core according to any of the preceding claims wherein said absorbent core further comprises an acquisition system.
13. A disposable diaper having a transverse and longitudinal dimension comprising a backsheet, a topsheet and an absorbent core disposed therebetween, said absorbent core being according to any of the preceding claims.
14. The disposable diaper according to claim 13 wherein said first absorbent structure faces toward the topsheet of said diaper.
15. The disposable diaper according to claim 13 wherein said first absorbent structure faces toward the backsheet of said diaper.