

DESCRIPTION
PHOTOCURABLE COMPOSITION

TECHNICAL FIELD

5 [0001]

The present invention relates to a photocurable composition from which a cured product having high concealing property is obtained by irradiation with an active energy ray such as ultraviolet ray, and which inhibits color fading
10 of the cured product in a high temperature and high humidity (85°C and 85% RH) environment or a high temperature (100°C) environment.

BACKGROUND ART

15

[0002]

Conventionally, a photocurable composition having high concealing property has been widely used in a coating material for a flexible wiring board (see Patent Literature 1), a casting
20 material for a replica of a prototype model (see Patent Literature 2), a black stripe of lenticular lens (see Patent Literature 3), an adhesive agent for assembling an electronic equipment and the like (see Patent Literature 4), a sealing agent for a liquid crystal display (see Patent Literature
25 5), or the like. As a typical technique of imparting concealing property to a photocurable composition, mixing of carbon black of pigment can be mentioned. However, concealing property can be obtained, but most of active energy rays such as UV rays are absorbed into the carbon black,
30 therefore, there has been a problem of causing poor curability when the concentration of the pigment is extremely high.

[0003]

Under these circumstances, in Patent Literature 2, there is a disclosure of a photosensitive composition for casting, which contains a photoradical polymerization initiator, a leuco dye, a photoacid generator, and an ethylenically unsaturated compound, and the cured product has excellent photocurability while being black. This utilizes the fact that the generation speed of the "radical species generated by light irradiation" is faster than the generation speed of the "acid generated by light irradiation". That is, the photosensitive resin composition is cured by the transmission of light to the extent of the deep portion before being blackened with an acid.

Citation Lists

Patent Literature

[0004]

Patent Literature 1 : JP 2013-194156 A

Patent Literature 2 : JP H11-060962 A

Patent Literature 3 : JP 2013-082924 A

Patent Literature 4 : JP 2014-025021 A

Patent Literature 5 : JP 2010-126630 A

SUMMARY OF INVENTION

[0005]

However, since the black-colored cured product of a photosensitive composition for casting disclosed in Patent Literature 2 exhibits a deteriorated concealing property due to color fading, which occurs when the cured product is left in a high temperature and high humidity (85°C and 85% RH) environment or a high temperature (100°C) environment, there have been problems in terms of use for various applications.

[0006]

To solve the aforementioned problems of the related art, the inventors of the present invention studied a photocurable composition. As a result, they found that the main cause of occurrence of color fading of a cured product is based on detachment of an acid from a leuco dye in a high temperature and high humidity (85°C and 85% RH) environment or a high temperature (100°C) environment, and completed the present invention accordingly.

[0007]

The present invention is devised in consideration of the circumstances described above, and an object of the invention is to provide a photocurable composition from which a cured product having high concealing property is obtained by irradiation with an active energy ray such as ultraviolet ray, and which inhibits color fading of the cured product in a high temperature and high humidity environment or a high temperature environment.

[0008]

The present invention is to deal with the aforementioned problems of the related art. Namely, the gist of the present invention is as follows.

[0009]

A photocurable composition including the following components (A) to (D):

component (A): a leuco dye;

component (B): a salt having an anion selected from the group consisting of $[P(Rf)_aF_{6-a}]^-$, $[Sb(Rf)_bF_{6-b}]^-$ and $[B(Rf)_cF_{4-c}]^-$ (in the formulae, Rf represents a fluoroalkyl group having 1 to 20 carbon atoms, a and b each independently represent an integer of from 1 to 5, and c represents an integer of from 1 to 3);

component (C): a radical polymerizable compound; and

component (D): a photoradical initiator.

DESCRIPTION OF EMBODIMENTS

[0010]

5 One embodiment of the present invention relates to a photocurable composition containing component (A): a leuco dye, component (B): a salt having an anion selected from the group consisting of $[P(Rf)_aF_{6-a}]^-$, $[Sb(Rf)_bF_{6-b}]^-$ and $[B(Rf)_cF_{4-c}]^-$ (in the formulae, Rf represents a fluoroalkyl
10 group having 1 to 20 carbon atoms, a and b each independently represent an integer of from 1 to 5, and c represents an integer of from 1 to 3), component (C): a radical polymerizable compound, and component (D): a photoradical initiator.

[0011]

15 A cured product formed of the photocurable composition having such constitution has not only an excellent concealing property but also well-inhibited color fading in a high temperature and high humidity (85°C and 85% RH) environment or a high temperature (100°C) environment.

20 [0012]

Hereinbelow, the photocurable composition according to the present invention (hereinbelow, also simply referred to as a "composition") and a cured product formed of the composition will be described in detail.

25 [0013]

Furthermore, in the present specification, "X to Y" is used to have a meaning which includes the numerical values described before and after them (X and Y) as a lower limit value and an upper limit value, respectively. Further, unless
30 otherwise specifically noted, operations and measurements of properties and the like are performed under the conditions of room temperature (20 to 25°C) / relative humidity 40 to

50% RH. In addition, the term "(meth)acrylate" includes both of "acrylate" or "methacrylate".

[0014]

<Component (A)>

5 A leuco dye that is a component (A) of the present invention is a compound developing color by coming into contact with an acid, and can give concealing property to a cured product. Further, the leuco dye can make the color black, blue, green, red, or the like depending on the type, but from
10 the viewpoint of being excellent in concealing property, a leuco dye capable of developing a black color is preferred.

[0015]

Examples of the component (A) include, although not particularly limited,

15 3-dibutylamino-6-methyl-7-anilinofluoran,
3-dipropylamino-6-methyl-7-anilinofluoran,
3-diethylamino-6-methyl-7-anilinofluoran,
3-dimethylamino-6-methyl-7-anilinofluoran,
3-diethylamino-6-methyl-7-xylylidinofluorane, and
20 3-(4-diethylamino-2-ethoxyphenyl)-3-(1-ethyl-2-methylindole-3-yl)-4-azaphthalide. These can be used singly or by mixing two or more kinds thereof. Among them, from the viewpoint of concealing property of the cured product,
3-dibutylamino-6-methyl-7-anilinofluoran, and
25 3-diethylamino-6-methyl-7-anilinofluoran, are preferred. The product available on the market of the component (A) is not particularly limited, but examples of the product include S-205, BLACK305, ETAC, BLACK100, and NIR BLACK78 (manufactured by YAMADA CHEMICAL CO., LTD.), and ODB, ODB-2,
30 ODB-4, ODB-250, and Black-XV (manufactured by Yamamoto Chemicals, Inc.).

[0016]

The mixing amount of the component (A) of the present invention is, based on 100 parts by mass of the component (C) described later, preferably in the range of 0.01 to 20 parts by mass, more preferably 0.05 to 10 parts by mass, even
5 more preferably 0.2 to 5 parts by mass, and particularly preferably 0.5 to 2 parts by mass. When the component (A) is 0.01 parts by mass or more, the cured product can have an excellent concealing property. Further, when the component (A) is 20 parts by mass or less, the composition
10 can have excellent photocurability.
[0017]

<Component (B)>

The component (B) is a compound which generates an acid such as a Lewis acid and a Broensted acid by irradiation with
15 an active energy ray (that is, photoacid generator), and with the generated acid, it becomes possible to have color exhibition of a leuco dye. Furthermore, by selecting the component (B) of the present invention among photoacid generators and combining it with other components of the
20 present invention, the effect of inhibiting color fading of a cured product in a high temperature and high humidity environment or a high temperature environment can be obtained. Although the reason for having enhanced fading resistance of a cured product by the component (B) of the present invention
25 remains unclear, it is expected that, with regard to a salt having a specific anion with large volume structure (P^+X^-) such as the component (B) of the present invention, when an acid (H^+X^-) is generated from the salt, the mobility of the acid is lowered due to large volume of the counter anion,
30 and the acid is hardly detached from the component (A). Therefore, color fading unlikely occur in the cured product. Furthermore, from the viewpoint of having excellent

concealing property and photocurability at the same time,
the component (B) is preferably a salt which has absorption
in a wavelength range of 365 nm or higher.

[0018]

5 The component (B) according to the composition of the
present invention is a salt having an anion selected from
the group consisting of $[P(Rf)_aF_{6-a}]^-$, $[Sb(Rf)_bF_{6-b}]^-$ and
 $[B(Rf)_cF_{4-c}]^-$ (in the formulae, Rf represents a fluoroalkyl
group having 1 to 20 carbon atoms, a and b each independently
10 represent an integer of from 1 to 5, and c represents an integer
of from 1 to 3). In particular, from the viewpoint of having
an excellent concealing property of a cured product, the
component (B) of the present invention is preferably a salt
which has an anion represented by $[P(Rf)_aF_{6-a}]^-$. The component
15 (B) may be used either singly or in combination of two or
more kinds thereof.

[0019]

 Rf represents an alkyl group having 1 to 20 carbon atoms
in which part or all of the hydrogen atoms are substituted
20 with a fluorine atom, and preferably represents an alkyl group
having 1 to 20 carbon atoms in which all of the hydrogen atoms
are substituted with a fluorine atom, that is, a perfluoroalkyl
group. The alkyl group of Rf is preferably those having 1
to 12 carbon atoms, more preferably those having 1 to 8 carbon
25 atoms, and even more preferably those having 1 to 4 carbon
atoms. Specific examples of Rf include, although not
particularly limited, CF_3 , CF_3CF_2 , $(CF_3)_2C$, $CF_3CF_2CF_2$,
 $CF_3CF_2CF_2CF_2$, and $(CF_3)_3C$. Among them, from the viewpoint of
easy obtainability of a raw material, CF_3CF_2 (perfluoroethyl
30 group) is preferable.

[0020]

 Examples of the alkyl group having 1 to 20 carbon atoms

include a methyl group, an ethyl group, a n-propyl group,
an isopropyl group, a cyclopropyl group, a n-butyl group,
an isobutyl group, a sec-butyl group, a tert-butyl group,
a cyclobutyl group, a n-pentyl group, an isopentyl group,
5 a neopentyl group, a 1,2-dimethylpropyl group, a cyclopentyl
group, a n-hexyl group, a cyclohexyl group, a
1,3-dimethylbutyl group, a 1-isopropylpropyl group, a
1,2-dimethylbutyl group, a n-heptyl group, a
1,4-dimethylpentyl group, a 2-methyl-1-isopropylpropyl
10 group, a 1-ethyl-3-methylbutyl group, a cycloheptyl group,
a n-octyl group, a 2-ethylhexyl group, a nonyl group, a decyl
group, a undecyl group, and a dodecyl group.

[0021]

From the viewpoint of easy obtainability of a raw material,
15 a is preferably an integer of from 1 to 4, more preferably
an integer of from 1 to 3, even more preferably an integer
of 2 or 3, and particularly preferably 3.

[0022]

b is preferably an integer of from 1 to 4, more preferably
20 an integer of from 1 to 3, even more preferably an integer
of 2 or 3, and particularly preferably 3.

[0023]

c is preferably 2 or 3, and more preferably 2.

[0024]

25 Furthermore, preferred examples of the $[P(Rf)_aF_{6-a}]^-$
include $[(CF_3CF_2)_3PF_3]^-$, $[(CF_3CF_2CF_2)_2PF_4]^-$, $[(CF_3CF_2CF_2)_3PF_3]^-$,
 $[(CF_3CF_2CF_2CF_2)_2PF_4]^-$ and $[(CF_3CF_2CF_2CF_2)_3PF_3]^-$. Among them,
 $[(CF_3CF_2)_3PF_3]^-$ or $[(CF_3CF_2CF_2)_3PF_3]^-$ is more preferable, and
 $[(CF_3CF_2)_3PF_3]^-$ is even more preferable from the viewpoint of
30 easy obtainability of a raw material.

[0025]

Furthermore, from the viewpoint of easy obtainability


of a raw material, the component (B) of the present invention is preferably a salt which has a cation selected from the group consisting of an arylodonium cation, an aryl sulfonium cation, and an aryldiazonium cation, and it is more preferably
5 a salt having an aryl sulfonium cation.

[0026]

The arylodonium cation is a cation which is represented by the following General Formula (1).

[0027]

10 [Chemical Formula 1]



General Formula (1)

[0028]

In General Formula (1), R₁ and R₂ are an aryl group having
15 6 to 30 carbon atoms which may be optionally substituted or a heteroaryl group having 1 to 20 carbon atoms which may be optionally substituted. R₁ and R₂ may be either the same substituent group or a different substituent group.

[0029]

20 Examples of the aryl group having 6 to 30 carbon atoms include, although not particularly limited, a non-fused hydrocarbon group such as a phenyl group, a biphenyl group, or a terphenyl group; and a fused polycyclic hydrocarbon group such as a pentarenyl group, an indenyl group, a naphthyl group,
25 an azulenyl group, a heptarenyl group, a biphenylenyl group, a fluorenyl group, an acenaphthylenyl group, an pleiadenyl group, an acenaphthenyl group, a phenalenyl group, a phenanthryl group, an anthryl group, a fluororanthrenyl group, an acephenantrylenyl group, an aceanthrylenyl group, a
30 triphenylenyl group, a pyrenyl group, a chrysenyl group, or a naphthacenyl group. Among them, a substituted or

non-substituted phenyl group is preferable.

[0030]

Examples of the heteroaryl group having 1 to 20 carbon atoms include, although not particularly limited, a pyridyl group, a pyrimidyl group, a pyrazinyl group, a triazinyl group, a furanyl group, a pyrrolyl group, a thiophenyl group (thienyl group), a quinolyl group, a furyl group, a piperidyl group, a coumarinyl group, a silafluorenyl group, a benzofuranyl group, a benzimidazolyl group, a benzoxazolyl group, a benzothiazolyl group, a dibenzofuranyl group, a benzothiophenyl group, a dibenzothiophenyl group, an indolyl group, a carbazolyl group, a pyrazolyl group, an imidazolyl group, an oxazolyl group, an isooxazolyl group, a thiazolyl group, an indazolyl group, a pyridazinyl group, a cinnolyl group, a quinazolyl group, a quinoxalyl group, a phthalazinyl group, a phthalazinedionyl group, a phthalamidyl group, a cromonyl group, a naphtholactamyl group, a quinolonyl group, a naphtharidinyl group, a benzimidazolonyl group, a benzoxazolonyl group, a benzothiazolonyl group, a benzothiazothionyl group, a quinazolonyl group, a quinoxalonyl group, a phthalazonyl group, a dioxypyrimidinyl group, a pyridonyl group, an isoquinolonyl group, an isoquinolinyl group, an isothiazolyl group, a benzisooxazolyl group, a benzisothiazolyl group, an indazilonyl group, an acridinyl group, an acridonyl group, a quinazolinedionyl group, a quinoxalinedionyl group, a benzoxazine dionyl group, a benzoxadinonyl group, a naphthalimidyl group, a dithienocyclopentadienyl group, a dithienosilacyclopentadienyl group, a dithienopyrrolyl group, and a benzodithiophenyl group. Among them, a substituted or non-substituted thiophenyl group is preferable.

a 4-phenylthiophenyldiphenyl sulfonium cation, a triphenyl sulfonium cation, and a tri-p-tolyl sulfonium cation. Among them, a 4-phenylthiophenyldiphenyl sulfonium cation is preferable.


5 [0037]

The aryldiazonium cation is a cation which is represented by the following General Formula (3).

[0038]

[Chemical Formula 3]

10



General Formula (3)

[0039]

In General Formula (3), R₆ is an aryl group having 6 to 30 carbon atoms which may be optionally substituted or a
15 heteroaryl group having 1 to 20 carbon atoms which may be optionally substituted. The aryl group or the heteroaryl group is the same as those exemplified above as an aryliodonium cation. In particular, a substituted or non-substituted phenyl group is preferable as an aryl group, and a substituted
20 or non-substituted thiophenyl group is preferable as a heteroaryl group.

[0040]

Specific examples of the aryldiazonium cation include a benzene diazonium cation.

25 [0041]

Furthermore, regarding R₁ to R₆ above, examples of the substituent group which is present depending on case include, although not particularly limited, a substituted or non-substituted alkyl group, a cycloalkyl group, an alkenyl
30 group, an alkynyl group, an aryl group, a heteroaryl group, an acyl group, an alkoxycarbonyl group, an amino group, an

alkoxy group, a cycloalkyloxy group, an aryloxy group, an
aryloxycarbonyl group, an acyloxy group, an acylamino group,
an alkoxy carbonylamino group, an aryloxycarbonylamino group,
a sulfonylamino group, a sulfamoyl group, a carbamoyl group,
5 an alkylthio group, an arylthio group, a silyl group, a sulfonyl
group, a sulfinyl group, a ureido group, a phosphoric acid
amino group, a halogen atom, a hydroxy group, a mercapto group,
a cyano group, a sulfo group, a carboxy group, a nitro group,
a hydroxamic acid group, a sulfino group, a hydrazino group,
10 and an imino group. Furthermore, with regard to the above,
there is no case in which substitution is made with the same
substituent group. Namely, in no case a substituted alkyl
is substituted with an alkyl group.

[0042]

15 The salt having an anion represented by $[P(Rf)_aF_{6-a}]^-$,
which is used as the component (B) of the present invention,
is preferably a salt selected from the group consisting of
triphenyl
sulfonium-tris(perfluoroethyl)trifluorophosphate salt,
20 triphenyl
sulfonium-tris(perfluoropropyl)trifluorophosphate salt,
tri-p-tolyl
sulfonium-tris(perfluoroethyl)trifluorophosphate salt,
tri-p-tolyl
25 sulfonium-tris(perfluoropropyl)trifluorophosphate salt,
4-phenylthiophenyldiphenyl
sulfonium-tris(perfluoroethyl)trifluorophosphate salt, and
4-phenylthiophenyldiphenyl
sulfonium-tris(perfluoropropyl)trifluorophosphate salt,
30 for example, although it is not particularly limited thereto.
Further examples thereof include the compounds that are
disclosed in WO 2005/116038 A. They may be used either singly

or as a mixture of two or more kinds thereof.

[0043]

Examples of the salt having an anion represented by $[\text{Sb}(\text{Rf})_b\text{F}_{6-b}]^-$, which is used as the component (B) of the present invention, include triphenyl sulfonium-tris(perfluoroethyl)trifluoroantimony acid salt, triphenyl sulfonium-tris(perfluoropropyl)trifluoroantimony acid salt, tri-p-tolyl sulfonium-tris(perfluoroethyl)trifluoroantimony acid salt, tri-p-tolyl sulfonium-tris(perfluoropropyl)trifluoroantimony acid salt, 4-phenylthiophenyldiphenyl sulfonium-tris(perfluoroethyl)trifluoroantimony acid salt, and 4-phenylthiophenyldiphenyl sulfonium-tris(perfluoropropyl)trifluoroantimony acid salt, although it is not particularly limited thereto. They may be used either singly or as a mixture of two or more kinds thereof.

20 [0044]

Examples of the salt having an anion represented by $[\text{B}(\text{Rf})_c\text{F}_{4-c}]^-$, which is used as the component (B) of the present invention, include triphenyl sulfonium-bis(perfluoroethyl)difluoroborate salt, triphenyl sulfonium-bis(perfluoropropyl)difluoroborate salt, tri-p-tolyl sulfonium-bis(perfluoroethyl)difluoroborate salt, and tri-p-tolyl sulfonium-bis(perfluoropropyl)difluoroborate salt, although it is not particularly limited thereto. They may be used either singly or as a mixture of two or more kinds thereof.

[0045]

As for the component (B) of the present invention, any one of a commercially available product and a representative synthetic product may be used. In the case of a synthetic product, a metathesis reaction can be mentioned as a synthetic method. Specific examples thereof include those disclosed in WO 2005/116038 A or the like, and it is not limited to them.

[0046]

The blending amount of the component (B) is, relative to 100 parts by mass of the component (C) which will be described later, preferably in the range of 0.1 to 20 parts by mass, more preferably 0.3 to 10 parts by mass, even more preferably 1 to 5 parts by mass, and particularly preferably 2 to 3 parts by mass. As the component (B) is 0.1 part by mass or more, the effect of having color exhibition of a leuco dye is high and the concealing property of a cured product is favorable. Furthermore, as the component (B) is 20 parts by mass or less, the heat resistance of a cured product is favorable. Furthermore, the blending amount of the component (B) is, relative to 1 part by mass of the component (A), preferably in the range of 0.1 to 20 parts by mass, more preferably 0.5 to 10 parts by mass, even more preferably 1 to 5 parts by mass, and particularly preferably 2 to 3 parts by mass.

[0047]

<Component (C)>

The radical polymerizable compound as the component (C) of the present invention is a compound having radical polymerizable functional group, which is commonly used for adhesives, paints, or the like. The component (C) is preferably a compound which contains any one of a (meth)acryloyl group, a vinyl group, and a propenyl group. In particular, a compound containing a (meth)acryloyl group

is more preferable from the viewpoint of the reactivity. Herein, the (meth)acryloyl group indicates a methacryloyl group and/or an acryloyl group. As for the component (C), any one of a monofunctional compound, a bifunctional compound,
5 a trifunctional compound, and a polyfunctional compound may be used. Furthermore, the component (C) may be at least any one of a monomer and an oligomer. They may be used either singly or as a mixture of two or more kinds thereof. In particular, from the viewpoint of having excellent
10 photocurability and physical property of a cured product, it is preferable to use a monomer and an oligomer in combination. Namely, a preferred aspect of the present invention relates to a photocurable composition in which the component (C) contains an oligomer and a monomer.

15 [0048]

Examples of the monofunctional monomer which can be used as the component (C) include, although not particularly limited, ethyl (meth)acrylate, n-butyl (meth)acrylate, tert-butyl (meth)acrylate, isobutyl methacrylate,
20 2-ethylhexyl (meth)acrylate, isodecyl (meth)acrylate, butoxydiethylene glycol (meth)acrylate, methoxypolyethylene glycol (meth)acrylate, glycidyl (meth)acrylate, lauryl (meth)acrylate, stearyl (meth)acrylate, tetrahydrofurfuryl (meth)acrylate,
25 caprolactone-modified tetrahydrofurfuryl (meth)acrylate, cyclohexyl (meth)acrylate, dicyclopentanyl (meth)acrylate, dicyclopentenyl (meth)acrylate, dicyclopentenyl (meth)acrylate, isobornyl (meth)acrylate, adamantyl (meth)acrylate, benzyl (meth)acrylate, phenyl
30 (meth)acrylate, phenoxyethyl (meth)acrylate, phenoxydiethylene glycol (meth)acrylate, phenoxytetraethylene glycol (meth)acrylate,

nonylphenoxyethyl (meth)acrylate, butoxyethyl
 (meth)acrylate, 2-hydroxyethyl (meth)acrylate,
 2-hydroxypropyl (meth)acrylate, 4-hydroxybutyl
 (meth)acrylate, glycerol (meth)acrylate, trifluoroethyl
 5 (meth)acrylate, methacryloxyethyl acid phosphate,
 2-hydroxyethyl methacrylic acid phosphate,
 γ -methacryloxypropyltrimethoxysilane,
 γ -acryloxypropyltrimethoxysilane, acryloylmorpholine,
 morpholinoethyl (meth)acrylate,
 10 dimethylaminoethyl (meth)acrylate,
 diethylaminoethyl (meth)acrylate,
 N,N-dimethylaminoethyl (meth)acrylate,
 N,N-dimethylaminopropyl (meth)acrylate,
 3-methacryloxypropylmethyldimethoxysilane,
 15 3-methacryloxypropyltrimethoxysilane,
 3-methacryloxypropylmethyldiethoxysilane,
 3-methacryloxypropyltriethoxysilane,
 3-acryloxypropyltrimethoxysilane,
 methacryloxyoctyltrimethoxysilane, vinyltrimethoxysilane,
 20 vinyltrichlorosilane, vinyltriethoxysilane, and
 vinyl-tris(β -methoxyethoxy)silane can be mentioned. From
 the viewpoint of the compatibility of the component (A) and
 component (B) of the present invention, and of being excellent
 in the curability, cyclohexyl (meth)acrylate,
 25 dicyclopentany (meth)acrylate, dicyclopentenyl
 (meth)acrylate, dicyclopentenyl (meth)acrylate,
 isobornyl (meth)acrylate, adamantyl (meth)acrylate, benzyl
 (meth)acrylate, phenyl (meth)acrylate, phenoxyethyl
 (meth)acrylate, 2-hydroxyethyl (meth)acrylate,
 30 2-hydroxypropyl (meth)acrylate, 4-hydroxybutyl
 (meth)acrylate, acryloylmorpholine,
 morpholinoethyl (meth)acrylate,

dimethylaminoethyl(meth)acrylate,
diethylaminoethyl(meth)acrylate,
N,N-dimethylaminoethyl(meth)acrylate, and
N,N-dimethylaminopropyl(meth)acrylate are preferable.
5 Among them, from the viewpoint of having an excellent
reactivity, isobornyl(meth)acrylate is more preferable.
They may be used either singly or in combination of two or
more kinds thereof.

[0049]

10 Examples of the bifunctional monomer which can be used
as the component (C) include, although not particularly
limited, ethylene glycol di(meth)acrylate, diethylene glycol
di(meth)acrylate, triethylene glycol di(meth)acrylate,
tetraethylene glycol dimethacrylate, 1,6-hexanediol
15 di(meth)acrylate, 1,9-nonanediol di(meth)acrylate,
glycerin di(meth)acrylate, neopentyl glycol
di(meth)acrylate, stearic acid-modified pentaerythritol
di(meth)acrylate, dicyclopentenyl diacrylate,
di(meth)acryloyl isocyanurate, and alkylene oxide-modified
20 bisphenol di(meth)acrylate. They may be used either singly
or in combination of two or more kinds thereof.

[0050]

Examples of the trifunctional monomer which can be used
as the component (C) include, although not particularly
25 limited, trimethylolpropane tri(meth)acrylate,
pentaerythritol tri(meth)acrylate, and
tris(acryloyloxyethyl) isocyanurate. They may be used
either singly or in combination of two or more kinds thereof.

[0051]

30 Examples of the polyfunctional monomer which can be used
as the component (C) include, although not particularly
limited, ditrimethylol propane tetra(meth)acrylate,

pentaerythritol tetra(meth)acrylate, dipentaerythritol monohydroxy penta(meth)acrylate, alkyl-modified dipentaerythritol pentaacrylate, and dipentaerythritol hexa(meth)acrylate. They may be used either singly or in combination of two or more kinds thereof.
[0052]

As for the oligomer which is used for the component (C), any one of a monofunctional oligomer, a bifunctional oligomer, a trifunctional oligomer, and a polyfunctional oligomer may be used. However, from the viewpoint of easy obtainability of a raw material, it is preferable to use a bifunctional oligomer. The weight average molecular weight (M_w) of the oligomer is preferably 1,000 to 100,000, and the viscosity is preferably 10 to 1,000,000 mPa·s (60°C). Herein, the weight average molecular weight (M_w) is a value which is measured by using gel permeation chromatography (GPC). Examples of the oligomer include, although not particularly limited, urethane (meth)acrylate having a polybutadiene skeleton, urethane (meth)acrylate having a hydrogenated polybutadiene skeleton, urethane (meth)acrylate having a polycarbonate skeleton, urethane (meth)acrylate having a polyether skeleton, urethane (meth)acrylate having a polyester skeleton, urethane (meth)acrylate having a castor oil skeleton, isoprene-based (meth)acrylate, hydrogenated isoprene-based (meth)acrylate, epoxy (meth)acrylate, and (meth)acrylic group-containing acrylic polymer (meth)acrylic group-containing polyisobutylene. In particular, from the viewpoint of the reactivity, it is preferable to use urethane (meth)acrylate having a polyester skeleton. They may be used either singly or in combination of two or more kinds thereof.
[0053]

As for the oligomer, any one of a commercially available

product and a synthetic product may be used. Examples of the commercially available product include UV-3000B, UV-3200B, UV-6640B, UV-6100B, and UV-3700B manufactured by The Nippon Synthetic Chemical Industry Co., Ltd., Light (meth)acrylate
5 3EG-A, 4EG-A, 9EG-A, 14EG-A, PTMGA-250, BP-4EA, BP-4PA, and BP-10EA manufactured by KYOEISHA CHEMICAL CO., LTD., and EBECRYL3700 manufactured by Daicel-Cytec Co., Ltd., but not particularly limited thereto.

[0054]

10 When the above monomer and oligomer are used in combination as the component (C), the mass ratio thereof is preferably 30 : 70 to 95 : 5, more preferably 40 : 60 to 90 : 10, even more preferably 50 : 50 to 80 : 20, and particularly preferably 65 : 35 to 75 : 25. As the mass ratio between the
15 monomer and the oligomer is within the aforementioned range, excellent photocurability can be obtained.

[0055]

The photoradical initiator that is a component (D) used in the present invention is not limited as long as being a
20 compound generating radicals by the irradiation with active energy rays. Further, from the viewpoint of capable of achieving both of concealing property and photocurability, a photoradical polymerization initiator having an absorption at a wavelength of 400 nm or more is preferred. In addition,
25 examples of the component (D) include an acetophenone-based photoradical polymerization initiator, a benzoin-based photoradical polymerization initiator, a benzophenone-based photoradical polymerization initiator, a thioxanthone-based photoradical polymerization initiator, an acylphosphine
30 oxide-based photoradical polymerization initiator, and a titanocene-based photoradical polymerization initiator. Among them, from the viewpoint of having excellent concealing

property of a cured product, an acetophenone-based photoradical polymerization initiator, an acylphosphine oxide-based photoradical polymerization initiator are preferable. They may be used alone or in combination of two or more kinds thereof. Namely, one embodiment of the present invention relates to a photocurable composition in which the component (D) is an acetophenone-based photoradical polymerization initiator or an acylphosphine oxide-based photoradical polymerization initiator.

10 [0056]

Examples of the acetophenone-based photoradical polymerization initiator include, although not particularly limited, diethoxy acetophenone, 2-hydroxy-2-methyl-1-phenylpropane-1-one, benzyl dimethyl ketal, 4-(2-hydroxyethoxy)phenyl-(2-hydroxy-2-propyl)ketone, 1-hydroxy-cyclohexyl-phenyl-ketone, 2-methyl-2-morpholino(4-thiomethylphenyl)propane-1-one, 2-benzyl-2-dimethylamino-1-(4-morpholinophenyl)butanone, and 2-hydroxy-2-methyl-1-[4-(1-methylvinyl)phenyl]propanone oligomer, but are not limited to these ones. Examples of the product available on the market of the acetophenone-based photoradical polymerization initiator include Speedcure (registered trademark, the same shall apply hereinafter) 84, Speedcure 73 (manufactured by LAMBSON), IRGACURE (registered trademark, the same shall apply hereinafter) 184, DAROCUR (registered trademark, the same shall apply hereinafter) 1173, IRGACURE 2959, IRGACURE 127 (manufactured by BASF), and ESACURE (registered trademark, the same shall apply hereinafter) KIP-150 (manufactured by Lamberti s.p.a.).

[0057]

Examples of the acylphosphine oxide-based photoradical polymerization initiator include, although not particularly limited, bis(2,4,6-trimethylbenzoyl)-phenyl-phosphine oxide, and 2,4,6-trimethylbenzoyl-diphenyl-phosphine oxide, but are not limited to these ones. Examples of the product available on the market of the acylphosphine oxide-based photoradical polymerization initiator include Speedcure TPO (manufactured by LAMBSON), LUCIRIN (registered trademark, the same shall apply hereinafter) TPO, IRGACURE 819, and IRGACURE819DW (manufactured by BASF).
[0058]

The mixing amount of the component (D) of the present invention is, based on 100 parts by mass of the component (C), preferably 0.1 to 15 parts by mass, more preferably 0.5 to 10 parts by mass, and particularly preferably 1 to 5 parts by mass. When the mixing amount of the component (D) is 0.1 part by mass or more, the composition has an excellent photocurability with active energy rays, and when the mixing amount of the component (D) is 15 parts by mass or less, the photocurable composition has an excellent storage stability.
[0059]

<Other components>

With regard to the present invention, additives including a tertiary amine compound, various elastomers such as styrene-based copolymer, a polythiol compound, a sensitizing agent, a filler, a conductive filler, a storage stabilizer, an anti-oxidizing agent, a photostabilizer, a storage stabilizer, a heavy metal inactivating agent, a silane coupling agent, a tackifying agent, a plasticizer, an anti-foaming agent, a pigment, an anti-corrosive agent, a leveling agent, a dispersing agent, a rheology adjusting agent, a flame retardant, and a surfactant may be used within a range

in which the purpose of the present invention is not impaired.
[0060]

Examples of the tertiary amine compound include, although not particularly limited, N-phenyl diethanolamine, N-methyl diethanolamine, p-methylphenyl diethanolamine, N-ethyl diethanolamine, N-propyl diethanolamine, N-butyl diethanolamine, triethanolamine, tributanolamine, triisopropanolamine, N-methyl diethanolamine, and N-methyl dimethanolamine; trimethylamine, triethylamine, tributylamine, N,N'-diethanolamine, N,N'-dimethyl-p-toluidine, N,N'-dimethyl-aniline, N-methyl-diethanolamine, N-methyl-dimethanolamine, N,N'-(dimethylamino)ethyl-methacrylate, N,N'-dimethylamino-acetophenone, N,N'-dimethylamino benzophenone, N,N'-diethylamino benzophenone, N-methylpiperidine, N-ethylpiperidine, dimethylbenzylamine, and N,N-dimethylcyclohexylamine. These can be used singly or by mixing two or more kinds thereof. Among them, N-phenyl diethanolamine, N-methyl diethanolamine, p-methylphenyl diethanolamine, N-ethyl diethanolamine, N-propyl diethanolamine, N-butyl diethanolamine, triethanolamine, tributanolamine, and triisopropylamine are preferable.
[0061]

The mixing amount of the tertiary amine compound is, based on 100 parts by mass of the component (C), preferably 0.01 to 200 parts by mass, more preferably 0.05 to 150 parts by mass, and particularly preferably 0.1 to 100 parts by mass. When the mixing amount of the component (E) is 0.1 part by mass or more, the composition can have an excellent photocurability with active energy rays, and when the mixing amount of the component (E) is 200 parts by mass, the cured product can have excellent concealing property.

[0062]

Into the present invention, a polythiol compound may be added for the purpose of improving the photocurability. Examples of the polythiol compound include, although not particularly limited, trimethylolpropane tris(3-mercaptopropionate), pentaerythritol tetrakis(3-mercaptopropionate), trimethylolpropane tris(3-mercaptopropionate), trimethylolpropane tris(3-mercaptopropionate), ethylene glycol bis(3-mercaptopropionate), butanediol bis(3-mercaptopropionate), trimethylolpropane tris(3-mercaptopropionate), pentaerythritol tetrakis(3-mercaptopropionate), tetraethylene glycol bis(3-mercaptopropionate), dipentaerythritol hexakis(3-mercaptopropionate), pentaerythritol tetrakis(3-mercaptopropionate), 1,4-bis(3-mercaptopropionyloxy)butane, and 1,3,5-tris(3-mercaptopropionyloxyethyl)-1,3,5-triazine-2,4,6(1H,3H,5H)-trione.

[0063]

Into the present invention, a sensitizer may be added for the purpose of improving the photocurability. Examples of the sensitizer include anthracene, pyrene, perylene, xanthone, thioxanthone, eosin, ketocoumarin, coumarin, and isobenzofuran.

[0064]

Into the present invention, for the purpose of improving the elastic modulus, the flowability, and the like of the cured product, a filling material in an amount not impairing

storage stability may be added. Specific examples of the filling material include organic powder and inorganic powder. [0065]

Examples of the filling material of inorganic powder include, although not particularly limited, glass, fumed silica, alumina, mica, ceramics, silicone rubber powder, calcium carbonate, aluminum nitride, carbon powder, kaolin clay, dry clay mineral, and dry diatomaceous earth. The mixing amount of the inorganic powder is, based on 100 parts by mass of the component (C), preferably 0.1 to 100 parts by mass. [0066]

The fumed silica can be mixed for the purpose of adjusting the viscosity of the photocurable composition or improving the mechanical strength of the cured product. The fumed silica that has been surface-treated preferably with dimethylsilane, trimethylsilane, alkylsilane, methacryloxysilane, organochlorosilane, polydimethylsiloxane, hexamethyldisilazane, or the like is used. Examples of the product available on the market of the fumed silica include AEROSIL (registered trademark) R972, R972V, R972CF, R974, R976, R976S, R9200, RX50, NAX50, NX90, RX200, RX300, R812, R812S, R8200, RY50, NY50, RY200S, RY200, RY300, R104, R106, R202, R805, R816, T805, R711, RM50, and R7200 (manufactured by NIPPON AEROSIL CO., LTD.).

[0067]

Examples of the filling material of organic powder include, although not particularly limited, polyethylene, polypropylene, nylon, crosslinked acryl, crosslinked polystyrene, polyester, polyvinyl alcohol, polyvinyl butyral, and polycarbonate. The mixing amount of the organic powder is, based on 100 parts by mass of the component (A), preferably 0.1 to 100 parts by mass.

[0068]

Examples of the conductive filler include, although not particularly limited thereto, gold, silver, platinum, nickel, palladium, and coated particles having metal thin film coated
5 on an organic polymer particle.

[0069]

As the storage stabilizer, a radical absorbent such as benzoquinone, hydroquinone, and hydroquinone monomethyl ether, ethylenediamine tetraacetic acid or the 2-sodium salt
10 thereof, a metal chelating agent such as oxalic acid, acetylacetone, and o-aminophenol, or the like can be added.

[0070]

Examples of the antioxidant include a quinone-based compound such as β -naphthoquinone,
15 2-methoxy-1,4-naphthoquinone, methylhydroquinone, hydroquinone, hydroquinone monomethyl ether, mono-tert-butylhydroquinone, 2,5-di-tert-butylhydroquinone, p-benzoquinone, 2,5-diphenyl-p-benzoquinone, and
20 2,5-di-tert-butyl-p-benzoquinone; a phenol-based compound such as phenothiazine, 2,2-methylene-bis(4-methyl-6-tert-butylphenol), catechol, tert-butylcatechol, 2-butyl-4-hydroxyanisole, 2,6-di-tert-butyl-p-cresol,
25 2-tert-butyl-6-(3-tert-butyl-2-hydroxy-5-methylbenzyl)-4-methylphenyl acrylate, 2-[1-(2-hydroxy-3,5-di-tert-pentylphenyl)ethyl]-4,6-di-tert-pentylphenyl acrylate, 4,4'-butylidene bis(6-tert-butyl-3-methylphenol), 4,4'-thio
30 bis(6-tert-butyl-3-methylphenol), 3,9-bis[2-[3-(3-tert-butyl-4-hydroxy-5-methylphenyl)propionyloxy]-1,1-dimethylethyl]-2,4,8,10-tetraoxaspiro[5,5]

undecane, pentaerythritol
 tetrakis[3-(3,5-di-tert-butyl-4-hydroxyphenyl)
 propionate], thiodiethylene
 bis[3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate],
 5 octadecyl-3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionat
 e, N,N'-hexane-1,6-diyl
 bis[3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionamide],
 benzenepropanoic acid,
 3,5-bis(1,1-dimethylethyl)-4-hydroxy, C7 to C9 side-chain
 10 alkyl ester, 2,4-dimethyl-6-(1-methylpentadecyl)phenol,
 diethyl[[3,5-bis(1,1-dimethylethyl)-4-hydroxyphenyl]meth
 yl]phosphonate,
 3,3',3'',5,5',5''-hexa-tert-butyl-a,a',a''-(mesitylene-2,4,
 6-tolyl)tri-p-cresol, calcium diethyl
 15 bis[[3,5-bis(1,1-dimethylethyl)-4-hydroxyphenyl]methyl]p
 hosphonate, 4,6-bis(octylthiomethyl)-o-cresol, ethylene
 bis(oxyethylene)bis[3-(5-tert-butyl-4-hydroxy-m-tolyl)pr
 opionate], hexamethylene
 bis[3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate],
 20 1,3,5-tris(3,5-di-tert-butyl-4-hydroxybenzyl)-1,3,5-tria
 zine-2,4,6(1H,3H,5H)-trione,
 1,3,5-tris[(4-tert-butyl-3-hydroxy-2,6-xylyl)methyl]-1,3
 ,5-triazine-2,4,6(1H,3H,5H)-trione, a reaction product of
 N-phenylbenzenamine and 2,4,6-trimethylpentene,
 25 2,6-di-tert-butyl-4-(4,6-bis(octylthio)-1,3,5-triazine-2
 -ylamino)phenol, picric acid, and citric acid; a
 phosphorus-based compound such as
 tris(2,4-di-tert-butylphenyl)phosphite,
 tris[2-[[2,4,8,10-tetra-tert-butyl]dibenzo[d,f][1,3,2]dio
 30 xaphosphaphine-6-yl]oxy]ethyl]amine,
 bis(2,4-di-tert-butylphenyl)pentaerythritol diphosphite,
 bis[2,4-bis(1,1-dimethylethyl)-6-methylphenyl]ethyl ester

phosphorous acid,
tetrakis(2,4-di-tert-butylphenyl)[1,1-bisphenyl]-4,4'-di
ylbisphosphonite, and
6-[3-(3-tert-butyl-4-hydroxy-5-methylphenyl)propoxy]-2,4
5 ,8,10-tetra-tert-butylldibenz[d,f][1,3,2]dioxaphosphine;
a sulfur-based compound such as dilauryl
3,3'-thiodipropionate, dimyristyl 3,3'-thiodipropionate,
distearyl 3,3'-thiodipropionate, pentaerythrityl
tetrakis(3-laurylthiopropionate), and
10 2-mercaptobenzimidazole; an amine-based compound such as
phenothiazine; a lactone-based compound; and a vitamin
E-based compound. Among them, a phenol-based compound is
suitable.

[0071]

15 Examples of the silane coupling agent include
 γ -chloropropyl trimethoxysilane, octenyltrimethoxysilane,
glycidooctyltrimethoxysilane,
 β -(3,4-epoxycyclohexyl)ethyltrimethoxysilane,
 γ -glycidopropyltrimethoxysilane,
20 γ -mercaptopropyltrimethoxysilane, γ -aminopropyl
triethoxysilane, N- β -(aminoethyl)- γ -aminopropyl
trimethoxysilane, N- β -(aminoethyl)- γ -aminopropylmethyl
dimethoxysilane, γ -ureidopropyltriethoxysilane, and
p-styryltrimethoxysilane. The mixing amount of the silane
25 coupling agent is, based on 100 parts by mass of the component
(C), preferably 0.05 to 30 parts by mass, and more preferably
0.2 to 10 parts by mass.

[0072]

The photocurable composition of the present invention
30 can be produced by a known method. For example, the
photocurable resin composition can be produced by blending
components (A) to (D) each in a predetermined amount, and

by mixing the resultant mixture at a temperature of preferably 10 to 70°C, more preferably 20 to 40°C, for preferably 0.1 to 5 hours using a mixing measure such as a mixer.

[0073]

5 By irradiating the photocurable composition of the present invention with an active energy ray such as ultraviolet ray or visible light, preferably with ultraviolet ray, a cured product can be obtained. Wavelength of ultraviolet ray is preferably 315 to 400 nm. Examples of the light source include, 10 although not particularly limited, a low-pressure mercury lamp, a medium-pressure mercury lamp, a high-pressure mercury lamp, an ultrahigh-pressure mercury lamp, a black-light lamp, a microwave excited-mercury lamp, a metal halide lamp, a sodium lamp, a halogen lamp, a xenon lamp, an LED, a fluorescent 15 lamp, sunlight, and an electron beam irradiator. The irradiation amount of the light irradiation is, from the viewpoint of the characteristics of the cured product, preferably 10 kJ/m² or more, more preferably 20 kJ/m² or more, even more preferably 50 kJ/m² or more, and particularly 20 preferably 100 kJ/m² or more. Irradiation intensity for irradiating with active energy ray is preferably 10 to 300 mW/cm², more preferably 20 to 200 mW/cm², even more preferably 30 to 150 mW/cm², and particularly preferably 50 to 100 mW/cm². Irradiation time for irradiating with active energy ray is 25 preferably 10 seconds to 20 minutes, more preferably 20 seconds to 10 minutes, even more preferably 30 seconds to 300 seconds, and particularly preferably 60 seconds to 120 seconds.

[0074]

30 Examples of a use for which the photocurable composition of the present invention is suitably used include a covering agent, a casting resin, a seal agent, a sealing agent, a potting agent, an adhesive, a coating agent, a lining agent, and ink.

In particular, from the viewpoint obtaining a cured product having high concealing property and inhibited color fading in a high humidity and high temperature environment by irradiation with an active energy ray such as ultraviolet ray, the photocurable composition of the present invention preferably has a use as a covering agent, a casting resin, a seal agent, a potting agent, an adhesive, and a coating agent. Namely, one embodiment of the present invention relates to a photocurable composition which is used as a covering agent, a casting agent, a seal agent, a potting agent, an adhesive, or a coating agent.

[0075]

Particularly preferred use of the photocurable composition of the present invention includes a coating material for flexible wiring board, a casting resin, black stripes of a lens, an image display device, an optical member, a CMOS sensor, an adhesive for assembling a case body and lens, and a liquid crystal display seal agent for the purpose of preventing light leakage of back light, preventing penetration of external light, or the like.

Examples

[0076]

Hereinafter, the present invention will be further explained in detail by way of Examples, but should not be limited at all by these Examples. Furthermore, in the following examples, the operations were carried out at room temperature (20 to 25°C) unless specifically described otherwise. Furthermore, "%" and "parts" mean "% by mass" and "parts by mass", respectively, unless specifically described otherwise.

[0077]

Test methods that are used in Examples and Comparative Examples are as described below.

[0078]

<b1: Synthesis of 4-phenylthiophenyldiphenyl
5 sulfonium-tris(perfluoroethyl)trifluorophosphate salt>

To a reaction vessel, 6.1 parts by mass of diphenyl sulfoxide (manufactured by TOKYO CHEMICAL INDUSTRY CO., LTD.), 4.7 parts by mass of diphenyl sulfide (manufactured by KISHIDA CHEMICAL Co., Ltd.), and 21.5 parts by mass of methane sulfonic
10 acid (manufactured by TOKYO CHEMICAL INDUSTRY CO., LTD.) were added. After mixing, 4.0 parts by mass of acetic anhydride (reagent manufactured by JUNSEI CHEMICAL CO., LTD.) were added dropwise thereto. After the reaction for 6 hours at 50°C, cooling to room temperature was carried out. The resulting
15 reaction solution was added dropwise to a vessel added with 62.3 parts by mass of 20% by mass aqueous solution of potassium tris(pentafluoroethyl)trifluorophosphate followed by mixing for 1 hour at room temperature. The precipitates were extracted with 60 parts by mass of ethyl acetate to separate
20 the aqueous layer. The solvent was removed from the organic layer by distillation, and the obtained residues were dissolved by adding 25 parts by mass of toluene. In order to remove unreacted raw materials and impurities such as by-products, 135 parts by mass of hexane were added to the
25 toluene solution followed by thorough stirring at 10°C for 1 hour, and then the solution was allowed to stand. To separate the solution into 2 layers, the top layer was removed by liquid fractionation. To the remaining bottom layer, 75 parts by mass of hexane were added, followed by thorough stirring at
30 room temperature to have precipitation of crystals. The crystals were filtered and dried under reduced pressure to obtain 12.3 parts by mass of 4-phenylthiophenyldiphenyl

sulfonium-tris(perfluoroethyl)trifluorophosphate salt.

[0079]

<Preparation of photocurable composition>

Each component was taken in parts by mass shown in Table
5 1. According to mixing for 60 minutes at room temperature
(25°C) using a planetary mixer, a photocurable composition
was prepared. Then, various physical properties were
measured as described below. Furthermore, the specific
preparation amount was as shown in Table 1, and all the
10 numerical values were expressed in terms of parts by mass.

[0080]

<Component (A)>

a1: 3-Dibutylamino-6-methyl-7-anilinothiophene (ODB-2,
manufactured by Yamamoto Chemicals, Inc.)

15 <Component (B)>

b1: 4-Phenylthiophenyldiphenyl
sulfonium-tris(perfluoroethyl)trifluorophosphate salt

<Comparative component of the component (B)>

b'1: Diphenyl-4-(phenylthio)phenyl
20 sulfonium-hexafluorophosphate salt (CPI-100P, manufactured
by San-Apro Ltd.)

<Component (C)>

c1: Urethane acrylate oligomer (UV-3000B, manufactured
by The Nippon Synthetic Chemical Industry Co., Ltd)

25 c2: Isobornyl acrylate (Light acrylate IBX-A,
manufactured by KYOEISHA CHEMICAL CO., LTD.)

<Component (D)>

d1: 2-Hydroxy-2-methyl-1-phenyl-propan-1-one (DAROCUR
1173, manufactured by BASF Japan Ltd.). Test methods that
30 are used in Examples and Comparative Examples in Table 1 are
as described below.

[0081]

<Determination of outer appearance of cured product>

Each photocurable composition was irradiated with ultraviolet ray of 120 kJ/m^2 ($100 \text{ mW/cm}^2 \times 120 \text{ seconds}$) using an LED irradiator (365 nm) to obtain a cured product. Outer appearance of the resulting cured product was determined with

[0082]

<Color fading test of cured product (measurement of transmittance)>

Each photocurable composition was spread to thickness of 0.2 mm so as to obtain a test specimen with smooth surface. By irradiating it with ultraviolet ray of 120 kJ/m^2 ($100 \text{ mW/cm}^2 \times 120 \text{ seconds}$), a cured product was obtained. In addition, transmittance (550 nm) of the cured product was measured with spectrophotometer UV-2450 (manufactured by Shimadzu Corporation). Furthermore, from the viewpoint of having excellent concealing property of a cured product, the transmittance is preferably less than 10% at dry thickness of 0.2 mm.

[0083]

<Color fading test of black-colored cured product in high temperature and high humidity environment or in high temperature environment (measurement of transmittance)>

Each photocurable composition was spread to thickness of 0.2 mm so as to obtain a test specimen with smooth surface. By irradiating it with ultraviolet ray of 120 kJ/m^2 ($100 \text{ mW/cm}^2 \times 120 \text{ seconds}$), a cured product was obtained. Next, to determine any color fading of the cured product in a high temperature and high humidity environment or in a high temperature environment, the cured product was allowed to stand in a high temperature and high humidity (85°C and 85% RH) environment or in a high temperature (100°C) environment

for 40 hours. Then, transmittance (550 nm) of the cured product after standing was measured with spectrophotometer UV-2450 (manufactured by Shimadzu Corporation). Furthermore, from the viewpoint of having excellent concealing property of a cured product, the transmittance is preferably less than 10% at dry thickness of 0.2 mm.

[0084]

[Table 1]

Component		Example 1	Example 2	Comparative Example 1	Comparative Example 2
Component (A)	a1	1	1	1	1
Component (B)	b1	3	2		
	b'1			3	2
Component (C)	c1	30	30	30	30
	c2	70	70	70	70
Component (D)	d1	3	3	3	3
Outer appearance of cured product		Black color	Black color	Black color	Black color
Transmittance of cured product		0.5%	0.7%	0.7%	0.9%
Color fading property after high temperature and high humidity resistance test (85°C × 85% × 40h)		1.4%	1.2%	40%	37%
Color fading property after heat resistance test (100°C × 40h)		3.0%	2.0%	27%	15%

[0085]

According to Table 1, Examples 1 and 2 corresponding to the present invention have a photocurable composition which allows obtainment of a cured product with high concealing property by irradiation with an active energy ray such as ultraviolet ray and has inhibited color fading of the cured product in a high temperature and high humidity (85°C and 85% RH) environment or a high temperature (100°C) environment.

[0086]

Furthermore, when Comparative Examples 1 and 2 related

to the photocurable composition containing a photoacid generator (diphenyl-4-(phenylthio)phenyl sulfonium-hexafluorophosphate salt), which is not the component (B) of the present invention, are compared with
5 Examples of the present invention, color fading of a cured product caused under high temperature and high humidity or high temperature was shown, and thus they were found to be inferior in terms of inhibition of color fading. In particular, significant color fading of a cured product caused under high
10 temperature and high humidity was shown.

Industrial Applicability

[0087]

According to the photocurable composition of the present
15 invention, a cured product having high concealing property can be obtained by irradiation with an active energy ray such as ultraviolet ray, and color fading of the cured product in a high temperature and high humidity (85°C and 85% RH) environment or a high temperature (100°C) environment is
20 inhibited, and thus the photocurable composition can be suitably used for various adhesive applications. Specifically, it is very effective as a covering agent, a casting resin, a seal agent, a sealing agent, a potting agent, an adhesive, a coating agent, a lining agent, an adhesive,
25 and ink. As being applicable to a broad field, the photocurable composition of the present invention has an industrial applicability.

[0088]

Further, the application of the present invention is
30 not limited to the embodiments described above, and appropriate changes may be made in the range where the gist of the present invention is not impaired.

[0089]

This application is based on Japanese Patent Application
No. 2015-9606, filed in Japan on January 21, 2015, and the
content of the disclosure is hereby incorporated as its
5 entirety by reference.

CLAIMS

1. A photocurable composition comprising the following components (A) to (D):

5 component (A): a leuco dye;

component (B): a salt having an anion selected from the group consisting of $[P(Rf)_aF_{6-a}]^-$, $[Sb(Rf)_bF_{6-b}]^-$ and $[B(Rf)_cF_{4-c}]^-$ (in the formulae, Rf represents a fluoroalkyl group having 1 to 20 carbon atoms, a and b each independently represent an integer of from 1 to 5, and c represents an integer of from 1 to 3);

component (C): a radical polymerizable compound; and

component (D): a photoradical initiator.

15 2. The photocurable composition according to claim 1, wherein

the component (B) is a salt having an anion represented by $[P(Rf)_aF_{6-a}]^-$ (in the formula, Rf represents a fluoroalkyl group having 1 to 20 carbon atoms and a represents an integer of from 1 to 5).

3. The photocurable composition according to claim 1 or 2, wherein

25 the component (B) is a salt having a cation selected from the group consisting of an aryliodonium cation, an aryl sulfonium cation, and an aryldiazonium cation.

4. The photocurable composition according to any one of claims 1 to 3, wherein

30 the component (B) is a salt having an aryl sulfonium cation.

5. The photocurable composition according to any one of claims 1 to 4, wherein

[P(Rf)_aF_{6-a}]⁻ of the component (B) is an anion selected from the group consisting of [(CF₃CF₂)₃PF₃]⁻, [(CF₃CF₂CF₂)₂PF₄]⁻,
5 [(CF₃CF₂CF₂)₃PF₃]⁻, [(CF₃CF₂CF₂CF₂)₂PF₄]⁻, and [(CF₃CF₂CF₂CF₂)₃PF₃]⁻.

6. The photocurable composition according to any one of claims 1 to 5, wherein

10 the component (B) is at least one salt selected from the group consisting of triphenyl sulfonium-tris(perfluoroethyl)trifluorophosphate salt, triphenyl sulfonium-tris(perfluoropropyl)trifluorophosphate salt,
15 tri-p-tolyl sulfonium-tris(perfluoroethyl)trifluorophosphate salt, tri-p-tolyl sulfonium-tris(perfluoropropyl)trifluorophosphate salt, 4-phenylthiophenyldiphenyl
20 sulfonium-tris(perfluoroethyl)trifluorophosphate salt, and 4-phenylthiophenyldiphenyl sulfonium-tris(perfluoropropyl)trifluorophosphate salt.

7. The photocurable composition according to any one of claims 1 to 6, wherein

25 the component (B) is contained at 0.1 to 20 parts by mass relative to 100 parts by mass of the component (C).

8. The photocurable composition according to any one of claims 1 to 7, wherein

30 the component (C) contains an oligomer and a monomer.

9. The photocurable composition according to any one of claims 1 to 8, wherein

the component (D) is an acetophenone-based photoradical polymerization initiator or an acylphosphine oxide-based photoradical polymerization initiator.

10. The photocurable composition according to any one of claims 1 to 9, wherein

the photocurable composition is used for a covering agent, a casting agent, a seal agent, a potting agent, an adhesive, or a coating agent.