

ABSTRACT

A method of selectively etching a silicon nitride film includes a first step of disposing a target substrate having the silicon nitride film formed thereon in a processing space, a second step of introducing a gas containing H and F into the processing space, and a third step of selectively introducing radicals of an inert gas into the processing space.

(Fig. 7)

