

Description

The present invention relates to a shadow mask type color picture tube and, more particularly, to a shadow mask-screen system thereof.

In a shadow mask-type color picture tube shown in Fig. 1, an envelope formed of glass substantially consists of a rectangular panel 1, a funnel 2 and a neck 3. On an inner surface of the panel 1, for example, a stripe phosphor screen 4 which emits red, green and blue light is provided. On the other hand, in-line electron guns 6, which are linearly arranged along a horizontal axis of the panel 1 and emit three electron beams 10 corresponding to red, green and blue, are provided in the neck 3. A shadow mask 5 having a main surface portion in which a plurality of apertures are formed is disposed adjacent and opposed to the screen 4. A peripheral portion of the shadow mask 5 has a skirt portion 8 which is bent in correspondence with an outer shape of the panel 1. The skirt portion 8 is supported and fixed by a mask frame 7 consisting of a frame having an L-shaped cross-section. Furthermore, the mask frame 7 is engaged through a spring 9 with a pin (not shown) which is buried in an inner wall of the panel 1. In such a color picture tube, the three electron beams 10 emitted from the electron guns 6 are deflected by a deflection apparatus (not shown) provided near the funnel 2 of the outer portion of the envelope. The beams 10 are color-selected by the apertures of the shadow mask 5 while scanning a rectangular region substantially corresponding to the rectangular-shaped panel 1, and respectively and properly bombard on the corresponding color-emitting phosphor stripes, thereby forming a color image.

In this case, an effective amount of the electron beams 10 passing through the apertures of the shadow mask 5 is less than 1/3 of the total electron beam emitted from the electron guns 6. The remaining electron beam bombards on the shadow mask 5 and is converted into heat energy. For this reason, the shadow mask 5 can be heated to about 80°C. The shadow mask 5 comprises a thin plate having a thickness of 0.1 to 0.3 mm and is formed of cold-rolled steel mainly consisting of iron having a relatively large thermal expansion coefficient of $1.2 \times 10^{-5}/^{\circ}\text{C}$. The mask frame 7 which supports the skirt portion 8 of the shadow mask 5 is formed of the same cold-rolled steel as that of the shadow mask 5 and has a thickness of about 1 mm and an L-shaped cross-section. A surface of the mask frame 7 is oxidized, thereby forming a black oxide layer thereon. Thermal expansion of the shadow mask 5 which is heated by bombardment of the electron beams 10 can easily occur. However, since the peripheral portion of the shadow mask 5 is in contact with the mask frame 7 which has been subjected to darkening and has a large thermal capacity, heat is transferred to the mask frame 7 from the peripheral portion of the shadow mask 5 by radiation and conduction. Therefore, the temperature of the peripheral portion of the shadow mask 5 becomes

lower than that of the central portion thereof. For this reason, a so-called doming occurs in which the central portion of the shadow mask 5 is thermally expanded by a greater extent than the peripheral portion thereof. By this doming, the relationship between the position of the apertures of the shadow mask 5 and that of the phosphor stripes formed corresponding to the apertures is changed. Therefore, a landing error occurs in which the electron beams 10 transmitting through the apertures do not bombard on the proper phosphor stripes, resulting in degradation of color purity. Particularly, this doming is considerable at the initial operating state of the color picture tube. When an image of partial high brightness is formed, the doming partially occurs at the shadow mask 5 in the same manner as described above.

With respect to such a doming in the initial operating state of such a color picture tube, many suggestions have been made relating to the promotion of heat radiation from the central portion of a shadow mask or prevention of thermal conduction to the shadow mask. For example, in U.S.P. No. 2,826,538, it was proposed that a black layer formed of graphite be formed on a surface of a shadow mask so as to facilitate heat radiation of the shadow mask. In such a color picture tube, since this black layer serves as a good radiator, the temperature of the shadow mask is lowered. However, the black layer formed of graphite has the following drawbacks. Adhesion of the black layer is degraded due to a heat cycle in the heat treatment during the manufacturing process of the color picture tube. When vibration acts on the color picture tube, a part of the black layer is separated, thereby causing microparticles to drop off. If these particles of the black layer become attached to the shadow mask, the apertures formed thereon are closed, resulting in degradation of the image quality on the phosphor screen. On the other hand, if the particles become attached to the electron gun, a spark between electrodes is induced, thereby degrading the quality of the color picture tube, and, in particular, causing degradation of the break-down voltage.

In U.S.P. No. 3,887,929 as a second example, a color picture tube was proposed. In this color picture tube, a porous layer of manganese dioxide is deposited at a side of an electron gun of a shadow mask, and an aluminum layer and a nickel oxide or nickel-iron layer are sequentially formed thereon by vacuum evaporation. In this case, since the thermal conduction coefficient of the porous layer is extremely small, heat caused by bombardment of an electron beam is not transmitted to the shadow mask but is radiated in a direction away from the shadow mask. For this reason, the temperature increase of the shadow mask can be effectively controlled. However, in order to provide three layers on a surface of the shadow mask, considerable equipment and operation time are needed, resulting in poor mass-productibility.

A cathode ray tube with a shadow mask having a layer on a major surface is also known under Article 54(3) of the EPC from EP-A-0 139 379. The layer consists essentially of a ceramic material which is bonded to the major surface and which has a coefficient of thermal expansion that is smaller at the same temperature than the coefficient of thermal expansion of the shadow mask so that the shadow mask has residual tensile stress.

It is an object of the present invention to provide a color picture tube in which a doming of the shadow mask in the initial operation state of a color picture tube is minimized, and degradation of color purity due to mis-registration of electron beams can be prevented, and which has good mass-productibility.

In order to achieve the above object of the present invention, there is provided a color picture tube comprising: an envelope; a phosphor screen formed on an inner surface of said envelope; a shadow mask which is disposed in a vicinity of said phosphor screen and which has a main surface portion with a number of apertures; and an electron gun for emitting electron beams which are selectively transmitted through said apertures and bombard said phosphor screen so as to emit multi-color light. A layer essentially consisting of a ceramic material is chemically bonded to a surface of at least an electron gun side of the main surface portion of the shadow mask. A conductive layer is formed on the ceramic material layer.

A material for the ceramic material layer in the color picture tube according to the present invention may be selected from any one of the materials which have smaller thermal expansion coefficients than that of a metal of the shadow mask, so that a residual tensile stress is left in the shadow mask when the layer is chemically bonded by a heat treatment to the one main surface of the shadow mask. The material for the ceramic material layer preferably comprises glass and more preferably lead borate glass. In addition to the ceramic material layer on the electron gun side of the main surface portion, the ceramic material layer may also be formed on the other surface of the main surface portion of the shadow mask.

The conductive layer formed on the ceramic material layer can comprise Ba, Al, or Mg but preferably comprises a getter layer such as a layer of Ba which has a getter effect.

According to the present invention, when the ceramic layer is formed by the heat treatment on a surface of the shadow mask, a residual tensile stress can occur in the shadow mask due to a difference between thermal expansion coefficients of the shadow mask and the ceramic material. For this reason, expansion of the shadow mask can be suppressed even if the temperature elevates due to bombardment of electron beams onto the shadow mask during the operation of the color picture tube. As a result, a change in the relationship between the position of

apertures of the shadow mask and phosphor stripes can also be reduced. Because a layer essentially consisting of a ceramic material has an extremely high insulation resistance, it becomes statically charged when electron beams hit thereon. Although this static charge on the ceramic layer prevents passing of electron beams through apertures of the shadow mask or irregularly deflects electron beams to cause misregistration, a conductive layer such as getter layer formed on the ceramic layer can prevent this static charge.

As described above, according to the present invention, the doming of a shadow mask can be effectively reduced and color purity degradation such as mis-registration and color irregularities can be prevented without the need for considerable manufacturing equipment and working time, thereby rendering it a valuable industrial process.

This invention can be more fully understood from the following detailed description when taken in conjunction with the accompanying drawings, in which:

Fig. 1 is a sectional view showing a general arrangement of a shadow mask type color picture tube;

Figs. 2A to 2C are views for explaining a bonding phenomenon between glass and metal; and

Fig. 3 is a graph for explaining a thermal expansion phenomenon of a solid material.

A color-picture tube according to an embodiment of the present invention will be described with reference to the accompanying drawings. The overall construction of the color picture tube is the same as that of the conventional color picture tube shown in Fig. 1, and a detailed description thereof will be omitted.

A layer having as a major constituent a ceramic material such as crystalline lead borate glass particles "ASF-1307" (tradename) available from Asahi Glass Co., Ltd. was formed on a concave surface at an electron gun side of a shadow mask 5 in the color picture tube in Fig. 1. The shadow mask 5 was arranged in the vicinity of a screen 4. The formation of the layer having crystalline lead borate glass particles as the major constituent was performed in the following manner. Lead borate glass particles having an average particle size of about 5 μm were dispersed in solution of butyl acetate dissolved in the amount of several % in an alcohol, e.g., 2% of nitrocellulose to prepare a suspension slurry or paste. The resultant suspension slurry or paste was coated on the concave surface to a thickness of 20 to 30 μm . The shadow mask 5 coated with a layer containing the glass particles was mounted at an inner side of a panel 1. Hereafter, the panel 1 and a funnel 2 were placed on a predetermined frame and were heated under a heat treatment furnace at a maximum temperature of about 440°C for over 35 minutes, thereby hermetically jointing the panel 1 and the funnel 2. At the same time, a crystallized lead borate glass layer was chemically bonded to



a dark oxide layer formed on an electron gun side of the shadow mask. This lead borate glass crystallizes with the PbO content of 44 to 93% by weight. The lead borate glass crystallizes more stably and preferably with the PbO content of 70 to 85% by weight. When electron beams are bombarded against the glass layer, the glass layer is heated to a temperature of higher than 300°C. In this manner, amorphous glass is not preferred since it flows at temperature above a softening point (350 to 600°C for lead borate glass). Therefore, crystalline glass is preferred since it has a high resoftening point.

In order to crystallize lead borate glass, a furnace is required which is capable of heating the glass at a maximum temperature of 400 to 600°C for over 30 minutes. When a heat treatment step by this furnace is performed separately, this leads to an industrial disadvantage. However, if the heat treatment for crystallization can be performed when the panel 1 is hermetically jointed with the funnel 2, it results in an industrial advantage. A shadow mask assembly as a combination of the shadow mask and the mask frame is stabilized together with the panel at a temperature of 400 to 450°C. If the glass crystallization can be performed in the stabilization step, mass production can be easily performed. When a fusing temperature and a stabilization temperature do not coincide with an optimal temperature of glass crystallization, ZnO or CuO may be added to lead borate glass to set an optimal temperature for glass crystallization. A thermal expansion coefficient of the shadow mask 5 made of a cold rolled steel plate is about $1.2 \times 10^{-5}/^{\circ}\text{C}$ at the jointing temperature of the panel 1 and the funnel 2. The lead borate glass layer containing 70 to 85% by weight of PbO has a thermal expansion coefficient of 0.7 to $1.2 \times 10^{-5}/^{\circ}\text{C}$ at about the jointing temperature. When the thermal expansion coefficient of the shadow mask is larger than that of glass, residual tensile stress occurs in the shadow mask, while residual compression stress occurs in glass.

As shown in Fig. 2A, when a metal 12 and a glass 11 are heated to a high temperature, e.g., 440°C before bonding, the length L of both materials is the same. In this state, as shown in Fig. 2B, when both materials are cooled to a normal temperature without bonding, since a thermal expansion coefficient of the metal is selected to be slightly larger than that of the glass, the relationship between the both length becomes $l_g > l_m$. On the other hand, as shown in Fig. 2C, when the metal 12 and the glass 11 are bonded at a high temperature and are cooled to a normal temperature, the glass shrinks more under the influence of the metal. On the other hand, shrinkage of the metal is reduced due to bonding with the glass. Therefore, lengths at a normal temperature of these materials after bonding satisfy $l_g > l > l_m$. As a result, a compression stress P_c remains in the glass, and a tensile stress P_t remains in the metal as residual stresses.

The lead borate glass layer is preferably formed such that its compression strength is about 10 times the tensile strength. The lead borate glass layer containing 70 to 85% by weight of PbO and having the thermal expansion coefficient of 0.7 to $1.2 \times 10^{-5}/^{\circ}\text{C}$ can be bonded to the cold rolled steel plate having the thermal expansion coefficient of about $1.2 \times 10^{-5}/^{\circ}\text{C}$. When the thickness of the lead borate glass layer is excessively large, a stress acting on the mask is excessively increased to deform the mask. In this sense, the lead borate glass layer preferably has a thickness of 20 μm to 30 μm .

A conductive layer such as a getter layer can be formed on the surface of the lead borate glass layer which is located at the side of the electron gun in such a manner that a boat containing a dispersing getter comprising an intermetallic compound of Ba and Al and Ni having a ratio of 1:1 is incorporated in the envelope to oppose the shadow mask, and that the envelope is evacuated and the boat is heated by RF heating. In this case, the getter layer adsorbs gas generated within the color picture tube.

When the color picture tube having the structure as described above is operated, the temperature of the shadow mask is increased by the heat generated in the crystalline lead borate glass on which the electron beams bombard. However, since the residual tensile stress acts on the shadow mask, thermal expansion of the shadow mask in the initial state can be considerably suppressed.

This mechanism will be described with reference to Fig. 3. Fig. 3 is a graph showing a potential energy existing between atoms (ordinate) as a function of a distance between atoms of material (abscissa). Since vibrations of atoms at a given temperature are not harmonic, a potential energy curve becomes asymmetrical with a potential energy point Z at absolute zero. Therefore, in Fig. 3, an average distance between atoms which respectively vibrate between positions corresponding to A and B at a normal temperature is given as a_n . Energy is increased in accordance with an increase in temperature, and if atoms vibrate at positions corresponding to C and D, an average distance between atoms becomes a_h due to asymmetry of the potential energy curve. Therefore, atoms are displaced from their equilibrium positions in accordance with an increase in amplitude of vibration. An average displacement $\Delta l = a_h - a_n$ of atoms in a solid body is known to be the cause for thermal expansion.

There will now be discussed the thermal expansion of the shadow mask in the case where, as the present invention, a residual tensile stress remains in the shadow mask by forming the crystalline glass layer on one surface of the shadow mask. In this case, the distance between atoms which constitute the shadow mask is extended by the residual tensile stress. This is expressed using Fig. 3, the ordinate, i.e., an amount of potential energy is constant, and the abscissa, i.e., a unit length of a distance between

atoms, is extended from u to u_T (new abscissa is shown by a dotted line). Therefore, thermal expansion of $a_H - a_R = \Delta l$ conventionally occurs by an increase in temperature of the shadow mask due to bombardment of electron beams (abscissa is shown by a solid line). However, in the shadow mask according to the present invention, since residual stress exists, thermal expansion of only $A_H - A_R = \Delta l_T$ occurs. As described above, since a unit length u of the abscissa shown by the solid line is smaller than a unit length u_T of the abscissa shown by the dotted line, the relationship between a conventional thermal expansion amount Δl and a thermal expansion amount Δl_T according to the present invention becomes

$$\Delta l_T = (u/u_T) \times \Delta l.$$

Therefore, as is apparent from the above description, the thermal expansion amount Δl_T of the shadow mask according to the present invention is smaller than that of the conventional one.

Furthermore, when the crystalline lead borate glass layer is formed at the side of the electron gun of the shadow mask as in this embodiment, since the thermal conductivity of the crystalline lead borate glass is extremely small, the amount of heat, which is generated by bombardment of electron beams on the surface of the crystalline lead borate glass and is radiated before it is transmitted to the shadow mask, is increased in comparison to the conventional shadow mask, resulting in satisfactory control of temperature increase of the shadow mask.

The lead borate glass has a very high insulating property, i.e., an electric conductivity of $10^{-15} \Omega^{-1} m^{-1}$. When electron beams are directly bombarded on the lead borate glass layer, the layer is charged and may influence the subsequent electron beams. For example, the subsequent electron beams will not be transmitted through the apertures, or the trajectory of the electron beams changes. However, according to the present invention, since the conductive layer such as the getter layer is formed on the surface of the lead borate glass layer which is located at the side of the electron gun, such a charge-up phenomenon can be prevented. In this case, the conductive layer must be electrically connected to the shadow mask. When the conductive layer is formed in a wide area exceeding the area of the lead borate glass layer (e.g., when the lead borate glass layer is formed to the peripheral portion of the shadow mask), the conductive layer can be electrically connected to the shadow mask with ease.

Another conductive layer excluding the getter layer as the conductive layer, such as an Al layer, may be formed by vacuum evaporation. However, this step is an additional step and will not always be a preferable step in mass production.


An application in which the present invention is applied to a 21-inch color picture tube will now be described. A suspension containing lead borate glass particles ("ASF-1307"; available from Asahi

Glass Co., Ltd.) having a thermal expansion coefficient of about $1.0 \times 10^{-5} / ^\circ C$ near the softening point was coated on a major surface on the electron gun side of the shadow mask, which was formed of cold rolled steel plate of a thickness of 0.22 mm in the above-mentioned manner. Thereafter, the resultant structure was heat treated so as to vitrify the glass in hermetically jointing the panel and the funnel, thereby obtaining a crystalline glass layer having a thickness of about 25 μm . The adopted shadow mask has a radius of curvature in a horizontal direction of about 1,000 mm, a horizontal pitch of phosphor stripes of about 260 μm , and a light-absorbing area of about 120 μm between respective phosphor stripes. After the electron gun was incorporated in the envelope, getter flash was performed to form a getter layer made of Ba on the crystalline glass layer.

Such a color picture tube was operated at an anode voltage of 25 kV and an anode average current of 1,500 μA . The maximum displacement along a horizontal direction of the electron beams after five minutes from the start of the operation was checked. A measuring point is a portion spaced about 140 mm apart from an image center along a horizontal direction at which the doming easily occurs. In this color picture tube, electron beams land on one phosphor stripe and two neighbouring light-absorbing stripes (negative landing). Luminance is decreased by a constant displacement even if the landing point is not moved to the next phosphor stripe. Particularly, with reference to the green phosphor which considerably affects luminance, the landing tolerance of the electron beam of the electron gun is about 75 μm . In this color picture tube, the mislanding amount of the electron beam was about 85 μm when the present invention was not adopted, and that of the electron beam according to the present invention was about 66 μm . Then, it was confirmed that the electron beam of the present invention was sufficiently within the allowed tolerance. In other words, thermal expansion in accordance with the increase in the residual tensile stress of the shadow mask by the crystalline glass layer, and an increase in temperature in accordance with the decrease in the thermal conductivity by the crystalline glass layer are effectively controlled.

The getter layer as the conductive layer is formed on the crystalline glass layer, so mislanding of electron beams which is caused by charge-up of the crystalline glass layer will not occur.

According to the present invention, the shadow mask can be effectively suppressed without accompanying increases in manufacturing equipment volume and work time, thereby improving color mis-registration and irregularity. In addition, the charge-up phenomenon of a ceramic material layer on the surface of the shadow mask can be prevented, thus providing great industrial advantages.





Claims

1. A color picture tube comprising: an envelope; a phosphor screen (4) formed on an inner surface of said envelope; a shadow mask (5) which is disposed in said envelope and in a vicinity of said phosphor screen (4) and which has a main surface portion with a number of apertures; and an electron gun (6) for emitting electron beams (10) which are selectively transmitted through said apertures and are bombarded on said phosphor screen (4) so as to emit multi-color light, wherein a layer having a ceramic material as a major constituent is chemically bonded so that surface of the main surface portion of the shadow mask which is located at a side of said electron gun (6), and a conductive layer is formed on said layer.

2. A color picture tube according to claim 1, characterized in that the ceramic material comprises crystalline glass.

3. A color picture tube according to claim 2, characterized in that the crystalline glass comprises crystalline lead borate glass.

4. A color picture tube according to claim 1, characterized in that said conductive layer comprises a getter layer.

5. A color picture tube according to claim 4, characterized in that said getter layer comprises barium.

6. A color picture tube according to claim 1, characterized in that said conductive layer comprises an aluminum layer.

7. A color picture tube according to claim 1, characterized in that said conductive layer is electrically connected to said shadow mask (5).

8. A color picture tube according to claim 7, characterized in that said conductive layer extends to a surface portion of said shadow mask (5) on which said layer having a ceramic material is not formed, thus being electrically connected to said shadow mask (5).

Patentansprüche

1. Farbbildröhre, umfassend:
einen Kolben,
einen Leuchtstoffschirm (4), der an einer Innenfläche des Kolbens ausgebildet ist,
eine Lochmaske (5), die im Kolben in der Nähe des Leuchtstoffschirms (4) angeordnet ist und einen Hauptflächenabschnitt mit einer Anzahl von Öffnungen aufweist, und
ein Elektronenstrahlsystem (6), das Elektronenstrahlen (10) aussendet, die selektiv durch die Öffnungen laufen und auf den Leuchtstoffschirm (4) treffen, so daß mehrfarbiges Licht ausgesendet wird,

wobei eine Schicht mit einem Keramikmaterial als Hauptbestandteil chemisch an diejenige Oberfläche des Hauptoberflächenteils der Lochmaske gebunden ist, die auf der Seite des Elektronenstrahlsystems (6) liegt, und eine leitende Schicht auf jener Schicht ausgebildet ist.

2. Farbbildröhre nach Anspruch 1, dadurch gekennzeichnet, daß das Keramikmaterial kristallines Glas umfaßt.

3. Farbbildröhre nach Anspruch 2, dadurch gekennzeichnet, daß das kristalline Glas kristallines Bleiboratglas ist.

4. Farbbildröhre nach Anspruch 1, dadurch gekennzeichnet, daß die leitende Schicht eine Getterschicht umfaßt.

5. Farbbildröhre nach Anspruch 4, dadurch gekennzeichnet, daß die Getterschicht Barium umfaßt.

6. Farbbildröhre nach Anspruch 1, dadurch gekennzeichnet, daß die leitende Schicht eine Aluminiumschicht umfaßt.

7. Farbbildröhre nach Anspruch 1, dadurch gekennzeichnet, daß die leitende Schicht elektrisch mit der Lochmaske (5) verbunden ist.

8. Farbbildröhre nach Anspruch 7, dadurch gekennzeichnet, daß die leitende Schicht dadurch elektrisch mit der Lochmaske (5) verbunden ist, daß sie sich zu einem von der ein Keramikmaterial aufweisenden Schicht freien Oberflächenabschnitt der Lochmaske (5) erstreckt.

Revendications

1. Tube-image en couleurs, comprenant une enveloppe, un écran électroluminescent (4) formé sur une surface interne de l'enveloppe, un masque (5) disposé dans l'enveloppe et au voisinage de l'écran électroluminescent (4) et ayant une partie principale de surface ayant un certain nombre d'ouvertures, et un canon à électrons (6) destiné à émettre des faisceaux d'électrons (10) qui sont transmis sélectivement par les ouvertures et bombardent l'écran électroluminescent (4) afin que de la lumière soit émise avec plusieurs couleurs, dans lequel une couche ayant un matériau céramique comme constituant principal est fixée chimiquement à la surface de la partie principale de surface du masque qui se trouve du côté du canon à électrons (6), et une couche conductrice est formée sur ladite couche.

2. Tube-image en couleurs selon la revendication 1, caractérisé en ce que le matériau céramique est un verre cristallin.

3. Tube-image en couleurs selon la revendication 2, caractérisé en ce que le verre cristallin est un verre cristallin de borate de plomb.


4. Tube-image en couleurs selon la revendication 1, caractérisé en ce que la couche conductrice est une couche d'un matériau de piégeage.

5. Tube-image en couleurs selon la revendication 4, caractérisé en ce que la couche du matériau de piégeage est formée de baryum.

6. Tube-image en couleurs selon la revendication 1, caractérisé en ce que la couche conductrice est une couche d'aluminium.

7. Tube-image en couleurs selon la revendication 1, caractérisé en ce que la couche conductrice est reliée électriquement au masque (5).

8. Tube-image en couleurs selon la revendication





11

EP 0 137 411 B1

12

tion 7, caractérisé en ce que la couche conductrice est disposée sur une partie de la surface du masque (5) sur laquelle ladite couche ayant le

matériau céramique n'est pas formée, si bien qu'elle est reliée électriquement au masque (5).

5

10

15

20

25

30

35

40

45

50

55

60

65

7