

DESCRIPTION

TITLE OF THE INVENTION: CATALYST AND PROCESS FOR PRODUCING THE SAME

TECHNICAL FIELD

5 [0001] This invention relates to a high-degree use of natural gas, biogas and methane hydrate, in which methane is a main component. Natural gas, biogas and methane hydrate are regarded as the most effective energy resources as a measure to counter global warming, and therefore an interest in techniques using them has grown. Methane resource attracts attention
10 as a novel organic resource in the next generation or as a hydrogen resource for use in fuel cells, by making use of its clean characteristic. The present invention relates to a catalytic, chemical conversion technique and a catalyst production method, for efficiently producing aromatic compounds, in which benzene and naphthalene are main components, which are raw materials of
15 chemical products, such as plastics, and a high purity hydrogen gas, from methane.

BACKGROUND TECHNIQUE

[0002] As a process for producing aromatic compounds, such as benzene, and hydrogen from methane, one is known in which methane is reacted in
20 the presence of a catalyst. As the catalyst on this occasion, molybdenum supported on a ZSM-5 series zeolite is said to be effective (Non-patent Publication 1, Patent Publication 1, and Patent Publication 2). Even in the case of using these catalysts, however, there occur problems that carbon is precipitated in a large amount, and the carbon precipitation causes the
25 catalyst activity to deteriorate in a short time and causes conversion of methane to be low.

[0003] In order to improve this problem, there has been a study in which the catalyst is shaped into pellet type, which is usable in a fixed bed type reaction facility, and the proportion of the catalyst component contained in
30 the pellets is increased to achieve an efficient reaction with methane. In the case of the fixed bed reaction type, however, there has been a problem,

since it becomes essential to use at least 10% of inorganic and organic caking agents in terms of mechanical strength, and since the size is limited to millimeter unit or more.

5 [0004] As shown in Patent Publication 3, there is also a study on the catalyst having a grain shape that is usable in a flow bed type reaction facility. However, the proportion of the catalyst component existing in the grains becomes 50% or lower from the viewpoints of wear resistance and impact resistance. This is inferior to the pellet type of a fixed bed type of the mechanical strength adjustment. Furthermore, since the catalyst is
10 deactivated in a short period of time, it is essential to regenerate the catalyst.

PRIOR ART PUBLICATIONS

NON-PATENT PUBLICATION

[0005] Non-patent Publication 1: JOURNAL OF CATALYSIS, 1997, pp. 165,
15 pp. 150-161

PATENT PUBLICATIONS

[0006] Patent Publication 1: Japanese Patent Application Publication
Heisei 10-272366

Patent Publication 2: Japanese Patent Application Publication Heisei
20 11-60514

Patent Publication 3: Japanese Patent Application Publication Showa
61-266306

SUMMARY OF THE INVENTION

TASK TO BE SOLVED BY THE INVENTION

25 [0007] In order to improve conversion of methane, it is essential to improve the efficiency of the contact between the reaction gas and the catalyst. The catalyst shape also gives a large influence to the reaction process. The shape is roughly classified into a pellet-type shaped body for fixed bed and granules for flow bed and moving bed. In the pellet-type shaped body, it is
30 necessary to have materials other than the catalyst, which are necessary upon shaping, such as organic caking additive, inorganic caking additive,

glass fibers, and pore-forming material. Thus, it is also necessary to consider the influence of these additives on the catalyst.

[0008] In the case of granules, there is an advantage that the efficiency of contact with the reaction gas is improved due to their small particle size of several tens of micrometers to several hundreds of micrometers. On the other hand, it is necessary to make the granules themselves flow in the reaction process. Therefore, it is essential that the granules are superior in wear resistance and thermal impact resistance. To satisfy these, it is necessary to mix or coat the granules with a large amount of the caking additive, besides the catalyst material. In particular, according to Patent Publication 3, it is possible to obtain roughly spherical granules of the catalyst by spray drying only a raw material zeolite powder slurry, but they are easily broken by the action of transportation or the like and vibration. Therefore, it is necessary to mix a suitable caking agent, besides the raw material zeolite powder.

MEANS FOR SOLVING THE TASK

[0009] Thus, a catalyst production process for solving the task is a catalyst production process for producing aromatic compounds and hydrogen from a lower hydrocarbon. It obtains granules of the catalyst by drying by a spray drying method a slurry containing a catalyst powder obtained by milling a metallosilicate-containing raw material.

[0010] Furthermore, the catalyst for solving the task is a catalyst prepared by the production process.

[0011] The metallosilicate-containing raw material may be one containing a metallosilicate having micropores of a size that is substantially 4.5 to 6.5 angstroms. It is better to mill the metallosilicate raw material by a bead mill such that the particle size of the metallosilicate becomes 1.0 μ m or less at a cumulative frequency of 50%. It is better that at least one metal component selected from rhenium, vanadium, molybdenum, tungsten, chromium, and their compounds is supported on the metallosilicate. It is better that the amount of the molybdenum supported is 2-12 weight %

relative to the total amount of the catalyst powder. It is better to dry the slurry by the spray drying method after aging. As the aging, it is possible to mention standing still under an atmosphere of an air of normal temperature and normal pressure. It is better that the metal component is supported on the metallosilicate by adding the metal component to the slurry. Furthermore, it is optional to add polyvinyl alcohol (hereinafter referred to as PVA) to the slurry.

ADVANTAGEOUS EFFECT OF THE INVENTION

[0012] According to the above-mentioned catalyst production process of the invention, it is possible to provide a catalyst in which granules of the catalyst are improved in crash strength with no use of the caking agent, while increasing the effective area of the crystalline surface part of the catalyst.

BRIEF DESCRIPTION OF THE DRAWING

[0013] Fig. 1 is an SEM photograph (accelerating voltage: 15.0kV; magnification: 1,000) of granules of Example 1;

Fig. 2 is an SEM photograph (accelerating voltage: 15.0kV; magnification: 20,000) of granules of Example 1;

Fig. 3 is an SEM photograph (accelerating voltage: 15.0kV; magnification: 1,000) of granules of Example 2;

Fig. 4 is an SEM photograph (accelerating voltage: 15.0kV; magnification: 20,000) of granules of Example 2;

Fig. 5 is an SEM photograph (accelerating voltage: 15.0kV; magnification: 1,000) of granules of Example 4;

Fig. 6 is an SEM photograph (accelerating voltage: 15.0kV; magnification: 5,000) of granules of Example 4;

Fig. 7 is an SEM photograph (magnification: 1,000) showing distributions of elements (O, Al, Si, and Mo) on the surface of granules of Example 4;

Fig. 8 is an SEM photograph (magnification: 10,000) showing distributions of elements (O, Al, Si, and Mo) on the surface of granules of

Example 4;

Fig. 9 is an SEM photograph (accelerating voltage: 15.0kV; magnification: 1,000) of granules of Example 5;

Fig. 10 is an SEM photograph (accelerating voltage: 15.0kV; magnification: 5,500) of granules of Example 5; and

Fig. 11 is an SEM photograph (magnification: 10,000) showing distributions of elements (O, Al, Si, and Mo) on the surface of granules of Example 5.

MODE FOR CARRYING OUT THE INVENTION

[0014] In a catalyst-containing slurry in which a metallosilicate-containing raw material has been milled and highly dispersed by a bead mill, it is converted to granules by spray drying immediately after the slurry preparation or after conducting aging for a given period of time in the catalyst production process according to the present invention. It is possible to conduct the aging by allowing the slurry to stand still under an atmosphere of an air of normal temperature and normal pressure.

[0015] (1) CATALYST SUPPORT

The metallosilicate-containing raw material contains as a catalyst material at least one metal component selected from rhenium, vanadium, molybdenum, tungsten, chromium, and their compounds and contains as a support, which supports this catalyst material, a metallosilicate having micropores of a size that is substantially 4.5 to 6.5 angstroms. The metallosilicate is illustrated in Japanese Patent Application Publication 2004-97891. Specifically, as the metallosilicate (a porous metallosilicate), for example, in the case of aluminosilicate, it is possible to mention molecular sieve 5A, faujasite (NaY and NaX), ZSM-5, and MCM-22, which are porous bodies formed of silica and alumina. Furthermore, it can be exemplified by a zeolite support, which is a porous body, in which phosphoric acid is a major component, and which is characterized by comprising micropores or channels of 6-13 angstroms, such as ALPO-5 and VPI-5, and a mesomicroporous support, which contains silica as a major component and

partially contains alumina as a component, and which is characterized by cylindrical micropores (channels) of mesomicro pores (10-1,000 angstroms), such as FSM-16 and MCM-41. Furthermore, besides the aluminasilicate, a metallosilicate formed of silica and titania, etc. can also be used as the catalyst.

[0016] (2) SUPPORTING OF SUPPORTED METAL ON CATALYST SUPPORT

It is a preferable method in which molybdenum of a predetermined concentration is supported by impregnation on a metallosilicate as a support.

10 The amount of molybdenum supported is preferably 2-12 wt% relative to the total amount of the catalyst after baking.

[0017] It is better to add PVA to the slurry. In the case of baking granules obtained by drying by the spray drying method the slurry containing the catalyst powder milled by a bead mill, gas is generated in the granules during the baking. With this, the spherical granules burst, and there occurs a phenomena to generate defects in the spherical granules. If PVA is added, PVA is vaporized and removed during the baking to produce many micropores in the granules. The gas escapes from this gas pore to the outside. With this, it is possible to prevent the burst and generation of the defects. The amount of PVA to be added is preferably 0.1-1 wt% relative to the metallosilicate in the slurry.

[0018] (3) MILLING OF CATALYST POWDER

There is mentioned a process for preparing a slurry obtained by milling by a bead mill a metallosilicate raw material or a metallosilicate, which supports the metal component, into 1 micrometer or less. The metallosilicate raw material or the metallosilicate supporting the metal component (hereinafter, catalyst powder) is weighed relative to water to make a slurry solution, for example, to have a ratio of catalyst powder : water = 1:4. The mixing ratio is not limited to this, and it is preferable to make a suitable adjustment depending on the properties of the metallosilicate used. The slurry viscosity on that occasion is preferably

100cps or lower. Upon mixing the catalyst powder and water, the total amount of water is previously put into a mixer, and then the catalyst powder is added under stirring by adjusting at about 0.4-1kg per minute. If it is faster than this, the catalyst powder coagulates and precipitates in the mixer.

5 Therefore, it is not preferable. On this occasion, there is used one that can arbitrarily set the blade shape and the speed of rotation.

In particular, the blade shape and the speed of rotation are not limited.

[0019] Zirconia is preferable for the milling beads used in the bead mill.

[0020] By using the bead mill of the above specification, a hose pump for
10 circulating the slurry is energized to conduct milling of the catalyst powder. The milling can be adjusted together with the bead size and the time. It is better to mill the metallosilicate raw material by the bead mill such that the particle size of the metallosilicate becomes 1.0 μ m or less at a cumulative frequency of 50%. For example, in the case of ZSM-5 raw material of an
15 average particle size of 42 μ m, a milling to 0.3 μ m becomes possible by a milling time of 1 hour. The slurry obtained by milling the catalyst powder is recovered by switching the supply line from closed system to open system.

[0021] (4) GRANULATION

A method for drying and granulating the catalyst powder in the
20 slurry with a spray dryer is mentioned. It is preferable to directly dry and granulate the slurry prepared by (3) with a spray dryer or use it after aging for a given time (e.g., 6 days). Although the type of the spray dryer is not particularly limited, a downward spray, parallel flow system is preferable. The nozzle is preferably of a two-liquid nozzle system. It is preferable to
25 suitably change the orifice diameter, depending on the slurry viscosity and the particle shape of the catalyst powder. Operation condition of the spray dryer is suitably adjusted depending on the slurry viscosity and the particle size of the catalyst powder in the slurry. The operation condition is not particularly limited.

30 [0022] According to the catalyst production process of the present invention, it is possible to provide a catalyst that has an increased effective area of the

catalyst crystal surface part by milling of the catalyst powder of nanometer size and that has an improved crash strength of the catalyst granules even if no caking agent is added. Therefore, it becomes easily possible to produce spherical granules, which has been difficult in rolling granulation method.

5 Furthermore, it becomes possible to omit or greatly reduce the inorganic caking agent. With this, it becomes easy to support the metal on the catalyst powder contained in the granules.

[0023] Furthermore, it becomes easy to uniformly support the metal on the catalyst powder and is possible to provide a catalyst that is superior in flow
10 property of the granules and is improved in crash strength, by impregnating the catalyst powder with the metal component by adding the metal component to the milled catalyst powder-containing slurry. Crash strength of the granules becomes further higher by adding PVA to the slurry.

[0024] In the following, examples according to the invention and
15 comparative example are shown.

[0025] (COMPARATIVE EXAMPLE 1)

As a catalyst powder according to Comparative Example 1, there was used a type of metallosilicate, a proton-type ZSM-5, having an average
particle size of 31 μ m and a crystalline size of 0.08 μ m. The particle size and
20 crystalline size were measured by calculating the average values of the particles selected at random from an electron microscope photograph. A slurry was prepared to have a solid matter concentration of 20wt% by using purified water as solvent.

[0026] This slurry was stirred for 1hr and then granulated by a spray dryer
25 (Type DL-41 made by YAMATO SCIENTIFIC CO., LTD.). After setting the operation conditions to have an inlet temperature of 230-240°C and an outlet temperature of 90°C, drying and granulation were conducted with a dry air rate of 0.8 m³/min, a nozzle spray air pressure of 0.1MPa, and a slurry feed rate of 20 g/min. The obtained granules were dried in the air at 120°C for
30 20hr. Regarding strength of the granules, crash strength of each particle was measured in accordance with JIS Z8841. Crash strength of 15 granules

obtained was measured. As shown in Table 3, every granule was less than 0.06 gf/mm², which was the measurement limit value of the measuring apparatus.

[0027] (EXAMPLE 1)

5 As a catalyst powder according to Example 1, there was used a type of metallosilicate, ZSM-5, having an average particle size of 42 μ m and a crystalline size of 5 μ m. The catalyst powder raw material was of ammonia-type and converted to proton-type by conducting a baking treatment at a predetermined temperature. Metal was not supported on
10 ZSM-5 used in the present example.

[0028] Firstly, the milling method of the catalyst powder by a bead mill is described. 4kg of purified water was weighed relative to 1kg of the catalyst powder, and the total amount of the purified water was put into a stirring container. While rotating a blade of a stirrer, the total amount of the
15 catalyst powder was added at 400 g/minute. After that, a slurry-circulating pump was energized, and it was started to circulate and mill the slurry. A part of the slurry was taken out at an interval of 15 minutes after the start to measure the slurry viscosity and the particle size distribution of the catalyst powder. Table 1 shows the change with time of the particle size distribution
20 of the catalyst powder. 1hr after the start of the milling, the circulating pump was stopped, and the slurry in the system was taken. The recovered slurry was 3.76kg relative to 5kg of the added slurry weight.

[0029] Then, the granulation method of the catalyst powder by a spray dryer is explained. The slurry formerly prepared was subjected to an aging for 5
25 days. In the aging, the slurry was allowed to stand still in the atmosphere of air of normal temperature and normal pressure. Then, the stirring was conducted in a stirring container. After setting at an inlet temperature of 230-240°C and an outlet temperature of 90°C, drying and granulation were started by a spray dryer (Type DL-41 made by YAMATO SCIENTIFIC CO.,
30 LTD.) under conditions of a dry air wind rate of 0.8 m³/min, a nozzle spray air pressure of 0.1MPa, and a slurry feed rate of 20 g/min. The obtained

granules were dried in the air at 120°C for 20hr. The SEM (scanning electron microscope) photograph after the drying is shown in Fig. 1. The result (the average value of 10 points) of crash strength of the granules is shown in Table 3.

5 [0030] (EXAMPLE 2)

As a catalyst powder according to Example 2, there was used a type of metallocsilicate, ZSM-5, having an average particle size of 39 μ m and a crystalline size of 4.2 μ m. The subsequent preparation conditions are similar to Example 1. Table 2 shows the change of the particle size
10 distribution of the catalyst powder milled by the bead mill. The SEM photograph of the granules by the spray dryer (Type DL-41 made by YAMATO SCIENTIFIC CO., LTD.) is shown in Fig. 2. Although not shown in Table 3, it was confirmed that crash strength of the granules according to Example 2 was almost equal to crash strength of the granules according to
15 Example 1.

[0031] It is understood from the results of Table 1 and Table 2 that milling of the catalyst powder of homogeneous nanometer size becomes possible in a short time. Furthermore, it is possible to obtain compact, spherical granules, as shown in Figs. 1 and 2, by spray drying the milled catalyst
20 powder. Furthermore, as is clear from the results of Table 3, it is possible to obtain a higher crash strength by granules of Example 1 obtained by aging and then spray drying a catalyst powder-containing slurry milled by the bead mill, as compared with a catalyst powder of Comparative Example 1 of a nano-size (crystal size: 80nm) obtained by simply spray drying a slurry.
25 Furthermore, it was shown that, since the granules of Example 1 have an increased crystal surface area resulting from the milling of the contained catalyst powder, the efficiency of the contact with the reaction gas increases, and they can act as efficient catalyst granules even in a reaction under a high flow rate condition, such as flow bed process. It was also confirmed
30 that the above crash strength can be obtained by milling the metallocsilicate raw material by a bead mill in a manner that the particle size of the

metallo-silicate becomes 1.0 μ m or less, particularly 0.5 μ m or less, at a cumulative frequency of 50%.

[0032] (EXAMPLE 3)

As a catalyst powder according to Example 3, there was used a type of metallo-silicate, ZSM-5, having an average particle size of 42 μ m and a crystalline size of 5 μ m. The catalyst powder raw material was of ammonia-type and converted to proton-type by conducting a baking treatment at a predetermined temperature. Metal was not supported on ZSM-5 used in the present example.

[0033] Firstly, the milling method of the catalyst powder by a bead mill is explained. 20kg of purified water was weighed relative to 5kg of the catalyst powder, and the total amount of the purified water was put into a stirring container. While rotating a blade of a stirrer, the total amount of the catalyst powder was added at 400 g/minute. After that, a slurry-circulating pump was energized, and it was started to circulate and mill the slurry. In 1hr after the start of the milling, the milling was conducted until a crystalline size of 0.2 μ m. After stopping the circulating pump, the slurry in the system was taken. The recovered slurry was 18.9kg relative to 25kg of the weight of the slurry introduced.

[0034] Then, the granulation method of the catalyst powder by a spray dryer is explained. The slurry formerly prepared was subjected to an aging for 5 days. In the aging, the slurry was allowed to stand still in the atmosphere of air of normal temperature and normal pressure. Then, the stirring was conducted in a stirring container. After setting at an inlet temperature of 230-240°C and an outlet temperature of 90°C, drying and granulation were started by a spray dryer (Type DL-41 made by YAMATO SCIENTIFIC CO., LTD.) under conditions of a dry air wind rate of 0.8 m³/min, a nozzle spray air pressure of 0.1MPa, and a slurry feed rate of 20 g/min. The obtained granules were dried in the air at 120°C for 20hr. Then, a baking was conducted for 5 hours under 550°C.

[0035] Regarding strength of the granules obtained, crash strength of 15

granules was measured by a measurement method in accordance with JIS Z8841. The measurement results are shown in Table 4. The average crash strength of the granules was not higher than 60.8 gf/mm².

[0036] Flow property of the granules was based on the bulk density

5 measurement method according to JIS Z2504 and JIS R6126 (to obtain flow property index from the way of decrease of bulk by conducting tapping).

The measurement was conducted according to Kawakami's way tap density measurement method. The measurement result is shown in Table 5. A smaller value in Kawakami's way flow property index means being better in
10 flow property. Flow property index of the granules was 0.38.

[0037] (EXAMPLE 4)

As to the catalyst powder according to Example 4, molybdenum as a metal component is supported on the metallosilicate. Furthermore, the catalyst production method of the present example is the same as the
15 catalyst production method according to Example 3, except in having a procedure of supporting a metal component by impregnation on the catalyst powder milled by a bead mill.

[0038] Firstly, there is explained a method of impregnation and supporting of a metal to be supported, after milling of the catalyst powder by a bead mill.

20 2kg of the slurry prepared under the same conditions as those of Example 3 was aged for 5 days, followed by stirring in a stirring container. Then, to this slurry, there was added an aqueous solution prepared by dissolving 42g of ammonium heptamolybdate in 200g of water, and then stirring was conducted for 3hr.

25 [0039] Then, the granulation method of the catalyst powder by a spray dryer is explained. After setting the slurry prepared as above at an inlet temperature of 230-240°C and an outlet temperature of 90°C, drying and granulation were started by a spray dryer (Type DL-41 made by YAMATO SCIENTIFIC CO., LTD.) under conditions of a dry air wind rate of 0.8
30 m³/min, a nozzle spray air pressure of 0.1MPa, and a slurry feed rate of 20 g/min. The obtained granules were dried in the air at 120°C for 20hr.

Then, a baking was conducted for 5 hours under 550°C.

[0040] The result (the average of ten points) of crash strength of the granules is shown in Table 4, and the result of flow property index is shown in Table 5. The measurements of crash strength and flow property index were conducted in the same methods as those of Example 3. SEM photographs of the granules after the baking are shown in Fig. 5 (magnification: 1,000) and Fig. 6 (magnification: 5,000). Furthermore, SEM photographs showing the distribution of elements (O, Al, Si, and Mo) on the surface of the granules are shown in Fig. 7 (magnification: 1,000) and Fig. 8 (magnification: 10,000).

[0041] (EXAMPLE 5)

The catalyst production method of the present example is the same as the catalyst production method according to Example 4, except in that it has a procedure of further adding a PVA aqueous solution to the slurry into which an ammonium heptamolybdate aqueous solution was introduced.

[0042] That is, 2kg of the slurry prepared under the same conditions as those of Example 3 was aged for 5 days, followed by stirring in a stirring container. Then, into this slurry, there was introduced an aqueous solution prepared by dissolving 42g of ammonium heptamolybdate in 200g of water. Furthermore, 8g of 10% PVA aqueous solution was added, followed by stirring for 3 hours. The subsequent granulation method is the same as the catalyst granulation procedure according to Example 4.

[0043] The result (the average of ten points) of crash strength of the granules is shown in Table 4, and the result of flow property index is shown in Table 5. The measurements of crash strength and flow property index were conducted in the same methods as those of Example 3. SEM photographs of the granules after the baking are shown in Fig. 9 (magnification: 1,000) and Fig. 10 (magnification: 5,500). Furthermore, SEM photographs (magnification: 10,000) showing distribution of elements (O, Al, Si, and Mo) on the surface of the granules are shown in Fig. 11.

[0044] It is understood from the results of Table 4 that the granules of

Example 4 obtained by supporting molybdenum by impregnation on the slurry, spray drying, and baking have a higher crash strength, as compared with spray drying and baking of a nano-size raw material slurry such as that of Example 3. Furthermore, it is understood that the granules of Example 5
5 obtained by adding PVA, spray drying and baking have a higher crash strength.

[0045] According to the results of Table 5, it is understood that the catalysts of Examples 4 and 5 are granules superior in flow property, since their flow property indexes are each lower than that of the catalyst of Example 3.

10 [0046] As shown in Fig. 5 to Fig. 8, compact, spherical granules are obtained as granules of Example 4. Furthermore, as shown in Fig. 9 to Fig. 11, it was confirmed that granules with little defect (depression) are obtained according to the catalyst production method of Example 5, to which PVA was added. The catalyst powder in the granules has an increased area of the
15 crystal surface by the milling. Therefore, the efficiency of the contact with the reaction gas increases, and they can act as efficient catalyst granules even in a reaction under a high flow rate condition, such as flow bed process.

[0047] Furthermore, in the element distribution photographs of Fig. 7, Fig. 8 and Fig. 11, the photographs of "O Ka1" show oxygen distribution. The
20 photographs of "Al Ka1" show aluminum distribution. The photographs of "Si Ka1" show silicon distribution. The photographs of "Mo La1" show molybdenum distribution. White parts of the photographs show the distribution of the elements. According to the above photographs, it is possible to confirm that the metal element components (Al and Mo) are
25 supported on the surface of the granules under a uniformly distributed condition. It is possible to confirm that Si is densely distributed over the whole surface, since main components of zeolite used in examples are AlO_3 and SiO_2 , and since the $\text{SiO}_2/\text{Al}_2\text{O}_3$ ratio of the main raw material is 40.

[0048] As is clear from the results of the above examples, according to the
30 catalyst production process of the present invention, the effective area of the crystal surface part of the catalyst increases by milling of the nano-size

catalyst powder by the bead mill. It becomes easily possible to produce spherical granules, which has been difficult by rolling granulation method. Furthermore, it is possible to omit or greatly reduce the inorganic caking agent. Then, it becomes easy to have a uniform metal supporting on a catalyst powder contained in granules by impregnating the catalyst powder with the metal component by adding the metal component, which is exemplified by molybdenum, to a slurry containing the milled catalyst powder. Furthermore, it is possible to make flow property of the granules better. Furthermore, crash strength of the granules becomes high. In particular, it is possible to further increase crash strength by adding PVA.

[0049] [Table 1]

Particle Size Distribution of Catalyst Powder (Example 1) Milled by Bead Mill

Cumulative (%)	Particle Size (μm)				
	0 min	15 min	30 min	45 min	60 min
10	7.137	0.478	0.351	0.214	0.184
20	9.594	0.560	0.409	0.269	0.231
30	11.43	0.633	0.456	0.314	0.270
40	13.04	0.716	0.500	0.357	0.307
50	14.63	0.816	0.546	0.398	0.346
60	16.33	0.950	0.598	0.442	0.387
70	18.33	1.139	0.662	0.495	0.436
80	21.01	1.424	0.755	0.565	0.502
90	25.68	1.946	0.926	0.687	0.617
95	30.75	2.548	1.123	0.825	0.748

[0050] [Table 2]

Particle Size Distribution of Catalyst Powder (Example 2) Milled by Bead Mill

Cumulative (%)	Particle Size (μm)				
	0 min	15 min	30 min	45 min	60 min
10	3.010	0.478	0.338	0.214	0.180
20	4.147	0.554	0.396	0.267	0.224
30	5.264	0.624	0.443	0.313	0.261
40	6.503	0.702	0.488	0.357	0.298
50	8.062	0.799	0.535	0.399	0.336
60	10.35	0.935	0.588	0.455	0.378
70	14.09	1.143	0.655	0.500	0.427
80	19.94	1.472	0.753	0.573	0.496
90	29.51	2.095	0.943	0.707	0.618
95	39.31	2.826	1.175	0.861	0.758

[0051] [Table 3]

	Crash Strength (gf/mm ²)
Comparative Example 1	Less than 0.06
Example 1	60.8

[0052]

[Table 4]

5

Crash Strength of Granules (gf/mm²)

Granule Size	40-125μm	125-250μm
Example 3		66.2
Example 4	607.7	349.2
Example 5	848.8	

[0053] [Table 5]

Flow Property Index of Granules

Granule Size	40-125μm
Example 3	0.38
Example 4	0.28
Example 5	0.29

CLAIMS

[Claim 1] A process for producing a catalyst for producing an aromatic compound and hydrogen from a lower hydrocarbon, the catalyst production
5 process being characterized by that a catalyst powder-containing slurry obtained by milling a metallosilicate-containing raw material is dried by a spray drying method to obtain granules of the catalyst.

[Claim 2] The catalyst production process according to claim 1, which is
10 characterized by that the metallosilicate-containing raw material contains a metallosilicate having micropores of a size that is substantially 4.5 to 6.5 angstroms.

[Claim 3] The catalyst production process according to claim 1 or 2, which
15 is characterized by that the metallosilicate raw material is milled by a bead mill such that particle size of the metallosilicate becomes 1.0 μ m or less at a cumulative frequency of 50%.

[Claim 4] The catalyst production process according to any one of claims 1
20 to 3, which is characterized by that as a metal component at least one selected from rhenium, vanadium, molybdenum, tungsten, chromium, and their compounds is supported on the metallosilicate.

[Claim 5] The catalyst production process according to claim 4, which is
25 characterized by that amount of the molybdenum supported is 2-12 weight % relative to total amount of the catalyst powder.

[Claim 6] The catalyst production process according to any one of claims 1
30 to 5, which is characterized by that the slurry is aged and then dried by the spray drying method.

[Claim 7] The catalyst production process according to claim 6, which is characterized by that the aging is to make the slurry stand still under an atmosphere of an air of normal temperature and normal pressure.

5 [Claim 8] The catalyst production process according to any one of claims 4 to 7, which is characterized by that the metal component is supported on the metallosilicate by adding the metal component to the slurry.

[Claim 9] The catalyst production process according to any one of claims 1
10 to 8, which is characterized by that polyvinyl alcohol is added to the slurry.

[Claim 10] A catalyst for producing an aromatic compound and hydrogen from a lower hydrocarbon, the catalyst being characterized by that it is prepared by the production process according to any one of claims 1 to 9.

15