



(51) International Patent Classification:

C08F 212/36 (2006.01) *C08F 218/18* (2006.01)
B60C 1/00 (2006.01) *C08F 222/10* (2006.01)
C08F 216/12 (2006.01) *C09J 4/00* (2006.01)

(21) International Application Number:

PCT/EP2016/067740

(22) International Filing Date:

26 July 2016 (26.07.2016)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

15178531.8 27 July 2015 (27.07.2015) EP

(71) Applicant: **ARLANXEO DEUTSCHLAND GMBH**
[DE/DE]; Alte Heerstrasse 2, 41540 Dormagen (DE).

(72) Inventors: **KOHL, Christopher**; Hinter den Wiesen 44,
55127 Mainz (DE). **SCHMIDT, Udo**; An der Schanz 2,
50735 Köln (DE). **ZHOU, Jiawen**; Bachstr. 131, 40217
Düsseldorf (DE). **FRÜH, Thomas**; Beethovenstrasse 5,
42115 Wuppertal (DE). **LUCASSEN, Alex**; Unter den
Hecken 82, 41540 Dormagen (DE).

(74) Agent: **WICHMANN, Birgid**; Kennedyplatz 1, 50569
Köln (DE).

(81) Designated States (unless otherwise indicated, for every
kind of national protection available): AE, AG, AL, AM,
AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY,
BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM,
DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT,
HN, HR, HU, ID, IL, IN, IR, IS, JP, KE, KG, KN, KP, KR,
KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME, MG,
MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM,
PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC,
SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN,
TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every
kind of regional protection available): ARIPO (BW, GH,
GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ,
TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU,
TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE,
DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU,
LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK,
SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ,
GW, KM, ML, MR, NE, SN, TD, TG).

Declarations under Rule 4.17:

— as to the applicant's entitlement to claim the priority of the
earlier application (Rule 4.17(iii))

Published:

— with international search report (Art. 21(3))

(54) Title: SEALING GELS, PROCESS FOR PRODUCTION THEREOF AND USE THEREOF IN SEALING COMPOUNDS
FOR SELF-SEALING TYRES

(57) Abstract: The present invention relates to: • a sealing gel having a Mooney viscosity (ML1 +4@100°C) in the range from 100
MU to 170 MU, • a sealing compound comprising inventive sealing gel, • a process for producing this sealing compound, • the use
of sealing gels for improving viscoelastic properties in sealing compounds, and • the use of sealing gel-containing sealing com-
pounds for improving rolling resistance properties in tyres having sealing layers.



Sealing gels, process for production thereof and use thereof in sealing compounds for self-sealing tyres

The present invention relates to:

- a sealing gel having a Mooney viscosity (ML1+4) @100°C in the range from 100 MU to 170 MU,
- a sealing compound comprising inventive sealing gel,
- a process for producing this sealing compound,
- the use of sealing gels in sealing compounds, and
- the use of sealing gel-containing sealing compounds in tyres.

In the operation of a pneumatic tyre for cars and trucks, there is the risk of damage to the tyre as a result of the penetration of foreign bodies and of the tyre losing air because of the damage. The loss of tyre air often leads to an unstable ride state which requires the immediate changing of or a makeshift repair to the tyre. In order not to have to stop and leave the vehicle for a tyre change or repair in hazardous traffic situations, various tyre and wheel designs have been developed. Thus, there exist on the market tyres having runflat properties which enable temporary continuation of the journey by lowering the tread onto a support ring beneath in the event of loss of tyre pressure. In addition, there are runflat tyres which feature a reinforced tyre sidewall which, in the event of loss of tyre pressure, can bear the axle load even without air pressure for a limited period, without getting into an unsafe ride situation. All these designs that are present on the market increase the weight of the tyre and the rolling resistance significantly, and hence the consumption of fuel in motor vehicle operation.

Tyres having a sealing compound in the form of a self-sealing layer which surrounds penetrating foreign bodies and/or directly closes the holes that they form are known in principle.

As early as 1968, US-A-3,565,151 disclosed a self-sealing tyre containing two plies of sealing compounds which are separated by the inner liner and are supported from bead to bead within the tyre carcass. The sealing material consists mainly of styrene-butadiene rubber (SBR) and a small amount of crosslinkers, wherein the SBR component is a mixture of 80 phr to 95 phr (parts per hundred rubber) of cold-polymerized SBR and 5 phr to 20 phr of hot-polymerized SBR. The document does not give any pointer at all to adhesion and cohesion properties.

Self-sealing tyres are also disclosed in US-A-3,981,342. The patent describes a self-sealing tyre having a layer including a mixture of a low molecular weight liquid elastomer and a high molecular weight solid elastomer, and an amount of crosslinking agent sufficient to produce partial crosslinking of the mixture, the liquid elastomer being present in a greater amount than the solid elastomer.

US-A-4,228,839 discloses a self-sealing tyre having a layer including a mixture of a polymeric material degradable by high-energy radiation and a polymeric material crosslinkable by radiation and/or by heat.

US-A-4,664,168 discloses a self-sealing tyre having a self-sealing layer on the inside and a multitude of support elements which partly overlap with the sealing layer, in order to keep the sealing compound in place during production and use.

US-B-7,004,217 discloses a self-sealing tyre comprising a sealing chamber having a sealing compound between the carcass and the inner liner.

US-A-4,113,799 discloses a sealing layer comprising a butyl rubber of high molecular weight and a butyl rubber of low molecular weight in a ratio of 20:80 to 60:40, with addition of tackifiers in an amount of 55% by weight to 70% by weight.

DE-A-10-2009-003333 discloses sealing compounds composed of viscoelastic gel for self-sealing pneumatic motor vehicle tyres, comprising a filler composed of polymers such as unvulcanized or vulcanized rubber in the form of particles having a mean diameter of 0.05 mm to 8 mm. The particles are intended to further improve the sealing action compared to known sealants composed of gel. The effects on the adhesion and cohesion properties are undisclosed.

WO-A-2008/019901 discloses, inter alia, sealing compounds based on partially crosslinked butyl rubber. In principle, useful sealants are those which are based on rubbers and on a combination of liquid rubber types of low molecular weight and solid rubber types of high molecular weight, as described, for example, in US-A-5,295,525.

The gel systems detailed in US-B-6,508,898 are based on polyurethane and silicone. However, vulcanizates made from silicone rubber lack resistance to naphthenic and aromatic oils, for example. Low adhesion to other substrates (low surface energy) and high water vapour and gas permeability are likewise disadvantageous for use for tyres. It has been stated that silicone rubber has a gas permeability 100 times higher than BR or natural rubber (Kautschuk Technologie [Rubber Technology], F. Röthemeyer, F. Sommer, Carl Hanser Verlag Munich Vienna, 2006; page 206). A disadvantage of the use of

polyurethane rubbers is their lack of compatibility with plasticizers. Phthalic and adipic esters are compatible at up to 30 phr. Polyester types require hydrolysis stabilizers; polyether types require UV stabilizers. Polyurethane elastomers that are to be found in the upper region of the hardness scale also have unfavourable heat resistance because of their propensity to hydrolysis (Kautschuk Technologie, F. Röthemeyer, F. Sommer, Carl Hanser Verlag Munich Vienna, 2006; page 218). For the reasons mentioned above, therefore, use of sealants for silicone rubber- and polyurethane rubber-based tyre applications is disadvantageous.

WO-A-2009/143895 discloses sealing compounds comprising precrosslinked SBR particles as a secondary component and natural or synthetic rubber as a main component. These crosslinked SBR particles are produced by hot emulsion polymerization. Various studies show that the reduction in the polymerization temperature from 50°C in the case of hot emulsion polymerization to 5°C in the case of cold emulsion polymerization had a strong influence on the molecular weight distribution. The formation of low molecular weight fractions in the rapid reaction of the thiols in the initial phase of the free-radical polymerization at 5°C was distinctly reduced, and so better control of the chain length of the polymers was enabled. It was shown that, as well as the improved chain length distribution, the unwanted and uncontrolled crosslinking reaction was also distinctly reduced. The SBR particles obtained by hot emulsion polymerization therefore have, compared to cold polymers, a very broad molecular weight distribution and a high level of uncontrolled branching. Controlled adjustment of the viscoelastic properties is therefore impossible (Science and Technology of Rubber, James E. Mark, Burak Erman, Elsevier Academic Press, 2005, page 50).

Viscoelasticity is a characteristic of the material in the sense that, as well as features of pure elasticity, features of viscous fluidity are also present, which is manifested, for example, in the occurrence of internal friction on deformation.

The resulting hysteresis is typically characterized by the measurement of the loss factor $\tan \delta$ at high temperature (e.g. 60°C) and is a key parameter for rubber mixtures in tyres, especially for tyre treads. The hysteresis is not just an indicator of the heat build up in rubber mixtures under dynamic stress (reversible elongation) but also a good indicator of the rolling resistance of a tyre (Rubber Technologist's Handbook, Volume 2; page 190). A measurement parameter for hysteresis losses is the $\tan \delta$, which is defined as the ratio of loss modulus to storage modulus; cf., for example, also DIN 53 513, DIN 53 535. Commercially available sealing compounds, for example ContiSeal® from Continental,

have a comparatively high $\tan \delta$ value at 60°C, 10 Hz and a heating rate of 3 K/min of 0.58.

The lowering of $\tan \delta$ in the temperature/frequency range and amplitude range of application-related relevance leads, for example, to reduced heat buildup in the elastomer.

5 Minimum rolling resistance of the tyres enables minimum fuel consumption of the vehicle equipped therewith.

Rolling resistance is understood to mean the conversion of mechanical energy to heat by the rotating tyre per unit length. The dimension of rolling resistance is joules per metre (Scale Models in Engineering, D. Schuring, Pergamon Press, Oxford, 1977).

10 It is known that what are called rubber gels can be used in blends with a wide variety of different rubbers in tyre treads, in order, for example, to improve the rolling resistance of car tyres (see, for example, DE-A-4220563, GB-A-1078400, EP-A-405216 and EP-A-0854171).

15 DE 60118364 T2, EP-A-1149866 and EP-A-1291369 describe the production of SBR microgels with the aid of cold emulsion polymerization for tyre applications.

DE-A-10345043 and DE-A-10-2005-014271 disclose that what are called microgels are also used in uncrosslinked mixtures containing a thermoplastic material or a functional additive.

20 However, none of these documents teaches the production of sealing gels based on different crosslinkers having different incorporating characteristics for use for sealing compounds.

The sealing compounds have to meet high demands in practical use. They have to be soft, tacky and dimensionally stable over the entire range of operating temperatures from -40°C to +90°C. At the same time, the sealing compounds also have to be viscous.

25 Following entry of an object through the tyre tread into the interior of the tyre, the sealing compound should enclose the object. If the object exits from the tyre, the sealing compound sticking to the object is drawn into the resulting hole or the sealing compound flows into the hole as a result of the internal tyre pressure and closes the hole. In addition, these sealing compounds have to be impervious to gas, such that temporary further travel

30 is enabled. The sealing compound should be applicable to the inner tyre liner in a simple process.

The sealing compounds additionally have to have high adhesion to the inner liner, and high cohesion in order to remain dimensionally stable within the tyre.

5 The prior art shows that the known sealing compounds are still not satisfactory for particular applications in which not only a minimum rolling resistance but also simultaneously excellent adhesion and cohesion properties are necessary.

The problem addressed by the present invention was therefore that of providing sealing gels for use in sealing compounds in self-sealing tyres, which fulfil the high demands in practical use, especially in terms of adhesion and cohesion properties, and may have viscoelastic properties improved over the prior art.

10 Accordingly, a further problem addressed by the present invention was that of providing sealing compounds having excellent adhesion and cohesion and having minimum deterioration of rolling resistance.

15 It has been found that, surprisingly, sealing gels which consist of specially polymerized diene rubber gels which have been crosslinked with different crosslinkers are particularly advantageous for the production of self-sealing compounds for self-sealing tyres.

The solution to the problems and the subject-matter of the present invention is therefore sealing gels having a Mooney viscosity (ML1+4) @ 100°C of 100 MU to 170 MU,

20 i) in the form of a mixture comprising diene rubber gel (A), having a Mooney viscosity (ML1+4) @ 100°C of 170 MU to 195 MU, obtainable by emulsion polymerization at 5°C to 20°C of at least one conjugated diene in the presence of at least one crosslinker (I) and diene rubber gel (B), having a Mooney viscosity (ML1+4) @ 100°C of 75 MU to 110 MU, obtainable by emulsion polymerization, preferably at 5°C to 20°C, of at least one conjugated diene in the presence of at least one crosslinker (II) or

25 ii) obtainable by emulsion polymerization, preferably at 5°C to 20°C, of at least one conjugated diene in the presence of at least one crosslinker (I) and in the presence of at least one crosslinker (II), referred to hereinafter as sealing gel (H),

where

crosslinker (I) is acrylates and methacrylates of polyhydric, preferably di- to tetrahydric, C₂-C₂₀ alcohols and

30 crosslinker (II) is compounds having two or more vinyl, allyl or isopropenyl groups or one maleimide unit.

Alternatively, sealing gels are also mixtures of at least one sealing gel (H) with diene rubber gel (A) or (B) or (A) and (B).

5 In an embodiment where styrene-butadiene copolymer (SBR) is the diene rubber gel (A) or diene rubber gel (B) or sealing gel (H), such a diene rubber gel (A) or diene rubber gel (B) or sealing gel (H) is obtainable by cold emulsion polymerization at 5°C to 20°C.

A connecting feature common to all the sealing gels is that at least one crosslinker (I) and at least one crosslinker (II) are required for production thereof.

The sealing gels of the invention have a Mooney viscosity (ML1+4) @ 100°C of 100 MU to 170 MU, preferably of 100 MU to 150 MU, more preferably of 100 MU to 130 MU.

10 The term diene rubber gel in the context of this invention is a diene rubber which has been reacted with at least one crosslinker (I) or with at least one crosslinker (II) during the polymerization.

The term sealing gel in the context of this invention encompasses

- 15 i) a mixture of a plurality of separately prepared diene rubber gels as defined above, and also
- ii) a sealing gel which has been produced by the polymerization of the monomers to give diene rubber gel with at least one crosslinker (I) and at least one crosslinker (II) simultaneously, and also
- 20 iii) a mixture of a sealing gel according to point ii) with at least one diene rubber gel as defined in point i) above.

Sealing compounds in the context of the invention are compositions comprising sealing gels and further additives.

25 In combination with resins (C) and optionally ageing stabilizers (D), optionally further natural and/or synthetic rubber (E) and optionally plasticizers (F), sealing compounds with tailored adhesion to the inner liner and cohesion, and also low rolling resistance are produced.

It should be noted at this point that the scope of the invention includes any and all possible combinations of the components, ranges of values and/or process parameters mentioned above and cited hereinafter, in general terms or within areas of preference.

30 The sealing gels of the invention are produced by

5 i-a) emulsion polymerization of monomers to give diene rubber gel , wherein diene rubber gel (A) is produced by the emulsion polymerization with at least one crosslinker (I) and diene rubber gel (B) is produced by the emulsion polymerization with at least one crosslinker (II), followed by mixing of the diene rubber gels (A) and (B) to give the sealing gel or

i-b) emulsion polymerization of monomers with at least one crosslinker (I) and simultaneously with at least one crosslinker (II) or

ii) mixing a sealing gel produced according to process i-b) with at least one diene rubber gel (A) or (B) or (A) and (B).

10 Sealing gels of the invention having a Mooney viscosity (ML1+4) @ 100°C of 100 MU to 170 MU can be established in a controlled manner by mixing of the diene rubber gels (A) and (B) in an A:B ratio = (1:9) to (9:1), preferably in an A:B ratio = (4:1) to (1:4), more preferably in an A:B ratio = (2.5:1) to (1:2.5) during the process for production thereof.

15 In addition, sealing gels of the invention having a Mooney viscosity (ML-1+4) @ 100°C of 100 MU to 170 MU can be produced in a controlled manner by mixing the diene rubber gels (A) and/or (B) with sealing gel (H).

The crosslinking with crosslinker (I) or with crosslinker (II) can be conducted as follows:

a) The at least one crosslinker (I) or the at least one crosslinker (II) or at least one crosslinker (I) and one crosslinker (II) are initially charged.

20 b) The at least one crosslinker (I) or the at least one crosslinker (II) or at least one crosslinker (I) and one crosslinker (II) are metered in during the polymerization.

In the production of the diene rubber gels (A) and (B) and in the case of the sealing gel (H) by emulsion polymerization, at least one conjugated diene is used as free-radically polymerizable monomer.

25 Examples of conjugated dienes are 1,3-butadiene, 2,3-dimethyl-1,3-butadiene, isoprene and chloroprene, preferably 1,3-butadiene.

The amount of diene monomer is typically 79.8 phm to 98.8 phm, preferably 86 phm to 91.8 phm (parts per hundred parts monomer).

In the production of the diene rubber gels (A) and (B) and in the case of the sealing gel (H) by emulsion polymerization, it is also possible to use further monomers other than the diene used.

In the production of the diene rubber gels and sealing gels by emulsion polymerization, for example, the following free-radically polymerizable monomers are used as further monomers other than the diene monomer: 1,3-butadiene, vinylaromatics, preferably styrene, 2-methylstyrene, 3-methylstyrene, 4-methylstyrene, α -methylstyrene, 2,4-dimethylstyrene, 2,4-diisopropylstyrene, 4-tert-butylstyrene and tert-butoxystyrene, more preferably styrene, acrylonitrile, isoprene, esters of acrylic acid and methacrylic acid, tetrafluoroethylene, vinylidene fluoride, hexafluoropropene, 2-chlorobutadiene, 2,3-dichlorobutadiene, carboxylic acids containing double bonds, preferably acrylic acid, methacrylic acid, maleic acid or itaconic acid, hydroxyl compounds containing double bonds, preferably hydroxyethyl methacrylate, hydroxyethyl acrylate or hydroxybutyl methacrylate, amine-functionalized (meth)acrylates, glycidyl methacrylate, acrolein, N-vinyl-2-pyrrolidone, N-allylurea, N-allylthiourea, secondary amino (meth)acrylates, preferably 2-tert-butylaminoethyl methacrylate and 2-tert-butylaminoethylmethacrylamide, or vinylic heteroaromatics such as 2-, 4-vinylpyridine and 1-vinylimidazole.

The amount of further monomers is typically 1 phm to 20 phm, preferably 8 phm to 14 phm, based on the total amount of monomers.

In the case of a vinylaromatic as further monomer, the amount of vinylaromatic is typically 1 phm to 20 phm, preferably 8 phm to 14 phm, based on the total amount of monomers.

In an embodiment where styrene-butadiene copolymer (SBR) is the diene rubber gel (A) or diene rubber gel (B) or sealing gel (H), such an SBR of the invention is one obtainable by cold emulsion polymerization at 5°C to 20°C. Cold emulsion polymerization is a polymerization method familiar to those skilled in the art (see, inter alia, US-A-3,565,151 (column 2 line 26), EP-A-1291369 [0055], EP-A-1149866 ([0077], [0080])) Kautschuk Technologie, F. Röthemeyer, F. Sommer, Carl Hanser Verlag Munich Vienna, 2006; page 95 ff.). Cold emulsion polymerization is conducted at a temperature of 5°C to 20°C, preferably 5°C to 15°C and more preferably of 5°C to 10°C. Compared to cold emulsion polymerization, hot emulsion polymerization is conducted at a temperature of more than 20°C up to 150°C, preferably 40°C to 80°C. The crosslinkers (I) and crosslinkers (II) differ by different incorporation characteristics during the emulsion polymerization.

Crosslinkers (I) feature incorporation at an early stage in the polymerization.

Crosslinkers (I) are acrylates and methacrylates of polyhydric, preferably di- to tetrahydric, C₂-C₂₀ alcohols.

5 Preferred crosslinkers (I) are selected from the group consisting of acrylates and methacrylates of ethylene glycol, propane-1,2-diol, butane-1,4-diol, hexanediol, polyethylene glycol having 2 to 8 and preferably 2 to 4 oxyethylene units, neopentyl glycol, bisphenol A, glycerol, trimethylolpropane, pentaerythritol, sorbitol with unsaturated polyesters of aliphatic di- and polyols and mixtures thereof.

10 Particularly preferred crosslinkers (I) are acrylates and methacrylates of propane-1,2-diol, butane-1,4-diol, neopentyl glycol, bisphenol A, glycerol, trimethylolpropane and pentaerythritol.

A very particularly preferred crosslinker (I) is trimethylolpropane trimethacrylate (TMPTMA).

Crosslinkers (II) feature incorporation at a late stage in the polymerization.

15 Crosslinkers (II) are compounds having two or more vinyl, allyl or isopropenyl groups or one maleimide unit.

Preferred crosslinkers (II) are selected from the group consisting of diisopropenylbenzene, divinylbenzene (DVB), divinyl ether, divinyl sulphone, diallyl phthalate, trivinylbenzene, triallyl cyanurate, triallyl isocyanurate, 1,2-polybutadiene, N,N'-m-phenylenemaleimide, tolylene-2,4-bis(maleimide) and triallyl trimellitate and mixtures thereof.

20 Particularly preferred crosslinkers (II) are diisopropenylbenzene, divinylbenzene, trivinylbenzene.

A very particularly preferred crosslinker (II) is divinylbenzene.

25 The amount of crosslinker used for the production of diene rubber gel (A) and (B) and for the production of sealing gel (H), in the case of crosslinker (I), is typically 1 phm to 6 phm, preferably 1 phm to 4 phm, and more preferably 1.5 phm to 3 phm and, in the case of crosslinker (II), 0.2 phm to 4 phm, preferably 0.2 phm to 3 phm, and more preferably 0.5 phm to 2.7 phm, based on the total amount of diene monomer, further monomer and crosslinker in the diene rubber gel (A) or (B) or the sealing gel (H), where the total amount of diene monomer, further monomer and crosslinker corresponds to 100 phm.

30 For the production of sealing gel (H), crosslinker (I) and crosslinker (II) are preferably used in a ratio of 5:1 to 1:5 and more preferably in a ratio of 5:1 to 1:1.

Emulsion polymerizations are generally conducted with use of emulsifiers. For this purpose, a wide range of emulsifiers are known and available to those skilled in the art. Emulsifiers used may, for example, be anionic emulsifiers or else uncharged emulsifiers. Preference is given to using anionic emulsifiers, more preferably anionic emulsifiers in the form of water-soluble salts.

Anionic emulsifiers used may be modified resin acids which are obtained by dimerization, disproportionation, hydrogenation and modification of resin acid mixtures comprising abietic acid, neoabietic acid, palustric acid, levopimaric acid. A particularly preferred modified resin acid is disproportionated resin acid (Ullmann's Encyclopedia of Industrial Chemistry, 2011, 6th edition, volume 31, p. 345-355).

Anionic emulsifiers used may also be fatty acids. These contain 6 to 22 carbon atoms per molecule. They may be fully saturated or contain one or more double bonds in the molecule. Examples of fatty acids are caproic acid, lauric acid, myristic acid, palmitic acid, stearic acid, oleic acid, linoleic acid, linolenic acid. The carboxylic acids are typically based on origin-specific oils or fats, for example ricinus oil, cottonseed, peanut oil, linseed oil, coconut fat, palm kernel oil, olive oil, rapeseed oil, soya oil, fish oil and bovine tallow etc. Preferred carboxylic acids derive from coconut fatty acid and from bovine tallow, and are partly or fully hydrogenated.

Such carboxylic acids based on modified resin acids or fatty acids are used in the form of water-soluble lithium, sodium, potassium and ammonium salts. The sodium salts and potassium salts are preferred.

Anionic emulsifiers are additionally sulphonates, sulphates and phosphates bonded to an organic radical. Useful organic radicals include aliphatic, aromatic, alkylated aromatic systems, fused aromatic systems, and methylene-bridged aromatic systems, where the methylene-bridged and fused aromatic systems may additionally be alkylated. The length of the alkyl chains is 6 to 25 carbon atoms. The length of the alkyl chains bonded to the aromatic systems is between 3 and 12 carbon atoms.

The sulphates, sulphonates and phosphates are used in the form of lithium salts, sodium salts, potassium salts and ammonium salts. The sodium salts, potassium salts and ammonium salts are preferred.

Examples of sulphonates, sulphates and phosphates of this kind are sodium laurylsulphate, sodium alkylsulphonate, sodium alkylarylsulphonate, sodium salts of methylene-bridged arylsulphonates, sodium salts of alkylated naphthalenesulphonates, and the sodium salts of methylene-bridged

naphthalenesulphonates, which may also be oligomerized, where the oligomerization level is between 2 and 10. Typically, the alkylated naphthalenesulphonic acids and the methylene-bridged (and optionally alkylated) naphthalenesulphonic acids are in the form of isomer mixtures which may also contain more than one sulphonic acid group (2 to 3 sulphonic acid groups) in the molecule. Particular preference is given to sodium laurylsulphate, sodium alkylsulphonate mixtures having 12 to 18 carbon atoms, sodium alkylarylsulphonates, sodium diisobutylenenaphthalenesulphonate, methylene-bridged polynaphthalenesulphonate mixtures and methylene-bridged arylsulphonate mixtures.

Uncharged emulsifiers derive from addition products of ethylene oxide and propylene oxide onto compounds having sufficiently acidic hydrogen. These include, for example, phenol, alkylated phenol and alkylated amines. The mean polymerization levels of the epoxides are between 2 and 20. Examples of uncharged emulsifiers are ethoxylated nonylphenols having 8, 10 and 12 ethylene oxide units. The uncharged emulsifiers are typically not used alone, but in combination with anionic emulsifiers.

Preference is given to the sodium and potassium salts of disproportionated abietic acid and partly hydrogenated tallow fatty acid, and mixtures thereof, sodium laurylsulphate, sodium alkylsulphonates, sodium alkylbenzenesulphonate, and alkylated and methylene-bridged naphthalenesulphonic acids.

The emulsifiers are used in an amount of 0.2 phm to 15 phm, preferably 0.5 phm to 12.5 phm, more preferably 1.0 phm to 10 phm, based on the total amount of diene monomer, further monomer and crosslinker.

The emulsion polymerization is generally conducted using the emulsifiers mentioned. If, on completion of the polymerization, latices having a tendency to premature self-coagulation because of a certain instability are obtained, said emulsifiers can also be added for post-stabilization of the latices. This may become necessary particularly prior to the removal of unconverted monomers by treatment with steam and before any storage of latex.

The emulsion polymerization is conducted in such a way that the SBR rubber which is preferred in accordance with the invention is crosslinked during the polymerization. Therefore, the use of molecular weight regulators is generally not obligatory. To control the crosslinking, however, it is advantageous to use molecular weight regulators, but the nature thereof is uncritical. In that case, the regulator is typically used in an amount of 0.01 phm to 3.5 phm, preferably 0.05 phm to 2.5 phm, per 100 phm, based on the total amount of diene monomer, further monomer and crosslinker. Molecular weight regulators

used may, for example, be mercaptan-containing carboxylic acids, mercaptan-containing alcohols, xanthogen disulphides, thiuram disulphides, halogenated hydrocarbons, branched aromatic or aliphatic hydrocarbons, or else linear or branched mercaptans. These compounds typically have 1 to 20 carbon atoms.

5 Examples of mercaptan-containing alcohols and mercaptan-containing carboxylic acids are monothioethylene glycol and mercaptopropionic acid. Examples of xanthogen disulphides are dimethylxanthogen disulphide, diethylxanthogen disulphide and diisopropylxanthogen disulphide.

10 Examples of thiuram disulphides are tetramethylthiuram disulphide, tetraethylthiuram disulphide and tetrabutylthiuram disulphide. Examples of halogenated hydrocarbons are carbon tetrachloride, chloroform, methyl iodide, diiodomethane, difluorodiiodomethane, 1,4-diiodobutane, 1,6-diiodohexane, ethyl bromide, ethyl iodide, 1,2-dibromotetrafluoroethane, bromotrifluoroethene, bromodifluoroethene.

15 Examples of branched hydrocarbons are those from which an H radical can readily be eliminated. Examples thereof are toluene, ethylbenzene, cumene, pentaphenylethane, triphenylmethane, 2,4-diphenyl-4-methyl-1-pentene, dipentene, and terpenes, for example limonene, α -pinene, β -pinene, α -carotene and β -carotene.

20 Examples of linear or branched mercaptans are n-hexyl mercaptan or else mercaptans containing 9 to 16 carbon atoms and at least three tertiary carbon atoms, where the sulphur is bonded to one of these tertiary carbon atoms. These mercaptans can be used either individually or in mixtures. Suitable examples are the addition compounds of hydrogen sulphide onto oligomerized propene, especially tetrameric propene, or onto oligomerized isobutene, especially trimeric isobutene, which are frequently referred to in the literature as tertiary dodecyl mercaptan ("t-DDM").

25 Such alkyl thiols or (isomer) mixtures of alkyl thiols are either commercially available or else are preparable by the person skilled in the art by processes that have been sufficiently well described in the literature (see, for example, JP-A-07-316126, JP-A-07-316127 and JP-A-07-316128, and also GB-A-823,823 and GB-A-823,824).

30 The individual alkyl thiols or mixtures thereof are typically used in an amount of 0.05 phm to 3 phm, preferably of 0.1 phm to 1.5 phm, based on the total amount of diene monomer, further monomer and crosslinker.

The metered addition of the molecular weight regulator or the molecular weight regulator mixture is effected either at the start of the polymerization or else in portions in the course

of the polymerization, preference being given to the addition of all or individual components of the regulator mixture in portions during the polymerization.

The emulsion polymerization is typically initiated using polymerization initiators which break down to free radicals (free-radical polymerization initiators). These include
5 compounds containing an -O-O- unit (peroxo compounds) or an -N=N- unit (azo compound).

The peroxo compounds include hydrogen peroxide, peroxodisulphates, peroxodiphosphates, hydroperoxides, peracids, peresters, peracid anhydrides and peroxides having two organic radicals. Suitable salts of peroxodisulphuric acid and
10 peroxodiphosphoric acid are the sodium, potassium and ammonium salts. Suitable hydroperoxides are, for example, tert-butyl hydroperoxide, cumene hydroperoxide and p-menthane hydroperoxide. Suitable peroxides having two organic radicals are dibenzoyl peroxide, 2,4-dichlorobenzoyl peroxide, di-tert-butyl peroxide, dicumyl peroxide, tert-butyl perbenzoate, tert-butyl peracetate etc. Suitable azo compounds are azobisisobutyronitrile,
15 azobisvaleronitrile and azobiscyclohexanenitrile.

Hydrogen peroxide, hydroperoxides, peracids, peresters, peroxodisulphate and peroxodiphosphate are also used in combination with reducing agents. Suitable reducing agents are sulphenates, sulphinates, sulfoxylates, dithionite, sulphite, metabisulphite, disulphite, sugar, urea, thiourea, xanthogenates, thioxanthogenates, hydrazine salts,
20 amines and amine derivatives such as aniline, dimethylaniline, monoethanolamine, diethanolamine or triethanolamine. Initiator systems consisting of an oxidizing agent and a reducing agent are referred to as redox systems. In the case of use of redox systems, salts of transition metal compounds such as iron, cobalt or nickel are frequently additionally used in combination with suitable complexing agents such as sodium
25 ethylenediaminetetraacetate, sodium nitrilotriacetate and trisodium phosphate or tetrapotassium diphosphate.

Preferred redox systems are, for example: 1) potassium peroxodisulphate in combination with triethanolamine, 2) ammonium peroxodiphosphate in combination with sodium metabisulphite ($\text{Na}_2\text{S}_2\text{O}_5$), 3) p-menthane hydroperoxide / sodium
30 formaldehydesulphoxylate in combination with iron(II) sulphate ($\text{FeSO}_4 \cdot 7 \text{H}_2\text{O}$), sodium ethylenediaminoacetate and trisodium phosphate; 4) cumene hydroperoxide / sodium formaldehydesulphoxylate in combination with iron(II) sulphate ($\text{FeSO}_4 \cdot 7 \text{H}_2\text{O}$), sodium ethylenediamineacetate and tetrapotassium diphosphate.

The amount of oxidizing agent is preferably 0.001 phm to 1 phm based on 100 phm, based on the total amount of diene monomer, further monomer and crosslinker. The molar amount of reducing agent is between 50% and 500% based on the molar amount of the oxidizing agent used.

- 5 The molar amount of complexing agent is based on the amount of transition metal used and is typically equimolar therewith.

To conduct the polymerization, all or individual components of the initiator system are metered in at the start of the polymerization or during the polymerization.

- 10 Addition of all and individual components of the activator system in portions during the polymerization is preferred. Sequential addition can be used to control the reaction rate.

The polymerization time is generally in the range from 5 h to 30 h.

The conversion in the emulsion polymerization is in the range from 85% to 100%, preferably 87% to 99.5% and more preferably 88% to 97%.

- 15 The aim in the polymerization is for very high polymerization conversions, in order to crosslink the rubber. For this reason, it is optionally possible to dispense with the use of stoppers. If stoppers are used, suitable examples are dimethyl dithiocarbamate, sodium nitrite, mixtures of dimethyl dithiocarbamate and sodium nitrite, hydrazine and hydroxylamine and salts derived therefrom, such as hydrazine sulphate and hydroxylammonium sulphate, diethylhydroxylamine, diisopropylhydroxylamine, water-
20 soluble salts of hydroquinone, sodium dithionite, phenyl- α -naphthylamine and aromatic phenols such as tert-butylcatechol, or phenothiazine.

- 25 The amount of water used in the emulsion polymerization is in the range from 70 to 300 phm, preferably in the range from 80 to 250 phm and more preferably in the range from 90 to 200 phm of water, based on the total amount of diene monomer, further monomer and crosslinker.

- 30 For reduction of the viscosity during the polymerization, for adjustment of the pH, and as a pH buffer, salts can be added to the aqueous phase in the course of the emulsion polymerization. Typical salts are salts of monovalent metals in the form of potassium hydroxide and sodium hydroxide, sodium sulphate, sodium carbonate, sodium hydrogencarbonate, sodium chloride and potassium chloride. Preference is given to sodium hydroxide or potassium hydroxide, sodium hydrogencarbonate and potassium chloride. The amounts of these electrolytes are in the range of 0 phm to 1 phm,

preferably 0 to 0.5 phm, based on the total amount of diene monomer, further monomer and crosslinker.

To achieve homogeneous running of the polymerization, only a portion of the initiator system is used for the start of the polymerization and the rest is metered in during the polymerization. Typically, the polymerization is commenced with 10% by weight to 80% by weight, preferably 30% by weight to 50% by weight, of the total amount of initiator. It is also possible to subsequently meter in individual constituents of the initiator system.

The polymerization can be performed batchwise, semi-continuously or else continuously in a stirred tank cascade. In the case of the semi-batchwise process, water, monomers, initiators and emulsifiers are fed into the reactor over a particular period (for example over the entire polymerization time). There are various methods of adding reactants: For example, it is possible to meter the remainder of monomer (often together with initiator) into an initial charge composed of water, emulsifier and initiator and frequently also a particular amount of monomer during the polymerization. Another method is, for example, the initial charging of a portion of an emulsion containing all the reactants, and the metered addition of the rest of the emulsion during the polymerization, in which case the composition of the emulsion metered in may differ from the initial charge of emulsion for the commencement of the polymerization (A. E. Hamielec, H. Tobita, Polymerization Processes, 1. Fundamentals, Ullmann's Encyclopedia of Industrial Chemistry, 2011, page 88).

The advantages of such a semi-batchwise process are not just the better control of the polymerization and the removal of heat, because the rate of metered addition can be altered during the polymerization. The concentration of the unconverted monomers can be minimized by this method, such that the better control increases the reliability of the reaction. Moreover, productivity can be enhanced when the amount metered in is cooled beforehand, because less cooling is required during the polymerization.

When the period of metered addition of the monomers is increased in the semi-batchwise emulsion polymerization, the concentration of the monomers remains low during the polymerization, and the effect of this is that long-chain branches and crosslinking are promoted (A. E. Hamielec, H. Tobita, Polymerization Processes, 1. Fundamentals. Ullmann's Encyclopedia of Industrial Chemistry, 2011, page 85).

To remove unconverted monomers and volatile constituents, the short-stopped latex is subjected to a steam distillation. In this case, temperatures in the range from 70°C to

150°C are employed, the pressure being reduced in the case of temperatures of <100°C.

Before the volatile constituents are removed, the latex can be post-stabilized with emulsifier. For this purpose, the aforementioned emulsifiers are appropriately used in
5 amounts of 0.1% by weight to 2.5% by weight, preferably 0.5% by weight to 2.0% by weight, based on 100 parts by weight of rubber.

Before or during the precipitation, one or more ageing stabilizers may be added to the latex. Suitable for this purpose are phenolic, aminic and also other ageing stabilizers.

10 Suitable phenolic ageing stabilizers are alkylated phenols, styrenated phenol, sterically hindered phenols such as 2,6-di-tert-butylphenol, 2,6-di-tert-butyl-p-cresol (BHT), 2,6-di-tert-butyl-4-ethylphenol, sterically hindered phenols containing ester groups, sterically hindered phenols containing thioether, 2,2'-methylenebis-(4-methyl-6-tert-butylphenol) (BPH), and also sterically hindered thiobisphenols.

15 If discolouration of the rubber is unimportant, aminic ageing stabilizers are also used, for example mixtures of diaryl-p-phenylenediamines (DTPD), octylated diphenylamine (ODPA), phenyl- α -naphthylamine (PAN), phenyl- β -naphthylamine (PBN), preferably those based on phenylenediamine. Examples of phenylenediamines are N-isopropyl-N'-phenyl-p-phenylenediamine, N-1,3-dimethylbutyl-N'-phenyl-p-phenylenediamine (6PPD), N-1,4-dimethylpentyl-N'-phenyl-p-phenylenediamine (7PPD), N,N'-bis-1,4-(1,4-
20 dimethylpentyl)-p-phenylenediamine (77PD), etc.

The other ageing stabilizers include phosphites such as tris(nonylphenyl) phosphite, polymerized 2,2,4-trimethyl-1,2-dihydroquinoline (TMQ), 2-mercaptobenzimidazole (MBI), methyl-2-mercaptobenzimidazole (MMBI), zinc methylmercaptobenzimidazole (ZMMBI). The phosphites are generally used in combination with phenolic ageing
25 stabilizers.

The workup of the diene rubber gels thus produced can be effected by concentration, coagulation, co-coagulation with a further latex polymer or by freeze-coagulation (cf. US-2,187,146) or by spray-drying. In the case of workup by spray-drying, it is also possible to add standard flow aids, for example calcium carbonate or silica. Preference is given to
30 workup by acid coagulation, optionally in the presence of monovalent salts such as sodium chloride and/or potassium chloride. Suitable acids are especially mineral acids such as sulphuric acid or phosphoric acid.

The diene rubber gels used for production of the sealing compounds may be either unmodified diene rubber gels having essentially no reactive groups, particularly at the surface, or modified diene rubber gels modified with functional groups, particularly at the surface. The following reagents in particular are useful for surface modification of the diene rubber gels with low molecular weight agents: elemental sulphur, hydrogen sulphide and/or alkyl polymercaptans such as 1,2-dimercaptoethane or 1,6-dimercaptohexane, and additionally dialkyl- and dialkylaryldithiocarbamate such as the alkali metal salts of dimethyldithiocarbamate and/or dibenzylthiocarbamate, and also alkyl- and arylxanthogenates such as potassium ethylxanthogenate and sodium isopropylxanthogenate, and the reaction with the alkali metal or alkaline earth metal salts of dibutyldithiophosphoric acid and dioctyldithiophosphoric acid, and also dodecyldithiophosphoric acid. Said reactions can advantageously also be conducted in the presence of sulphur, in which case the sulphur is also incorporated with formation of polysulphidic bonds. For addition of these bonds, it is possible to add free-radical initiators such as organic and inorganic peroxides and/or azo initiators.

Modification of the diene rubber gels, for example by ozonolysis and by halogenation with chlorine, bromine and iodine, is also an option. The amount of the modifying agent used is guided by the efficacy thereof and the demands made on the individual case and is in the range from 0.05% by weight to 30% by weight, based on the total amount of diene rubber gel used, more preferably 0.5% by weight to 10% by weight, based on the total amount of diene rubber gel.

The modification reactions can be conducted at temperatures of 0°C to 180°C, preferably 5°C to 95°C, optionally under pressure of 1 bar to 30 bar (1 bar = 100 000 Pa). The modifications can be undertaken on diene rubber gels in substance or in the form of a dispersion thereof.

The diene rubber gels have an approximately spherical geometry. Primary particles refer, according to DIN 53206:1992-08, to the diene rubber gel particles which are dispersed in the coherent phase and are recognizable as individual species by suitable physical methods (electron microscope) (cf., for example, Römpp Lexikon, Lacke und Druckfarben [Römpp's Lexikon, Coatings and Printing Inks], Georg Thieme Verlag, 1998). An "approximately spherical" geometry means that the dispersed primary particles of the diene rubber gels appear essentially as a circular surface when the composition is viewed, for example with an electron microscope. Since the diene rubber gels essentially do not change shape or morphology on further processing to give sealing compounds of the

invention, the remarks made above and below also apply equally to the diene rubber gel-containing sealing compounds of the invention.

In the primary particles of the diene rubber gel present in the sealing compound of the invention, the deviation in the diameter of an individual primary particle, defined as

5
$$[(d1 - d2) / d2] \times 100,$$

in which d1 and d2 are any two diameters of the primary particle and $d1 > d2$, is preferably less than 250%, more preferably less than 100%, even more preferably less than 80%, even more preferably less than 50%.

10 Preferably at least 80%, more preferably at least 90% and even more preferably at least 95% of the primary particles of the diene rubber gel have a deviation in the diameter, defined as

$$[(d1 - d2) / d2] \times 100,$$

15 in which d1 and d2 are any two diameters of the primary particle and $d1 > d2$, of less than 250%, preferably less than 100%, even more preferably less than 80%, even more preferably less than 50%.

The aforementioned deviation in the diameters of the individual particles can be determined by the method which follows. First of all, a thin section of the solidified composition of the invention is produced. Then a transmission electron micrograph is taken at a magnification of, for example, 10 000-fold or 200 000-fold. In an area of 833.7 x 828.8 nm, the greatest and smallest diameter in 10 diene rubber gel primary particles are determined as d1 and d2. If the above-defined deviation of at least 80%, more preferably at least 90% and even more preferably at least 95% of the diene rubber gel primary particles analysed in each case is below 250%, preferably below 100%, even more preferably less than 80% and even more preferably below 50%, the diene rubber gel primary particles have the above-defined deviation feature.

20

25

If the concentration of the diene rubber gels in the sealing compound is so high that there is significant overlap of the visible diene rubber gel primary particles, the quality of evaluation can be improved by prior suitable dilution of the measurement sample.

30 In the sealing compound of the invention, the primary particles of the diene rubber gels (A) and (B) and of the sealing gel (H) preferably have an average particle diameter of 5 nm to 500 nm, more preferably of 20 nm to 400 nm, more preferably of 20 nm to 300 nm, more preferably of 20 nm to 250 nm, even more preferably 20 nm to 99 nm, even more

preferably 30 nm to 80 nm (diameter figures according to DIN 53206). The production of particularly finely divided diene rubber gels by emulsion polymerization is effected by controlling the reaction parameters in a manner known per se (see, for example, H. G. Elias, *Macromolecules*, Volume 2, *Industrial Polymers and Syntheses*, Wiley-VCH Verlag GmbH & Co. KGaA, Weinheim, 2007, page 160 ff.).

Since the morphology of the diene rubber gels (A) and (B) and of the sealing gel (H) essentially does not change in the course of further processing of the composition of the invention, the average particle diameter of the dispersed primary particles in the further processing products obtained with the composition of the invention, such as diene rubber gel-containing sealing compounds, essentially corresponds to the average particle diameter of the dispersed primary particles.

The diene rubber gels (A) and (B) and the sealing gel (H) have insoluble fractions in toluene at 23°C, called the gel content, of at least 60% by weight, more preferably about 80% by weight, even more preferably about 90% by weight.

The diene rubber gels (A) and (B) and the sealing gel (H) appropriately have, in toluene at 23°C, a swelling index of less than about 80, preferably of less than 60, even more preferably of less than 40. For instance, the swelling indices (Q_i) of the diene rubber gels and sealing gels may more preferably be from 5 to 35.

The diene rubber gels (A) and (B) and the sealing gel (H) have a glass transition temperature of -80°C to -50°C, preferably of -75°C to -60°C and more preferably of -75°C to -65°C.

In addition, the diene rubber gels (A) and (B) and the sealing gel (H) preferably have a glass transition range (ΔT_g) of less than 20°C, preferably less than 15°C, more preferably less than 10°C, especially preferably in the range from 5°C to 10°C.

Cold-polymerized diene rubber gels (A) and (B) and sealing gel (H) may differ in terms of their microstructure from hot-polymerized diene rubber gels.

For example, in the case of 1,3-butadiene as diene monomer used, the difference in the microstructure relates to the relative proportions of 1,3-butadiene incorporated.

The relative proportions of 1,4-trans-, 1,2-vinyl- and 1,4-cis-butadiene units were determined on the basis of the measurement of the relative absorptions of 1,4-trans-, 1,2-vinyl- and 1,4-cis-butadiene bands in the IR spectrum of polymer films of the diene rubber gel. The method is calibrated with rubber samples having a microstructure known

accurately from NMR studies. The figures in % by weight are based only on the incorporated butadiene units in the diene rubber gel and together add up to 100% by weight.

5 Cold polymerized diene rubber gels (A) and (B) and the sealing gel (H) containing 1,3-butadiene as diene each have a proportion of cis-1,4-butadiene units of 8% by weight to 17% by weight, a proportion of trans-1,4-butadiene of 59% by weight to 75% by weight and a proportion of 1,2-vinylbutadiene of 17% by weight to 21% by weight, based on 1,3-butadiene incorporated.

In addition, the invention encompasses a sealing compound comprising

10 sealing gel and
at least one resin (C).

In a preferred embodiment, the sealing compound comprises

sealing gel,
at least one resin (C) and
15 at least one natural and/or synthetic rubber (E) which differs from the sealing gel.

In a further-preferred embodiment, the sealing compound comprises

sealing gel,
at least one resin (C),
at least one ageing stabilizer (D) and
20 at least one natural and/or synthetic rubber (E) which differs from the sealing gel.

In the most preferred embodiment, the sealing compound comprises

sealing gel,
at least one resin (C),
at least one ageing stabilizer (D),
25 at least one natural and/or synthetic rubber (E) which differs from the sealing gel
and

at least one plasticizer (F).

The aforementioned sealing compounds may additionally comprise further constituents such as fillers and rubber auxiliaries.

5 The sealing compounds of the invention comprise the sealing gels of the invention, as described above. In a preferred embodiment of the composition of the invention, the diene rubber gel is based on cold polymerized E-SBR.

10 The total amount of the sealing gels of the invention in the sealing compound is typically 45 phr to 100 phr, preferably 60 phr to 100 phr, more preferably 70 phr to 100 phr (parts per hundred rubber), the total amount of sealing gel and further natural and/or synthetic rubber corresponding to 100 phr.

15 The resin (C) used is appropriately one from the group of the hydrocarbon resins. Hydrocarbon resins are understood by those skilled in the art to mean polymers based on carbon and hydrogen which are used preferentially as tackifiers in polymer mixtures. They are miscible (compatible) with the polymer mixture in the amount used and act as diluents/extenders in the mixture. The hydrocarbons resins may be solid or liquid. The hydrocarbon resins may contain aliphatic, cycloaliphatic, aromatic and/or hydrogenated aromatic monomers. Different synthetic and/or natural resins may be used and may be oil-based (mineral oil resins). The Tg of the resins used should be above -30°C. The hydrocarbon resins may also be described as thermoplastic resins which soften and can
20 thus be formed when heated. They may be characterized by the softening point or that temperature at which the resin sticks together, for example in the form of granules.

The resins used with preference have at least one and preferably all of the following properties:

- Tg greater than -30°C,
- 25 - softening point greater than 5°C (especially in the range from 5°C to 135°C),
- the number-average molecular weight (Mn) is in the range from 400 g/mol to 2000 g/mol,
- the polydispersity (PDI = Mw/Mn, with Mw = weight-average molecular weight) is less than 3.

The softening point is determined by the "Ring and Ball" method of standard ISO 4625. Mn and Mw can be determined by means of techniques familiar to those skilled in the art, for example gel permeation chromatography (GPC).

5 Examples of the hydrocarbon resins used are cyclopentadiene (CPD) or dicyclopentadiene (DCPD) homopolymer or cyclopentadiene copolymer resins, terpene homopolymer or copolymer resins, terpene/phenol homopolymer or copolymer resins, homopolymer or copolymer resins of the C₅ fraction or C₉ fraction, homo- or copolymer resins of α -methylstyrene and mixtures of those described. Particular mention should be made here of the copolymer resins consisting of (D)CPD/vinylaromatic copolymer resins,
10 (D)CPD/terpene copolymer resins, (D)CPD/C₅ fraction copolymer resins, (D)CPD/C₉ fraction copolymer resins, terpene/vinylaromatic copolymer resins, terpene/phenol copolymer resins, C₅ fraction/vinylaromatic copolymer resins and mixtures of those described.

The term "terpene" encompasses monomers based on α -pinene, β -pinene and limonene,
15 preference being given to limonene or a mixture of the limonene enantiomers. Suitable vinylaromatics are, for example, styrene, α -methylstyrene, o-methylstyrene, m-methylstyrene, p-methylstyrene, vinyltoluene, p-(tert-butyl)styrene, methoxystyrene, chlorostyrene, hydroxystyrene, vinylmesitylene, divinylbenzene, vinylnaphthalene or any vinylaromatic from the C₉ fraction or from the C₈ to C₁₀ fraction.

20 The amount of resin (C) in the sealing compound of the invention is typically 10 phr to 60 phr, preferably 20 phr to 50 phr, more preferably 25 phr to 45 phr, and in at least one embodiment less than 30 phr based on the total amount of sealing gel and further natural and/or synthetic rubber (E).

25 The ageing stabilizers (D) used may be the same substances as described above for the cold emulsion polymerization of the diene rubber gels (A), (B) and sealing gel (H).

The amount of ageing stabilizer (D) in the sealing compound is typically 0.5 phr to 20 phr, preferably 1 phr to 10 phr, more preferably 1 phr to 5 phr, based on the total amount of sealing gel and further natural and/or synthetic rubber (E).

30 The natural and synthetic rubbers (E) differ from the diene rubber gels and sealing gels and generally have Mooney viscosities ML (1+4)@100 °C (DIN 53 523) of 10 MU to 80 MU, preferably 15 MU to 60 MU.

Preferred rubbers (E) are copolymers based on conjugated diolefins from a group comprising 1,3-butadiene, isoprene, 2,3-dimethyl-1,3-butadiene, 1,3-pentadiene, 1,3-

hexadiene, 3-butyl-1,3-octadiene, 2-phenyl-1,3-butadiene or mixtures thereof, more preferably from a group comprising natural cis-1,4-polyisoprene, synthetic cis-1,4-polyisoprene, 3,4-polyisoprene, polybutadiene, 1,3-butadiene-acrylonitrile copolymer and mixtures thereof.

5 Further preferred synthetic rubbers are described, for example, in I. Franta, *Elastomers and Rubber Compounding Materials*, Elsevier, New York 1989, or else in Ullmann's *Encyclopedia of Industrial Chemistry*, Vol. A 23, VCH Verlagsgesellschaft, Weinheim 1993. They include

BR - polybutadiene,

10 Nd-BR - neodymium polybutadiene rubber,

Co-BR - cobalt polybutadiene rubber,

Li-BR - lithium polybutadiene rubber,

Ni-BR - nickel polybutadiene rubber,

Ti-BR - titanium polybutadiene rubber,

15 PIB - polyisobutylene,

ABR - butadiene/C₁₋₄-alkyl acrylate copolymers,

IR - polyisoprene,

SBR - styrene/butadiene copolymers having styrene contents of 1% by weight to 60% by weight, preferably 2% by weight to 50% by weight,

20 E-SBR - emulsion styrene/butadiene copolymers,

S-SBR - solution styrene/butadiene copolymers,

25 XSBR - styrene/butadiene copolymers and graft polymers with acrylic acid, methacrylic acid, acrylonitrile, hydroxyethyl acrylate and/or hydroxyethyl methacrylate, glycidyl methacrylate having styrene contents of 2% by weight to 50% by weight and contents of copolymerized polar monomers of 1% by weight to 30% by weight,

IIR - isobutylene/isoprene copolymers, preferably having isoprene contents of 0.5% by weight to 10% by weight,

- BIIR - brominated isobutylene/isoprene copolymers, preferably having bromine content 0.1% by weight to 10% by weight,
- CIIR - chlorinated isobutylene/isoprene copolymers, preferably having chlorine content 0.1% by weight to 10% by weight,
- 5 NBR - butadiene/acrylonitrile copolymers, typically having acrylonitrile contents of 5% by weight to 60% by weight, preferably 10% by weight to 50% by weight,
- HNBR - fully and partly hydrogenated NBR rubber in which up to 100% of the double bonds are hydrogenated,
- 10 HXNBR - carboxylated partly and fully hydrogenated nitrile rubbers,
- EP(D)M - ethylene/propylene/(diene) copolymers,
- EVM- ethylene-vinyl acetate,

and mixtures of these rubbers.

- 15 The amount of natural and/or synthetic rubber (E) in sealing compounds of the invention is typically 0 phr to 55 phr, preferably 0 phr to 40 phr, more preferably 0 phr to 30 phr, based on the total amount of sealing gel and further natural and/or synthetic rubber (E).

The total amount of sealing gel and further natural and/or synthetic rubber (E) in the sealing compound is 100 phr.

- 20 For the sealing mixture of the invention, plasticizers (F) are typically used in an amount of less than 60 phr. The plasticizer dilutes the matrix consisting of diene elastomers and resins and makes it softer and more supple, in order that the sealing effect of the sealing mixture under cold conditions in particular, typically at temperatures below 0°C, is improved. The plasticizer used typically has a Tg of less than -20°C and preferably less than -40°C.

- 25 Suitable plasticizers are any liquid elastomers or lubricant oils, which may be either aromatic or nonaromatic, and any liquid substances which are known for their plasticizing action in elastomers, especially in diene-containing elastomers. Particularly suitable are liquid elastomers having an Mn of 400 to 90 000 g/mol. Examples of lubricant oils are paraffinic oils, naphthenic oils having low or high viscosity, in hydrogenated or non-
- 30 hydrogenated form, aromatic or DAE (Distilled Aromatic Extracts) oils, MES (Medium

Extracted Solvates) oils, TDAE (Treated Distillate Aromatic Extracts) oils, mineral oils, vegetable oils (and oligomers thereof, for example palm oil, rapeseed oil, soya oil or sunflower oil) and mixtures of the oils mentioned.

Also suitable are oils based on polybutene, especially polyisobutylene (PIB)-based oils, and ether-, ester-, phosphate- and sulphonate-based plasticizers, preference being given to esters and phosphates. Preferred phosphate plasticizers are those having 12 to 30 carbon atoms, for example trioctyl phosphate. Preferred ester plasticizers are substances from the group comprising trimellitates, pyromellitates, phthalates, 1,2-cyclohexanedicarboxylates, adipates, azelates, sebacates, glycerol triesters and mixtures thereof. The fatty acids used with preference, in synthetic or natural form (in the case of sunflower oil or rapeseed oil, for example), are those containing more than 50% by weight and more preferably more than 80% by weight of oleic acid. Among the triesters, preference is given to glycerol triesters consisting predominantly to an extent of more than 50% by weight, more preferably more than 80% by weight, of unsaturated C₁₈ fatty acids, for example oleic acid, linoleic acid, linolenic acid and mixtures thereof. Such **triesters** have a high content of oleic acid and are described in the literature as plasticizers for rubber mixtures which are used in tyre treads, for example in US-A-2004/0127617.

Unlike in the case of liquid elastomers, the number-average molecular weight (M_n) of the liquid plasticizer is preferably in the range from 400 to 25 000 g/mol, even more preferably in the range from 800 to 10 000 g/mol (measured by means of GPC).

In summary, preference is given to using liquid plasticizers from the group of the liquid elastomers, polyolefin oils, naphthene oils, paraffin oils, DAE oils, MES oils, TDAE oils, mineral oils, vegetable oils, plasticizers composed of ethers, esters, phosphates, sulphonates and mixtures of those described.

The amount of plasticizer (F) in the sealing compounds of the invention is typically 0 phr to 60 phr, preferably 10 phr to 50 phr, more preferably 15 phr to 40 phr, based on the total amount of sealing gel and further natural and/or synthetic rubber (E).

The above-described sealing compounds of the invention may optionally contain additional fillers (G). A filler is understood in the present invention to mean both reinforcing fillers (typically particles having an average size of less than 500 nm, especially in the range from 20 nm to 200 nm) and non-reinforcing or inert fillers (typically particles having an average size of more than 1 µm, for example in the range from 2 µm to 200 µm). The reinforcing and non-reinforcing fillers are intended to improve cohesion in the sealing compound. These include:

- carbon blacks which are used in the sealing compounds of the invention are appropriately those which are used in tyre production, for example carbon blacks according to ASTM Standard 300, 600, 700 or 900 (N326, N330, N347, N375, N683, N772 or N990), and typically produced by the thermal black, furnace black or gas black method and having BET surface areas of 20 m²/g to 200 m²/g (determined by means of absorption of CTAB as described in ISO 6810 Standard), for example SAF, ISAF, IISAF, HAF, FEF or GPF carbon blacks. Alternatively, it is also possible to use carbon blacks having a surface area of less than 20 m²/g.

- finely divided silicas, produced, for example, by precipitation of solutions of silicates or flame hydrolysis of silicon halides having specific surface areas of 5 to 1000 and preferably 30 m²/g to 400 m²/g (BET surface area measured by the ISO 5794/1 Standard) and having primary particle sizes of 5 to 400 nm. The silicas may optionally also be in the form of mixed oxides with other metal oxides, such as oxides of Al, Mg, Ca, Ba, Zn and Ti.

- synthetic silicates, such as aluminium silicate, alkaline earth metal silicates such as magnesium silicate or calcium silicate, having BET surface areas (measured by the ISO 5794/1 Standard) of 20 m²/g to 400 m²/g and primary particle diameters of 10 nm to 400 nm.

- natural silicates, such as kaolin and other naturally occurring silicas.

- metal oxides, such as zinc oxide, calcium oxide, magnesium oxide, aluminium oxide.

- metal carbonates, such as magnesium carbonate, calcium carbonate, zinc carbonate.

- metal sulphates, such as calcium sulphate, barium sulphate.

- metal hydroxides, such as aluminium hydroxide and magnesium hydroxide.

- colouring fillers or coloured fillers, such as pigments.

- rubber gels based on polychloroprene, NBR and/or polybutadiene having particle sizes of 5 nm to 1000 nm.

The fillers mentioned can be used alone or in a mixture.

The fillers are present in the sealing compounds of the invention typically in an amount of 1 phr to 50 phr, preferably in an amount of 1 phr to 30 phr, more preferably in an amount of 1 phr to 20 phr, based on the total amount of sealing gel and further natural and/or synthetic rubbers (E).

The sealing compounds of the invention may optionally contain further rubber auxiliaries which are typically used in rubber mixtures, for example one or more further crosslinkers, accelerators, thermal stabilizers, light stabilizers, ozone stabilizers, processing aids, extenders, organic acids or retardants.

5 The rubber auxiliaries can be used individually or in mixtures.

The rubber auxiliaries are used in standard amounts guided by the end use among other factors. Standard amounts are, for example, amounts of 0.1 phr to 50 phr.

In a preferred embodiment, the sealing compound of the invention comprises

- 10 • 45 phr to 100 phr, preferably 60 phr to 100 phr and more preferably 70 phr to 100 phr of the sealing gels of the invention, preference being given to styrene-butadiene-diene rubber gels,
- 10 phr to 60 phr, preferably 20 phr to 50 phr and more preferably 25 phr to 45 phr of at least one resin (C),
- 15 • 0 phr to 20 phr, preferably 1 phr to 10 phr and more preferably 1 phr to 5 phr of at least one ageing stabilizer (D),
- 0 phr to 55 phr, preferably 0 phr to 40 phr and more preferably 0 phr to 30 phr of at least one natural and/or synthetic rubber (E),
- 0 phr to 60 phr, preferably 10 phr to 50 phr and more preferably 15 phr to 40 phr of at least one plasticizer (F),
- 20 • optionally 1 phr to 50 phr, preferably 1 phr to 30 phr and more preferably 1 phr to 20 phr of at least one filler (G),

based in each case on the total amount of sealing gel and further natural and/or synthetic rubbers (E).

25 The sealing compound of the invention preferably has at least one of the preferred properties described hereinafter.

The sealing compound of the invention typically has a Mooney viscosity (ML1+4@100 °C) of 5 MU up to 50 MU, preferably 8 MU up to 40 MU. The Mooney viscosity is determined by the standard ASTM D1646 (1999) and measures the torque of the sample at elevated temperature. It has been found to be useful to calender the sealing compound
30 beforehand. For this purpose, the sealing compound is processed on a roller at a roller

temperature of $T \leq 60^{\circ}\text{C}$ to give a rolled sheet. The cylindrical sample punched out is placed into the heating chamber and heated up to the desired temperature. After a preheating time of one minute, the rotor rotates at a constant 2 revolutions/minute and the torque is measured after four minutes. The Mooney viscosity measured (ML 1+4) is in
5 "Mooney units" (MU, with 100 MU = 8.3 Nm).

In the SAFT test, the sealing compound of the invention typically has a failure temperature (Shear Adhesion Failure Temperature) of $> 70^{\circ}\text{C}$, preferably $> 85^{\circ}\text{C}$, more preferably $> 95^{\circ}\text{C}$.

For the sealing compounds of the invention, the distance that the steel ball covers in the rolling ball tack test is typically less than 3 cm, more preferably less than 2 cm, most
10 preferably in the range from 0.05 cm to 2.0 cm.

The sealing compound should exert a minimum influence on the rolling resistance of the tyre. For this purpose, the loss factor $\tan \delta$ at 60°C , which is established in industry as a rolling resistance indicator, is employed as the measurement parameter, this being
15 determined by dynamic-mechanical analysis (DMA) with a rheometer. From the measurement, the temperature-dependent storage and loss moduli G' and G'' are obtained. The temperature-dependent $\tan \delta$ value is calculated from the quotient of loss modulus to storage modulus. The $\tan \delta$ value at 60°C and 10 Hz for the sealing compounds of the invention is typically less than 0.35, preferably less than 0.30 and more
20 preferably less than 0.25.

The invention further relates to a process for producing sealing compounds. In this case, the sealing gel of the invention can also be produced by mixing latices of the diene rubber gels (A) and (B), or (A) and/or (B), with sealing gel (H) and co-processing the mixture. Constituents of the sealing compound can likewise be produced by mixing the diene
25 rubber gel/sealing gel latices with latices of the natural rubbers and/or synthetic rubbers and by mixing further sealing compound constituents, preferably in the form of suspensions thereof, and processing them together. For this purpose, the sealing compound of the invention can be produced in a masterbatch. The sealing compounds of the invention, composed of at least one sealing gel and at least one resin (C), can be
30 produced in various ways. For example, it is possible to mix the solid or liquid individual components. Examples of equipment suitable for the purpose are rollers, internal mixers or mixing extruders. In a first step, the sealing gels are mixed with at least one resin (C) at a temperature (1st mixing temperature) which is above the softening temperature of the resin. It should be noted here that the temperature is not the target temperature for the
35 mixer but the actual temperature of the mixture.

It is optionally possible to add various additives to the masterbatch, for example stabilizers, pigments, ageing stabilizers, etc. The masterbatch can be produced in a compounding system, for example in a paddle mixer, in an open two-roll mill, an extruder or any other mixing system capable of sufficient mixing and kneading of the various components of the sealing compound, such that a homogeneous mixture can be obtained. Preference is given to using a screw extruder with or without a constant screw helix, which can introduce high shear into the mixture.

The resin (C) may be solid or liquid in the initial phase prior to the addition to the sealing gels, which are solid. In the blending of the resin (C) with the sealing gel during the mixing, preference is given to a liquid form of the resin in order to obtain better mixing. This is achieved by the heating of the resin above the softening temperature. Depending on the resin used, the mixing temperature is typically above 70°C, preferably above 80°C, for example between 100°C and 150°C. Preferably, the resin (C) is metered into the mixer under pressure in the form of an injection of the liquid resin with exclusion of oxygen. This step can be combined with the mixing at the 1st mixing temperature.

Further processing steps are preferably effected at a temperature below the softening temperature of the resin (C), for example at 50°C (2nd mixing temperature).

One example for production of the sealing compound as a masterbatch in a screw extruder is as follows:

a single-screw extruder is used, having a 1st metered addition for the mixture constituents and a 2nd metered addition (metering pump) for the liquefied resin (C). The mixing is effected by rotating the screw, and the mixture components experience high shear. The mixture then passes to the homogenizer with a chopper tool. Downstream of this zone, the masterbatch is finally extruded in the desired shape through a simple extrusion head. The sealing mixture obtained is, for example, packed between two silicone-coated films and cooled down, and is ready to use. The extrudate can also be conducted beforehand to a twin-roller system in order to be able to meter in further mixture ingredients (pigments, fillers, etc.) if necessary in this step. The metered addition may be continuous. The roll temperature is preferably below 100°C. The sealing mixture is packed analogously. It is possible to produce this sealing mixture under industrial conditions without entering into the risk of contamination/soiling of the tools, for example as a result of sticking of the sealing compound to the roll.

The application of the sealing layer to the tyre may follow the vulcanization of the tyre. Typical methods of applying the sealing layer are described, for example, in US-A-

5,295,525. The sealing compounds based on diene rubber gels may be applied, for example, to the tyre lining in a continuous process without having to be subjected to a vulcanization. The sealing compound may be extruded, for example, as a sealing layer or strip on the inside of the tyre. In an alternative embodiment, the sealing compound may be processed as a strip which is then bonded to the inside of the tyre.

In a further alternative embodiment, the sealing compound can be prepared as a solvent cement which is sprayed, for example, onto the inside of the tyre. A further alternative mode of application as a laminate is described in US-A-4,913,209.

The invention therefore further relates to the use of the sealing gels in sealing compounds, especially to improve the adhesion and cohesion properties.

The invention further relates to the use of sealing gel-containing sealing compounds as sealing layer in tyres, preferably on inner liners of pneumatic motor vehicle tyres.

The present invention thus further provides a pneumatic motor vehicle tyre comprising a sealing gel-containing sealing compound of the invention.

The invention also relates to the use of the sealing gels in sealing compounds for seals of hollow bodies and membranes.

The advantage of the invention lies especially in the excellent cohesion and adhesion properties and in the low rolling resistance of the sealing compound.

The examples which follow describe the invention but without limiting it.

Examples:

In the examples which follow, the following substances are used:

Name	Source
Styrene (ST)	Azelis
1,3-Butadiene unstabilized (BDN)	Air Liquide Deutschland GmbH
tert-Dodecyl mercaptan (tDDM)	Phillips
Dresinate 835 (Abieta TM DRS 835) (emulsifier)	Arizona Chemical B.K.
Oleic acid	Merck KGaA
Trimethylolpropane trimethylacrylate (TMPTMA)	Sigma-Aldrich Chemie GmbH
Divinylbenzene (DVB)	Sigma-Aldrich Chemie GmbH
Potassium hydroxide (KOH)	Riedel-de-Haen
Potassium chloride (KCl)	Riedel-de-Haen
p-Menthane hydroperoxide (Trigonox® NT 50)	Akzo-Degussa
Sodium phosphate dodecahydrate (Na ₃ PO ₄ * 12 H ₂ O)	Merck KGaA
Rongalit® C (for synthesis)	Merck KGaA
Ethylenediaminetetraacetic acid EDTA (ultrapure)	Merck KGaA
Iron(II) sulphate heptahydrate (FeSO ₄ * 7 H ₂ O)	Merck KGaA
Sodium chloride (NaCl)	Merck KGaA
Phosphoric acid (H ₃ PO ₄)	VWR
Calcium chloride anhydrous (CaCl ₂)	Merck KGaA
E-SBR rubber (Buna SE 1502 H)	LANXESS Deutschland GmbH
Butyl rubber (X_Butyl TM RB 301)	LANXESS Deutschland GmbH
EPDM rubber (Keltan® 2660)	LANXESS Deutschland GmbH
Natural rubber (SVR 3L)	Weber & Schaefer
EVM rubber (Levamelt® 600)	LANXESS Deutschland GmbH
Polyisobutylene rubber (Oppanol B15N)	BASF

Escorez™ 2173 (hydrocarbon resin)	ExxonMobil Chemical
Novares C90 (hydrocarbon resin)	Rütgers Chemicals
TDAE oil Vivatec® 500 (plasticizer)	LANXESS Deutschland GmbH
Vulkanox® HS LG (ageing stabilizer)	LANXESS Deutschland GmbH
Vulkanox® MB2/MG-C (ageing stabilizer)	LANXESS Deutschland GmbH
Vulkanox® 4020 (ageing stabilizer)	LANXESS Deutschland GmbH
Radglo® GM-25 (pigment)	Radiant Color N.V.
Regal SRF (carbon black)	Cabot
Tronox® Titanium Dioxide (pigment)	Tronox
Oppasin Blue 6900 (pigment)	BASF

Test methods:

CHARACTERIZATION OF THE DIENE RUBBER GELS AND SEALING GELS

Determination of conversion: The conversion of the cold emulsion polymerization is calculated from the solids content of the latex solution. The determination of solids in the latex is effected by means of a halogen moisture analyser (Mettler Toledo, Halogen Moisture Analyzer HG63). For this purpose, an aluminium pan (Mettler, article no. 13865) is inserted into the sample holder and tared. Then an HAF1 glass fibre filter (Mettler, article no. 214464) is placed on top and the measurement is started. Typically, the glass fibre filter in the course of storage absorbs about 0.5% air humidity. Subsequently, the aluminium pan with the dried glass fibre filter is inserted into the sample holder and the balance is tared. About 1 g to 1.5 g of latex are weighed in and distributed over a maximum area in order to enable complete absorption of the liquid through the glass fibre filter. Then the measurement is started. When the weight loss of the sample is less than 1 mg per 50 seconds, the measurement is ended and the solids content is noted. The measured solids content of the latex and the theoretical solids content of the latex at the end of the polymerization are used to calculate the conversion of the emulsion polymerization.

Determination of gel content: The fraction insoluble in toluene is determined in toluene at 23°C. This is done by swelling 250 mg of the diene rubber gel in 20 ml of toluene with agitation at 23°C for 24 hours. After centrifugation at 20 000 rpm, the insoluble fraction is

removed and dried. The gel content is calculated from the quotient of the dried residue and the starting weight and is reported in per cent.

Glass transition temperature: The glass transition temperatures (T_g) and the breadth of the glass transition (ΔT_g) of the diene rubber gels are determined by differential thermoanalysis (DTA, differential scanning calorimetry (DSC)) on a 2003 Perkin Elmer DSC-7 calorimeter. For the determination of T_g and ΔT_g , two cooling/heating cycles are conducted. T_g and ΔT_g are determined in the second heating cycle. For the determinations, 10 mg to 12 mg of the diene rubber gels are used in a DSC sample holder (standard aluminium pan) from Perkin Elmer. The first DSC cycle is conducted by first cooling the sample down to -100°C with liquid nitrogen and then heating it up to $+150^\circ\text{C}$ at a rate of 20 K/min. The second DSC cycle is commenced by immediate cooling of the sample as soon as a sample temperature of $+150^\circ\text{C}$ has been achieved. The cooling is effected at a rate of about 320 K/min. In the second heating cycle, the sample is heated up once more to $+150^\circ\text{C}$ as in the first cycle. The heating rate in the second cycle is again 20 K/min. T_g and ΔT_g are determined from the graph of the DSC curve of the second heating operation. For this purpose, three straight lines are applied to the DSC curve. The first straight line is applied to the part of the DSC curve below T_g , the second straight line to the curve section with a turning point that runs through T_g , and the third straight line to the curve section of the DSC curve above T_g . In this way, three straight lines with two points of intersection are obtained. Each point of intersection is characterized by a characteristic temperature. The glass transition temperature T_g is obtained as the mean of these two temperatures and the breadth of the glass transition ΔT_g is obtained from the difference between the two temperatures.

To determine the swelling index, 250 mg of the diene rubber gel are swollen under agitation in 25 ml of toluene at 23°C for 24 h. The gel is centrifuged off at 20 000 rpm, weighed and then dried to constant weight at 70°C and weighed once again. The swelling index is calculated as follows:

$$Q_i = \text{wet weight of the gel} / \text{dry weight of the gel}.$$

The Mooney viscosity of the diene rubber gels and the sealing gels is determined by the standard ASTM D1646 (1999) and measures the torque of the sample at elevated temperature using a 1999 Alpha Technologies MV 2000 Mooney viscometer (manufacturer serial number: 25AIH2753). It has been found to be useful to calender the diene rubber gel or the sealing gel beforehand. For this purpose, the diene rubber gel or the sealing gel is processed on a roller at a roller temperature of $T \leq 60^\circ\text{C}$ to give a rolled sheet. The roller gap is varied between 1 mm and 3 mm, the friction is -10% and the roller

5 revolutions per minute are 7-8 rpm. The measurement is conducted as follows: The cylindrical sample punched out is placed into the heating chamber and heated up to the desired temperature (here 100°C). After a preheating time of one minute, the rotor (of size L) rotates at a constant 2 revolutions/minute and the torque is measured after four minutes. The Mooney viscosity measured (ML 1+4) is in "Mooney units" (MU, with 100 MU = 8.3 Nm).

CHARACTERIZATION OF THE SEALING COMPOUND

10 The tackiness (measurement parameter for adhesion) of the sealing compound of the invention is determined by means of a rolling ball tack tester.

The test is conducted on the basis of the standard ASTM D3121-06 at a temperature of 7°C. The sealing compound is pressed to a thickness of 1 mm at 105°C and 120 bar for 10 min and cooled to room temperature under pressure over a period of 12 h. The sealing compound thus pressed is cut to a rectangle of edge length 20 cm x 10 cm, ensuring a smooth and contamination-free surface. The rectangular sealing compound of thickness 1 mm is placed onto a flat surface and the rolling ball tack tester is set up on the rectangular sealing film such that the tester is likewise flat (checked by means of a spirit level) and a ball rolling distance of ≥ 6 cm is possible. The polished steel ball having a diameter of 1 cm (ChemInstruments) is cleaned in acetone before each test and then placed onto the rolling ball tack tester. In this case, surface contamination of the ball, which can be caused, for example, by direct contact with the hands, should be avoided. By actuating the trigger mechanism of the rolling ball tack tester, the ball is put in a state of controlled movement. The distance that the ball has rolled on the test material is measured. This is done by measuring from the end of the rolling ball tester to the middle of the ball. Each experiment is conducted on a contamination-free surface. The experiment is repeated at least three times and the average is reported as the result.

30 To determine the failure temperature (measurement parameter for cohesion), the SAFT test (Shear Adhesion Failure Temperature) is conducted on the basis of standard ASTM D4498-07 (called Heat Fail Temperature therein). For this purpose, the sealing compound is pressed to a thickness of 1 mm at 105°C and 120 bar for 10 min and cooled to room temperature under pressure over a period of 12 h. The pressed sealing compound which has been cut to an edge length of 2.5 cm x 2.5 cm is positioned halfway between two polished stainless steel plates of dimensions 7.5 cm x 7.5 cm x 2.5 cm which have been cleaned beforehand with acetone, so as to give a square sample geometry of dimensions

2.5 cm x 2.5 cm x 0.1 cm between the two plates. The stainless steel plates from ChemInstruments each have a hole at the end of the plate. The sealing compound is pressed between the two stainless steel plates at room temperature at 5.4 bar with the stainless steel plates for 3 min, in order to establish an adhesive bond between stainless steel plate and sealing compound. Subsequently, the adhesive bond construction is suspended in a shear tester (ChemInstruments SS-HT-8). It should be ensured that the stainless steel plates along with the sealing compound hang vertically. A weight of 500 g is suspended on the hole in the plate pointing downward. The temperature of the shear testing oven (Mettmert, UF 110 Plus) is left at room temperature for one hour. Subsequently, the time measurement is started and the temperature is increased to 40°C in a linear manner within 10 min and kept constant for 20 min, before the oven is heated up to 175°C at a heating rate of 0.5°C/min and kept constant for not more than 4 hours. The temperature and time at which the adhesive construction fails and the weight falls down are noted.

The determination of the loss factor $\tan \delta$ at 60°C as an indicator of rolling resistance is effected on the basis of standard DIN-ISO 6721-1 and 6721-2. The preparation of the sealing compound for the measurement of the loss factor as an indicator of rolling resistance is conducted as follows: The sealing compound is processed on a roller at a roller temperature of $T \geq 60^\circ\text{C}$ to give a rolled sheet. The sheet is subsequently passed through a roll gap of 0.5 mm, which results in a sheet having a thickness of ≤ 3.5 mm. A sample of size 10 cm x 10 cm is taken from this sheet and pressed in a mould of 10 cm x 10 cm x 0.1 cm at a pressure of 120 bar and a temperature $T \geq 105^\circ\text{C}$ for 10 min. After cooling to room temperature within 10 minutes, a round sample having a diameter of 8 mm is punched out of the pressed material for dynamic-mechanical measurements. This sample is fixed between two plates. Before the temperature run, a time run is conducted on the sample for a period of 10 min at 100°C and an initial force of 2 N. Subsequently, a temperature run is conducted with an initial force of 2 N and maximum deformation of 2% in the range from -100°C to 170°C at a constant frequency of 10 Hz and a heating rate of 3 K/min.

Production and characterization of the diene rubber gels and sealing gels

There follows a description of the production of the cold-polymerized diene rubber gels (A) of the invention (A1 to A4), (B) (B1 to B4) and the sealing gel (H) (H1 to H3), and the diene rubber gels A1, A4 and B2, B4 and the sealing gel H3 were used in the further examples. Also described is the production of hot-polymerized SBR comparative

examples W1 and W2 that are not in accordance with the invention and of the sealing gel N1 that is not in accordance with the invention.

The diene rubber gels A1 to A4 and B1 to B4 and the sealing gels H1 to H3 are produced by emulsion polymerization, using 1,3-butadiene (BDN) and styrene (ST) as monomers and trimethylolpropane trimethacrylate (TMPTMA) and/or divinylbenzene (DVB) as crosslinkers. The monomers and essential formulation constituents used for the production of the diene rubber gels (A), (B) and (W) and the sealing gels (H) are summarized in the following table:

Table 1a:

Diene rubber gel	Solvent	Emulsifiers		Monomers		Crosslinker	
	Water [g]	Oleic acid [g]	Dresinate [g]	BDN [g]	ST [g]	TMPTMA [g]	DVB [g]
A1	11939	80	171	3492	400	112.5	--
A2	11939	80	171	3516	400	87.5	--
A3	11939	80	171	3528	400	75.0	--
A4	11939	80	171	3892	--	112,5	--
B1	11939	80	171	3540	400	--	75.0
B2	11939	80	171	3528	400	--	90.0
B3	11939	80	171	3128	800	--	90
B4	11939	80	171	4193	--	--	134
W1	11939	80	171	3528	400	75	--
W2	11939	80	171	3540	400	--	75

Table 1b:

Sealing gel	Solvent	Emulsifiers		Monomers		Crosslinker	
	Water [g]	Oleic acid [g]	Dresinate [g]	BDN [g]	ST [g]	TMPTMA [g]	DVB [g]
H1	11939	80	171	3528	400	62.5	15
H2	11939	80	171	3516	400	62.5	30
H3	11939	80	171	3504	400	62.5	45

(a) Emulsion polymerization and crosslinking of the BR and SBR rubber

Examples A1 to A4, B1 to B4 and H1 to H3:

The figures relate to 100% pure feedstocks. The diene rubber gels are produced in a 20 l autoclave with stirrer system. Monomers, crosslinker, emulsifiers and the amounts of water specified in the table (minus the amounts of water required for the production of the aqueous premix and initiator solutions) were initially charged in the autoclave.

After adjusting the temperature of the reaction mixture to 10°C, freshly produced aqueous premix solution (4% strength) was introduced into the autoclave to activate the initiator. These premix solutions consisted of 1.10 g of ethylenediaminetetraacetic acid, 0.86 g of

iron(II) sulphate * 7 H₂O (calculated without water of crystallization) and 2.07 g of Rongalit® C (sodium formaldehydesulphoxylate 2-hydrate, calculated without water of crystallization). At first, half the solution was added. Also metered into the reactor for initiation was 0.058% by weight (again based on the sum total of all the monomers) of p-menthane hydroperoxide (Trigonox® NT 50 from Akzo-Degussa), which was emulsified in 200 ml of the emulsifier solution prepared in the reactor. On attainment of 30% conversion, the remaining 50% of the premix solution was metered in.

The temperature was controlled during the polymerization by adjusting the coolant volume and coolant temperature at $10 \pm 0.5^{\circ}\text{C}$.

On attainment of a polymerization conversion of more than 85% (typically: 90% to 100%), the polymerization was stopped by adding an aqueous solution of 2.35 g of diethylhydroxylamine. To remove volatile constituents from the latex, the latex was stripped with steam.

Comparative examples W1 and W2:

SBR rubber gels that are not in accordance with the invention were produced by means of hot emulsion polymerizations. The production of W1 and W2 was effected like the cold emulsion polymerization in each case, but at a polymerization temperature of 50°C .

(b) Workup of the diene rubber gels

The precipitation of the diene rubber gel was conducted as follows:

A 15 l stainless steel pot equipped with a dissolver stirrer was initially charged with 3 kg of latex while stirring, and heated to 60°C . Then 1 kg of a 20% NaCl solution (333 g/kg of latex) was added, forming a very fine coagulate. Subsequently, the suspension was heated to 75°C and 25% phosphoric acid was slowly added dropwise. In the course of this, it was important that the dissolver stirrer ran at maximum stirrer speed (1500 rpm), since the coagulate otherwise conglomerated readily to a large ball. In the neutral pH range, the suspension formed a foam, which disappeared completely in the acidic range. The precipitation was complete and the serum was colourless and clear.

Then the coagulate was filtered through a 200 μm cloth and then washed to neutrality with demineralized water. Two washing cycles were sufficient for the purpose.

Subsequently, the polymer was dried down to a residual moisture content of $\leq 0.5\%$ in a vacuum drying cabinet at 55°C .

The analytical data, determined by the methods described above, are reproduced in Table 2 below.

Table 2:

	Conversion [%]	Primary particle diameter [nm]	Gel content [%]	Swelling index QI	T _g [°C]	ΔT _g [°C]	(ML1+4) @100 °C [MU]
A1	93	42	88	24	-70	7	183
A2	87	38	83	29	-71	7	187
A3	87	39	77	34	-71	6	188
A4	96	29	90	24	-78	10	194
B1	88	39	86	12	-69	6	87
B2	92	41	94	12	-69	6	77
B3	92	44	93	9	-58	8	84
B4	92	45	94	11	-74	12	88
H1	92	36	88	32	-71	6	123
H2	92	34	93	15	-70	7	129
H3	92	39	92	12	-69	7	124
W1	97	36	17	15	-71	6	74
W2	97	39	44	9	-71	6	61

The cold-polymerized BR and SBR rubber gels (A) and (B) shown in Table 2, at a conversion of more than 85%, have a gel content of more than 75% and a Mooney viscosity (ML1+4@100°C) of more than 75 MU.

- 5 The cold-polymerized SBR gels (H) shown in Table 2, at a conversion of more than 85%, have a gel content of more than 75% and a Mooney viscosity (ML1+4@100°C) of more than 100 MU.

Cold-polymerized SBR rubber gels of the invention differ from the hot-polymerized SBR rubber gels that are not in accordance with the invention in terms of microstructure. A comparison of the microstructure of the cold-polymerized SBR rubber gels A1 and B2 of the invention and the sealing gels H1 and H2 with the corresponding hot-polymerized SBR rubber gels W1 and W2 which have been produced by a hot emulsion polymerization and are not in accordance with the invention is compiled in Table 3 below. Additionally, the microstructure of the cold-polymerized BR gels A4 and B4 of the invention is shown in Table 3. The measurements were conducted on a 1999 Thermo Scientific Nicolet FTIR Nexus instrument.

Table 3:

Diene rubber gel	cis [% by wt.]	trans [% by wt.]	vinyl [% by wt.]
A1	13.9	66.3	19.8
W1	21.7	57.1	21.2
B2	14.9	64.8	20.3
W2	22.2	55.7	22.1
H1	14.4	65.3	20.2
H2	14.5	65.4	20.1
A4	15	64	21
B4	15	65	20

Cold-polymerized diene rubber gels (A) and (B) of the invention have a proportion of cis-1,4-butadiene units of 8% by weight to 17% by weight, a proportion of trans-1,4-butadiene units of 59% by weight to 75% by weight and a proportion of 1,2-vinylbutadiene units of 17% by weight to 21% by weight, based on 1,3-butadiene incorporated.

- 5 Cold-polymerized sealing gels (H) of the invention have a proportion of cis-1,4-butadiene units of 8% by weight to 17% by weight, a proportion of trans-1,4-butadiene units of 59% by weight to 75% by weight and a proportion of 1,2-vinylbutadiene units of 17% by weight to 21% by weight, based on 1,3-butadiene incorporated.

- 10 Production and characterization of sealing gels M1 to M7 of the invention and the sealing gel N not in accordance with the invention

The sealing gels M1 to M7 and N1 were produced on the basis of A1, A4, B2, B4, H3 and W1 on a Collin W 150 G roll mill built in 04/2013. The roll temperature during the mixing operation was $\leq 60^{\circ}\text{C}$. The roller gap was varied between 1 mm and 3 mm, the friction was -10% and the roller revolutions per minute were 7 rpm to 8 rpm.

- 15 The compositions of the sealing gels (M) of the invention and of the sealing gel (N) that is not in accordance with the invention are specified in Table 4 below. The determination of the Mooney viscosity was determined by the above-described method with a rolled sheet using an Alpha Technologies MV 2000 Mooney viscometer. The amounts of the individual components are reported in % by weight. By varying the composition of the diene rubber gels, it is possible to control the Mooney viscosity of the sealing gel.
- 20

Table 4:

Sealing gel	A1 [% by wt.]	B2 [% by wt.]	A4 [% by wt.]	B4 [% by wt.]	H3 [% by wt.]	W1 [% by wt.]	(ML1+4) @ 100 °C [MU]
M1	70	30	0	0	0	0	168
M2	50	50	0	0	0	0	125
M3	30	70	0	0	0	0	103
M4	20	80	0	0	0	0	104
M5	0	0	0	0	100	0	124
M6	20	0	0	0	80	0	108
M7	0	0	70	30	0	0	113
N1	0	50	0	0	0	50	73

Production and characterization of the sealing compounds VV1 to VV3 that are not in accordance with the invention and the sealing compounds V1 to V16 of the invention

The sealing compound was produced on a Collin W 150 G roll mill built in 04/2013. The roll temperature during the mixing operation was 90°C. The roller gap was varied between 1 mm and 3 mm, the friction was -10% and the roller revolutions per minute were 7 rpm to 8 rpm.

- 5 For the production of the sealing compounds V1 to V4 and V6 to V16 of the invention, the diene rubber gels A1, A4, B2, B4 and H3 were first each mixed together homogeneously on the roll as described above to give the sealing gels M1 to M4 and M6 and M7. Subsequently, rubber (E) was added in each case and well-dispersed. Thereafter, resin (C) was added gradually in small portions, followed by the ageing stabilizers (D), the
- 10 pigment (G) and lastly the plasticizer (F). For the production of the sealing compound V5 of the invention, the sealing gel H3 on the roller was mixed homogeneously together with the rubber (E) on the roller and then resin (C) was added gradually in small portions, followed by the ageing stabilizers (D), the pigment (G) and lastly the plasticizer (F). Rolling was continued until the mixture appeared homogeneous to the eye.
- 15 The composition of the sealing compounds VV1 to VV3 that are not in accordance with the invention and of the sealing compounds V1 to V16 of the invention and the amounts thereof are specified in Table 5 and 6. The amounts of the individual components are reported in phr.

Table 5:

Sealing compound	VV1	VV2	VV3	V1	V2	V3	V4	V5	V6	V7	V8
Diene rubber gel A1 [phr]	80	0	0	56	40	24	16	0	16	25.5	0
Diene rubber gel B2 [phr]	0	80	40	24	40	56	64	0	0	59.5	0
Diene rubber gel A4 [phr]	0	0	0	0	0	0	0	0	0	0	25.5
Diene rubber gel B4 [phr]	0	0	0	0	0	0	0	0	0	0	59.5
Diene rubber gel W1 [phr]	0	0	40	0	0	0	0	0	0	0	0
Sealing gel H3 [phr]	0	0	0	0	0	0	0	80	64	0	0
Resin (C) Escorez 2173 [phr]	40	40	40	40	40	40	40	40	40	30	30
Ageing stabilizer (D) Vulkanox HS LG [phr]	1.5	1.5	1,5	1.5	1.5	1.5	1.5	1.5	1.5	1.5	3
Ageing stabilizer (D) Vulkanox	1.5	1.5	1,5	1.5	1.5	1.5	1.5	1.5	1.5	0	0

[illegible]

Table 6:

[illegible]

Ageing stabilizer (D) Vulkanox HS LG [phr]	3	3	3	3	3	3	3	3	3
Ageing stabilizer (D) Vulkanox 4020 [phr]	3	3	3	3	3	3	3	3	3
Rubber (E) Buna SE 1502H [phr]	15	0	0	0	0	0	0	0	0
Rubber (E) NR (SVR-3L ML (1+4) @100 °C = 20 MU) [phr]	0	15	0	15	0	0	0	0	15
Rubber (E) X_Butyl™ RB 301	0	0	15		0	0	0	0	0
Rubber (E) Keltan® 2660	0	0	0	0	15	0	0	0	0
Rubber (E) Levamelt® 600	0	0	0	0	0	15	0	0	0
Rubber (E) Oppanol B15N	0	0	0	0	0	0	15	15	0
Plasticizer (F) TDAE oil Vivatec 500 [phr]	40	50	40	40	40	40	40	40	45
Pigment (G) Radglo GM-25 [phr]	0	1	0	0	0	0	0	0	0
Pigment (G) Oppasin Blue [phr]	1	0	1	1	1	1	1	1	1
Pigment	1	0	1	1	1	1	1	1	1

(G) Tronox [phr]									
------------------------	--	--	--	--	--	--	--	--	--

The characterization of the sealing compounds VV1 to VV3 and V1 to V16 is compiled in Table 7 and 8 below.

Table 7:

Sealing compound	VV1	VV2	VV3	V1	V2	V3	V4	V5	V6	V7	V8
(ML1+4) @ 100 °C [MU]	21	11	10	16	15	13	13	15	13	12	12
Rolling ball tack tester [cm]	4.78	1.13	0.8	2.70	2.53	1.90	1.10	2.66	1.32	1.10	3
tan δ @ 60°C	0.21	0.21	0.3	0.19	0.18	0.20	0.18	0.19	0.19	0.28	0.23

5

Table 8:

Sealing compound	V9	V10	V11	V12	V13	V14	V15	V16
(ML1+4) @ 100 °C [MU]	9.8	14	12	14	15	910	11	13
Rolling ball tack tester [cm]	0.2	1.8	1.6	1.4	1.8	1.7	0.8	1.2
tan δ @ 60°C	0.28	0.19	0.24	0.22	0.19	0.20	0.21	0.27

The Mooney viscosity is determined by the methods described above on an Alpha Technologies MV 2000 Mooney viscometer.

10

Tackiness is determined by the methods described above on a rolling ball tack tester (RBT-100) from ChemInstruments.

The tan δ value is determined by the methods described above by means of an ARES-G2 rheometer from TA Instruments.

15

The determination of the failure temperature of the particular sealing compound by means of the SAFT test was effected in a double determination on two specimens of the particular sealing compound. The measurements were conducted by the methods described above on a ChemInstruments HT-8 shear tester in a Memmert UF 110 Plus heating cabinet. The mean values for the results are compiled in Table 9 and 10 below.

Table 9:

	VV1	VV2	VV3	V1	V2	V3	V4	V5	V6	V7
Failure temperature [°C]	117	66	51	101	108	103	95	98	76	72

Table 10:

	V8	V9	V10	V11	V12	V13	V14	V15	V16
Failure temperature [°C]	150	70	111	71	115	121	71	96	72

5 A sealing compound which is ready to use in practice has to pass both the rolling ball tack test and the SAFT test. In this case, the rolling ball tack test is considered to have been passed when the distance that the ball rolls is less than 3 cm.

The SAFT test is considered to have been passed when the failure temperature is greater than 70°C. An overall assessment of the sealing compounds VV1 to VV3 and V1 to V16 is compiled in Table 11 and 12 below.

10 Table 11:

Sealing compound	VV1	VV2	VV3	V1	V2	V3	V4	V5	V6	V7
Rolling ball tack test assessment	F	P	P	P	P	P	P	P	P	P
SAFT test assessment	P	F	F	P	P	P	P	P	P	P
Overall assessment	F	F	F	P	P	P	P	P	P	P

P means "passed" and F means "failed".

Table 12:

Sealing compound	V8	V9	V10	V11	V12	V13	V14	V15	V16
Rolling ball tack test assessment	P	P	P	P	P	P	P	P	P
SAFT test assessment	P	P	P	P	P	P	P	P	P
Overall assessment	P	P	P	P	P	P	P	P	P

P means "passed" and F means "failed".

The sealing compounds of the invention are notable in that they pass both tests.

15 The sealing compounds that are not in accordance with the invention fail at least one of the two tests.

If the sealing compound of the invention is applied to the tyre liner as a film of thickness 3 mm and the tyre is filled with air such that it has an air pressure of 2.5 bar, the sealing compound has a self-sealing effect when a nail which has been hammered in (to diameter 20 5 mm) is pulled out. The air pressure in the tyre remains constant for at least one week.

Claims:

1. Sealing gels having a Mooney viscosity (ML1+4) @ 100°C of 100 MU to 170 MU,

i) in the form of a mixture comprising diene rubber gel (A), having a Mooney viscosity (ML1+4) @ 100°C of 170 MU to 195 MU, obtainable by emulsion polymerization, preferably at 5°C to 20°C, of at least one conjugated diene in the presence of at least one crosslinker (I) and diene rubber gel (B), having a Mooney viscosity (ML1+4) @ 100°C of 75 MU to 110 MU, obtainable by emulsion polymerization, preferably at 5°C to 20°C, of at least one conjugated diene in the presence of at least one crosslinker (II) or

ii) obtainable by emulsion polymerization, preferably at 5°C to 20°C, of at least one conjugated diene in the presence of at least one crosslinker (I) and in the presence of at least one crosslinker (II),

where

crosslinkers (I) are acrylates and methacrylates of polyhydric, preferably di- to tetrahydric, C₂-C₂₀ alcohols, preferably selected from the group consisting of acrylates and methacrylates of ethylene glycol, propane-1,2-diol, butane-1,4-diol, hexanediol, polyethylene glycol having 2 to 8 and preferably 2 to 4 oxyethylene units, neopentyl glycol, bisphenol A, glycerol, trimethylolpropane, pentaerythritol, sorbitol with unsaturated polyesters of aliphatic di- and polyols and mixtures thereof, more preferably selected from the group consisting of acrylates and methacrylates of propane-1,2-diol, butane-1,4-diol, neopentyl glycol, bisphenol A, glycerol, trimethylolpropane and pentaerythritol, and crosslinker (I) is most preferably trimethylolpropane trimethacrylate (TMPTMA),

and

crosslinkers (II) are compounds having two or more vinyl, allyl or isopropenyl groups or one maleimide unit, preferably selected from the group consisting of diisopropenylbenzene, divinylbenzene (DVB), divinyl ether, divinyl sulphone, diallyl phthalate, trivinylbenzene, triallyl cyanurate, triallyl isocyanurate, 1,2-polybutadiene, N,N'-m-phenylenemaleimide, tolylene-2,4-bis(maleimide) and triallyl trimellitate and mixtures thereof, more preferably selected from the group of diisopropenylbenzene, divinylbenzene and trivinylbenzene, and crosslinker (II) is most preferably divinylbenzene.

2. Sealing gels according to Claim 1, characterized in that the at least one conjugated diene is 1,3-butadiene, 2,3-dimethyl-1,3-butadiene, isoprene or chloroprene, preferably 1,3-butadiene.
3. Sealing gels according to any of Claim 2, characterized in that further monomers are used in the emulsion polymerization of the at least one conjugated diene, wherein said further monomers are 1,3-butadiene, vinylaromatics, preferably styrene, 2-methylstyrene, 3-methylstyrene, 4-methylstyrene, α -methylstyrene, 2,4-dimethylstyrene, 2,4-diisopropylstyrene, 4-tert-butylstyrene or tert-butoxystyrene, more preferably styrene, acrylonitrile, isoprene, esters of acrylic acid and methacrylic acid, tetrafluoroethylene, vinylidene fluoride, hexafluoropropene, 2-chlorobutadiene, 2,3-dichlorobutadiene, carboxylic acids containing double bonds, preferably acrylic acid, methacrylic acid, maleic acid or itaconic acid, hydroxyl compounds containing double bonds, preferably hydroxyethyl methacrylate, hydroxyethyl acrylate or hydroxybutyl methacrylate, amine-functionalized (meth)acrylates, glycidyl methacrylate, acrolein, N-vinyl-2-pyrrolidone, N-allylurea, N-allylthiourea, secondary amino (meth)acrylates, preferably 2-tert-butylaminoethyl methacrylate and 2-tert-butylaminoethylmethacrylamide, or vinylic heteroaromatics such as 2-, 4-vinylpyridine and 1-vinylimidazole.
4. Sealing gels according to Claim 3, characterized in that the at least one conjugated diene is 1,3-butadiene and the further monomer is styrene and wherein said emulsion polymerization is performed at 5°C to 20°C.
5. Sealing gels according to any of Claims 1 to 4, characterized in that 1,3-butadiene is used as at least one conjugated diene and the diene rubber gels and the sealing gels have a proportion of cis-1,4-butadiene units of 8% by weight to 17% by weight, a proportion of trans-1,4-butadiene units of 59% by weight to 75% by weight and a proportion of 1,2-vinylbutadiene units of 17% by weight to 21% by weight, based on 1,3-butadiene incorporated.
6. Sealing gels according to any of Claims 1 to 5, characterized in that the amount of crosslinker (I) is typically 1 phm to 6 phm, preferably 1 phm to 4 phm, and more preferably 1.5 phm to 3 phm, based on the total amount of diene monomer, further monomer and crosslinker.
7. Sealing gels according to any of Claims 1 to 6, characterized in that the amount of crosslinker (II) is typically 0.2 phm to 4 phm, preferably 0.2 phm to 3 phm, and more

preferably 0.5 phm to 2.7 phm, based on the total amount of diene monomer, further monomer and crosslinker.

5 8. Sealing gels according to any of Claims 1 to 7, wherein the amount of further monomer in the diene rubber gel is typically 1 phm to 20 phm, and preferably 8 phm to 14 phm, based on the total amount of monomers and crosslinkers, and the amount of diene monomer in the diene rubber gel is typically 79.8 phm to 98.8 phm, preferably 86 phm to 91.8 phm, based on the total amount of diene monomer, further monomer and crosslinker.

10 9. Sealing gels according to any of Claims 1 to 8, wherein the ratio of the diene rubber gels (A) and (B) is (1:9) to (9:1), preferably (4:1) to (1:4), more preferably (2.5:1) to (1:2.5).

10. Sealing gels according to any of Claims 1 to 9, obtainable by mixing the diene rubber gels (A) and/or (B) with sealing gel (H).

11. Sealing compounds comprising

15 at least one sealing gel according to any of Claims 1 to 10 in an amount of 45 phr to 100 phr, preferably 60 phr to 100 phr and more preferably 70 phr to 100 phr,

resin (C) in an amount of 10 phr to 60 phr, preferably 20 phr to 50 phr and more preferably 25 phr to 45 phr, and

20 optionally a natural rubber or synthetic rubber (E), preferably copolymers based on conjugated diolefins from a group comprising 1,3-butadiene, isoprene, 2,3-dimethyl-1,3-butadiene, 1,3-pentadiene, 1,3-hexadiene, 3-butyl-1,3-octadiene, 2-phenyl-1,3-butadiene or mixtures thereof, more preferably from a group comprising natural cis-1,4-polyisoprene, synthetic cis-1,4-polyisoprene, 3,4-polyisoprene, polybutadiene, 1,3-butadiene-acrylonitrile copolymer and mixtures thereof, in an amount of 0 phr to 55 phr, preferably 0 phr to 40 phr and more preferably 0 phr to 30 phr,

based in each case on the total amount of sealing gel and optionally natural and/or synthetic rubber (E) in the sealing compound.

12. Sealing compounds according to Claim 11, comprising

30 ageing stabilizer (D), preferably in an amount of 1 phr to 10 phr and more preferably in an amount of 1 phr to 5 phr.

13. Sealing compounds according to Claim 11 or 12, comprising
plasticizer (F), preferably 10 phr to 50 phr and more preferably 15 phr to 40 phr of at
least one plasticizer (F).

14. Sealing compounds according to any of Claims 11 to 13, comprising

5 at least one filler (G) in an amount of 1 phr to 50 phr, preferably 1 phr to 30 phr and
more preferably 1 phr to 20 phr.

15. Process for producing sealing compounds according to any of Claims 11 to 14, by
mixing the components in solid or liquid form.

10 16. Process for producing sealing compounds according to any of Claims 11 to 14, by
mixing the rubber components in the form of their latices and co-processing and
mixing the further components, preferably in the form of suspensions.

17. Use of sealing gels according to any of Claims 1 to 9 in sealing compounds,
especially for improving adhesion and cohesion properties.

15 18. Use of sealing compounds according to any of Claims 11 to 13 as sealing layer in
tyres, preferably on inner liners in pneumatic motor vehicle tyres, hollow bodies or
membranes.

19. Pneumatic motor vehicle tyres having a sealing gel-containing sealing compound
comprising a sealing gel according to Claims 1 to 9.

INTERNATIONAL SEARCH REPORT

International application No
PCT/EP2016/067740

A. CLASSIFICATION OF SUBJECT MATTER INV. C08F212/36 B60C1/00 C08F216/12 C08F218/18 C08F222/10 C09J4/00 ADD. According to International Patent Classification (IPC) or to both national classification and IPC																	
B. FIELDS SEARCHED Minimum documentation searched (classification system followed by classification symbols) C08F B60C C09J Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched Electronic data base consulted during the international search (name of data base and, where practicable, search terms used) EPO-Internal, WPI Data																	
C. DOCUMENTS CONSIDERED TO BE RELEVANT <table border="1" style="width: 100%; border-collapse: collapse;"> <thead> <tr> <th style="width: 10%;">Category*</th> <th style="width: 70%;">Citation of document, with indication, where appropriate, of the relevant passages</th> <th style="width: 20%;">Relevant to claim No.</th> </tr> </thead> <tbody> <tr> <td style="text-align: center; vertical-align: top;">A</td> <td>US 2010/152370 A1 (STEINHAUSER NORBERT [DE] ET AL) 17 June 2010 (2010-06-17) the whole document paragraph [0012] - paragraph [0028] -----</td> <td style="text-align: center; vertical-align: top;">1-19</td> </tr> <tr> <td style="text-align: center; vertical-align: top;">A</td> <td>US 2015/105515 A1 (BRANDAU SVEN [FR] ET AL) 16 April 2015 (2015-04-16) the whole document -----</td> <td style="text-align: center; vertical-align: top;">1-19</td> </tr> <tr> <td style="text-align: center; vertical-align: top;">A</td> <td>US 3 565 151 A (COURTNEY JOHN A) 23 February 1971 (1971-02-23) cited in the application the whole document -----</td> <td style="text-align: center; vertical-align: top;">1-19</td> </tr> <tr> <td style="text-align: center; vertical-align: top;">A</td> <td>US 3 981 342 A (FARBER MILTON ET AL) 21 September 1976 (1976-09-21) cited in the application the whole document -----</td> <td style="text-align: center; vertical-align: top;">1-19</td> </tr> </tbody> </table>			Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.	A	US 2010/152370 A1 (STEINHAUSER NORBERT [DE] ET AL) 17 June 2010 (2010-06-17) the whole document paragraph [0012] - paragraph [0028] -----	1-19	A	US 2015/105515 A1 (BRANDAU SVEN [FR] ET AL) 16 April 2015 (2015-04-16) the whole document -----	1-19	A	US 3 565 151 A (COURTNEY JOHN A) 23 February 1971 (1971-02-23) cited in the application the whole document -----	1-19	A	US 3 981 342 A (FARBER MILTON ET AL) 21 September 1976 (1976-09-21) cited in the application the whole document -----	1-19
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.															
A	US 2010/152370 A1 (STEINHAUSER NORBERT [DE] ET AL) 17 June 2010 (2010-06-17) the whole document paragraph [0012] - paragraph [0028] -----	1-19															
A	US 2015/105515 A1 (BRANDAU SVEN [FR] ET AL) 16 April 2015 (2015-04-16) the whole document -----	1-19															
A	US 3 565 151 A (COURTNEY JOHN A) 23 February 1971 (1971-02-23) cited in the application the whole document -----	1-19															
A	US 3 981 342 A (FARBER MILTON ET AL) 21 September 1976 (1976-09-21) cited in the application the whole document -----	1-19															
☐ Further documents are listed in the continuation of Box C. ☒ See patent family annex.																	
* Special categories of cited documents : "A" document defining the general state of the art which is not considered to be of particular relevance "E" earlier application or patent but published on or after the international filing date "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) "O" document referring to an oral disclosure, use, exhibition or other means "P" document published prior to the international filing date but later than the priority date claimed "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art "&" document member of the same patent family																	
Date of the actual completion of the international search 29 September 2016		Date of mailing of the international search report 06/10/2016															
Name and mailing address of the ISA/ European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Fax: (+31-70) 340-3016		Authorized officer Droghetti, Anna															

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/EP2016/067740

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 2010152370	A1	17-06-2010	AT 545521 T 15-03-2012
		BR PI0905810 A2 29-03-2011	
		CA 2683225 A1 20-04-2010	
		CN 101724186 A 09-06-2010	
		DE 102008052116 A1 22-04-2010	
		EP 2177374 A1 21-04-2010	
		ES 2379750 T3 03-05-2012	
		JP 5739094 B2 24-06-2015	
		JP 2010095724 A 30-04-2010	
		KR 20100044110 A 29-04-2010	
		TW 201031709 A 01-09-2010	
		US 2010152370 A1 17-06-2010	
US 2015105515	A1	16-04-2015	BR 102014025502 A2 21-06-2016
		CA 2866490 A1 14-04-2015	
		CN 104558418 A 29-04-2015	
		EP 2860196 A1 15-04-2015	
		EP 2860197 A1 15-04-2015	
		JP 2015078367 A 23-04-2015	
		KR 20150043211 A 22-04-2015	
		RU 2014141104 A 27-04-2016	
		US 2015105515 A1 16-04-2015	
		US 2016108162 A1 21-04-2016	
US 3565151	A	23-02-1971	NONE
US 3981342	A	21-09-1976	US 3981342 A 21-09-1976
		US 4064922 A 27-12-1977	