

**PCT**WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : B29B 9/08, B29C 47/36, C22B 1/16, 1/245, 7/02		A1	(11) International Publication Number: WO 96/39290
			(43) International Publication Date: 12 December 1996 (12.12.96)
(21) International Application Number: PCT/US96/01798		(81) Designated States: AM, AT, AU, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, ES, FI, GB, GE, HU, JP, KE, KG, KP, KR, KZ, LK, LT, LU, LV, MD, MG, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG , SI, SK, TJ, TR, TT, UA, UZ, VN, ARIPO patent (KE, LS, MW, SD, SZ, UG), European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).	
(22) International Filing Date: 8 February 1996 (08.02.96)		Published With international search report.	
(30) Priority Data: 08/468,104 6 June 1995 (06.06.95) US 08/546,975 23 October 1995 (23.10.95) US			
(71) Applicant: COVOL TECHNOLOGIES, INC. [US/US]; 3280 North Frontage Road, Lehi, UT 84043 (US).			
(72) Inventor: FORD, George, W., Jr.; 1256 South 1700 East, Salt Lake City, UT 84108 (US).			
(74) Agent: FOSTER, Lynn, G.; 602 East 300 South, Salt Lake City, UT 84102 (US).			

REPLACED SHEETS SG

☒ Description : paged 1... to paged 17...

☒ Claim(s) : paged 18... to paged 21...

☐ Drawing(s) : paged to paged

☐ Abstract : paged to paged

(54) Title: PROCESS FOR RECOVERING IRON FROM IRON-RICH MATERIAL

(57) Abstract

Iron-rich material waste products, such as electric arc furnace dust, are formed with an organic binder into discrete shapes, such as briquettes and/or other solid shapes. The shapes can then be used in iron and steel making processes and the iron and heavy metal values in the waste product recovered.

