



PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : D21H	A2	(11) International Publication Number: WO 96/24719 (43) International Publication Date: 15 August 1996 (15.08.96)
(21) International Application Number: PCT/US96/01145 (22) International Filing Date: 22 January 1996 (22.01.96) (30) Priority Data: 08/381,250 31 January 1995 (31.01.95) US (71) Applicant: THE PROCTER & GAMBLE COMPANY [US/US]; One Procter & Gamble Plaza, Cincinnati, OH 45202 (US). (72) Inventors: TROKHAN, Paul, Dennis; 1356 Warvel Road, Hamilton, OH 45013 (US). PHAN, Dean, Van; 6512 Tylers Crossing, West Chester, OH 45069 (US). (74) Agents: REED, T., David et al.; The Procter & Gamble Company, 5299 Spring Grove Avenue, Cincinnati, OH 45217 (US).		(81) Designated States: AL, AM, AT, AU, AZ, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IS, JP, KE, KG, KP, KR, KZ, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, UZ, VN, ARIPO patent (KE, LS, MW, SD, SZ, UG), Eurasian patent (AZ, BY, KG, KZ, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>Without international search report and to be republished upon receipt of that report.</i>
(54) Title: SOFT TISSUE PAPER CONTAINING AN OIL AND A POLYHYDROXY COMPOUND (57) Abstract Tissue paper having an enhanced bulk and tactile softness through incorporation of an effective amount of a polyhydroxy compound and an oil is disclosed. Preferably, from about 0.05 % to about 2.0 % of the polyhydroxy compound, on a dry fiber weight basis, and from about 0.05 % to about 2.0 % of an oil, on a dry fiber weight basis, are incorporated in the tissue paper. These nonionic compounds have high rates of retention when applied to wet tissue paper webs according to the process described herein. Tissue embodiments of the present invention may further comprise a quantity of strength additive, such as starch, to increase paper strength.		