



ABSTRACT OF THE DISCLOSURE



LIQUID CRYSTAL POLYESTER RESIN MIXTURE

A liquid crystal polyester resin mixture having a stabilized plastication time and accordingly possible to be molded in constant cycles and giving a molded article excellent in mechanical properties and thermal stability is provided. The liquid crystal polyester resin mixture comprises 100 parts by weight of a liquid crystal polyester resin composition which comprises 100 parts by weight of a liquid crystal polyester and from 0 to 150 parts by weight of a filler, and either from 0.001 to 5 parts by weight of a fatty acid amide having a formula; $R_1 \cdot CO \cdot NH_2$ (wherein R_1 denotes a saturated or unsaturated hydrocarbon of 10 to 30 carbons) or from 0.001 to 2 parts by weight of a high molecular weight polyethylene with a molecular weight of 10,000 or higher.