PROCESS FOR THE PREPARATION OF EPOXIDATION CATALYSTS

The present invention relates to the preparation of an epoxidation catalyst and to the process of preparing alkylene oxide with the help of such catalyst.

Background of the Invention

An epoxidation catalyst is understood to be a catalyst which catalyses the manufacture of an epoxy group containing compound. A well known process comprises contacting a hydroperoxide and alkene with a heterogeneous epoxidation catalyst and withdrawing a product stream comprising alkylene oxide and an alcohol.

Catalysts for the manufacture of an epoxy group containing compound, are well known. EP-A-345856 describes the preparation of such catalyst comprising titanium in chemical combination with a solid silica and/or inorganic silicate. The preparation comprises (a) impregnating a silicium compound with a stream of gaseous titanium tetrachloride preferably comprising an inert gas, (b) calcining the obtained reaction product of step (a), and (c) hydrolysis of the product of step (b). The stream of inert gas also has the function of a carrier for the gaseous titanium tetrachloride. For such use, the gas is to be present in a relatively large amount.

There is a continuous interest in improving the selectivity of epoxidation processes in general, and more specifically of processes for the preparation of alkylene oxide. We found a simple and attractive way to achieve this.

Summary of the Invention

The present invention relates to a process for the preparation of an epoxidation catalyst, which process comprises impregnating a silicon containing carrier with a gas stream consisting of titanium halide.

A catalyst of improved selectivity was obtained even though the carrier had been in contact with the same amount of titanium halide.

Detailed description of the invention

The catalyst of the present invention is obtained by impregnating a silicon containing carrier. In principle, any silicon containing carrier is suitable for use in the preparation process according to the present invention. Examples of silicon containing carriers comprise zeolites. Preferably, the silicon containing carrier is a silica carrier.

Silica carriers will substantially consist of silicon dioxide. However, limited amounts of further compounds such as contaminants can be present as well.

It is known that contaminants can influence the performance of the final catalyst. The silica carrier for use in the present invention preferably contains at most 1200 ppm of sodium, more specifically at most 1000 ppm of sodium. Further, the silica carrier preferably comprises at most 500 ppm of aluminium, at most 500 ppm of calcium, at most 200 ppm of potassium, at most 100 ppm of magnesium and at most 100 ppm of iron. The amounts are based on amount of carrier.

The silica carrier preferably is a silica gel. The silica gel carrier for use in the present invention can in principle be any carrier derived from a silicon containing gel. In general, silica gels are a solid, amorphous form of hydrous silicon dioxide distinguished

temperature of from 450 to 800 °C, more preferably of from 500 to 700 °C.

The silica gel carrier for use in the present invention preferably has a surface area of at most 1000 m^2/gram, more preferably at most 800 m^2/gram, most preferably at most 500 m^2/gram.

Titanium halides which can be used in the process according to the present invention comprise tri- and tetra-substituted titanium complexes which have of from 1 to 4 halide substituents with the remainder of the substituents, if any, being alkoxide or amino groups. The titanium halide can be either a single titanium halide compound or can be a mixture of titanium halide compounds. Preferably, the titanium halide comprises at least 50 %wt of titanium tetrachloride, more specifically at least 70 %wt of titanium tetrachloride. Most preferably, the gas stream consists of titanium tetrachloride.

The present invention comprises impregnating the carrier with gas consisting of titanium halide. Surprisingly, it was found that catalyst having higher selectivity for the desired alkylene oxide could be obtained if the silicon containing carrier was impregnated with gas consisting of titanium halide. The preparation according to the present invention is carried out in the absence of a carrier gas. Without wishing to be bound to any theory, it is thought that the carrier gas interferes with the impregnation. However, limited amounts of further gaseous compounds are allowed to be present during the contact between the silicon containing carrier and the gaseous titanium halide. The gas in contact with the carrier during impregnation preferably consists for at least 70 %wt of titanium halide, more

specifically at least 80 %wt, more specifically at least 90 %wt, most specifically at least 95 %wt.

Gaseous titanium halide can be prepared in any way known to someone skilled in the art. A simple and easy way comprises heating a vessel containing titanium halide to such temperature that the gaseous titanium halide is obtained.

Generally, the impregnated carrier will be calcined and subsequently hydrolysed before being used as a catalyst. It is believed that calcination removes hydrogen halide, more specifically hydrogen chloride which is formed upon reaction of titanium halide and silicon compounds present on the surface of the silicon containing carrier.

The optional calcination of the impregnated carrier generally comprises subjecting the impregnated carrier to a temperature of at least 500 °C, more specifically at least 600 °C. Preferably, the calcination is carried out at a temperature of at least 650 °C. From a practical point of view, it is preferred that the calcination temperature applied is at most 1000 °C.

Hydrolysis of the impregnated and calcined carrier can remove Ti-halide bonds. The hydrolysis of the impregnated carrier will generally somewhat more severe than the optional hydrolysis of the carrier before impregnation. Accordingly, this hydrolysis of the impregnated carrier is suitably carried out with steam at a temperature in the range of from 150 to 400 °C.

Preferably, the hydrolysed impregnated carrier is subsequently silylated for instance by contacting the hydrolysed impregnated carrier with a silylating agent, preferably at a temperature of between 100 and 425 °C. Suitable silylating agents include organosilanes like

tetra-substituted silanes with C_1-C_3 hydrocarbyl substituents. A very suitable silylating agent is hexamethyldisilazane. Examples of specific suitable silylating methods and silylating agents are, for instance, described in US-A-3,829,392 and US-3,923,843 which are referred to in US-A-6,011,162, and in EP-A-734764.

The amount of titanium (as metallic titanium) will normally be in the range of from 0.1 to 10% by weight, suitably of from 1 to 5% by weight, based on total weight of the catalyst. Preferably, titanium or a titanium compound, such as a salt or an oxide, is the only metal and/or metal compound present.

As mentioned above, it is well known in the art to produce alkylene oxides, such as propylene oxide, by epoxidation of the corresponding olefin using a hydroperoxide such as hydrogen peroxide or an organic hydroperoxide as the source of oxygen. The hydroperoxide can be hydrogen peroxide or any organic hydroperoxide such as tert-butyl hydroperoxide, cumene hydroperoxide and ethylbenzene hydroperoxide. The alkene will generally be propene which gives as alkylene oxide, propylene oxide. The catalyst prepared according to the present invention has been found to give especially good results in such process. Therefore, the present invention further relates to a process for the preparation of alkylene oxide which process comprises contacting a hydroperoxide and alkene with a heterogeneous epoxidation catalyst and withdrawing a product stream comprising alkylene oxide and an alcohol and/or water, in which process the catalyst has been prepared according to the present invention.

A specific organic hydroperoxide is ethylbenzene hydroperoxide, in which case the alcohol obtained is 1-phenyl ethanol. The 1-phenylethanol usually is converted further by dehydration to obtain styrene.

Another method for producing propylene oxide is the co-production of propylene oxide and methyl tert-butyl ether (MTBE) starting from isobutane and propene. This process is well known in the art and involves similar reaction steps as the styrene/propylene oxide production process described in the previous paragraph. In the epoxidation step tert-butyl hydroperoxide is reacted with propene forming propylene oxide and tert-butanol. Tert-butanol is subsequently etherified into MTBE.

A further method comprises the manufacture of propylene oxide with the help of cumene. In this process, cumene is reacted with oxygen or air to form cumene hydroperoxide. Cumene hydroperoxide thus obtained is reacted with propene in the presence of an epoxidation catalyst to yield propylene oxide and 2-phenyl propanol. The latter can be converted into cumene with the help of a heterogeneous catalyst and hydrogen. Suitable processes are described for example in WO 02/48126.

The conditions for the epoxidation reaction according to the present invention are those conventionally applied. For propene epoxidation reactions with the help of ethylbenzene hydroperoxide, typical reaction conditions include temperatures of 50 to 140 °C, suitably 75 to 125 °C, and pressures up to 80 bar with the reaction medium being in the liquid phase.

The invention is further illustrated by the following Examples.

Examples

The silica gel carrier used in the examples had a surface area of 300 m^2/g and a weight average particle size of about 1 mm. Substantially all particles had a particle size between 0.6 and 1.4 mm.

75 grams of silica gel carrier was dried at 250 °C during 2 hours.

The dried silica gel carrier was contacted with a gas stream containing titaniumtetrachloride. The gas stream was obtained by heating titaniumtetrachloride to 200 °C with the help of an electrical heating system. Different gas streams were obtained by adding different amounts of nitrogen. At the end of each experiment, each silica carrier had been in contact with the same amount of titaniumtetrachloride.

The impregnated catalysts thus obtained were calcined at 600 °C during 7 hours. The calcined catalysts were subsequently contacted with steam at 325 °C during 6 hours. The steam flow consisted of 3 grams of water per hour and 8 Nl of nitrogen per hour. Finally, the catalysts were silylated at 185 °C during 2 hours by being contacted with 18 grams of hexamethyldisilazane per hour in a nitrogen flow of 1.4 Nl per hour.

The catalysts obtained were analysed for the amount of titanium deposited on the carrier.

The selectivity of the catalysts was tested in a continuous epoxidation bench scale unit containing a number of vessels on automatic weight balances containing respectively the ethylbenzene hydroperoxide and propene feed streams, two high pressure pumps, a fixed bed reactor, a third pump for pumping a recycle stream over the reactor, means to maintain the reactor continuously at temperatures between 60 and 120 °C, a stripper to

remove light boiling components like propene, a cooler and a vessel for receiving the product.

The feeds were supplied to the reactor via the two high pressure pumps and mixed together before entering the reactor. The reactor was operated liquid full at 40 bara pressure and 90 °C. A large recycle stream was maintained over the reactor to have isothermal operation of the reactor bed and to ensure that the catalyst to be re-activated is contacted with epoxidation reaction product. The feed was mixed with the recycle stream prior to introduction into the reactor.

The feed consisted of 40 %wt of propene, 20 %wt of ethylbenzene hydroperoxide and 40 %wt of ethylbenzene.

The results obtained are given in Table 1. The selectivity is the molar ratio of propylene oxide formed to ethylbenzene hydroperoxide converted.

Example 2

Further catalysts were prepared in a way similar to the one described in Example 1. However, the impregnated catalysts were calcined for 6 hours (instead of 7 hours) while the steam flow during the subsequent hydrolysis contained 5 grams of water per hour (instead of 3 grams of water per hour). The results of these experiments are shown in Table 2.

TABLE 1

	Example 1	Comparative Example 1	Comparative Example 2
Impregnating gas %wt titaniumtetrachloride	100	75	60
Catalyst titanium (%wt) sodium (%wt)	4.1 0.07	4.0 0.07	4.1 0.07
Selectivity to propylene oxide 100-200 hours on stream 200-300 hours on stream	90.9 91.3	89.7 90.4	90.1 91.1

TABLE 2

	Example 2	Comparative Example 3	Comparative Example 4
Impregnating gas			
%wt titaniumtetrachloride	100	26	1
Catalyst			
titanium (%wt)	3.8	4.1	4.1
sodium (%wt)	0.07	0.05	0.07
Selectivity to propylene oxide			
100-200 hours on stream	90.5	89.6	88.4
200-270 hours on stream	90.5	89.3	88.3
270-340 hours on stream	92.5	91.2	90.6
370-420 hours on stream	92.5	91.4	90.8

C L A I M S

1. Process for the preparation of an epoxidation catalyst, which process comprises impregnating a silica containing carrier with a gas stream consisting of titanium halide, and which process is carried out in the absence of a carrier gas.

2. Process according to claim 1, in which process the silica containing carrier is a silica gel.

3. Process according to any one of the preceding claims, in which process the gas stream consists of titanium tetrachloride.

4. Process according to any one of the preceding claims, in which process the silica containing carrier comprises at most 1200 ppm of sodium, based on amount of carrier.

5. Process according to any one of the preceding claims, which process comprises drying the silica containing carrier before impregnation.

6. Process according to any one of the preceding claims in which process the impregnated carrier is calcined and subsequently hydrolysed.

7. Process according to claim 6, in which process the hydrolysed impregnated carrier is subsequently contacted with a silylating agent.

8. Process for the preparation of alkylene oxide which process comprises contacting a hydroperoxide and alkene with a heterogeneous epoxidation catalyst and withdrawing a product stream comprising alkylene oxide and an alcohol and/or water, in which process the catalyst has been prepared by a process according to any one of the preceding claims.

9. Process according to claim 8, in which process the alkene is propene and the alkylene oxide is propylene oxide.

10. Process according to claim 9, in which process the organic hydroperoxide is ethylbenzene hydroperoxide and in which the alcohol is 1-phenyl ethanol.

11. Process according to claim 10, which process further comprises dehydration of 1-phenylethanol to obtain styrene.