

DESCRIPTION

Title of the Invention: THERMOPLASTIC RESIN COMPOSITION AND
USE THEREOF

5

TECHNICAL FIELD

[0001]

The present invention relates to a thermoplastic resin
composition containing a metal oxide and a use thereof.

10

BACKGROUND ART

[0002]

Thermoplastic resins such as polyolefins and ABS resins
are molded by various methods and used in many fields. On
15 the other hand, polyolefins such as polypropylene have
inferior mechanical properties such as heat resistance,
rigidity, and tensile strength compared to engineering
plastics such as polyamide and polycarbonate, and therefore
inorganic fillers such as talc, and heat-resistant fibers
20 such as glass fibers and carbon fibers are added as
reinforcements depending on the use.

[0003]

For example, Patent Literature 1 proposes a polyolefin composition containing a large amount of 20 to 80 parts by weight of inorganic filler composed of an inorganic compound.

On the other hand, the kneadability with polyolefins was found to be inferior when inorganic compounds such as metal oxides are contained in large quantities, and to improve the kneadability, for example, Patent Literature 2 proposes to add 0.1 to 20 parts by mass of a modified polyolefin-based wax to a composition containing 10 to 50 parts by mass of a thermoplastic resin and 50 to 90 parts by mass of a metal oxide.

CITATION LIST

PATENT LITERATURE

[0004]

Patent Literature 1: JP S52(1977)-15542A

Patent Literature 2: WO2017/209215

SUMMARY OF INVENTION

TECHNICAL PROBLEM

[0005]

However, it was found that with thermoplastic resin compositions obtained by adding modified polyolefin-based waxes, the hydroxyl group density on the surface of the

resulting molded article tends to be relatively high, which increases hydrophilicity and gives it a moist texture, and that under certain conditions (such as acid solutions), inorganic compounds may elute, causing a loss of texture.

5 [0006]

An object of the present invention is to obtain a thermoplastic resin composition that is suitable for obtaining a molded article that does not produce increased hydrophilic properties (has a low water absorption rate), and
10 that has a hard feel and a texture closer to that of earthenware.

SOLUTION TO PROBLEM

[0007]

15 The present invention relates to, for example, the following items [1] to [20].

In the present specification, the term "polymer" includes both homopolymer and copolymer unless otherwise specified.

20 [1] A thermoplastic resin composition containing 10 to 50 parts by mass of a thermoplastic resin (A), 50 to 90 parts by mass of a metal oxide (B), provided that a total amount of (A)+(B) is 100 parts by mass, and an unmodified polyolefin-

based wax (C) in a range of 0.1 to 20 parts by mass per 100 parts by mass of the total amount of (A)+(B).

[0008]

[2] The thermoplastic resin composition according to [1],

5 wherein the thermoplastic resin (A) is one or more selected from the group consisting of ethylene-based polymers, propylene-based polymers, 1-butene-based polymers, 4-methyl-1-pentene-based polymers, and ABS resins.

[3] The thermoplastic resin composition according to [1] or

10 [2], wherein the metal oxide (B) includes magnesium oxide.

[4] The thermoplastic resin composition according to any of

[1] to [3], wherein an average particle size of the metal oxide (B) is in a range of 0.1 to 110 μm .

[0009]

15 [5] The thermoplastic resin composition according to any of [1] to [4], wherein a thermal conductivity of the metal oxide (B) is in a range of 10 to 300 W/mK.

[6] The thermoplastic resin composition according to any of

[1] to [5], wherein a thermal conductivity of the

20 thermoplastic resin composition is in a range of 0.5 to 5 W/mK.

[7] The thermoplastic resin composition according to any of

[1] to [6], wherein a specific gravity of the thermoplastic resin composition is in a range of 1.0 to 5.0.

[0010]

[8] The thermoplastic resin composition according to any of [1] to [7], containing 10 to 30 parts by mass of the thermoplastic resin (A) and 70 to 90 parts by mass of the metal oxide (B), provided that the total amount of (A)+(B) is 100 parts by mass.

[9] The thermoplastic resin composition according to any of [1] to [8], wherein an antibacterial activity value after 24 hours is 2.0 or more in an antibacterial test performed using Escherichia coli in accordance with JIS Z 2801:2012 (film adhesion method) under conditions where no water or light resistance pretreatment is performed.

[0011]

[10] The thermoplastic resin composition according to any of [1] to [9], wherein an antibacterial activity value after 24 hours is 2.0 or more in an antibacterial test performed using Staphylococcus aureus in accordance with JIS Z 2801:2012 (film adhesion method) under conditions where no water or light resistance pretreatment is performed.

[11] The thermoplastic resin composition according to any of [1] to [10], wherein an antiviral activity value is 2.0 or more in an antiviral test performed using Feline calicivirus conducted in accordance with ISO 21702:2019.

[12] The thermoplastic resin composition according to any of [1] to [11], containing a fibrous filler (D) in a range of 0.1 to 20 parts by mass per 100 parts by mass in total of the thermoplastic resin (A) and the metal oxide (B).

5 [0012]

[13] A molded article containing the thermoplastic resin composition according to any of [1] to [12].

[14] A door handle, door knob, handrail or switch containing the thermoplastic resin composition according to any of [1]
10 to [12].

[15] A case containing the thermoplastic resin composition according to any of [1] to [12].

[16] A fashion accessory containing the thermoplastic resin composition according to any of [1] to [12].

15 [0013]

[17] A container containing the thermoplastic resin composition according to any of [1] to [12].

[18] Stationery containing the thermoplastic resin composition according to any of [1] to [12].

20 [19] Tableware or alcoholic drink ware containing the thermoplastic resin composition according to any of [1] to [12].

[20] A mouse or keyboard containing the thermoplastic resin composition according to any of [1] to [12].

ADVANTAGEOUS EFFECTS OF INVENTION

[0014]

The thermoplastic resin composition of the present
5 invention has an extremely low water absorption rate and a
thermal conductivity equivalent to that of earthenware, and
is therefore suitable for obtaining a molded article that has
a cool feel, as well as a hard feel and a texture closer to
that of earthenware. On the other hand, since the present
10 product has antibacterial properties due to the effect of the
metal oxide contained therein, it is suitable for obtaining a
molded article for uses where the texture can be felt by
direct touch.

15 DESCRIPTION OF EMBODIMENTS

[0015]

Hereinafter, the present invention will be specifically
described.

<Thermoplastic resin (A)>

20 For example, olefin-based polymers, ABS resins, styrene-
based resins, and polyesters can be used as the thermoplastic
resin (A), which is one of the components in the
thermoplastic resin composition of the present invention.

[0016]

Olefin-based polymers are homopolymers of α -olefins (including ethylene) such as ethylene, propylene, 1-butene, and 4-methyl-1-pentene, copolymers of the α -olefins and other α -olefins, and copolymers of the α -olefins and monomers other
5 than α -olefins, where α -olefin is the main component.

Specific examples of the thermoplastic resin (A) according to the present invention includes the following polymers.

[0017]

10 <Ethylene-based polymer (A1)>

The ethylene-based polymer (A1) according to the present invention is a homopolymer of ethylene, or a copolymer of ethylene and an α -olefin having 3 to 20 carbon atoms, and usually includes polymers containing structural units derived
15 from ethylene as the main component, which are referred to as high density polyethylene (HDPE), medium density polyethylene (MDPE), low density polyethylene (LDPE), linear low density polyethylene (LLDPE), and ethylene- α -olefin copolymer.

Specific examples of the α -olefins having 3 to 20 carbon
20 atoms to be copolymerized with ethylene include propylene, 1-butene, 1-pentene, 1-hexene, 4-methyl-1-pentene, 1-octene, 1-decene, 1-dodecene, 1-tetradecene, 1-hexadecene, 1-octadecene, 1-eicosene, 2-methyl-1-butene, 3-methyl-1-butene, 3,3-dimethyl-1-butene, and 3,5,5-trimethyl-1-hexene. Of these,

α -olefins having 3 to 10 carbon atoms are preferred, α -olefins having 3 to 8 carbon atoms are more preferred, and particularly, ethylene, 1-butene, 1-hexene, 4-methyl-1-pentene, and 1-octene are even more preferred. The molar
5 ratio of ethylene to α -olefin (ethylene/ α -olefin) is preferably 99/1 to 60/40, more preferably 95/5 to 70/30, and even more preferably 90/10 to 60/25.

[0018]

Suitable specific examples of ethylene- α -olefin
10 copolymers include ethylene-propylene copolymer, ethylene-1-butene copolymer, ethylene-1-hexene copolymer, ethylene-4-methyl-1-pentene copolymer, ethylene-1-octene copolymer, ethylene-propylene-1-butene copolymer, and ethylene-propylene-1-octene copolymer. Of these, ethylene-propylene
15 copolymer, ethylene-1-butene copolymer, ethylene-1-hexene copolymer, ethylene-4-methyl-1-pentene copolymer, and ethylene-1-octene copolymer are preferred, and ethylene-1-butene copolymer is more preferred.

The density (measured according to JIS K7112) of the
20 ethylene-based polymer (A1) is preferably 850 to 980 kg/m³, more preferably 855 to 978 kg/m³, even more preferably 860 to 976 kg/m³, and particularly preferably 862 to 973 kg/m³.

[0019]

When the thermoplastic resin composition of the present invention contains the ethylene-based polymer (A1), the molded article obtained from the thermoplastic resin composition tends to have a higher thermal conductivity than
5 when it contains the propylene-based polymer (A2) described below, have excellent warm-cold sensation, and produce a high sound when tapped. Such molded article can be suitably used for various applications without any limitation, but can be suitably used, for example, as a base material to modify
10 metal-evaporated surfaces.

[0020]

<Propylene-based polymer (A2)>

The propylene-based polymer (A2) according to the present invention is a polymer containing structural units
15 derived from propylene as the main component, such as a homopolymer of propylene (propylene homopolymer: homo PP), a copolymer of propylene and ethylene and/or an α -olefin having 4 to 20 carbon atoms (random copolymer: random PP), and a composition of a homopolymer of propylene and an ethylene-
20 propylene copolymer (block copolymer: block PP). Specific examples of the α -olefin in the propylene- α -olefin copolymer include ethylene, 1-butene, 1-pentene, 1-hexene, 4-methyl-1-pentene, 1-octene, 1-decene, 1-dodecene, 1-tetradecene, 1-hexadecene, 1-octadecene, 1-eicosene, 2-methyl-1-butene, 3-

methyl-1-butene, 3,3-dimethyl-1-butene, 3-methyl-1-hexene, and 3,5,5-trimethyl-1-hexene. Of these, ethylene and α -olefins having 4 to 10 carbon atoms are preferred, ethylene and α -olefins having 4 to 8 carbon atoms are more preferred, and particularly, ethylene, 1-butene, 1-hexene, 4-methyl-1-pentene, and 1-octene are even more preferred. The molar ratio of propylene to α -olefin (propylene/ α -olefin) is preferably 99/1 to 60/40, more preferably 95/5 to 70/30, and even more preferably 90/10 to 70/30.

10 [0021]

Suitable specific examples of propylene- α -olefin copolymers (random PP) include propylene-ethylene copolymer, propylene-1-butene copolymer, propylene-1-hexene copolymer, propylene-4-methyl-1-pentene copolymer, propylene-1-octene copolymer, and propylene-ethylene-1-butene copolymer. Of these, propylene-ethylene copolymer and propylene-1-butene copolymer are preferred, and propylene-ethylene copolymer is particularly preferred.

[0022]

20 In the case of a propylene homopolymer, the preferred melting point is 155 to 170°C, more preferably 158 to 165°C.

In the case of a propylene-ethylene random copolymer, the ethylene content of the propylene-ethylene random copolymer is preferably 1.9 to 5.4% by mass, more preferably

2.0 to 4.8% by mass. The crystalline melting point of the propylene-ethylene random copolymer, as measured by a differential scanning calorimeter (DSC) in accordance with JIS K7121, is preferably usually 130 to 150°C, more
5 preferably 130 to 145°C, and particularly preferably 135 to 145°C.

[0023]

The density (measured according to JIS K7112) of the propylene-based polymer (A2) is preferably 850 to 910 kg/m³,
10 more preferably 875 to 909 kg/m³, and more preferably 890 to 908 kg/m³.

As the propylene-based polymer (A2) according to the present invention, a propylene-based polymer containing a fibrous filler (D) such as glass fibers as described below
15 can be used, and in this case, the density (measured according to JIS K7112) of the propylene-based polymer containing the fibrous filler (D) is preferably 910 to 1220 kg/m³, more preferably 940 to 1200 kg/m³, even more preferably 970 to 1160 kg/m³, and particularly preferably 1000 to 1120
20 kg/m³.

[0024]

The propylene-ethylene block copolymer and the propylene-ethylene random copolymer may be used singly, or

two or more copolymers in mixture may be used. For example,
two or more copolymers can be mixed for MFR adjustment.

When the thermoplastic resin composition of the present
invention contains the propylene-based polymer (A2), the
5 molded article obtained from the thermoplastic resin
composition can be suitably used for various applications
without any limitation. While it has a thermal conductivity
close to that of earthenware and a specific gravity
equivalent to that of earthenware, it does not break like
10 earthenware upon impact such as from falling, making it
highly safe, and therefore can be suitably used for
applications that are touched by hand, for example, tableware
such as cups, containers, and door handles.

[0025]

15 <1-Butene-based polymer (A3)>

The 1-butene-based polymer (A3) according to the present
invention is a polymer containing structural units derived
from 1-butene as the main component, such as a homopolymer of
1-butene (polybutene) and copolymers of 1-butene with
20 ethylene, propylene, and α -olefins having 5 to 20 carbon
atoms (1-butene- α -olefin copolymers).

[0026]

<4-Methyl-1-pentene-based polymer (A4)>

The 4-methyl-1-pentene-based polymer (A4) according to the present invention is a polymer containing structural units derived from 4-methyl-1-pentene as the main component, such as a homopolymer of 4-methyl-1-pentene and copolymers of
5 4-methyl-1-pentene and α -olefins having 2 to 20 carbon atoms (excluding 4-methyl-1-pentene) (4-methyl-1-pentene- α -olefin copolymers).

[0027]

Specific examples of the α -olefin in the 4-methyl-1-
10 pentene- α -olefin copolymer include linear α -olefins having 2 to 20 carbon atoms (preferably 2 to 15 carbon atoms, more preferably 2 to 10 carbon atoms) such as ethylene, propylene, 1-butene, 1-pentene, 1-hexene, 1-octene, 1-decene, 1-undecene, 1-dodecene, 1-tetradecene, 1-hexadecene, 1-octadecene, and 1-
15 eicosene; and branched α -olefins having 5 to 20 carbon atoms (preferably 5 to 15 carbon atoms) such as 3-methyl-1-butene, 3-methyl-1-pentene, 3-ethyl-1-pentene, 4,4-dimethyl-1-pentene, 4-methyl-1-hexene, 4,4-dimethyl-1-hexene, 4-ethyl-1-hexene, and 3-ethyl-1-hexene. Of these, ethylene, propylene, 1-
20 butene, 1-pentene, 1-hexene and 1-octene are preferred, and ethylene and propylene are particularly preferred. The α -olefin may be derived from one of these compounds or from two or more.

The molar ratio of 4-methyl-1-pentene to α -olefin (4-methyl-1-pentene/ α -olefin) is preferably 55/45 to 90/10, more preferably 60/40 to 86/14 and even more preferably 68/32 to 85/15.

5 [0028]

In one embodiment, the 4-methyl-1-pentene-based polymer (A4) has a temperature at which the loss tangent ($\tan \delta$), obtained by dynamic viscoelastic measurement at a frequency of 10 rad/s (1.6 Hz), reaches its peak value within a
10 temperature range of -40 to 150°C , is 0°C or more and 60°C or less, preferably 10°C or more and 50°C or less, more preferably 20°C or more and 45°C or less, and particularly preferably 25°C or more and 44°C or less.

In the 4-methyl-1-pentene-based polymer (A4), the peak
15 value of the above $\tan \delta$ is 0.6 or more and 5.0 or less. This peak value of $\tan \delta$ is preferably 0.7 or more and 4.5 or less, and more preferably 0.8 or more and 3.5 or less.

[0029]

Tan δ can be calculated as the ratio of the storage
20 modulus (G') to the loss modulus (G'') (G''/G' : loss tangent) using the storage modulus (G') and loss modulus (G'') obtained when measuring dynamic viscoelasticity.

[0030]

In the present invention, the temperature at which $\tan \delta$ reaches its peak value (maximum value) in the range of -40 to 150°C is defined as the temperature at which the above $\tan \delta$ reaches its peak value (hereinafter referred to as " $\tan \delta$ peak temperature"), and the value of $\tan \delta$ at that time is defined as the peak value of the above $\tan \delta$ (hereinafter referred to as " $\tan \delta$ peak value"). The above peak is thought to be derived from the glass transition temperature of the 4-methyl-1-pentene-based polymer (A4).

10 [0031]

In other aspects, the 4-methyl-1-pentene-based polymer (A4) has a $\tan \delta$ peak temperature, obtained by dynamic viscoelastic measurement at a frequency of 10 rad/s (1.6 Hz) within a temperature range of -40 to 150°C , of preferably 15°C or more and 45°C or less. In terms of the lower limit of the $\tan \delta$ peak temperature, the $\tan \delta$ peak temperature is more preferably 20°C or more, and even more preferably 25°C or more. In an exemplary aspect of the present invention, the $\tan \delta$ peak temperature is 40°C or less, but it may exceed 40°C as long as the object of the present invention can be achieved. In a typical aspect of the invention, the $\tan \delta$ peak temperature is preferably 20°C or more and 45°C or less, and even more preferably 25°C or more and 43°C or less. By having a $\tan \delta$ peak temperature within the above temperature

range, the value of $\tan \delta$ at room temperature can be further increased.

[0032]

The 4-methyl-1-pentene-based polymer (A4) preferably has
5 a $\tan \delta$ peak value, obtained by dynamic viscoelastic
measurement at a frequency of 10 rad/s (1.6 Hz) within a
temperature range of -40 to 150°C, of 0.6 or more and 5.0 or
less, more preferably 1.0 or more and 4.8 or less, even more
preferably 1.3 or more and 4.5 or less, and particularly
10 preferably 1.8 or more and 4.0 or less. By having a $\tan \delta$
peak value within the above range, the vibration absorption,
material hardness and followability can be varied depending
on the rate of tension and deformation.

[0033]

15 The 4-methyl-1-pentene-based polymer (A4) has a melting
point (T_m), as measured by a differential scanning
calorimeter (DSC), of preferably 160°C or less or not
observed, more preferably 140°C or less or not observed, and
even more preferably not observed. Meeting such requirements
20 allows to improve the kneadability with inorganic materials
in the resin composition of the present invention and to
improve vibration absorption and stress relaxation properties.

[0034]

The intrinsic viscosity $[\eta]$ of the 4-methyl-1-pentene-based polymer (A4) measured in decalin at 135°C is preferably 0.1 dL/g or more and 5.0 dL/g or less, more preferably 0.5 dL/g or more and 4.0 dL/g or less, and even more preferably 0.5 dL/g or more and 3.5 dL/g or less. The 4-methyl-1-pentene-based polymer (A4) with the above intrinsic viscosity $[\eta]$ within the above range allows to easily produce a molded article.

[0035]

The above intrinsic viscosity $[\eta]$ of the 4-methyl-1-pentene-based polymer (A4) can be adjusted to the above range by adding hydrogen during production by polymerization to control the molecular weight and polymerization activity.

[0036]

The above intrinsic viscosity $[\eta]$ can be obtained by determining the viscosity increase rate η_{sp} per unit concentration c (i.e., η_{sp}/c) of each polymer, when different amounts of the thermoplastic resin composition are dissolved in decalin at 135°C, to obtain the reduced viscosity η_{red} , and then extrapolating η_{red} so that the unit concentration c of the polymer is zero.

[0037]

The ratio of the weight-average molecular weight (M_w) measured by gel permeation chromatography (GPC) to the

number-average molecular weight (Mn) of the 4-methyl-1-pentene-based polymer (A4) (molecular weight distribution: Mw/Mn) is preferably 1.0 or more and 3.5 or less, more preferably 1.2 or more and 3.0 or less, and even more preferably 1.5 or more and 2.8 or less. The 4-methyl-1-pentene-based polymer (A4) with the above Mw/Mn in the above range is less susceptible to a loss of moldability caused by a low-molecular-weight and low-stereoregularity polymer, and is easy to mold.

10 [0038]

In addition, the weight-average molecular weight (Mw) measured by gel permeation chromatography (GPC) of the 4-methyl-1-pentene-based polymer (A4) is preferably 500 or more and 10,000,000 or less, more preferably 1,000 or more and 5,000,000 or less, and even more preferably 1,000 or more and 2,500,000 or less, in terms of polystyrene.

[0039]

The Mw/Mn and Mw of the 4-methyl-1-pentene-based polymer (A4) can be adjusted to the above ranges, for example, by using a metallocene catalyst.

The above Mw and Mw/Mn can be determined, for example, by analyzing the chromatograms obtained by measuring at a flow rate of 1.0 ml/min at 140°C using ALC/GPC 150-C plus type (integrated differential refractor detector) made by

Waters as a liquid chromatograph, two GMH6-HTs and two GMH6-HTs made by Tosoh Corporation connected in series as columns, and o-dichlorobenzene as a mobile phase medium, using a calibration curve using a standard polystyrene sample.

5 [0040]

The density (measured according to JIS K7112) of the 4-methyl-1-pentene-based polymer (A4) is preferably 870 to 830 kg/m³, more preferably 865 to 830 kg/m³, and even more preferably 855 to 830 kg/m³. Details such as measurement
10 conditions are as described in the section of Examples described later.

The density can be appropriately varied according to the comonomer composition ratio of the 4-methyl-1-pentene-based polymer (A4), and a polymer (A4) whose density is within the
15 above range is advantageous in producing a molded article.

[0041]

When the thermoplastic resin composition of the present invention contains the 4-methyl-1-pentene-based polymer (A4), the molded article obtained from the thermoplastic resin
20 composition can be suitably used for various applications without any limitation. Such a molded article has superior flexibility compared to when the propylene-based polymer (A2) is contained, and has properties such as easily bending when

touched and retaining its shape at room temperature by imparting it heat conducting characteristics.

[0042]

<ABS Resin (A5)>

5 The ABS resin (A5) according to the present invention is
a resin that includes not only acrylonitrile-butadiene-
styrene copolymer, but also graft copolymers obtained by
graft polymerization of a monomer containing aromatic vinyl
or vinyl cyanide with a rubber component made from a monomer
10 including butadiene, and copolymers produced from other
monomers that can be copolymerized with aromatic vinyl or
vinyl cyanide. Here, the rubber component is produced, for
example, by a conventionally known solution polymerization
method, bulk polymerization method, or emulsion
15 polymerization method. The above graft polymers with this
rubber or copolymers with this rubber that are produced by
any of the conventionally known methods such as solution
polymerization, bulk polymerization, and emulsion
polymerization can be used, and are readily available in the
20 market.

[0043]

Specific examples of the ABS resin (A5) include
commercial products such as KRALASTIC manufactured by NIPPON
A&L INC., TECHNO ABS and UMG ABS manufactured by Techno-UMG

Co., Ltd., TOYOLAC manufactured by Toray Industries, Inc. and
Denka ABS manufactured by Denka Company Limited.

[0044]

The density (measured in accordance with ISO 1183) of
5 the ABS resin (A5) is preferably 1000 to 1070 kg/m³, more
preferably 1001 to 1060 kg/m³, and more preferably 1002 to
1050 kg/m³.

The ABS resin (A5) may be used singly, or two or more
copolymers in mixture may be used. For example, two or more
10 copolymers can be mixed for MFR adjustment.

[0045]

When the thermoplastic resin composition of the present
invention contains the ABS resin (A5), the molded article
obtained from the thermoplastic resin composition can be
15 suitably used for various applications without any limitation.
In addition, it has superior impact resistance and tends to
have a higher surface hardness compared to when the
propylene-based polymer (A2) is contained, and therefore can
be suitably used for applications such as trays, kitchen
20 countertop surfaces, desks, bathroom counters where objects
are expected to be rubbing against, and door handles that
require strength.

[0046]

<Other thermoplastic resin (A6)>

Examples of the thermoplastic resin (A6) other than (A1) to (A5) described above include styrene-based resins such as polystyrene, polyesters such as PET, polyamide, and acrylic-based resins. These other thermoplastic resins (A6) can be
5 produced by known methods, or commercially available products thereof may be used. The other thermoplastic resins (A6) may be used singly or in combinations of two or more thereof.

[0047]

Of these thermoplastic resins (A), the olefin-based
10 polymers (A1) to (A4) and ABS resin (A5) are preferred, and the ethylene-based polymer (A1), propylene-based polymer (A2), 4-methyl-1-pentene-based polymer (A4) and ABS resin (A5) are more preferred. Two or more of the thermoplastic resins (A) may be used in combination.

15 [0048]

The MFR (ASTM D1238, 230°C, 2.16 kg load) of the thermoplastic resin (A) is preferably 7 to 300 g/10 min. In terms of the lower limit of the MFR, it is preferably 11 g/10 min or more, more preferably 13 g/10 min or more, even more
20 preferably 15 g/10 min or more, and particularly preferably 18 g/10 min or more. Moreover, in terms of the upper limit of the MFR, it is preferably 200 g/10 min or less, more preferably 150 g/10 min or less, and even more preferably 100 g/10 min or less.

A thermoplastic resin (A) with an MFR in the above range has good moldability such as injection moldability, and the resulting molded article has also good mechanical properties.
[0049]

5 When the thermoplastic resin (A) is the 4-methyl-1-pentene-based polymer (A4), the upper limit of the MFR (ASTM D1238, 230°C, 2.16 kg load) is preferably 50 g/10 min or less, more preferably 30 g/10 min or less, even more preferably 15 g/10 min or less, and particularly preferably 13 g/10 min or
10 less.
[0050]

When the thermoplastic resin (A) is the ethylene-based polymer (A1), the MFR (ASTM D1238, 190°C, 2.16 kg load) is preferably 6 to 100 g/10 min. In terms of the lower limit of
15 the MFR, it is preferably 8 g/10 min or more, more preferably 10 g/10 min or more, and even more preferably 11 g/10 min or more. Moreover, in terms of the upper limit of the MFR, it is preferably 80 g/10 min or less, more preferably 60 g/10 min or less, and even more preferably 50 g/10 min or less.
20 [0051]

When the thermoplastic resin (A) is the ABS resin (A5), the MVR (ASTM D1133, 220°C, 10 kg load) is preferably 10 to 100 cm³/10 min. In terms of the lower limit of the MVR, it is preferably 18 cm³/10 min or more, more preferably 30 cm³/10

min or more, and even more preferably 40 cm³/10 min or more. Moreover, in terms of the upper limit of the MVR, it is preferably 95 cm³/10 min or less, more preferably 90 cm³/10 min or less, and even more preferably 85 cm³/10 min or less.

5 [0052]

<Metal oxide (B)>

The type of metal oxide (B), which is one of the components in the thermoplastic resin composition of the present invention, is not particularly limited as long as it is an oxide of a metal, but it should be a metal oxide having a higher thermal conductivity than the thermoplastic resin (A). For example, metal oxides such as magnesium oxide (45 to 60 W/mK), aluminum oxide (17 to 36.0 W/mK), zinc oxide (25 to 54 W/mK), and titanium oxide (8.4 W/mK) can be used. Two or more of metal oxides may be used in combination. The values in parentheses after the substance name indicate the value of the thermal conductivity at 300 K.

[0053]

The metal oxide (B) according to the present invention is preferably a metal oxide having a thermal conductivity in the range of 10 to 300 W/mK. The lower limit of the thermal conductivity is more preferably 15 W/mK, even more preferably 20 W/mK, particularly preferably 30 W/mK, and most preferably 40 W/mK.

[0054]

Moreover, the upper limit of the thermal conductivity is more preferably 250 W/mK, even more preferably 200 W/mK, and particularly preferably 100 W/mK.

5 Using a metal oxide (B) having a thermal conductivity in the above range allows the thermoplastic resin composition obtained by mixing the metal oxide (B) with the above thermoplastic resin (A) to have an appropriate thermal conductivity, and therefore to obtain a molded article such
10 as a container that feels cool to the touch and warm when something hot is placed in it.

[0055]

Unlike the case where titanium dioxide is used as a photocatalyst, the metal oxide (B) is preferably magnesium
15 oxide or zinc oxide for applications where light irradiation is unnecessary and antibacterial and/or antiviral properties are required, and furthermore, more preferably magnesium oxide as it is white, easy to color, and low cost.

[0056]

20 The shape of the metal oxide (B) according to the present invention can be, for example, spherical, cubic, plate-like, columnar, or hexagonal-plate-like, of which spherical is preferred. The metal oxide (B) can also be pulverized.

[0057]

The metal oxide (B) according to the present invention preferably has an average particle size in the range of 0.1 to 110 μm . The lower limit of the average particle size is
5 more preferably 0.2 μm , even more preferably 0.5 μm , and particularly preferably 1 μm .

[0058]

Moreover, the upper limit of the average particle size is more preferably 105 μm , even more preferably 90 μm , and
10 particularly preferably 85 μm .

If the average particle size is too small, it is more likely to aggregate, which may reduce handling properties and make it difficult to uniformly mix with the thermoplastic resin (A). On the other hand, if the average particle size
15 is too large, the thermal conductivity of the resulting thermoplastic resin composition may become too low, and the mechanical properties of the resulting molded article may also decrease.

[0059]

20 In applications where higher thermal conductivity is required, it is preferable to use, for example, a combination of a metal oxide (b1) and a metal oxide (b2) with different average particle sizes of 0.1 μm or more and less than 10 μm and 10 μm or more and 110 μm or less, respectively. In this

case, the formulation ratio (mass ratio) is, for example, preferably $(b1)/(b2) = 1/99$ to $49/51$, more preferably $5/95$ to $45/55$, and more preferably $10/90$ to $40/60$.

[0060]

5 By using a combination of a metal oxide (b1) with a small average particle size and a metal oxide (b2) with a large average particle size, the metal oxide (b1) fills the gaps between the metal oxides (b2), increasing the packing density and thus improving the thermal conductivity of the
10 resulting thermoplastic resin composition.

[0061]

 The aspect ratio of the metal oxide (B) is preferably small from the viewpoint of uniformity of heat conduction, for example. Specifically, the aspect ratio is preferably
15 less than 1.2, more preferably less than 1.1.

[0062]

 The metal oxide (B) according to the present invention has preferably been subjected to a waterproof treatment. The metal oxide (B) is preferably substantially free of metal
20 hydroxides, hydrates thereof and hydrates of metal oxides. Specifically, the content of metal hydroxides, hydrates thereof, and hydrates of metal oxides in 100% by mass of the total metal oxide (B) is preferably 1% by mass or less, more

preferably 0.5% by mass or less, and particularly preferably 0.3% by mass or less.

[0063]

<Unmodified Polyolefin-Based Wax (C)>

5 The unmodified polyolefin-based wax (C), which is one of the components in the thermoplastic resin composition of the present invention, is a low molecular weight polymer and is not particularly limited as long as it is an unmodified wax composed of a polyolefin such as polyethylene wax and
10 polypropylene wax, and is preferably a polyethylene-based wax or a polypropylene-based wax, and is more preferably a polyethylene-based wax.

[0064]

 The unmodified polyolefin-based wax (C) according to the
15 present invention has not been oxidized or modified with, for example, unsaturated carboxylic acids, and is unmodified.

 The unmodified polyolefin-based wax (C) according to the present invention preferably has an acid value of 0.01 mg KOH/g or less, and more preferably 0 mg KOH/g, as measured in
20 accordance with JIS K0070.

[0065]

<Polyethylene-based wax>

 The polyethylene-based wax used as the unmodified polyolefin-based wax (C) according to the present invention

is a wax composed of, for example, a homopolymer of ethylene or a copolymer of ethylene and an α -olefin. As the α -olefin, α -olefins having 3 to 10 carbon atoms are preferred, α -olefins having 3 to 8 carbon atoms are more preferred, and 1-butene is even more preferred.

[0066]

The polyethylene-based wax according to the present invention preferably has a density in the range of 890 to 980 kg/m³, more preferably in the range of 895 to 975 kg/m³, as measured in accordance with the density-gradient tube method of JIS K7112 (1999). When the density of the polyethylene-based wax is in such a range, the dispersibility of the polyethylene-based wax in the thermoplastic resin composition is improved.

15 [0067]

The polyethylene-based wax according to the present invention preferably has a standard polyethylene-equivalent number-average molecular weight as measured by gel permeation chromatography of 700 to 4000, and more preferably 1500 to 3800.

[0068]

A polyethylene-based wax with a number-average molecular weight (M_n) of 700 to 4000 can be appropriately dispersed by the thermoplastic resin (A) when molding the thermoplastic

resin composition of the present invention, and also
contribute to the dispersibility of the metal oxide (B). It
can also reduce the extrusion load during molding extrusion.
As a result, the productivity of the molded article can be
5 further improved.

[0069]

The polyethylene-based wax according to the present
invention preferably has a standard polyethylene-equivalent
weight-average molecular weight (Mw) as measured by gel
10 permeation chromatography of 1000 to 9000, more preferably
1500 to 8000, and even more preferably 2000 to 7000.

[0070]

The polyethylene-based wax according to the present
invention preferably has a melting point of 70 to 130°C, and
15 more preferably 80 to 129°C.

The melting point of the polyethylene-based wax was
measured by differential scanning calorimeter (DSC) in
accordance with JIS K7121.

[0071]

20 <Polypropylene-based wax>

The polypropylene-based wax used as the unmodified
polyolefin-based wax (C) according to the present invention
is a wax composed of, for example, a homopolymer of propylene
or a copolymer of propylene and ethylene or an α -olefin. As

the α -olefin, α -olefins having 4 to 10 carbon atoms are preferred, α -olefins having 4 to 8 carbon atoms are more preferred, and 1-butene is even more preferred.

[0072]

5 <Thermoplastic resin composition>

The thermoplastic resin composition of the present invention is a composition containing 10 to 50 parts by mass of the above thermoplastic resin (A), 50 to 90 parts by mass of the above metal oxide (B) [provided that the total amount
10 of (A)+(B) is 100 parts by mass], and the above unmodified polyolefin-based wax (C) in a range of 0.1 to 20 parts by mass per 100 parts by mass of the total amount of (A)+(B).

[0073]

The lower limit of the content of the thermoplastic
15 resin (A) in the thermoplastic resin composition of the present invention is preferably 12 parts by mass, more preferably 16 parts by mass, and even more preferably 20 parts by mass. When the content of the thermoplastic resin (A) in the thermoplastic resin composition is a certain
20 amount or more, existing molding methods such as injection molding can be performed.

[0074]

The upper limit of the content of the thermoplastic resin (A) is preferably 45 parts by mass, more preferably 40 parts by mass, and even more preferably 36 parts by mass.

When the content of the thermoplastic resin (A) in the thermoplastic resin composition of the present invention is a certain amount or less, the heat conduction of the resulting thermoplastic resin composition is sufficiently exhibited and the resulting molded article has a feeling of weight and texture.

10 [0075]

On the other hand, the lower limit of the content of the metal oxide (B) is preferably 55 parts by mass, more preferably 60 parts by mass, and even more preferably 68 parts by mass.

15 Moreover, the upper limit of the content of the metal oxide (B) is preferably 88 parts by mass, more preferably 84 parts by mass, and even more preferably 80 parts by mass.

[0076]

In applications where antibacterial and/or antiviral properties are required, the lower limit of the content of metal oxide (B) is preferably 70 parts by mass, more preferably 72 parts by mass, and even more preferably 74 parts by mass. Naturally, the upper limit of the content of the thermoplastic resin (A) is preferably 30 parts by mass,

20

more preferably 28 parts by mass, and even more preferably 26 parts by mass.

[0077]

Having the amounts of the thermoplastic resin (A) and
5 the metal oxide (B) within the above range allows to obtain a molded article with good moldability and having antibacterial and/or antiviral properties.

The thermoplastic resin composition of the present invention contains 0.1 to 20 parts by mass of the unmodified
10 polyolefin-based wax (C) when the total of the thermoplastic resin (A) and the metal oxide (B) is 100 parts by mass. The lower limit of the content of the unmodified polyolefin-based wax (C) is preferably 0.2 parts by mass, more preferably 0.4 parts by mass, and even more preferably 0.5 parts by mass.

15 [0078]

Moreover, the upper limit of the content of the unmodified polyolefin-based wax (C) is preferably 15 parts by mass, more preferably 10 parts by mass, and even more preferably 5 parts by mass.

20 When the thermoplastic resin composition of the present invention contains the unmodified polyolefin-based wax (C) in the above range, it is possible to improve kneadability by decreasing the mold torque during molding when obtaining the thermoplastic resin composition and when using the

thermoplastic resin composition to perform the molding process. In addition, having a lower melt temperature than the thermoplastic resin (A) allows it to act as a lubricant and to prevent screw and cylinder wear.

5 [0079]

On the other hand, since the thermoplastic resin composition of the present invention does not contain a modified polyolefin-based wax, there is no risk of generating strange odors during the molding process.

10 Furthermore, the molded article obtained from the thermoplastic resin composition of the present invention containing the unmodified polyolefin-based wax (C) has a harder feel and a texture closer to that of earthenware than a molded article obtained from a composition containing a
15 modified polyolefin-based wax, and since there is no change in hydrophilicity, there is no risk of elution of the metal oxide or of causing a loss of texture.

[0080]

The specific gravity of the thermoplastic resin
20 composition of the present invention is preferably in the range of 1.0 to 5.0. The lower limit of the specific gravity of the thermoplastic resin composition of the present invention is more preferably 1.2, even more preferably 1.4, and particularly preferably 1.6. Moreover, the upper limit

of the specific gravity is more preferably 4.0, even more preferably 3.0, and particularly preferably 2.5.

[0081]

When the above range of specific gravity is satisfied, a
5 molded article with a better texture can be obtained.

The thermal conductivity of the thermoplastic resin composition of the present invention is preferably in the range of 0.5 to 5 W/mK. The lower limit of the thermal conductivity of the thermoplastic resin composition of the
10 present invention is more preferably 0.6 W/mK, even more preferably 0.65 W/mK, and particularly preferably 0.7 W/mK. Moreover, the upper limit of the thermal conductivity is more preferably 4.5 W/mK, even more preferably 4.0 W/mK, and particularly preferably 3.6 W/mK.

15 [0082]

When the above range of thermal conductivity is satisfied, a molded article such as a container that feels cool to the touch and has a better texture can be obtained.

The thermoplastic resin composition of the present
20 invention preferably has an antibacterial activity value of 2.0 or more using *Escherichia coli* or *Staphylococcus aureus*, and more preferably an antibacterial activity value of 2.0 or more using *Escherichia coli* and *Staphylococcus aureus*. The antibacterial activity value of the thermoplastic resin

composition of the present invention can be increased, for example, by increasing the content of the metal oxide (B) (e.g., magnesium oxide). When the antibacterial activity value is 2.0 or more, it is considered to have an

5 antibacterial effect. A higher antibacterial activity value is preferred as it indicates a higher antibacterial effect, and the upper limit thereof is not particularly limited.

[0083]

The antibacterial activity value in the present
10 invention is an index value in accordance with the test method in JIS Z 2801: 2012 "film adhesion method".

[0084]

The thermoplastic resin composition of the present invention preferably has an antiviral activity value of 2.0
15 or more using Feline calicivirus. When the antiviral activity value is 2.0 or more, it is considered to have an antiviral effect. A higher antiviral activity value is preferred as it indicates a higher antiviral effect, and the upper limit thereof is not particularly limited.

20 The antiviral activity value in the present invention is an index value in accordance with the test method in ISO 21702:2019 "Measurement of antiviral activity on plastics and other non-porous surfaces".

[0085]

The thermoplastic resin composition of the present invention may contain a fibrous filler (D) in addition to the unmodified polyolefin-based wax (C).

[0086]

5 <Fibrous filler (D)>

The fibrous filler (D) according to the present invention is a fibrous filler, and specific examples thereof include glass fibers, carbon fibers, magnesium sulfate fibers, polyester fibers, nylon fibers, kenaf fibers, bamboo fibers, jute fibers, and inorganic crystal whisker fibers. Of these, glass fibers and carbon fibers are suitable.

[0087]

When the thermoplastic resin composition of the present invention contains the fibrous filler (D), it improves mechanical properties such as strength of the resulting molded article.

If the thermoplastic resin composition of the present invention contains the fibrous filler (D), it is contained in a range of 0.1 to 20 parts by mass per 100 parts by mass of the total amount of the thermoplastic resin (A) and the metal oxide (B). The lower limit of the content of the fibrous filler (D) is preferably 0.2 parts by mass, and more preferably 0.3 parts by mass. Moreover, the upper limit of the content of the fibrous filler (D) is preferably 15 parts

by mass, more preferably 10 parts by mass, and even more preferably 8 parts by mass.

[0088]

The thermoplastic resin composition of the present invention may contain fillers other than the fibrous filler (D) as long as the effects of the present invention are not impaired. Examples of such fillers include inorganic fillers such as talc, mica, calcium carbonate, ammonium phosphate salts, silicates, carbonates, and carbon black; and organic fillers such as wood flour, cellulose, rice flour, starch, and cornstarch.

[0089]

In addition to the above fibrous filler (D), the thermoplastic resin composition of the present invention may contain various known additives, such as plasticizers, lubricants, antioxidants, ultraviolet absorbers, heat stabilizers, pigments, pigment masterbatches, dyes, antistatic agents, flame retardants, coupling agents, and dispersing agents depending on the application as long as the object of the present invention is not impaired.

[0090]

<Method for producing thermoplastic resin composition>

The thermoplastic resin composition of the present invention is obtained by mixing each of the above components

by, for example, dry blending, a Henschel mixer, a Banbury mixer, or a kneader, or by melt-kneading them after mixing in a single-screw extruder, a twin-screw extruder, or a high-speed twin-screw extruder.

5 [0091]

<Molded article>

The thermoplastic resin composition of the present invention has excellent moldability and can therefore be used in various molding methods. Specific examples of the molded
10 article obtained from the thermoplastic resin composition of the present invention include an injection molded article, a foam molded article, an injection foam molded article, an extruded article, a hollow molded article, a vacuum/pressure formed article, a calender molded article, a stretched film,
15 and an inflation film.

[0092]

More specific examples include containers, for example, for food, tableware such as forks, knives, spoons, plates, teapots, and teacups, alcoholic drink ware such as tokkuri or
20 choshi, and cutlery rests such as chopstick rests. These are very useful as tableware, alcoholic drink ware, containers, and cutlery as an alternative to ceramics in that they can be easily molded by injection molding, they allow to feel the warm/cold sensation of the contents, and appear heavy. It is

also possible to expand to other applications using ceramics, for example, everyday items such as lampshades and vases, cases and structural materials for specific acoustic speakers (such as high-end speakers), plumbing products such as sinks and toilet bowls, and vases and pots for plants. In addition to applications using ceramics, its characteristics of imparting a heavy feeling and stability can be used to expand to applications such as models and toys typified by plastic models, furniture such as desks and chairs, home appliances such as refrigerators, rice cookers and vacuum cleaners, musical instruments such as piano keyboards, constructions such as tiles, artificial marble alternatives, and building materials, and fashion such as buttons. It may also be suitable as a filament for 3D printers by utilizing its warm/cold sensation and moldability.

[0093]

In addition, the molded article of the present invention can be used in places that are touched by hands on a daily basis, and examples thereof include various containers such as bottles and jars, steering and shift knobs for vehicles and ships, door handles and door knobs, various switches, handrails, mice, keyboards, controllers, decorative accessories, stationery, smartphone covers, tablet covers, computer/tablet cases, and book covers, using its

characteristics such as designability, stability,
antibacterial properties, and feel.

[0094]

Suitable examples of containers include containers for
5 beauty-related products such as cosmetics (such as lotions
and creams), shampoo (including body shampoo), and rinse,
where these performances tend to have a high impact on the
commercial value. More specific examples include lidded
containers (including airless containers), containers in the
10 form of compacts (for cosmetics), palettes (for cosmetics),
and bottles.

[0095]

In recent years, containers made of plastic such as
polyolefin, which are lightweight and have excellent impact
15 resistance, have been used in most of these applications, but
it is an unsuitable material for producing a premium look and
feel (including thermal conductivity and heavy feeling).
Containers such as ceramics are suitable for producing a
premium appearance, but they have major problems such as
20 limited flexibility in terms of design and mass production,
as well as low impact resistance.

[0096]

Since the same molding methods as conventional plastic
products can be applied to the container of the present

invention, it can be considered suitable for the above applications not only because of its superior productivity and design, but also because it has superior impact resistance compared to ceramics and has the same weight
5 feeling and thermal conductivity as ceramics.

[0097]

Furthermore, the molded article obtained from the thermoplastic resin composition of the present invention is also useful as a heat-dissipating member in applications
10 requiring high thermal conductivity. For example, it is very useful as a heat-dissipating member such as a heat-dissipating sheet in electronic components requiring high thermal conductivity and in various electronic devices such as notebook computers and mobile devices. In addition, if
15 the thermoplastic resin composition of the present invention is applied to part or all of the cases of various electronic devices such as notebook computers and mobile devices, and used in combination with a heat-dissipating sheets, the heat dissipation performance of electronic devices can be expected
20 to be further enhanced. Furthermore, it is possible to produce a case that can reduce the possibility of suffering, for example, from low temperature burn during prolonged manipulation by using the thermoplastic resin composition of the present invention for a part of the case of various

electronic devices such as notebook computers and mobile devices, and using a material with a reduced metal oxide content or a material free of metal oxide for the other parts, for example, the parts that are often in contact with the hands during manipulation. Such a case can be produced, for example, by a method of installing a plurality of resin injection gates in a mold for molding the case and injecting resin of different composition into each gate.

[0098]

As another application, it is also useful as an alternative material for metal cases by making use of, for example, its excellent thermal conductivity, freedom of shape during molding, and high impact strength. For example, it can be expected to be expanded to watch and wristwatch cases and belts, furniture parts (e.g., metal handles), and exterior materials for home appliances such as washing machines and refrigerators.

EXAMPLES

[0099]

Hereinafter, the present invention will be more specifically described by way of Examples, but the present invention is not limited to the following Examples as long as the gist of the present invention is not exceeded. Each

material used in the Examples is as follows. The evaluation method for each property is described below.

[0100]

The thermoplastic resins (A) used in the Examples and
5 Comparative Examples are shown below.

(1) Thermoplastic resin (A)

(1-1) Propylene-based polymer (A2-1): Propylene-ethylene
block copolymer (manufactured by Prime Polymer Co., Ltd.,
trade name X860, MFR (230°C, 2.16 kg load) = 60 g/10 min,
10 density = 900 kg/m³, 25°C xylene-soluble fraction = 24% by
mass, intrinsic viscosity of 25°C xylene-soluble fraction [η]
= 2.5 dl/g, ethylene content of 25°C xylene-soluble fraction
= 30% by mass).

(1-2) Propylene-based polymer (A2-2): Propylene-ethylene
15 block copolymer (manufactured by Prime Polymer Co., Ltd.,
trade name J-6083HP, MFR (230°C, 2.16 kg load) = 60 g/10 min,
density = 900 kg/m³).

(1-3) Propylene-based polymer (A2-3): Short glass fiber
reinforced propylene (manufactured by Prime Polymer Co., Ltd.,
20 Prime Polypro (registered trademark) V7100, glass fiber
content = 20 wt%, MFR (230°C, 2.16 kg load) = 18 g/10 min,
density = 1030 kg/m³).

(1-4) Ethylene-based polymer (A1-1): High-density
polyethylene (manufactured by Prime Polymer Co., Ltd., HI-ZEX

(registered trademark) trade name 1300J, MFR (190°C, 2.16 kg load) = 13 g/10 min, density = 967 kg/m³).

(1-5) Ethylene-based polymer (A1-2): High-density polyethylene (manufactured by Prime Polymer Co., Ltd., HI-ZEX

5 (registered trademark) trade name 1700J, MFR (190°C, 2.16 kg load) = 16 g/10 min, MFR (230°C, 2.16 kg load) = 28 g/10 min, density = 967 kg/m³).

(1-6) Ethylene-based polymer (A1-3): Ethylene-1-butene copolymer (manufactured by Mitsui Chemicals, Inc., TAFMER

10 (registered trademark) trade name A-35070S, MFR (190°C, 2.16 kg load) = 35 g/10 min, MFR (230°C, 2.16 kg load) = 65 g/10 min, density = 870 kg/m³).

(1-7) Propylene-based polymer (A2-4): Propylene homopolymer (manufactured by Prime Polymer Co., Ltd., trade name J13B,

15 MFR (230°C, 2.16 kg load) = 200 g/10 min, density = 890 kg/m³).

(1-8) 4-Methyl-1-pentene-based polymer (A4-1): 4-Methyl-1-pentene-propylene copolymer was produced by the method described below.

20 (1-9) ABS resin (A5-1): ABS resin (manufactured by NIPPON A&L INC., trade name GA-704, MVR (220°C, 10 kg load) = 62 cm³/10 min, MFR (230°C, 5 kg load) = 39.8 g/10 min, MFR (230°C, 2.16 kg load) = 13 g/10 min, density: 1040 kg/m³)

[0101]

[Method for producing 4-methyl-1-pentene-based polymer (A4-1)]

Into a fully nitrogen-substituted SUS autoclave with stirring blades having a capacity of 1.5 L, 300 ml of n-hexane (dried over activated alumina in dry nitrogen gas atmosphere) and 450 ml of 4 methyl-1-pentene were charged at 23°C. The autoclave was charged with 0.75 ml of a 1.0 mmol/ml toluene solution of triisobutylaluminum (TIBAL) and the stirrer was turned.

10 [0102]

The autoclave was then heated to an internal temperature of 60°C and pressurized with propylene to a total pressure (gauge pressure) of 0.40 MPa.

Subsequently, 0.34 ml of a toluene solution containing 1 mmol of methylaluminoxane converted in terms of Al and 0.01 mmol of diphenylmethylen (1-ethyl-3-t-butyl-cyclopentadienyl) (2,7-di-t-butyl-fluorenyl) zirconium dichloride, which had been prepared in advance, was injected into an autoclave under pressure with nitrogen to initiate a polymerization reaction. The temperature was adjusted so that the internal temperature of the autoclave was 60°C during the polymerization reaction.

[0103]

After 60 minutes from the initiation of the polymerization, 5 ml of methanol was injected into the autoclave under pressure with nitrogen to terminate the polymerization reaction, and then the autoclave was

5 depressurized to atmospheric pressure. After depressurization, acetone was added to the reaction solution while stirring the reaction solution to obtain a polymerization reaction product containing a solvent.

[0104]

10 The resulting polymerization reaction product containing a solvent was then dried under reduced pressure at 100°C for 12 hours to obtain 36.9 g of powdered 4-methyl-1-pentene-based polymer (A4-1).

[0105]

15 The content of 4-methyl-1-pentene in the 4-methyl-1-pentene-based polymer (A4-1) was 72.5 mol%, and the propylene content was 27.5 mol%. The physical properties of the 4-methyl-1-pentene-based polymer (A4-1) are as follows.

The density was 839 kg/m³, the intrinsic viscosity [η] was 1.5 dl/g, the weight-average molecular weight (M_w) was 337,000, the molecular weight distribution (M_w/M_n) was 2.1, the melt flow rate (MFR; 230°C, 2.16 kg load) was 11 g/10 min, and the melting point (T_m) was not observed. The peak temperature of tan δ was 30°C and the peak value was 2.78.

[0106]

The MFR and density of each of the above thermoplastic resins (A) were measured by the following methods.

[Melt flow rate (MFR) (g/10 min)]

5 The melt flow rate was measured in accordance with ASTM D1238 at a temperature of 190°C and a load of 2.16 kg, at a temperature of 230°C and a load of 2.16 kg, or at a temperature of 230°C and a load of 5 kg.

[Density]

10 The density was measured in accordance with JIS K 7112.

[0107]

[Composition of 4-methyl-1-pentene-based polymer (A4-1)]

The content (mol%) of each structural unit (4-methyl-1-pentene and α -olefins) in the 4-methyl-1-pentene-based
15 polymer (A4-1) was measured by ^{13}C -NMR.

- Measuring equipment: Nuclear magnetic resonance apparatus (Model ECP500, manufactured by JEOL Ltd.)

- Observed nucleus: ^{13}C (125 MHz)

- Sequence: Single-pulse proton decoupling

20 - Pulse width: 4.7 μsec (45° pulse)

- Repetition time: 5.5 sec

- Number of scans: 10,000 or more

- Solvent: mixed solvent of o-

dichlorobenzene/hexadeuterobenzene (Volume ratio: 80/20)

- Sample concentration: 55 mg/0.6 mL
- Measurement temperature: 120°C
- Chemical shift reference value: 27.50 ppm

[0108]

5 [Intrinsic viscosity $[\eta]$ of 4-methyl-1-pentene-based
polymer (A4-1)]

The intrinsic viscosity $[\eta]$ was measured at 135°C in a decalin solvent using an Ubbelohde viscometer as the measuring apparatus.

10 After dissolving about 20 mg of a specific 4-methyl-1-pentene-based copolymer in 25 ml of decalin, the specific viscosity η_{sp} is measured in an oil bath at 135°C using an Ubbelohde viscometer. 5 ml of decalin was added to this decalin solution for dilution, and then the specific
15 viscosity η_{sp} was measured in the same manner as described above. This dilution operation was repeated twice more, and the value of η_{sp}/C when the concentration (C) was extrapolated to 0 was determined as the intrinsic viscosity $[\eta]$ (unit: dl/g) (see Equation 1 below).

20 $[\eta] = \lim(\eta_{sp}/C) \quad (C \rightarrow 0) \quad \text{Equation 1}$

[0109]

[Weight-average molecular weight (Mw) and molecular weight distribution (Mw/Mn) of the 4-methyl-1-pentene-based polymer (A4-1)]

The weight-average molecular weight (M_w), and the molecular weight distribution (M_w/M_n) expressed as the ratio of the weight-average molecular weight (M_w) to the number-average molecular weight (M_n) were calculated by a standard polystyrene conversion method using gel permeation chromatography (GPC).

- Conditions -

Measuring equipment: GPC (ALC/GPC 150-C plus type, integrated differential refractometer detector, manufactured by Waters)

Column: Two GMH6-HT (manufactured by Tosoh Corporation) and two GMH6-HTL (manufactured by Tosoh Corporation) connected in series

Eluent: o-dichlorobenzene

Column temperature: 140°C

Flow rate: 1.0 mL/min

[0110]

[Melting point (T_m) of 4-methyl-1-pentene-based polymer (A4-1)]

The melting point (T_m) was measured using a differential scanning calorimeter (DSC220C model, manufactured by Seiko Instruments Inc) as the measurement apparatus. About 5 mg of the polymer was sealed into an aluminum pan for measurement and heated from room temperature to 200°C at 10°C/min. The

polymer was held at 200°C for 5 min for complete melting and then cooled to -50°C at 10°C/min. After 5 minutes at -50°C, it was heated for the second time to 200°C at 10°C/min, and the peak temperature (°C) at this second heating was regarded
5 as the melting point (T_m) of the polymer. When a plurality of peaks were detected, the peak detected on the highest temperature side was taken.

[0111]

[Dynamic viscoelasticity of 4-methyl-1-pentene-based
10 polymer (A4-1)]

In the measurement of dynamic viscoelasticity, a 3 mm thick press sheet composed of the resin to be measured was used as the measurement sample, and a 45 mm x 10 mm x 3 mm strip required for the dynamic viscoelasticity measurement
15 was further cut out. Using MCR 301 manufactured by ANTON Paar, the temperature dependence of the dynamic viscoelasticity was measured at a frequency of 10 rad/s (1.6 Hz) at -40 to 150°C and the temperature at which the loss tangent ($\tan \delta$) due to the glass transition temperature
20 reached its peak value (maximum value) (hereinafter also referred to as "peak value temperature") and the value of the loss tangent ($\tan \delta$) at that time were measured in the range of 0 to 40°C.

[0112]

The metal oxides (B) used in the Examples and Comparative Examples are shown below.

(2) Metal oxide (B)

(2-1) Magnesium oxide (B-1): MgO (manufactured by Kyowa Chemical Industry, PYROKISUMA 5301, average particle size = 2 μm).

(2-2) Magnesium oxide (B-2): MgO (manufactured by Kyowa Chemical Industry, PYROKISUMA 3320, average particle size = 20 μm).

10 (2-3) Magnesium oxide (B-3): Magnesium oxide treated as shown below was used.

MgO (DENMAG KMAO-H manufactured by Tateho Chemical Industries Co., Ltd. (average particle size = 45 to 355 μm)) was sieved through a 180-250 mesh sieve to obtain the
15 magnesium oxide (B-3) with an average particle size = about 60 to 80 μm .

[0113]

The unmodified polyolefin-based wax (C) used in the Examples and Comparative Examples is shown below.

20 (3) Unmodified Polyolefin-Based Wax (C)

(3-1) Unmodified polyolefin-based wax (C-1): Ethylene-1-butene copolymer (manufactured by Mitsui Chemicals, Inc., trade name EXCEREX 30050B, density = 907 kg/m^3 , acid value =

0 mgKOH/g, melting point = 91°C, weight-average molecular weight = 5100, molecular weight distribution $M_w/M_n = 2.6$).

[0114]

(4) Modified Polyolefin-Based Wax

- 5 (4-1) Modified polyolefin-based wax: Modified polyolefin polymer (manufactured by Mitsui Chemicals, Inc., trade name EXCEREX 15341PA, density = 930 kg/m³, acid value = 14 mgKOH/g, melting point = 89°C).

[0115]

- 10 Properties of the thermoplastic resin compositions prepared in Examples and Comparative Examples were measured by the following methods.

[Specific gravity]

- The specific gravity was measured by relative comparison
15 with the density of water at 4°C by the substitution in water method.

[Melt flow rate (MFR) (g/10 min)]

- The melt flow rate was measured in accordance with ASTM D1238 at a temperature of 230°C and a load of 2.16 kg, or at
20 a temperature of 230°C and a load of 5 kg.

[0116]

[Pencil hardness]

The pencil hardness was measured at a test load of 750 g.

[Thermal conductivity (W/m·K)]

The thermal conductivity was measured by the steady method heat flow meter method. Specifically, it was measured at a temperature of 30°C in accordance with ASTM E1530 using a GH-1 measuring instrument manufactured by ULVAC-RIKO, Inc.

5 [0117]

[Measurement of deflection temperature under load (°C)]

The deflection temperature under load was measured in accordance with the method A of ISO 75-2 using test specimens (2 mm x 10 mm x 80 mm) at a temperature increase rate of
10 120°C/hour, a test starting temperature: 35°C, and a bending stress of 1.8 MPaG. For the HDT measurement, a fully automated HDT tester Model 6A-2 (manufactured by Toyo Seiki Seisaku-sho, Ltd.) was used.

[0118]

15 [Water absorption rate (wt%)]

The water absorption rate was measured at 23°C for 24 hours.

[0119]

[Antibacterial activity value (-)]

20 The test was performed in accordance with the test method in JIS Z 2801: 2012 "film adhesion method" and the antibacterial activity value was calculated by the following formula.

"Antibacterial activity value" = "common logarithm of number of viable bacteria in blank sample 24 hours after inoculation with *Escherichia coli* or *Staphylococcus aureus*" - "common logarithm of number of viable bacteria in test specimen 24 hours after inoculation with *Escherichia coli* or *Staphylococcus aureus*".

The test strains used in the test are shown below.

Antibacterial activity value (*Escherichia coli*):

Escherichia coli NBRC 3972

10 Antibacterial activity value (*Staphylococcus aureus*):

Staphylococcus aureus NBRC 12732

[0120]

[Antiviral activity value (-)]

The antiviral activity values of the thermoplastic resin compositions were determined in accordance with the test method in ISO 21702:2019.

Specifically, a 50 mm square sample was placed in a sterile petri dish and 0.4 mL of viral solution was inoculated onto the sample. The sample was then covered by a coated film. After covering the petri dish, the sample was inoculated with the virus for 24 hours at a temperature of 25°C and humidity of 90% or more. The viruses were collected from the sample, the viral infectivity titer was measured by

the plaque method, and the antiviral activity value was calculated by the following formula.

"Antiviral activity value" = "common logarithm of viral infectivity titer of blank sample 24 hours after inoculation with virus [Ut]" - "common logarithm of viral infectivity titer of test specimen 24 hours after inoculation with virus [At]"

The virus used in the test is shown below.

Feline calicivirus: ATCC VR-782

10 [0121]

(1) Antibacterial properties (water resistance category 0 and light resistance category 0: where no light or water resistance pretreatment is performed)

For water resistance category 0 and light resistance category 0, a test by the above "film adhesion method" was performed on samples that had not undergone any water or light resistance pretreatment as described in the "Society of International sustaining growth for Antimicrobial Articles, Test Methods, Sustainability Test Methods (2020 Edition) (1) Water Resistance Test" and "Society of International sustaining growth for Antimicrobial Articles, Test Methods, Sustainability Test Methods (2020 Edition) (2) Light resistance test" to calculate the antibacterial activity values.

In the pretreatment, samples are treated under the test conditions (water temperature, immersion time, or light source exposure time) specified for each category, assuming that products with antibacterial or antiviral properties will have a degradation of their performance by contact with water, for example, or exposure to light.

[0122]

(2) Antibacterial sustainability (water resistance category 1 and water resistance category 2)

For water resistance category 1 and water resistance category 2, a test by the above "film adhesion method" was performed using samples pretreated in accordance with the "Society of Industrial Technology for Antibacterial Articles, Test Methods, Sustainability Test Methods (2020 Edition) (1) Water Resistance Test" to calculate the antibacterial activity values.

[0123]

(3) Antibacterial sustainability (light resistance category 1 and light resistance category 2)

For light resistance category 1 and light resistance category 2, a test by the above "film adhesion method" was performed using samples pretreated in accordance with the "Society of Industrial Technology for Antibacterial Articles, Test Methods, Sustainability Test Methods (2020 Edition) (2)

Light Resistance Test" to calculate the antibacterial activity values.

[0124]

[Example 1]

5 30 parts by mass of the propylene-based polymer (A2-1),
70 parts by mass of the magnesium oxide (B-1), and 0.6 parts
by mass of the unmodified polyolefin-based wax (C-1) were
kneaded using a kneader (tabletop kneader (manufactured by
IRIE SHOKAI Co., Ltd.)) at 200°C and 15 to 35 rpm to obtain a
10 thermoplastic resin composition. The resulting pellets of
thermoplastic resin composition were made into press sheets
at 200°C using a manual hydraulic heat press machine
(manufactured by Imoto Machinery Co., LTD) to obtain samples
for testing physical properties. The resulting sheets, for
15 example, were used to measure the physical properties by the
methods described above.

The results are shown in Table 1.

[0125]

[Example 2]

20 The samples for testing physical properties were
produced in the same manner as in Example 1, except that 23
parts by mass of the propylene-based polymer (A2-2), 2.0
parts by mass of the ethylene-based polymer (A1-3), 75 parts
by mass of the magnesium oxide (B-2), and 0.6 parts by mass

of the unmodified polyolefin-based wax (C-1) were used instead of the raw materials used as the raw materials for the thermoplastic resin composition in Example 1, and the physical properties were measured by the methods described
5 above. In addition, the antibacterial sustainability test in water resistance category 0 and light resistance category 0 were performed by the method described above.

The results are shown in Table 1.

[0126]

10 In addition, the antibacterial and antiviral sustainability tests in water resistance category 1, water resistance category 2, light resistance category 1, and light resistance category 2 were performed by the method described above.

15 The results of the antibacterial sustainability test in water resistance categories 1 and 2 and light resistance categories 1 and 2 are shown in Table 2, and the results of the antiviral sustainability tests in water resistance categories 1 and 2 and light resistance categories 1 and 2
20 are shown in Table 3.

[0127]

[Example 3]

The samples for testing physical properties were produced in the same manner as in Example 1, except that 23

parts by mass of the propylene-based polymer (A2-2), 2.0
parts by mass of the ethylene-based polymer (A1-3), 15 parts
by mass of the magnesium oxide (B-1), 60 parts by mass of the
magnesium oxide (B-2), and 0.6 parts by mass of the
5 unmodified polyolefin-based wax (C-1) were used instead of
the raw materials used as the raw materials for the
thermoplastic resin composition in Example 1, and the
physical properties were measured by the methods described
above.

10 The results are shown in Table 1.

[0128]

[Example 4]

The samples for testing physical properties were
produced in the same manner as in Example 1, except that 23
15 parts by mass of the propylene-based polymer (A2-2), 2.0
parts by mass of the ethylene-based polymer (A1-3), 22.5
parts by mass of the magnesium oxide (B-1), 52.5 parts by
mass of the magnesium oxide (B-2), and 0.6 parts by mass of
the unmodified polyolefin-based wax (C-1) were used instead
20 of the raw materials used as the raw materials for the
thermoplastic resin composition in Example 1, and the
physical properties were measured by the methods described
above.

The results are shown in Table 1.

[0129]

[Example 5]

The samples for testing physical properties were produced in the same manner as in Example 1, except that 24.5 parts by mass of the propylene-based polymer (A2-2), 0.5 parts by mass of the ethylene-based polymer (A1-3), 75 parts by mass of the magnesium oxide (B-2), and 0.6 parts by mass of the unmodified polyolefin-based wax (C-1) were used instead of the raw materials used as the raw materials for the thermoplastic resin composition in Example 1, and the physical properties were measured by the methods described above.

The results are shown in Table 1.

[0130]

[Example 6]

The samples for testing physical properties were produced in the same manner as in Example 1, except that 29.5 parts by mass of the propylene-based polymer (A2-2), 0.5 parts by mass of the ethylene-based polymer (A1-3), 70 parts by mass of the magnesium oxide (B-2), and 0.6 parts by mass of the unmodified polyolefin-based wax (C-1) were used instead of the raw materials used as the raw materials for the thermoplastic resin composition in Example 1, and the

physical properties were measured by the methods described above.

The results are shown in Table 1.

[0131]

5 [Example 7]

The samples for testing physical properties were produced in the same manner as in Example 1, except that 34.5 parts by mass of the propylene-based polymer (A2-2), 0.5 parts by mass of the ethylene-based polymer (A1-3), 65 parts
10 by mass of the magnesium oxide (B-2), and 0.6 parts by mass of the unmodified polyolefin-based wax (C-1) were used instead of the raw materials used as the raw materials for the thermoplastic resin composition in Example 1, and the physical properties were measured by the methods described
15 above. In addition, the antibacterial sustainability test in water resistance category 0 and light resistance category 0 were performed by the method described above.

The results are shown in Table 1.

[0132]

20 [Example 8]

The samples for testing physical properties were produced in the same manner as in Example 1, except that 23 parts by mass of the propylene-based polymer (A2-3), 2.0 parts by mass of the ethylene-based polymer (A1-3), 75 parts

by mass of the magnesium oxide (B-2), and 0.6 parts by mass of the unmodified polyolefin-based wax (C-1) were used instead of the raw materials used as the raw materials for the thermoplastic resin composition in Example 1, and the physical properties were measured by the methods described above.

The results are shown in Table 1.

[0133]

The propylene-based polymer (A2-3) is blended with 20% by mass glass fiber as described above. The formulation ratio when the total amount of propylene-based polymer (A2-3) excluding the glass fiber (PP portion) and magnesium oxide (B-2) is calculated as 100 parts by mass is as follows. 19.3 parts by mass of the PP portion of the propylene-based polymer (A2-3), 2.1 parts by mass of the ethylene-based polymer (A1-3), 78.6 parts by mass of the magnesium oxide (B-2), 0.6 parts by mass of the unmodified polyolefin-based wax (C-1), and 4.8 parts by mass of the glass fiber portion of the propylene-based polymer (A2-3).

[0134]

[Example 9]

The samples for testing physical properties were produced in the same manner as in Example 1, except that 11.5 parts by mass of the propylene-based polymer (A2-2), 11.5

parts by mass of the propylene-based polymer (A2-3), 2.0 parts by mass of the ethylene-based polymer (A1-3), 75 parts by mass of the magnesium oxide (B-2), and 0.6 parts by mass of the unmodified polyolefin-based wax (C-1) were used instead of the raw materials used as the raw materials for the thermoplastic resin composition in Example 1, and the physical properties were measured by the methods described above.

The results are shown in Table 1.

10 [0135]

The propylene-based polymer (A2-3) is blended with 20% by mass glass fiber as described above. The formulation ratio when the total amount of propylene-based polymer (A2-3) excluding the glass fiber (PP portion), propylene-based polymer (A2-2), and magnesium oxide (B-2) is calculated as 100 parts by mass is as follows. 11.8 parts by mass of the propylene-based polymer (A2-2), 9.4 parts by mass of the PP portion of the propylene-based polymer (A2-3), 2.0 parts by mass of the ethylene-based polymer (A1-3), 76.8 parts by mass of the magnesium oxide (B-2), 0.6 parts by mass of the unmodified polyolefin-based wax (C-1), and 2.4 parts by mass of the glass fiber portion of the propylene-based polymer (A2-3).

20 [0136]

[Example 10]

The samples for testing physical properties were produced in the same manner as in Example 1, except that 15.3 parts by mass of the propylene-based polymer (A2-2), 7.7 parts by mass of the propylene-based polymer (A2-3), 2.0 parts by mass of the ethylene-based polymer (A1-3), 75 parts by mass of the magnesium oxide (B-2), and 0.6 parts by mass of the unmodified polyolefin-based wax (C-1) were used instead of the raw materials used as the raw materials for the thermoplastic resin composition in Example 1, and the physical properties were measured by the methods described above.

The results are shown in Table 1.

[0137]

The propylene-based polymer (A2-3) is blended with 20% by mass glass fiber as described above. The formulation ratio when the total amount of propylene-based polymer (A2-3) excluding the glass fiber (PP portion), propylene-based polymer (A2-2), and magnesium oxide (B-2) is calculated as 100 parts by mass is as follows. 15.5 parts by mass of the propylene-based polymer (A2-2), 6.3 parts by mass of the PP portion of the propylene-based polymer (A2-3), 2.0 parts by mass of the ethylene-based polymer (A1-3), 76.2 parts by mass of the magnesium oxide (B-2), 0.6 parts by mass of the

unmodified polyolefin-based wax (C-1), and 1.6 parts by mass of the glass fiber portion of the propylene-based polymer (A2-3).

[0138]

5 [Example 11]

The samples for testing physical properties were produced in the same manner as in Example 1, except that 25 parts by mass of the ethylene-based polymer (A1-1), 22.5 parts by mass of the magnesium oxide (B-1), 52.5 parts by mass of the magnesium oxide (B-2), and 0.6 parts by mass of the unmodified polyolefin-based wax (C-1) were used instead of the raw materials used as the raw materials for the thermoplastic resin composition in Example 1, and the physical properties were measured by the methods described above.

The results are shown in Table 1.

[0139]

[Example 12]

The samples for testing physical properties were produced in the same manner as in Example 1, except that 25 parts by mass of the ethylene-based polymer (A1-1), 75 parts by mass of the magnesium oxide (B-2), and 0.6 parts by mass of the unmodified polyolefin-based wax (C-1) were used instead of the raw materials used as the raw materials for

the thermoplastic resin composition in Example 1, and the physical properties were measured by the methods described above.

The results are shown in Table 1.

5 [0140]

[Example 13]

The samples for testing physical properties were produced in the same manner as in Example 1, except that 33 parts by mass of the ethylene-based polymer (A1-1), 2.0 parts
10 by mass of the ethylene-based polymer (A1-3), 65 parts by mass of the magnesium oxide (B-2), and 0.6 parts by mass of the unmodified polyolefin-based wax (C-1) were used instead of the raw materials used as the raw materials for the thermoplastic resin composition in Example 1, and the
15 physical properties were measured by the methods described above.

The results are shown in Table 1.

[0141]

[Example 14]

20 The samples for testing physical properties were produced in the same manner as in Example 1, except that 18 parts by mass of the ethylene-based polymer (A1-1), 2.0 parts by mass of the ethylene-based polymer (A1-3), 80 parts by mass of the magnesium oxide (B-2), and 0.6 parts by mass of

the unmodified polyolefin-based wax (C-1) were used instead of the raw materials used as the raw materials for the thermoplastic resin composition in Example 1, and the physical properties were measured by the methods described
5 above.

The results are shown in Table 1.

[0142]

[Example 15]

The samples for testing physical properties were
10 produced in the same manner as in Example 1, except that 25 parts by mass of the ethylene-based polymer (A1-2), 75 parts by mass of the magnesium oxide (B-2), and 0.6 parts by mass of the unmodified polyolefin-based wax (C-1) were used instead of the raw materials used as the raw materials for
15 the thermoplastic resin composition in Example 1, and the physical properties were measured by the methods described above.

The results are shown in Table 1.

[0143]

20 [Example 16]

The samples for testing physical properties were produced in the same manner as in Example 1, except that 23 parts by mass of the ethylene-based polymer (A1-2), 2.0 parts by mass of the ethylene-based polymer (A1-3), 75 parts by

mass of the magnesium oxide (B-2), and 0.6 parts by mass of the unmodified polyolefin-based wax (C-1) were used instead of the raw materials used as the raw materials for the thermoplastic resin composition in Example 1, and the physical properties were measured by the methods described above. In addition, the antibacterial sustainability test in water resistance category 0 and light resistance category 0 were performed by the method described above.

The results are shown in Table 1.

[0144]

[Example 17]

The samples for testing physical properties were produced in the same manner as in Example 1, except that 23 parts by mass of the ethylene-based polymer (A1-2), 2.0 parts by mass of the ethylene-based polymer (A1-3), 75 parts by mass of the magnesium oxide (B-2), 0.6 parts by mass of the unmodified polyolefin-based wax (C-1), and 1.0 parts by mass of carbon black were used instead of the raw materials used as the raw materials for the thermoplastic resin composition in Example 1, and the physical properties were measured by the methods described above.

The results are shown in Table 1.

[0145]

[Example 18]

The samples for testing physical properties were produced in the same manner as in Example 1, except that 28 parts by mass of the propylene-based polymer (A2-2), 2.0 parts by mass of the ethylene-based polymer (A1-3), 70 parts by mass of the magnesium oxide (B-3), and 0.6 parts by mass of the unmodified polyolefin-based wax (C-1) were used instead of the raw materials used as the raw materials for the thermoplastic resin composition in Example 1, and the physical properties were measured by the methods described above.

The results are shown in Table 1.

[0146]

[Example 19]

The samples for testing physical properties were produced in the same manner as in Example 1, except that 28 parts by mass of the propylene-based polymer (A2-2), 2.0 parts by mass of the ethylene-based polymer (A1-3), 70 parts by mass of the magnesium oxide (B-3), and 1 parts by mass of the unmodified polyolefin-based wax (C-1) were used instead of the raw materials used as the raw materials for the thermoplastic resin composition in Example 1, and the physical properties were measured by the methods described above.

The results are shown in Table 1.

[0147]

[Example 20]

The samples for testing physical properties were produced in the same manner as in Example 1, except that 28 parts by mass of the propylene-based polymer (A2-2), 2.0 parts by mass of the ethylene-based polymer (A1-3), 70 parts by mass of the magnesium oxide (B-3), and 2 parts by mass of the unmodified polyolefin-based wax (C-1) were used instead of the raw materials used as the raw materials for the thermoplastic resin composition in Example 1, and the physical properties were measured by the methods described above.

The results are shown in Table 1.

[0148]

15 [Example 21]

The samples for testing physical properties were produced in the same manner as in Example 1, except that 23 parts by mass of the propylene-based polymer (A2-2), 2.0 parts by mass of the ethylene-based polymer (A1-3), 75 parts by mass of the magnesium oxide (B-3), and 0.6 parts by mass of the unmodified polyolefin-based wax (C-1) were used instead of the raw materials used as the raw materials for the thermoplastic resin composition in Example 1, and the

physical properties were measured by the methods described above.

The results are shown in Table 1.

[0149]

5 [Example 22]

The samples for testing physical properties were produced in the same manner as in Example 1, except that 14 parts by mass of the propylene-based polymer (A2-2), 14 parts by mass of the propylene-based polymer (A2-4), 2.0 parts by mass of the ethylene-based polymer (A1-3), 70 parts by mass of the magnesium oxide (B-2), and 0.6 parts by mass of the unmodified polyolefin-based wax (C-1) were used instead of the raw materials used as the raw materials for the thermoplastic resin composition in Example 1, and the physical properties were measured by the methods described above.

The results are shown in Table 1.

[0150]

[Example 23]

20 The samples for testing physical properties were produced in the same manner as in Example 1, except that 18.7 parts by mass of the propylene-based polymer (A2-2), 9.3 parts by mass of the propylene-based polymer (A2-3), 2.0 parts by mass of the ethylene-based polymer (A1-3), 70 parts

by mass of the magnesium oxide (B-2), and 0.6 parts by mass of the unmodified polyolefin-based wax (C-1) were used instead of the raw materials used as the raw materials for the thermoplastic resin composition in Example 1, and the physical properties were measured by the methods described above.

The results are shown in Table 1.

[0151]

The propylene-based polymer (A2-3) is blended with 20% by mass glass fiber as described above. The formulation ratio when the total amount of propylene-based polymer (A2-3) excluding the glass fiber (PP portion), propylene-based polymer (A2-2), and magnesium oxide (B-2) is calculated as 100 parts by mass is as follows. 19.1 parts by mass of the propylene-based polymer (A2-2), 7.6 parts by mass of the PP portion of the propylene-based polymer (A2-3), 2.0 parts by mass of the ethylene-based polymer (A1-3), 71.3 parts by mass of the magnesium oxide (B-2), 0.6 parts by mass of the unmodified polyolefin-based wax (C-1), and 1.9 parts by mass of the glass fiber portion of the propylene-based polymer (A2-3).

[0152]

[Example 24]

The samples for testing physical properties were produced in the same manner as in Example 1, except that 11.5 parts by mass of the propylene-based polymer (A2-3), 11.5 parts by mass of the propylene-based polymer (A2-4), 2.0 parts by mass of the ethylene-based polymer (A1-3), 75 parts by mass of the magnesium oxide (B-2), and 0.6 parts by mass of the unmodified polyolefin-based wax (C-1) were used instead of the raw materials used as the raw materials for the thermoplastic resin composition in Example 1, and the physical properties were measured by the methods described above.

The results are shown in Table 1.

[0153]

The propylene-based polymer (A2-3) is blended with 20% by mass glass fiber as described above. The formulation ratio when the total amount of propylene-based polymer (A2-3) excluding the glass fiber (PP portion), propylene-based polymer (A2-4), and magnesium oxide (B-2) is calculated as 100 parts by mass is as follows. 9.4 parts by mass of the PP portion of the propylene-based polymer (A2-3), 11.8 parts by mass of the propylene-based polymer (A2-4), 2.0 parts by mass of the ethylene-based polymer (A1-3), 76.8 parts by mass of the magnesium oxide (B-2), 0.6 parts by mass of the unmodified polyolefin-based wax (C-1), and 2.4 parts by mass

of the glass fiber portion of the propylene-based polymer (A2-3).

[0154]

[Example 25]

5 The samples for testing physical properties were produced in the same manner as in Example 1, except that 14 parts by mass of the propylene-based polymer (A2-3), 14 parts by mass of the propylene-based polymer (A2-4), 2.0 parts by mass of the ethylene-based polymer (A1-3), 70 parts by mass
10 of the magnesium oxide (B-2), and 0.6 parts by mass of the unmodified polyolefin-based wax (C-1) were used instead of the raw materials used as the raw materials for the thermoplastic resin composition in Example 1, and the physical properties were measured by the methods described
15 above.

The results are shown in Table 1.

[0155]

The propylene-based polymer (A2-3) is blended with 20% by mass glass fiber as described above. The formulation
20 ratio when the total amount of propylene-based polymer (A2-3) excluding the glass fiber (PP portion), propylene-based polymer (A2-4), and magnesium oxide (B-2) is calculated as 100 parts by mass is as follows. 11.5 parts by mass of the PP portion of the propylene-based polymer (A2-3), 14.4 parts

by mass of the propylene-based polymer (A2-4), 2.1 parts by mass of the ethylene-based polymer (A1-3), 72 parts by mass of the magnesium oxide (B-2), 0.6 parts by mass of the unmodified polyolefin-based wax (C-1), and 2.9 parts by mass of the glass fiber portion of the propylene-based polymer (A2-3).

[0156]

[Example 26]

The samples for testing physical properties were produced in the same manner as in Example 1, except that 14 parts by mass of the propylene-based polymer (A2-3), 14 parts by mass of the propylene-based polymer (A2-4), 2.0 parts by mass of the ethylene-based polymer (A1-3), 70 parts by mass of the magnesium oxide (B-2), and 1.0 parts by mass of the unmodified polyolefin-based wax (C-1) were used instead of the raw materials used as the raw materials for the thermoplastic resin composition in Example 1, and the physical properties were measured by the methods described above.

The results are shown in Table 1.

[0157]

The propylene-based polymer (A2-3) is blended with 20% by mass glass fiber as described above. The formulation ratio when the total amount of propylene-based polymer (A2-3)

excluding the glass fiber (PP portion), propylene-based polymer (A2-4), and magnesium oxide (B-2) is calculated as 100 parts by mass is as follows. 11.5 parts by mass of the PP portion of the propylene-based polymer (A2-3), 14.4 parts
5 by mass of the propylene-based polymer (A2-4), 2.1 parts by mass of the ethylene-based polymer (A1-3), 72 parts by mass of the magnesium oxide (B-2), 1.0 parts by mass of the unmodified polyolefin-based wax (C-1), and 2.9 parts by mass of the glass fiber portion of the propylene-based polymer
10 (A2-3).

[0158]

[Example 27]

The samples for testing physical properties were produced in the same manner as in Example 1, except that 33
15 parts by mass of the ethylene-based polymer (A1-2), 2.0 parts by mass of the ethylene-based polymer (A1-3), 65 parts by mass of the magnesium oxide (B-2), and 0.6 parts by mass of the unmodified polyolefin-based wax (C-1) were used instead of the raw materials used as the raw materials for the
20 thermoplastic resin composition in Example 1, and the physical properties were measured by the methods described above.

The results are shown in Table 1.

[0159]

[Example 28]

The samples for testing physical properties were produced in the same manner as in Example 1, except that 35.0 parts by mass of the 4-methyl-1-pentene-based polymer (A4-1),
5 65 parts by mass of the magnesium oxide (B-2), and 0.6 parts by mass of the unmodified polyolefin-based wax (C-1) were used instead of the raw materials used as the raw materials for the thermoplastic resin composition in Example 1, and the physical properties were measured by the methods described
10 above.

The results are shown in Table 1.

[0160]

[Example 29]

The samples for testing physical properties were
15 produced in the same manner as in Example 1, except that 30 parts by mass of the 4-methyl-1-pentene-based polymer (A4-1), 70 parts by mass of the magnesium oxide (B-2), and 0.6 parts by mass of the unmodified polyolefin-based wax (C-1) were used instead of the raw materials used as the raw materials
20 for the thermoplastic resin composition in Example 1. In addition, the antibacterial sustainability test in water resistance category 0 and light resistance category 0 were performed by the method described above.

The results are shown in Table 1.

[0161]

[Example 30]

The samples for testing physical properties were produced in the same manner as in Example 1, except that 25 parts by mass of the 4-methyl-1-pentene-based polymer (A4-1), 75 parts by mass of the magnesium oxide (B-2), and 0.6 parts by mass of the unmodified polyolefin-based wax (C-1) were used instead of the raw materials used as the raw materials for the thermoplastic resin composition in Example 1, and the physical properties were measured by the methods described above.

The results are shown in Table 1.

[0162]

[Example 31]

The samples for testing physical properties were produced in the same manner as in Example 1, except that 35 parts by mass of the ABS resin (A5-1), 65 parts by mass of the magnesium oxide (B-2), and 0.6 parts by mass of the unmodified polyolefin-based wax (C-1) were used instead of the raw materials used as the raw materials for the thermoplastic resin composition in Example 1, and the physical properties were measured by the methods described above.

The results are shown in Table 1.

[0163]

[Example 32]

The samples for testing physical properties were produced in the same manner as in Example 1, except that 30 parts by mass of the ABS resin (A5-1), 70 parts by mass of the magnesium oxide (B-2), and 0.6 parts by mass of the unmodified polyolefin-based wax (C-1) were used instead of the raw materials used as the raw materials for the thermoplastic resin composition in Example 1, and the physical properties were measured by the methods described above.

The results are shown in Table 1. In addition, the antibacterial sustainability test in water resistance category 0 and light resistance category 0 were performed by the method described above.

[0164]

[Example 33]

The samples for testing physical properties were produced in the same manner as in Example 1, except that 25 parts by mass of the ABS resin (A5-1), 75 parts by mass of the magnesium oxide (B-2), and 0.6 parts by mass of the unmodified polyolefin-based wax (C-1) were used instead of the raw materials used as the raw materials for the thermoplastic resin composition in Example 1.

The results are shown in Table 1.

[0165]

[Comparative Example 1]

The samples for testing physical properties were
5 produced in the same manner as in Example 1, except that 68
parts by mass of the propylene-based polymer (A2-2), 2.0
parts by mass of the ethylene-based polymer (A1-3), 30 parts
by mass of the magnesium oxide (B-2), and 0.6 parts by mass
of the unmodified polyolefin-based wax (C-1) were used
10 instead of the raw materials used as the raw materials for
the thermoplastic resin composition in Example 1, and the
physical properties were measured by the methods described
above.

The results are shown in Table 1. The composition
15 obtained by Comparative Example 1 does not provide a premium
texture like ceramics as it does not easily transmit heat due
to its low thermal conductivity.

[0166]

[Comparative Example 2]

20 The samples for testing physical properties were
produced in the same manner as in Example 1, except that 23
parts by mass of the propylene-based polymer (A2-2), 2.0
parts by mass of the ethylene-based polymer (A1-3), 75 parts
by mass of the magnesium oxide (B-2), and 0.6 parts by mass

of modified polyolefin-based wax were used instead of the raw materials used as the raw materials for the thermoplastic resin composition in Example 1, and the physical properties were measured by the methods described above.

5 The results are shown in Table 1. The composition obtained by Comparative Example 2 had a lower deflection temperature under load and lower physical properties. This is thought to be because the acid value of the modified polyolefin-based wax is low, resulting in weak hydrogen bonds
10 with the metal oxide (hereinafter also referred to as filler), and the filler not uniformly dispersed in the resin. On the other hand, it is thought that while the unmodified polyolefin-based wax (C) used in the Examples has an acid value of 0, resulting in weak hydrogen bonds with the filler,
15 the interaction in the small amount of resin acting as a binder is stronger, and therefore the deflection temperature under load and physical properties of the resulting composition are good.

[0167]

20 [Comparative Example 3]

The samples for testing physical properties were produced in the same manner as in Example 1, except that 23 parts by mass of the propylene-based polymer (A2-2), 2.0 parts by mass of the ethylene-based polymer (A1-3), and 75

parts by mass of the magnesium oxide (B-2) were used instead of the raw materials used as the raw materials for the thermoplastic resin composition in Example 1, and the physical properties were measured by the methods described
5 above.

The results are shown in Table 1. Since the composition obtained by Comparative Example 3 did not contain the unmodified polyolefin-based wax (C), the filler tended to agglomerate and was difficult to disperse uniformly, making
10 it difficult to produce and uneven, resulting in inferior kneadability and resin fluidity (MFR).

[0168]

[Table 1-1]

Table 1

				Example 1	Example 2	Example 3	Example 4	Example 5
Thermoplastic resin (A)	Propylene-based polymer (A2)	(A2-1)	parts by mass	30.0				
		(A2-2)	parts by mass		23.0	23.0	23.0	24.5
		(A2-3) PP portion	parts by mass					
		(A2-4)	parts by mass					
	Ethylene-based polymer (A1)	(A1-1)	parts by mass					
		(A1-2)	parts by mass					
		(A1-3)	parts by mass		2.0	2.0	2.0	0.5
	4-Methyl-1-pentene-based polymer (A4)	(A4-1)	parts by mass					
	ABS resin (A5)	(A5-1)	parts by mass					
	Subtotal			30.0	25.0	25.0	25.0	25.0
Metal oxide (B)	Magnesium oxide (B-1)		parts by mass	70.0		15.0	22.5	
	Magnesium oxide (B-2)		parts by mass		75.0	60.0	52.5	75.0
	Magnesium oxide (B-3)		parts by mass					
	Subtotal			70.0	75.0	75.0	75.0	75.0
	(B-1)/(B-2) ratio		Mass ratio	100/0	0/100	20/80	30/70	0/100
Total			parts by mass	100	100	100	100	100
Unmodified polyolefin-based wax (C)	(C-1)		parts by mass	0.6	0.6	0.6	0.6	0.6
Other components	Modified polyolefin-based wax		parts by mass					
	(A2-3) glass fiber portion		parts by mass					
	Carbon black		parts by mass					
Mechanical properties	Specific gravity		g/cm ³	2.30	2.01	1.98	1.95	2.00
	MFR (230°C, 2.16 kgf)		g/10 min	1.0	25.3	19	19.2	28.3
	MFR (230°C, 5 kgf)		g/10 min		92.7	68.2	70.3	104
	Pencil hardness				HB	3B	4B	2H
Thermal properties	Thermal conductivity		W/m•K	1.8	1.32	1.37	1.41	1.2
	Deflection temperature under load (1.8 MPa)		°C	58	75.5	67	66	71.5
Chemical properties	Water absorption rate		wt%	0.01	0.01	0	0	0.01
Antibacterial properties (water resistance category 0/light resistance category 0)	Antibacterial activity value (Escherichia coli)		-		5.4			
	Antibacterial activity value (Staphylococcus aureus)		-		4.0			

Table 1 (continued)

				Example 6	Example 7	Example 8	Example 9	Example 10
Thermoplastic resin (A)	Propylene-based polymer (A2)	(A2-1)	parts by mass					
		(A2-2)	parts by mass	29.5	34.5		11.8	15.5
		(A2-3) PP portion	parts by mass			19.3	9.4	6.3
		(A2-4)	parts by mass					
	Ethylene-based polymer (A1)	(A1-1)	parts by mass					
		(A1-2)	parts by mass					
		(A1-3)	parts by mass	0.5	0.5	2.1	2.0	2.0
	4-Methyl-1-pentene-based polymer (A4)	(A4-1)	parts by mass					
	ABS resin (A5)	(A5-1)	parts by mass					
		Subtotal		30.0	35.0	21.4	23.2	23.8
Metal oxide (B)	Magnesium oxide (B-1)		parts by mass					
	Magnesium oxide (B-2)		parts by mass	70.0	65.0	78.6	76.8	76.2
	Magnesium oxide (B-3)		parts by mass					
	Subtotal			70.0	65.0	78.6	76.8	76.2
	(B-1)/(B-2) ratio		Mass ratio	0/100	0/100	0/100	0/100	0/100
Total			parts by mass	100	100	100	100	100
Unmodified polyolefin-based wax (C)	(C-1)		parts by mass	0.6	0.6	0.6	0.6	0.6
Other components	Modified polyolefin-based wax		parts by mass					
	(A2-3) glass fiber portion		parts by mass			4.8	2.4	1.6
	Carbon black		parts by mass					
Mechanical properties	Specific gravity		g/cm ³	1.85	1.73	2.09	2.07	2.03
	MFR (230°C, 2.16 kgf)		g/10 min	36.6	43.7	8.0	9.47	12.8
	MFR (230°C, 5 kgf)		g/10 min	132	156	29.8	41.3	48.9
	Pencil hardness			B	B	4H	3H	4H
Thermal properties	Thermal conductivity		W/m·K	1.05	0.79	1.82	1.58	1.28
	Deflection temperature under load (1.8 MPa)		°C	72.3	72.3	107.6	89.8	87.8
Chemical properties	Water absorption rate		wt%	0	0.01	0.01	0.01	0.01
Antibacterial properties (water resistance category 0/light resistance category 0)	Antibacterial activity value (Escherichia coli)		-		1.5			
	Antibacterial activity value (Staphylococcus aureus)		-		3.9			

[Table 1-2]

Table 1 (continued)

				Example 11	Example 12	Example 13	Example 14	Example 15	Example 16
Thermoplastic resin (A)	Propylene-based polymer (A2)	(A2-1)	parts by mass						
		(A2-2)	parts by mass						
		(A2-3)	parts by mass						
		PP portion	mass						
	Ethylene-based polymer (A1)	(A1-1)	parts by mass	25.0	25.0	33.0	18.0		
		(A1-2)	parts by mass					25.0	23.0
		(A1-3)	parts by mass			2.0	2.0		2.0
	4-Methyl-1-pentene-based polymer (A4)	(A4-1)	parts by mass						
	ABS resin (A5)	(A5-1)	parts by mass						
		Subtotal		25.0	25.0	35.0	20.0	25.0	25.0
Metal oxide (B)	Magnesium oxide (B-1)		parts by mass	22.5					
	Magnesium oxide (B-2)		parts by mass	52.5	75.0	65.0	80.0	75.0	75.0
	Magnesium oxide (B-3)		parts by mass						
	Subtotal			75.0	75.0	65.0	80.0	75.0	75.0
	(B-1)/(B-2) ratio		Mass ratio	30/70	0/100	0/100	0/100	0/100	0/100
Total			parts by mass	100	100	100	100	100	100
Unmodified polyolefin-based wax (C)	(C-1)		parts by mass	0.6	0.6	0.6	0.6	0.6	0.6
Other components	Modified polyolefin-based wax		parts by mass						
	(A2-3) glass fiber portion		parts by mass						
	Carbon black		parts by mass						
Mechanical properties	Specific gravity		g/cm ³	2.13	2.05	1.80	2.22	2.08	2.07
	MFR (230°C, 2.16 kgf)		g/10 min	8.3	6.7	15.2	1.3	6.7	9.5
	MFR (230°C, 5 kgf)		g/10 min	25.9	22.2	49	5.4	24.4	33.9
	Pencil hardness			5B	5B	3B	B	HB	F
Thermal properties	Thermal conductivity		W/m·K	2.82	2.78	1.51	2.89	3.06	2.84
	Deflection temperature under load (1.8 MPa)		°C	64.4	54.8	61.2	61.2	69.4	52.2
Chemical properties	Water absorption rate		wt%	0.01	0.01	0	0	0	0
Antibacterial properties (water resistance category 0/light resistance category 0)	Antibacterial activity value (Escherichia coli)		-						6.1
	Antibacterial activity value (Staphylococcus aureus)		-						4.2

Table 1 (continued)

Table 1 (continued)				Example 17	Example 18	Example 19	Example 20	Example 21	Example 22
Thermoplastic resin (A)	Propylene-based polymer (A2)	(A2-1)	parts by mass						
		(A2-2)	parts by mass		28.0	28.0	28.0	23.0	14.0
		(A2-3) PP portion	parts by mass						
		(A2-4)	parts by mass						14.0
	Ethylene-based polymer (A1)	(A1-1)	parts by mass						
		(A1-2)	parts by mass	23.0					
		(A1-3)	parts by mass	2.0	2.0	2.0	2.0	2.0	2.0
	4-Methyl-1-pentene-based polymer (A4)	(A4-1)	parts by mass						
	ABS resin (A5)	(A5-1)	parts by mass						
		Subtotal		25.0	30.0	30.0	30.0	25.0	30.0
Metal oxide (B)	Magnesium oxide (B-1)		parts by mass						
	Magnesium oxide (B-2)		parts by mass	75.0					70.0
	Magnesium oxide (B-3)		parts by mass		70.0	70.0	70.0	75.0	
	Subtotal			75.0	70.0	70.0	70.0	75.0	70.0
	(B-1)/(B-2) ratio		Mass ratio	0/100	0/0	0/0	0/0	0/0	0/100
Total			parts by mass	100	100	100	100	100	100
Unmodified polyolefin-based wax (C)	(C-1)		parts by mass	0.6	0.6	1.0	2.0	0.6	0.6
Other components	Modified polyolefin-based wax		parts by mass						
	(A2-3) glass fiber portion		parts by mass						
	Carbon black		parts by mass	1.0					
Mechanical properties	Specific gravity		g/cm ³	2.10	1.87	1.86	1.86	2.00	1.91
	MFR (230°C, 2.16 kgf)		g/10 min	7.0	20.4	23.2	28.0	139.0	55.2
	MFR (230°C, 5 kgf)		g/10 min	23.6	67.8	87.8	98.8	*1	228
	Pencil hardness			2B	H	B	HB	H	H
Thermal properties	Thermal conductivity		W/m•K	3.32	0.93	0.85	0.99	1.28	0.92
	Deflection temperature under load (1.8 MPa)		°C	66.3	69.1	47.6	Too deflected to take	81.9	54.8
Chemical properties	Water absorption rate		wt%	0	0	0	0	0	0
Antibacterial properties (water resistance category 0/light resistance category 0)	Antibacterial activity value (Escherichia coli)		-						
	Antibacterial activity value (Staphylococcus aureus)		-						

[Table 1-3]

Table 1 (continued)

				Example 23	Example 24	Example 25	Example 26	Example 27	Example 28	Example 29
Thermoplastic resin (A)	Propylene- based polymer (A2)	(A2-1)	parts by mass							
		(A2-2)	parts by mass	19.1						
		(A2-3)	parts by mass	7.6	9.4	11.5	11.5			
		PP portion	parts by mass		11.8	14.4	14.4			
	Ethylene- based polymer (A1)	(A1-1)	parts by mass							
		(A1-2)	parts by mass					33.0		
		(A1-3)	parts by mass	2.0	2.0	2.1	2.1	2.0		
	4-Methyl-1- pentene- based polymer (A4)	(A4-1)	parts by mass						35.0	30.0
	ABS resin (A5)	(A5-1)	parts by mass							
		Subtotal		28.7	23.2	28.0	28.0	35.0	35.0	30.0
Metal oxide (B)	Magnesium oxide (B-1)		parts by mass							
	Magnesium oxide (B-2)		parts by mass	71.3	76.8	72.0	72.0	65.0	65.0	70.0
	Magnesium oxide (B-3)		parts by mass							
	Subtotal			71.3	76.8	72.0	72.0	65.0	65.0	70.0
	(B-1)/(B-2) ratio		Mass ratio	0/100	0/100	0/100	0/100	0/100	0/100	0/100
Total			parts by mass	100	100	100	100	100	100	100
Unmodified polyolefin-based wax (C)	(C-1)		parts by mass	0.6	0.6	0.6	1.0	0.6	0.6	0.6
Other components	Modified polyolefin- based wax		parts by mass							
	(A2-3) glass fiber portion		parts by mass	1.9	2.4	2.9	2.9			
	Carbon black		parts by mass							
Mechanical properties	Specific gravity		g/cm ³	1.90	2.03	1.91	1.87	1.80	1.65	1.73
	MFR (230°C, 2.16 kgf)		g/10 min	21.9	21.4	41.4	36.5	15.2	10.7	9.7
	MFR (230°C, 5 kgf)		g/10 min	83.6	87.5	164	135	49	45.1	44.1
	Pencil hardness			2H	4H	5H	4H	3B	<6B	<6B
Thermal properties	Thermal conductivity		W/m·K	1.03	1.47	1.16	1.15	1.51	0.56	0.63
	Deflection temperature under load (1.8 MPa)		°C	92.9	104.8	112.4	57.2	61.2	Too deflected to take	Too deflected to take
Chemical properties	Water absorption rate		wt%	0.01	0.01	0.01	0.01	0	0.13	0.01
Antibacterial properties (water resistance category 0/light resistance category 0)	Antibacterial activity value (Escherichia coli)		-							2.1
	Antibacterial activity value (Staphylococcus aureus)		-							4.9

Table 1 (continued)

				Example 30	Example 31	Example 32	Example 33	Comparative Example 1	Comparative Example 2	Comparative Example 3
Thermoplastic resin (A)	Propylene-based polymer (A2)	(A2-1)	parts by mass							
		(A2-2)	parts by mass					68.0	23.0	23.0
		(A2-3)	parts by mass							
		PP portion	parts by mass							
	Ethylene-based polymer (A1)	(A1-1)	parts by mass							
		(A1-2)	parts by mass							
		(A1-3)	parts by mass					2.0	2.0	2.0
	4-Methyl-1-pentene-based polymer (A4)	(A4-1)	parts by mass	25.0						
	ABS resin (A5)	(A5-1)	parts by mass		35.0	30.0	25.0			
		Subtotal		25.0	35.0	30.0	25.0	70.0	25.0	25.0
Metal oxide (B)	Magnesium oxide (B-1)	parts by mass								
	Magnesium oxide (B-2)	parts by mass		75.0	65.0	70.0	75.0	30.0	75.0	75.0
	Magnesium oxide (B-3)	parts by mass								
	Subtotal			75.0	65.0	70.0	75.0	30.0	75.0	75.0
	(B-1)/(B-2) ratio	Mass ratio		0/100	0/100	0/100	0/100	0/100	0/100	0/100
Total		parts by mass		100	100	100	100	100	100	100
Unmodified polyolefin-based wax (C)	(C-1)	parts by mass		0.6	0.6	0.6	0.6	0.6		
Other components	Modified polyolefin-based wax	parts by mass							0.6	
	(A2-3) glass fiber portion	parts by mass								
	Carbon black	parts by mass								
Mechanical properties	Specific gravity	g/cm ³		1.93	1.91	2.03	2.11	1.16	1.99	2.00
	MFR (230°C, 2.16 kgf)	g/10 min		6.4	4.8	2.8	1.3	58.4	15.1	14.9
	MFR (230°C, 5 kgf)	g/10 min		39.9	13.7	11.3	5.4	232	59.1	62
	Pencil hardness			<6B	2H	4H	6H	3B	HB	2H
Thermal properties	Thermal conductivity	W/m·K		0.77	0.84	0.74	1.13	0.32	1.43	1.25
	Deflection temperature under load (1.8 MPa)	°C		Too deflected to take	90.7	89	93.1	Too deflected to take	52.6	76.7
Chemical properties	Water absorption rate	wt%		0	0.02	0.13	1.13	0.01	0	0
Antibacterial properties (water resistance category 0/light resistance category 0)	Antibacterial activity value (Escherichia coli)	-				6.0				
	Antibacterial activity value (Staphylococcus aureus)	-				3.7				

[0171]

"*1" in Table 1 (Example 21) indicates that the thermoplastic resin composition flowed too much to be measured.

5 [0172]

[Table 2]

Table 2

Example 2	Antibacterial activity value	
	Staphylococcus aureus	Escherichia coli
Water resistance category 0/light resistance category 0	5.4	4.0
Water resistance category 1	4.2	6.0
Water resistance category 2	4.2	6.0
Light resistance category 1	4.2	2.8
Light resistance category 2	4.3	2.6

[0173]

10 [Table 3]

Table 3

	Common logarithm of viral infectivity titer			[Ut-At]
	Blank sample immediately after inoculation [U0]	Blank sample after 24 hours [Ut]	Example 2 after 24 hours [At]	Antiviral activity [Ut-At]
Water resistance category 1	5.63	4.31	<0.80	3.5
Water resistance category 2	5.53	4.39	<0.80	3.5
Light resistance category 1	5.7	4.4	<0.80	3.5
Light resistance category 2	5.7	4.29	1.5	2.7

CLAIMS

[Claim 1]

A thermoplastic resin composition comprising 10 to 50 parts by mass of a thermoplastic resin (A), 50 to 90 parts by mass of a metal oxide (B), provided that a total amount of (A)+(B) is 100 parts by mass, and an unmodified polyolefin-based wax (C) in a range of 0.1 to 20 parts by mass per 100 parts by mass of the total amount of (A)+(B).

[Claim 2]

The thermoplastic resin composition according to claim 1, wherein the thermoplastic resin (A) is one or more selected from the group consisting of ethylene-based polymers, propylene-based polymers, 1-butene-based polymers, 4-methyl-1-pentene-based polymers, and ABS resins.

[Claim 3]

The thermoplastic resin composition according to claim 1, wherein the metal oxide (B) comprises magnesium oxide.

[Claim 4]

The thermoplastic resin composition according to claim 1, wherein an average particle size of the metal oxide (B) is in a range of 0.1 to 110 μm .

[Claim 5]

The thermoplastic resin composition according to claim 1, wherein a thermal conductivity of the metal oxide (B) is in a range of 10 to 300 W/mK.

[Claim 6]

5 The thermoplastic resin composition according to claim 1, wherein a thermal conductivity of the thermoplastic resin composition is in a range of 0.5 to 5 W/mK.

[Claim 7]

The thermoplastic resin composition according to claim 1,
10 wherein a specific gravity of the thermoplastic resin composition is in a range of 1.0 to 5.0.

[Claim 8]

The thermoplastic resin composition according to claim 1, comprising 10 to 30 parts by mass of the thermoplastic resin
15 (A) and 70 to 90 parts by mass of the metal oxide (B), provided that the total amount of (A)+(B) is 100 parts by mass.

[Claim 9]

The thermoplastic resin composition according to claim 1,
20 wherein an antibacterial activity value after 24 hours is 2.0 or more in an antibacterial test performed using Escherichia coli in accordance with JIS Z 2801:2012 (film adhesion method) under conditions where no water or light resistance pretreatment is performed.

[Claim 10]

The thermoplastic resin composition according to claim 1,
wherein an antibacterial activity value after 24 hours is 2.0
or more in an antibacterial test performed using

5 Staphylococcus aureus in accordance with JIS Z 2801:2012
(film adhesion method) under conditions where no water or
light resistance pretreatment is performed.

[Claim 11]

The thermoplastic resin composition according to claim 1,
10 wherein an antiviral activity value is 2.0 or more in an
antiviral test performed using Feline calicivirus conducted
in accordance with ISO 21702:2019.

[Claim 12]

The thermoplastic resin composition according to claim 1,
15 comprising a fibrous filler (D) in a range of 0.1 to 20 parts
by mass per 100 parts by mass in total of the thermoplastic
resin (A) and the metal oxide (B).

[Claim 13]

A molded article comprising the thermoplastic resin
20 composition according to any one of claims 1 to 12.

[Claim 14]

A door handle, door knob, handrail or switch comprising
the thermoplastic resin composition according to any one of
claims 1 to 12.

[Claim 15]

A case comprising the thermoplastic resin composition according to any one of claims 1 to 12.

[Claim 16]

5 A fashion accessory comprising the thermoplastic resin composition according to any one of claims 1 to 12.

[Claim 17]

A container comprising the thermoplastic resin composition according to any one of claims 1 to 12.

10 [Claim 18]

Stationery comprising the thermoplastic resin composition according to any one of claims 1 to 12.

[Claim 19]

15 Tableware or alcoholic drink ware comprising the thermoplastic resin composition according to any one of claims 1 to 12.

[Claim 20]

A mouse or keyboard comprising the thermoplastic resin composition according to any one of claims 1 to 12.

20