

**PCT**WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶: C10M 169/04 // (C10M 169/04, 101:04, 129:10, 129:40, 129:58, 135:18, 137:10, 159:18), C10N 10:02, 10:04, 10:10, 30:10, 40:00, 40:25	A1	(11) International Publication Number: ☒ WO 97/43361 (43) International Publication Date: 20 November 1997 (20.11.97)
(21) International Application Number: ☒ PCT/US97/08384 (22) International Filing Date: ☒ 12 May 1997 (12.05.97) (30) Priority Data: 08/644,964 ☒ 15 May 1996 (15.05.96) ☒ US (71) Applicant: RENEWABLE LUBRICANTS, INC. [US/US]; 476 Griggy Road, Hartville, OH 44632 (US). (72) Inventor: GARMIER, William, W.; 476 Griggy Road, Hartville, OH 44632 (US). (74) Agents: LAFERTY, Samuel, B. et al.; Hudak & Shunk Co., L.P.A., Suite 808, 7 West Bowery Street, Akron, OH 44308- 1133 (US).	(81) Designated States: AL, AU, BB, BG, BR, CA, CN, CZ, EE, GE, HU, IL, IS, JP, KP, KR, LK, LR, LT, LV, MG, MK, MN, MX, NO, NZ, PL, RO, (SG) SI, SK, TR, TT, UA, UZ, VN, ARIPO patent (GH, KE, LS, MW, SD, SZ, UG), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>	
(54) Title: BIODEGRADABLE LUBRICANT COMPOSITION FROM TRIGLYCERIDES AND OIL-SOLUBLE COPPER ☒		
(57) Abstract A lubricant composition is disclosed which comprises a triglyceride oil lubricant and an oil soluble copper compound antioxidant. The oil soluble copper compounds are particularly effective antioxidants for triglycerides. The lubricant composition can include soluble zinc compounds which reduce wear and/or soluble antimony compounds which reduce wear and can function as adjuvant antioxidants reducing the amount of oil soluble copper required. Preferred zinc and antimony compounds are zinc dithiophosphate antiwear/antioxidant, and antimony dialkyldithiocarbamate antioxidant adjuvant.		