

REMOVING CARBON NANOTUBES FROM A WATER SYSTEM

RELATED APPLICATIONS

[0001] The present provisional application is related to United States Patent
5 Application Serial No. 13/263,311 by Noyes and titled "Method for Producing Solid
Carbon by Reducing Carbon Oxides," which was filed 06 October 2011, which
claims priority based on International Patent Application Number
PCT/US2010/029934, by Noyes, entitled "Method for Producing Solid Carbon by
Reducing Carbon Oxides," which was filed on 05 April 2010, which in turn claims
10 priority based on United States Provisional Patent Application Serial No. 61/170,199
filed 17 April 2009 and titled "Method for Producing Solid Carbon by Reducing
Carbon Oxides," the disclosures of all of which are incorporated herein by this
reference.

FIELD

[0002] The present techniques relate to an industrial scale process for purifying a
water stream containing carbon nanotubes.

BACKGROUND

20 [0003] This section is intended to introduce various aspects of the art, which may
be associated with exemplary embodiments of the present techniques. This
discussion is believed to assist in providing a framework to facilitate a better
understanding of particular aspects of the present techniques. Accordingly, it should
be understood that this section should be read in this light, and not necessarily as
25 admissions of prior art.

[0004] Materials formed predominately of solid or elemental carbon have been
used in numerous products for many years. For example, carbon black is a high
carbon content material used as a pigment and reinforcing compound in rubber and
plastic products, such as car tires. Carbon black is usually formed by the incomplete
30 thermal pyrolysis of hydrocarbons, such as methane or heavy aromatic oils.

Thermal blacks, formed by the pyrolysis of natural gas, include large unagglomerated particles, for example, in the range of 200-500 nm in size, among others. Furnace blacks, formed by the pyrolysis of heavy oils, include much smaller particles, in the range of 10-100 nm in size, that agglomerate or stick together to form structures. In both cases, the particles may be formed from layers of graphene sheets that have open ends or edges. Chemically, the open edges form reactive areas that can be used for absorption, bonding into matrices, and the like.

[0005] More recent forms of elemental carbon, such as fullerenes, have been developed, and are starting to be developed in commercial applications. In contrast to the more open structures of carbon black, fullerenes are formed from carbon in a closed graphene structure, i.e., in which the edges are bonded to other edges to form spheres, tubes, and the like. Two structures, carbon nanofibers and carbon nanotubes, have numerous potential applications, ranging from batteries and electronics to the use in concrete in the construction industry. Carbon nanomaterials may have a single wall of graphene or multiple nested walls of graphene or form a fiber structure from a stacked set of sheets in a cup or plate form. The ends of the carbon nanotubes are often capped with hemispherical structures, in a fullerene-like configuration. Unlike for carbon black, large scale production processes have not been implemented for carbon nanomaterials. However, research has been conducted on a number of proposed production processes.

[0006] Arc-based, laser-based ablation techniques and chemical vapor deposition have classically been used to generate carbon nanotubes from a carbon surface. For example, techniques for generating carbon nanotubes are reviewed in Karthikeyan, et al., "Large Scale Synthesis of Carbon Nanotubes," E-Journal of Chemistry, 2009, 6(1), 1-12. In one technique described, an electric arc is used to vaporize graphite from electrodes in the presence of metal catalysts, achieving production rates of about 1 gram/min. Another technique described uses laser ablation to vaporize carbon from a target electrode in an inert gas stream. However, the laser technique uses high purity graphite and high power lasers, but provides a low yield of carbon nanotubes, making it impractical for large scale synthesis. A third

technique described by the authors, is based on chemical vapor deposition (CVD), in which a hydrocarbon is thermally decomposed in the presence of a catalyst. In some studies, these techniques have achieved production rates of up to a few kilograms/hour at a 70 % purity level. However, none of the processes described
5 are practical for large scale commercial production.

[0007] Hydrocarbon pyrolysis is used in the production of carbon black and various carbon nanotube and fullerene products. Various methods exist for creating and harvesting various forms of solid carbon through the pyrolysis of hydrocarbons using temperature, pressure, and the presence of a catalyst to govern the resulting
10 solid carbon morphology. For example, Kauffman, et al., (US Patent No. 2,796,331) discloses a process for making fibrous carbon of various forms from hydrocarbons in the presence of surplus hydrogen using hydrogen sulfide as a catalyst, and methods for collecting the fibrous carbon on solid surfaces. Kauffman also claims the use of coke oven gas as the hydrocarbon source.

[0008] In another study, a flame based technique is described in Vander Wal, R.L., et al., "Flame Synthesis of Single-Walled Carbon Nanotubes and Nanofibers," Seventh International Workshop on Microgravity Combustion and Chemically Reacting Systems, Aug. 2003, 73-76 (NASA Research Publication: NASA/CP—2003-212376/REV1). The technique used the introduction of a CO or CO/C₂H₂
20 mixture into a flame along with a catalyst to form the carbon nanotubes. The authors noted the high productivity that could be achieved using flame based techniques for the production of carbon black. However, the authors noted that scaling the flame synthesis presented numerous challenges. Specifically, the total time for catalyst particle formation, inception of the carbon nanotubes, and growth of the carbon
25 nanotubes was limited to about 100 ms.

[0009] International Patent Application Publication WO/2010/120581, by Noyes, discloses a method for the production of various morphologies of solid carbon product by reducing carbon oxides with a reducing agent in the presence of a catalyst. The carbon oxides are typically either carbon monoxide or carbon dioxide.
30 The reducing agent is typically either a hydrocarbon gas or hydrogen. The desired

morphology of the solid carbon product may be controlled by the specific catalysts, reaction conditions and optional additives used in the reduction reaction.

[0010] While all of the techniques described above can be used to form carbon nanotubes, none of the processes provide a practical method for bulk or industrial scale production. Specifically, the amounts formed and the process efficiencies are both low. Furthermore, the techniques described above do not provide for the efficient separation and purification of water used for such a bulk or industrial scale production method.

10 SUMMARY

[0011] An embodiment described herein provides a method for removing carbon nanotubes from a water stream. The method includes flowing the water stream into a purification vessel, wherein the purification vessel is configured to form a carbon oxide from the carbon nanotubes within the water stream.

15 [0012] Another embodiment provides a system for removing carbon nanotubes from a water stream. The system includes a purification vessel, wherein the purification vessel is configured to form a carbon oxide from the carbon nanotubes within the water stream.

[0013] Another embodiment provides a method for purifying a water stream comprising carbon nanotubes. The method includes flowing the water stream into a purification vessel and injecting a chemical substance into the purification vessel. The method also includes effecting a separation of the carbon nanotubes from the water stream through an interaction of the chemical substance with the carbon nanotubes within the purification vessel.

25

DESCRIPTION OF THE DRAWINGS

[0014] The advantages of the present techniques are better understood by referring to the following detailed description and the attached drawings, in which:

[0015] **Fig. 1** is a block diagram of a reaction system that generates carbon structures, for example, as a by-product of a carbon dioxide sequestration reaction;

30

[0016] **Fig. 2** is an equilibrium diagram that identifies conditions under which a solid carbon product will form;

[0017] **Fig. 3** is a schematic of a catalytic reaction for the formation of carbon nanotubes (CNTs) on a catalyst particle;

5 [0018] **Fig. 4** is a drawing of a fluidized bed reactor for forming CNTs;

[0019] **Fig. 5** is a simplified process flow diagram of a one reactor system for making CNTs from a gas feed that includes carbon dioxide and methane;

[0020] **Fig. 6** is a simplified process flow diagram of a one reactor system for making CNTs from a gas feed that includes carbon dioxide and methane, in which
10 the carbon dioxide is in excess;

[0021] **Fig. 7** is a schematic of a water purification system that is configured to separate the water into the purified water stream and the waste stream through the addition of a flocculant;

[0022] **Fig. 8** is a schematic of a water purification system that is configured to
15 separate the water into the purified water stream and the waste stream through an air sparging process, or any number of other gas injection processes, including, for example, an ozonolysis process;

[0023] **Fig. 9** is a schematic of a water purification system that is configured to
20 separate the water into the purified water stream and the waste stream through an oxidation process;

[0024] **Fig. 10** is a schematic of a water purification system that is configured to separate the water into the purified water stream and the waste stream through a reverse osmosis process;

[0025] **Fig. 11** is a schematic of a flame degradation vessel that may be used to
25 remove CNTs from the water through the formation of steam;

[0026] **Fig. 12** is a schematic of a hydrocyclone that may be used to separate the water into the purified water stream and the waste stream;

[0027] **Fig. 13** is a process flow diagram showing a method for generating CNTs from a feed gas that includes methane and carbon dioxide; and

[0028] **Fig. 14** is a process flow diagram showing a method for the removal of CNTs from a water stream.

DETAILED DESCRIPTION

5 [0029] In the following detailed description section, specific embodiments of the present techniques are described. However, to the extent that the following description is specific to a particular embodiment or a particular use of the present techniques, this is intended to be for exemplary purposes only and simply provides a description of the exemplary embodiments. Accordingly, the techniques are not
10 limited to the specific embodiments described below, but rather, include all alternatives, modifications, and equivalents falling within the spirit and scope of the appended claims.

[0030] At the outset, for ease of reference, certain terms used in this application and their meanings as used in this context are set forth. To the extent a term used
15 herein is not defined below, it should be given the broadest definition persons in the pertinent art have given that term as reflected in at least one printed publication or issued patent. Further, the present techniques are not limited by the usage of the terms shown below, as all equivalents, synonyms, new developments, and terms or techniques that serve the same or a similar purpose are considered to be within the
20 scope of the present claims.

[0031] As used herein, "air sparging" is a water purification technique in which air is injected directly into water. The injected air may help to purify the water by volatilizing contaminants within the water. The removal of the contaminants through physical contact with air is often called "stripping," and, thus, air sparging is
25 sometimes referred to as "air stripping."

[0032] Carbon fibers, nanofibers, and nanotubes are allotropes of carbon that have a cylindrical structure, which can be in the nanometer range. Carbon nanofibers and nanotubes are members of the fullerene structural family, which includes the spherical carbon balls termed "Buckminster fullerene." The walls of the
30 carbon nanotubes are formed from sheets of carbon in a graphene structure. As

used herein, nanotubes may include single wall nanotubes and multiple wall nanotubes of any length.

5 [0033] A “compressor” is a device for compressing a working gas, including gas-vapor mixtures or exhaust gases, and includes pumps, compressor turbines, reciprocating compressors, piston compressors, rotary vane or screw compressors, and devices and combinations capable of compressing a working gas. In some embodiments, a particular type of compressor, such as a compressor turbine, may
10 be preferred. A piston compressor may be used herein to include a screw compressor, rotary vane compressor, and the like.

[0034] “Flocculation” is a process wherein colloids are brought out of suspension in the form of “floc” or “flakes” through the addition of a clarifying agent. Flocculation may result in the aggregation of small particles into larger particles. Other types of
15 flocculation may include adding solvents configured to trap substances or particles from one phase and move them to another phase. For example, counter current flow of an organic solvent through a water solution may be useful for removing hydrophobic particles from the water solution, as described herein.

[0035] A “hydrocarbon” is an organic compound that primarily includes the
20 elements hydrogen and carbon, although nitrogen, sulfur, oxygen, metals, or any number of other elements may be present in small amounts. As used herein, hydrocarbons generally refer to components found in natural gas, oil, or chemical processing facilities.

[0036] “Incineration” is a waste treatment process that involves the combustion of
25 organic substances contained in waste materials. The incineration of the waste material converts the waste material into ash, flue gas, and heat.

[0037] As used herein, the term “natural gas” refers to a multi-component gas obtained from a crude oil well or from a subterranean gas-bearing formation. The composition and pressure of natural gas can vary significantly. A typical natural gas
30 stream contains methane (CH_4) as a major component, i.e., greater than 50 mol % of

the natural gas stream is methane. The natural gas stream can also contain ethane (C_2H_6), higher molecular weight hydrocarbons (e.g., C_3 - C_{20} hydrocarbons), one or more acid gases (e.g., hydrogen sulfide), or any combination thereof. The natural gas can also contain minor amounts of contaminants such as water, nitrogen, iron sulfide, wax, crude oil, or any combination thereof. The natural gas stream may be substantially purified prior to use in embodiments, so as to remove compounds that may act as poisons.

[0038] A "low-BTU natural gas" is a gas that includes a substantial proportion of CO_2 as harvested from a reservoir. For example, a low BTU natural gas may include 10 mol % or higher CO_2 in addition to hydrocarbons and other components. In some cases, the low BTU natural gas may include mostly CO_2 .

[0039] "Oxidation" is a reaction in which atoms in an element lose electrons, and the valence of the element is correspondingly increased. As used herein, the term "oxidation" may refer to a chemical oxidation process used for water purification.

Oxidation may help to reduce the concentrations of contaminants within water through the introduction of strong chemical oxidizers directly into the contaminated water to destroy the contaminants. It can also be used to remediate a variety of organic compounds.

[0040] "Ozonolysis" is a reaction in which an alkene or alkyne cleaves with ozone to form organic compounds. The multiple carbon-carbon bonds in the resulting organic compounds are replaced by double bonds to oxygen.

[0041] As used herein, a "plant" is an ensemble of physical equipment in which chemical or energy products are processed or transported. In its broadest sense, the term plant is applied to any equipment that may be used to produce energy or form a chemical product. Examples of facilities include polymerization plants, carbon black plants, natural gas plants, and power plants.

[0042] "Reverse osmosis" is a process by which a solvent such as water is purified of solutes by being forced through a semipermeable membrane through which the solvent, but not the solutes, may pass. In many cases, reverse osmosis is

initiated by the application of pressure to the solution, which forces the solvent to pass through the semipermeable membrane.

[0043] A "thickening agent," or "thickener," is a substance that increases the viscosity of a liquid/solid mixture without substantially modifying its other properties.

5 A thickening agent may also be referred to as a "gelling agent" or a "solidifier." The thickening agent may result in the formation of a gel-like material that can be removed from the surface of a liquid by skimming, or through the use of suction devices or nets.

[0044] Overview

10 [0045] Embodiments described herein provide a system and methods for removing carbon nanotubes from a water stream. The water stream may be waste water from a process for creating the carbon nanotubes. The carbon nanotubes may be removed from the water stream in order to obtain a purified water stream. In addition, in some embodiments, a carbon nanotube product may be obtained from
15 the carbon nanotubes. It can be noted that the techniques described herein are not limited to carbon nanotubes (CNTs). Other carbon allotropes, such as carbon nanofibers, carbon black, and the like, may be removed from water streams using the current techniques.

20 [0046] In various embodiments, the CNTs may be removed by the formation of a carbon oxide from the CNTs within a purification vessel. The carbon oxide may be, for example, carbon monoxide or carbon dioxide. The carbon oxide may be formed as a result of an interaction between the CNTs and, for example, an oxidizing agent, or ozone. The carbon oxide may also be formed by the incineration of the CNTs. In
25 some embodiments, the CNTs may be removed from the water stream through an air sparging process, which may or may not result in the production of carbon oxides.

[0047] Further, in some embodiments, the CNTs may be removed from the water stream through an interaction with any of a number of different types of chemical substances. For example, a flocculant may be injected into the water stream and
30 used to effect the removal of the CNTs by causing the contaminants to agglomerate.

A thickening agent may be injected into the water stream and used to effect the removal of the CNTs by causing the contaminants to float to the surface of the water stream.

[0048] In some embodiments, a reverse osmosis process may be used to remove the CNTs from the water stream. In the reverse osmosis process, pure water within the water stream can be forced through a semipermeable membrane due to an application of pressure, removing the CNTs from the water stream. A settling process may also be used to remove the CNTs from the water stream within, for example, a tank, or settling pond. Further, in some embodiments, techniques based on centripetal force may be used to effect the separation, such as a hydrocyclone, a multihydrocyclone, or a centrifuge.

[0049] According to embodiments described herein, the CNTs may be removed from the water stream according to any type of suitable separation process. In addition, any number of the techniques described above may be used in conjunction with one another to increase the degree of purification of the water stream.

[0050] Embodiments described herein provide a system and methods for purifying a waste water stream formed while making carbon fibers, carbon nanofibers, and CNTs (CNTs) on an industrial scale. The process is conducted under high temperature and pressure conditions using a Bosch reaction or a Bosch-like reverse degasification reaction, as discussed with respect to **Fig. 2**.

[0051] The process may be slightly exothermic, energy neutral, or slightly endothermic. Accordingly, at least a portion of the heat from the reaction can be recovered and used to heat the feed gases, providing a portion of the heat used by the process during continuous operations. As a high pressure process is used, an ambient temperature heat exchanger is sufficient for the removal of water vapor from the product stream, without using cryogenic coolers. While the process upstream may have separation devices such as cyclones or filters, for example, the condensation of the water vapor may result in some contamination of the water stream with residual CNTs.

[0052] As used herein, an ambient temperature heat exchanger can include water chillers, air coolers, or any other cooling system that exchanges heat with a source that is at substantially ambient temperature. It can be understood that ambient temperature is substantially the temperature of the outside air at the location of the facility, e.g., ranging from about -40 °C to about +40 °C, depending on the location of the facility. Further, different types of ambient temperature heat exchangers may be used depending on current ambient temperature. For example, a facility that uses water chillers in a summer season may use air coolers in a winter season. It can be understood that an appropriate type of heat exchanger may be used at any point herein that describes the use of an ambient temperature heat exchanger. The ambient temperature heat exchangers may vary in type across the plant depending on the amount of cooling needed.

[0053] In some embodiments described, industrial quantities of carbon products such as fullerenes, CNTs, carbon nanofibers, carbon fibers, graphite, carbon black, and graphene, among others, can be produced using carbon oxides as the primary carbon source. The balance of the possible products may be adjusted by the conditions used for the reaction, including catalyst compositions, temperatures, pressures, feedstocks, and the like. In a reactor system, the carbon oxides are catalytically converted to solid carbon and water. The carbon oxides may be obtained from numerous sources, including the atmosphere, combustion gases, process off-gases, well gases, and other natural and industrial sources.

[0054] The present process can use various feedstocks, including for example, a carbon oxide, e.g., carbon dioxide (CO₂) or carbon monoxide (CO), and a reducing agent, e.g., methane (CH₄) or other hydrocarbons, hydrogen (H₂), or any combinations thereof. The reducing agent may include other hydrocarbon gases, hydrogen (H₂), or mixtures thereof. A hydrocarbon gas can act as both an additional carbon source and as the reducing agent for the carbon oxides. Other gases, such as syngas, may be created as intermediate compounds in the process or may be contained in the feed. These gases can also be used as the reducing agent. Syngas, or "synthetic gas," includes carbon monoxide (CO) and hydrogen (H₂) and,

thus, includes both the carbon oxide and the reducing gas in a single mixture.

Syngas may be used as all or a portion of the feed gas.

[0055] Carbon oxides, particularly carbon dioxide, are abundant gases that may be extracted from exhaust gases, low-BTU well gas, and from some process off-gases. Although carbon dioxide may also be extracted from the air, other sources often have much higher concentrations and are more economical sources from which to harvest the carbon dioxide. Further, carbon dioxide is available as a by-product of power generation. The use of CO₂ from these sources may lower the emission of carbon dioxide by converting a portion of the CO₂ into carbon products.

[0056] The systems described herein may be incorporated into power production and industrial processes for the sequestration of carbon oxides, allowing their conversion to solid carbon products. For example, the carbon oxides generated in combustion or process off-gases may be separated and concentrated to become a feedstock for this process. In some cases, these methods may be incorporated directly into the process flow without separation and concentration, for example as an intermediate step in a multi-stage gas turbine power station. In other embodiments, the systems may be incorporated into waste processing systems used to form CNTs from carbonaceous feedstocks.

[0057] As used herein, an industrial scale process may provide large quantities of carbon allotropes in short periods of time. For example, the techniques used herein may provide carbon allotropes in quantities greater than about 0.5 Kg / hr, greater than about 1 Kg / hr, greater than about 2 Kg / hr, greater than about 5 Kg / hr, greater than about 10 Kg / hr, greater than about 100 Kg / hr, or greater than 1000 Kg / hr. The amounts produced depend on the scale of the equipment and the catalysts chosen.

[0058] **Fig. 1** is a block diagram of a reaction system **100** that generates carbon structures, for example, as a by-product of a carbon dioxide sequestration reaction. The reaction system **100** is provided a feed gas **102**, which can be a mixture of CO₂ and CH₄. In some embodiments, the reaction may allow for sequestration of CO₂ from exhaust streams of power plants and the like. In other embodiments, the CH₄ is

at a higher concentration, for example, in a gas stream from a natural gas field. Other components may be present in the feed gas **102**, such as C_2H_6 , C_2H_4 , and the like. In one embodiment, the feed gas **102** has been treated to remove these components, for example, for sale as product streams.

5 **[0059]** The feed gas **102** is passed through a heat exchanger **104** to be heated for reaction. During continuous operation, a portion of the heating is provided using heat **106** recovered from the reaction. The remaining heat for the reaction may be provided by an auxiliary heater, as described below. During start-up, the auxiliary heater is used to provide the total heat to bring the feed to the appropriate reaction
10 temperature, e.g., about 500 °C (about 930 °F). In one embodiment, the feed is heated to between about 500 °C (about 932 °F) to about 550 °C (about 1022 °F). In another embodiment, the feed is heated to between about 700 °C (about 1292 °F) to about 750 °C (about 1382 °F). In another embodiment, the feed is heated to between about 800 °C (about 1472 °F) to about 850 °C (about 1562 °F). The heated
15 feed gas **108** is fed to a reactor **110**.

[0060] In the reactor **110**, a catalyst reacts with a portion of the heated feed gas **108** to form CNTs **112** using the Bosch reaction. As described in more detail below, the reactor **110** can be a fluidized bed reactor that uses any number of different catalysts, including, for example, metal shot, supported catalysts, and the like. The
20 CNTs **112** are separated from the flow stream **114** out of the reactor **110**, leaving a waste gas stream **116** containing excess reagents and water vapor. At least a portion of the heat from the flow stream **114** is used to form the heated feed gas **108** prior to the flow stream **114** entering the chiller as the waste gas stream **116**.

[0061] The waste gas stream **116** is passed through an ambient temperature heat
25 exchanger, such as water chiller **118**, which condenses out some amount of the water **120** within the waste gas stream **116**. The partially dried waste gas stream **122** may then be passed to a water separation system **124**, which may separate most of the remaining water **120** from the partially dried waste gas stream **122**. The resulting dry waste gas stream **126** is used as a feed stream for a gas fractionation
30 system **128**. It can be understood that a dry waste gas stream, as used herein, has

the bulk of the water removed, but may still have small amounts of water vapor. For example, the dew point of a dry waste gas stream may be greater than about -5 °C, greater than about 0 °C, greater than about 5 °C, greater than about 10 °C, greater than about 20 °C, or higher. A dryer may be used to lower the dewpoint, for example, to about -50 °C, about -70 °C, or lower, prior to gas fractionation.

[0062] The water **120** that is condensed and removed from the waste gas stream **116** and the partially dried waste gas stream **122** may contain CNTs that have were not removed in the separation process. Accordingly, the water **120** can be fed into a water purification system **130**. The water purification system **130** may be configured to generate a purified water stream **132** by removing CNTs and other impurities from the water **120**.

[0063] The water purification system **130** may include any of a number of devices that are configured to effect the separation of the CNTs from the purified water stream **132**. In some embodiments, the water purification system **130** is configured to form a carbon oxide from the CNTs within the water **120**. This may be accomplished by, for example, the incineration of the water **120**, the mixing of the water **120** with ozone, or the mixing of the water **120** with an oxidizing agent. Some portion of the steam from an incineration process may then be condensed within a heat exchanger to form the purified water stream **132**. An underwater burner or a flame degradation vessel, among others, may be used to incinerate the CNTs in the water **120**.

[0064] Further, in some embodiments, the separation of the CNTs from the water **120** may be effected within an air sparge. An injection of air into the water **120** within the air sparge may cause the CNTs to float to the surface of the water **120** in a froth phase, and the CNTs may then be drained from the water **120** over the top of a weir.

[0065] In some embodiments, the CNTs may be separated from the water **120** through a reverse osmosis process, in which the purified water stream **132** is forced to pass through a semipermeable membrane that is impermeable to the CNTs. The purified water stream **132** may also be generated using centripetal force to separate CNTs, for example, in a hydrocyclone, in a multihydrocyclone, or in a centrifuge. In

addition, molecular sieves or a zeolite bed may be used to remove the CNTs from the water **120**.

[0066] In some embodiments, the water separation and purification process may be accomplished within the water chiller **118**. For example, a flocculant, an oxidizing agent, a thickening agent, ozone, or any number of other chemical substances may be used to effect the separation of the CNTs within the water chiller **118**.

[0067] In some embodiments, the gas fractionation system **128** removes a portion of the reagent having the lower concentration in the feed gas **102** and recycles it to the process, for example, by blending a recycle stream **134** with the feed gas **102**.

The higher concentration gas in the feed gas **102** can be disposed of as excess feed **136**, for example, by sales to downstream users. As an example, if CO₂ is the highest concentration gas in a blend with CH₄, the gas fractionation system **128** can be used to remove CH₄ remaining in the waste gas stream, and send it back into the process as the recycle stream **134**. The process functions as an equilibrium reaction between the reagents and solid carbon, as discussed further with respect to **Fig. 2**.

The gas fractionation system **128** may not be utilized when the CH₄ is in excess, as much of the CO₂ may be consumed in the reaction. Thus, the excess feed **136** that contains the CH₄, and which may also contain H₂, CO, and other gases, may be used to generate power in a power plant, or may be used as fuel for another purpose, without further purification or gas separation.

[0068] **Fig. 2** is an equilibrium diagram that identifies conditions under which a solid carbon product will form. This diagram is a triangular diagram **200** with the elements, C **202**, H **204**, and O **206**, at the apexes of the triangle. As one moves from any location towards an apex the molar ratio of the element, C **202**, H **204**, and O **206**, increases. In this way all of the possible compositions of the three elements can be mapped onto the triangular diagram **200**.

[0069] Any chemical compound, or mixture, with any two or all these three elements can be mapped onto the triangular diagram **200** as indicated by the exemplary points marked. Some of the chemical compounds include hydrocarbons such as alkanes, alkenes, and alkynes, as well as many other types of

hydrocarbons. The hydrocarbons are located on the C-H edge **208** connecting C **202** and H **204**. Chemical compounds that include only the elements C **202** and O **206**, including carbon monoxide (CO) and carbon dioxide (CO₂), occur along the C-O edge **210** connecting C **202** and O **206**. Chemical compounds that include only the elements H **204** and O **206**, such as water (H₂O), occur along the H-O edge **212** connecting H **204** and O **206**.

[0070] In the central region of the triangular diagram **200** are chemical compounds and mixtures that have all three elements, C **202**, H **204**, and O **206**. For example, these chemical compounds may include a very large number of individual components, such as alcohols, aldehydes, ethers, and materials with more complex structures, such as carbohydrates. Further, mixtures of compounds such as hydrogen, carbon oxides, and hydrocarbons may also be present.

[0071] Some of the first experiments to form fullerenes, C₆₀ and C₇₀, as well as carbon nanotubes (CNTs) were performed by laser ablation of a carbon electrode, capturing the carbon material in a mass spectrometer. The curves **214** shown in **Fig. 2** show the limit of carbon production at various temperatures. These curves **214** were determined by performing a stoichiometrically constrained Gibbs minimization, which minimizes the Gibbs free energy of the resulting compounds based on the constraint that the amount of carbon, oxygen, and hydrogen are to be the same both before and after the reaction. The point where solid carbon formation occurs for the first time was noted as the composition was moved from a first composition point to a second composition point on the triangular diagram **200**.

[0072] In thermodynamic terms, the curves **214** identify the points where the activity of carbon is about 1.0. Above a carbon activity of about 1.0, solid carbon forms in the center region, while below the carbon activity of about 1.0, no solid carbon forms. The triangular diagram **200** is useful for identifying the conditions where carbon allotropes, such as carbon nanotubes (CNTs) can possibly be produced, as well as determining compounds and mixtures that can be used for their production.

[0073] At the temperatures indicated in **Fig. 2**, most hydrocarbons, and other organic compounds, undergo thermal decomposition to produce small, thermodynamically stable, gas molecules, such as CO, CO₂, CH₄, H₂O, H₂, and the like. Under certain reaction conditions, these small gas molecules can react to produce carbon allotropes. In some cases, the carbon allotropes will be in the form of CNTs. Both single walled and multi-walled CNTs of various dimensions and chiralities can be made in these ways.

[0074] Reaction Pathways for the Formation of Carbon Allotropes


[0075] Hydrocarbons undergo thermal decomposition in two ways, depending upon the concentration of oxygen. Without oxygen being present, large hydrocarbon molecules will thermally decompose into smaller hydrocarbons, such as methane, ethane, propane, and hydrogen. These small hydrocarbons will further decompose to carbon and more hydrogen, giving an overall reaction as shown in Rxn. 1. This reaction, termed a pyrolysis reaction, occurs along the C-H edge **208**.



A representative case is the thermal decomposition of methane, shown in Rxn. 2.




[0076] In the presence of a low amount of oxygen, hydrocarbons will react to form carbon monoxide and carbon dioxide and water as well as carbon allotropes and hydrogen according to the reaction shown in Rxn. 3. This reaction is termed the Bosch reaction, and occurs in the center region of the triangular diagram **200**.



The ratio of CO to H₂O after reaction may differ depending upon the temperature of the system. Further, depending upon the amount of oxygen in the system, there may be some carbon dioxide in the product gases. Any carbon monoxide or carbon dioxide produced may react to form carbon allotropes at the high temperature conditions. Higher concentrations of O₂ typically results in higher temperatures, due to combustion, resulting in the production of more CO and CO₂ and less solid carbon

and hydrogen. Thus, the reaction system must restrict the amount of oxygen present in the system in order to produce larger amounts of carbon allotropes.

[0077] Organic compounds that include small amounts of oxygen may also be useful in the production of carbon allotropes. These compounds thermally
 5 decompose to form small, thermodynamically stable, gas molecules which can further react on a catalyst surface to produce carbon allotropes and water according to the overall reaction shown in Rxn. 4, which is another example of the Bosch reaction.



10 [0078] Any carbon monoxide or carbon dioxide produced has a tendency to react to carbon at these high-temperature conditions, adding to the overall productivity. These reactions form the simplest embodiments of the Bosch reaction, shown in Rxn. 5.



15 The Bosch reaction can be mechanistically written as two separate reactions in which CO is produced as an intermediate, as shown in Rxns. 6 and 7.




The first, Rxn. 6, is fast and tends toward equilibrium. The second, Rxn. 7, is slow.

20 Another reaction that can produce carbon allotropes is the Boudouard reaction that is shown in Rxn. 8. The Boudouard reaction takes place on the C-O edge **210**, and produces carbon allotropes and carbon dioxide from carbon monoxide.



[0079] In addition to forming small molecules directly in the reactor, a number of
 25 other approaches may be used to provide the reactants to form the carbon allotropes. For example, steam reforming of hydrocarbons and other organic

chemicals may be used. In these reactions, shown in Rxns. 9 and 10, a mixture of CO and hydrogen, called syngas, is formed.



5 At the reaction temperatures shown in the triangular diagram **200**, the syngas forms carbon allotropes via the second step of the Bosch reaction mechanism, shown in Rxn. 7.

[0080] As is apparent in the reactions shown above, there is a multitude of starting points for the production of carbon allotropes, such as CNTs. However, the reactions can be simplified by focusing on the conversion of the feedstock compounds into a mixture of small, thermodynamically stable, gases. These gases can then react to form carbon allotropes in the presence of a catalyst. This simplification can be performed by noting that a given hydrocarbon reacting with oxygen or with steam will be converted to carbon monoxide, carbon dioxide, water vapor, and hydrogen. Similarly, a given oxygenate reacting with itself, or with oxygen or steam, will also be converted to carbon monoxide, carbon dioxide, water vapor, and hydrogen. The ultimate mixture of small thermodynamically stable gases can be determined by performing equilibrium calculations on the reactions described above.

20 [0081] The gas mixture can then be converted to carbon allotropes in the Boudouard Reaction shown in Rxn. 8, step two of the Bosch reaction shown in Rxn. 7, the methane pyrolysis reaction shown in Rxn. 2, or some combinations of these. As all of these reactions produce carbon allotropes, they may be used to predict the carbon activity as a function of the composition of carbon monoxide, carbon dioxide, hydrogen, water vapor, methane, or the like, which are produced by some previous thermal decomposition reaction.

[0082] Oxidation Poisoning of Metal Catalysts

[0083] Another aspect of the catalytic reaction to produce carbon allotropes is that certain gas compositions and temperatures will oxidize the metal catalyst used in the reaction, rendering it ineffective for further catalytic reaction, as shown in

5 Rxn. 11. The point where oxygen causes a metal or alloy to oxidize depends upon its properties. For elemental metals, this is determined by the Gibbs free energy of formation of the oxide.



[0084] If a catalyst includes iron, there are various oxides that may be formed.

10 The most common include Wüstite (FeO), magnetite (Fe₃O₄), and hematite (Fe₂O₃). Wüstite is thermodynamically favored at the temperatures and pressures shown in **Fig. 2** and forms by the reaction shown in Rxn. 12.



An equilibrium constant, K_{FeO} , for Rxn 12 can be determined by the formula shown in


15 Eqn. 4.

$$K_{FeO} = \exp [-\Delta G_{FeO}/(R_g T)] = [P_{O_2}/P_T]^{-1/2} \quad \text{Eqn. 4}$$

In Eqn. 4, ΔG_{FeO} is the Gibbs free energy of iron oxidation to Wüstite which is a function of temperature, R_g is the gas constant, T is the absolute temperature, P_{O_2} is the partial pressure of oxygen (O₂), and P_T is the total pressure of the system. The
20 ratio, P_{O_2}/P_T , is simply the mole fraction of O₂ in the system. Using this equation, the partial pressure of oxygen that will initiate the oxidation of iron at any temperature can be identified.

[0085] The partial pressure of oxygen can be obtained from one of the fast

25 reaction equilibria presented in Eqns. 5 and 6.



$$\text{CO}_2 \leftrightarrow \text{CO} + \frac{1}{2} \text{O}_2, \quad P_{\text{O}_2} = P_T \sqrt{K_{\text{CO}_2} \frac{Y_{\text{CO}_2}}{Y_{\text{CO}}}} \quad \text{Eqn. 6}$$

In these equilibria calculations, K_i is the equilibrium constant, a function of temperature, for the decomposition of gas i . As shown by Eqns. 5 and 6, the partial pressure of oxygen is controlled by either the mole fraction ratio of water vapor to hydrogen or the mole fraction ratio of carbon dioxide to carbon monoxide at a given temperature.

[0086] As shown in Eqns. 1-6, the mole fraction ratios are important in the determination of the partial pressure of oxygen and in the definition of carbon activity for the Boudouard and Bosch reaction mechanisms. For example, the mole fraction ratio sets both the carbon activity and the partial pressure of oxygen, so that there will be a given activity of carbon that will initiate the oxidation of the metal catalyst.

[0087] As the pyrolysis reactions are endothermic, their zone of influence is near the H **204** apex of the triangular diagram **200**, where the temperature lines curve, inverting the temperature sequence as the amount of carbon in the system

increases. As a result, a zone **216** near the C-H edge **208** may be delineated in the triangle near the H apex, where pyrolysis reactions dominate over Bosch reactions. As the transition point changes as the temperature of the system changes, two lines **218** and **220** can be used to indicate the edge of the zone **216**, depending on the temperature. The first line **218** delineates the zone **216** at about 1173.45 K (about 900 °C), while the second line **220** delineates the zone **216** at about 973.15 K (about 700 °C). The pyrolysis reactions dominate over the Bosch reactions in the zone between either of the lines **218** or **220** and the C-H edge **208**.

[0088] Further, from the Ac produced by both the Bosch second step and the Boudouard reactions, a zone near the C-O edge **210** can be identified at which there is an equal probability for the first solid carbon allotropes to be produced by either reaction, based on the thermodynamics. One edge of this zone can be delineated by a first line **222** in the triangle diagram **200**. Further, as discussed above, there is a point at which the second step of the Bosch reaction generates sufficient water to

cause the partial pressure of oxygen to be sufficiently high that the iron catalyst will oxidize to Wüstite. At this point **224** the first line **222** becomes dotted and a second line **226**, at a fixed hydrogen (H) content of about 0.14 for FeO, limits the Boudouard zone at about 1 atm system pressure. The Boudouard zone **228** dominates over the Bosch reaction at reaction conditions above and to the right of the first line **222** and to the right of the second line **222** (FeO oxidation).

[0089] Conclusion

[0090] The calculations discussed with respect to **Fig. 2** identify carbon activity as the driving force for the production of carbon allotropes, such as CNTs. Thus, various reaction mixtures in the C-H-O system can be reduced to a prediction of the carbon activity using three carbon forming reactions that are applicable on the C-H edge **208**, C-O edge **210**, and the central portion of the triangular diagram of the C-H-O system. Carbon activities larger than about 1.0 produces carbon by each of the three carbon forming reactions. In some cases the carbon activity is a predictor of the transformation of iron to Wüstite, FeO. In these cases, the carbon activity where iron oxidizes will limit the carbon activity range where carbon can form to values larger than about 1.0. In the case of the Bosch second step reaction with equimolar CO:H₂ feed at about 973.15 K (about 700 °C) the carbon activity is limited to values larger than about 35 for example.

[0091] Further, the calculations show clearly delineated zones where pyrolysis (zone **216**) and Boudouard reactions (zone **228**) dominate on the C-H edge **208** and C-O edge **210**, respectively, of the triangular diagram **200**. This also shows that experimental conditions in the central part of the triangular diagram of the C-H-O system define a Bosch reaction region **230** that provides the largest reactor conversion resulting in faster production and higher yields than reactions on the C-H edge **208** or C-O edge **210** of the triangular diagram **200**. In this region, the concentration of the carbon is set by the Ac, and is greater than about 10 %. Further, the oxygen content is greater than about 10 %, and the hydrogen concentration is greater than about 20 %.

[0092] Reactor Systems

[0093] **Fig. 3** is a schematic of a catalytic reaction **300** for the formation of CNTs on a catalyst particle **302**. An initial reaction **304** between a portion of the compounds in the hot gas feed stream **306**, for example, CH_4 and the CO_2 , results in the formation of CO and H_2 in stoichiometric amounts. Excess amounts of the source gases **306** continue to flow through the reactor, helping to fluidize the bed and carrying away CNTs **308** and catalyst particles **310**.

[0094] The reactions that form the CNTs **308** take place on the catalyst particle **302**. The size of the CNTs **308**, and the type of CNTs **308**, e.g., single wall or multiwall CNTs **308**, may be controlled by the size of the grains **312**. Without being limited by theory, a nucleus of iron atoms of sufficient size at the grain boundary may form the nucleating point for the growth of the carbon products on the catalyst particle **302**. Generally, smaller grains **312** will result in fewer layers in the CNTs **308**, and may be used to obtain single wall CNTs **308**. Other parameters may be used to affect the morphology of the final product as well, including reaction temperature, pressure, and feed gas flow rates.

[0095] The CO and H_2 can react at grain boundaries **314**, lifting active catalyst particles **316** off the catalyst particle **302**, and forming H_2O **318** and the solid carbon of the CNTs **308**. The CNTs **308** break off from the catalyst particle **302** and from the catalyst particle **1010**. Larger catalyst particles **310** can be captured and returned to the reactor, for example, by a catalyst separator discussed further with respect to **Fig. 4**, while very fine catalyst particles **310** will be carried out with the CNTs **308**. The final product will include about 70 mol % solid carbon and about 15 mol % metal, about 80 mol % solid carbon and about 10 mol % metal, about 90 mol % solid carbon and about 7 mol % metal, or about 95 mol % solid carbon and about 5 mol % metal. The CNTs **308** will often agglomerate to form clusters **320**, which are the common form of the final product. Some amount of the CO and H_2 passes through the reactor without reacting and are contaminants in the reactor effluent streams, e.g., causing degradation reactions in downstream equipment.

[0096] As the reaction proceeds, the catalyst particle **302** is degraded and finally consumed. Accordingly, the reaction may be described as a metal dusting reaction. In some embodiments, metal surfaces in the reactor and downstream equipment are protected from attack by a protective lining, e.g., a ceramic or gold lining, since the metal surfaces in contact with the reaction conditions would not only degrade, but
5 may also result in the formation of poorer quality products.

[0097] The catalyst particle **302** any number of metals from different IUPAC Groups on the periodic table, such as Group 10 (e.g., nickel), Group 8 (e.g., iron or ruthenium), Group 9 (e.g., cobalt), or Group 6 (e.g., chromium or molybdenum),
10 among others. Other metals that may be present include Group 7 metals (e.g., manganese), or Group 5 metals (e.g., cobalt), among others. It can be understood that the metals listed above are merely exemplary of the Groups mentioned and other metals from those Groups may be included. However, the catalytic sites on the catalyst particles **302** are principally composed of iron atoms. In one
15 embodiment, the catalyst particle **302** includes metal shot, for example, about 25-50 mesh metal beads that are used for shot blasting. In one embodiment, the catalyst may be a stainless ball bearing, and the like.

[0098] The H₂O **318** that is created according to the catalytic reaction **300** may be substantially mixed with the CNTs **308**, the catalyst particles **310**, and the clusters
20 **320**. According to embodiments described herein, the H₂O **318** may be separated from these impurities through a purification process. The purification process may be implemented within the reactor systems discussed further with respect to **Figs. 5** and **6**.

[0099] **Fig. 4** is a drawing of a fluidized bed reactor **400** for forming CNTs **402**. A hot gas feed stream **404** is fed through a line **406** into the bottom of the fluidized bed reactor **400**. A control valve **408** may be used to regulate the flow of the hot gas feed stream **404** into the fluidized bed reactor **400**. The hot gas feed stream **404** flows through a distributor plate **410** and will fluidize a bed of catalyst particles **412** held in place by the reactor walls **414**. As used herein, "fluidize" means that the
30 catalyst particles **412** will flow around each other to let gas bubbles through,

providing a fluid-like flow behavior. As discussed herein, the reaction conditions are very harsh to any exposed metal surface as the metal surface will act as a catalyst for the reaction. Thus, the reaction will result in the slow degradation of an exposed metal surface. Accordingly, the interior surface of the reactor, including the reactor walls **414** and heads **416**, as well as the distributor plate **410**, and other parts, can be made of a protective material such as ceramic or gold.

[0100] As the hot gas feed stream **404** flows through the fluidized bed of catalyst particles **412**, CNTs **402** will form from catalyst particles **412**. The flowing hot gas feed stream **404** carries the CNTs **402** into an overhead line **418** where they are removed from the reactor **400**. Depending on the flow rate, for example, as adjusted by the control valve **408**, some amount of catalyst particles **412**, or particles fragmented from the catalyst particles **412**, may be carried into the overhead line **418**. In addition, water formed in the process may be carried out of the fluidized bed reactor **400** into the overhead line **418**. This water can be condensed to form a

waste water stream, which may be contaminated with some portion of the CNTs **402**.

[0101] Reactor Systems

[0102] **Fig. 5** is a simplified process flow diagram of a one reactor system **500** for making CNTs from a gas feed that includes carbon dioxide and methane. As shown, the one reactor system **500** can be used for feed gas **502** that is higher in CO₂ or higher in CH₄. In the reaction system **500**, the feed gas **502** is combined with a recycle gas **504** that has an enhanced concentration of the lesser gas. The mixing can be performed using a static mixer **506**.

[0103] The combined gas stream **508** is passed through a heat exchanger **510** or set of heat exchangers **510** in series to be heated by a reactor effluent stream. The temperature can be raised from a near ambient temperature, as defined herein, to an appropriate reaction temperature, such as about 500 °C (930 °F), about 600 °C (about 1112 °F), about 700 °C (about 1292 °F), about 800 °C (about 1472 °F), or about 900 °C (about 1652 °F) for the heated gas stream **512**. This temperature may be sufficient for maintaining the reaction during continuous operations. However, part of the heat may be provided by a package heater **514**, which may be especially

useful for adding heat to bring the reactants up to temperature during start-up. The hot gas stream **516** is then introduced into a fluidized bed reactor **518**. A general fluidized bed reactor that may be used in embodiments is discussed above with respect to **Fig. 4**. In the fluidized bed reactor **518**, CNTs are formed on catalyst particles. The catalyst particles and reactions are discussed above with respect to **Fig. 3**.

[0104] The CNTs are carried from the fluidized bed reactor **518** in a reactor effluent stream **520**. The reactor effluent stream **520** may be at an elevated temperature, for example, about 600 °C (about 1112 °F), about 700 °C (about 1292 °F), about 800 °C (about 1472 °F), or about 900 °C (about 1652 °F), and may be cooled by exchanging heat with the combined gas stream **508**, for example, providing some or all of the heat used to heat the reactants. Either prior to or after cooling, the reactor effluent stream **520** is passed through a separation device **522**, such as a cyclonic separator, to remove the CNTs **524**. The resulting waste gas stream **526** can be used to provide heat to the combined gas stream **508** in the heat exchanger **510**. The carbon may also be removed in secondary separation devices (not shown) at lower temperatures than the waste gas stream **526**.

[0105] After providing heat to the combined gas stream **508**, the cooled waste stream **528** is passed through an ambient temperature heat exchanger **530** and then fed to a separation vessel **532**. Water **534** settles in the separation vessel **532** and is removed from the bottom. The water **534** may then be fed into a water purification system **536**. The water purification system **536** may produce a purified water stream **538**, as well as a waste stream **540**.

[0106] The water purification system **536** may be used to remove CNTs from the cooled waste stream **528** through a number of separation techniques. In various embodiments, the water purification system **536** may be configured to produce a carbon oxide from the CNTs within the water **534**. For example, an oxidation process may be used to form the carbon oxide from the CNTs within the water **534**. The carbon oxide may then be released as the waste stream **540**. An ozone stream

may also be mixed with the water **534** to effect the separation of the CNTs from the water **534**.

[0107] In some embodiments, an air sparging process may be used to effect a separation of the CNTs from the water **534**. A flocculant may be added to the water **534** within the water purification system **536** to effect a separation of the CNTs from the water **534**. Further, in some embodiments, a hydrocyclone, zeolite beds, molecular sieves, or a filter, such as a filter configured to perform a reverse osmosis process, may be used to remove the CNTs, as well as any other impurities included within the waste stream **540**, from the water **534**.

[0108] In some embodiments, flame degradation may be used to dispose of the CNTs. For example, an underwater burner may be used to produce an underwater flame for degrading the CNTs. As another example, an incineration process may be used to dispose of the water **534**. A heat exchanger may be used to recover at least a portion of the water **534** from the steam through a condensation process.

[0109] The resulting gas stream **542** from the separation vessel **532** may be significantly cooler, for example, at about 30 °C, about 38 °C (about 100 °F), about 40 °C and at a pressure of about 2500, kiloPascals (kPa), about 3000 kPa, about 3720 kPa (about 240 psia), or about 4000 kPa. In one embodiment, the gas is then dried to a low dew point in a drier (not shown). The stream enters a compressor **544** that increases the pressure of the gas stream **542** to about 5000 kPa, about 6000 kPa, about 7000 kPa, about 7,240 kPa (about 1050 psia), or about 8000 kPa, forming a high pressure stream **546** that is passed through another ambient temperature heat exchanger **548**. From the ambient temperature heat exchanger **548**, the high pressure stream **546** is fed to a separation vessel **550** for removal of any remaining water **534**, for example, if a drier has not been used. The water **534** may be combined with the water **534** from the separation vessel **532** and fed into the water purification system **536**.

[0110] In embodiments in which the CO₂ is in excess in the feed gas **502**, the dried gas stream **552** can be sent to a gas fractionation system **554**, which separates the excess feed **556** from the recycle gas **504**. In reaction systems **500** based on a

proportionate excess of CO₂, the excess feed **556** may primarily include CO₂, and the recycle gas **504** may primarily include CH₄. In reaction systems **500** based on a proportionate excess of CH₄, the excess feed **556** will not have a substantial CO₂ content, and a portion may be recycled without further purification, for example, replacing the gas fractionation system **554** with a manifold. In some embodiments, a portion of the excess feed **556**, the recycle gas **504**, or both may be used to provide a fuel gas stream, a purge gas stream, or both for use in the plant.

[0111] **Fig. 6** is a simplified process flow diagram of a one reactor system **600** for making CNTs from a gas feed that includes carbon dioxide and methane, in which the carbon dioxide is in excess. In **Fig. 6**, like numbered items are as described with respect to **Fig. 5**. As described with respect to **Fig. 5**, the feed gas **502** passes through a static mixer **506** where it is combined with a recycle gas **504**, which is high in methane. The combined gas stream **508** is passed through a heat exchanger **510**, for example, including multiple shell and tube heat exchangers **602**. The main difference between the more detailed process flow diagram of **Fig. 6** and that of **Fig. 5** is the use of heat exchangers to cool the reactor effluent stream **520** prior to separating the CNTs from the reactor effluent stream **520**.

[0112] In this embodiment, the heated gas stream **512** is raised to a temperature of about 300 °C, about 400 °C, about 427 °C (about 800 °F), or about 500 °C in the heat exchanger **510** prior to flowing through a second heat exchanger **604**. In the second heat exchanger **604**, the heated gas stream **512** flows through a first ceramic block heat exchanger **606**, as indicated by arrows **608**. Heat stored in the first ceramic block heat exchanger **606** is exchanged to the heated gas stream **512** and may increase the temperature to between about 500 °C (about 932 °F) and to about 550 °C (about 1022 °F). In another embodiment, the feed is heated to between about 700 °C (about 1292 °F) to about 750 °C (about 1382 °F). In another embodiment, the feed is heated to between about 800 °C (about 1472 °F) to about 850 °C (about 1562 °F).

[0113] While the first ceramic block heat exchanger **606** is used to heat the heated gas stream **512**, a second ceramic block heater **610** is used to cool the

reactor effluent stream **520** by flowing this stream through the second ceramic block heater **610**, as indicated by arrows **612**. When the second ceramic block heat exchanger **610** reaches a selected temperature, or the first ceramic block heat exchanger **606** drops to a selected temperature, the positions of the inlet valves **614** and outlet valves **616** are changed. In other words, open valves are closed and closed valves are opened. The change in the positions of the valves changes which ceramic block heat exchanger **606** or **610** is being heated by the flow from the reactor **518**, as well as which ceramic block heat exchanger **606** or **610** is used to heat the heated gas stream **512**.

[0114] The heat may not be sufficient to increase the temperature sufficiently for reaction. Thus, as described with respect to **Fig. 5**, a package heater **514** can be used to further boost the temperature of the heated gas stream **512**, forming the hot gas stream **516**, which can be fed to the fluidized bed reactor **518**. CNTs are formed in the fluidized bed reactor **518**, and carried out in the reactor effluent stream **520**.

[0115] After flowing through the second ceramic block heater **610**, the reactor effluent **520** is flowed to a separation system **618**, which is used to remove the CNTs from the reactor effluent **520**. In this embodiment, the separation system **618** for the CNTs includes a cyclonic separator **620**, a lock hopper **622**, and a filter **624**. After the majority of the CNTs are removed by the cyclonic separator **620** and deposited into the lock hopper **622**, the filter **624** is used to remove remaining CNTs from the waste gas stream **626**. This may help to prevent plugging, or other problems, caused by residual CNTs in the waste gas stream **626**. The filter **624** can include bag filters, sintered metal filters, and ceramic filters, among other types. From the separation system **618**, the CNTs may be directed to a packaging system. After the filter **624**, the waste gas stream **626** is flowed through the heat exchanger **510** before flowing to the ambient temperature heat exchanger **530** and then fed to a separation vessel **532** for separation of the water **534**. After flowing through the separation vessel **532**, the flow is as described with respect to **Fig. 5**.

[0116] In this embodiment, two extra streams may be provided from the separated streams out of the gas fractionation system **554**. A fuel gas stream **628**

may be taken from the recycle gas **504** and sent to a power plant. A purge gas stream **630** may be taken from the CO₂ outlet stream, which can be used to purge various pieces of equipment, such as the filter **624** or cyclone **620**.

[0117] Water Purification Systems

- 5 **[0118]** **Fig. 7** is a schematic of a water purification system **700** that is configured to separate the water **534** into the purified water stream **538** and the waste stream **540** through the addition of a flocculant **702**. Like numbered items are as described with respect to **Fig. 5**. The flocculant **702** may be an organic liquid hydrocarbon or any other material not miscible in water. The water **534** may include CNTs and other
- 10 impurities when it enters the water purification system **700**. The water **534** may be injected into the top of the water purification system **700** via a first sparge ring **704**. The flocculant **702** may be injected into the bottom of the water purification system via a second sparge ring **706**. The flocculant **702** may capture the CNTs and other organic material, for example, by agglomeration, flocculation, or dissolution, and
- 15 move the contaminants out of an aqueous phase **708** and into an organic phase **710**. The CNTs and other organic material may then exit the water purification system **700** as the waste stream **540** via an overhead line **712**. Pure water may sink to the bottom of the water purification system **700**, and may exit the water purification system **700** as the purified water stream **538**.
- 20 **[0119]** **Fig. 8** is a schematic of a water purification system **800** that is configured to separate the water **534** into the purified water stream **538** and the waste stream **540** through an air sparging process, or any number of other gas injection processes, including, for example, an ozonolysis process. Like numbered items are as described with respect to **Fig. 5**. The water **534** may be injected into the top of
- 25 the water purification system **800** via an overhead line **802**, as shown in **Fig. 8**, or may injected into the side of the water purification system **800**. The rate of injection of the water **534** may be controlled using a valve **804**, which may be opened, partially opened, or closed, depending on the fluid level within the water purification system **800** as measured by a fluid level sensor **806**. In some embodiments, the
- 30 fluid level sensor **806** may be a differential pressure sensor.

[0120] A gas stream **808** may be injected into the bottom of the purification system **800** through a sparge ring **810**, which may contain pores **812**, or holes, through which the gas stream **808** may pass, forming bubbles. In the case of an air sparging process, the gas stream **808** can be an air stream, an argon stream, or a nitrogen stream, among others. In the case of an ozonolysis process, the gas stream **808** includes ozone.

[0121] As the bubbles from the gas stream **808** rise through the purification system **800**, the gas stream **808**, e.g., the air stream or the ozone stream, may mix with the water **534**, resulting in the formation of a mixture **814**. This may cause a chemical or physical reaction in which impurities within the water **534** separate from the purified water stream **538**, forming the waste stream **540**. For example, the bubbles can carry small particles, such as CNTs, to the surface.

[0122] In various embodiments, as the gas stream **808** mixes with the water **534**, the waste stream **540** is generated in the form of a froth **816**, which floats to a surface **818** of the mixed stream **814**. This may result in the separation of the mixed stream **814** within the purification system **800** into two separate layers, i.e. the purified water stream **538** and the waste stream **540**.

[0123] In various embodiments, the froth **816** may be removed from the purification system **800** by skimming the froth **816** from the surface over a weir **820** and into a tank **822**. The tank **822** may be physically attached to the purification system **800**. Once the froth **816** enters the tank **822**, the froth **816** may be removed from the tank as the waste stream **540**, as shown in **Fig. 8**. In some embodiments, the waste stream **540** may then be flowed into any of a number of separation devices, such as a dryer, filter, centrifuge, or flocculation tank, among others. Thus, remaining CNTs may be recovered from the waste stream **540**. In addition, residual water within the waste stream **540** may be recovered through a secondary water purification process.

[0124] In addition, as the mixed stream **814** is generated within the purification system **800**, a waste gas stream **824** is generated. The waste gas stream **824** may include sparged gas, such as air, nitrogen, argon, or ozone, among others, that was

injected into the purification system **800** as the gas stream **808**, as well as other light ends degassed from the water. In various embodiments, the waste gas stream **824** may be a carbon oxide, such as carbon monoxide or carbon dioxide. The waste gas stream **824** may be removed from the purification system **800** through an overhead line **826**. In some embodiments, the waste gas stream **824** may be recycled and reused within the purification system **800**, or may be flowed to a separation system for the recovery of any valuable gaseous components from the waste gas stream **824**, for example, for recycling into the CNT production process.

[0125] The purified water stream **538** may be removed from the purification system **800** through a line **828**. In addition, a valve **830** may be used to control the rate of removal of the purified water stream **538**. The valve **830** may be opened, partially opened, or closed, depending on the fluid level within the water purification system **800** as measured by the fluid level sensor **806**.

[0126] Fig. 9 is a schematic of a water purification system **900** that is configured to separate the water **534** into the purified water stream **538** and the waste stream **540** through an oxidation process. Like numbered items are as described with respect to Fig. 5. The water **534** may be flowed into the purification system **900** through an overhead line **902**. In addition, an oxygen stream **904** may be flowed into the bottom of the purification system **900** through a sparge ring **906**. The sparge ring **906** may contain pores **908**, or holes, through which the oxygen stream **904** may pass.

[0127] As the oxygen stream **904** rises through the purification system **900**, it mixes with the water **534**, resulting in the formation of a mixed stream **910**. In addition, a gas stream, i.e., the waste stream **540**, may be generated. The waste stream **540** may include carbon oxides produced during the oxidation process.

[0128] As the waste stream **540** separates from the mixed stream **910**, it may rise through the purification system **900** and exit through an overhead line **912**. In some embodiments, the waste stream **540** may be flowed into a separation system, in which carbon products, such as any residual CNTs, may be recovered. In addition, water vapor contained within the waste stream **540** may be condensed to recover

additional water. The additional water may then be combined with the purified water stream **538**. In some embodiments, the purified water stream **538** may be flowed to additional purification systems. For example, the purified water stream **538** may be flowed through a hydrocyclone, a filter, or an incinerator, among others.

5 **[0129]** Further, in some embodiments, the oxygen stream **904** is an ozone stream. In such embodiments, the water **534** is separated into the purified water stream **538** and the waste stream **540** through an ozonolysis process. In addition, the waste stream **540** may include carbon oxides produced during the ozonolysis process.

10 **[0130]** **Fig. 10** is a schematic of a water purification system **1000** that is configured to separate the water **534** into the purified water stream **538** and the waste stream **540** through a reverse osmosis process. Like numbered items are as described with respect to **Fig. 5**. The water **534** may be flowed into the purification system **1000** through a line **1002**. In some embodiments, the line **1002** includes a
15 pump **1004** that is used to increase the pressure within the purification system **1000**.

20 **[0131]** The purification system **1000** includes a semipermeable membrane **1006**, which allows molecules in a certain size and polarity range to pass through, while blocking salts, larger molecules, and particulates. In various embodiments, the semipermeable membrane **1006** is permeable to water but impermeable to CNTs and other residual impurities contained within the water **534**. Thus, the purified water stream **538** may separate from the waste stream **540** by passing through the semipermeable membrane **1006**.

25 **[0132]** The purified water stream **538** may then be flowed out of the purification system **1000** through an overhead line **1008**, while the waste stream **540** may be flowed out of the bottom of the purification system **1000** through a line **1010**. In some embodiments, the waste stream **540** may be flowed to further separation systems, which may recover CNTs and any other components from the waste stream **540**.

30 **[0133]** **Fig. 11** is a schematic of a flame degradation vessel **1100** that may be used to remove CNTs from the water **534** through the formation of steam **1102**. Like

numbered items are as described with respect to **Fig. 5**. The flame degradation vessel **1100**, or incinerator, may be utilized for the recovery of the purified water stream **538** in the form of steam **1102**. The flame degradation vessel **1100** may be used for cases in which the full recovery of the purified water stream **540** is not
5 desired.

[0134] The water **534** may be injected into the top of the flame degradation vessel **1100** through a number of water sprayers **1104**. A combustion air inlet **1106** located below the water sprayers **1104** may be configured to inject an oxidizing agent **1108**, such as air or enriched air, into the flame degradation vessel **1100**. The oxidizing
10 agent **1108** may mix with the water **534** as it passes through the flame degradation vessel **1100**.

[0135] Burners **1110** may be located below the combustion air inlet **1106** on each side of the flame degradation vessel **1100**. The burners **1110** may be configured to inject a fuel **1112**, such as oil or natural gas, into the flame degradation vessel **1100**.
15 The fuel **1112** may mix with the oxidizing agent **1108** and the water **534**, resulting in the combustion of the oxidizable impurities in the water **534**.

[0136] As a result of the combustion reaction, the CNTs and other impurities within the water **534** may be reduced to ash **1114** or carbon oxides. The ash **1114** may be removed from the flame degradation vessel **1100** through an exit portal
20 **1116**. In addition, the water **534** and any carbon oxides, including those formed by combusting the fuel, may be removed from the flame degradation vessel **1100** in the form of the steam **1102**. In some embodiments, some portion of the purified water stream **538** may be recovered from the steam **1102** through a condensation process. This may be accomplished using, for example, a heat exchanger or chiller, among
25 others.

[0137] **Fig. 12** is a schematic of a hydrocyclone **1200** that may be used to separate the water **534** into the purified water stream **538** and the waste stream **540**. Like numbered items are as described with respect to **Fig. 5**. The hydrocyclone **1200** may include a single hydrocyclone, as shown in **Fig. 9**, or multiple
30 hydrocyclones.

[0138] The water **534** may be injected into the hydrocyclone **1200** through a line **1202** located near the top of the hydrocyclone **1200**. As water **534** enters the hydrocyclone **1200**, a swirl element within the hydrocyclone **1200** may impart a radial acceleration and a tangential velocity component to the water **534** through the rotation of twisted swirl vanes. The swirl vanes may be arranged parallel or in series on the swirl element. The swirling of the water **534** may cause the waste stream **540**, which contains CNTs and other impurities that are heavier and denser than the other particles within the water **534**, to migrate to the outer rim of the hydrocyclone **1200** and begin traveling in a wide circular path, while the water molecules may migrate towards the center of the hydrocyclone **1200** and begin traveling in a narrow circular path. As the water **534** nears the end of the hydrocyclone **1200**, the water molecules may be captured and sent out of the hydrocyclone **1200** as the purified water stream **538** via an overhead line **1204**. The waste stream **540** may also be sent out of the bottom of the hydrocyclone **1200** via a line **1206**.

[0139] Method

[0140] **Fig. 13** is a process flow diagram showing a method **1300** for generating CNTs from a feed gas that includes methane and carbon dioxide. The method **1300** begins at block **1302**, at which a mixed CO_2 / CH_4 feedstock is obtained. The feedstock may be obtained from any number of sources. As mentioned, the feedstock may include a natural gas harvested from a sub-surface reservoir, an exhaust gas from a power generation plant, or any number of other gases from natural or plant sources. Further, other feedstocks may be used in embodiments, including other materials, such as syngas, CO , H_2 , other hydrocarbons, and the like.

[0141] At block **1304**, the feedstock is combined with a recycle gas obtained from the wastes gases generated in the process. As described herein, the recycle gas may be obtained from the waste gases by cryogenic gas fractionation, as well as any number of other techniques. At block **1306**, the combined gas stream is heated with waste heat recovered from the reaction process. After heating, at block **1308**, the combined gas stream is reacted with a metal catalyst in a reactor to form the CNTs.

At block **1310**, the CNTs are separated from the waste gas. At block **1312**, the separated CNTs are purged, cooled, and packaged to be sent to market.

[0142] At block **1314**, the waste gas is cooled to remove excess water formed during the reaction. As the process is conducted at high temperatures and pressures, an ambient temperature heat exchanger provides sufficient cooling to
5 condense out the water vapor. The processes described at blocks **1306-1314** will be repeated for each sequential reactor in the reaction system.

[0143] At block **1316**, the excess water that was removed from the waste gas may be purified. The purification of the water may be accomplished using any of a
10 number of purification systems, such as those discussed with respect to **Figs. 7-12**. For example, one method by which the water may be purified is discussed below with respect to **Fig. 14**.

[0144] At block **1318**, the waste gas may be fractionated into a CO₂ enriched stream and a CH₄ enriched stream. If a low CO₂ feedstock was used, the excess
15 reagents may be recycled without further processing. At block **1320**, whichever stream contains the excess reagent can be sold, while the other stream can be recycled to block **1304** to be used in the process.

[0145] **Fig. 13** is not intended to indicate that the steps of the method **1300** are to be executed in any particular order, or that all of the steps of the method **1300** are to
20 be included in every case. Further, any number of additional steps may be included within the method **1300**, depending on the specific application.

[0146] **Fig. 14** is a process flow diagram showing a method **1400** for the removal of CNTs from a water stream. The method begins at block **1402** with the flowing of a water stream into a purification vessel. The water stream may include water that is
25 contaminated with residual CNTs. The purification vessel may be a water purification system that is configured to remove or degrade the residual CNTs in the water within the water stream. In some embodiments, the water stream may be flowed into the purification vessel from a separation vessel, as discussed above.

[0147] At block **1404**, a chemical substance may be injected into the purification
30 vessel. The chemical substance may be, for example, air, a flocculant, or ozone.

[0148] At block **1406**, a separation of the CNTs from the water stream may be effected through an interaction of the chemical substance with the CNTs within the purification vessel. In some embodiments, if the chemical substance is air, effecting the separation of the CNTs from the water stream includes effecting a removal of the CNTs through an air sparging process. In other embodiments, if the chemical substance is a flocculant, effecting the separation of the CNTs from the water stream includes removing the CNTs through an interaction of the flocculant with the CNTs within the sparge vessel. Further, in other embodiments, if the chemical substance is ozone, effecting the separation of the CNTs from the water stream includes removing the CNTs from the water stream through an ozonolysis process. In addition, the CNTs may be removed from a sparge vessel by flowing the CNTs over a weir and into a collection vessel.

[0149] **Fig. 14** is not intended to indicate that the steps of the method **1400** are to be executed in any particular order, or that all of the steps of the method **1400** are to be included in every case. Further, any number of additional steps may be included within the method **1400**, depending on the specific application.

[0150] Embodiments

[0151] Embodiments of the invention may include any combinations of the methods and systems shown in the following numbered paragraphs. This is not to be considered a complete listing of all possible embodiments, as any number of variations can be envisioned from the description above.

1. A method for removing carbon nanotubes from a water stream, including flowing the water stream into a purification vessel, wherein the purification vessel is configured to form a carbon oxide from the carbon nanotubes within the water stream.

2. The method of paragraph 1, including using an air sparging process to form the carbon oxide from the carbon nanotubes within the water stream.

3. The method of any of paragraphs 1 or 2, including adding a flocculant to the water stream to effect a separation of the carbon nanotubes from the water stream.

4. The method of any of paragraphs 1-3, including mixing an ozone stream with the water stream to effect a separation of the carbon nanotubes from the water stream.

5 5. The method of any of paragraphs 1-4, including using a hydrocyclone to remove the carbon nanotubes from the water stream.

6. The method of any of paragraphs 1-5, including filtering the carbon nanotubes out of the water stream through a reverse osmosis process.

10 7. The method of any of paragraphs 1-6, including forming the carbon oxide from the carbon nanotubes within the water stream through an oxidation process.

8. The method of any of paragraphs 1-7, including using an underwater burner to produce an underwater flame for degrading the carbon nanotubes.

15 9. The method of any of paragraphs 1-8, including using a flame degradation vessel to remove the carbon nanotubes from the water stream through a formation of steam.

10. The method of paragraph 9, including using a heat exchanger to recover at least a portion of the water stream from the steam through a condensation process.

20 11. The method of any of paragraphs 1-9, including removing the carbon nanotubes from the water stream through a filtration process.

12. The method of any of paragraphs 1-9 or 11, including obtaining the water stream from a stream coming from a reactor through a chilling process.

13. The method of any of paragraphs 1-9, 11, or 12, including using molecular sieves to remove the carbon nanotubes from the water stream.

25 14. The method of any of paragraphs 1-9 or 11-13, including using zeolites to remove the carbon nanotubes from the water stream.

15. The method of any of paragraphs 1-9 or 11-14, wherein flowing the water stream into the purification vessel includes flowing the water stream from a separation vessel to the purification vessel, and wherein the separation vessel is

configured to perform an initial separation of the water stream from a carbon nanotube product.

16. A system for removing carbon nanotubes from a water stream including a purification vessel, wherein the purification vessel is configured to form a carbon oxide from the carbon nanotubes within the water stream.

17. The system of paragraph 16, wherein the purification vessel includes an air sparge vessel configured to remove the carbon nanotubes from the water stream by forming a froth phase that can be separated from a clean water phase using injected air.

18. The system of any of paragraphs 16 or 17, wherein the purification system is configured to inject a flocculant into the water stream, and wherein the flocculant causes a removal of the carbon nanotubes from the water stream.

19. The system of any of paragraphs 16-18, wherein the purification system is configured to form the carbon oxide from the carbon nanotubes within the water stream through an ozonolysis process.

20. The system of any of paragraphs 16-19, including a hydrocyclone for removing large carbon nanotubes from the water stream before the water stream is flowed into the purification vessel.

21. The system of any of paragraphs 16-20, including removing the carbon nanotubes from the water stream through a reverse osmosis process.

22. The system of any of paragraphs 16-21, wherein the purification vessel includes an underwater burner configured to produce an underwater flame for degrading the carbon nanotubes.

23. The system of any of paragraphs 16-22, wherein the purification vessel includes a flame degradation vessel configured to remove the carbon nanotubes from the water stream through a formation of steam.

24. The system of any of paragraphs 16-23, wherein the water stream is obtained from a stream coming from a reactor through a condensation process.

25. A method for purifying a water stream including carbon nanotubes, including:

flowing the water stream into a purification vessel;
injecting a chemical substance into the purification vessel; and
effecting a separation of the carbon nanotubes from the water stream through
an interaction of the chemical substance with the carbon nanotubes
within the purification vessel.

26. The method of paragraph 25, wherein the chemical substance includes air, and wherein effecting the separation of the carbon nanotubes from the water stream includes effecting a removal of the carbon nanotubes through an air sparging process.

27. The method of any of paragraphs 25 or 26, wherein the chemical substance includes a flocculant, and wherein effecting the separation of the carbon nanotubes from the water stream includes removing the carbon nanotubes through an interaction of the flocculant with the carbon nanotubes within the purification vessel.

28. The method of any of paragraphs 25-27, wherein the chemical substance includes ozone, and wherein effecting the separation of the carbon nanotubes from the water stream includes removing the carbon nanotubes from the water stream through an ozonolysis process.

29. The method of any of paragraphs 25-28, including removing the carbon nanotubes from the purification vessel by flowing the carbon nanotubes over a weir and into a collection vessel.

[0152] While the present techniques may be susceptible to various modifications and alternative forms, the embodiments discussed above have been shown only by way of example. However, it should again be understood that the techniques is not intended to be limited to the particular embodiments disclosed herein. Indeed, the present techniques include all alternatives, modifications, and equivalents falling within the true spirit and scope of the appended claims.

CLAIMS

1. A method of producing carbon nanotubes, comprising:
reacting a feed gas with a catalyst in a reactor in a Bosch reaction to form carbon nanotubes;
discharging a reactor effluent from the reactor;
separating product carbon nanotubes from the reactor effluent, forming a waste gas stream comprising residual carbon nanotubes;
heating, via a heat exchanger, the feed gas with waste heat from the waste gas stream;
condensing, via a second heat exchanger, water in the waste gas stream to give a water stream; and
removing carbon nanotubes from the water stream to give a purified water stream, the removing comprising forming a carbon oxide from the carbon nanotubes within the water stream.
2. The method of claim 1, comprising using an air sparging process to form the carbon oxide from the carbon nanotubes within the water stream, wherein the reactor comprises a fluidized-bed reactor.
3. The method of claim 1, wherein removing the carbon nanotubes comprises adding a flocculant to the water stream to effect a separation of the carbon nanotubes from the water stream.
4. The method of claim 1, wherein forming the carbon oxide from the carbon nanotubes comprises mixing an ozone stream with the water stream.
5. The method of claim 1, wherein removing the carbon nanotubes comprises using a hydrocyclone to remove the carbon nanotubes from the water stream.
6. The method of claim 1, wherein removing the carbon nanotubes comprises filtering the carbon nanotubes out of the water stream through a reverse osmosis process.
7. The method of claim 1, wherein forming the carbon oxide comprises forming the carbon oxide from the carbon nanotubes within the water stream through an oxidation process.
8. The method of claim 1, wherein forming the carbon oxide comprises using an underwater burner to produce an underwater flame for degrading the carbon nanotubes.
9. The method of claim 1, comprising using a flame degradation vessel to form the carbon oxide to remove the carbon nanotubes from the water stream through a formation of steam.

10. The method of claim 9, comprising using a third heat exchanger to recover at least a portion of the water stream from the steam through a condensation process.

11. The method of claim 1, wherein removing the carbon nanotubes comprises removing the carbon nanotubes from the water stream through a filtration process.

12. The method of claim 1, wherein condensing water in the waste gas stream comprises chilling the waste gas stream in a chilling process.

13. The method of claim 1, wherein removing the carbon nanotubes comprises using molecular sieves to remove the carbon nanotubes from the water stream.

14. The method of claim 1, wherein removing the carbon nanotubes comprises using zeolites to remove the carbon nanotubes from the water stream.

15. The method of claim 1, comprising:

separating the condensed water from the waste gas via a separation vessel to give the water stream;

flowing the water stream from the separation vessel to a purification system for the removing of the carbon nanotubes from the water stream; and

discharging from the purification system the purified water stream and a waste stream.

16. A system for producing carbon nanotubes, comprising:

a reactor to react a feed gas with a catalyst in a Bosch reaction to form carbon nanotubes, and to discharge a reactor effluent;

a separator to separate product carbon nanotubes from the reactor effluent, leaving a waste gas stream;

a first heat exchanger to heat the feed gas with waste heat from the waste gas stream;

a second heat exchanger to condense water in the waste gas stream to give a water stream; and

a purification system for removing carbon nanotubes from the water stream to give a purified water stream, the purification system comprising a purification vessel, wherein the purification system is configured to form a carbon oxide from the carbon nanotubes within the water stream to remove the carbon nanotubes from the water stream.

17. The system of claim 16, wherein the purification vessel comprises an air sparge vessel configured to remove the carbon nanotubes from the water stream by forming a froth phase that can be separated from a clean water phase using injected air.

18. The system of claim 16, wherein the reactor comprises a fluidized bed reactor, wherein the purification system is configured to inject a flocculant into the water stream, and wherein the flocculant causes a removal of the carbon nanotubes from the water stream.

19. The system of claim 16, wherein the separator comprises a cyclonic separator, and wherein the purification system is configured to form the carbon oxide from the carbon nanotubes within the water stream through an ozonolysis process.

20. The system of claim 16, comprising a hydrocyclone for removing large carbon nanotubes from the water stream before the water stream is flowed into the purification vessel.

21. The system of claim 16, wherein the purification system comprises a semipermeable membrane to facilitate removal of the carbon nanotubes from the water stream through a reverse osmosis process.

22. The system of claim 16, wherein the purification vessel comprises an underwater burner to produce an underwater flame for degrading the carbon nanotubes to form the carbon oxide.

23. The system of claim 16, wherein the purification vessel comprises a flame degradation vessel configured to form the carbon oxide to remove the carbon nanotubes from the water stream through a formation of steam.

24. The system of claim 16, comprising a separation vessel downstream of the second heat exchanger to remove the condensed water from the waste gas stream to give the water stream.

25. A method for producing carbon nanotubes including purifying a water stream comprising carbon nanotubes, comprising:

reacting a feed gas with a catalyst in a reactor in a Bosch reaction to form carbon nanotubes;
discharging a reactor effluent from the reactor;

separating product carbon nanotubes from the reactor effluent, forming a waste gas stream
comprising residual carbon nanotubes;

heating, via a heat exchanger, the feed gas with waste heat from the waste gas stream;

condensing, via a second heat exchanger, water in the waste gas stream to give a water stream; and

flowing the water stream into a purification vessel;

injecting a chemical substance into the purification vessel; and

effecting a separation of the carbon nanotubes from the water stream through an interaction
of the chemical substance with the carbon nanotubes within the purification vessel to
give a purified water stream.

26. The method of claim 25, wherein the reactor comprises a fluidized-bed reactor, wherein the chemical substance comprises air, and wherein effecting the separation of the carbon nanotubes from the water stream comprises effecting a removal of the carbon nanotubes through an air sparging process.

27. The method of claim 25, comprising discharging from the purification vessel a purified water stream and a waste stream, wherein the chemical substance comprises a flocculant, and wherein effecting the separation of the carbon nanotubes from the water stream comprises removing the carbon nanotubes through an interaction of the flocculant with the carbon nanotubes within the purification vessel.

28. The method of claim 25, wherein the chemical substance comprises ozone, and wherein effecting the separation of the carbon nanotubes from the water stream comprises removing the carbon nanotubes from the water stream through an ozonolysis process.

29. The method of claim 25, comprising removing the carbon nanotubes from the purification vessel by flowing the carbon nanotubes over a weir and into a collection vessel.