

DESCRIPTION

GLASS FOR DATA STORAGE MEDIUM SUBSTRATE, GLASS SUBSTRATE
FOR DATA STORAGE MEDIUM AND MAGNETIC DISK

5

TECHNICAL FIELD

The present invention relates to a glass substrate
to be used for a data storage medium such as a magnetic
disk or an optical disk, glass therefor and a magnetic
10 disk.

BACKGROUND ART

As glass for a data storage medium substrate such as
a magnetic disk or an optical disk, for example, lithium-
15 containing aluminosilicate glass having a high Young's
modulus or one having chemical reinforcing treatment
applied thereto (e.g. Patent Document 1), or crystallized
glass having a crystal layer precipitated by heat-
treating glass having a specific composition (e.g. Patent
20 Document 2), is used.

In recent years, along with an increase of the
storage capacity of a hard disk drive, development for
high recording density has been in progress at a high
pace. However, along with the development for high
25 recording density, microsizing of magnetic particles
tends to impair the thermal stability, and crosstalk or a
decrease in the SN ratio of playback signals is

problematic. Here, a heat-assisted magnetic recording technology has attracted attention as a united technique of light and magnetism. This is a technique wherein a magnetic recording layer is irradiated with a laser beam or near-field light to have the coercive force locally reduced at the heated portion, and in such a state, an external magnetic field is applied for recording, and the recorded magnetization is read out by e.g. a GMR element. Thus, recording can be made on a high-coercive force medium, whereby it becomes possible to microsize the magnetic particles while maintaining the thermal stability. However, in order to form such a high-coercive force medium in the form of a multilayer film, the substrate is required to be sufficiently heated, and a highly heat resistant substrate is required.

Patent Document 1: JP-A-2001-180969

Patent Document 2: JP-A-2000-119042

DISCLOSURE OF THE INVENTION

PROBLEMS TO BE SOLVED BY THE INVENTION

Substrate glass for chemical reinforcing treatment has heat resistance adjusted to be low so that chemical reinforcing treatment can efficiently be applied, and is likely to be buckled by heating at the time of forming the above-mentioned high-coercive force medium in the form of a multilayer film. Further, when a chemically reinforced glass substrate is subjected to the above-

mentioned heating, the ion exchange-treated layer is likely to be diffused by such heating, whereby the strength is likely to be deteriorated.

Further, if it is attempted to employ a crystallized
5 glass substrate, the substrate surface is likely to be distorted by the above-mentioned heating due to a difference in the thermal expansion coefficient between the crystalline layer and the bulk body.

It is an object of the present invention to provide
10 glass for a data storage medium substrate, whereby high heat resistance can be obtained even if no chemical reinforcing treatment or crystallizing treatment is applied, a glass substrate for a data storage medium, and a magnetic disk.

15

MEANS TO SOLVE THE PROBLEMS

The present invention provides glass for a data storage medium substrate (hereinafter referred to as the glass of the present invention), which comprises, as
20 represented by mol percentage based on the following oxides, from 55 to 70% of SiO_2 , from 2.5 to 9% of Al_2O_3 , from 0 to 10% of MgO , from 0 to 7% of CaO , from 0.5 to 10% of SrO , from 0 to 12.5% of BaO , from 0 to 2.5% of TiO_2 , from 0.5 to 3.7% of ZrO_2 , from 0 to 2.5% of Li_2O ,
25 from 0 to 8% of Na_2O , from 2 to 8% of K_2O and from 0.5 to 5% of La_2O_3 , provided that the total content of Al_2O_3 and ZrO_2 ($\text{Al}_2\text{O}_3 + \text{ZrO}_2$) is at most 12%, and the total content of

Li_2O , Na_2O and K_2O (R_2O) is at most 12%.

Further, the present invention provides glass for a data storage medium substrate (hereinafter referred to as the first glass or the glass 1), which comprises, as
5 represented by mol percentage based on the following oxides, from 55 to 70% of SiO_2 , from 2.5 to 9% of Al_2O_3 , from 0 to 10% of MgO , from 0 to 7% of CaO , from 1 to 10% of SrO , from 0.5 to 12.5% of BaO , from 0 to 2.5% of TiO_2 , from 0.5 to 3.7% of ZrO_2 , from 0 to 2.5% of Li_2O , from 0
10 to 5% of Na_2O , from 2 to 8% of K_2O and from 0.5 to 5% of La_2O_3 , provided that $\text{Al}_2\text{O}_3 + \text{ZrO}_2$ is at most 12%, the difference obtained by subtracting the Li_2O content from the total content of SrO and BaO is at least 2%, and R_2O is at most 10%.

15 Further, the present invention provides glass for a data storage medium substrate (hereinafter referred to as the second glass or the glass 2), which comprises, as represented by mol percentage based on the following oxides, from 60 to 70% of SiO_2 , from 2.5 to 9% of Al_2O_3 ,
20 from 2 to 10% of MgO , from 0 to 7% of CaO , from 0.5 to 10% of SrO , from 0 to 5% of BaO , from 0 to 1% of TiO_2 , from 1 to 3.7% of ZrO_2 , from 0 to 2.5% of Li_2O , from 2 to 8% of Na_2O , from 2 to 8% of K_2O and from 0.5 to 3% of La_2O_3 , provided that $\text{Al}_2\text{O}_3 + \text{ZrO}_2$ is at most 12%, the total
25 content of MgO , CaO , SrO and BaO (RO) is at least 10 mol%, and R_2O is at most 12%.

Further, the present invention provides a glass

substrate for a data storage medium, which is made of the above glass for a data storage medium substrate.

Further, the present invention provides a magnetic disk having a magnetic recording layer formed on the
5 above glass substrate for a data storage medium.

EFFECTS OF THE INVENTION

According to the present invention, it becomes possible to obtain a highly heat resistant glass
10 substrate for a data storage medium suitable for a heat-assisted magnetic recording even without applying chemical reinforcing treatment or crystallization treatment.

According to a preferred embodiment of the present
15 invention, it is possible to obtain glass having a small content of an alkali metal oxide, whereby an improvement of the weather resistance of a glass substrate can be expected.

Further, it becomes possible to obtain a glass
20 substrate having a thermal expansion coefficient comparable with a conventional glass substrate.

Further, it becomes possible to use a float process, which is useful for mass production of a glass substrate.

Further, it becomes possible to obtain glass having
25 a Young's modules (E) of at least 75 GPa, whereby the glass substrate tends to be scarcely deflected, and it becomes possible to increase the storage capacity. Even

when the storage medium is subjected to a shock, it tends to be hardly breakable.

Further, when E is adjusted to be at most 90 GPa, the polishing processing of the glass substrate tends to
5 be easy.

Further, it becomes possible to minimize the surface roughness of glass after the final polishing.

BRIEF DESCRIPTION OF DRAWINGS

10 Fig. 1 is a graph showing the relation between a value obtained by dividing a product of the Al_2O_3 content multiplied by the total content of ZrO_2 , K_2O and La_2O_3 , by the total content of MgO , CaO , SrO and BaO ($\text{Al}(\text{ZrKLa})/\text{RO}$), and the difference ΔT obtained by subtracting the liquid
15 phase temperature from the temperature where the viscosity becomes 10^4 dPa's.

Fig. 2 is a graph showing the relation between a value obtained by dividing a product of the sum of the MgO and CaO contents multiplied by the sum of the La_2O_3
20 and TiO_2 contents, by the ZrO_2 content $((\text{MgO} + \text{CaO}) \times (\text{La}_2\text{O}_3 + \text{TiO}_2) \div \text{ZrO}_2)$, unit: mol%, and the scattered peak intensity (optional unit) obtained by carrying out the measurement of small-angle X-ray scattering of the glass.

25 Fig. 3 is a graph showing the relation between the scattered peak intensity (optional unit) obtained by carrying out the measurement of small-angle X-ray

scattering of the glass, and the surface roughness Ra (unit: nm) of the polished glass, as measured by an atomic force microscope.

5 BEST MODE FOR CARRYING OUT THE INVENTION

The glass substrate for a data storage medium in the present invention is typically a circular glass plate having a thickness of from 0.5 to 1.5 mm and a diameter of from 48 to 93 mm, and in the case of a magnetic disk
10 glass substrate or the like, a hole having a diameter of from 15 to 25 mm is usually formed at its center.

In a magnetic disk of the present invention, at least a magnetic layer being a magnetic recording layer is formed on the main surface of the glass substrate for
15 a data storage medium of the present invention, and in addition, an underlayer, a protective layer, a lubricating layer or a roughness-controlling layer may, for example, be formed as the case requires.

A process for producing the glass substrate for a
20 data storage medium of the present invention is not particularly limited. For example, materials for the respective components commonly used may be blended to have a desired composition, such a mixture is heated and melted in a glass melting furnace, the molten glass is
25 homogenized by e.g. bubbling, stirring or addition of a clarifier, followed by forming into a plate glass having a predetermined thickness made of the glass for a data

storage medium substrate of the present invention, by a well known method such as a float process, a press method or a Down-draw method. Then, after annealing, processing such as grinding or polishing may be carried out to
5 obtain a glass substrate having prescribed size and shape. As the forming method, a float process suitable for mass production is preferred.

The glass transition temperature (T_g) of the glass of the present invention is preferably at least 660°C .
10 If it is lower than 660°C , it tends to be difficult to apply the above-mentioned heat-assisted magnetic recording technique to be carried out at a high heat treating temperature to form a magnetic layer. It is more preferably at least 680°C , particularly preferably
15 at least 690°C , and especially when it is desired to increase the heat resistance, it is preferably at least 700°C . T_g is typically at most 740°C .

The glass of the present invention preferably has an average linear expansion coefficient (α) of at least
20 $75 \times 10^{-7}/^{\circ}\text{C}$ within a range of from 50 to 350°C . If α is less than $75 \times 10^{-7}/^{\circ}\text{C}$, it is smaller than α of conventional glass, and on the other hand, α of the metal of the hub to be attached to the substrate is typically at least
100 $\times 10^{-7}/^{\circ}\text{C}$, whereby the difference in α between the hub
25 and the glass substrate becomes large, and the glass substrate is likely to be easily broken. α is more preferably at least $76 \times 10^{-7}/^{\circ}\text{C}$, particularly preferably at

least $77 \times 10^{-7}/^{\circ}\text{C}$, most preferably at least $78 \times 10^{-7}/^{\circ}\text{C}$, and typically at most $90 \times 10^{-7}/^{\circ}\text{C}$.

With the glass of the present invention, the difference between the temperature (T_4) at which the
5 viscosity becomes 10_4 dPa·s and the liquid phase temperature (T_L) i.e. $\Delta T (=T_4 - T_L)$ is preferably at least -70°C . If the difference is less than -70°C , forming into a glass plate tends to be difficult.

ΔT is more preferably at least 0°C . If ΔT is less
10 than 0°C , forming by a float process tends to be difficult. ΔT is particularly preferably at least 10°C , most preferably at least 20°C .

The density (d) of the glass of the present invention is preferably at most 3.3 g/cm^3 . If d exceeds
15 3.3 g/cm^3 , weight reduction of the data storage medium tends to be difficult, the power consumption required for driving the recording medium tends to increase, the disk tends to be vibrated by an influence of a windage loss during its rotation thus leading to an error in reading
20 out, or when a recording medium receives a shock, the substrate tends to be easily deflected and is likely to be broken by formation of a stress. Thus, d is more preferably at most 3.0 g/cm^3 , most preferably at most 2.8 g/cm^3 . Of the glass 2, d is typically at most 2.75 g/cm^3 .

25 The Young's modulus (E) of the glass of the present invention is preferably from 75 to 90 GPa. If E is less than 75 GPa, the disk tends to be vibrated by an

influence of a windage loss during its rotation thus leading to an error in reading out, or when a recording medium receives a shock, the substrate tends to be easily deflected and is likely to be broken by formation of a stress. E is more preferably at least 78 GPa, most preferably at least 80 GPa. If E exceeds 90 GPa, the polishing rate tends to be low, or a local stress is likely to be formed whereby breakage is likely to result, and it is typically at most 87 GPa.

10 E/d is typically from 25 to 35 MN/kg, and in the case of the glass 2, it is typically from 28 to 33 MN/kg.

 The above-mentioned first glass is glass of the present invention and is one wherein SrO is at least 1 mol%, BaO is at least 0.5 mol%, Na₂O is from 0 to 5 mol%,
15 the difference obtained by subtracting the Li₂O content from the total content of SrO and BaO is at least 2 mol%, and R₂O is at most 10 mol%.

 This first glass is suitable in a case where e.g. T₄ is desired to be lowered, ΔT is desired to be increased,
20 or T_g is desired to be made high.

 The above-mentioned second glass is glass of the present invention and is one wherein SiO₂ is at least 60 mol%, MgO is at least 2 mol%, BaO is from 0 to 5 mol%, TiO₂ is from 0 to 1 mol%, ZrO₂ is from 1 to 3.7 mol%, Na₂O
25 is at least 2 mol%, La₂O₃ is at most 3%, and RO is at least 10 mol%.

 This second glass is suitable in a case where e.g. d

or E/d is desired to be made small, or phase separation is desired to be made to hardly occur.

Now, the composition of the glass of the present invention will be described. Here, the contents of the
5 respective components are represented by mol percentage unless otherwise specified.

SiO_2 is an essential component to form the skeleton of the glass. If SiO_2 is less than 55%, the glass tends to be unstable, or the weather resistance or acid
10 resistance tends to deteriorate. SiO_2 is preferably at least 57%, typically at least 60%. If SiO_2 exceeds 70%, α tends to be too small, or the melting temperature to prepare the glass tends to be too high. SiO_2 is preferably at most 68%, typically at most 67%.

15 In the glass 2, SiO_2 is at least 60%. If SiO_2 is less than 60%, the glass tends to be unstable, the glass tends to undergo phase separation, or T_g , weather resistance or acid resistance tends to deteriorate. SiO_2 is preferably at least 61%, typically at least 63%.

20 In the glass 2, the content of SiO_2 as represented by mass percentage is typically less than 60.2%.

Al_2O_3 has an effect to increase T_g , weather resistance or E and is an essential component. If Al_2O_3 is less than 2.5%, the above effect tends to be small,
25 and it is preferably at least 4%. If Al_2O_3 exceeds 9%, ZrO_2 type or K-Al-Si type crystals are likely to precipitate, and T_L is likely to be high, and it is

preferably at most 8%. Further, in the glass 1, the Al_2O_3 content represented by mass percentage is typically less than 11%, more typically at most 10.5%.

MgO is not an essential component, but has an effect
5 to lower the viscosity of the molten glass thereby to facilitate melting of the glass, to reduce d or to increase E , and thus it may be contained in an amount of up to 10%. If MgO exceeds 10%, the chemical durability tends to deteriorate, the glass tends to be unstable, or
10 T_L tends to be too high, and further, the glass is likely to undergo phase separation. And accordingly, it is preferably at most 9%. In a case where MgO is contained, it is preferably contained in an amount of at least 1%. In the glass 2, MgO is particularly preferably at most 9%.

15 In the glass 2, MgO is an essential component. If MgO is less than 2%, the viscosity of the molten glass tends to be so high that the glass tends to be hardly melted, d tends to be large, or E tends to be low. MgO is preferably at least 4%.

20 CaO is not an essential component, but has an effect to lower the viscosity of the molten glass to facilitate melting of the glass, or to increase E , and it may be contained up to 7%. If CaO exceeds 7%, it tends to form crystals with Si or La, T_L is likely to be high, the
25 glass tends to be unstable, or the chemical durability tends to deteriorate, and further, the glass is likely to undergo phase separation. CaO is preferably at most 6%,

and in the glass 2, it is typically at most 4%. In a case where CaO is contained, the content is typically at least 1%.

SrO has an effect to increase α , to lower the
5 viscosity of the molten glass thereby to facilitate melting of the glass, or to lower T_L and is essential. If SrO is less than 0.5%, the above effect tends to be small, and it is preferably at least 1%, more preferably at least 2%. If SrO exceeds 10%, the chemical durability
10 tends to be low, the glass tends to be unstable, or d tends to be too large, and it is preferably at most 8%.

In the glass 1, if SrO is less than 1%, the above effect tends to be low, and SrO is at least 1%, preferably at least 2%.

15 BaO is not an essential component, but has an effect to increase α , to lower the viscosity of the molten glass thereby to facilitate melting of the glass, or to lower T_L , and it may be contained in an amount of up to 12.5%. If BaO exceeds 12.5%, Ba-Al-Si type crystals are likely
20 to be formed, whereby T_L is rather likely to be high, the weather resistance tends to deteriorate, d tends to be too large, or E tends to deteriorate, and it is preferably at most 10%. In a case where BaO is contained, the content is typically at least 0.1%.

25 In the glass 1, BaO is essential. If BaO is less than 0.5%, the viscosity of the molten glass tends to be high, whereby the glass tends to be hardly melted, or T_L

tends to be high, and it is preferably at least 1%.

In the glass 2, if BaO is contained, the content is at most 5%. If BaO exceeds 5%, d is likely to be too large, or E tends to deteriorate, and it is preferably at
5 most 3%.

The total content RO of MgO, CaO, SrO and BaO is preferably at least 10%. If RO is less than 10%, α is likely to be too small, and it is typically at least 12%.

On the other hand, RO is preferably at most 30%. If
10 RO exceeds 30%, T_g is likely to be low, or d is likely to be large, and it is preferably at most 25%, typically at most 22%.

In the glass 2, RO is required to be at least 10%. If RO is less than 10%, α is likely to be too small, and
15 it is typically at least 12%.

TiO₂ is not an essential component, but has an effect to increase T_g , weather resistance or E , and thus, it may be contained in an amount of up to 2.5%. If TiO₂ exceeds 2.5%, the glass is likely to be unstable, and it is
20 preferably at most 2%. In a case where TiO₂ is contained, the content is typically at least 0.5%.

In the glass 1, the total content of MgO, CaO and TiO₂ is preferably at most 16%. If the total content exceeds 16%, phase separation is likely to take place in
25 a case where the annealing temperature is high at the time of annealing the glass or in a case where the cooling rate is slow.

In the glass 2, in a case where TiO_2 is contained, the content is at most 1%. If TiO_2 exceeds 1%, the glass is likely to undergo phase separation, and it is preferably at most 0.9%, more preferably at most 0.5%.

5 In order to suppress phase separation, it is preferred not to contain TiO_2 .

ZrO_2 has an effect to increase T_g , the weather resistance or E and thus is essential. If it is less than 0.5%, the above effect tends to be small, and it is
10 preferably at least 1%. If ZrO_2 exceeds 3.7%, ZrO_2 crystals are likely to precipitate, T_L is likely to be high, or d is likely to be too large, and it is preferably at most 3.6%.

If the total content of Al_2O_3 and ZrO_2 ($\text{Al}_2\text{O}_3 + \text{ZrO}_2$)
15 exceeds 12%, T_L is likely to be too high, and the total content is typically at most 11%.

In the glass 2, ZrO_2 is at least 1%. If ZrO_2 is less than 1%, the weather resistance is likely to deteriorate, E tends to be small, or phase separation is likely to
20 take place.

In the glass 2, the ratio of the content of SiO_2 represented by mass percentage to the sum of the TiO_2 and ZrO_2 contents represented by mass percentage ($\text{SiO}_2 / (\text{TiO}_2 + \text{ZrO}_2)$) is preferably more than 10. If the
25 ratio is 10 or less, T_L is likely to be high, and the ratio is preferably at least 12.

Li_2O is not an essential component, but has an effect

to increase α , to lower the viscosity of the molten glass thereby to facilitate melting of the glass, or to increase E, and may be contained in an amount of up to 2.5%. If Li_2O exceeds 2.5%, T_g is likely to

5 substantially decrease, or the weather resistance is likely to deteriorate, and in the glass 2, phase separation is likely to take place in addition, and it is preferably at most 1%, and typically preferably no Li_2O is contained.

10 In the glass 1, the difference obtained by deducting the Li_2O content from the total content of SrO and BaO [$(\text{SrO}+\text{BaO})-\text{Li}_2\text{O}$] is at least 2%. If this difference is less than 2%, T_g is likely to be too low, and the difference is preferably at least 3.5%.

15 Na_2O is not an essential component, but has an effect to increase α , or to lower the viscosity of the molten glass thereby to facilitate melting of the glass, and thus may be contained in an amount of up to 8%. If Na_2O exceeds 8%, T_g of the weather resistance is likely to
20 deteriorate, and it is preferably at most 6%.

In the glass 1, when Na_2O is contained, the content is at most 5%. If Na_2O exceeds 5%, T_g or the weather resistance is likely to deteriorate, and it is preferably at most 4%. In the glass 2, Na_2O is an essential
25 component. If Na_2O is less than 2%, α tends to be small, or the viscosity of the molten glass is likely to be large whereby the glass tends to be hardly melted, and it

is preferably at least 3%.

K_2O has an effect to increase α or to lower the viscosity of the molten glass thereby to facilitate melting of the glass and is essential. If K_2O is less
5 than 2%, such an effect tends to be small, and it is preferably at least 3%. If K_2O exceeds 8%, K-Si-Al type crystals are likely to be formed, whereby T_L is likely to be high, or the weather resistance or E is likely to be low, and it is preferably at most 7%.

10 If the total content of Li_2O , Na_2O and K_2O i.e. R_2O exceeds 12%, T_g or the weather resistance is likely to deteriorate, and it is preferably at most 10%.

R_2O is preferably at least 5%. If it is less than 5%, α tends to be too small, or the viscosity of the glass is
15 likely to be high.

In the glass 1, R_2O is at most 10%. If R_2O exceeds 10%, T_g or the weather resistance is likely to deteriorate, and it is preferably at most 9%.

The molar ratio of the total content of Li_2O and Na_2O
20 to the K_2O content i.e. $(Li_2O+Na_2O)/K_2O$ is preferably at most 3. If the molar ratio exceeds 3.0, T_g is likely to be too low, or the effect to lower T_g tends to be not negligible rather than the effect to increase α , and it is preferably at most 1.4, typically at most 1.1. In the
25 glass 1, such a molar ratio is preferably at most 1.4.

La_2O_3 has an effect to increase T_g , to increase α or to increase E and thus is essential. If La_2O_3 is less

than 0.5%, such an effect tends to be small, and it is preferably at least 1%. If La_2O_3 exceeds 5%, Si-La type crystals or Si-Ca-La type crystals are likely to be formed, whereby T_L is likely to be high, or d is likely
 5 to be too large, and it is preferably at most 3%.

In the glass 2, La_2O_3 is at most 3%. If La_2O_3 exceeds 3%, Si-La type crystals or Si-Ca-La type crystal are likely to be formed, whereby T_L is rather likely to be high, d is likely to be large, or phase separation is
 10 likely to take place, and it is preferably at most 2%.

In connection with the glass 1, Fig. 1 is a graph wherein a value obtained by dividing a product of the Al_2O_3 content multiplied by the total content of ZrO_2 , K_2O and La_2O_3 , by the total content of MgO , CaO , SrO and BaO
 15 i.e. $\text{Al}(\text{ZrKLa})/\text{RO}$ (abscissa, unit: mol%), and $\Delta T = T_4 - T_L$ (ordinate, unit: °C) were plotted with respect to 67 types of glass with compositions comprising, as represented by mol percentage, from 52 to 67.5% of SiO_2 , from 4 to 15% of Al_2O_3 , from 0 to 8.5% of MgO , from 0 to
 20 8% of CaO , from 0.5 to 9% of SrO , from 0 to 10% of BaO , from 0 to 4% of TiO_2 , from 0 to 4% of ZrO_2 , from 0 to 2.5% of Li_2O , from 0 to 6% of Na_2O , from 3 to 7% of K_2O and from 0 to 5% of La_2O_3 . Here, with respect to T_4 of some of glass, values calculated from their compositions
 25 were employed.

From Fig. 1, it is evident that $\text{Al}(\text{ZrKLa})/\text{RO}$ should preferably be made to be at most 4.0% when it is desired

to adjust ΔT to be at least 0°C . If $\text{Al}(\text{ZrKLa})/\text{RO}$ exceeds 4.0%, ΔT is likely to be less than 0°C , whereby forming by a float process is likely to be difficult. It is more preferably at most 3.5%, particularly preferably at most 3.0%.

In the glass 1, in a case where the total content of Al_2O_3 and ZrO_2 is at most 9%, the total content of Al_2O_3 , ZrO_2 , K_2O and La_2O_3 is preferably at most RO. Otherwise, Si-Al-La type crystals, ZrO_2 type crystals or Si-K-La type crystals are likely to precipitate, whereby ΔT is likely to be small.

In the glass 1, in a case where the total content of Al_2O_3 and ZrO_2 exceeds 9%, the total content of ZrO_2 and K_2O is preferably less than 9%. Otherwise, ZrO_2 type crystals or Si-K-La type crystals are likely to precipitate, whereby ΔT is likely to be small.

In connection with the glass 2, Fig. 2 is a graph wherein a value obtained by dividing a product of the sum of the MgO and CaO contents multiplied by the sum of the La_2O_3 and TiO_2 contents, by the ZrO_2 content i.e. $(\text{Mg}+\text{Ca})(\text{La}+\text{Ti})/\text{Zr}$ (abscissa, unit: mol%), and the scattered peak intensity obtained by carrying out the measurement of small-angle X-ray scattering of the glass i.e. SAXS intensity (ordinate, optional unit) were plotted with respect to 20 types of glass with compositions comprising, as represented by mol percentage, from 64.3 to 67.3% of SiO_2 , from 7.2 to 8.0% of Al_2O_3 ,

from 4.5 to 8.5% of MgO, from 0 to 8% of CaO, from 0.5 to 6.0% of SrO, from 0 to 2.0% of BaO, from 0 to 2.0% of TiO₂, from 1.0 to 3.0% of ZrO₂, from 3.0 to 6.5% of Na₂O, from 2.5 to 6.3% of K₂O, and from 0.5 to 1.3% of La₂O₃.

5 Here, the measurement of small-angle X-ray scattering of the glass was carried out as follows for the purpose of evaluating fine phase separation in the glass. Namely, using NANO-Viewer manufactured by Rigaku K.K. as a small-angle X-ray scattering apparatus, and a
10 imaging plate as a detector, X-ray was passed through a glass sample having a thickness of about 0.1 mm and a size of about 1 cm × 1 cm, and the obtained two-dimensional data was estimated by the average characteristics of radiation emitted by a circular ring
15 and then data-conversion to obtain one-dimensional data, which was then subjected to transmittance correction, in-air scattering correction and sample-thickness correction to obtain a scattered peak intensity. This scattered peak intensity has a correlation with the surface
20 roughness AFM-Ra of the glass at the time of the final polishing as described hereinafter, as shown in Fig. 3.

 In a case where a surface recording density of at least 1 Tb/inch² is desired to be realized, such AFM-Ra is required to be adjusted to a level of at most 0.15 nm,
25 more preferably at most 0.12 nm. For such a purpose, for example from Fig. 3, it is evident that when AFM-Ra is desired to be adjusted to a level of at most 0.15 nm, the

above scattered peak intensity is preferably adjusted to a level of at most 220 (optional unit) or when AFM-Ra is desired to be adjusted to a level of at most 0.12 nm, the above scattered peak intensity is preferably adjusted to a level of at most 50 (optional unit). Accordingly, in such a case, it is evident from Fig. 2 that

(Mg+Ca)(La+Ti)/Zr is preferably adjusted to be level of at most 12.0%. If (Mg+Ca)(La+Ti)/Zr exceeds 12.0%, the compositional fluctuation due to phase separation tends to be large, and the surface roughness at the time of the final polishing is likely to deteriorate, and it is more preferably at most 10.0%, particularly preferably at most 8.0%.

The glass of the present invention consists essentially of the above-mentioned components, but may contain other components within a range not to impair the purpose of the present invention. In a case where such other components are contained, the total content of such other components is preferably at most 5%, more preferably at most 2%. Now, such other components will be exemplified.

A clarifier such as SO_3 , Cl, As_2O_3 or Sb_2O_3 may be contained in a total amount of up to 1%.

Further, in a case where heating by irradiation with infrared ray is carried out for heating a substrate, in order to increase the emissivity in the irradiation wavelength zone, a colorant such as Fe_2O_3 , NiO, CoO, Cr_2O_3 ,

CuO, MnO₂, CeO₂, Er₂O₃ or Yb₂O₃ may be contained in a total amount of up to 0.5%.

ZnO may have an effect to lower the viscosity of the molten glass thereby to facilitate melting of the glass,
5 or to lower T_L , and in such a case, it may be contained in an amount of up to 5%. If ZnO exceeds 5%, T_g is likely to be low, or d is likely to be large, and it is preferably at most 3%.

B₂O₃ may sometimes be contained in an amount of up to
10 5% in order to e.g. lower T_L , but it may decrease the uniformity or phase separation characteristics of the glass, and in such a case, it is preferably not contained.

EXAMPLES

15 In each of Examples 1 to 21, 28 to 50 and 52 to 65 in Tables 1 to 8, materials were prepared and mixed to obtain a composition shown by mol percentage in sections for from SiO₂ to La₂O₃ and by means of a platinum crucible, melted at a temperature of from 1,550 to 1,650°C for from
20 3 to 5 hours. Typically, the mixture was melted at a temperature of from 1,550 to 1,650°C for from 1 to 2 hours, then stirred for 1 hour and further clarified for 1 hour. Then, the molten glass was cast to form a plate, followed by annealing.

25 With respect to a glass plate thus obtained, T_g (unit: °C), α (unit: 10⁻⁷/°C), the density d (unit: g/cm³), the Young's modulus E (unit: GPa), the specific modulus

E/d (unit: MNm/kg), the temperature T_4 at which the viscosity becomes $10^4 P = 10^4$ dPa·s (unit: °C), the liquid phase temperature T_L (unit: °C), the phase separation property, and the above-mentioned scattered peak

5 intensity (optional unit) were measured or evaluated by the following methods. The results are shown in Tables. In the Tables, "-" means that no measurement was carried out, and "*" means that the value was one obtained by calculation from the composition.

10 T_g: By means of a differential thermal dilatometer and using quartz glass as a reference sample, the rate of elongation of glass when it was heated from room temperature at a rate of 5°C/min to a temperature at which the glass softened and elongation no longer
15 observed i.e. a yield point, whereby a temperature corresponding to the critical point in the thermal expansion curve was taken as the glass transition temperature.

α: From the thermal expansion curve obtained in the
20 same manner as the above measurement of T_g, an average linear expansion coefficient within a range of from 50 to 350°C was calculated.

d: Measured by an Archimedes method.

E: With respect to a glass plate having a thickness
25 of from 4 to 10 mm and a size of about 4 cm × 4 cm, the measurement was made by an ultrasonic pulse method.

T₄: Measured by means of a rotation viscometer.

T_L: A glass specimen of about 1 cm × 1 cm × 0.8 cm was placed on a platinum plate and heat-treated for 3 hours in an electric furnace set at every 10°C within a temperature range of from 1,100 to 1,300°C. The glass
5 was left to cool in atmospheric air and then observed by a microscope, whereby the temperature range where crystals were precipitated was taken as a liquid phase temperature.

Phase separation property: A glass specimen of about
10 1 cm × 1 cm × 0.8 cm was placed on a platinum plate and put in an electric furnace set at 850°C and 750°C and maintained for about 20 minutes, whereupon it was annealed at a cooling rate of -1°C/min or -10°C/min to room temperature, followed by irradiation with a high
15 luminance power source, whereby whether or not turbidity was observed, was visually confirmed. As a result, one where no turbidity was observed in all tests was identified by ⊙, one where no turbidity was observed under the conditions of 750°C and -1°C/min was identified
20 by ○, one where no turbidity was observed under the conditions of 750°C and -10°C/min was identified by △, and one where turbidity was observed in all tests was identified by ×. The results are shown in the section for "Phase separation property 1" in the Tables.

25 Scattered peak intensity: As mentioned above, the measurement of small-angle X-ray scattering of glass was carried out, and data treatments were carried out to

obtain the scattered peak intensity. The results are shown in the section for "Phase separation property 2" in the Tables. As mentioned above, in a case where the after-mentioned AFM-Ra is desired to be adjusted to be at most 0.15 nm, this scattered peak intensity is preferably at most 220.

In Examples 22 to 27 and 51, no glass was prepared, and T_g, etc. were obtained by calculation from the compositions.

10 Examples 1 to 52 represent Examples of the present invention, and among them, Examples 1 to 27 and 31 to 36 are examples for the glass 1, and Examples 9, 11, 16 and 28 to 48 are examples for the glass 2. Example 53 is a Reference Example, and Examples 54 to 65 are Comparative
15 Examples.

Tables 9 to 16 show the compositions of the glasses in Examples 1 to 65 as represented by mass percentage.

The following test was carried out to measure the surface roughness after the polishing of each glass in
20 Examples 6, 16, 28 to 31, 34, 37 to 39, 41, 43, 44, 52 and 63 to 65.

As a test specimen, one obtained by finishing a glass plate having a thickness of about 1.5 mm and a size of about 4 cm x 4 cm by means of a cerium oxide slurry so
25 that the surface roughness would be from 0.3 to 0.4 nm as measured by an atomic force microscope, was prepared.

Firstly, a suede abrasive cloth was mounted on a

polishing plate of a small single-side polishing machine
manufactured by Hamai Co., Ltd. and subjected to truing
by means of a diamond dresser. This abrasive cloth was
washed with pure water and by means of a brush, and then
5 polishing operation was carried out by supplying a
colloidal silica slurry with an average particle size of
30 nm having the pH adjusted to 2. The polishing
pressure was 10 kPa, the sun gear rotational speed was 40
rpm, and the polishing time was 20 minutes.

10 After the polishing, each glass was washed with pure
water and an alkaline cleanser and then dried by blowing
dry air thereto.

The surface roughness Ra of each glass thus obtained
was measured by means of an atomic force microscope
15 SPA400, manufactured by SII NanoTechnology Inc. The
results are shown in the section for "Surface roughness"
(unit: nm) in the Tables. The surface roughness Ra thus
obtained is referred to as AFM-Ra in this specification.

Fig. 3 is one wherein the above scattered peak
20 intensity (phase separation property 2) and this AFM-Ra
were plotted. From this Fig., it is evident that a
positive correlation exists between the two.

TABLE 1

Examples	1	2	3	4	5	6	7	8
SiO ₂	57.5	60.0	60.0	62.5	63.0	63.5	65.0	65.0
Al ₂ O ₃	7.5	7.5	6.5	7.5	5.5	5.5	5.0	5.0
MgO	2.0	2.0	6.0	2.0	6.5	3.6	2.0	2.0
CaO	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0
SrO	7.0	7.0	7.0	7.0	3.2	6.8	7.0	7.0
BaO	10.0	7.5	5.5	5.0	5.5	5.0	5.0	5.0
ZnO	0	0	0	0	0	0	0	0
TiO ₂	1.5	1.5	2.0	1.5	1.5	1.5	1.5	1.5
ZrO ₂	3.0	3.0	3.0	3.0	3.0	3.0	3.0	3.0
Li ₂ O	0	0	0	0	0	0	0	0
Na ₂ O	4.0	4.0	1.0	4.0	1.3	1.1	1.5	4.0
K ₂ O	4.0	4.0	5.0	4.0	7.0	6.5	6.5	4.0
La ₂ O ₃	1.5	1.5	2.0	1.5	1.5	1.5	1.5	1.5
RO	21.0	18.5	20.5	16.0	17.2	17.4	16.0	16.0
R ₂ O	8.0	8.0	6.0	8.0	8.3	7.6	8.0	8.0
LiNa/K	1.00	1.00	0.20	1.00	0.19	0.17	0.23	1.00
Al (ZrKLa)/RO	3.04	3.45	3.17	3.98	3.68	3.48	3.44	2.66
LaTi·CaMg/Zr	4	4	10.67	4	8.5	5.6	4	4
T _g	682	691	736	697	711	716	707	681
α	84	82	75	79	80	78	79	80
d	3.22	3.12	3.10	3.01	2.95	3.00	3.00	3.00
E	83.4*	82.8*	85.9*	82.1*	81.8	81.6	83.1	81.2*
E/d	25.9*	26.6*	27.7*	27.3*	27.7	27.2	27.7	27.0*
T ₄	1117	1132	1150	1164	1173	1174	1166	1142
T _L	1110	1130	1150	1160	1170	1170	1120	<1100
Phase separation property 1	—	—	—	—	—	⊙	—	—
Phase separation property 2	—	—	—	—	—	43	—	—
Surface roughness	—	—	—	—	—	0.13	—	—

TABLE 2

Examples	9	10	11	12	13	14	15	16
SiO ₂	66.5	67.5	64.0	63.5	62.5	63.05	63.3	63.5
Al ₂ O ₃	4.0	5.0	7.0	6.5	7.0	7.0	6.8	7.0
MgO	5.0	2.0	7.0	7.5	8.5	8.1	8.3	8.0
CaO	0	2.0	6.0	4.0	4.0	4.7	5.5	5.0
SrO	7.0	7.0	4.0	5.5	5.0	3.7	2.7	3.3
BaO	4.0	2.5	1.0	1.0	1.0	1.0	1.0	1.0
ZnO	0	0	0	0	0	0	0	0
TiO ₂	1.0	1.5	1.0	1.5	1.5	1.5	1.5	1.0
ZrO ₂	2.5	3.0	1.25	1.5	1.5	1.5	1.5	1.65
Li ₂ O	0	0	0	0	0	0	0	0
Na ₂ O	3.0	4.0	2.0	3.0	2.5	2.6	2.7	2.6
K ₂ O	5.0	4.0	5.75	5.0	5.5	5.6	5.5	5.7
La ₂ O ₃	2.0	1.5	1.0	1.0	1.0	1.25	1.2	1.25
RO	16.0	13.5	18.0	18.0	18.5	17.5	17.5	17.3
R ₂ O	8.0	8.0	7.75	8.0	8.0	8.2	8.2	8.3
LiNa/K	0.60	1.00	0.35	0.60	0.45	0.46	0.49	0.46
Al (ZrKLa) /RO	2.38	3.15	3.11	2.71	3.03	3.34	3.19	3.48
LaTi·CaMg/Zr	6	4	20.8	19.17	20.83	23.47	24.84	17.73
T _g	687	690	708	695	709	710	710	711
α	76	77	78	79	75	78	79	78
d	2.98	2.90	2.74	2.78	2.78	2.77	2.75	2.76
E	83.4*	80.6*	81.2	82.0	82.1	81.6	81.8	81.5
E/d	25.9*	27.8*	29.6	29.4	29.5	29.5	29.8	29.6
T ₄	1146	1176	1184	1154*	1167*	1170	1147	1177
T _L	1130	1140	1160	1120	1170	1140	1145	1160
Phase separation property 1	—	—	—	—	—	○	△	○
Phase separation property 2	—	—	—	—	—	—	—	843
Surface roughness	—	—	—	—	—	—	—	0.17

TABLE 3

Examples	17	18	19	20	21	22	23	24
SiO ₂	63.7	62.5	65.0	63.0	63.0	64.0	64.5	63.5
Al ₂ O ₃	6.5	6.5	7.5	6.5	6.5	7.0	5.5	5.5
MgO	4.0	7.0	2.0	3.5	6.0	7.0	0	3.0
CaO	2.0	1.0	2.0	2.0	0	5.0	3.0	2.0
SrO	7.0	2.0	7.0	5.0	6.5	6.0	7.8	7.6
BaO	3.0	7.0	2.5	4.5	3.5	1.5	5.0	5.9
ZnO	0	0	0	0	0	0	0	0
TiO ₂	1.5	1.0	1.5	2.0	2.0	0	1.5	1.5
ZrO ₂	2.6	2.5	3.0	3.5	2.5	1.0	2.5	3.0
Li ₂ O	0	0	0	0	0	0	0	0
Na ₂ O	1.5	2.0	4.0	2.0	1.5	1.8	2.2	0
K ₂ O	6.7	6.5	4.0	6.0	6.5	5.7	6.5	6.5
La ₂ O ₃	1.5	2.0	1.5	2.0	2.0	1.0	1.5	1.5
RO	16.0	17.0	13.5	15.0	16.0	19.5	15.8	18.5
R ₂ O	8.2	8.5	8.0	8.0	8.0	7.5	8.7	6.5
LiNa/K	0.22	0.31	1.00	0.33	0.23	0.32	0.34	0
Al (ZrKLa) /RO	4.39	4.21	4.72	4.98	4.47	2.76	3.66	3.27
LaTi·CaMg/Zr	6.92	9.6	4	6.29	9.6	12	3.6	5
T _g	702	711	701*	727	725	705*	694*	730*
α	79.5*	81.0	74.3*	77.9	78.1	77.7*	82.4*	75.7*
d	2.92*	2.99*	2.90*	3.00*	2.96*	2.78*	3.00*	3.05*
E	80.4*	80.7*	81.5*	82.2*	81.8*	80.3*	78.1*	81.3*
E/d	27.5*	26.9*	28.1*	27.4*	27.6*	28.8*	26.0*	26.6*
T ₄	1172	1178	1182*	1171	1156	1168*	1156*	1174*
T _L	1210	1220	1230	1200	1220			
Phase separation property 1	—	—	—	—	—			
Phase separation property 2	—	—	—	—	—			
Surface roughness	—	—	—	—	—			

TABLE 4

Examples	25	26	27	28	29	30	31	32
SiO ₂	64.55	67.0	69.0	66.5	67.0	65.0	65.0	65.4
Al ₂ O ₃	6.0	5.0	4.0	7.5	7.5	7.5	7.2	7.4
MgO	3.2	2.5	4.5	6.0	6.0	6.0	8.0	7.8
CaO	2.0	2.0	2.0	6.0	6.0	6.0	4.0	4.7
SrO	4.5	6.1	2.5	2.5	2.5	2.5	2.5	1.8
BaO	5.0	3.0	1.0	0	0	0	2.0	0.8
ZnO	0	0	0	0	0	0	0	0
TiO ₂	1.5	1.5	2.0	0.5	0	0	0	0
ZrO ₂	3.0	3.0	3.0	1.0	1.0	3.0	1.7	1.8
Li ₂ O	2.5	0	0	0	0	0	0	0
Na ₂ O	1.0	4.9	4.5	4.0	4.0	4.0	3.0	4.2
K ₂ O	5.0	3.5	5.5	5.0	5.0	5.0	5.6	5.0
La ₂ O ₃	1.75	1.5	2.0	1.0	1.0	1.0	1.0	1.1
RO	14.7	13.6	10.0	14.5	14.5	14.5	16.5	15.1
R ₂ O	8.5	8.4	10.0	9.0	9.0	9.0	8.6	9.2
LiNa/K	0.70	1.40	0.82	0.80	0.80	0.80	0.54	0.84
Al (ZrKLa) /RO	3.98	2.94	4.2	3.62	3.62	4.66	3.62	3.87
LaTi·CaMg/Zr	5.63	4.5	8.7	18	12	4	7.06	7.64
T _g	680*	683*	688*	703	703	722	696	694
α	75.1*	75.3*	77.7*	77	77	76	76	76
d	2.97*	2.90*	2.79*	2.65	2.64	2.70	2.74	2.69
E	83.4*	80.9*	79.0*	80.4	79.8	83.1	81.2	81.9
E/d	28.1*	27.9*	28.4*	30.4	30.3	30.8	29.7	30.4
T ₄	1144*	1156*	1171*	—	—	—	1195	—
T _L				1160	1160	>1200	<1100	1160
Phase separation property 1				—	—	—	—	—
Phase separation property 2				245	210	86	65	—
Surface roughness				0.16	0.14	0.14	0.13	—

TABLE 5

Examples	33	34	35	36	37	38	39	40
SiO ₂	64.3	66.0	66.5	66.5	66.5	66.5	65.8	65.9
Al ₂ O ₃	7.4	7.4	7.4	7.4	7.7	7.4	8.0	7.5
MgO	8.0	5.0	6.5	6.5	7.0	7.0	5.5	6.5
CaO	5.8	5.0	2.5	0	1.0	1.0	0	0
SrO	1.7	3.0	3.5	6.0	4.0	4.0	6.0	5.9
BaO	0.6	0.6	0.6	0.6	0.6	0.6	0.6	0.6
ZnO	0	0	0	0	0	0	0	0
TiO ₂	0	0	0	0	0	0	0	0
ZrO ₂	1.8	2.5	2.0	2.0	2.0	2.0	2.5	2.5
Li ₂ O	0	0	0	0	0	0	0	0
Na ₂ O	4.2	4.5	4.5	4.5	4.3	4.3	4.3	4.0
K ₂ O	5.45	5.5	5.5	5.5	5.9	5.9	6.3	6.3
La ₂ O ₃	0.75	0.5	1.0	1.0	1.0	1.3	1.0	0.8
RO	16.1	13.6	13.1	13.1	12.6	12.6	12.1	13.0
R ₂ O	9.65	10.0	10.0	10.0	10.2	10.2	10.6	10.3
LiNa/K	0.77	0.82	0.82	0.82	0.73	0.73	0.68	0.63
Al (ZrKLa) /RO	3.68	4.63	4.80	4.80	5.44	5.40	6.48	5.54
LaTi·CaMg/Zr	5.75	2	4.5	3.25	4	5.2	2.2	2.08
T _g	689	684	685	688	691	693	696	694
α	80	78	78	78	79	79	80	77
d	2.66	2.67	2.70	2.73	2.69	2.71	2.74	2.72
E	81.2	80.6	80.4	79.8	79.5	79.9	78.9	79.5
E/d	30.5	30.2	29.8	29.2	29.6	29.5	28.8	29.2
T ₄	—	—	—	—	—	—	—	—
T _L	1170	1140	1120	<1100	1120	1160	1180	1140
Phase separation property 1	—	—	—	—	—	—	—	—
Phase separation property 2	—	21	114	29	72	—	33	17
Surface roughness	—	0.10	—	—	0.12	0.11	0.10	—

TABLE 6

Examples	41	42	43	44	45	46	47	48
SiO ₂	66.3	66.1	66.0	65.8	66.0	67.0	67.3	66.4
Al ₂ O ₃	7.7	7.6	7.2	7.5	7.5	7.5	7.4	7.5
MgO	4.5	4.7	8.0	8.0	8.5	5.0	5.5	5.6
CaO	4.5	4.7	6.0	6.0	6.0	3.5	5.5	5.6
SrO	3.2	3.2	1.0	1.0	0.5	4.2	2.0	2.3
BaO	0	0.2	0	0	0	0	0	0
ZnO	0	0	0	0	0	0	0	0
TiO ₂	0	0	0	0	0	0	0	0
ZrO ₂	2.5	2.5	1.8	1.7	1.5	2.5	2.0	2.2
Li ₂ O	0	0	0	0	0	0	0	0
Na ₂ O	4.6	4.7	6.5	6.5	6.5	6.0	5.8	5.7
K ₂ O	6.0	5.6	2.5	2.5	2.5	3.5	3.7	3.8
La ₂ O ₃	0.7	0.7	1.0	1.0	1.0	0.8	0.8	0.9
RO	12.2	12.8	15.0	15.0	15.0	12.7	13.0	13.5
R ₂ O	10.6	10.3	9.0	9.0	9.0	9.5	9.5	9.5
LiNa/K	0.77	0.84	2.6	2.6	2.6	1.71	1.57	1.50
Al (ZrKLa) /RO	5.81	5.23	2.54	2.60	2.50	4.02	3.70	3.83
LaTi·CaMg/Zr	2.52	2.63	7.78	8.24	9.67	2.72	4.4	4.58
T _g	690	695	689	694	694	694	694	690
α	80	81	75	75	75	76	77	78
d	2.66	2.67	2.65	2.65	2.63	2.68	2.63	2.66
E	80.2	80.4	83.4	83.0	83.2	80.5	80.8	82.1
E/d	30.2	30.2	31.5	31.4	31.6	30.0	30.7	30.9
T ₄	1236	—	—	1165	—	—	—	—
T _L	1150	1150	1170	1170	1190	1160	1150	1140
Phase separation property 1	—	—	—	—	—	—	—	—
Phase separation property 2	31	—	92	—	—	30	57	—
Surface roughness	0.10	—	0.13	0.12	—	—	—	—

TABLE 7

Examples	49	50	51	52	53	54	55	56
SiO ₂	63.0	63.0	67.5	65.0	62.5	60.0	57.5	62.5
Al ₂ O ₃	7.5	7.5	5.0	7.5	10.0	10.0	10.0	6.0
MgO	6.0	7.5	2.0	6.0	2.0	2.0	2.0	4.0
CaO	5.0	5.0	2.0	6.0	2.0	2.0	2.0	1.5
SrO	1.75	1.75	7.0	2.5	7.0	7.0	7.0	5.5
BaO	1.5	1.5	2.5	0	2.5	5.0	7.5	5.0
ZnO	0	0	0	0	0	0	0	0
TiO ₂	1.5	1.5	1.5	2.0	1.5	1.5	1.5	2.0
ZrO ₂	3.0	1.5	3.0	1.0	3.0	3.0	3.0	4.0
Li ₂ O	1.5	1.5	0	0	0	0	0	0
Na ₂ O	2.0	2.0	4.8	4.0	4.0	4.0	4.0	2.0
K ₂ O	6.25	6.25	3.2	5.0	4.0	4.0	4.0	5.5
La ₂ O ₃	1.0	1.0	1.5	1.0	1.5	1.5	1.5	2.0
RO	14.25	15.75	13.5	14.5	13.5	16.0	18.5	16.0
R ₂ O	9.75	9.25	8.0	9.0	8.0	8.0	8.0	7.5
LiNa/K	0.56	0.56	1.50	0.80	1.00	1.00	1.00	0.36
Al (ZrKLa)/RO	5.92	4.17	2.85	3.62	6.30	5.31	4.59	4.31
LaTi·CaMg/Zr	9.17	20.83	4	36	4	4	4	5.5
T _g	666	663	679*	702	715*	714*	713*	724*
α	75.2	81.5	77.0*	83	74.0*	77.4*	80.7*	76.8*
d	2.67	2.73	2.90*	2.67	2.91*	3.02*	3.12*	3.05*
E	81.9	82.1	81.2*	81.0	82.4*	83.0*	83.7*	83.8*
E/d	30.7	30.1	28.0*	30.4	28.3*	27.5*	26.8*	27.5*
T ₄	1210*	1166*	1158*	—	1197*	1170*	1150*	1159*
T _L	>1300	1190		1160	1240	1280	1230	1270
Phase separation property 1	—	—		—	—	—	—	—
Phase separation property 2	—	—		671	—	—	—	—
Surface roughness	—	—		0.20	—	—	—	—

TABLE 8

Examples	57	58	59	60	61	62	63	64	65
SiO ₂	61.25	55.0	55.0	58.5	56.5	57.5	66.5	60.0	65.0
Al ₂ O ₃	7.5	14.0	10.0	12.0	12.0	11.0	4.7	8.5	7.5
MgO	7.0	2.0	3.0	3.0	2.0	2.0	3.4	7.0	6.0
CaO	8.0	2.0	5.0	3.0	2.0	2.0	6.2	4.5	8.0
SrO	2.25	4.75	8.0	7.0	6.5	5.0	4.7	7.0	2.5
BaO	0	8.0	0	4.0	8.0	8.0	3.6	0	0
ZnO	0	0	0	0	0	2.0	0	0	0
TiO ₂	1.5	2.0	3.5	0	2.0	1.0	0	3.5	0
ZrO ₂	3.0	2.5	2.0	3.0	2.5	2.0	1.7	1.0	1.0
Li ₂ O	0.8	0	0	0	0	0	0	0	0
Na ₂ O	1.2	3.0	3.5	1.0	2.75	3.0	4.8	4.0	4.0
K ₂ O	6.5	5.0	5.0	6.0	4.0	4.0	4.4	4.5	5.0
La ₂ O ₃	1.0	1.75	5.0	2.5	1.75	2.5	0	0	1.0
RO	17.25	16.75	16.0	17.0	18.5	17.0	17.9	18.5	16.5
R ₂ O	8.5	8.0	8.5	7.0	6.75	7.0	9.2	8.5	9.0
LiNa/K	0.31	0.6	0.7	0.17	0.69	0.75	1.09	0.89	0.80
Al (ZrKLa) /RO	4.57	7.73	7.5	8.12	5.35	5.5	1.6	2.53	3.18
LaTi·CaMg/Zr	12.5	6	34	5	6	7	0	40.25	14
Tg	709	741	739	768	733	717	691	691	698
α	76.9	79.0	84.8	75.4	78.7	78.6	81	81	80
d	2.74	3.08	2.96	3.05	3.13	3.18	2.77	2.71	2.67
E	85.4	83.7	86.4	82.9	86.3*	82.8	76.5	82.4	81.3
E/d	31.2	27.1	29.2	27.2	27.2*	26.1	27.6	30.4	30.5
T ₁	1178*	1203*	1019*	1169*	1173	1175*	1145	1147	—
T _L	>1300	>1300	>1300	>1300	>1300	1290	1080	1140	1160
Phase separation property 1	×	—	—	—	—	—	—	—	—
Phase separation property 2	—	—	—	—	—	—	12	954	354
Surface roughness	—	—	—	—	—	—	0.10	0.17	0.18

TABLE 9

Examples	1	2	3	4	5	6	7	8
SiO ₂	41.75	44.83	45.61	48.10	49.72	49.14	50.17	50.70
Al ₂ O ₃	9.24	9.51	8.38	9.79	7.37	7.22	6.55	6.62
MgO	0.97	1.00	3.06	1.03	3.44	1.87	1.04	1.05
CaO	1.36	1.39	1.42	1.44	1.47	1.44	1.44	1.46
SrO	8.77	9.02	9.18	9.29	4.36	9.08	9.32	9.42
BaO	18.53	14.30	10.67	9.82	11.08	9.88	9.85	9.95
ZnO	0	0	0	0	0	0	0	0
TiO ₂	1.45	1.49	2.02	1.54	1.57	1.54	1.54	1.56
ZrO ₂	4.47	4.60	4.68	4.73	4.86	4.76	4.75	4.80
Li ₂ O	0	0	0	0	0	0	0	0
Na ₂ O	3.00	3.08	0.78	3.18	1.06	0.88	1.19	3.22
K ₂ O	4.55	4.69	5.96	4.83	8.66	7.89	7.87	4.89
La ₂ O ₃	5.91	6.08	8.24	6.26	6.42	6.30	6.28	6.34

TABLE 10

Examples	9	10	11	12	13	14	15	16
SiO ₂	52.30	54.29	55.16	54.38	53.56	53.89	54.69	54.38
Al ₂ O ₃	5.34	6.83	10.24	9.45	10.18	10.15	9.97	10.17
MgO	2.64	1.08	4.05	4.31	4.89	4.64	4.81	4.60
CaO	0	1.50	4.83	3.20	3.20	3.75	4.44	4.00
SrO	9.49	9.71	5.95	8.12	7.39	5.45	4.02	4.87
BaO	8.03	5.13	2.20	2.19	2.19	2.18	2.21	2.19
ZnO	0	0	0	0	0	0	0	0
TiO ₂	1.05	1.60	1.15	1.71	1.71	1.71	1.72	1.14
ZrO ₂	4.03	4.95	2.21	2.63	2.64	2.63	2.66	2.90
Li ₂ O	0	0	0	0	0	0	0	0
Na ₂ O	2.43	3.32	1.78	2.65	2.21	2.29	2.41	2.30
K ₂ O	6.17	5.04	7.77	6.71	7.39	7.50	7.45	7.65
La ₂ O ₃	8.53	6.54	4.67	4.64	4.65	5.79	5.62	5.81

TABLE 11

Examples	17	18	19	20	21	22	23	24
SiO ₂	45.45	42.30	50.53	47.89	44.72	46.73	44.04	43.78
Al ₂ O ₃	16.10	18.27	8.75	8.45	13.20	14.42	13.00	15.50
MgO	1.59	1.03	2.13	3.60	1.57	1.71	1.54	1.53
CaO	2.21	1.44	1.48	0.72	3.63	3.97	3.57	3.55
SrO	10.91	6.30	9.58	2.64	10.73	11.72	10.57	10.50
BaO	0	15.70	6.07	13.69	0	0	0	0
ZnO	0	0	0	0	0	0	0	0
TiO ₂	1.58	2.05	1.58	1.02	3.62	3.96	1.53	1.52
ZrO ₂	6.48	3.94	4.23	3.93	3.19	3.49	3.14	3.12
Li ₂ O	0	0	0	0	0	0	0	0
Na ₂ O	2.85	2.38	1.23	1.58	2.81	3.07	2.77	2.75
K ₂ O	6.20	6.03	8.33	7.81	6.10	6.66	6.00	5.97
La ₂ O ₃	10.72	7.30	6.45	8.31	10.54	23.04	18.69	10.32

TABLE 12

Examples	25	26	27	28	29	30	31	32
SiO ₂	45.27	46.36	47.73	58.71	59.24	56.42	55.78	57.09
Al ₂ O ₃	13.36	16.42	16.91	11.24	11.25	11.05	10.49	10.96
MgO	1.58	2.70	2.78	3.55	3.56	3.49	4.61	4.57
CaO	3.67	0.75	0	4.94	4.95	4.86	3.20	3.83
SrO	10.86	11.12	11.45	3.81	3.81	3.74	3.70	2.71
BaO	0	0	0	0	0	0	4.38	1.78
ZnO	0	0	0	0	0	0	0	0
TiO ₂	1.57	1.61	1.66	0.59	0	0	0	0
ZrO ₂	6.46	6.61	6.81	1.81	1.81	5.34	2.99	3.22
Li ₂ O	0	0	0	0	0	0	0	0
Na ₂ O	2.84	2.91	3.00	3.64	3.65	3.58	2.66	3.78
K ₂ O	6.17	6.32	6.51	6.92	6.93	6.80	7.54	6.84
La ₂ O ₃	10.67	10.93	15.76	4.79	4.79	4.71	4.65	5.21

TABLE 13

Examples	33	34	35	36	37	38	39	40
SiO ₂	57.03	57.70	57.27	56.31	56.92	56.38	54.92	55.77
Al ₂ O ₃	11.14	10.98	10.82	10.63	11.18	10.65	11.33	10.77
MgO	4.76	2.93	3.76	3.69	4.02	3.98	3.08	3.69
CaO	4.80	4.08	2.01	0	0.80	0.79	0	0
SrO	2.60	4.52	5.20	8.76	5.90	5.85	8.64	8.61
BaO	1.36	1.34	1.32	1.30	1.31	1.30	1.28	1.30
ZnO	0	0	0	0	0	0	0	0
TiO ₂	0	0	0	0	0	0	0	0
ZrO ₂	3.27	4.48	3.53	3.47	3.51	3.48	4.28	4.34
Li ₂ O	0	0	0	0	0	0	0	0
Na ₂ O	3.84	4.06	4.00	3.93	3.80	3.76	3.70	3.49
K ₂ O	7.58	7.54	7.43	7.30	7.92	7.84	8.24	8.36
La ₂ O ₃	3.61	2.37	4.67	4.59	4.64	5.98	4.53	3.67

TABLE 14

Examples	41	42	43	44	45	46	47	48
SiO ₂	57.56	57.42	59.65	59.41	59.99	58.40	59.90	58.60
Al ₂ O ₃	11.35	11.20	11.04	11.49	11.57	11.09	11.18	11.23
MgO	2.62	2.74	4.85	4.85	5.18	2.92	3.28	3.32
CaO	3.65	3.81	5.06	5.06	5.09	2.85	4.57	4.61
SrO	4.79	4.79	1.56	1.56	0.78	6.31	3.07	3.50
BaO	0	0.44	0	0	0	0	0	0
ZnO	0	0	0	0	0	0	0	0
TiO ₂	0	0	0	0	0	0	0	0
ZrO ₂	4.45	4.45	3.34	3.15	2.80	4.47	3.65	3.98
Li ₂ O	0	0	0	0	0	0	0	0
Na ₂ O	4.12	4.21	6.06	6.05	6.10	5.39	5.33	5.19
K ₂ O	8.17	7.63	3.54	3.54	3.56	4.78	5.16	5.26
La ₂ O ₃	3.30	3.30	4.90	4.90	4.93	3.78	3.86	4.31

TABLE 15

Examples	49	50	51	52	53	54	55	56
SiO ₂	49.81	50.70	46.64	57.14	46.55	45.18	43.89	43.76
Al ₂ O ₃	17.34	17.65	15.15	11.19	15.93	15.46	15.02	15.50
MgO	1.71	1.74	1.09	3.54	1.57	1.53	1.48	1.53
CaO	2.38	2.43	1.51	4.92	2.19	2.13	2.07	2.13
SrO	10.28	10.46	9.80	3.79	8.10	5.24	5.09	5.25
BaO	4.35	8.85	16.56	0	0	0	3.77	3.88
ZnO	0	0	0	0	0	0	0	0
TiO ₂	0	0	1.07	2.34	1.56	1.51	1.47	1.52
ZrO ₂	5.24	5.33	3.33	1.80	6.42	6.23	6.05	6.24
Li ₂ O	0	0	0	0	0	0	0	0
Na ₂ O	2.64	0.89	2.51	3.63	2.82	2.74	2.66	4.32
K ₂ O	8.01	8.15	5.09	6.89	6.13	8.33	5.78	5.97
La ₂ O ₃	11.54	11.75	8.75	4.77	10.61	10.29	10.00	10.32

TABLE 16

Examples	57	58	59	60	61	62	63	64	65
SiO ₂	49.82	41.85	41.14	43.21	42.06	42.07	57.74	52.97	57.54
Al ₂ O ₃	16.17	13.58	13.36	14.03	13.66	13.66	6.93	12.73	11.27
MgO	1.16	0.98	0.96	1.01	0.98	0.98	1.98	4.14	3.56
CaO	1.62	1.36	1.34	1.40	1.37	1.37	5.02	3.71	6.61
SrO	10.46	8.79	6.17	9.07	8.83	8.83	7.04	10.66	3.82
BaO	17.69	14.86	14.61	11.51	11.20	11.20	7.98	0	0
ZnO	0	0	1.94	2.04	1.98	1.98	0	0	0
TiO ₂	1.15	0.97	0.95	1.00	0.97	0.97	0	4.11	0
ZrO ₂	3.55	2.99	2.93	3.08	1.50	0	3.03	1.81	1.82
Li ₂ O	0	0	0	0	0	0	0	0	0
Na ₂ O	2.68	2.25	2.21	2.33	2.26	2.26	4.30	3.64	3.65
K ₂ O	5.43	4.56	4.49	4.71	4.59	4.59	5.99	6.23	6.94
La ₂ O ₃	11.75	5.94	9.70	10.19	9.92	9.92	0	0	4.80

INDUSTRIAL APPLICABILITY

The present invention is useful for a data recording medium, its substrate and their production.

- 5 The entire disclosure of Japanese Patent Application No. 2008-16550 filed on January 28, 2008 including specification, drawings and summary is incorporated herein by reference in its entirety.

Claims:

1. Glass for a data storage medium substrate, which comprises, as represented by mol percentage based on the following oxides, from 55 to 70% of SiO_2 , from 2.5 to 9% of Al_2O_3 , from 0 to 10% of MgO , from 0 to 7% of CaO , from 0.5 to 10% of SrO , from 0 to 12.5% of BaO , from 0 to 2.5% of TiO_2 , from 0.5 to 3.7% of ZrO_2 , from 0 to 2.5% of Li_2O , from 0 to 8% of Na_2O , from 2.5 to 8% of K_2O and from 0.5 to 5% of La_2O_3 , provided that Al_2O_3 and ZrO_2 ($\text{Al}_2\text{O}_3 + \text{ZrO}_2$): is at most 12%, and Li_2O , Na_2O and K_2O (R_2O): is at most 12%, and which glass has a glass transition temperature of at least 660° C.

2. The glass for a data storage medium substrate according to claim 1, wherein SiO_2 is at least 60 mol %, MgO is at least 2 mol %, BaO is from 0 to 5 mol %, TiO_2 is from 0 to 1 mol %, ZrO_2 is from 1 to 3.7 mol %, Na_2O is at least 2 mol %, La_2O_3 is at most 3 mol %, and MgO , CaO , SrO and BaO ($\text{MgO} + \text{CaO} + \text{SrO} + \text{BaO}$) is at least 10 mol %.

3. The glass for a data storage medium substrate according to claim 2, wherein the mol ratio of Li_2O and Na_2O to the K_2O content ($(\text{Li}_2\text{O} + \text{Na}_2\text{O})/\text{K}_2\text{O}$): is at most 3.0.

4. The glass for a data storage medium substrate according to claim 2, wherein a value obtained by dividing a product of the sum of MgO and CaO contents multiplied by the sum of La_2O_3 and TiO_2 contents, by ZrO_2 content $((\text{MgO} + \text{CaO}) \times (\text{La}_2\text{O}_3 + \text{TiO}_2) / \text{ZrO}_2)$: is at most 12.0 mol %.

5. The glass for a data storage medium substrate according to claim 2, wherein the ratio of SiO_2 content as represented by mass percentage to the sum of TiO_2 and ZrO_2 contents ($\text{SiO}_2 / (\text{TiO}_2 + \text{ZrO}_2)$), is more than 10.0.

6. The glass for a data storage medium substrate according to claim 2, which contains no TiO_2 .

7. The glass for a data storage medium substrate according to claim 1, wherein R_2O is at least 5 mol %.

8. The glass for a data storage medium substrate according to claim 1, which contains no B_2O_3 .

9. The glass for a data storage medium substrate according to claim 1, which has a glass transition temperature of at least 680° C.

10. The glass for a data storage medium substrate according to claim 1, which has an average linear expansion coefficient of at least $75 \times 10^{-7}/^{\circ}\text{C}$. within a range of from 50 to 350° C.

11. The glass for a data storage medium substrate according to claim 1, of which temperature at which the viscosity becomes 10^4 dPa·s is at least a liquidus temperature.

12. The glass for a data storage medium substrate according to claim 1, comprising from 61 to 70% of SiO_2 .

13. The glass for a data storage medium substrate according to claim 1, which has a density of at most 2.8 g/cm^3 .