

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
28 December 2000 (28.12.2000)

PCT

(10) International Publication Number
WO 00/78820 A1

(51) International Patent Classification⁷: C08F 4/658,
10/00

(IT). BRITA, Diego [IT/IT]; Via Mulinetto, 63, I-44100
Ferrara (IT).

(21) International Application Number: PCT/EP00/05349

(74) Agents: COLUCCI, Giuseppe; Montell Italia S.p.A., In-
tellectual Property, P.le G. Donegani, 12, I-44100 Ferrara
et al. (IT).

(22) International Filing Date: 8 June 2000 (08.06.2000)

(25) Filing Language: English

(81) Designated States (*national*): AU, BR, CA, CN, HU, IL,
IN, JP, KR, MX, RU, SG, US, ZA.

(26) Publication Language: English

(84) Designated States (*regional*): European patent (AT, BE,
CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC,
NL, PT, SE).

(30) Priority Data:
99201969.5 18 June 1999 (18.06.1999) EP

Published:

- With international search report.
- Before the expiration of the time limit for amending the
claims and to be republished in the event of receipt of
amendments.

(71) Applicant (*for all designated States except US*): BASELL
TECHNOLOGY COMPANY B.V. [NL/NL]; Hoeksteen
66, NL-2132 MS Hoofddorp (NL).

(72) Inventors; and

*For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.*

(75) Inventors/Applicants (*for US only*): SACCHETTI,
Mario [IT/IT]; Viale Krasnodar, 138, I-44100 Ferrara



WO 00/78820 A1

(54) Title: CATALYST COMPONENTS FOR THE POLYMERIZATION OF OLEFINS AND CATALYSTS THEREFROM OB-
TAINED

(57) Abstract: The invention relates to catalyst components, suitable for the preparation of homopolymers and copolymers of ethy-
lene having a broad molecular weight distribution (MWD), which comprise Ti, Mg, Cl, and are characterized by the following
properties: surface area, determined by BET method, of lower than 100 m²/g, a total porosity, measured by the mercury method, of
higher than 0.25 cm³/g, a pore radius distribution such that at least 45% of the total porosity is due to pores with radius up to 0.1 µm.