

5

**METHOD FOR PREPARING POLYOLEFINS
CONTAINING A HIGH PERCENTAGE
OF EXO-OLEFIN CHAIN ENDS**

FIELD OF THE INVENTION

- 10 This application claims the benefit of U.S. Provisional Application No. 60/603,422, filed August 20, 2004.

The present invention is directed to a method for preparing polyolefins containing a high percentage of exo-olefin chain ends. The method involves ionizing a polyolefin containing tert-chloride chain ends and reacting the
15 ionized polyolefin with one or more nitrogen-containing five-membered aromatic ring or one or more hindered secondary or tertiary amines, or mixtures thereof.

BACKGROUND OF THE INVENTION

- Linear polyolefins made using a mono-functional initiator containing a single
20 "exo-olefin", "di-substituted" olefin, or "methyl vinylidene group," end group are useful precursors for the preparation of polymers containing specific functional end groups. Polymers made using multi-functional initiators would have multiple exo-olefinic end groups. Polymers containing specific end groups are useful as lubricating oil additives. One example of a functionalized
25 polymer containing hetero atoms is polyisobutenylsuccinic anhydride. Functional end groups may also be desirable for making polymers with potential for further reactions.

- Conventional ionic polymerizations can be anionic or cationic. Anionic polymerizations proceed, in the presence of a base, through carbanions and
30 favor monomers having electron withdrawing groups. Cationic polymerizations proceed, in the presence of an acid, through a carbocation, also called a carbenium ion, and favor monomers that have electron releasing groups.

5 Similarly to the conventional polymerization systems, living polymerization systems may be either anionic or cationic. The difference between conventional polymerizations and living polymerizations is that an ideal living polymerization proceeds in the absence of chain transfer and chain
10 importance because the degree of polymerization may be controlled by controlling the feed ratio of monomer to initiator and sequential addition of two or more different monomers affords the ability to produce block copolymers. Polymerization continues until the monomer is exhausted, but the polymers retain their ability to add additional monomers any time in the
15 future. A number of such systems are well known in the art.

A further development is the cationic quasi-living polymerization systems using conventional monomers. Quasi-living polymerization requires certain restrictive conditions, for example anhydrous reagents. Cationic quasi-living polymerizations differ from truly living polymerizations in that, although the
20 rate of chain transfer approaches zero, chain termination is present but reversible. One important example of a cationic quasi-living polymerization is the cationic quasi-living polymerization of isobutylene.

Typically, cationic quasi-living polymerizations of isobutylene yield narrow molecular weight distribution and one major polymer product containing the
25 2-chloro-2-methylpropyl end group, also referred to as the "tert-chloride" end group. Under certain conditions minor amounts of olefinic isomers may also be produced.

On the other hand, there are two major olefinic isomers produced during conventional polymerization of isobutylene with BF_3 , for example, the highly
30 reactive exo-olefin isomer and the relatively unreactive 2-methyl-1-propenyl isomer, also referred to as the "tri-substituted" isomer or "endo olefin" isomer. Furthermore, conventional polymerizations of isobutylene yield polymers with broad molecular weight distributions or polydispersity indices.

- 5 Exclusive production of the exo-olefin isomer has not been previously achieved under conventional polymerization conditions for isobutylene.

There are two established methods for producing polyisobutylene containing only the exo-olefin end group. One method involves chemical dehydrohalogenation of tert-chloride terminated polyisobutylene using
10 potassium tert-butoxide in a post polymerization reaction (U.S. Patent No. 4,342,849). The other method involves in situ quenching of quasi-living isobutylene with methallyltrimethylsilane, which converts an active, living carbenium ion to the exo-olefin end group. (M. Roth and H. Mayr, Macromolecules, 29, 6104, 1996)

- 15 Polyisobutylene polymers containing more than one exo-olefin end group may be prepared using the above methods by the use of a multi-functional initiator.

The preparation of polyolefins, including polyisobutylene polymers, is well known in the art. A number of patents have discussed processes for making polyisobutylene polymers containing exo-olefin end groups, but none using
20 reacting an ionized polyolefin with a nitrogen-containing five-membered aromatic ring compound or a hindered secondary or tertiary amine.

European Patent No. 341012 discloses a method for producing polymers with narrow molecular weight distribution, where the ratio of the weight average molecular weight, $M(w)$, to the number average molecular weight, $M(n)$,
25 approaches 1.

U.S. Patent No. 4,152,499 discloses isobutene polymers having a mean degree of polymerization from 10 to 100 and where the proportion of theoretically possible terminal double bonds is greater than in conventional products. The patent also discloses the method of making the isobutene
30 polymers using boron trifluoride as the initiator.

U.S. Patent No. 4,342,849 discloses the synthesis of polyisobutylene carrying either unsaturation or hydroxyl groups at both ends, in the case of a linear

5 polymer, or at all ends in the case of a star polymer. The method involves the steps of refluxing a solution of telechelic di-halogen polyisobutylene, adding a solution strong base such as potassium t-butoxide and stirring to form the telechelic di-olefin polyisobutylene.

U.S. Patent No. 4,393,199 discloses a method for carrying out cationic
10 polymerization with molecular weight control in which a pre-initiator and a catalyst effective for cationic polymerization are mixed with a monomer. The resulting living polymer is then treated as desired.

U.S. Patent No. 4,758,631 discloses a method of preparing allyl-terminated polyisobutylene by allylation with allyltrimethylsilane of tertiary chloro-capped
15 polyisobutylene by electrophilic substitution. The synthesis begins with the boron trichloride catalyzed mono- or oligo-tertiary chloride "inifer" initiated polymerization of isobutylene, followed in the same reaction vessel by the addition of hexane, allyltrimethylsilane and titanium tetrachloride.

U.S. Patent Nos. 4,910,321 and 5,122,572 disclose a catalyst composed of a
20 complex of an organic acid or its ester and a Lewis acid, preferably boron trichloride that can add olefin monomers to increase the molecular weight of the complex from as low as 200 to in excess of a million. The patents also disclose polymers of different molecular weights having useful end groups such as halogens and specifically chloride, allyl, acryl or methacryl, acetate or
25 formate.

U.S. Patent Nos. 4,929,683 and 5,066,730 disclose a catalyst composed of a complex of an organic ether and a Lewis acid, preferably boron trichloride that can add olefin monomers to increase the molecular weight of the complex from as low as 200 to in excess of a million. The patents also disclose
30 polymers of different molecular weights having useful end groups such as halogens and specifically chloride, allyl, acryl or methacryl, acetate or formate.

U.S. Patent No. 5,219,948 discloses a method for preparing elastomeric polymers comprising alpha-olefins or conjugated alkadienes by cationic

- 5 polymerization in the presence of titanium tetrachloride and an electron pair donor selected from pyridine or a non-hindered alkylpyridine. The polymers have very narrow, mono-modal molecular weight distribution.

U.S. Patent No. 5,336,745 discloses a method for the direct synthesis of polymeric materials functionalized with desirable nitrogen-containing
10 functional groups such as terminal azido, cyano, carbonylamino or thiocarbonylamino groups. Polymerization and functionalization occur in a substantially simultaneous manner.

U.S. Patent No. 5,428,111 discloses a process for the living polymerization of aromatic, preferably styrenic monomers initiated from a living polyolefin,
15 particularly polyisobutylene, chain end for making block copolymers having polyolefin mid-blocks and styrenic end-blocks.

U.S. Patent No. 5,448,000 discloses a one-pot method of preparing sulfonic acid-terminated polyisobutylene by sulfonation with acetyl sulfate of a living polyisobutylene in a single step. The method involves "inifer" initiated
20 carbocationic polymerization with Lewis acid to form the polymer followed by the sulfonation.

U.S. Patent Nos. 5,637,647 and 5,677,386 disclose the capping of a living polymer with one or more capping compounds comprising non-polymerizable monomer selected from a group consisting of substituted or unsubstituted
25 diphenyl alkylene, methoxystyrene, trans-stilbene, 1-isopropenylnaphthalene and 2,4-dimethyl styrene.

U.S. Patent Application No. 10/433,439, Publication No. 2004/0015029 A1, discloses a process for the preparation of polyisobutylenes in which at least 60 percent of the polymer chains have at least one olefinically unsaturated
30 terminal group, by cationic polymerization of isobutene or isobutene-containing monomer mixtures in the condensed phase and in the presence of an initiator system.

5 U.S. Patent Application Serial No. 10/600,898, Publication No. 2004/0260033 A1, discloses the method for manufacturing and producing monodisperse telechelic polymers through cationic polymerization of suitable monomer under living polymerization conditions and quenching the polymerization with an N-substituted-pyrrole. The functionalized polymers containing N-
10 substituted-pyrroles may be employed as fuel additives and/or lubricating oil additives.

PCT International Application No. PCT/EP/05472, International Publication No. WO99/09074, discloses a process for functionalizing polymers prepared by cationic polymerization wherein a living carbocationic polymerization
15 system is reacted with one or more aromatic ring systems, and the use of substituted or unsubstituted reaction products of said process in lubricating oil or fuel compositions and additive concentrates, for example as dispersants, detergents or antioxidant additives or VI improvers.

β -Proton elimination by Free Bases in the Living cationic Polymerization of
20 Isobutylene, by Young Cheol Bae and Rudolf Faust, *Macromolecules*, Volume 30, 7341-7344 (1997). The authors investigated β -proton elimination from quasi-living polyisobutylene, after observing *exo*-olefin formation in the presence of 2,6-di-*tert*-butylpyridine (DTBP) of low purity. They ascribed elimination to the presence of a sterically hindered cyclic imine base present
25 in the DTBP in a concentration of 6×10^{-6} moles per liter. They simulated this impurity using 2-*tert*-butylpyridine (TBP) and discovered that the latter, when added to the reactor at the start of the polymerization (i.e., in the presence of monomer) resulted in about 65 percent elimination after 3 hours of reaction time to produce exclusively *exo*-olefin. When the extent of elimination had
30 reached 20 percent or higher, significant coupling was observed from both ^1H NMR and GPC analyses. Bae and Faust clearly considered that elimination by sterically hindered bases, such as TBP, was undesirable and should be avoided. The first paragraph of the paper was summarized as follows:
"Finally, strong bases may also eliminate β -protons, which should be
35 avoided." Later, they refer to the cyclic imine base impurity in DTBP as "the

- 5 culprit." Finally, they summarized the entire paper by saying that the elimination process should be avoided for polymer preparation purposes, although it might facilitate the measurement of kinetic rate constants: "While β -proton elimination should be avoided for the synthesis of well-defined macromolecules, if diffusion control of this process can be shown, it may
- 10 provide a novel method of establishing the concentration of active centers, from which absolute propagation rate constants could be calculated."

SUMMARY OF THE INVENTION

- Disclosed herein is a method for preparing polyolefins containing a high percentage of exo-olefin chain ends. The method may involve
- 15 ionizing a polyolefin containing terminal tert-chloride chain ends and reacting the ionized polyolefin with one or more nitrogen-containing five-membered aromatic ring compounds or one or more hindered secondary or tertiary amines, or mixtures thereof.

- 20 In one aspect, there is provided a method for preparing a polyolefin product containing exo-olefin chain ends on the polyolefin polymer chain, which method comprises:

- (a) ionizing a polyolefin containing terminal tert-chloride chain ends on the polymer chain in the presence of a Lewis acid; and
- (b) reacting the ionized polyolefin with one or more nitrogen-
25 containing five-membered aromatic ring compounds selected from pyrroles and imidazoles having at least two hydrocarbyl substituents on the ring, or one or more hindered secondary or tertiary amines containing only carbon, hydrogen, and nitrogen atoms, or mixtures thereof, provided the nitrogen containing five-
30 membered aromatic ring is not:
 - (i) 2,4-dimethylpyrrole;
 - (ii) 2-phenylindole;

- 5 (iii) 2-methylbenzimidazole;
 (iv) 1,2-dimethylimidazole;
 (v) 2-phenylimidazole; and
 (vi) 2,4,5-triphenylimidazole;

and provided the hindered secondary or tertiary amines are not:


- 10 (i) Triethylamine;
 (ii) Tri-n-butylamine;
 (iii) Trihexylamine;
 (iv) Triisooctylamine;
 (v) 2-phenylpyridine;
15 (vi) 2,3-cyclododecenopyridine;
 (vii) Di-p-tolylamine;
 (viii) Quinaldine; and
 (ix) 1-pyrrolidino-1-cyclopentene;

20 to thereby obtain the polyolefin product containing exo-olefinic end groups on
 the polyolefin polymer chain.

Preferably the polyolefin is polyisobutylene.

Preferably steps (a) and (b) are independently carried out at a temperature in
the range of from about -130°C to about 10°C. More preferably steps (a) and
(b) are independently carried out at a temperature in the range of from about
25 -80°C to about 0°C. Yet more preferably steps (a) and (b) are independently
carried out at a temperature in the range from about -70°C to about -10°C.
Most preferably steps (a) and (b) are independently carried out at a
temperature in the range from about -60°C to about -20°C.

- 5 In one embodiment of the above method the one or more nitrogen-containing five-membered aromatic ring compounds in step (b) is a substituted-pyrrole having the general formula:



wherein:

- 10 (a) R_1 and R_4 are independently an alkyl containing one carbon atom to about 20 carbon atoms, R_2 and R_3 are independently hydrogen or alkyl containing one carbon atom to about 20 carbon atoms, cycloalkyl of about 3 to about 7 carbon atoms, aryl of about 6 to about 30 carbon atoms, alkaryl of about 7 to about 30 carbon atoms, or aralkyl of about 7 to about 30 carbon atoms; or
- 15 (b) R_1 and R_2 form a fused aromatic ring of from 6 carbon atoms to 10 carbon atoms or aliphatic ring of from 4 carbon atoms to about 8 carbon atoms, R_4 is alkyl containing one carbon atom to about 20 carbon atoms, and R_3 is hydrogen or alkyl containing one carbon atom to about 20 carbon atoms, cycloalkyl of about 3 to about 7 carbon atoms, aryl of about 6 to about 30 carbon atoms, alkaryl of about 7 to about 30 carbon atoms, or aralkyl of about 7 to about 30 carbon atoms; or
- 20 (c) R_2 and R_3 form a fused aromatic ring of from 6 carbon atoms to 10 carbon atoms or aliphatic ring of from 4 carbon atoms to about 8 carbon atoms, and R_1 and R_4 are independently an alkyl containing one carbon atom to about 20 carbon atoms; or
- 25


- 5 (d) both R_1 and R_2 , and R_3 and R_4 , taken in pairs, independently form a aromatic ring of from 6 carbon atoms to 10 carbon atoms or aliphatic ring of from 4 carbon atoms to about 8 carbon atoms.

Preferably R_1 and R_4 are methyl and R_2 and R_3 are hydrogen.

- 10 In another preferred embodiment of the above method R_1 , R_2 , R_3 and R_4 are methyl.

In another preferred embodiment R_1 and R_2 are methyl and R_3 and R_4 form a fused benzo ring.


In a preferred embodiment the substituted-pyrrole has the following formula:



15

The nitrogen-containing five-membered aromatic ring employed in another embodiment of the present invention is a substituted imidazole.

The substituted imidazole in the method disclosed herein has the general formula:



20

wherein R_3 is branched alkyl containing from about 4 carbon atoms to about 20 carbon atoms, and wherein

- 5 (a) R_1 and R_2 are independently hydrogen, alkyl of one carbon atom to about 20 carbon atoms, cycloalkyl of about 3 to about 7 carbon atoms, aryl of about 6 to about 30 carbon atoms, alkaryl of about 7 to about 30 carbon atoms, or aralkyl of about 7 to about 30 carbon atoms; or
- 10 (b) R_1 and R_2 form a fused aromatic ring of from 6 carbon atoms to 10 carbon atoms or aliphatic ring of from 4 carbon atoms to about 8 carbon atoms.


In another preferred embodiment of the above method R_1 is methyl, R_2 is hydrogen and R_3 is tert-butyl.

- 15 Preferably the alkyl group on the nitrogen-containing five-membered aromatic ring in the method of the present invention has from about one carbon atom to about 20 carbon atoms. More preferably the alkyl group on the alkyl-substituted hetero-aromatic has from about one carbon atoms to about 12 carbon atoms. Most preferably the alkyl group on the alkyl-substituted
- 20 hetero-aromatic has from about one carbon atoms to about 4 carbon atoms.

- Preferably the Lewis acid in step (a) is a halide of titanium or boron. More preferably the Lewis acid is a titanium halide. Most preferably the Lewis acid is titanium tetrachloride. Preferred concentrations of the titanium tetrachloride exceed 2 times the combined concentrations of protic impurities, electron
- 25 donor, common ion salt or its precursor, and the quenching agent or quenching agents.

The hindered secondary or tertiary amine in step (b) in the above method may be a linear secondary or tertiary amine, a cyclic secondary or tertiary amine or an aromatic secondary or tertiary amine.

- 30 In an embodiment of the above method the hindered secondary or tertiary amine in step (b) has the general formula:



5


wherein R_1 , R_2 and R_3 are independently hydrogen, alkyl containing one carbon atom to about 20 carbon atoms, cycloalkyl of about 3 to about 7 carbon atoms, aryl of about 6 to about 30 carbon atoms, alkaryl of about 7 to about 30 carbon atoms, or aralkyl of about 7 to about 30 carbon atoms; or at least one of R_1 and R_2 , R_2 and R_3 and R_1 , taken in pairs, independently form a fused aliphatic ring of from about 4 carbon atoms to about 8 carbon atoms;

10

provided that no more than one of R_1 , R_2 and R_3 is hydrogen, and provided that R_1 , R_2 , and R_3 are not all linear alkyl of about 3 carbons or less.

15

In the above method the hindered amine is a tertiary or secondary amine has the general formula:




20

wherein R_6 is a divalent hydrocarbyl group of one carbon atom to about 4 carbon atoms each of which may be substituted with an alkyl group having one carbon atom to about 6 carbon atoms, and R_1 , R_2 , R_3 , R_4 , and R_5 are independently hydrogen, alkyl containing one carbon atom to about 20 carbon atoms, cycloalkyl of about 3 to about 8 carbon atoms, aryl of about 6 to about 30 carbon atoms, alkaryl of 7 to 30 carbon atoms, or aralkyl of 7 to 30 carbon atoms; provided if R_1 , R_2 , R_3 , and R_4 are hydrogen, then R_5 is a branched alkyl from about 4 to about 20 carbon atoms, aryl of about 6 to about 30 carbon atoms, or aralkyl of about 7 to about 30 carbon atoms, and provided if R_5 is hydrogen, then R_1 , R_2 , R_3 , and R_4 are not hydrogen, unless one of R_1

25


- 5 or R_2 and one of R_3 or R_4 is a branched alkyl having from about 4 to about 20 carbon atoms.

In a particularly preferred embodiment of the above method the hindered amine is a secondary or tertiary amine of the formula:




- 10 wherein R_5 is hydrogen or methyl.

In another preferred embodiment of the above method the hindered secondary or tertiary amine has the general formula:




- 15 wherein R is hydrogen or alkyl containing one to about 20 carbon atoms or an aromatic or aliphatic ring of about 3 carbon atoms to about 7 carbon atoms.

In a particularly preferred embodiment of the above method the hindered secondary or tertiary amine has the formula:




- 20 In a further preferred embodiment of the above method the hindered amine is a secondary amine of the formula:

5




In another preferred embodiment of the above method the hindered amine is a tertiary amine of the formula:




10

In yet another preferred embodiment of the above method the hindered amine is a tertiary amine of the formula:



15

The hindered secondary or tertiary amine in another embodiment of the method disclosed herein has the general formula:




20

wherein R_1 is a divalent hydrocarbyl group of one carbon atom to about 4 carbons and R_2 , R_3 , R_4 , R_7 , R_8 , and R_9 are independently hydrogen, alkyl containing one carbon atom to about 20 carbon atoms, cycloalkyl of about 3 to about 8 carbon atoms, aryl of about 6 to about 30 carbon


- 5 atoms, alkaryl of about 7 to about 30 carbon atoms, or aralkyl of about 7 to about 30 carbon atoms, and one of R_5 and R_6 is hydrogen and the other is linear alkyl from one carbon atom to about 20 carbon atoms.

10 In a preferred embodiment of the above method one of R_5 and R_6 is hydrogen.

In an embodiment of the above method the amine has the general formula:



- 15 In yet another preferred embodiment of the above method the hindered amine is a tertiary amine of the formula:




- 20 wherein one of R_1 and R_5 is hydrogen and the other is a branched alkyl of about 3 to about 20 carbon atoms, aryl of about 10 to about 30 carbon atoms, or aralkyl of about 11 to about 30 carbon atoms; R_2 , R_3 and R_4 are independently hydrogen, alkyl of one carbon atom to about 20 carbon atoms, cycloalkyl of about 3 to about 7 carbon atoms, aryl of about 6 to about 30 carbon atoms, alkaryl of about 7 to about 30 carbon atoms, or aralkyl of about 7 to about 30 carbon atoms; or at least one of R_1 and R_2 , R_2 and R_3 , R_3 and R_4 , and R_4 and R_5 , taken in pairs, independently form a fused aromatic ring of from 5 carbon atoms to 7 carbon atoms or aliphatic ring of from about 4 carbon atoms to about 8 carbon atoms,
- 25

5 provided that if R_1 and R_2 form a fused aliphatic or aromatic ring, then
 R_5 is a branched alkyl of about 3 to about 20 carbon atoms, aryl of
 about 10 to about 30 carbon atoms, or aralkyl of about 11 to about 30
 carbon atoms, and provided that if R_4 and R_5 form a fused aliphatic or
 aromatic ring, then R_1 is a branched alkyl of about 3 to about 20 carbon
 10 atoms, aryl of about 10 to about 30 carbon atoms, or aralkyl of about
 11 to about 30 carbon atoms.

In a further embodiment of the above method R_1 , R_2 , R_3 and R_4 are hydrogen
 and R_5 is tert-butyl.

15 In another embodiment of the method disclosed herein the hindered amine is nitrogen
 containing hetero-aromatic ring having the following formulas, (a), (b) and (c):




(a)

wherein in formula (a)

20 one of R_1 and R_4 is hydrogen and the other is alkyl of one carbon atom
 to about 20 carbon atoms, cycloalkyl of about 3 to about 8 carbon
 atoms, aryl of about 6 to about 30 carbon atoms, alkaryl of about 7 to
 about 30 carbon atoms, or aralkyl of about 7 to about 30 carbon atoms,
 one of R_2 and R_3 is hydrogen and the other is alkyl of one carbon atom
 to about 20 carbon atoms, cycloalkyl of about 3 to about 8 carbon
 25 atoms, aryl of about 6 to about 30 carbon atoms, alkaryl of about 7 to
 about 30 carbon atoms, or aralkyl of about 7 to about 30 carbon atoms;
 or at least one of R_1 and R_2 and R_3 and R_4 , taken in pairs,
 independently form a fused aromatic ring of from 5 carbon atoms to 7

- 5 carbon atoms or aliphatic ring of from about 4 carbon atoms to about 8 carbon atoms;




(b)

wherein in formula (b)

- 10 R₁, R₂ and R₄ are independently hydrogen or alkyl of one carbon atom to about 20 carbon atoms, cycloalkyl of about 3 to about 8 carbon atoms, aryl of about 6 to about 30 carbon atoms, alkaryl of about 7 to about 30 carbon atoms, or aralkyl of about 7 to about 30 carbon atoms, R₃ is hydrogen, alkyl of one carbon atom to about 20 carbon atoms, cycloalkyl of about 3 to about 8 carbon atoms, aryl of about 6 to about 30 carbon atoms, alkaryl of about 7 to about 30 carbon atoms, or aralkyl of about 7 to about 30 carbon atoms; or at least one of R₂ and R₃ or R₃ and R₄, taken in pairs, independently form a fused aromatic ring of from 5 carbon atoms to 7 carbon atoms or aliphatic ring of from about 4 carbon atoms to about 8 carbon atoms,
- 15 provided that if R₁ is hydrogen then R₂ and R₄ are independently alkyl of one carbon atom to about 20 carbon atoms, cycloalkyl of about 3 to about 8 carbon atoms, aryl of about 6 to about 30 carbon atoms, alkaryl of about 7 to about 30 carbon atoms, or aralkyl of about 7 to about 30 carbon atoms, and further provided that if R₂ or R₄ is
- 20 hydrogen, then R₁ is alkyl of one carbon atom to about 20 carbon atoms, cycloalkyl of about 3 to about 8 carbon atoms, aryl of about 6 to about 30 carbon atoms, alkaryl of about 7 to about 30 carbon atoms, or aralkyl of about 7 to about 30 carbon atoms;
- 25


5 and




wherein in formula (c)

10 R_1 , R_2 and R_3 are independently hydrogen or alkyl of one carbon to about 20 carbon atoms, cycloalkyl of about 3 to about 8 carbon atoms, aryl of about 6 to about 30 carbon atoms, alkaryl of about 7 to about 30 carbon atoms, or aralkyl of about 7 to about 30 carbon atoms.


In a preferred embodiment of the above method the hindered amine has the formula:



15 In a further embodiment of the above method the hindered amine has the formula:



20 In yet another preferred embodiment of the above method the hindered amine has the formula:



5

In the above method the exo-olefinic end group on the polymer chain of the polyolefin product in step (b) is present in the range of about one percent to about 100 percent of the total olefin yield. Preferably the exo-olefinic end group on the polymer chain in step (c) is at least 3 percent of the total olefin yield. More preferably the exo-olefinic end group on the polymer chain in step (c) is at least 20 percent, still more preferably at least 50 and most preferably at least 70 percent of the total olefin yield.

In another aspect, there is provided a method for preparing a polyolefin product containing exo-olefinic end groups on the polyolefin polymer chain, which method comprises:

- (a) ionizing a polyolefin containing terminal tert-chloride chain ends on the polymer chain in the presence of a Lewis acid; and
- (b) reacting the ionized polyolefin with one or more nitrogen-containing five-membered aromatic ring compounds selected from pyrroles and imidazoles having at least two hydrocarbyl substituents on the ring, or one or more hindered secondary or tertiary amines containing only carbon, hydrogen, and nitrogen atoms, or mixtures thereof, wherein the nitrogen-containing aromatic amine compounds or the hindered secondary or tertiary amines are pre-reacted with a Lewis acid, provided the nitrogen containing five-membered aromatic ring is not:

(i) 2,4-dimethylpyrrole;

(ii) 2-phenylindole;

- 5
- (iii) 2-methylbenzimidazole;
 - (iv) 1,2-dimethylimidazole;
 - (v) 2-phenylimidazole; and
 - (vi) 2,4,5-triphenylimidazole;

and provided the hindered secondary or tertiary amines are not:

- 10
- (i) Triethylamine;
 - (ii) Tri-n-butylamine;
 - (iii) Trihexylamine;
 - (iv) Triisooctylamine;
 - (v) 2-phenylpyridine;
 - 15 (vi) 2,3-cyclododecenopyridine;
 - (vii) Di-p-tolylamine;
 - (viii) Quinaldine; and
 - (ix) 1-pyrrolidino-1-cyclopentene;

20 to thereby obtain the polyolefin product containing exo-olefinic end groups on the polyolefin polymer chain.

The nitrogen containing five-membered aromatic ring compound in a preferred embodiment of the above method is 2,5-dimethyl pyrrole and the Lewis acid is Titanium tetrachloride.

25 In a preferred embodiment of the above method the Lewis acid is titanium tetrachloride and the hindered amine is 1,2,2,6,6-pentamethylpiperidine.

DETAILED DESCRIPTION OF THE INVENTION

Definitions


As used herein, the following terms have the following meanings unless expressly stated to the contrary:

- 5 The term "alkyl" as used herein refers to straight chain and branched chain saturated aliphatic groups typically having from one to about 20 carbon atoms. Some examples of straight chain and branched chain saturated aliphatic groups are methyl, ethyl, propyl, butyl, isopropyl, isobutyl, sec-butyl, tert-butyl, and the like.
- 10 The term "aromatic or aliphatic fused ring" as used herein refers to the ring formed by two adjacent carbon atoms on the pyrrole or imidazole ring, and the ring thus formed is fused to the pyrrole or imidazole ring. An example of a fused aromatic ring is a benzo group fused to the pyrrole ring or imidazole ring. A fused aliphatic ring may be any cyclic ring structure fused to the
- 15 pyrrole ring or imidazole ring.

The term "branched alkyl" as used herein refers to an alkyl group in which the carbon atom representing the point of attachment of the group to the rest of the molecule is either a tertiary or quaternary carbon atom. The term "tertiary carbon" as used herein refers to a carbon atom that is attached to three other carbon atoms.

20 carbon atoms. The term "quaternary carbon" as used herein refers to a carbon atom that is attached to 4 other carbon atoms.

The terms "carbenium ion" or "carbocation" as used herein refer to a positively charged carbon atom bearing three sp^2 -bonded substituents and an empty p orbital.



25

PIB Carbenium Ion

The term "chain transfer" as used herein refers to the cessation of growth of one polymerization chain with the possible initiation of another polymerization chain.

- The term "common ion salt" as used herein refers to an ionic salt that is
- 30 optionally added to a quasi-living cationic polymerization mixture to prevent

5 dissociation of the propagating carbenium ion and counter-ion pairs. The anion of the common ion salt is identical to the counter-ions of the propagating chain ends. The cation of the common ion salt is typically a fatty quaternary ammonium cation, such as tetra-n-butyl ammonium ion, which confers solubility in the organic media.


10 The term "coupled product" as used herein refers to the product of addition of a PIB terminal carbenium ion to a PIB exo-olefin chain end. Coupled product has a number average molecular weight that is approximately twice that of the main polymer product.

The term "coupling" as used herein refers to the addition of a polyisobutylene
15 terminal carbenium ion to a polyisobutylene exo-olefin chain end.

The term "conventional polymerization" as used herein refers to polymerization wherein the chain-reaction polymerization involving olefins proceeds with ions as chain carrying particles, either anions or cations. Polymerization proceeds through the steps of chain initiation, chain
20 propagation, chain transfer and chain termination.

The term "di-EAS product" as used herein refers to the product which results when two separate polyisobutylene terminal carbenium ions react to form a covalent bond with a single quenching agent molecule. Di-EAS product contains in its structure a residue from the quenching agent.

25 The terms "di-substituted olefin" or "exo-olefin" or "methyl vinylidene" as used herein refer to an olefin polymer chain containing an exo-olefin chain end as shown below.




The term "di-valent hydrocarbyl" as used herein refers to a hydrocarbyl group
30 which possesses two points of attachment to the rest of the molecule.

- 5 The term "EAS product" as used herein refers to the product which results when one polyisobutylene terminal carbenium ion reacts to form a covalent bond with a single quenching agent molecule. EAS product contains in its structure a residue from the quenching agent.

- The term "electron donor" as used herein refers to a basic and/or nucleophilic substance added to the polymerization reaction that is either fully complexed with the Lewis acid or fully non-complexed with the Lewis acid. The concentration of electron donor exceeds the concentration of the protic impurities, for example water.
- 10

- The term "electrophilic aromatic substitution or EAS" as used herein refers to the process by which the EAS product is produced.
- 15

The term "gem-dimethyl carbons" as used herein refers to the two methyl carbons alpha to the carbenium ion or the chloride bonded carbon of the polyolefin polymer chain end as depicted in the structure below.



- 20 The term "hydrocarbyl" refers to an organic radical primarily composed of carbon and hydrogen which may be aliphatic, alicyclic, aromatic or combinations thereof, e.g., aralkyl or alkaryl. Such hydrocarbyl groups may also contain aliphatic unsaturation, i.e., olefinic or acetylenic unsaturation, and may contain minor amounts of heteroatoms, such as oxygen or nitrogen, or
- 25 halogens, such as chlorine.

- The term "hindered secondary or tertiary amine" as used herein refers to a compound that is appropriately substituted such that it is sufficiently sterically hindered to be not fully complexed with the Lewis acid, yet sufficiently sterically hindered to allow its reaction with the carbenium ion. Preferably the hindered amine is a tertiary amine.
- 30

- 5 The term "Lewis acid" as used herein refers to a compound that can accept a pair of electrons to form a covalent bond.

The term "living polymerization" as used herein refers to the polymerizations that proceed in the absence of measurable chain transfer and chain termination.

- 10 The term "nitrogen-containing five-membered aromatic ring" as used herein refers to pyrroles and imidazoles containing at least one nitrogen atom in the aromatic ring and a maximum of 2 nitrogen atoms in the aromatic ring, and having from about 2 alkyl groups to about 4 alkyl groups containing from about one carbon atom to about 20 carbon atoms attached to the ring. Some
15 examples of nitrogen-containing five-membered aromatic ring compounds contemplated for use in the present invention are substituted-pyrroles.

The term "quasi-living polymerization" as used herein refers to living polymerizations wherein reversible chain terminations is operable, but irreversible chain termination and chain transfer approaches zero.

- 20 The term "polyolefin" as used herein refers to a polymer of one or more olefins, such as ethylene, propylene, styrene, isobutylene, etc.

The term "regiospecific" as used herein refers to chemical reactions that give exclusively or nearly exclusively one of several possible isomeric products.

- 25 The term "reacting agent" as used herein refers to a chemical compound which is added to the ionized polyolefin to react with the ionized polyolefin chain end.

The term "termination" as used herein refers to the chemical reaction that terminates polymerization process or the quenching reaction by destruction of the Lewis acid.


- 30 The term "terminator" as used herein refers to the chemical compound that terminates polymerization process or the quenching reaction, but may not

- 5 simultaneously initiate a new polymer chain. A number of alcohols may be used as terminators.

The term "tert-chloride" refers to the 2-chloro-2-methylpropyl end group on a polyolefin polymer chain.

Unless otherwise specified, all percentages are in weight percent.

- 10 It has been determined that the nitrogen-containing five-membered aromatic ring compounds, such as substituted-pyrroles and substituted-imidazoles, and hindered secondary and tertiary amines used as reacting agents in the preparation of polyolefin polymers of the present invention are capable of quantitatively converting polyolefin polymer endo-olefin chain ends and tert-
- 15 chloride chain ends to the exo-olefin chain ends. Without being bound by any theory it is believed that these reacting agents selectively catalyze the elimination of a proton exclusively from the gem-dimethyl carbon of the ionized polyisobutylene chain end as shown below.



- 20 This result was unexpected since the reacting agents used in the preparation of the polyolefin polymers of the present invention are known to quench living polymerizations by an addition mechanism. Compounds which provide the highest addition yields are typically substituted with electron donating groups located at strategic positions on the ring. It is believed that these substituents
- 25 provide stabilization for the Friedel-Craft intermediates formed when, for example polyisobutylene, carbenium ions react with olefins in the ring.

- The reacting agents used in the present invention are able to quantitatively convert polyolefin polymers containing tert-chloride chain ends to the exo-olefin chain ends. A 100 percent conversion was observed within 15
- 30 minutes after addition of the reacting agent.

5 General Procedure for Preparation of Polyolefin Polymers
 Containing Exo-olefin End Groups on the Chain

A typical procedure for the preparation of polyolefin polymers of the present invention is given below:

- 10 The method of the present invention may be conducted as a batch process, a continuous process, a semi-batch process or by any process known by persons skilled in the art.

The polymerization reaction is carried out under inert gas and in a substantially anhydrous environment. The reactor is charged with the
15 following reactants:

1. A polyolefin containing tert-chloride chain ends,
2. a diluent,
3. an electron donor or common ion salt,
4. monomers, and
- 20 5. a Lewis acid, which typically comprises a halide of titanium or boron;

The reaction mixture is equilibrated at the desired temperature, ranging from above -130°C to about 10°C. The method of the present invention may be carried out at any desired pressure, atmospheric, sub-atmospheric or super-atmospheric pressure.

- 25 6. One or more nitrogen-containing five-membered ring compounds or hindered secondary or tertiary amine reacting agents is added to the reaction mixture to react with the ionized polyolefin chain end.

Additional aliquots are removed from the reaction mixture at various time intervals after addition of the reacting agent to determine the concentration of
30 the exo-olefin chain ends on the polyolefin polymers. The reaction is

- 5 terminated in all the aliquot samples and the remaining reaction mixture with an appropriate alcohol equilibrated at the desired temperature.

Although, the concentration of the reactants may be varied to obtain the desired product, it has been found that certain ratios of the reactants are important for obtaining high exo-olefin chain end yield. The ratios are
10 described below:

The molar ratio of Lewis acid to chain ends is in the range from about 0.1:1 to about 2500:1. Preferably the molar ratio of Lewis acid to chain ends is in the range of about 2:1 to about 200:1. More preferably the molar ratio of Lewis acid to chain ends is about 2:1 to 15:1.

- 15 The molar ratio of Lewis acid to electron donor is in the range from about 1.1:1 to about 10,000:1. Preferably the molar ratio of Lewis acid to electron donor is in the range of about 2:1 to about 100:1. More preferably the molar ratio of Lewis acid to electron donor is about 4:1 to 30:1.

The molar ratio of Lewis acid to reacting agent is in the range from about
20 1.1:1 to about 2500:1. Preferably the molar ratio of Lewis acid to reacting agent is in the range of about 2:1 to about 100:1. More preferably the molar ratio of Lewis acid to reacting agent is about 2:1 to 15:1.

The molar ratio of reacting agent to chain ends is in the range from about 0.25:1 to about 20:1. Preferably the molar ratio of reacting agent to chain end
25 is in the range of about 0.5:1 to about 5:1. More preferably the molar ratio of reacting agent to chain end is about 0.5:1 to 4:1.

The concentration of the exo-olefin chain ends, along with the concentration of the endo-olefin and tert-chloride chain ends, is quantified using ^1H NMR. GPC spectra are also obtained to qualitatively determine the amount of the
30 EAS product, the di-EAS product and the coupled product.

Compounds suitable for use in the preparation of the polyolefin polymers of the present invention are given below:

5 Diluents

Diluents influence the ionization equilibria and rates of exchange of growing species through their polarity, which can be estimated from their dielectric constants. Typically, solvents having low dielectric constants are preferred since ion pairs are less dissociated. Suitable solvents include, but are not
10 limited to, low-boiling alkanes and alkyl mono or polyhalides with reasonably low freezing points to be used at the preferred polymerization temperature. Illustrative solvents include alkanes (generally C₂ to C₁₀ alkanes, including normal alkanes such as propane, normal butane, normal pentane, normal hexane, normal heptane, normal octane, normal nonane and normal decane,
15 and branched alkanes including isobutane, isopentane, isohexane, 3-methylpentane, 2,2-dimethylbutane, 2,3-dimethylbutane and the like), alkenes and alkenyl halides (such as vinyl chloride), carbon disulfide, chloroform, ethylchloride, N-butyl chloride, methylene chloride, methyl chloride, 1,2-dichloroethane, 1,1,2,2-tetrachloroethane, sulfur dioxide, acetic
20 anhydride, carbon tetrachloride, acetonitrile, neopentane, benzene, toluene, methylcyclohexane, chlorobenzene, 1,1-dichloroethane, 1,1-dichloroethene, 1,2-dichloroethene, n-propyl chloride, iso-propyl chloride, 1,2-dichloropropane, or 1,3-dichloropropane, nitro-alkanes (such as nitropropane) to name a few of the representative liquid diluents or solvents
25 useful in cationic polymerizations. Mixed solvents (for example combinations of those listed above) can also be used.

Electron Donors

Electron donors have been shown to convert traditional polymerization systems into living and/or quasi-living cationic polymerizations systems. The
30 proton trap used in the present invention is not specifically limited to any particular compound or class of compounds. Examples include pyridines and *n*-alkyl amines, aprotic amides, sulfoxides, esters, metal compounds having an oxygen atom bonded to a metal atom, and others. Pyridine compounds include 2,6-di-*tert*-butylpyridine, 2,6-dimethylpyridine, 2,4-dimethylpyridine,
35 2,4,6-trimethylpyridine, 2-methylpyridine, pyridine; N,N-dimethylaniline,

5 aniline. Amide compounds include N,N-dimethylformamide, N,N-dimethylacetamide, N,N-diethylacetamide. An example of a sulfoxide compound is dimethyl sulfoxide. Diethyl ether is an example of an ether compound, and methyl acetate and ethyl acetate are examples of ester compounds. Phosphate compounds such as trimethyl phosphate, tributyl
10 phosphate, triamide hexamethylphosphate may also be employed. Oxygen-containing metal compounds such as tetraisopropyl titanate are also useful as electron donors.

The concentration of the electron donors in the total reaction mixture may be
15 in the range from about 0.001 moles per liter to about 0.1 moles per liter. Preferably the concentration of the electron donors is in the range from about 0.001 moles per liter to about 0.05 moles per liter. More preferably the concentration of the electron donors is in the range from about 0.002 moles per liter to about 0.02 moles per liter.

20

Common Ion Salts and Common Ion Salt Precursors

Common ion salts or salt precursors may be optionally added to the reaction mixture in addition to or replacement of the electron donor. Typically, these salts are used to increase the ionic strength, suppress free ions, and
25 beneficially interact with ligand exchange. Particularly preferred are common ion salt precursors, for example tetra-*n*-butylammonium chloride (*n*-Bu₄NCl).

The concentration of the common ion salts or salt precursors in the total reaction mixture may be in the range from about 0.0005 moles per liter to about 0.05 moles per liter. Preferably the concentration of the common ion
30 salts or salt precursors is in the range from about 0.0005 moles per liter to about 0.025 moles per liter. More preferably the concentration of the common ion salt or salt precursors is in the range from about 0.001 moles per liter to about 0.007 moles per liter.

35

5 Lewis Acids

Lewis acids that are suitable as catalysts for purposes of the invention include, but are not limited to, titanium and boron halides, particularly titanium tetrachloride and boron trichloride, aluminum trichloride, tin tetrachloride, zinc chloride, ethyl aluminum dichloride and others. Use of the titanium halides and particularly titanium tetrachloride is preferred. The strength of the Lewis acid and its concentration should be adjusted for the particular monomer. Additionally, the strength of these Lewis acids can be adjusted using nucleophilic additives. In some instances these Lewis acids are also referred to as co-initiators.

15

The amount of the Lewis acid present in the initiator system may vary. However, it is desirable that the concentration of Lewis acid is sufficient to achieve an appropriate rate of polymerization and quenching. The Lewis acid concentration should not be so high as to precipitate the formed polymer.


20 The concentration of the Lewis acid in the total reaction mixture may be in the range from about 0.001 moles per liter to about 3.0 moles per liter. Preferably the concentration of the Lewis acid is in the range from about 0.005 moles per liter to about 1.5 moles per liter. More preferably the concentration of the Lewis acid is in the range from about 0.05 moles per liter to about 1.0 moles per liter.

25

Reacting agents

Reacting agents contemplated for use in preparation of the polyolefin in the present invention are nitrogen-containing five membered aromatic ring compounds such as substituted-pyrroles and substituted imidazoles.

30 The substituted pyrrole employed in the present invention has the general formula:




5

wherein R_1 , R_2 , R_3 and R_4 are as described below:

- (a) wherein R_1 and R_4 are independently an alkyl containing one carbon atom to about 20 carbon atoms, R_2 and R_3 are independently hydrogen or alkyl containing one carbon atom to about 20 carbon atoms, cycloalkyl of about 3 to about 7 carbon atoms, aryl of about 6 to about 30 carbon atoms, alkaryl of about 7 to about 30 carbon atoms, or aralkyl of about 7 to about 30 carbon atoms; or
- (b) R_1 and R_2 form a fused aromatic ring of from 6 carbon atoms to 10 carbon atoms or aliphatic ring of from 4 carbon atoms to about 8 carbon atoms, R_4 is alkyl containing one carbon atom to about 20 carbon atoms, and R_3 is hydrogen or alkyl containing one carbon atom to about 20 carbon atoms, cycloalkyl of about 3 to about 7 carbon atoms, aryl of about 6 to about 30 carbon atoms, alkaryl of about 7 to about 30 carbon atoms, or aralkyl of about 7 to about 30 carbon atoms; or
- (c) R_2 and R_3 form a fused aromatic ring of from 6 carbon atoms to 10 carbon atoms or aliphatic ring of from 4 carbon atoms to about 8 carbon atoms, and R_1 and R_4 are independently an alkyl containing one carbon atom to about 20 carbon atoms; or
- (d) both R_1 and R_2 , and R_3 and R_4 , taken in pairs, independently form a aromatic ring of from 6 carbon atoms to 10 carbon atoms or aliphatic ring of from 4 carbon atoms to about 8 carbon atoms.

- 5 The substituted-imidazole employed in the present invention has the general formula:




wherein R_3 is branched alkyl containing from about 4 carbon atoms to about 20 carbon atoms, and wherein


- 10 (a) R_1 and R_2 are independently hydrogen, alkyl of one carbon atom to about 20 carbon atoms, cycloalkyl of about 3 to about 7 carbon atoms, aryl of about 6 to about 30 carbon atoms, alkaryl of about 7 to about 30 carbon atoms, or aralkyl of about 7 to about 30 carbon atoms; or
- 15 (b) R_1 and R_2 form a fused aromatic ring of from 6 carbon atoms to 10 carbon atoms or aliphatic ring of from 4 carbon atoms to about 8 carbon atoms.

Structures of other nitrogen-containing five-membered aromatic ring compounds that may be employed in the method of the present invention are given below. The given structures are only intended as examples and in no way limit the scope of the present invention.

20




2,3-dimethyl indole



Carbazole

- 5 Reacting agents contemplated for use in preparation of the polyolefin in the present invention may be hindered secondary or tertiary amine compounds, such as 2-tertbutyl pyridine, n-tributylamine, 1,2,2,6,6-pentamethyl piperidine and N-methyldiphenylamine.


The hindered secondary or tertiary amine employed as a reacting agent in the
 10 present invention has the general formula:



wherein R_1 , R_2 and R_3 are independently hydrogen, alkyl containing one carbon atom to about 20 carbon atoms, cycloalkyl of about 3 to about 7 carbon atoms, aryl of about 6 to about 30 carbon atoms,
 15 alkaryl of about 7 to about 30 carbon atoms, or aralkyl of about 7 to about 30 carbon atoms; or at least one of R_1 and R_2 , R_2 and R_3 and R_3 and R_1 , taken in pairs, independently form a fused aliphatic ring of from about 4 carbon atoms to about 8 carbon atoms;


provided that no more than one of R_1 , R_2 and R_3 is hydrogen, and
 20 provided that R_1 , R_2 , and R_3 are not all linear alkyl of about 3 carbons or less.

In a preferred embodiment of the above method the hindered secondary or tertiary amine has the general formula:



5 wherein one of R_1 and R_5 is hydrogen and the other is a branched alkyl of about 3 to about 20 carbon atoms, aryl of about 10 to about 30 carbon atoms, or aralkyl of about 11 to about 30 carbon atoms; R_2 , R_3 and R_4 are independently hydrogen, alkyl of one carbon atom to about 20 carbon atoms, cycloalkyl of about 3 to about 7 carbon atoms, aryl of
10 about 6 to about 30 carbon atoms, alkaryl of about 7 to about 30 carbon atoms, or aralkyl of about 7 to about 30 carbon atoms; or at least one of R_1 and R_2 , R_2 and R_3 , R_3 and R_4 , and R_4 and R_5 , taken in pairs, independently form a fused aromatic ring of from 5 carbon atoms to 7 carbon atoms or aliphatic ring of from about 4 carbon atoms to
15 about 8 carbon atoms,
provided that if R_1 and R_2 form a fused aliphatic or aromatic ring, then R_5 is a branched alkyl of about 3 to about 20 carbon atoms, aryl of about 10 to about 30 carbon atoms, or aralkyl of about 11 to about 30 carbon atoms, and provided that if R_4 and R_5 form a fused aliphatic or
20 aromatic ring, then R_1 is a branched alkyl of about 3 to about 20 carbon atoms, aryl of about 10 to about 30 carbon atoms, or aralkyl of about 11 to about 30 carbon atoms.

The hindered amine employed in the method of the present invention may be a nitrogen containing hetero-aromatic ring having the following formulas, (a),
25 (b) and (c):




wherein in formula (a)

one of R_1 and R_4 is hydrogen and the other is alkyl of one carbon atom to about 20 carbon atoms, cycloalkyl of about 3 to about 8 carbon

5 atoms, aryl of about 6 to about 30 carbon atoms, alkaryl of about 7 to about 30 carbon atoms, or aralkyl of about 7 to about 30 carbon atoms, one of R_2 and R_3 is hydrogen and the other is alkyl of one carbon atom to about 20 carbon atoms, cycloalkyl of about 3 to about 8 carbon atoms, aryl of about 6 to about 30 carbon atoms, alkaryl of about 7 to about 30 carbon atoms, or aralkyl of about 7 to about 30 carbon atoms;
 10 or at least one of R_1 and R_2 and R_3 and R_4 , taken in pairs, independently form a fused aromatic ring of from 5 carbon atoms to 7 carbon atoms or aliphatic ring of from about 4 carbon atoms to about 8 carbon atoms;

15




wherein in formula (b)

R_1 , R_2 and R_4 are independently hydrogen or alkyl of one carbon atom to about 20 carbon atoms, cycloalkyl of about 3 to about 8 carbon atoms, aryl of about 6 to about 30 carbon atoms, alkaryl of about 7 to about 30 carbon atoms, or aralkyl of about 7 to about 30 carbon atoms,
 20 R_3 is hydrogen, alkyl of one carbon atom to about 20 carbon atoms, cycloalkyl of about 3 to about 8 carbon atoms, aryl of about 6 to about 30 carbon atoms, alkaryl of about 7 to about 30 carbon atoms, or aralkyl of about 7 to about 30 carbon atoms; or at least one of R_2 and R_3 or R_3 and R_4 , taken in pairs, independently form a fused aromatic ring of from 5 carbon atoms to 7 carbon atoms or aliphatic ring of from about 4 carbon atoms to about 8 carbon atoms,

25

5 provided that if R_1 is hydrogen then R_2 and R_4 are independently alkyl of one carbon atom to about 20 carbon atoms, cycloalkyl of about 3 to about 8 carbon atoms, aryl of about 6 to about 30 carbon atoms, alkaryl of about 7 to about 30 carbon atoms, or aralkyl of about 7 to about 30 carbon atoms, and further provided that if R_2 or R_4 is
10 hydrogen, then R_1 is alkyl of one carbon atom to about 20 carbon atoms, cycloalkyl of about 3 to about 8 carbon atoms, aryl of about 6 to about 30 carbon atoms, alkaryl of about 7 to about 30 carbon atoms, or aralkyl of about 7 to about 30 carbon atoms;

and



(c)


15

wherein in formula (c)


R_1 , R_2 and R_3 are independently hydrogen or alkyl of one carbon to about 20 carbon atoms, cycloalkyl of about 3 to about 8 carbon atoms, aryl of about 6 to about 30 carbon atoms, alkaryl of about 7 to about
20 30 carbon atoms, or aralkyl of about 7 to about 30 carbon atoms.

Structures of other hindered secondary or tertiary amines that may be employed in the method of the present invention are given below. The given structures are only intended as examples and in no way limit the scope of the present invention.


5




Quinoline




Isoquinoline



Acridine





10




Pyrazine

5



Pyrimidine



Pteridine

The concentration of the reacting agent in the total reaction mixture may be in the range from about 0.0001 moles per liter to about 2.0 moles per liter.

- 10 Preferably the concentration of the reacting agent is in the range from about 0.001 moles per liter to about 1.0 moles per liter. More preferably the concentration of the reacting agent is in the range from about 0.005 moles per liter to about 0.5 moles per liter.

Terminators

- 15 Any soluble alcohol may be used to terminate the polymerization reaction in the present invention. Preferred are mono-alcohols containing from about one carbon atom to about 8 carbon atoms.

5

EXAMPLESExample 1Preparation of polyisobutylene containing exo-olefin chain ends
using 2,5-dimethylpyrrole

- 10 A four-neck 250 milliliter round-bottom flask was equipped with an overhead mechanical stirrer and platinum resistance thermometer. This assembly was immersed into a heptane bath at -62°C under dry nitrogen gas in a substantially inert atmosphere MBraun glovebox. The flask was then charged with the following reactants:
- 15 75 milliliters methyl chloride equilibrated at -60°C.
113 milliliters hexane equilibrated at -60°C.
6.03 grams polyisobutylene containing 100 percent tert-chloride chain ends with a molecular weight of approximately 2,000 grams per mole equilibrated at -60°C.
- 20 0.23 milliliters 2,6-dimethylpyridine equilibrated at room temperature.
- The contents of the round-bottom flask were equilibrated.
- With continued stirring, next 1.82 milliliters titanium tetrachloride was charged to the flask. Fifteen seconds later, to the reaction mixture in the round-
- 25 bottomed flask was charged the reacting agent, 0.40 milliliters 2,5-dimethylpyrrole (neat and at room temperature). After the addition of the 2,5-dimethylpyrrole, aliquots, approximately 5-10 milliliter, were removed from the flask using a glass pipette and charged into a scintillation vial containing 4 milliliters anhydrous methanol equilibrated at -60°C to terminate the reaction.
- 30 Next to the remaining reaction mixture in the round-bottom flask was charged an appropriate amount of anhydrous methanol equilibrated at -60°C to terminate the reaction at 223 minutes after the addition of the 2,5-dimethylpyrrole.

- 5 The aliquots samples and the final terminated reaction mixture were allowed to warm to room temperature. Next the volatile components were evaporated. To each aliquot sample 1-2 milliliter hexane was added and the polymer was precipitated in methanol. Polyisobutylene was recovered in each aliquot sample and agitated in a vortex with fresh methanol to remove any remaining
- 10 contaminants and the methanol was decanted. Polyisobutylene samples recovered in each aliquot were placed in a vacuum oven at room temperature for at least 24 hours to remove any remaining solvents.

Tables I and II below summarize the reaction conditions and the molar quantities of the reactants used in Example I.

- 15 The following abbreviations are used for the reactants in Tables I and II below:

TMPCl is an abbreviation of 2-chloro-2,4,4-trimethylpentane.

25DMPy is an abbreviation of 2,5-dimethylpyrrole.

- The diluent used in Example 1 was a mixture of hexane and methyl chloride in
- 20 a volume ratio of 60:40.

Table I

Example	Polyisobutylene (grams)	2,6-Dimethyl pyridine (grams)	TiCl ₄ (grams)	Reacting Agent	Reacting Agent (grams)	Total Reaction Volume (liters)	Total Diluent (liters)	Temperature (°C)
1	6.03	0.2143	3.1489	25DMPy	0.373	0.200	0.189	-60

Table II

Example	Polyisobutylene (moles per liter)	2,6-Dimethyl pyridine (moles per liter)	TiCl ₄ (moles per liter)	Reacting Agent	Quenching Agent (moles per liter)	Total Reaction Volume (liters)	Total Diluent (liters)	Temperature (°C)
1	0.537	0.010	0.083	25DMPy	0.0196	0.200	0.189	-60

- 5 Polyisobutylene samples were analyzed using ^1H NMR and GPC as described below.

Procedure for Collecting ^1H NMR Data

- ^1H NMR spectra were collected using a Bruker AC-300 (300MHz) spectrophotometer using samples concentrations of 3 percent to 5 percent
10 (weight/weight) in CDCl_3 . ^1H NMR spectra were used for analysis of the end groups. Fractions of exo-olefin, endo-olefin, tert-chloride and coupled olefin chain ends were obtained using ^1H NMR integration as described in the following section.

Procedure for Collecting GPC Data

- 15 GPC data were used to determine number average molecular weight (M_n), weight average molecular weight (M_w) and Polydispersity index (PDI), i.e. M_w/M_n . GPC was also used to qualitatively detect olefin coupled product.

Procedure for Calculating the Fractional Amounts
of Chain Ends on the Polyisobutylene product

- 20 The fractions of exo-olefin, endo-olefin, and tert-chloride chain ends, and EAS, di-EAS, and coupled products in the polyisobutylene samples were quantified using ^1H NMR integration. It was assumed that these six species represent 100 percent of the chain ends. In some instances, EAS, di-EAS, and coupled products were deemed to be absent by qualitative inspection of
25 the ^1H NMR spectrum, and for di-EAS and coupled products, by confirming the absence of a shoulder on the low elution volume side of the main polymer peak in the GPC chromatogram. Two procedures are given below. The "General Procedure" was used when coupled product was detected; the "Special Procedure" was used when coupled product was deemed to be
30 absent.

5 General Procedure

The fractional molar amount of each type of chain end was obtained using an equation analogous to the equation given below for determining the fractional amount of *exo*-olefin,

$$F(\text{exo}) = (A_{\text{exo}}) / (A_{\text{exo}} + A_{\text{endo}} + A_{\text{tert-Cl}} + A_{\text{EAS}} + 2A_{\text{di-EAS}} + 2A_{\text{coupled}}) \quad (1)$$

- 10 where A_{endo} is the area of the single olefinic resonance at 5.15ppm, A_{exo} is the area of the *exo*-olefinic resonance 4.63ppm, and $A_{\text{tert-Cl}}$ was calculated as follows:

$$A_{\text{tert-Cl}} = (A_{1.65-1.72}/6) - A_{\text{endo}} \quad (2)$$

- 15 where $A_{1.65-1.72}$ is the integrated area of the convoluted peaks associated with the gem-dimethyl protons of the *endo*-olefin and the tert-chloride chain ends. The integrated area of EAS or di-EAS product, when present, was evaluated on a situation-by-situation basis; the integration was determined based on a peak that is not convoluted by other peaks, and the area was normalized based on the number of protons that have that characteristic peak. It will be
20 noted that a co-efficient of 2 appears in equation (1) for both di-EAS and coupled product, to account for the fact that creation of either of these products consumes 2 polyisobutylene chains. A_{coupled} was calculated as follows:

$$A_{\text{coupled}} = (A_{5.0-4.75} - A_{4.5-4.75})/2 \quad (3)$$

- 25 where $A_{5.0-4.75}$ is the integrated area of the convoluted peaks associated with one of the *exo*-olefin protons and the two identical protons of the coupled product, and where $A_{4.5-4.75}$ is the integrated area of the peak associated with the other *exo*-olefin proton.

5 Special Procedure

In the qualitative absence of coupled product, the fractional molar amount of each type of chain end was obtained using an equation analogous to the equation given below for determining the fractional amount of exo-olefin,

$$F(\text{exo}) = (A_{\text{exo}}) / (A_{\text{exo}} + A_{\text{endo}} + A_{\text{tert-Cl}} + A_{\text{EAS}} + 2A_{\text{di-EAS}}) \quad (1)$$

- 10 where A_{endo} is the area of the single olefinic resonance at 5.15 parts per million, A_{exo} is the average area of the two exo-olefinic resonances at 4.63 and 4.85 parts per million, and $A_{\text{tert-Cl}}$, A_{EAS} , and $A_{\text{di-EAS}}$ were calculated in the same manner as described in the "General Procedure."

- 15 Table III below summarizes the ^1H NMR data obtained on the polyisobutylene product of Example I. The chain ends are given as mole percent of the total chain ends.

Table III

Example	Exo-Olefin Chain End (mole %)	Endo-Olefin Chain End (mole %)	Tert-Cl Chain End (mole %)	EAS Chain End (mole %)	di-EAS Chain End (mole %)	Coupled Product (mole %)	Reaction Temperature (°C)
1	100	0	0	0	0	0	-60

5 WHAT IS CLAIMED IS:


1. A method for preparing a polyolefin product containing exo-olefinic end groups on the polyolefin polymer chain, which method comprises:
 - (a) ionizing a polyolefin containing terminal tert-chloride chain ends on the polymer chain in the presence of a Lewis acid; and
 - 10 (b) reacting the ionized polyolefin with one or more nitrogen-containing five-membered aromatic ring compounds selected from pyrroles and imidazoles having at least two hydrocarbyl substituents on the ring, or one or more hindered secondary or tertiary amines containing only carbon, hydrogen, and nitrogen
 - 15 atoms, or mixtures thereof, provided the nitrogen containing five-membered aromatic ring is not:
 - (i) 2,4-dimethylpyrrole;
 - (ii) 2-phenylindole;
 - (iii) 2-methylbenzimidazole;
 - 20 (iv) 1,2-dimethylimidazole;
 - (v) 2-phenylimidazole; and
 - (vi) 2,4,5-triphenylimidazole;
- and provided the hindered secondary or tertiary amines are not:
 - (i) Triethylamine;
 - 25 (ii) Tri-n-butylamine;
 - (iii) Trihexylamine;
 - (iv) Triisooctylamine;
 - (v) 2-phenylpyridine;
 - (vi) 2,3-cyclododecenopyridine;
 - 30 (vii) Di-p-tolylamine;

(viii) Quinaldine; and

(ix) 1-pyrroliidino-1-cyclopentene;

to thereby obtain the polyolefin product containing exo-olefinic end groups on the polyolefin polymer chain.


2. The method of claim 1, wherein steps (a) and (b) are independently carried out at a temperature in the range of -130°C to 10°C.
3. The method of claim 2, wherein steps (a) and (b) are independently carried out at a temperature in the range of -80°C to 0°C.
4. The method of claim 2, wherein steps (a) and (b) are independently carried out at a temperature in the range of -70°C to -10°C.
5. The method of claim 4, wherein steps (a) and (b) are independently carried out at a temperature in the range of -60°C to -20°C.
6. The method of claim 1, wherein the one or more nitrogen-containing five-membered aromatic ring compounds in step (b) is a substituted-pyrrole having the general formula:




wherein:

- (a) R_1 and R_4 are independently an alkyl containing one carbon atom to 20 carbon atoms, R_2 and R_3 are independently hydrogen or alkyl containing one carbon atom to 20 carbon atoms, cycloalkyl of 3 to 7 carbon atoms, aryl of about 6 to 30 carbon atoms, alkaryl of 7 to 30 carbon atoms, or aralkyl of 7 to 30 carbon atoms; or
- (b) R_1 and R_2 form a fused aromatic ring of from 6 carbon atoms to 10 carbon atoms or an aliphatic ring of from 4 carbon atoms to 8 carbon atoms, R_4 is alkyl containing one carbon atom to 20 carbon atoms, and R_3 is hydrogen or alkyl containing one carbon atom to 20 carbon atoms, cycloalkyl of 3 to 7 carbon atoms, aryl of 6 to 30 carbon atoms, alkaryl of 7 to 30 carbon atoms, or aralkyl of 7 to 30 carbon atoms; or
- (c) R_2 and R_3 form a fused aromatic ring of from 6 carbon atoms to 10 carbon atoms or an aliphatic ring of from 4 carbon atoms to 8 carbon atoms, and R_1 and R_4 are independently an alkyl containing one carbon atom to 20 carbon atoms; or
- (d) both R_1 and R_2 , and R_3 and R_4 , taken in pairs, independently form a fused aromatic ring of from 6 carbon atoms to 10 carbon atoms or an aliphatic ring of from 4 carbon atoms to 8 carbon atoms.
7. The method of claim 6, wherein R_1 and R_4 are methyl and R_2 and R_3 are hydrogen.
8. The method of claim 6, wherein R_1 , R_2 , R_3 and R_4 are methyl.

9. The method of claim 6, wherein the substituted-pyrrole has the following formula:




10. The method of claim 1, wherein the nitrogen-containing five-membered aromatic ring is a substituted imidazole,
11. The method of claim 10, wherein the substituted imidazole has the general formula:



wherein R_3 is branched alkyl containing from 4 carbon atoms to 20 carbon atoms, and wherein

- (a) R_1 and R_2 are independently hydrogen, alkyl of one carbon atom to 20 carbon atoms, cycloalkyl of 3 to 7 carbon atoms, aryl of 6 to 30 carbon atoms, alkaryl of 7 to 30 carbon atoms, or aralkyl of 7 to 30 carbon atoms; or
- (b) R_1 and R_2 form a fused aromatic ring of from 6 carbon atoms to 10 carbon atoms or an aliphatic ring of from 4 carbon atoms to 8 carbon atoms.


12. The method of claim 11, wherein R_1 is methyl, R_2 is hydrogen and R_3 is tert-butyl.
13. The method of claim 1, wherein in step (a) the Lewis acid is a halide of titanium or boron.
14. The method of claim 13, wherein in step (a) the Lewis acid is a titanium halide.
15. The method of claim 14, wherein in step (a) the Lewis acid is titanium tetrachloride.
16. The method of claim 1, wherein the polyolefin is polyisobutylene.
17. The method of claim 1, wherein in step (b) the ionized polyolefin is reacted with one or more hindered secondary or tertiary amines.
18. The method of claim 17, wherein the hindered secondary or tertiary amine has the general formula:




wherein R_1 , R_2 and R_3 are independently hydrogen, alkyl containing one carbon atom to 20 carbon atoms, cycloalkyl of 3 to 7 carbon atoms, aryl of 6 to 30 carbon atoms, alkaryl of 7 to 30 carbon atoms, or aralkyl of 7 to 30 carbon atoms; or at least one of R_1 and R_2 , R_2 and R_3 and R_3 and R_1 , taken in pairs, independently form a fused aliphatic ring of from 4 carbon atoms to 8 carbon atoms;

provided that no more than *one* of R_1 , R_2 and R_3 is hydrogen, and provided that R_1 , R_2 , and R_3 are not all linear alkyl of about 3 carbons or less.

- 5 19. The method of claim 18, wherein the hindered amine is a tertiary amine of the formula:




20. The method of claim 18, wherein the hindered amine is a tertiary amine of the formula:




10

21. The method of claim 18, wherein the hindered amine is a tertiary amine of the formula:




15

22. The method of claim 18, wherein the hindered amine is a tertiary amine of the formula:




23. The method of claim 17 wherein the hindered amine is a tertiary or secondary amine has the general formula:




wherein R_6 is a divalent hydrocarbyl group of one carbon atom to 4 carbon atoms, each of which may be substituted with an alkyl group having one carbon atom to 6 carbon atoms, and R_1 , R_2 , R_3 , R_4 , and R_5 are independently hydrogen, alkyl containing one carbon atom to 20 carbon atoms, cycloalkyl of 3 to 8 carbon atoms, aryl of 6 to 30 carbon atoms, alkaryl of 7 to 30 carbon atoms, or aralkyl of 7 to 30 carbons; provided if R_1 , R_2 , R_3 , and R_4 are hydrogen, then R_5 is a branched alkyl having from 4 to 20 carbon atoms, aryl of 6 to 30 carbon atoms, or aralkyl of 7 to 30 carbon atoms, and provided if R_5 is hydrogen, then R_1 , R_2 , R_3 , and R_4 cannot be hydrogen unless either R_1 or R_2 and either R_3 or R_4 is a branched alkyl from 4 to 20 carbon atoms.

24. The method of claim 22, wherein the hindered amine is a secondary or tertiary amine of the formula:



wherein R_5 is hydrogen or methyl.


25. The method of claim 17 wherein the hindered secondary or tertiary amine has the general formula:




wherein R_1 is a divalent hydrocarbyl group of one carbon atom to 4 carbons and R_2 , R_3 , R_4 , R_7 , R_8 , and R_9 are independently hydrogen, alkyl containing one carbon atom to 20 carbon atoms cycloalkyl of 3 to 8 carbon atoms, aryl of 6 to 30 carbon atoms, alkaryl of 7 to 30 carbon atoms, or aralkyl of 7 to 30 carbons, and one of R_5 and R_6 is hydrogen and the other is linear alkyl from one carbon atom to 20 carbon atoms.

26. The method of claim 24, wherein one of R_5 and R_6 is hydrogen.

27. The method of claim 22, wherein the amine has the formula:




28. The method of claim 17, wherein the hindered amine is a tertiary amine of the general formula:



wherein one of R_1 and R_5 is hydrogen and the other is a branched alkyl of 3 to 20 carbon atoms, aryl of 10 to 30 carbon atoms, or aralkyl of 11 to 30 carbon atoms; R_2 , R_3 and R_4 are independently hydrogen, alkyl of one carbon atom to 20 carbon atoms, cycloalkyl of 3 to 7 carbon atoms, aryl of 6 to 30 carbon atoms, alkaryl of 7 to 30 carbon atoms, or aralkyl of 7 to 30 carbon atoms; or at least one of R_1 and R_2 , R_2 and R_3 , R_3 and R_4 , and R_4 and R_5 , taken in pairs, independently form a fused aromatic ring of from 5 carbon atoms to 7 carbon atoms or aliphatic ring of from 4 carbon atoms to 8 carbon atoms,

provided that if R_1 and R_2 form a fused aliphatic or aromatic ring, then R_5 is a branched alkyl of 3 to 20 carbon atoms, aryl of 10 to 30 carbon atoms, or aralkyl of 11 to 30 carbon atoms, and provided that if R_4 and R_5 form a fused aliphatic or aromatic ring, then R_1 is a branched alkyl of 3 to 20 carbon atoms, aryl of 10 to 30 carbon atoms, or aralkyl of 11 to 30 carbon atoms.


29. The method of claim 27, wherein R_1 is hydrogen and R_5 is tert-butyl and R_2 , R_3 , and R_4 are hydrogen.
30. The method of claim 17, wherein the hindered amine is a nitrogen containing hetero-aromatic ring having the following formulas, (a), (b) and (c):



(a)

wherein in formula (a)

one of R_1 and R_4 is hydrogen and the other is alkyl of one carbon atom to 20 carbon atoms, cycloalkyl of 3 to 8 carbon atoms, aryl of 6 to 30 carbon atoms, alkaryl of 7 to 30 carbon atoms, or aralkyl of 7 to 30 carbon atoms, one of R_2 and R_3 is hydrogen and the other is alkyl of one carbon atom to 20 carbon atoms, cycloalkyl of 3 to 8 carbon atoms, aryl of 6 to 30 carbon atoms, alkaryl of 7 to 30 carbon atoms, or aralkyl of 7 to 30 carbon atoms; or at least one of R_1 and R_2 and R_3 and R_4 , taken in pairs, independently form a fused aromatic ring of from 5 carbon atoms to 7 carbon atoms or aliphatic ring of from 4 carbon atoms to 8 carbon atoms;




wherein in formula (b)

R_1 , R_2 and R_4 are independently hydrogen or alkyl of one carbon atom to 20 carbon atoms, cycloalkyl of 3 to 8 carbon atoms, aryl of 6 to 30 carbon atoms, alkaryl of 7 to 30 carbon atoms, or aralkyl of 7 to 30 carbon atoms, R_3 is hydrogen, alkyl of one carbon atom to 20 carbon atoms, cycloalkyl of 3 to 8 carbon atoms, aryl of 6 to 30 carbon atoms, alkaryl of 7 to 30 carbon atoms, or aralkyl of 7 to 30 carbon atoms; or at least one of R_2 and R_3 or R_3 and R_4 , taken in pairs, independently form a fused aromatic

ring of from 5 carbon atoms to 7 carbon atoms or aliphatic ring of from 4 carbon atoms to 8 carbon atoms,
 provided that if R_1 is hydrogen then R_2 and R_4 are independently alkyl of one carbon atom to 20 carbon atoms, cycloalkyl of 3 to 8 carbon atoms, aryl of 6 to 30 carbon atoms, alkaryl of 7 to 30 carbon atoms, or aralkyl of 7 to 30 carbon atoms, and further provided that if R_2 or R_4 is hydrogen, then R_1 is alkyl of one carbon atom to 20 carbon atoms, cycloalkyl of 3 to 8 carbon atoms, aryl of 6 to 30 carbon atoms, alkaryl of 7 to 30 carbon atoms, or aralkyl of 7 to 30 carbon atoms;


and




wherein in formula (c)

R_1 , R_2 and R_3 are independently hydrogen or alkyl of one carbon to 20 carbon atoms, cycloalkyl of 3 to 8 carbon atoms, aryl of 6 to 30 carbon atoms, alkaryl of 7 to 30 carbon atoms, or aralkyl of 7 to 30 carbon atoms.


31. The method of Claim 1, where the hindered amine has the formula:



32. The method of Claim 29, where the hindered amine has the formula:



33. The method of Claim 29, where the hindered amine has the formula:



34. The method of claim 1, wherein the exo-olefinic end group on the polyolefin product is present in the range of one percent to 100 percent of the total end groups.
35. The method of claim 33, wherein the polyolefin product has at least 3 percent exo-olefin end groups.
36. The method of claim 34, wherein the polyolefin product has at least 20 percent exo-olefin end groups.
37. The method of claim 35, wherein the polyolefin product has at least 50 percent exo-olefin end groups.
38. The method of claim 36, wherein the polyolefin product has at least 70 percent exo-olefin end groups.
39. A method for preparing a polyolefin product containing exo-olefinic end groups on the polyolefin polymer chain, which method comprises:
- (a) ionizing a polyolefin containing terminal tert-chloride chain ends on the polymer chain in the presence of a Lewis acid;
 - and

5 (b) reacting the ionized polyolefin with one or more nitrogen-
containing five-membered aromatic ring compounds selected
from pyrroles and imidazoles having at least two hydrocarbyl
substituents on the ring, or one or more hindered secondary or
tertiary amines containing only carbon, hydrogen, and nitrogen
10 atoms, or mixtures thereof, wherein the nitrogen-containing
aromatic amine compounds or the hindered secondary or
tertiary amines are pre-reacted with a Lewis acid, provided the
nitrogen containing five-membered aromatic ring is not:

- (i) 2,4-dimethylpyrrole;
- 15 (ii) 2-phenylindole;
- (iii) 2-methylbenzimidazole;
- (iv) 1,2-dimethylimidazole;
- (v) 2-phenylimidazole; and
- (vi) 2,4,5-triphenylimidazole;

20 and provided the hindered secondary or tertiary amines are not:

- (i) Triethylamine;
- (ii) Tri-n-butylamine;
- (iii) Trihexylamine;
- (iv) Triisooctylamine;
- 25 (v) 2-phenylpyridine;
- (vi) 2,3-cyclododecenopyridine;
- (vii) Di-p-tolylamine;
- (viii) Quinaldine; and
- (ix) 1-pyrrolidino-1-cyclopentene;

30 to thereby obtain the polyolefin product containing exo-olefinic end
groups on the polyolefin polymer chain.

- 5 40. The method of claim 39, wherein the Lewis acid is titanium tetrachloride and the nitrogen containing five-membered aromatic ring compound is 2,5-dimethyl pyrrole.
41. The method of claim 39, wherein the Lewis acid is titanium tetrachloride and the substituted pyrrole is 2,3-dimethyl indole.
- 10 42. The method of claim 39, wherein the Lewis acid is titanium tetrachloride and the hindered amine is 1,2,2,6,6-pentamethylpiperidine.
43. The method of claim 39, wherein the Lewis acid is titanium tetrachloride.
- 15 44. The method of claim 39, wherein the nitrogen-containing five-membered aromatic ring compound is 2,5-dimethylpyrrole.