


ORGANOSILOXANES FOR USE AS SUNSCREEN AGENTS

This invention is concerned with novel organosilicon compounds which are effective in absorbing ultra violet radiation and is also
5 concerned with a process of preparing such compounds.

A number of organic compounds, generally organic acids and derivatives thereof, are known to be chromophores having U.V.-absorbing properties and are employed on a commercial scale as ingredients in sunscreen preparations or as plastic additives. Although
10 such materials function adequately they are easily removed from the substrate to which they have been applied. For example, cosmetic sunscreen preparations can be removed during bathing thus requiring repeated applications if protection is to be maintained. It is also desirable that the active ingredient remain on the surface of the skin
15 rather than penetrate into or through the skin.


Compounds which overcome this problem to a certain extent are disclosed for example in European Patent Specification 305 059, which provides organosilicon compounds having at least one unit of the general formula



This Sheet Has Been Replaced

THIS SHEET HAS BEEN
REPLACED

any other units present in the said siloxanes being those represented by the general formula





This Sheet Has Been Replaced



wherein R represents a C₁₋₁₈ alkyl group, R' is a divalent alkylene or oxyalkylene group having from 2 to about 20 carbon atoms, or a divalent alkenylene or oxyalkenylene group having from 2 to 20 carbon atoms, wherein the carbon-carbon double bond is adjacent to the silicon atom, R'' is a halogen atom, an alkyl, aryl, alkoxy or alkoxyalkoxy group having less than 9 carbon atoms, Q represents a hydrogen atom, a monovalent C₁₋₁₈ hydrocarbon or halogenated hydrocarbon group, Z is an alkyl or an alkoxy group having from 1 to 8 carbon atoms or a hydroxyl group, a and b each have a value of 0, 1, 2 or 3 and c is 0 or 1, provided that at least one of Z and R' is linked to the multivalent aryl group via an ether linkage.

It was found, however, that although the materials described above were, in comparison with the prior art, less susceptible to hydrolysis at the ester linkage, for example by enzymatic hydrolysis on the skin when these materials were used as cosmetic sunscreen agents, they were not sufficiently photostable when exposed to UV irradiation.


EP publication 392 882 discloses the use of diorganopolysiloxanes with a benzalmalonate functionality in cosmetic applications. The diorgano-polysiloxanes which are useful in said application have the average general formula




wherein R is C₁₋₁₀ alkyl, phenyl or trifluoropropyl, B is R or A, r is from 0 to 200, s is from 0 to 50, u is from 1 to 20, t is from 0 to 20, t+u is at least 3, there being at least one group A per molecule and A denotes a structure of the general formula

THIS SHEET HAS BEEN REPLACED

- 3 -



This Sheet Has Been Replaced




wherein R^1 is H, OH, trimethylsiloxy, C_{1-6} alkoxy or a divalent group $-(O)_n-(CH_2)_p-CH(R'')-CH_2-$, n is 0 or 1, p is 1 to 10, R'' is H or C_{1-4} alkyl, R^2 is H, C_{1-6} alkyl or C_{1-6} alkoxy, R^3 is C_{1-6} alkyl, at least one of the R^1 groups being the divalent group.

We have found that although the materials described in both above identified references perform well in many applications, and although there is a reduction in the amount of chromophore which penetrates through the skin when applied thereto in comparison with the amount of chromophore which penetrates when it has been applied as a pure compound (i.e. not linked to an organosilicon compound), there is still a need to further reduce the amount of penetration through the skin.

We have now found that if certain novel chromophores are used in the preparation of organosilicon compounds, improved cosmetic preparations, effective in absorbing ultra violet radiation can be obtained.

According to a first aspect of the invention there is provided an organosiloxane compound having at least one unit of the general formula




any other units present in the said siloxanes being those represented by the general formula


THIS SHEET HAS BEEN REPLACED

SUBSTITUTE SHEET


- 4 -



This Sheet Has Been Replaced



wherein R represents a C₁₋₈ alkyl or an aryl group, R¹ is a hydrogen atom or a C₁₋₅ alkyl group, R² is a hydrogen atom, a C₁₋₅ alkyl group or a group OR¹, R³ is a C₁₋₅ alkyl group, R'' represents a hydrogen atom, a monovalent C₁₋₈ hydrocarbon or halogenated hydrocarbon group, a has a value of 0, 1 or 2, b has a value of 0, 1, 2 or 3 and n has a value of from 1 to 6, provided that the



group and the two R² groups are linked to the aromatic ring at the para and both meta positions in relation to the group




In the general formula of the organosilicon compounds of the invention R may be for example methyl, ethyl, butyl or phenyl. R'' is hydrogen or a monovalent hydrocarbon or halogenated hydrocarbon group having less than 8 carbon atoms, for example alkyl, alkenyl, aryl, alkaryl, aralkyl and halogen substituted alkyl, alkenyl, aryl, alkaryl and aralkyl groups. Examples include methyl, ethyl, vinyl, phenyl and 3,3,3-trifluoropropyl. R³ denotes alkyl groups having up to 5 carbon atoms for example methyl, ethyl, propyl, isopropyl, butyl, secondary butyl, isobutyl, pentyl and neopentyl. R¹ is either a group R³ or a hydrogen atom and R² is a group R¹ or a group OR¹.


It is preferred that at least 80% of all R and R'' groups are methyl groups, most preferably substantially all R and R'' groups are methyl groups. It is also preferred that R¹ is either hydrogen, methyl or ethyl, most preferably hydrogen. Preferably each R² group is H or one R² group is a hydrogen, while the other one is an alkoxy group, preferably methoxy or ethoxy. R³ is preferably methyl or ethyl. a is preferably 1 while b is preferably 2, making the organosilicon compound a substantially linear or cyclic diorgano-siloxane polymer. However, if the diorgano-siloxane is a substantially linear polymer at least two endblocking units must be present, thus requiring the presence of 2 units in which a has a value of 2, two units in which the value of b is 3 or one unit wherein a is 2 and one unit in which b is 3. n is preferably 1, 2 or 3. Suitable preferred polymers have therefore either the general formula

THIS SHEET HAS BEEN
REPLACED

- 5 -




wherein R and R'' are as defined above, X denotes a group Y or a group R'' and Y denotes a group of the formula




r has a value of from 0 to 100, s has a value of from 0 to 20, whereby at least one X denotes Y in the case that s=0, t has a value of from 0 to 10, v has a value of from 1 to 10 and v+t has a value of at least 3.

In the substituent Y of the organosilicon compounds according to the invention, the group



may occupy the meta-position or the para-position of the aromatic ring in relation to the group $-\text{CH} = \text{C}[\text{C}(\text{O})\text{OR}^3]_2$. Preferably the para-position is thus occupied. The groups R² occupy the remaining two positions out of the para- and meta-positions in relation to the group $-\text{CH} = \text{C}[\text{C}(\text{O})\text{OR}^3]_2$. Examples of preferred substituents Y thus include



This Sheet Has Been Replaced



20

The organosilicon compounds of the present invention have at least one unit falling within the general formula (i), preferably at least 2.

SUBSTITUTE SHEET

THIS SHEET HAS BEEN
REPLACED

Suitable organosilicon compounds are polymeric materials which may be homopolymers consisting only of such units (i), or they may be copolymers containing both units (i) and units having the general formula (ii). The organosilicon compounds may vary from freely
5 flowing liquids to highly viscous gum-like materials or resinous solids. Preferred, at least for cosmetic applications, are the liquid substantially linear organosiloxane homopolymers and copolymers, for example those having a viscosity of from 100 to 20000mm²/s, more preferably 500 to 5000mm²/s as these are more easily mixed with other ingredients to
10 make cosmetic compositions and as they will spread more easily onto the skin.

Organosilicon compounds of the invention which are especially preferred are those wherein the number of units (i) is limited to a maximum of 20% of the total number of siloxane units in the molecule.
15 For maximum efficiency in its U.V. absorbing property it is preferred that the number of units (i) be limited to 10% or less of the total. The units of formula (i) may be distributed randomly in an organosiloxane polymer, they may be end-blocking units of the polymer or they may be located at the end of the polymer and pending in chain of the polymer at
20 the same time. Units of the general formula (i) are preferably situated at the end of the organosiloxane polymer forming one or more endblocking units of the polymer. In the most preferred organosilicon compounds which are substantially linear polyorganosiloxane polymers, both endblocking units have a structure represented by the
25 general formula (i), while all other units are according to the general formula (ii). The most preferred organosilicon compounds have two units of the formula (i) and a larger number of units according to the general formula (ii), e.g. 8 to 90, especially 8 to 40.

The organosilicon compounds according to the invention are
30 effective in absorbing ultra violet radiation in the erythemic region (290 - 320nm) which makes them particularly suitable for use in cosmetic sunscreen preparations where absorption in the UV-B region is particularly desirable. Most preferred for this application are those that have a maximum absorbance at 300 - 320nm.

This Sheet Has Been Replaced




THIS SHEET HAS BEEN
REPLACED


SUBSTITUTE SHEET




The organosilicon compounds of the present invention can, quite generally, be prepared by the reaction of an organosilicon compound in which each unit (i) is replaced with a unit having the general formula



5 with a chromophore of the general formula



10 These chromophores are in themselves novel compounds and the invention therefore includes in one of its aspects a compound of the formula




15 wherein R^1 is a hydrogen atom or a C_{1-5} alkyl group, R^2 is a hydrogen atom, a C_{1-5} alkyl group or a group OR^1 , R^3 is a C_{1-5} alkyl group and n has a value of from 1 to 6, provided that the group containing the unsaturated carbon-carbon triple bond and the two R^2 groups are linked to the two meta-positions and to the para-position of the aromatic ring in relation to the ester containing group.

20 Compounds of the general formula (iii) may be prepared e.g. by reacting a hydroxy or dihydroxy benzaldehyde with halogenopropyne, followed by a further reaction with a diester of malonic acid. The first reaction is preferably carried out in the presence of a suitable solvent, e.g. acetone, preferably at reflux temperatures. The presence of a catalyst is also preferred. The second reaction is also preferably carried out in the presence of a solvent, e.g. toluene at reflux temperatures. The
25 final product of formula (iii) is a light brown crystal.

The invention also includes a process for the preparation of organosilicon compounds of the kind specified herein, which comprises reacting together

(A) a compound of the general formula





wherein R^1 is a hydrogen atom or a C_{1-5} alkyl group, R^2 is a hydrogen atom, a C_{1-5} alkyl group or a group OR^1 , R^3 is a C_{1-5} alkyl group and n has a value of from 1 to 6, provided that the group containing the unsaturated triple bond and the two R^2 groups are linked to the two meta-positions and to the para-position of the aromatic ring in relation to the group


-CH=C-[C(O)OR³]₂ and

(B) an organosilicon compound having at least one unit of the general formula



10


any other units present in the organosilicon compound being those represented by the general formula



wherein R , R'' , a and b are as hereinabove defined.

The reaction is preferably carried out employing stoichiometric proportions of (A) and (B) or a slight stoichiometric excess of (A). However, a stoichiometric deficiency of (A) can be employed if residual silicon-bonded hydrogen is desired in the product.


Alternatively polymeric organosilicon compounds of the invention can also be obtained by first preparing the corresponding hydrolysable silane, employing in place of the organosilicon compound (B) the corresponding SiH containing silane (C) which has the general formula



wherein R is as defined above, Z is a hydrolysable group, preferably alkoxy having 1 to 8 carbon atoms and x has a value of 0, 1 or 2.

The silane (D) resulting from this reaction may be submitted thereafter to cohydrolysis with a further hydrolysable silane or equilibration with (E) cyclic or (F) linear polyorganosiloxanes consisting essentially of units of the formula (ii). Silanes (D) which can be used in this method are novel in themselves and are included in the scope of the present invention. Silanes (D) have the general formula


THIS SHEET HAS BEEN
REPLACED



wherein R, R¹, R², R³, Z, x and n are as defined above:


Thus, in more detail, the process comprises

- 5 I) the preparation of a hydrolysable silane by reacting a silane of the general formula




wherein R represents a C₁₋₈ alkyl or aryl group, Z is a hydrolysable group and x has a value of 0, 1 or 2,

- 10 with a compound of the general formula



- 15 wherein R¹ is a hydrogen atom or a C₁₋₅ alkyl group, R² is a hydrogen atom, a C₁₋₅ alkyl group or a group OR¹, R³ is a C₁₋₅ alkyl group and n has a value of from 1 to 6, provided that the group containing the unsaturated triple bond and the two R² groups are linked to the two meta-positions and to the para-position of the aromatic ring in relation to the group -CH=C-[C(O)OR³]₂, and

- 20 II) submitting the hydrolysable silane to cohydrolysis or equilibration with cyclic or linear polydiorganosiloxanes consisting essentially of units of the formula



wherein R'' represents a hydrogen atom a monovalent C₁₋₈ hydrocarbon or halogenated hydrocarbon, and b has a value of 0, 1, 2 or 3.

- 25 Z is preferably an alkoxy group having from 1 to 8 carbon atoms.

As concerns the cohydrolysis, such reaction will conveniently be in conjunction with other hydrolysable silanes (e.g. diorgano-dihalosilanes, or diorgano-alkoxysilanol, etc.) or with siloxanes



having hydrolysable endgroups (e.g. α,ω dihydroxy polydimethylsiloxanes).

As concerns the equilibrium aspect on the linear or cyclic polydiorganosiloxanes, cyclic siloxanes will conveniently have the general formula $[R^2SiO]_n$, wherein n has a value of from 3 to 9, and linear polydiorganosiloxanes are usually used as end-blocking units, and will be short chain triorganosiloxane end-blocked polydiorgano-siloxanes (in the shortest form hexaorganodisiloxane $[R_3Si-O-SiR_3]$).

This alternative process involves thus technique which is known per se.

In order to obtain the particularly preferred polymeric organosilicon compounds of the invention the reaction is carried out in such a way that in the reaction product at least one siloxane unit and no more than 20% of the total number of siloxane units has a structure according to formula (i). This may be achieved by reacting polymeric organosilicon compounds (B) which have a maximum of 20 mole % silicon-bonded hydrogen atoms, with stoichiometric amounts of compound (A). Excess amounts of (A) may also be used in this case. If residual SiH groups are desired in the organosilicon compound product less than stoichiometric amounts of compound (A) may be employed. The particularly preferred polymeric organosilicon compounds of the invention may also be obtained by reacting polymeric organosilicon compounds (B) having more than 20 mole % silicon-bonded hydrogen atoms, with less than stoichiometric amounts of compound (A). Most preferably, however, organosilicon compounds (B) are employed which are polydiorganosiloxanes endblocked with diorganohydrosiloxane units provided the siloxane has a minimum chain length of 10 silicon atoms.

The reaction between (A) and (B) may be carried out employing known procedures for the addition of silicon-bonded hydrogen atoms to groups containing aliphatic unsaturation. Thus, such reactions are generally catalysed by a platinum group metal or a compound or complex of such a metal. Examples of catalysts which may be employed



in the reaction between (A) and (B) are platinum on carbon, chloroplatinic acid, platinum acetyl acetonate, complexes of platinum compounds with unsaturated compounds e.g. olefins and vinyl siloxanes, complexes of rhodium and palladium compounds and
5 complexes of platinum compounds supported on inorganic substrates. The addition reaction may be performed at reduced, atmospheric or increased pressure. It is generally preferred to employ a solvent e.g. toluene or xylene in the reaction mixture although the presence of a solvent is not essential. It is also preferred to carry the reaction out at
10 elevated reaction temperatures e.g. from about 50° C. up to the reflux temperature of the reaction mixture.

The organosilicon compounds of this invention have similar UV absorbance characteristics to those disclosed in the prior art. They are useful as agents for preventing sunburn and are thus useful in skin
15 care and hair care applications. They may be applied per se to the skin or hair but are more preferably formulated into cosmetic compositions with, for example, inert carriers e.g. solvents such as water, ethanol, isopropanol, glycerine and mineral oil and cream base materials such as stearic acid, propylene glycol, beeswax and cetyl alcohol. Other
20 conventional ingredients e.g. perfumes and known U.V. absorbing substances may also be included in the formulated compositions. The organosilicon compounds of the present invention are also useful in the coating of substrates e.g. wood, plastics or metal, to which they may be applied either per se or as additives to coating compositions or they may
25 be incorporated as additives in plastics materials.


The following examples, in which parts and percentages are expressed by weight illustrate the invention.

Example 1

Preparation of propanedioic

30 { [4- (2-propynyloxy)phenyl]methylene} -diethyl ester (the most preferred compound).

To a stirred suspension of 4-hydroxybenzaldehyde (425.8g) and K₂CO₃ (807.6g) in acetone (2,960ml) at reflux temperature of about 60° C under a nitrogen atmosphere, was added dropwise 3-bromo-propyne
35 (502.4g) over a period of 2 hours. The reaction was heated at reflux for 3



more hours. After cooling to room temperature the reaction mixture was filtered and the excess of K_2CO_3 removed and washed several times with acetone. The filtrate was washed with saturated aqueous solution of $NaHCO_3$ and $NaCl$. The aqueous phase was extracted with diethyl ether. The combined organic extracts were dried over Na_2SO_4 , filtered and concentrated to a volume of 1 litre. The solution was kept in the refrigerator overnight. The crystals were filtered out and washed with cold diethyl ether. The filtrate was kept in the refrigerator and some more crystals were formed and removed. This procedure was repeated 3 times resulting in 1,385.26g of 4-(2-propynyloxy) benzaldehyde in 83% yield. The material was analysed by gas chromatography, and shown to be 99.9% pure. Infrared and mass spectroscopic analysis confirmed the structure.

The resulting compound (449.2g) was added in small amounts to a stirred solution of diethyl malonate (448.5g), piperidine (23.84g), toluene (1,400ml) and acetic acid (59g) at about 50° C. The acetic acid had been added in three equal portions after 1, 1.5 and 2 hours respectively. The reaction mixture was heated to reflux. After four hours the mixture was allowed to cool to room temperature and washed with saturated aqueous solution of $NaHCO_3$ and $NaCl$, dried with Na_2SO_4 , filtered and concentrated, giving 853.4g of a dark brown oily product. Diethyl ether (458ml) and n-hexane (358ml) were added and the solution kept in a refrigerator overnight. The solution was filtered, giving 564.8g of light brown crystals (67% yield) having a melt-ing point of 45.5 to 48° C. Recrystallisation in ethanol and n-hexane yielded 543g of the title compound as light brown crystals. Analysis revealed a melting point of 48.5 to 49.5° C and a purity by capillary gas chromatography of 99.9%.

Example 2

Preparation of propanedioic

{ [4- (2-propynyloxy)phenyl]methylene) -dimethyl ester


The procedure of the above method was repeated except that dimethyl malonate was used instead of diethyl malonate.

Example 3

THIS SHEET HAS BEEN
REPLACED

SUBSTITUTE SHEET

- 5g of ([4-(2-propynyloxy)phenyl]methylene)-diethyl ester were dissolved in 20g of toluene and heated under nitrogen to about 80° C. 13.2g of a hydrosiloxane having a degree of polymerisation of 20 and 10mpc SiH groups (3.62% SiH) were then added dropwise after a platinum complex was also added, giving 10⁻⁴ mole of Pt per mole of SiH of the hydro-siloxane. The mixture was heated to reflux and maintained until all SiH had disappeared of the infrared spectroscopic analysis. It was then allowed to cool to room temperature. The toluene was then evaporated to leave after washing 16.5g of a slightly brown polymer having the average structure R-[(CH₃)₂SiO]₂₀-R, wherein R has the formula




- Only 1.6% by weight of the total reaction product of unreacted ([4-(2-propynyloxy)phenyl]methylene)-diethyl ester was present in the endproduct.

Example 4


- 10g of ([4-(2-propynyloxy)phenyl]methylene)-diethyl ester were dissolved in 10g of toluene and heated under nitrogen to about 80° C. 13.2g of a hydrosiloxane having a degree of polymerisation of 100 and 20mpc SiH groups (8.43% SiH) were then added dropwise after a platinum complex was also added, giving 10⁻⁴ mole of Pt per mole of SiH of the hydro-siloxane. The mixture was heated to reflux and maintained until all SiH had disappeared of the infrared spectroscopic analysis. It was then allowed to cool to room temperature. The toluene was then evaporated to leave after washing 21.2g of a hazy, very viscous polymer having the average structure



- wherein R has the formula




THIS SHEET HAS BEEN
REPLACED




Examples 5 and 6

Similar procedures as described for Examples 3 and 4 were used to make polymers with the average formulae

- 5 (5) $R-[(CH_3)_2SiO]_2-R$ wherein R has the formula



- (6) $(CH_3)_3SiO-[(CH_3)_2SiO]_6-[(CH_3)RSiO]_2-Si(CH_3)_3$
wherein R has the formula




10

Comparative Example 1

A similar procedure as described for Examples 3 and 4 was used to make a polymer with the average formula

- 15 $Q-[(CH_3)_2SiO]_{20}-Q$

wherein Q has the formula



3.3% by weight of the total reaction product of unreacted
([4-(2-allyloxy)phenyl]methylene)-diethyl ester was present in the
20 endproduct.

Comparative Example 2

A similar procedure as described for Examples 3 and 4 was used to make a polymer with the average formula

- 25 $(CH_3)_3SiO-Si(CH_3)_2Z-OSi(CH_3)_3$,

wherein Z has the formula

THIS SHEET HAS BEEN
REPLACED



Comparative Example 3

Commercially available Parsol MCX was used which has the
5 formula



UV Absorption Tests

Comparative Example 1 and Example 1 were both tested for their
10 absorption at 300nm (E 1%,cm). To this effect the samples were
dissolved in tetrahydrofuran. Example 1 showed an absorption of 211
while Comparative Example 1 only gave a value of 83. This shows that
the organosilicon compounds according to the invention are better than
the prior art.

15 Stability and water resistance

Each sample was tested and found satisfactory in view of the
stability to UV radiation and its resistance to washing off with water.

Skin Penetration Tests

Invitro penetration tests were carried out on rat skin. The samples
20 were dissolved in tetrahydrofuran at a concentration of 10%, and this
was applied to the skin at a dosage of 30 μl per 5 cm^2 and penetration
was checked after 16 hours. After the test the penetration level was
inspected by measuring the amount of material on the skin surface, in
the horny layer, in the upper part of the skin, in the lower part of the
25 skin and in the chamber (vitro). This was tested by wiping the surface to
remove all non-penetrated material and placing it in a glass vial,
followed by stripping the cleaned skin several times with adhesive tape
to remove the horny layer and placing the tapes in a second glass vial.
The stripped skin was then divided in an upper and lower part. The
30 upper part was homogenised in 10ml of tetrahydrofuran and placed in a
third vial, while the lower part was treated separately in the same way
and placed in a fourth vial. The chamber liquid was then placed in a



fifth vial, the chamber rinsed with tetrahydrofuran which was also added to the vial.

The content of each of the vials was then extracted with tetrahydrofuran and analysed by high performance liquid chromatography. The most preferred materials are those where the amount of penetration in the lower skin is minimal. The results, based on an average from 2 experiments each, are shown in Table I.

Table I: Skin penetration values in %

	Example	Skin surface	Horny layer	Upper skin	Lower skin	Chamber liquid
10	3	90.7	1.6	7.5	0.2	<0.1
	4	73.7	24.0	2.1	0.2	<0.1
	5	89.4	6.7	3.5	0.4	<0.1
	6	98.5	3.2	0.9	0.4	<0.1
15	Comp. 1	88.9	6.1	3.3	1.7	<0.1
	Comp. 2	52.2	6.8	7.8	3.2	<0.1
	Comp. 3	46.3	3.0	8.5	2.8	9.4


It is clear that materials according to the invention have less penetration through the skin than prior art materials.

THIS SHEET HAS BEEN
REPLACED




Claims

1. An organosiloxane compound having at least one unit of the
5 general formula




any other units present in the said siloxanes being those represented by the general formula



10

- wherein R represents a C₁₋₈ alkyl or an aryl group, R¹ is a hydrogen atom or a C₁₋₅ alkyl group, R² is a hydrogen atom, a C₁₋₅ alkyl group or a group OR¹, R³ is a C₁₋₅ alkyl group, R'' represents a hydrogen atom, a monovalent C₁₋₈ hydrocarbon or halogenated
15 hydrocarbon group, a has a value of 0, 1 or 2, b has a value of 0, 1, 2 or 3 and n has a value of from 1 to 6, provided that the



group and the two R² groups are linked to the aromatic ring at the para- and both meta-positions in relation to the group -CH=C[C(O)OR³]₂.

20

2. An organosiloxane compound according to Claim 1 wherein at least 80% of all R and R'' groups are methyl groups.
3. An organosiloxane compound according to Claim 1 or 2 wherein
25 each R¹ is selected from hydrogen, methyl and ethyl.


THIS SHEET HAS BEEN
REPLACED



4. An organosiloxane compound according to anyone of the preceding claims wherein at least one R^2 group is a hydrogen, the other being hydrogen, methoxy or ethoxy.
5. An organosiloxane compound according to anyone of the preceding claims wherein R^3 is methyl or ethyl.
6. An organosiloxane compound according to anyone of the preceding claims wherein each R^1 and R^2 group is hydrogen.
- 10 7. An organosiloxane compound according to anyone of the preceding claims which is a substantially linear or cyclic diorganosiloxane polymer.
- 15 8. An organosiloxane compound according to anyone of the preceding claims wherein the group
- $$-C(R^1)=CH-(CR_2^1)_n-O-$$
- occupies the para-position on the aromatic ring in relation to the group $-CH=C[C(O)OR^3]_2$, and both groups R^2 occupy the meta-positions on the aromatic ring in relation to the group $-CH=C[C(O)OR^3]_2$.
- 20
9. An organosiloxane compound according to anyone of the preceding claims wherein the number of units (i) is limited to a maximum of 20% of the total number of siloxane units in the molecule.
- 25 10. An organosiloxane compound according to anyone of the preceding claims wherein the number of units (i) be limited to 10% or less of the total number of units.



THIS SHEET HAS BEEN
REPLACED




11. An organosiloxane compound according to anyone of the preceding claims wherein units of the general formula (i) are situated at the end of the organosiloxane compound.




12. An organosiloxane compound according to anyone of the preceding claims having two end-blocking units of formula (i) and from 8 to 90 units of the general formula (ii).

13. A compound of the formula



wherein R^1 is a hydrogen atom or a C_{1-5} alkyl group, R^2 is a hydrogen atom, a C_{1-5} alkyl group or a group OR^1 , R^3 is a C_{1-5} alkyl group and n has a value of from 1 to 6, provided that the group containing the unsaturated carbon-carbon triple bond and the two R^2 groups are linked to the two meta-positions and to the para-position on the aromatic ring in relation to the ester containing group.


14. A silane having the general formula



wherein R , R^1 , R^2 , R^3 and n are as defined above, Z is a hydrolysable group and x has a value of 0, 1 or 2.

15. A process for the preparation of the organosilicon compounds of claim 1 which comprises reacting together

(A) a compound of the general formula




wherein R^1 is a hydrogen atom or a C_{1-5} alkyl group, R^2 is a hydrogen atom, a C_{1-5} alkyl group or a group OR^1 , R^3 is a C_{1-5} alkyl




group and n has a value of from 1 to 6, provided that the group containing the unsaturated triple bond and the two R² groups are linked to the two meta-positions and to the para-position of the aromatic ring in relation to the group

5 -CH=C-[C(O)OR³]₂ and

(B) an organosilicon compound having at least one unit of the general formula



any other units present in the organosilicon compounds being those
10 represented by the general formula



wherein R, R'', a and b are as hereinabove defined.

16. A process according to Claim 15, wherein stoichiometric
15 proportions of (A) and (B) or a slight stoichiometric excess of (A) are used.

17. A process for the preparation of the organosilicon compounds of claim 1, which comprises submitting a hydrolysable silane of claim 14
20 to cohydrolysis with a further hydrolysable silane or submitting it to equilibration with a cyclic or linear polydiorganosiloxane exhibiting the units of formula (ii) as given in Claim 1.

18. A cosmetic or a coating composition comprising an
25 organosiloxane compound according to anyone of Claims 1 to 12.

19. The use of an organosiloxane compound according to anyone of Claims 1 to 12 as absorber for the ultraviolet light.

AMENDED CLAIMS

[received by the International Bureau on 2 October 1992 (02.10.92);
original claim 14 amended; remaining claims unchanged (1 page)]

11. An organosiloxane compound according to anyone of the preceding claims wherein units of the general formula (i) are situated at the end of the organosiloxane compound.




5 12. An organosiloxane compound according to anyone of the preceding claims having two end-blocking units of formula (i) and from 8 to 90 units of the general formula (ii).

This Sheet Has Been Replaced




13. A compound of the formula



wherein R^1 is a hydrogen atom or a C_{1-5} alkyl group, R^2 is a hydrogen atom, a C_{1-5} alkyl group or a group OR^1 , R^3 is a C_{1-5} alkyl group and n has a value of from 1 to 6, provided that the group containing the unsaturated carbon-carbon triple bond and the two R^2 groups are linked to the two meta-positions and to the para-position on the aromatic ring in relation to the ester containing group.


14. A silane having the general formula



wherein R , R^1 , R^2 , R^3 and n are as defined above, Z is a hydrolysable group and x has a value of 0, 1 or 2.

15. A process for the preparation of the organosilicon compounds of claim 1 which comprises reacting together

(A) a compound of the general formula



wherein R^1 is a hydrogen atom or a C_{1-5} alkyl group, R^2 is a hydrogen atom, a C_{1-5} alkyl group or a group OR^1 , R^3 is a C_{1-5} alkyl

THIS SHEET HAS BEEN
REPLACED