CLAIMS

Claim 1. A preform coating method comprising:

a step of using a deaeration module having hollow fiber membranes to deaerate a coating solution; and

a step of coating the deaerated coating solution on a preform.

Claim 2. The preform coating method according to claim 1, wherein the coating solution to be deaerated is not degassed in advance.

Claim 3. The preform coating method according to any one of claims 1 and 2, wherein the coating solution is a barrier coating solution having a gas barrier property or a protective coating solution for protecting the barrier coating solution.

Claim 4. The preform coating method according to any one of claims 1 to 3, wherein the coating solution has a viscosity of 25 mPa·s to 10000 mPa·s.

Claim 5. The preform coating method according to claim 4, wherein the coating solution has a viscosity of 50 mPa·s to 10000 mPa·s.

Claim 6. The preform coating method according to claim 5, wherein the coating solution has a viscosity of 100 mPa·s to 10000 mPa·s.