



POLYMER MODIFIED GYPSUM MEMBRANE AND USES THEREFOR

This invention relates to a composition containing a polymer component and gypsum
5 and its utility as a membrane coating on various target substrates. It is useful in the
construction industry as coatings for sandwich panels, molding, duct-work, piping and
cladding systems. It also is useful in traffic paint applications and other transportation
industry safety coatings. It is of particular value, though, as a semi-impervious reinforcing
membrane on the internal surfaces of subterranean mines. Further, this invention provides a
10 method for applying the novel composition to rapidly set up on these substrate surfaces. In
addition, the invention may be used in the manufacture of fiber reinforced composite
structures and composite construction components, for example laminated panels for use in
cladding. Although the description below relates primarily to the use of the invention as a
reinforcing membrane for use in subterranean mines, the invention is not limited to such
15 applications and may be used in, for example, any of the applications mentioned
hereinbefore.

Particular problems exist in underground mining operations for coal, gold, platinum
and the like in which it is necessary to provide support to the wall and ceiling surfaces of the
mine shafts as soon after excavation as possible. This is because the recently excavated rock
20 facing may be susceptible to cracking and spalling. If exposed for too long a period of time,
rock fragments will begin to fall away from the wall and ceiling surfaces of the newly
excavated rocks. This presents an obvious hazard to both mining personnel and machinery.

An additional problem that must be addressed by any coating membrane is the
prevention of gas exchange, such as methane, from the newly exposed rock surfaces. The
25 spread of such gases throughout the mining tunnel system can pose serious health threats to
the mining personnel. Further, any coating must be virtually impervious to moisture, thus
setting up a barrier between the excavated rock and the internal mine environment.

Mine tunnel systems are made up of different areas. The main access tunnels tend to
be much larger than regions referred to as "stopes". Stopes are the primary excavation areas
30 of the mine. It is advantageous to apply a coating membrane to both areas. Each area,
however, presents its own unique problems.

Conventional coatings in the main access areas are cementitious. These coatings
require large equipment to perform the application process. They are often used in these
areas because of the adequate amount of room available to accommodate heavy application



equipment. One type of cementitious coating is referred to as "shotcrete". As disclosed in U.S. Patent No. 4,046,357, shotcrete is a slurry made up of Portland cement which is sprayed under pressure onto the internal surfaces of the larger access areas. The problems with use of these types of coatings are that the application process is very messy, creating "splash back" and excessive dripping. Further, these coatings often take a long time to set up, from 15 minutes to over four hours. This time frame, coupled with the need to clean up from the messy application process, may require shutting down the recently coated area to vehicular traffic or other activities, thus adversely affecting productivity.

These types of heavy cementitious coatings have proven to be unacceptable in the stope regions of the mine because these regions are very confining with ceiling heights sometimes no greater than 1.2 to 1.5 meters. Lighter weight resin systems, which can be applied with lighter weight and smaller equipment are preferable. Polyesters and polyurethanes had been tried and had shown some promise but are now widely banned in mining operations due to safety and health concerns. They tend to generate toxic fumes upon curing and exhibit poor resistance to flammability. Neither of these results are desirable in a closed environment such as a subterranean mine system.

Gypsum formulations have been widely used for mining operations. Gypsum is inexpensive but it has its drawbacks. For example, gypsum forms a notoriously poor moisture barrier. Resistance to moisture seeping out of the excavated rock is important in mining operations. If moisture is allowed to seep into the mine shafts and tunnels, at the very least, it will create a very unpleasant working environment for the miners, and in the worst case, will cause erosion or pooling on walkways or roadbeds, requiring constant preventative or rehabilitative maintenance. Organic polymer resins have been blended with gypsum materials with the objective of resolving this problem. However, such systems have always been designed around using gypsum as the primary film forming barrier. The addition of polymer resins as a secondary, non-continuous barrier only reduces severity of moisture permeability. Also, as with shotcrete, due to the difficulty in applying a heavy gypsum based coating onto the internal surfaces of such a confining work environment as the stope regions of a mine, this type of coating is undesirable here, as well.

As a result of the difficulties attendant with the use of gypsum or cement based coatings, coupled with the current ban on polyester and polyurethane coatings, there has existed for some time a need for a non-toxic, moisture and gas impermeable coating which may be applied with light weight equipment and which will set very rapidly upon contact

with excavated rock surfaces. The present invention presents a viable solution to these problems.

The present invention provides a composition which comprises, as its primary ingredients, a polymer resin and gypsum. The polymer resin is in the form of an aqueous emulsion. The composition is prepared in two separate components, one containing a resin and the gypsum and a set retarder to prevent the premature setting of the gypsum. The second component contains a different resin, a filler and a set activator, which, when combined with the first component, will initiate the setting of the gypsum.

The composition may be supplied to the work site in two components, one consisting primarily of the polymer resin and the other containing the gypsum. The two components are applied to the target surface either separately or immediately after being blended where they rapidly react to form a quick setting membrane.

One aspect of the invention is a composition containing components A and B, wherein component A comprises:

- gypsum,
- an alkaline polymer resin, and
- a set retarder,

and component B comprises:

- an acidic polymer resin,
- a filler, and
- a set activator.

A second aspect of the invention is a method for applying a membrane coating onto a substrate surface. This method is particularly well suited for application onto the newly excavated surfaces of a subterranean mine system. During application, components A and B are applied at a volume ratio of from 7 to 3, respectively, to 3 to 7. The optimum ratio may be determined by considering factors such as the surface to be treated, the time required for cure and other processing concerns.

A third aspect of the invention is a membrane which forms on the surface of a substrate comprising a continuous polymeric resin film and cured gypsum. Even though the membrane is very thin, it is substantially impervious to gas and moisture seepage out of the substrate. The membrane may be from 0.1 to 10mm thick, depending on the working environment and application conditions.

Application is most conveniently done by use of pressurized spray applicators. Component A and component B may be fed via separate hose or duct systems to either a

single or dual applicator nozzles, where both are sprayed either simultaneously, as through dual nozzles, or as a blend, via a single nozzle, onto the target excavated rock surface. By applying pre-determined volumes of components A and B, the person performing the task of applying the membrane is not left with the task of trying to calibrate the amounts of both components being sprayed so as to optimize cure times and coating thicknesses. This optimization has already been determined prior to formulating and delivering components A and B to the work site.

At the moment components A and B are combined, the activator from component B will initiate the setting of the gypsum from component A. Since it is originally in a hemihydrate state, as it sets, the gypsum will require water. The gypsum rapidly withdraws water from the polymer resins, which are in an emulsified state. This then causes the polymers to "film over" the surface of the substrate. It is this polymeric film that provides resistance to the escape of gases and moisture from the newly exposed rock surface.

The membrane formed by the application of the present composition provides excellent resistance to the exchange of gases, such as methane, which might leach out from the newly exposed rock. Further, it provides a coating which is substantially impervious to moisture. The present composition readily adheres to various substrates, especially newly excavated subterranean rock, which helps to reinforce the exposed facing of these rocks so as to prevent fragments from "calving" off and falling onto either mining personnel or their equipment.

An additional advantage associated with this invention relates to its ease of handling. It is possible to eliminate measuring or the addition of ingredients at the point of use. Since the two components, A and B, are applied at pre-determined rates, the application equipment may be relatively simple in design. Components A and B may be mixed off site and transported to the work site in closed containers. Although various application techniques may be used, it may be preferable to use a spray applicator, especially if the target substrate is the recently excavated rock surface of a subterranean mine. Once at the point of use, the two components may then be fed into spray equipment and sprayed together onto the surface to be treated. The blended components will then set up very rapidly to form a membrane on the rock surface.

The membrane coating thickness may vary as conditions warrant, but generally, they range from 0.1 to 10mm. The preferred thickness is in the range of 0.5 to 5mm and most preferably from 1 to 2 mm. The novel polymer/gypsum composition of the present invention will set up quickly on the treated rock surface. A final membrane coating thickness in the

range of 1 to 2 mm will set up in less than 3 minutes and most probably in approximately 1 minute.

The polymer resins useful in this invention are primarily derived from polymers of ethylenically unsaturated monomers and include vinyl resins and polymers of acrylates and methacrylates. Examples include methyl acrylate, butyl acrylate, ethyl acrylate, methyl methacrylate, ethyl methacrylate, butyl methacrylate, hexyl methacrylate and lauryl methacrylate. Other polymer resins which may be used are styrene, vinyl acetate, vinyl versatate and vinyl chloride. Copolymers of two or more of these classes of monomers can be employed as desired depending on the properties required in the final membrane composition. The term "copolymer" as used herein is intended to include polymer blends as well as true copolymers. An example of a suitable alkaline copolymer is AC339, which is an acrylate polymer, available from the Rohm and Haas Co. of Philadelphia, PA. An example of a suitable acidic copolymer is HA16, also available from Rohm and Haas, which is an acrylate/acrylamide copolymer.

When selecting monomers or monomer blends for use in the composition of the invention, it is necessary to keep in mind the various properties of each monomer. For example, polystyrene is alkali-resistant and water resistant, but its long term aging properties are not very good. For some applications, this negative feature may be an acceptable accommodation. Polyvinylacetate has low water resistance but in certain applications, e.g., when the composition is applied to a subterranean surface which is substantially devoid of moisture, this may be acceptable. The acrylate and methacrylate resins have good long term aging properties and good water and alkali resistance, but they may require flow additives to improve their flow characteristics. For applications where having good flow characteristics is not an issue, the choice of this resin is not a problem and may in fact be desired based on the many other valuable properties exhibited by the acrylate class of resins. The amount of polymer resin present in either component A or component B is from 20 -99 parts, based on the total weight of the respective component.

One of the properties which should be considered in the choice of a polymer is the "glass transition temperature" or "Tg". The glass transition temperature of a polymer is the temperature at which a polymer transitions from a rigid, glassy state at temperatures below Tg to a fluid or rubbery state at temperatures above Tg. The Tg of a polymer is typically measured by differential scanning calorimetry (DSC) using the mid-point in the heat versus temperature transition as the Tg value. A typical heating rate for the DSC measurement is 20°C/minute. The Tg of various homopolymers may be found, for example in Polymer

Handbook, edited by J. Brandrup and E. H. Immergut, Interscience Publishers. The Tg of a polymer is calculated using the Fox equation (T. G. Fox, Bull. Am. Physics Soc., Vol. 1, Issue No. 3, page 123, 1956).

5 The preferred Tg for the polymer resin is in the range of -20° to 50°C, with the most preferred range being from 0° to 40°C. As for the examples cited earlier, the Tg of AC339 is 26°C and for HA16 it is 35°C.

10 The pH of the polymer is important in that it affects the stability of the formulation. Specifically, in order for the gypsum to remain stable and not set up after being formulated but before use, the specific polymer binder must be alkaline. Thus, the polymer formulated into component A must be alkaline. The pH of the polymer in component B is not as critical since it does not come into contact with the gypsum until the two components are blended with the intent of causing the gypsum to set up. This polymer may be either acidic or alkaline. However, it may be preferable to use an acidic polymer since, once components A and B are blended, the resulting blend will have a final pH in the neutral range, thus avoiding
15 any potentially negative consequences from the formation of a membrane either too acidic or too alkaline.

The polymer resin may be emulsified or it may be in the form of a water redispersible powder. While either system may work in the operation of the present invention, it may be commercially more feasible to utilize emulsified polymer resins. Emulsions which are
20 formulated for the composition of the invention may contain about 35 to 65% solids, preferably 45 to 55%, by volume. The concentration used will, of course, depend on the characteristics required in the final membrane coating and the speed of cure. However, since the continuous phase of the membrane formed consists of a polymer film and not a gypsum film, a high polymer loading is necessary to achieve the objectives of the invention.

25 Numerous emulsion processes are known in the art. While any of these may be employed to create the specific polymer resin emulsions of the invention, reference is directed to "The Fundamental Principles of Polymerization" by D'Alelio (Wiley, pub., 1952) and "Principles of Polymer Chemistry" by R.J. Flory (Cornell University Press, pub., 1969) as indicative of suitable polymerization techniques.

30 The gypsum used in this invention may comprise a wide variety of settable forms of calcium sulphate which may include anhydrous calcium sulphate and/or chemical gypsum, commonly called synthetic gypsum, as well as calcium sulphate hemihydrate.

There are primarily two types of hemihydrate ($\text{CaSO}_4 \cdot 1/2\text{H}_2\text{O}$) which are commercially available and conventionally referred to as the alpha and beta forms. The alpha hemihydrate is conventionally prepared by placing lump gypsum into an autoclave and calcining it at controlled superatmospheric pressure in the presence of steam. In contrast, 5 beta hemihydrate is prepared by heating the dihydrate at atmospheric pressure in either a kettle or rotary calciner. Although the physical appearances of these two types of gypsum may be the same, they differ in the water/gypsum ratio required to produce workable products. The dissimilarity in the physical nature of the gypsum particles of the two forms arises from the differences in their respective surface properties. The larger alpha crystals 10 have low water absorption and smaller surface area per unit weight. This translates into a lower water requirement to cause setting up, or curing, of the gypsum. The lower the weight of water in proportion to the weight of dry gypsum solids, the greater the strength of the final product after curing. The amount of gypsum used in the formulation of component A is from 50 to 80 parts, based on the total weight of component A. Preferably, 60-70 parts is 15 used.

The composition of the invention contains a hydration inhibitor to prevent the setting of the gypsum. It is incorporated into the "A" component in an amount of from 0.1 to 2.0 parts, based on the total weight of component A. The hydration inhibitor is a polymer or copolymer of a polycarboxylic acid. Examples include acrylic acid, methacrylic acid, 20 itaconic acid and fumaric acid. Copolymers of acrylic acid or methacrylic acid and an alkyl ester of acrylic acid or methacrylic acid, or esters thereof, such as methyl acrylate, or polycarboxylic acid anhydrides are preferred hydration inhibitors. The polymeric inhibitor may conveniently be in the form of the sodium or ammonium salt. A preferred hydration inhibiting copolymer may contain from about 50 to 99.9 percent acrylic acid and about 0.1 to 25 about 50 percent acrylamide, by weight. More preferably, the copolymer consists of about 95 to 98 percent acrylamide, by weight, and about 1 to 5 percent, by weight, of acrylic acid. Examples of suitable hydration inhibitors are Acumer 9141, sold by the Rohm and Haas Co., Philadelphia, PA and Coatex TP-30.

An activator is included in the "B" component so that upon intermixing with the "A" 30 component, setting of the gypsum will be initiated. This then leads to the formation of a polymer resin film on the targeted substrate. The amount of activator required will be based on the amount of alpha gypsum and hydration inhibitor present in the composition. The activator will preferably be added in an amount of from 0.1 to 6.0 weight percent, and more preferably from 0.1 to 4.0 weight percent, based on the weight of the solids content of

component B. Suitable activators include metallic salts which can provide acidic cations. Preferable metallic salts are aluminum sulfate, calcium sulfate, ferric sulfate, zinc sulfate and ferric chloride. The most preferred activator for this composition is aluminum sulfate.

A filler may be used in the present composition to provide bulk to the formulation.

- 5 Examples of suitable fillers are sand, mica, silica aluminate and fly ash. A low density fly ash is commercially available as "Hollowfill". The filler is best added to component B and may be present in an amount of 30-50%, by weight. Preferably, filler may be added in an amount of 35-45%, by weight.

- 10 The composition of the invention will now be described by example. It should be understood that other ingredients are added to the composition in order to aid processing, handling or formulating. Ingredients which are traditionally utilized in coatings include anti-foamers, surfactants, rheology modifiers, set control agents, coalescing agents and expansion agents.

15 .Legend: Ingredients

Alkaline binder:	AC339: acrylic latex emulsion;Rohm and Haas Co.
Antifoam:	S882, Wacker Silicones
Surfactant:	X405/70, Triton
20 Expansion agent:	Potassium Hydrogen Tartrate
Coalescing agent:	Butyl Carbitol
Set control agent:	Sodium citrate
Rheology Modifier:	RM 2020; acrylic polymer: Rohm and Haas Co.
Hydration Inhibitor:	TP-30; polycarboxylate; Coatex Corp.
25 Acidic binder	HA16:acrylic/acrylate polymer;Rohm and Haas
Activator:	Aluminum sulphate
Gypsum:	Alpha hemi-hydrate
Filler:	Millisil C-7; aluminum silicate

30 EXAMPLE

Component A (pre-mix)

<u>ingredient</u>	<u>parts by weight</u>
-------------------	------------------------

	alkaline binder	93.94
	antifoam	1.00
	surfactant	1.75
	rheology modifier	.11
5	hydration inhibitor	1.35
	excess water	1.86
	total	100.00

10 Formulated Component A

	gypsum	69.23
	pre-mix (A)	30.77
	total	100.00

15

pH	8.4
solids	83.8%
density	1.84

20 Component B (pre-mix)

<u>ingredient</u>	<u>parts by weight</u>
acidic binder	57.18
defoamer	.57
25 expansion control	.56
coalescing agent	1.50
activator	2.79
filler	143.0
excess water	2.79
30 total	208.40

pH	2.7
solids	83.4%
density	1.82

Formulation

	ratio by volume	ratio by weight
Component A	1	50.17
Component B	1	49.83

5

Application

Components A and B are then transported to the point of use in separate containers. The method of application is via spray application. Appropriate spray applicators may be acquired from the Sagola Co. in Spain. The container holding the aqueous dispersion of component A is attached to one of the feed systems. Similarly, the container holding the aqueous dispersion of component B is attached to another feed system. Both components A and B are combined in equal volumes inside the spray applicator immediately prior to application. The blended solution is then sprayed onto a rock surface at 30 psi.

10

15

Results

set time:	1 minute
thickness:	2mm
moisture permeability	low
gas exchange	low

20

Claims:

1. A composition comprising component A and component B;
wherein component A comprises:
 - 5 -gypsum,
 - an alkaline polymer resin, and
 - a hydration inhibitor; and
 - wherein component B comprises:
 - an acidic polymer resin,
 - 10 -a filler, and
 - an activator.

2. The composition of claim 1 wherein both components A and B are dispersed in water to create an aqueous dispersion.

- 15 3. The composition of claim 2 wherein the volume ratio of component A to component B is from, and including, 7 to 3 to, and including, 3 to 7.

4. The composition of claim 1 wherein the polymer resins are derived from polymers of ethylenically unsaturated monomers.

- 20 5. The composition of claim 4 wherein the ethylenically unsaturated monomers are selected from the group consisting of vinyl, acrylates, methacrylates, styrene, vinyl acetate, vinyl acetate and vinyl versatate.

- 25 6. The composition of claim 1 wherein the hydration inhibitor is an aqueous polycarboxylate.

7. The composition of claim 1 wherein set activator is selected from the group consisting of aluminum sulfate, potassium sulfate, calcium sulfate, ferric sulfate, zinc sulfate and ferric chloride.

- 30 8. The composition of claim 7 wherein the set activator is aluminum sulfate.

9. The composition of claim 1 wherein the gypsum is calcium sulfate hemihydrate.

10. The composition of claim 9 wherein the calcium sulfate hemihydrate is alpha hemihydrate.

5

11. The composition of claim 1 wherein the amounts, by weight, of the ingredients of component A are: 20-99 parts alkaline polymer resin; 50-80 parts gypsum and 0.1-2.0 parts hydration inhibitor, based on the total weight of Component A.

10 12. The composition of claim 1 wherein the amounts of the ingredients of component B are: 20-99 parts acidic polymer resin; 30-50 parts filler and 0.1-6.0 parts activator, based on the total weight of component B.

13. A method of forming a membrane onto a substrate comprising applying to said
15 substrate the composition of claim 1.

14. The method of claim 13 wherein the substrate is the excavated rock surface of a subterranean mine.

20 15. The method of claim 13 wherein the composition comprises components A and B.

16. The method of claim 15 wherein the volume ratio of A:B is from 7:3 to 3:7.

17. The method of claim 16 wherein the volume ratio of A:B is 1:1.

25

18. The method of claim 13 wherein the components A and B are blended immediately prior to being applied to the substrate by means of a pressurized spray applicator.

19. The method of claim 13 wherein the thickness of the membrane is from 0.1mm to
30 10mm.

20. A membrane formed on the surface of a substrate comprising a continuous polymeric resin film and gypsum.

21. The membrane of claim 20 wherein the substrate is the rock surface of a subterranean mine.
22. The membrane of claim 20 wherein the thickness of the membrane is from 0.1 to
5 10mm.
23. The membrane of claim 22 wherein the thickness of the membrane is from 0.5 to 5.0mm.
- 10 24. The membrane of claim 20 wherein the continuous polymeric resin film and gypsum are formed by applying onto the surface of the substrate the composition of claim 1.