

Description

The invention relates to fibrous structures, for example fibrous mats or fibrous tubular structures. More particularly but not exclusively, the invention relates to fibrous synthetic vascular grafts.

In the past, it has been proposed to produce fibrous structures such as mats by a process using electrostatic attraction, where a polymer such as polyurethane in solution is ejected from a fine nozzle towards a surface, between which surface and the nozzle exists an electrostatic potential. Between the nozzle and the surface, fibres of the polymer are formed and the fibres are attracted to the surface. This process has been adapted to make tubular fibrous structures usable as synthetic vascular grafts by providing the surface in the form of a rotating mandrel so that a fibrous tube is gathered around the mandrel.

The electrostatic spinning process is described in some detail in U.S. Patent Specification No. 4044404 and proposals to use the electrostatic spinning process for making synthetic vascular grafts have been made, for example, in a paper by Annis et al in 1978 (Trans. Am. Soc. Intern. Organs). The microstructure of the fibrous material produced during electrostatic spinning is also described in the Annis et al paper. More recently, developments have been made in matching properties of synthetic vascular grafts to in vivo conditions, as in our British Patent Application No. 8217487 published under No. 2120946A and in controlling anisotropic properties of grafts in our British Patent Application No. 8216066, published under No. 2121286A.

According to the invention there is provided an integral fibrous structure of a plurality of continuous, polymeric filaments, individual filaments extending from one side of the structure to the opposite side of the structure, the portions of the filaments on one side of the structure being of a first polymeric composition and the portions of the filaments on the opposite side of the structure being of a second polymeric composition different from the first polymeric composition.

The term "different polymeric composition" is intended to cover a variation of the composition of the filaments where the polymer itself does not change across the structure but, for example, an additive is present in the composition at one side of the structure but not present at the opposite side of the structure.

The structure may comprise a transition area between the sides of the structure, and the portions of the filaments in the transition area may have a polymeric composition comprising a mixture of the first and second polymeric compositions.

The polymeric composition of the filaments may vary progressively between the two sides of the structure, and the composition of the portions of the filaments in the transition area adjacent the one side of the structure may contain a large proportion of the first polymeric composition and

the portions of the filaments adjacent the opposite side of the structure may contain a large proportion of the second polymeric composition.

Alternatively, the composition of the filaments may change abruptly to provide distinct layers within the structure having different polymeric compositions. There may be more than two layers in the structure.

The structure may be in the form of a mat, or may be a tubular member.

When the structure is a tubular member, the portions of the filaments at the inner surface of the tubular member are preferably of the first polymeric composition to provide compatibility with material with which the inner surface will come into contact, and the portions of the filaments at the outer surface of the tubular member are preferably of the second polymeric composition to provide desirable strength characteristics and other physical properties to the tubular member.

The tubular member may be cut to provide one or more segmental elements from the tubular wall. If the internal diameter of the tubular member is large enough, for example a few centimetres, the segmental element or elements will tend towards being planar, and may be used as pledgets.

The invention further provides a method of forming an integral fibrous structure according to the invention, which method comprises the steps of directing filaments of a first polymeric composition at a surface to start building up a fibrous structure of the first polymeric composition, and altering the composition of the filaments during production thereof such that the portions of the filaments at the side of the structure remote from the surface is of the second polymeric composition.

The composition of the filaments may be changed abruptly or may be varied gradually across the structure.

By way of example, one embodiment of a fibrous structure and its method of production according to the invention will now be described with reference to the accompanying drawings, in which:—

Figure 1 is a diagrammatic view of apparatus for producing a tubular fibrous structure;

Figure 2 is a graph illustrating concentration of one polymeric composition in a structure wall; and

Figure 3 is a part sectional view of a tubular fibrous structure produced by the apparatus of Figure 1.

Figure 1 shows diagrammatically apparatus for electrostatically spinning a synthetic vascular graft. Polymer solution is ejected from capillary needles 10 towards an electrostatically charged mandrel 11 rotating at several thousand revolutions per minute, for example 5000 r.p.m. Typically, the mandrel 11 is at a potential of -12kV with respect to the needles 10. As polymer solution leaves the needles 10, polymer filaments form and these filaments are attracted to the

rotating electrostatically charged mandrel 11 to form a fibrous structure around the mandrel. When the fibrous structure has been built up, the structure is removed from the mandrel to provide a fibrous tube.

Mechanical properties of the tubular fibrous structure formed on the mandrel 11 can be controlled by variation of the speed of rotation of the mandrel, the type of polymer used and by altering, the potential of auxiliary electrodes 12.

The capillary needles 10 are supplied with polymer solution from a manifold 13, the manifold 13 being supplied by tubes 14 and 15 meeting in a T connector 16. Both tubes 14 and 15 include a flexible coil 17 and 18 respectively. The tube 14 has a valve 19 and the tube 15 has a valve 20 to enable the respective tubes to be closed. Control lines 21 and 22 control opening and closing of the valves 19 and 20.

The tube 14 is supplied from a first air-ram driven syringe 23 and the tube 15 is fed from a second air-ram driven syringe 24 and the apparatus enables polymer solution from either syringe 23 or syringe 24 to be ejected from the needles 10 towards the mandrel 11. A purge line 25 including a closure valve 26 allows purging of the manifold 13.

The apparatus of Figure 1 allows formation of an integral, uninterrupted fibrous structure of continuous polymeric filaments around the surface of the mandrel 11, the portions of the filaments at the inside surface having a different polymeric composition from the portions of the filaments of the outside surface of the fibrous structure. This can be advantageous when the tubular fibrous structures are used for, for example, synthetic vascular grafts. It has been found that different polymers have different haemocompatibilities and that different polymers have different strength characteristics. In a particular example, one polyurethane has advantageous haemocompatibility but poor elastic properties, exhibiting high creep. A second polyurethane having a higher Young's modulus has satisfactory strength properties but poor haemocompatibility. The apparatus of Figure 1, as will be described in the following example, allows production of a synthetic vascular graft having a thin inner lining of the first polyurethane on a wall of the second polyurethane, the graft, however, being formed of fibres spun continuously, with individual fibres changing composition between their ends to provide an integral, uninterrupted, fibrous structure.

Example

The sequence of operation of the apparatus of Figure 1 in this example is as follows:—

1. Fill the syringe 24 with a first polymer dope and fill the syringe 23 with a second polymer dope.

2. Using the valves 19, 20 and 26, prime the tube 14 with the second polymer dope and then prime the tube 15 and the manifold 13 with first polymer dope.

3. With the valves 19 and 26 closed, commence electrostatic spinning with the first polymer dope contained in the syringe 24, the tube 15 and the manifold 13.

4. After a time, open the valve 19 and close the valve 20. After expression of remaining first polymer dope out of the needles 10, spinning continues in an uninterrupted fashion with second polymer.

5. The abruptness of the transition from the first polymer dope to the second polymer dope is a function of the rate of flow of second polymer dope into the manifold 13 and the volume of the manifold 13, needles 10 and T junction 16. This transition can be controlled by the use of the valve 26 on the purge line 25 which can be used to vent at a variable rate remaining first polymer dope. The concentration gradient of the two polymers in the graft wall will follow a defined, controllable relationship as illustrated in Figure 2 where the solid line shows an abrupt change where the valve 26 is used and the chain line shows a slow change.

A further development of the first example arises in that on porosity testing, it was found that the permeability of the bi-layer graft was too high. A situation was envisaged where transmural flow of blood or plasma might lead to excessive blood platelet capture on the inner surface and compromise the thromboresistance of the graft. The solution here would be to include an outer layer of a third polymer, for example one having a high Young's modulus, which when deposited on the second polymer produces a dense matrix with low interstitial volume. In this way, the overall graft wall permeability is determined by this outer layer. Figure 3 shows in cross section part of a bi-layer graft. The further development would mean addition of an outer layer of a third polymer to the graft shown in Figure 3.

Many different polymers can be used in the electrostatic spinning process. Several examples are given in U.S. Patent Specification No. 4044404, such as polyurethanes, polyamides and polyacrylonitrile, all of which can be spun from solution, and polytetrafluoroethylene and polyesters which may be spun from dispersion. Water soluble polymers such as polyvinyl alcohol, polyvinyl pyrrolidone and polyethylene oxide may be spun from aqueous solution.

The constraint on the fibrous structure and method of production according to the invention is that the two or more polymers used to vary the composition of the filaments during the spinning process must be either dispersible or alternatively soluble in the same solvent system. Thus it would be possible to spin with different polyurethanes, as used in the preferred example, or with different polyesters in dispersion, but it would not be possible to change, for example, from a polyurethane to a polyester.

It will also be appreciated that the properties of a particular polymeric composition may be varied by the presence of an additive, even if the polymeric composition itself does not vary along

the length of a filament. For example, a silicone lubricant could be added to a polyurethane polymer and spun as the inner surface of a graft, the outer surface of the graft being the same polyurethane without the silicone lubricant. Such an example is included in the scope of the invention.

The advantage of the embodiments of grafts hereinbefore described are that the different layers can be optimised for particular properties, either in its morphology (e.g. porosity, pore shape, fibre size) or in its chemistry (e.g. type of polymer, presence of drug. For example, a drug such as heparin or prostacyclin may be included in the inner layer to improve the property with regard to contacting blood). If such layers are built up discontinuously, lines of weakness exist between the contiguous surfaces and delamination is likely to occur at quite low mechanical stresses. The advantage of the method hereinbefore described is that it builds different layers into an integrally formed fibrous structure so that the successive wall components are merged in a well controlled way.

An illustration of the advantage of a bi-layer graft according to the example described is that in an initial canine common carotid trial, a 300% improvement in patency over non-laminated, single component grafts were found. Other possibilities, for example pledgets and drug releasing vascular grafts are also quite possible.

It will be appreciated that while the embodiments described relate to tubular fibrous structures for use as vascular grafts, the invention is equally applicable to planar fibrous structures such as mats and that such alternative structures would have wide applications.

Claims

1. An integral fibrous structure of a plurality of continuous polymeric filaments, individual filaments extending from one side of the structure to the opposite side of the structure, the portions of the filaments on one side of the structure being of a first polymeric composition and the portions of the filaments on the opposite side of the structure being of a second polymeric composition different from the first polymeric composition.

2. A fibrous structure as claimed in Claim 1 comprising a transition area between the sides of the structure, the portions of the filaments in the transition area having a polymeric composition comprising a mixture of the first and second polymeric compositions.

3. A fibrous structure as claimed in Claim 2 wherein the composition of the portions of the filaments in the transition area adjacent the one side of the structure contain a large proportion of the first polymeric composition and the portions of the filaments in the transition area adjacent the opposite side of the structure contain a large percentage of the second polymeric composition.

4. A fibrous structure as claimed in any preceding Claim wherein the polymeric composition of

the structure varies progressively between the two sides of the structure.

5. A fibrous structure as claimed in Claim 1 wherein the composition of the filaments changes abruptly to provide distinct layers within the structure having different polymeric compositions.

6. A fibrous structure as claimed in any preceding Claim comprising a multiplicity of changes in polymeric composition of the fibres.

7. A fibrous structure as claimed in any preceding Claim in the form of a mat.

8. A fibrous structure as claimed in any one of Claims 1 to 7 in the form of a tubular member.

9. A fibrous structure as claimed in Claim 8 wherein the portions of the filaments at the inner surface of the tubular member are of the first polymeric composition to provide compatibility with material with which the inner surface will come into contact, and the portions of the filaments at the outer surface of the tubular member are of the second polymeric composition to provide desirable strength characteristics and other physical properties to the tubular member.

10. A fibrous structure comprising a tubular member as claimed in Claim 8 or Claim 9 cut to provide one or more segmental elements from the tubular wall.

11. A method of forming an integral fibrous structure as claimed in any preceding Claim, which method comprises the steps of directing filaments of a first polymeric composition at a surface to start building up a fibrous structure of the first polymeric composition, and altering the composition of the filaments during production thereof such that the portions of the filaments at the side of the structure remote from the surface is of the second polymeric composition.

12. A method as claimed in Claim 11 wherein the composition of the filaments is changed abruptly.

13. A method as claimed in Claim 11 wherein the composition of the filaments is varied gradually across the structure.

Patentansprüche

1. Integrale faserige Struktur einer Vielzahl von kontinuierlichen polymeren Fasern, wobei einzelne Fasern sich von einer Seite bis zur entgegengesetzten Seite der Struktur erstrecken, die Teile der Fasern auf einer Seite der Struktur aus einer ersten polymeren Zusammensetzung und die Teile der Fasern auf der entgegengesetzten Seite der Struktur aus einer zweiten polymeren Zusammensetzung, die unterschiedlich zur ersten polymeren Zusammensetzung ist, gebildet werden.

2. Faserige Struktur nach Anspruch 1, umfassend einen Übergangsbereich zwischen den Seiten der Struktur, wobei die Teile der Fasern in dem Übergangsbereich eine polymere Zusammensetzung aufweisen, die ein Gemisch der ersten und der zweiten polymeren Zusammensetzung ist.

the length of a filament. For example, a silicone lubricant could be added to a polyurethane polymer and spun as the inner surface of a graft, the outer surface of the graft being the same polyurethane without the silicone lubricant. Such an example is included in the scope of the invention.

The advantage of the embodiments of grafts hereinbefore described are that the different layers can be optimised for particular properties, either in its morphology (e.g. porosity, pore shape, fibre size) or in its chemistry (e.g. type of polymer, presence of drug. For example, a drug such as heparin or prostacyclin may be included in the inner layer to improve the property with regard to contacting blood). If such layers are built up discontinuously, lines of weakness exist between the contiguous surfaces and delamination is likely to occur at quite low mechanical stresses. The advantage of the method hereinbefore described is that it builds different layers into an integrally formed fibrous structure so that the successive wall components are merged in a well controlled way.

An illustration of the advantage of a bi-layer graft according to the example described is that in an initial canine common carotid trial, a 300% improvement in patency over non-laminated, single component grafts were found. Other possibilities, for example pledgets and drug releasing vascular grafts are also quite possible.

It will be appreciated that while the embodiments described relate to tubular fibrous structures for use as vascular grafts, the invention is equally applicable to planar fibrous structures such as mats and that such alternative structures would have wide applications.

Claims

1. An integral fibrous structure of a plurality of continuous polymeric filaments, individual filaments extending from one side of the structure to the opposite side of the structure, the portions of the filaments on one side of the structure being of a first polymeric composition and the portions of the filaments on the opposite side of the structure being of a second polymeric composition different from the first polymeric composition.

2. A fibrous structure as claimed in Claim 1 comprising a transition area between the sides of the structure, the portions of the filaments in the transition area having a polymeric composition comprising a mixture of the first and second polymeric compositions.

3. A fibrous structure as claimed in Claim 2 wherein the composition of the portions of the filaments in the transition area adjacent the one side of the structure contain a large proportion of the first polymeric composition and the portions of the filaments in the transition area adjacent the opposite side of the structure contain a large percentage of the second polymeric composition.

4. A fibrous structure as claimed in any preceding Claim wherein the polymeric composition of

the structure varies progressively between the two sides of the structure.

5. A fibrous structure as claimed in Claim 1 wherein the composition of the filaments changes abruptly to provide distinct layers within the structure having different polymeric compositions.

6. A fibrous structure as claimed in any preceding Claim comprising a multiplicity of changes in polymeric composition of the fibres.

7. A fibrous structure as claimed in any preceding Claim in the form of a mat.

8. A fibrous structure as claimed in any one of Claims 1 to 7 in the form of a tubular member.

9. A fibrous structure as claimed in Claim 8 wherein the portions of the filaments at the inner surface of the tubular member are of the first polymeric composition to provide compatibility with material with which the inner surface will come into contact, and the portions of the filaments at the outer surface of the tubular member are of the second polymeric composition to provide desirable strength characteristics and other physical properties to the tubular member.

10. A fibrous structure comprising a tubular member as claimed in Claim 8 or Claim 9 cut to provide one or more segmental elements from the tubular wall.

11. A method of forming an integral fibrous structure as claimed in any preceding Claim, which method comprises the steps of directing filaments of a first polymeric composition at a surface to start building up a fibrous structure of the first polymeric composition, and altering the composition of the filaments during production thereof such that the portions of the filaments at the side of the structure remote from the surface is of the second polymeric composition.

12. A method as claimed in Claim 11 wherein the composition of the filaments is changed abruptly.

13. A method as claimed in Claim 11 wherein the composition of the filaments is varied gradually across the structure.

Patentansprüche

1. Integrale faserige Struktur einer Vielzahl von kontinuierlichen polymeren Fasern, wobei einzelne Fasern sich von einer Seite bis zur entgegengesetzten Seite der Struktur erstrecken, die Teile der Fasern auf einer Seite der Struktur aus einer ersten polymeren Zusammensetzung und die Teile der Fasern auf der entgegengesetzten Seite der Struktur aus einer zweiten polymeren Zusammensetzung, die unterschiedlich zur ersten polymeren Zusammensetzung ist, gebildet werden.

2. Faserige Struktur nach Anspruch 1, umfassend einen Übergangsbereich zwischen den Seiten der Struktur, wobei die Teile der Fasern in dem Übergangsbereich eine polymere Zusammensetzung aufweisen, die ein Gemisch der ersten und der zweiten polymeren Zusammensetzung ist.



3. Faserige Struktur nach Anspruch 2, in der die Zusammensetzung der Teile der Fasern in dem der einen Seite der Struktur benachbarten Übergangsbereich einen großen Anteil der ersten polymeren Zusammensetzung enthält und die Teile der Fasern in dem der entgegengesetzten Seite der Struktur benachbarten Übergangsbereich einen großen Anteil der zweiten polymeren Zusammensetzung enthalten.

4. Faserige Struktur nach einem der vorstehenden Ansprüche, in der sich die polymere Zusammensetzung der Struktur zwischen den zwei Seiten der Struktur nach und nach ändert.

5. Faserige Struktur nach Anspruch 1, in der sich die Zusammensetzung der Fasern plötzlich ändert, um verschiedene Schichten in der Struktur mit unterschiedlichen polymeren Zusammensetzungen bereitzustellen.

6. Faserige Struktur nach einem der vorstehenden Ansprüche, umfassend eine Vielzahl von Änderungen in der polymeren Zusammensetzung der Fasern.

7. Faserige Struktur nach einem der vorstehenden Ansprüche in Form einer Matte.

8. Faserige Struktur nach einem der Ansprüche 1 bis 7 in Form eines röhrenförmigen Teiles.

9. Faserige Struktur nach Anspruch 8, in der die Teile der Fasern an der inneren Oberfläche des röhrenförmigen Teiles die erste polymere Zusammensetzung aufweisen, um Verträglichkeit mit einem Material, das mit der inneren Oberfläche in Kontakt kommt, zu erzeugen, und die Teile der Fasern an der äußeren Oberfläche des röhrenförmigen Teiles die zweite polymere Zusammensetzung aufweisen, um dem röhrenförmigen Teil erwünschte Festigkeitseigenschaften und andere physikalische Eigenschaften zu verleihen.

10. Faserige Struktur, umfassend ein röhrenförmiges Teil nach Anspruch 8 oder 9, das geschnitten wird, um ein oder mehrere Teilelemente aus der röhrenförmigen Wand bereitzustellen.

11. Verfahren zur Bildung einer integralen faserigen Struktur nach einem der vorstehenden Ansprüche, wobei das Verfahren die Schritte umfaßt, daß man Fasern einer ersten polymeren Zusammensetzung auf einer Oberfläche anordnet, um den Aufbau einer faserigen Struktur der ersten polymeren Zusammensetzung zu beginnen, und man die Zusammensetzung der Fasern während deren Herstellung ändert, so daß die Teile der Fasern auf der von der Oberfläche abgelegenen Seite der Struktur die zweite polymere Zusammensetzung aufweisen.

12. Verfahren nach Anspruch 11, bei dem die Zusammensetzung der Fasern plötzlich geändert wird.

13. Verfahren nach Anspruch 11, bei dem sich die Zusammensetzung der Fasern durch die Struktur nach und nach ändert.

Revendications

1. Structure unitaire fibreuse d'une série de filaments polymères continus, les filaments indi-

viduels s'étendant depuis un côté de la structure jusqu'au côté opposé de la structure, les portions de filaments sur un côté de la structure étant en une première composition polymère et les portions de filaments sur le côté opposé de la structure étant en une seconde composition polymère différente de la première composition polymère.

2. Structure fibreuse selon la revendication 1, comprenant une zone de transition entre les côtés de la structure, les portions de filaments dans la zone de transition ayant une composition polymère qui est un mélange des première et seconde compositions polymères.

3. Structure fibreuse selon la revendication 2, dans laquelle la composition des portions de filaments dans la zone de transition adjacentes à un côté de la structure contient une proportion importante de la première composition polymère alors que les portions de filaments dans la zone de transition adjacentes au côté opposé de la structure contiennent un pourcentage élevé de la seconde composition polymère.

4. Structure fibreuse selon l'une quelconque des revendications précédentes, dans laquelle la composition polymère de la structure varie progressivement entre les deux côtés de la structure.

5. Structure fibreuse selon la revendication 1, dans laquelle la composition des filaments change de façon brutale pour former des couches distinctes dans la structure ayant des compositions polymères différentes.

6. Structure fibreuse selon l'une quelconque des revendications précédentes comprenant une multiplicité de changements de la composition polymère de fibres.

7. Structure fibreuse selon l'une quelconque des revendications précédentes, qui est sous forme d'une nappe.

8. Structure fibreuse selon l'une quelconque des revendications 1 à 7, sous forme d'un élément tubulaire.

9. Structure fibreuse selon la revendication 8, dans laquelle les portions des filaments à la surface intérieure de l'élément tubulaire sont en une première composition polymère pour assurer la compatibilité avec les matières avec lesquelles ladite surface intérieure peut venir en contact, et les portions des filaments à la surface extérieure de l'élément tubulaire sont en une seconde composition polymère pour conférer des caractéristiques avantageuses de résistance et d'autres propriétés physiques à l'élément tubulaire.

10. Structure fibreuse comprenant un élément tubulaire selon la revendication 8 ou 9, découpé pour présenter un ou plusieurs éléments segmentés pour la paroi tubulaire.

11. Procédé de production d'une structure fibreuse unitaire selon l'une quelconque des revendications précédentes, qui consiste à diriger les filaments d'une première composition polymère à une surface pour commencer la construction d'une structure fibreuse en pre-



B

mière composition polymère et à changer la composition des filaments en cours de production de façon que les portions des filaments sur le côté de la structure éloigné de la surface soient en seconde composition polymère.

12. Procédé selon la revendication 11, dans

lequel on change de façon brutale la composition des filaments.

13. Procédé selon la revendication 11, dans lequel on change progressivement la composition des filaments à travers la structure.

5

10

15

20

25

30

35

40

45

50

55

60

65

6



* C L M S *