

ABSTRACT

A methacrylic resin [1] having a triad syndiotacticity (rr) of not less than 65% and a methacrylic resin [2] having a triad syndiotacticity (rr) of 45 to 58% are melt kneaded in a mass ratio of the methacrylic resin [1]/the methacrylic resin [2] of 40/60 to 70/30, and further melt kneaded preferably with a polycarbonate resin in a ratio of 1 to 10 parts by mass of the polycarbonate resin to the total 100 parts by mass of the methacrylic resin [1] and the methacrylic resin [2] to obtain a methacrylic resin composition.