

5
/

This Sheet Has Been Replaced

- 74 -



ABSTRACT OF THE DISCLOSURE

A magnetic toner for developing an electrostatic image is disclosed which has a binder resin, a magnetic material and an iron compound of the formula (I). The magnetic toner has a saturation magnetization of 20 to 50 Am²/kg and a coercive force of 40 to 200 oersted.

THIS SHEET HAS BEEN
REPLACED