

Description

[Technical Field]

5 The present invention relates to a liquid crystal display device and a retardation film, in which coloring in a birefringent liquid crystal display device is decolorized by compensation using a retardation film.

[Prior Art]

10 As an improved twisted liquid crystal display device in which a nematic liquid crystal panel having a twisting angle of 90° is arranged between a pair of polarizing plates, a device which realizes a sharp change in light transmittance with respect to a drive voltage by increasing the twisting angle to be about 270° is known as an STN (Super Twisted Nematic) liquid crystal display device (see, for example, U.S.P. No. 4,634,229).

15 In this STN liquid crystal display device, the polarizing direction of polarizing plates is arranged to cross the orientation direction of liquid crystal molecules, and high contrast is obtained by a birefringent effect derived from this arrangement.

Because the birefringent effect has wavelength dependency, when white light is transmitted through a birefringent liquid crystal display device, the transmitted light is undesirably colored.

20 In order to obtain full color display by using color filters of primaries R, G, and B in combination with this liquid crystal display device, therefore, coloring caused by the wavelength dependency of the birefringent effect must be decolorized.

25 As a method of decoloring coloring in the STN liquid crystal display device, a method in which an optical anisotropic layer is arranged together with an STN liquid crystal panel between a pair of polarizing plates so that the effect of the former is compensated for by the birefringent effect of the latter to obtain a colorless state is proposed (see, for example, U.S.P. No. 4,844,569).

In this case, although a second twisted liquid crystal panel or a retardation film is used as the optical anisotropic layer, the retardation film consisting of a stretched polymeric film is more advantageous in terms of a manufacturing cost.

30 When a polymeric film is uniaxially or biaxially stretched, polymer molecules are mainly oriented in a direction along which a stretching ratio is highest, i.e., in a main stretching direction to obtain a retardation film having optical anisotropy. In this case, assuming that a refractive index in the stretching direction is n_e and that in a direction perpendicular to the stretching direction in a film plane, i.e., in a widthwise direction is n_o , a value of $n_e - n_o = \Delta n$ is called a refractive index anisotropy or orientation birefringence. This value is determined by an intrinsic birefringent value, i.e., a specific optical anisotropy of a monomer which is a constituting unit of the polymeric film and a degree of orientation of high molecules. $n_e > n_o$ is obtained in an orientation film formed by stretching a polymeric material in which a refractive index in a molecular axis direction is larger than that in a direction perpendicular to the molecular axis direction, i.e., a polymeric material having a positive intrinsic birefringence value.

40 $n_e < n_o$, on the other hand, is obtained in an orientation film formed by stretching a polymeric material having a negative intrinsic birefringence value.

A product $\Delta n \cdot d$ of the refractive index anisotropy Δn and a film thickness d is called a retardation. In addition, the main stretching direction is sometimes called an optical axis for convenience.

45 By optimally balancing the retardation $\Delta n \cdot d$ of a retardation film with the product $\Delta n \cdot d$ of the refractive index anisotropy Δn of a liquid crystal and the thickness d of a liquid crystal layer and arranging the optical axis direction of the retardation film through an optimal angle with respect to the orientation direction of liquid crystal molecules, coloring caused by the birefringent effect of a liquid crystal panel can be compensated for to decolor a liquid crystal display device.

50 The above description is based on observation obtained when the liquid crystal display device is viewed from the front. When the device is viewed in an oblique direction, since values of $\Delta n \cdot d$ of the liquid crystal layer and the retardation $\Delta n \cdot d$ of the retardation film change, the coloring compensation conditions are lost. In this case, $\Delta n \cdot d$ of the retardation film varies more largely than that of the liquid crystal layer. In order to eliminate viewing angle dependency of the display device, therefore, it is most important to minimize viewing angle dependency of the retardation of the retardation film.

55 In view of the foregoing, there has been proposed a method of laminating a plurality of retardation films such that their optical axes are twistedly oriented (Japanese Patent Laid-Open No. 2-53025) or a method of overlapping two retardation films having positive and negative refractive index anisotropies with their stretching directions parallel to each other (Japanese Patent Laid-Open No. 2-67518), but neither methods can eliminate viewing angle dependency of the retardation $\Delta n \cdot d$. In addition, light transmittance is undesirably de-

creased because the thickness d of the retardation film must be increased to obtain a required retardation.

The present invention, therefore, arranges a retardation film having small viewing angle dependency of the retardation, using a combination of a plurality of anisotropic polymeric films within an allowable thickness range and provides an STN liquid crystal display device which is decoloured by compensating for colouring by using the retardation film.

According to the present invention there is provided a liquid crystal display device comprising a liquid crystal panel constituted by a nematic liquid crystal layer with positive dielectric anisotropy, having a twisted structure with a twisting angle of 180° to 300° and a pair of electrode substrates which sandwich said liquid crystal layer, a pair of polarizing plates arranged one on each of the sides of said liquid crystal panel, and a retardation film combination for colour compensation arranged between said pair of polarizing plates, characterised in that said retardation film combination comprises a first retardation film whose refractive index in a main stretching direction is greater than its refractive index in a direction perpendicular to its main stretching direction and a second retardation film whose refractive index in a main stretching direction is smaller than its refractive index in a direction perpendicular to its main stretching direction both said retardation films being constituted by stretched polymeric films and arranged such that said main stretching directions thereof cross each other within an angle range of $90^\circ \pm 35^\circ$.

Also, a retardation film combination according to the present invention is as claimed in claim 5.

Fig. 1 is a perspective view showing a retardation film, for explaining a relationship between a stretching direction and optical characteristics of a retardation film formed by stretching a polymeric film, Fig. 2 is a graph showing a change in retardation caused by viewing angle dependency of a retardation film according to an embodiment of the present invention, compared to comparative examples of independent retardation films, Fig. 3 is a developed perspective view showing an arrangement of an embodiment of a liquid crystal display device according to the present invention, and Fig. 4 is a front view showing a relationship between the optical directions of members constituting the liquid crystal display device shown in Fig. 3.

[Best Mode of Carrying Out the Invention]

Before description of an embodiment of the present invention, birefringence of a retardation film formed by stretching a polymeric film and viewing angle dependency of a retardation $\Delta n \cdot d$ will be described below with reference to the accompanying drawings.

Fig. 1 is a perspective view showing a retardation film 20 formed by stretching a polymeric film.

Assuming that a refractive index in a stretching direction 21 is n_e and that in a direction perpendicular to the stretching direction in a retardation film plane, i.e., in a widthwise direction 22 is n_o , $n_e - n_o = \Delta n$ is called birefringence or orientation birefringent value, and a product $\Delta n \cdot d$ of Δn and a thickness d of the retardation film is a retardation.

When a viewing point is moved along a curved arrow 24 from a position immediately above the retardation film while a viewing direction (observation direction) is set to agree the stretching direction 21, a change in retardation $\Delta n \cdot d$ observed in a vertical direction 23 is decreased as indicated by curves 31 and 32 shown in Fig. 2. When the viewing point is moved along a curved arrow 25 from the position immediately above the retardation film while the viewing direction is set to agree the widthwise direction 22, the change in retardation $\Delta n \cdot d$ is increased as indicated by curves 33 and 34 shown in Fig. 2.

By overlapping a first retardation film having a positive intrinsic birefringence value $n_{o1} - n_{o1} > 0$ and a second retardation film having a negative intrinsic birefringence value $n_{o2} - n_{o2} < 0$ such that their stretching directions are substantially perpendicular to each other, therefore, the widthwise direction along which the viewing angle dependency of a retardation is increased is combined with the stretching direction along which it is decreased, and a synthetic viewing angle dependency becomes very small as indicated by curves 35 and 36 shown in Fig. 2.

In addition, since larger refractive indexes (n_{e1} and n_{e2}) of the first and second retardation films are superposed on each other and their smaller refractive indexes (n_{o1} and n_{o2}) are superposed on each other, the anisotropy Δn of a synthetic refractive index becomes sufficiently large to realize a satisfactory retardation $\Delta n \cdot d$ even by a comparatively thin retardation film.

Note that Fig. 2 is a graph showing a change in retardation $\Delta n \cdot d$, caused by the viewing angle dependency, of each of Example 1 and Comparative Examples 1 and 4 to be described later.

An embodiment of a liquid crystal display device according to the present invention will be described below with reference to Figs. 3 and 4.

Fig. 3 is a developed perspective view showing an arrangement of the embodiment of a liquid crystal display device according to the present invention.

Referring to Fig. 3, a retardation film 102 having a positive intrinsic birefringence value and a retardation

film 103 having a negative intrinsic birefringence value are overlapped and arranged above an STN liquid crystal panel 104, and these three members are arranged between a pair of polarizing plates, i.e., upper and lower polarizing plates 101 and 105. A reflecting plate 106 for allowing the display device to be observed as a reflection-type device is arranged below the lower polarizing plate 105.

Fig. 4 is a front view showing a relationship between the optical directions of the constituting members shown in Fig. 3.

The liquid crystal panel 104 is an STN liquid crystal panel having positive dielectric anisotropy, in which nematic liquid crystals having refractive index anisotropy $\Delta n = 0.150$ are oriented in liquid crystal layer thickness $d = 6.4 \mu\text{m}$ to form a left-handed twisted structure having a twisting angle of 240° . The $\Delta n \cdot d$ value of the liquid crystal panel 104 is 960 nm .

Referring to Fig. 4, an alternate long and short dashed line 41 represents the orientation direction of liquid crystal molecules in an upper portion of the liquid crystal layer, and an alternate long and short dashed line 42 represents that in its lower portion. A twisting angle between the upper and lower orientation directions 41 and 42 is 240° , and an X-Y orthogonal coordinate system is defined such that a direction dividing this twisting angle into two equal parts is taken as the Y axis.

The retardation $\Delta n \cdot d$ of the negative retardation film 103 is -310 nm , and its main stretching direction is set to coincide with the direction of a straight line 43. An angle θ_1 defined between the line 43 and the X axis is set at 30° .

The retardation of the positive retardation film 102 is $+310 \text{ nm}$, and its main stretching direction is set to coincide with the direction of a straight line 44. An angle θ_2 defined between the line 44 and the X axis is set at 60° .

The polarization axis of the upper polarizing plate 101 is set along the direction of a straight line 45, and an angle P_1 defined between the line 45 and the X axis is set at 75° . The polarization axis of the lower polarizing plate 105 is set along the direction of a straight line 46, and an angle P_2 defined between the line 46 and the X axis is 15° .

The material of the retardation film according to the present invention will be described below.

Note that the retardation film of the present invention can be effectively applied to an industrial brilliancy analyzer, a circular dichroism device, a polarizing microscope, an antireflection plate, and the like as well as a liquid crystal display device.

Examples of a material having a positive intrinsic birefringence value are a transparent homopolymer or copolymer of, e.g., a polycarbonate resin, a cellulosediacetate resin, a polyphenyleneoxide resin, a polyester resin such as a polyethyleneterephthalate resin and a polyvinylalcohol-based resin, examples of a material having a negative intrinsic birefringent value are a transparent homopolymer or copolymer of, e.g., a poly(meth)acrylate resin, an unsaturated aromatic compound resin such as polystyrene, and a mixture or polymer alloy mainly consisting of the homopolymer or copolymer.

In particular, a polycarbonate resin, a cellulosediacetate resin, an acrylic resin mainly consisting of a methacrylate, and a styrene-based resin all of which have good transparency, mainly consisting of styrene are preferred.

Table 1 shows the results obtained by measuring the viewing angle dependency of a retardation of each of retardation films having a positive or negative intrinsic birefringence value, manufactured by stretching the polymeric materials as described above, and retardation films obtained by combining the retardation films thus manufactured such that their main stretching directions are substantially perpendicular to each other.

The viewing angle dependency is represented by an average value (%) of absolute values of changes in retardation observed when a viewing angle is inclined with respect to two orthogonal directions corresponding to the stretching and widthwise directions as shown in Fig. 1. As shown in Fig. 2, the retardation is increased when the viewing angle is inclined in one direction and is decreased in the other direction, but absolute values of the changes are substantially equal to each other in the two directions.

Table 1

	Arrangement			
	Intrinsic Birefringence Value (Positive)		Intrinsic Birefringence Value (Negative)	
	Resin	Stretching Method (Ratio)	Resin	Stretching Method (Ratio)
Example 1	PC	Uniaxial (2.5)	PS	Uniaxial (1.5)
Example 2	PC	Uniaxial (2.5)	PS	Uniaxial (1.5)
Example 3	PC	Uniaxial (2.5)	PS	Uniaxial (2.5)
Example 4	PC	Uniaxial (2.5)	PS	Biaxial (2.5 x 1.1)
Comparative Example 1	PC	Uniaxial (2.5)	-	-
Comparative Example 2	-	-	PS	Uniaxial (2.5)
Comparative Example 3	-	-	PS	Biaxial (2.5 x 1.1)
Example 5	PC	Biaxial (2.2 x 1.1)	Acryl	Uniaxial (1.5)
Example 6	PC	Biaxial (2.2 x 1.1)	Acryl	Biaxial (3.5 x 1.1)
Comparative Example 4	PC	Biaxial (2.2 x 1.1)	-	-
Example 7	PC	Uniaxial (2.5)	MS	Uniaxial (2.5)
Example 8	DAC	-	PS	Uniaxial (1.5)
Comparative Example 5	DAC	-	-	-

Table 1 (Continued)

	Thickness (μm)	Optical Path Difference (nm) (nm)	Viewing Angle Dependency (%)		
			15	30	45
Example 1	480	403	0	1	2
Example 2	420	246	1	2	4
Example 3	339	374	1	4	7
Example 4	327	309	1	3	7
Comparative Example 1	205	124	4	12	27
Comparative Example 2	134	-296	3	8	17
Comparative Example 3	122	-220	5	15	34
Example 5	522	218	1	2	5
Example 6	522	182	2	5	9
Comparative Example 4	198	106	7	21	42
Example 7	329	340	1	4	8
Example 8	406	272	1	4	9
Comparative Example 5	191	150	7	25	56

- PC : Polycarbonate resin A-2500, available from Idemitsu Sekiyu Kagaku K.K.
- PS : Polystyrene resin DIAFLEX HF-77, available from Mitsubishi Monsanto K.K.
- MS : MS resin ESTYRENE MS-300, available from Shinnittetsu Kagaku K.K.
- Acryl : Acrylic resin PARAPETT SH, available from Kyowa Gas Kogyo K.K.
- DAC : Cellulosediacetate resin quarter-wave plate, available from Fuji Photo Film Co., Ltd.

Examples and comparative examples obtained by the present inventors by manufacturing retardation films using various materials under various conditions will be described below.

Examples 1 - 4

Constant-width uniaxial stretching was performed for a polycarbonate resin (A-2500 available from Idemitsu Sekiyu Kagaku K.K.) at a stretching temperature of 185°C and a stretching ratio of 2.5 times to form an anisotropic film having a thickness of 205 μm and a retardation of 124 nm. A free-width uniaxially stretched

product, constant-width uniaxially stretched products, and a biaxially stretched product respectively obtained from a polystyrene resin (DIAREX HF-77 available from Mitsubishi Monsanto K.K.) at a stretching temperature of 120°C and stretching ratios of 1.5 times, 1.5 and 2.5 times, and 2.5 x 1.1 times were independently overlapped on the above anisotropic film such that their main stretching directions became perpendicular to each other, thereby manufacturing retardation films.

The viewing angle dependencies of the manufactured retardation films were small, as shown in Table 1.

Note that the thicknesses and retardations of the polystyrene resin anisotropic films were 275 µm and -313 nm, 215 µm and -157 nm, 134 µm and -296 nm, and 122 µm and -220 nm, respectively.

Comparative Examples 1 - 3

The viewing angle dependencies of the polycarbonate resin anisotropic film used in Example 1 and the polystyrene resin anisotropic films used in Examples 3 and 4 were independently measured. As a result, the measurement values were large, as shown in Table 1.

Example 5

Biaxial stretching was performed for a polycarbonate resin at a stretching temperature of 180°C and a stretching ratio of 2.2 x 1.1 times to form an anisotropic film having a thickness of 198 µm and a retardation of 106 nm. A constant-width uniaxially stretched product having a thickness of 324 µm and a retardation of -138 nm, obtained from an acrylic resin (PARAPET SH available from Kyowa Gas Kagaku Kogyo K.K.) at a stretching temperature of 130°C and a stretching ratio of 1.5 times was overlapped on the above anisotropic film such that their main stretching directions became perpendicular to each other, thereby manufacturing a retardation film.

The viewing angle dependency of this retardation film was small, as shown in Table 1.

When solvent resistances against butyl acetate and toluene were tested on the acrylic resin anisotropic film side, good results were obtained without causing any changes including whitening.

Comparative Example 4

When the viewing angle dependency of the polycarbonate resin anisotropic film used in Example 5 was independently measured, the measurement result was large, as shown in Table 1. In addition, the film was whitened by a solvent resistance test using butyl acetate and toluene.

Example 6

A biaxially stretched product having a thickness of 324 µm and a retardation of -109 nm, obtained from an acrylic resin at a stretching temperature of 130°C and a stretching ratio of 3.5 x 1.5 times was overlapped on the polycarbonate resin anisotropic film used in Example 5, thereby manufacturing a retardation film.

The viewing angle dependency of this retardation film was small, as shown in Table 1. In addition, this acrylic resin anisotropic film had higher strength than that of a uniaxially stretched product and was easier to handle, and the impact strength of a retardation film manufactured by using this film was improved.

Example 7

A constant-width uniaxially stretched product having a thickness of 124 µm and a retardation of -254 nm, obtained from an MS resin (ESTYRENE MS-300 available from Shinnittetsu Kagaku K.K.) at a stretching temperature of 130°C and a stretching ratio of 2.5 times was overlapped on the polycarbonate resin anisotropic film used in Example 1 such that their main stretching directions became perpendicular to each other, thereby manufacturing a retardation film.

The viewing angle dependency of this retardation film was small, as shown in Table 1.

Example 8

The polystyrene resin constant-width uniaxially stretched product used in Example 2 was overlapped on a cellulosediacetate resin quarter-wave plate (FUJITACK available from Fuji Photo Film Co., Ltd.) such that their stretching directions became perpendicular to each other, thereby manufacturing a retardation film.

The viewing angle dependency of this retardation film was small, as shown in Table 1.

Comparative Example 5

When the viewing angle dependency of the cellulosediacetate resin used in Example 8 was measured, the measurement value was large, as shown in Table 1.

It was confirmed by the present inventors that in the liquid crystal display device arranged as shown in Figs. 3 and 4, a coloring phenomenon caused by the wavelength dependency of birefringence of the liquid crystal panel was effectively eliminated to realize essentially decolored black-and-white display. In addition, the viewing angle dependency was minimized, and essentially no significant change was found in quality of the display at an inclination angle of the viewing angle of up to about 45° in all directions.

Note that the reflecting plate 106 is a member for observing the liquid crystal display device as a reflection type device and therefore can be omitted when the device is to be observed as a transmission type device.

Although the STN liquid crystal panel having a twisting angle of 240° is exemplified in the above embodiment, the present invention can be effectively applied to any liquid crystal panels having a problem of coloring caused by a birefringent effect. Practically, the present invention is applied to an STN liquid crystal panel having a twisting angle of 180° to 300°.

In the present invention, it is important to arrange at least one pair of retardation films having positive and negative intrinsic birefringence values such that their main stretching directions cross each other, but the crossing angle need not be the right angle, 90° as described in the above embodiment.

Although the retardation of each retardation film, $\Delta n \cdot d$ of the liquid crystal panel, and a relative arrangement angle with respect to the orientation direction of liquid crystal molecules must be totally optimized, the effect of crossing the positive and negative retardation films is achieved within the range of a crossing angle of $90^\circ \pm 35^\circ$ with respect to the right angle, 90°, as the center.

In addition, in the above embodiment, a pair of positive and negative retardation films are overlapped and arranged on one side of the liquid crystal panel. But decoloring of the liquid crystal display device and elimination of the viewing angle dependency can be optimized by combining a plurality of other retardation films and arranging the retardation films on both the sides of the liquid crystal panel.

In the present invention, by crossing the retardation films having positive and negative specific refringent values, the viewing angle dependencies cancel each other, and at the same time the refractive index anisotropies are synthesized. Therefore, a satisfactory retardation can be obtained by a combination of comparatively thin retardation films, and a loss derived from light absorption can be reduced.

For this reason, in an STN liquid crystal display device, not only the coloring and viewing angle dependency can be eliminated but also the contrast and brightness can be improved and the thickness of the device can be decreased.

Claims

1. A liquid crystal display device comprising a liquid crystal panel (104) constituted by a nematic liquid crystal layer with positive dielectric anisotropy, having a twisted structure with a twisting angle of 180° to 300° and a pair of electrode substrates which sandwich said liquid crystal layer, a pair of polarizing plates (101, 105) arranged one on each of the sides of said liquid crystal panel, and a retardation film combination for colour compensation arranged between said pair of polarizing plates, characterised in that said retardation film combination comprises a first retardation film (102) whose refractive index in a main stretching direction is greater than its refractive index in a direction perpendicular to its main stretching direction and a second retardation film (103) whose refractive index in a main stretching direction is smaller than its refractive index in a direction perpendicular to its main stretching direction both said retardation films being constituted by stretched polymeric films and arranged such that said main stretching directions thereof cross each other within an angle range of $90^\circ \pm 35^\circ$.
2. A liquid crystal display device according to claim 1, characterised in that said retardation film combination is a uniaxially stretched product or an anisotropic biaxially stretched product of polymeric
3. A liquid crystal display device according to claim 1 or 2, characterised in that said first retardation film is a stretched film consisting of a polycarbonate resin or a cellulosediacetate resin.
4. A liquid crystal display device according to claim 1, 2 or 3, characterised in that said second retardation film is a stretched film consisting of an acrylic resin or a styrene-based resin.



Comparative Example 5

When the viewing angle dependency of the cellulosediacetate resin used in Example 8 was measured, the measurement value was large, as shown in Table 1.

5 It was confirmed by the present inventors that in the liquid crystal display device arranged as shown in Figs. 3 and 4, a coloring phenomenon caused by the wavelength dependency of birefringence of the liquid crystal panel was effectively eliminated to realize essentially decolored black-and-white display. In addition, the viewing angle dependency was minimized, and essentially no significant change was found in quality of the display at an inclination angle of the viewing angle of up to about 45° in all directions.

10 Note that the reflecting plate 106 is a member for observing the liquid crystal display device as a reflection type device and therefore can be omitted when the device is to be observed as a transmission type device.

Although the STN liquid crystal panel having a twisting angle of 240° is exemplified in the above embodiment, the present invention can be effectively applied to any liquid crystal panels having a problem of coloring caused by a birefringent effect. Practically, the present invention is applied to an STN liquid crystal panel having
15 a twisting angle of 180° to 300°.

In the present invention, it is important to arrange at least one pair of retardation films having positive and negative intrinsic birefringence values such that their main stretching directions cross each other, but the crossing angle need not be the right angle, 90° as described in the above embodiment.

20 Although the retardation of each retardation film, $\Delta n \cdot d$ of the liquid crystal panel, and a relative arrangement angle with respect to the orientation direction of liquid crystal molecules must be totally optimized, the effect of crossing the positive and negative retardation films is achieved within the range of a crossing angle of $90^\circ \pm 35^\circ$ with respect to the right angle, 90°, as the center.

In addition, in the above embodiment, a pair of positive and negative retardation films are overlapped and arranged on one side of the liquid crystal panel. But decoloring of the liquid crystal display device and elimination of the viewing angle dependency can be optimized by combining a plurality of other retardation films and
25 arranging the retardation films on both the sides of the liquid crystal panel.

In the present invention, by crossing the retardation films having positive and negative specific refringent values, the viewing angle dependencies cancel each other, and at the same time the refractive index anisotropies are synthesized. Therefore, a satisfactory retardation can be obtained by a combination of comparatively thin retardation films, and a loss derived from light absorption can be reduced.
30

For this reason, in an STN liquid crystal display device, not only the coloring and viewing angle dependency can be eliminated but also the contrast and brightness can be improved and the thickness of the device can be decreased.

35

Claims

1. A liquid crystal display device comprising a liquid crystal panel (104) constituted by a nematic liquid crystal layer with positive dielectric anisotropy, having a twisted structure with a twisting angle of 180° to 300° and a pair of electrode substrates which sandwich said liquid crystal layer, a pair of polarizing plates (101, 105) arranged one on each of the sides of said liquid crystal panel, and a retardation film combination for colour compensation arranged between said pair of polarizing plates, characterised in that said retardation film combination comprises a first retardation film (102) whose refractive index in a main stretching direction is greater than its refractive index in a direction perpendicular to its main stretching direction and a second retardation film (103) whose refractive index in a main stretching direction is smaller than its refractive index in a direction perpendicular to its main stretching direction both said retardation films being constituted by stretched polymeric films and arranged such that said main stretching directions thereof cross each other within an angle range of $90^\circ \pm 35^\circ$.
40
2. A liquid crystal display device according to claim 1, characterised in that said retardation film combination is a uniaxially stretched product or an anisotropic biaxially stretched product of polymeric
45
3. A liquid crystal display device according to claim 1 or 2, characterised in that said first retardation film is a stretched film consisting of a polycarbonate resin or a cellulosediacetate resin.
50
4. A liquid crystal display device according to claim 1, 2 or 3, characterised in that said second retardation film is a stretched film consisting of an acrylic resin or a styrene-based resin.
55



5. A retardation film combination comprising a multilayered body of a first retardation film whose refractive index in a main stretching direction is greater than its refractive index in a direction perpendicular to its main stretching direction and a second retardation film whose refractive index in a main stretching direction is smaller than its refractive index in a direction perpendicular to its main stretching direction, characterised in that said first and second retardation films are constituted by stretched polymeric films and arranged such that said main stretching directions thereof cross each other within an angle range of $90^\circ \pm 35^\circ$.

10 Patentansprüche

1. Flüssigkristall-Anzeigevorrichtung mit einer Flüssigkristalltafel (104), die durch eine nematische Flüssigkristallschicht mit positiver dielektrischer Anisotropie gebildet wird, die eine gedrehte Struktur mit einem Verdrehungswinkel von 180° bis 300° und ein Paar von Elektroden substraten, zwischen denen die Flüssigkristallschicht angeordnet ist, aufweist, einem Paar von polarisierenden Platten (101, 105), von denen eine auf jeder der Seiten der Flüssigkristalltafel angeordnet ist, und einer Verzögerungs-Filmkombination zur Farbkompensation, die zwischen dem Paar von polarisierenden Platten angeordnet ist, dadurch gekennzeichnet, daß die Verzögerungs-Filmkombination einen ersten Verzögerungsfilm (102), dessen Brechungsindex in einer Hauptstreckrichtung größer als sein Brechungsindex in einer zu seiner Hauptstreckrichtung senkrechten Richtung ist, und einen zweiten Verzögerungsfilm (103), dessen Brechungsindex in einer Hauptstreckrichtung kleiner als sein Brechungsindex in einer zu seiner Hauptstreckrichtung senkrechten Richtung ist, aufweist, wobei beide Verzögerungsfilme durch gestreckte polymere Filme gebildet und so angeordnet sind, daß deren besagte Hauptstreckrichtungen einander in einem Winkelbereich von $90^\circ \pm 35^\circ$ kreuzen.
2. Flüssigkristall-Anzeigevorrichtung nach Anspruch 1, dadurch gekennzeichnet, daß die Verzögerungs-Filmkombination ein einachsig gestrecktes Produkt oder ein anisotropisches zweiachsig gestrecktes Produkt aus polymeren Filmen ist.
3. Flüssigkristall-Anzeigevorrichtung nach Anspruch 1 oder 2, dadurch gekennzeichnet, daß der erste Verzögerungsfilm ein gestreckter Film bestehend aus einem Polycarbonatharz oder einem Cellulosediacetatharz ist.
4. Flüssigkristall-Anzeigevorrichtung nach Anspruch 1, 2 oder 3, dadurch gekennzeichnet, daß der zweite Verzögerungsfilm ein gestreckter Film bestehend aus einem Acrylharz oder einem Harz auf Styrolbasis ist.
5. Verzögerungs-Filmkombination mit einem mehrschichtigen Körper aus einem ersten Verzögerungsfilm, dessen Brechungsindex in einer Hauptstreckrichtung größer als sein Brechungsindex in einer zu seiner Hauptstreckrichtung senkrechten Richtung ist, und einem zweiten Verzögerungsfilm, dessen Brechungsindex in einer Hauptstreckrichtung kleiner als sein Brechungsindex in einer zu seiner Hauptstreckrichtung senkrechten Richtung ist, dadurch gekennzeichnet, daß der erste und der zweite Verzögerungsfilm durch gestreckte polymere Filme gebildet und so angeordnet sind, daß deren besagte Hauptstreckrichtungen einander in einem Winkelbereich von $90^\circ \pm 35^\circ$ kreuzen.

45 Revendications

1. Dispositif d'affichage à cristaux liquides, comprenant un panneau (104) à cristaux liquides constitué par une couche de cristaux liquides nématiques ayant une anisotropie diélectrique positive, ayant une structure retordue avec un angle de torsion compris entre 180° et 300° , et une paire de substrats à électrodes qui entourent la couche cristalline liquide, deux lames polarisantes (101, 105) placées chacune sur une face du panneau à cristaux liquides, et une combinaison de films retardateurs destinés à assurer la compensation de couleur est placée entre les deux lames polarisantes, caractérisé en ce que la combinaison de films retardateurs comprend un premier film retardateur (102) dont l'indice de réfraction dans une direction d'étirage principal est supérieur à son indice de réfraction en direction perpendiculaire à sa direction d'étirage principal, et un second film retardateur (103) dont l'indice de réfraction dans la direction d'étirage principal est inférieur à son indice de réfraction en direction perpendiculaire à sa direction d'éti-



rage principal, les deux films retardateurs étant constitués par des films polymères étirés et étant disposés de manière que les directions d'étirage principal se recoupent mutuellement dans une plaque angulaire de $90 \pm 35^\circ$.

- 5 2. Dispositif d'affichage à cristaux liquides selon la revendication 1, caractérisé en ce que la combinaison de films retardateurs est un produit étiré uniaxialement ou un produit étiré biaxialement anisotrope de films polymères.
- 10 3. Dispositif d'affichage à cristaux liquides selon la revendication 1 ou 2, caractérisé en ce que le premier film retardateur est un film étiré constitué d'une résine de polycarbonate ou d'une résine de diacétate de cellulose.
4. Dispositif d'affichage à cristaux liquides selon la revendication 1, 2 ou 3, caractérisé en ce que le second film retardateur est un film étiré constitué d'une résine acrylique ou d'une résine à base de styrène.
- 15 5. Combinaison de films retardateurs, comprenant un corps multicouche d'un premier film retardateur dont l'indice de réfraction dans une direction d'étirage principal est supérieur à l'indice de réfraction dans une direction perpendiculaire à la direction d'étirage principal, et d'un second film retardateur dont l'indice de réfraction dans une direction d'étirage principal est inférieur à l'indice de réfraction en direction perpendiculaire à sa direction d'étirage principal, caractérisée en ce que le premier et le second film retardateurs sont constitués par des films polymères étirés et sont disposés de manière que les directions d'étirage principal se recoupent mutuellement dans une plage angulaire de $90 \pm 35^\circ$.
- 20
- 25
- 30
- 35
- 40
- 45
- 50
- 55