We Claim:

1. A composition, comprising:

a phosphorous-containing compound from a reaction of:

at least one organophosphorus compound having a group selected from the group of H-P=O, P-H and P-OH; and

at least one compound having the following Formula (I):

Formula I: $[R'(Y)_{m'}]_m(X - O - R'')_n$

wherein R' is an organic group; Y is a functional group selected from the group of hydroxy, carboxylic acid, carboxylate, acid anhydride, amine, -SH, $-SO_3H$, $-CONH_2$, -NHCOOR phosphinate, phosphate and combinations thereof; X is a hydrocarbylene group; R" is a hydrogen or a hydrocarbyl group having from 1 to 8 carbon atoms, R is alkyl or aryl group having from 1 to 12 carbon atoms; and m', m and n are, independently, numbers equal to or greater than 1;

a cyanate ester; and

an epoxy resin, wherein the phosphorous-containing compound does not contain an aliphatic alcohol, wherein the composition includes an aprotic solvent and wherein the viscosity of the composition increases less than 100% as measured by Gardner Bubble Viscosity at a temperature of 23 °C for at least 3 days.

2. The composition of claim 1, wherein the aprotic solvent is a ketone selected from the group of methyl ethyl ketone, methyl isobutyl ketone and combinations thereof.

3. The composition of claim 1, wherein the composition includes a maleimide.

4. The composition of claim 3, wherein the maleimide is selected from the group of phenylmaleimide, 4,4'-bismaleimidodiphenylmethane and combinations thereof.

5. The composition of claim 1, wherein the cyanate ester is a trimer of the cyanate ester.